
2022►2023

General Catalogue

# SUMITOMO


## CARBIDE - CBN - DIAMOND

# PERFORMANCE CUTTING TOOLS




SUMITOMO ELECTRIC

SUMITOMO ELECTRIC GROUP



A Insert Selection



B Grades


C Negative & Positive Inserts



D External Holders


E Boring Bars



F Parting-Off Grooving Threading Holders



G Milling Cutters



H Indexable Endmills


J Solid Carbide Endmills



K Multi-Drills



L SumiBoron SumiDia


M CBN/PCD Inserts & Tools


N P Guidance Spare Parts Index, App


# Contents




Insert Selection A1 –





Grades B1 –



Inserts
Negative Type C1 –


Inserts
Positive Type C63 –


External Holders D1 –


Boring Bars E1 –


Grooving Holders
Parting-Off Holders F1 –



Threading
Holders F62 –

| | Negative | Positive |
|---|---|---|
| C 80° Diamond Type | C20 | C63 |
| D 55° Diamond Type | C29 | C70 |
| R Round Type | | C74 |
| S Square Type | C37 | C75 |
| T 60° Triangular Type | C46 | C80 |
| V 35° Diamond Type | C55 | C90 |
| W 80° Trigon Type | C58 | C94 |


CBN Inserts M1 –


PCD Inserts M1 –



Guidance N1 –



**Milling Cutters** G1 –



**Milling Cutters** G53 –
High Feed / Special Purpose Cutters


**Indexable Endmills** H1 –



**Endmills** J1 –
Coated Solid Types


**Endmills** J36–
Uncoated Solid Types


**Multi-Drills** K1 –


**SumiBoron** L1 –
CBN Grades


**SumiDia** L24 –
PCD Grades


**CBN / PCD Inserts and Tools** M1 –


**Spare Parts** P1 –


**Index** P9 –

# Dimension symbols are compliant with ISO13399

The following table shows ISO13399-compliant dimension symbols. Contents corresponding to the sample symbols/notations are shown below. Tool shape diagrams and stock charts use the symbols and notation examples from the table below.


## (1) Inserts (For Turning / For Milling)

| Symbol | Description |
|---|---|
| **AN** | Clearance angle major |
| **APMX** | Depth of cut maximum |
| **BS** | Wiper edge length |
| **CDX** | Cutting depth maximum |
| **CHW** | Corner chamfer width |
| **CW** | Cutting width |
| **D1** | Fixing hole diameter |
| **DMIN** | Minimum bore diameter |
| **IC** | Inscribed circle diameter |
| **INSL** | Insert length |
| **L** | Cutting edge length |
| **PDX** | Profile distance ex |
| **PDY** | Profile distance ey |
| **PNA** | Profile included angle |
| **RE** | Corner radius |
| **RER** | Right side corner radius |
| **REL** | Left side corner radius |
| **S** | Insert thickness |
| **W1** | Insert width |
| **WF** | Functional width |


## (2) Tool Holders For Turning

| Symbol | Description |
|---|---|
| **APMX** | Depth of cut maximum |
| **B** | Shank width |
| **BD** | Body diameter |
| **CDX** | Cutting depth maximum |
| **CRKS** | Connection retention knob thread size |
| **DC** | Cutting diameter |
| **DCB** | Connection bore diameter |
| **DCON** | Connection diameter |
| **DCSFMS** | Contact surface diameter machine side |
| **DMIN** | Minimum bore diameter |
| **DMM** | Shank diameter |
| **DN** | Neck diameter |
| **GAMF** | Rake angle radial |
| **GAMP** | Rake angle axial |
| **H** | Shank height |
| **HBH** | Head bottom offset height |
| **HBKL** | Head back offset length |
| **HBKW** | Head back offset width |
| **HBL** | Head bottom offset length |
| **HF** | Functional height |
| **KDP** | Groove depth |
| **KWW** | Keyway width |
| **LF** | Functional length |
| **LH** | Head length |
| **LHD** | Head length |
| **LS** | Shank length |
| **LSCX** | Clamping length maximum |
| **LU** | Usable length |
| **LUX** | Usable length maximum |
| **WF** | Functional width |

(Turning Insert Example)




(Grooving Insert Example)




(External Holder Example)






Figure shows right-handed tool.

(Grooving Tool Holder Example)




Notes: The symbols in the above table are compliant with ISO13399 and do not include symbols unique to our company.
As symbols under review are not included, these may change over time.

## (3) Cutters / Indexable Endmills

| Symbol | Description |
|---|---|
| **APMX** | Depth Of Cut Maximum |
| **BD** | Body Diameter |
| **BDX** | Body Diameter Maximum |
| **CBDP** | Connection Bore Depth |
| **CRKS** | Connection Retention Knob Thread Size |
| **CW** | Cutting Width |
| **DBC** | Connection Bore Diameter |
| **DC** | Cutting Diameter |
| **DCB** | Clamping Diameter, Nominal, on Workpiece Side |
| **DCON** | Connection Diameter |
| **DCSFMS** | Contact Surface Diameter Machine Side |
| **DCX** | Cutting Diameter Maximum |
| **DMM** | Shank Diameter |
| **DN** | Neck Diameter |
| **H** | Shank Height |
| **KDP** | Groove Depth |
| **KWW** | Keyway Width |
| **LBX** | Body Length Maximum |
| **LF** | Functional Length |
| **LH** | Head Length |
| **LS** | Shank Length |
| **LU** | Usable Length |
| **OAL** | Overall Length |
| **RMPX** | Maximum Ramping Angle |
| **THUB** | Hub Thickness |


## (4) Endmills

| Symbol | Description |
|---|---|
| **APMX** | Depth Of Cut Maximum |
| **CHW** | Corner Chamfer Width |
| **DC** | Cutting Diameter |
| **DMM** | Shank Diameter |
| **DN** | Neck Diameter |
| **LF** | Functional Length |
| **LFS** | Functional Length Secondary |
| **LU** | Usable Length |
| **RE** | Corner Radius |


## (5) Drills / Reamers

| Symbol | Description |
|---|---|
| **BD** | Body Diameter |
| **BDX** | Body Diameter Maximum |
| **CW** | Cutting Width |
| **DC** | Cutting Diameter |
| **DCB** | Clamping Diameter, Nominal, on Workpiece Side |
| **DCON** | Connection Diameter |
| **DCSFMS** | Contact Surface Diameter Machine Side |
| **DF** | Flange Diameter |
| **DMM** | Shank Diameter |
| **LBX** | Body Length Maximum |
| **LCF** | Length Chip Flute |
| **LF** | Functional Length |
| **LFA** | A Dimension On Lf |
| **LFS** | Functional Length Secondary |
| **LH** | Head Length |
| **LPR** | Protruding Length |
| **LS** | Shank Length |
| **LU** | Usable Length |
| **LUX** | Usable Length Maximum |
| **OAL** | Overall Length |
| **PL** | Point Length |
| **WBTHK** | Web Thickness |


(Shell Type Example)





(Shank Type Example)





(Modular Type Example)




(Endmill Example)




(Drill Example)



## Notice

Thank you for using the Sumitomo Electric Hardmetal General Catalogue
(Sumitomo/SUMIBORON/SUMIDIA Cutting Tools Catalogue).

This catalogue presents the major items in the Sumitomo Cutting Tools product line.
The catalogue ist organised as follows:
(1) Cutting Tool Grades
(2) Sumitomo Products
(3) SUMIBORON, SUMIDIA Products
Ask for our brochures and pamphlets.
This catalogue is current as of January 2022.

As a result ot our ongoing research, product may reflect enhancements in qualitiy, performance and specifications not listed in this catalogue.
To order Sumitomo/SUMIBORON/SUMIDIA products, contact your nearest Sumitomo Electric Hardmetal dealer or distributor.
For inquiries or other requests, feel free to contact your nearest sales office.

## Stock Marking Chart

● : Euro stock item

❍ : Japan stock item

❑ : Delivery on request

▲ : To be replaced by new item

□ : Made to order item

– : We cannot produce

**Note:**
Stocking policy may change without prior notice, please consult our sales representative for actual stock situation.

## Meaning of Icons

### Common




Featured for the first time in this catalogue




Newly added to expand our selection of items

### Grade

ISO classification of work material:




Steel




Stainless Steel




Cast Iron




Non Ferrous Alloy





Exotic Alloy




Hardened Steel

### Miling Cutter




Max. depth of cut

Cutting edge angle

### Endmill

Shape



Sharp edge



Corner with honing




Helix angle (ex.)




Radius




Ballnose

No. of teeth




Flutes

# Insert Selection

A



**A1–A20**






Insert Selection


**Sumitomo Grades (Turning)** ..... A2
**Sumitomo Grades (Milling)** ..... A3


Chipbreaker and Grade Selection

**Steel Turning Inserts** ..... A 4–7
**Stainless Steel Turning Inserts** ..... A 8–9
**Cast Iron Turning Inserts** ..... A10–11
**Exotic Alloy Inserts** ..... A12–13
**Hardened Steel Turning Inserts** ..... A14–15
**Non-Ferrous Metal Turning Inserts** ..... A16–17
**Small Product Machining** ..... A18–19

# Selection of Sumitomo Grades (Turning)













: 1st Recommendation : 2nd Recommendation : CVD Coating : PVD Coating Blank: Uncoated

# Selection of Sumitomo Grades (Milling)








: 1st Recommendation : 2nd Recommendation : CVD Coating : PVD Coating Blank: Uncoated

## Main Chipbreakers

### Negative Type





### Positive Type





## Sub-Chipbreakers

### Negative Type


**Chipbreakers for High-Efficiency Machining**





**Strong Edge Chipbreakers**





**Chipbreakers for Small Depths**




**Wiper Inserts**





**Chipbreakers for Heavy Cutting**





## Grades

**Fine Finishing to Finishing**




**Finishing to Rough Cutting**



## Grades

Uncoated Cermet Coated Cermet New

**T1000A / T1500A / T1500Z / T2500Z**

T1000A High-hardness cermet with outstanding wear resistance and toughness. Realises high dimensional accuracy for continuous steel machining or finishing of Sintered Alloy or cast iron.

T1500A General-purpose cermet made from hard grains with different grain sizes, delivering functionality that provides an excellent balance of wear resistance and toughness. Also achieves good surface finish quality.


T1500Z Employs Brilliant Coat PVD coating with excellent lubricity to provide better wear resistance and consistent surface finishes in low-speed cutting applications such as machining of small products or low carbon steel.

T2500Z A new cermet substrate with excellent thermal conductivity is used to achieve outstanding thermal crack resistance. Also uses Brilliant Coat, which has excellent lubricity.


## Performance

### T1000A

**Wear Resistance**





**Fracture Resistance**





### T1500A

**Wear Resistance**





**Machined Surface Finish**





### T1500Z

**Wear Resistance**





**Machined Surface Finish**





### T2500Z

**Wear Resistance**




**Fracture Resistance**




## P Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

| Work Material | Cutting Process | Chipbreaker | Grades | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (m/min) |
|---|---|---|---|---|---|---|
| Soft Steel | Fine Finishing | NFA / NFL | T1500Z | 0,2–**0,5**–1,0 | 0,05–**0,15**–0,25 | 150–**280**–400 |
| | Finishing | NLU | T3000Z | 0,3–**1,0**–1,8 | 0,08–**0,20**–0,35 | 150–**280**–400 |
| Alloy Steel Carbon Steel | Fine Finishing | NFA / NFL | T1500A | 0,2–**0,5**–1,0 | 0,05–**0,15**–0,25 | 100–**200**–300 |
| | Finishing | NSU / NSE | T1500A | 0,5–**1,0**–2,0 | 0,08–**0,20**–0,35 | 100–**200**–300 |
| | Medium | NGU | T1500Z | 0,8–**2,2**–4,0 | 0,15–**0,25**–0,50 | 100–**200**–300 |
| High Carbon Steel Carbon Steel | Fine Finishing | NFA / NFL | T1000A | 0,2–**0,5**–1,0 | 0,05–**0,15**–0,25 | 50–**150**–250 |
| | Finishing | NSU / NSE | T1500Z | 0,5–**1,0**–2,0 | 0,08–**0,20**–0,35 | 50–**150**–250 |
| | Medium | NGU | T1500Z | 0,8–**2,2**–4,0 | 0,15–**0,25**–0,50 | 50–**150**–250 |

## Grades

ABSOTECH ABSOTECH New ABSOTECH ABSOTECH ABSOTECH

# AC8015P / AC8020P / AC8025P / AC8035P / AC1030U


Covers a wide range of machining applications from high-speed cutting to interrupted cutting and small lathe machining.

| | |
|---|---|
| AC8015P | Development of crater damage is suppressed by controlling the orientation of the alumina crystal grains. Achieves long, stable tool life during high-speed and high feed cutting. |
| AC8020P | Alumina coating with even higher strength balances outstanding stability and wear resistance in mill-scale work on forged material. Gold-colored coating makes used corners easily identifiable. |
| AC8025P | The 1st recommendation grade for turning steel. Surface smoothing technology significantly suppresses adhesion of work material components. Achieves long, stable tool life with various cutting speeds and work materials. |
| AC8035P | Tensile stress removal of the coating layer greatly improves fracture resistance. Achieves long, stable tool life during heavy interrupted cutting. |
| AC1030U | Employs a new PVD coating and a dedicated tough carbide substrate. High-quality cutting edge grade suppresses adhesion and micro-chipping, realizing excellent machined surface quality. |

## Performance

### AC8015P

Alumina crystal grain orientation control technology suppresses crater damage due to chip abrasion.





Work Material: 100Cr6 /(external contiuous)
Insert: CNMG120408NGU
Cutting Data: $v_c$ = 300 m/min, f = 0,3 mm/rev, $a_p$ = 1,5 mm, wet

Suppresses crater damage due to chip abrasion → Twice the crater wear resistance

### AC8020P

Alumina coating with even higher strength suppresses chipping.





Work Material: 34CrMo4/(incl. intermittent forge sections)
Insert: CNMG120408NGU
Cutting Data: $v_c$ = 250 m/min, f = 0,3 mm/rev, $a_p$ = 1,5 mm, wet

Balance of high wear resistance and stability → 2,5x chipping resistance or more

### AC8025P

Surface smoothing treatment significantly suppresses adhesion and chipping.





Work Material: 15CrMo5 (Face)
Insert: CNMG120408NGU
Cutting Data: $v_c$ = 100–300 m/min, f = 0,3 mm/rev, $a_p$ = 1,5 m, wet

Suppresses adhesion with ultra-smooth surface → Twice the adhesion fracture resistance

### AC8035P

Special surface treatment reduces tensile stress in the coating layer, significantly suppressing breakages.




Work Material: 34CrMo4 (external interrupted)
Insert: CNMG120408NGU
Cutting Data: $v_c$ = 160 m/min, f = 0,2–0,3 mm/rev, $a_p$ = 2,0 mm, dry


Suppresses crack growth and breakages by reducing tensile stress → Twice the fracture resistance











## Grades and Chip breaker Selection Guide

| 1st Recommended Grade | |
|---|---|
| General Purpose | **AC8025P** |

+



1st Recommendation: **NGU**




| | Chipbreakers for High-efficiency Machining | Main Chipbreakers | Strong Cutting Edge Chipbreakers |
|---|---|---|---|
| Finish – Small Depth | **NFE**  **NSE**  | **NSU**  | **NSX**  |
| General Purpose | **NGE**  | **NGU**  | **NUX**  |
| Rough – Larger Cutting Depth | **NME**  | **NMU**  | **NMX**  |



### For High-speed Continuous Machining of Mild Steel

| High Speed | **AC8015P** |
|---|---|

| | |
|---|---|
| To improve tool life at small depths of cut | **NFE**  |
| To improve finishing efficiency | **NSE**  |



### For Heavy Interrupted Cutting Emphasizing Stability

| Interrupted Cut | **AC8035P** |
|---|---|

| | |
|---|---|
| To improve tool life | **NGU**  |
| To improve machining stability | **NUX**  |

### For High-efficiency Machining of High Carbon Steel and Forged Steel

| High Efficiency | **AC8020P** |
|---|---|

| | |
|---|---|
| To increase feed rate | **NGE**  |
| To increase cutting speed | **NGU**  |


## Recommended Cutting Conditions

(Min. - **Optimum** - Max.)


| Work Material | Cutting Process | Chipbreaker | Grade | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (mm/min) |
|---|---|---|---|---|---|---|
| Soft Steel Low Carbon Steel (SS400, C15, etc.) | Fine Finishing | NFB, NFE | T1500Z | 0,2–**0,6**–1,0 | 0,05–**0,15**–0,25 | 100–**250**–400 |
| | Continuous | NGU, NGE | AC8015P | 1,0–**2,5**–4,0 | 0,1–**0,25**–0,4 | 260–**350**–440 |
| | General–Interrupted | **NGU, NGE** | **AC8025P** | 1,0–**2,5**–4,0 | 0,2–**0,35**–0,5 | 200–**260**–320 |
| | Heavy Interrupted | NMU, NME | AC8035P | 1,5–**4,0**–6,0 | 0,3–**0,45**–0,6 | 140–**150**–220 |
| Medium to High Carbon Steel Alloy Steel, Hard Steel (C45, 34CrMo4, etc.) | Fine Finishing | NFB, NFE | T1500Z | 0,2–**0,6**–1,0 | 0,05–**0,15**–0,25 | 50–**200**–300 |
| | Continuous–General | **NGU, NGE** | **AC8020P** | 1,0–**2,5**–4,0 | 0,2–**0,35**–0,5 | 150–**235**–290 |
| | Interrupted | NGU, NGE | AC8025P | 1,0–**2,5**–4,0 | 0,2–**0,35**–0,5 | 130–**165**–230 |
| | Heavy Interrupted | NMU, NME | AC8035P | 1,5–**4,0**–6,0 | 0,3–**0,45**–0,6 | 90–**135**–160 |

## Chipbreakers


### Negative Type




### Positive Type




## Grades




## M Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

| Work Material | | | Cutting Range | Chipbreaker | Grade | Cutting Conditions | | |
|---|---|---|---|---|---|---|---|---|
| | | | | | | Depth of Cut $a_p$ (mm) | Feed Rate f (mm/rev) | Cutting Speed $v_c$ (m/min) |
| Cr-Based | Ferritic Materials | X6CrAl 13, X8CrNiS 18 9, X29CrS 13, X6CrMoS 17, X12CrS 13 | Finishing | NEF (NSU) | AC6020M | 0,5–**1,5**–2,0 | 0,05–**0,15**–0,25 | 170–**230**–300 |
| | | | Medium | **NEG** · **NGU** · NEX | **AC6030M** | 1,0–**2,5**–4,0 | 0,10–**0,25**–0,40 | 140–**170**–250 |
| | | | Roughing | NEM | AC6040M | 1,5–**3,5**–6,0 | 0,20–**0,35**–0,60 | 140–**170**–200 |
| | Martensitic Materials | X12Cr 13, X20Cr 13, X30Cr 13, X6Cr 17, X19CrNi 17 2, X6CrNi 18 9 | Finishing | NEF (NSU) | AC6020M | 0,5–**1,5**–2,0 | 0,05–**0,15**–0,25 | 120–**180**–240 |
| | | | Medium | **NEG** · **NGU** · NEX | **AC6030M** | 1,0–**2,5**–4,0 | 0,10–**0,25**–0,40 | 100–**150**–200 |
| | | | Roughing | NEM | AC6040M | 1,5–**3,5**–6,0 | 0,20–**0,35**–0,60 | 80–**130**–180 |
| Cr/Ni-Based | Austenitic Materials | X5CrNi 18 10, X2CrNi 19 11, X2CrNiMo 18 10, X4CrNiMo 17 12 2, X2CrNiMo 17 12 2, X5CrNiMo 17 13, X6CrNiTi 18 10, X70CrMo 15 | Finishing | NEF (NSU) | AC6020M | 0,5–**1,5**–2,0 | 0,05–**0,15**–0,25 | 120–**180**–240 |
| | | | Medium | **NEG** · **NGU** · NEX | **AC6030M** | 1,0–**2,5**–4,0 | 0,10–**0,25**–0,40 | 100–**150**–200 |
| | | | Roughing | NEM | AC6040M | 1,5–**3,5**–6,0 | 0,20–**0,35**–0,60 | 80–**130**–180 |
| | Two-Phase (Austenite / Ferrite) Materials | X5CrNi 17 7, X2CrNi 18 9, X6CrNi 25 20, X2CrNiMoN 17 12 2, X6CrNiNb 18 10 | Finishing | NEF (NSU) | AC6030M | 0,5–**1,5**–2,0 | 0,05–**0,15**–0,25 | 100–**145**–180 |
| | | | Medium | **NEG** · **NGU** · NEX | **AC6030M** | 1,0–**2,5**–4,0 | 0,10–**0,25**–0,40 | 80–**120**–160 |
| | | | Roughing | NEM | AC6040M | 1,5–**3,5**–6,0 | 0,20–**0,35**–0,60 | 70–**100**–140 |
| | Precipitation Hardening | X5CrNiCuNb 16 4, X7CrNiAl 17 7, X4CrNuMo 27 5 2, X2CrNiMoN 22 5 3, X2CrNiMoCuN 25 6 3 | Finishing | NEF (NSU) | AC6030M | 0,5–**1,5**–2,0 | 0,05–**0,15**–0,25 | 90–**115**–140 |
| | | | Medium | **NEG** · **NGU** · NEX | **AC6030M** | 1,0–**2,5**–4,0 | 0,10–**0,25**–0,40 | 70–**90**–110 |
| | | | Roughing | NEM | AC6040M | 1,5–**3,5**–6,0 | 0,20–**0,35**–0,60 | 50–**80**–120 |

## Grades

ABSOTECH ABSOTECH ABSOTECH ABSOTECH

### AC6020M / AC6030M / AC6040M / AC1030U

**AC6020M** Employes "Absotech Platinum", a new CVD coating. The first recommended grade for continuous stainless steel machining that achieves a good balance between wear resistance and fracture resistance by combining a hardened substrate with excellent wear resistance.

**AC6030M** Employes "Absotech Platinum", a new CVD coating. The first recommended grade for general machining of stainless steel that drastically reduces the occurrence of abnormal damage, which is a problem in stainless steel machining. Achieves long and stable machining thanks to the improved coating strength and excellent adhesion.


**AC6040M** Employes "Absotech Bronze", a new PVD coating and exclusive tough carbide substrate. The first recommended grade for interrupted machining of stainless steel that drastically improves the reliability in unstable machining thanks to the excellent adhesion and peel-off resistance of the new PVD coating as well as the improved fracture resistance of the exclusive carbide substrate.

**AC1030U** Employes "Absotech Bronze", a new PVD coating with a special tough carbide substrate. Achieving excellent machined surface quality with a high-quality cutting edge that reduces adhesion and micro-chipping.

## Performance


### AC6020M

**Continuous Cutting** (Medium Speed)




Work Material: X2CrNiMo17 13 2 Insert: CNMG 120408 NGU
Cutting Conditions: $v_c$ = 150 m/min, f = 0,3 mm/rev, $a_p$ = 2,0 mm, wet


**Continuous Cutting** (High Speed)




Work Material: X2CrNiMo17 13 2 Insert: CNMG 120408 NGU
Cutting Conditions: $v_c$ = 200 m/min, f = 0,3 mm/rev, $a_p$ = 2,0 mm, wet


### AC6030M

**Continuous Cutting**




Work Material: X6CrMo17 12 2 Insert: CNMG 120408 NEX
Cutting Conditions: $v_c$ = 200 m/min, f = 0,2 mm/rev, $a_p$ = 2,0 mm, wet


**Interrupted Cutting**




Work Material: X6CrMo17 12 2 Insert: CNMG 120408 NGU
Cutting Conditions: $v_c$ = 100 m/min, f = 0,1 mm/rev, $a_p$ = 1,0 mm, wet


### AC6040M

**Continuous Cutting**




Work Material: X6CrMo17 12 2 Insert: CNMG 120408 NGU
Cutting Conditions: $v_c$ = 150 m/min, f = 0,2 mm/rev, $a_p$ = 2,0 mm, wet

**Interrupted Cutting**





Work Material: CNMG 120408 NGU Insert: CNMG 120408 NGU
Cutting Conditions: $v_c$ = 230 m/min, f = 0,23 mm/rev, $a_p$ = 0,80 mm, dry

Insert Selection


BNC500 / BN7000 / BNC8115 / BNS8125 → L18-L23

## Chipbreakers

### Negative Type





### Positive Type





## Grades

### Grey Cast Iron (GG)




### Ductile Cast Iron (GGG)




## Recommended Cutting Conditions


(Min. - **Optimum** - Max.)

| Work Materials | Cutting Process | Grades | Cutting Conditions | | |
|---|---|---|---|---|---|
| | | | Depth of Cut $a_p$ (mm/rev) | Feed Rate f (mm/rev) | Cutting Speed $v_c$ (m/min) |
| Gray Cast Iron (GG-25, etc.) | High Speed Cutting | BN7000 | 0,1–**0,3**–1,0 | 0,10–**0,20**–0,50 | 500–**1.500**–2.000 |
| | Continuous – General | **AC4010K** | 0,5–**2,0**–6,0 | 0,10–**0,25**–0,40 | 200–**400**–700 |
| | Interrupted | AC4015K | 0,5–**2,0**–6,0 | 0,10–**0,30**–0,50 | 180–**300**–450 |
| | Heavy Interrupted | AC420K | 0,5–**2,0**–6,0 | 0,10–**0,30**–0,60 | 150–**200**–300 |
| Ductile Cast Iron (GGG-40.3, etc.) | High Speed Cutting | BNC500 | 0,1–**0,2**–0,5 | 0,10–**0,20**–0,40 | 150–**350**–500 |
| | Continuous – General | AC4010K | 0,5–**2,0**–6,0 | 0,10–**0,25**–0,40 | 180–**300**–450 |
| | Interrupted | **AC4015K** | 0,5–**2,0**–6,0 | 0,10–**0,30**–0,50 | 160–**250**–400 |
| | Heavy Interrupted | AC420K | 0,5–**2,0**–6,0 | 0,10–**0,30**–0,60 | 120–**170**–250 |
| High-strength Ductile Cast Iron (GGG-70, etc.) | High Speed Cutting | BNC500 | 0,1–**0,2**–0,5 | 0,10–**0,20**–0,40 | 200–**350**–500 |
| | Continuous – General | AC4010K | 0,5–**2,0**–6,0 | 0,10–**0,25**–0,40 | 160–**250**–400 |
| | Interrupted | **AC4015K** | 0,5–**2,0**–6,0 | 0,10–**0,30**–0,50 | 140–**200**–350 |
| | Heavy Interrupted | AC420K | 0,5–**2,0**–6,0 | 0,10–**0,30**–0,60 | 80–**150**–220 |

## Grades

ABSOTECH ABSOTECH

### AC4010K / AC4015K / AC420K



AC4010K The 1st recommended grade for machining grey cast iron. Adopts an ultra-thick new CVD coating to realise ultra-high-speed machining at Vc = 700 m/min.


AC4015K The 1st recommendation grade for ductile cast iron. New high-adhesion, high-strength CVD coating realises both wear resistance and chipping resistance.

AC420K Superior fracture resistance, providing excellent stability in interrupted unstable cutting and when cutting mill-scaled work.

## Performance

### AC4010K / AC4015K

**Wear Resistance, Gray Cast Iron (GG)**









Work Material: GG-25, Continuous, Insert: CNMG120408
Cutting Conditions: $v_c$ = 600 m/min, f = 0,4 mm/rev, $a_p$ = 2,0 mm, dry

**Wear Resistance, Ductile Cast Iron (GGG)**





Work Material: GGG-70, Continuous, Insert: CNMG120408
Cutting Conditions: $v_c$ = 140 m/min, f = 0,3 mm/rev, $a_p$ = 1,5 mm, wet


### AC4010K / AC4015K

**Chipping Resistance, Gray Cast Iron (GG)**




Work Material: GG-25, Interrupted, Insert: CNMG120408
Cutting Conditions: $v_c$ = 400 m/min, f = 0,3 mm/rev, $a_p$ = 2,0 mm, wet


**Chipping Resistance, Ductile Cast Iron (GGG)**




Work Material: GGG-40.3, Interrupted, Insert: CNMG120408
Cutting Conditions: $v_c$ = 450 m/min, f = 0,3 mm/rev, $a_p$ = 1,5 mm, wet

### AC420K Fracture Resistance

**GGG-40.3 Grooved (Heavy Interrupted Acceleration Test)**





**Edge Wear Comparison (After 150s)**





Work Material: GGG-40.3, Toolholder: PCLNR2525-43 Insert: CNMG120408
Cutting Conditions: $v_c$ = 350 m/min, f = 0,25 mm/rev, $a_p$ = 1,5 mm, wet

## Chipbreakers


Negative Type




Positive Type




## Grades




## S Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

| Work Material | Cutting Process | Chipbreakers | Grades | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (m/min) |
|---|---|---|---|---|---|---|
| Heat-Resistant Alloy | Finishing | NEF (NSU) | AC5005S **AC5015S** AC5025S | 0,2–**0,5**–1,5 | 0,10–**0,12**–0,20 | 50–**70**–110 |
| | Light | NEX | AC5005S **AC5015S** AC5025S | 0,5–**1,0**–3,0 | 0,10–**0,20**–0,30 | 40–**60**–90 |
| | Medium | NEG | AC5005S **AC5015S** AC5025S | 0,5–**2,0**–4,0 | 0,15–**0,25**–0,30 | 40–**60**–90 |
| | Rough | NMU/NEM | **AC5015S** AC5025S | 1,0–**2,0**–4,0 | 0,20–**0,25**–0,40 | 30–**55**–80 |
| Titanium Alloy | Finishing | NEF (NSU) | **EH510** (AC5005S, AC5015S) | 0,2–**0,5**–1,5 | 0,10–**0,15**–0,20 | 50–**65**–80 |
| | Light | NEX | AC5005S AC5015S | 0,5–**1,0**–2,5 | 0,10–**0,20**–0,25 | 40–**55**–70 |
| | Medium Rough | NEG | **EH510** (AC5005S, AC5015S) | 0,5–**2,0**–3,5 | 0,15–**0,25**–0,30 | 40–**55**–70 |
| | | NMU/NEM | AC5025S | 1,0–**2,0**–3,5 | 0,20–**0,25**–0,30 | 30–**40**–50 |

## Grades

ABSOTECH New ABSOTECH ABSOTECH

# AC5005S / AC5015S / AC5025S / EH510 / EH520

PVD grade with excellent wear and thermal resistance.

AC5005S High-speed, high-efficiency grade with great high-temperature strength, which realises excellent wear resistance in high-efficiency machining.

AC5015S The 1st recommended grade for turning exotic alloys as it realises stable tool life with high-speed, high-efficiency machining.

AC5025S High-toughness grade for realising stable tool life for interrupted cutting machining or mill-scaled work.

Carbides with excellent thermal, wear, and fracture resistance for use with exotic alloys. Lineup also includes new chipbreaker design.


EH510 General purpose grade for titanium machining that features excellent wear and thermal resistance. For applications from roughing to finishing.

EH520 Tough grade for titanium machining with excellent fracture and thermal resistance. Perfect for interrupted cutting and mill-scaled work.

## Performance


### AC5005S

**Wear Resistance (High-speed)**




Work Material: Inconel 718 (44 HRC) Insert: DNMG150408 NEF
Cutting Conditions: $v_c$ = 100 m/min, f = 0,15 mm/rev, $a_p$ = 0,5 mm, wet


**Wear Resistance (High-feed)**




Work Material: Inconell 718 (44 HRC), Insert: CNMG120408 NEG
Cutting Conditions: $v_c$ = 50 m/min, f = 0,25 mm/rev, $a_p$ = 1,2 mm, wet


### AC5015S

**Wear Resistance**




Work Material: Inconel 718 (44 HRC) Insert: CNMG120408 NEX
Cutting Conditions: $v_c$ = 40 m/min, f = 0,1 mm/rev, $a_p$ = 1,5 mm, wet


**Fracture Resistance**




Work Material: Hastelloy (22 HRC), Insert: CNMG120408 NEX
Cutting Conditions: $v_c$ = 50 m/min, f = 0,1 mm/rev, $a_p$ = 1,5 mm, wet


### AC5025S

**Wear Resistance**




Work Material: Inconel 718 (44 HRC) Insert: CNMG120408 NEX
Cutting Conditions: $v_c$ = 40 m/min, f = 0,1 mm/rev, $a_p$ = 1,5 mm, wet


**Fracture Resistance**




Work Material: Hastelloy (22 HRC), Insert: CNMG120408 NEX
Cutting Conditions: $v_c$ = 50 m/min, f = 0,1 mm/rev, $a_p$ = 1,5 mm, wet


## Chipbreakers

NSV Type Chipbreaker: For chip control during carburized layer removal
NLV Type / NFV Type Chipbreaker: For chip control during finishing of hardened steel





## Grades

Coated SUMIBORON




Uncoated SUMIBORON




## H Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

| Cutting Process | Grade | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (m/min) |
|---|---|---|---|---|
| Continuous Cutting | **BNC2115** | 0,03–**0,20**–0,35 | 0,03–**0,10**–0,20 | 110–**180**–300 |
| | BNC2010 | 0,03–**0,20**–0,35 | 0,03–**0,10**–0,20 | 50–**140**–180 |
| | BNC100 | 0,03–**0,15**–0,20 | 0,03–**0,10**–0,20 | 80–**200**–300 |
| | BN1000 | 0,03–**0,15**–0,20 | 0,03–**0,10**–0,15 | 120–**180**–300 |
| | AC503U | 0,03–**0,50**–1,00 | 0,02–**0,05**–0,10 | 40–**70**–100 |
| General Turning | **BNC2125** | 0,05–**0,30**–0,50 | 0,05–**0,20**–0,40 | 110–**160**–300 |
| | BNC2020 | 0,05–**0,30**–0,50 | 0,03–**0,20**–0,40 | 50–**120**–180 |
| | BNC160 | 0,03–**0,20**–0,35 | 0,03–**0,10**–0,20 | 80–**160**–270 |
| | BNC200 | 0,03–**0,30**–0,50 | 0,05–**0,10**–0,35 | 80–**140**–270 |
| | BN2000 | 0,03–**0,20**–0,30 | 0,03–**0,10**–0,20 | 30–**100**–200 |
| | BNX20 | 0,03–**0,30**–0,50 | 0,03–**0,15**–0,30 | 70–**130**–170 |
| Interrupted Cutting | **BNC300** | 0,03–**0,20**–0,30 | 0,03–**0,10**–0,20 | 50–**100**–150 |
| | BN350 | 0,03–**0,20**–0,30 | 0,03–**0,10**–0,20 | 50–**100**–150 |
| | BNX25 | 0,03–**0,20**–0,50 | 0,03–**0,15**–0,30 | 120–**160**–220 |

## Grades

## BNC2115 / BNC2125 / BN1000 / BN2000

BNC2115 — High-precision grade realizing long tool life with excellent surface roughness and stable machining. Maintains excellent surface roughness thanks to a high notch-wear resistant coating and tough CBN substrate.

BNC2125 — 1st recommendation grade, balancing excellent wear resistance and fracture resistance in hardened steel machining. Along with a tough CBN substrate, the coating combines wear resistance and toughness to achieve long, stable tool life even in high-efficiency and interrupted machining.


BN1000 — For high speed machining. BN1000 provides the highest wear resistance of all uncoated SUMIBORON grades. Features improved fracture resistance while still placing a priority on wear resistance.

BN2000 — General purpose grade suitable for typical hardened steel machining applications. Provides a high degree of fracture and wear resistance.

## Performance

### BNC2115


Continuous Cutting of Hardened Steel




| | |
|---|---|
| Work Material: | SCM415H, 58-62HRC |
| Insert: | DNGA 150408 NC4 |
| Cutting Conditions: | $v_c$ = 200 m/min, f = 0,1 mm/rev, $a_p$ = 0,15mm, wet |

### BNC2125


Interrupted Cutting of Hardened Steel





| | |
|---|---|
| Work Material: | SUJ2, 58-62HRC |
| Insert: | DNGA 150408 NC4 S01225 |
| Cutting Conditions: | $v_c$ = 150 m/min, f = 0,15 mm/rev, $a_p$ = 0,5 mm, 63 m/times, dry |

### BN1000 / BN2000

Wear Resistance (Continuous Cutting)





Work Material: 15CrMo5, Round Bar (58-62HRC)
Cutting Conditions: $v_c$ = 100 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry




Work Material: 100Cr6, Round Bar (58-62HRC)
Cutting Conditions: $v_c$ = 150 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry

Chipping Resistance (Interrupted Cutting)


(Comparison based on conventional BN2000 as 100%.)





Work Material: 15CrMo5, 8V Grooved Material (58-62HRC)
Insert: CNGA120408 NU-2
Cutting Conditions: $v_c$ = 150 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry


## Chipbreakers

**Negative Type**





**Positive Type**




## Grades




## N Recommended Cutting Conditions


(Min. - **Optimum** - Max.)

| Cutting Process | Category | Grades | Cutting Conditions | | |
|---|---|---|---|---|---|
| | | | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (m/min) |
| Continuous Cutting General Turning Interrupted Cutting | SUMIDIA | **DA1000** | 0,1–**0,5**–3,0 | 0,05–**0,10**–0,20 | –2000 |
| | Carbide | **H1** | 0,3–**1,0**–5,0 | 0,1–**0,20**–0,5 | –1000 |


## Grades DA1000

- Ultra-high-density sintered, ultra-fine diamond particles
- Significantly improved surface roughness on machined surfaces
- World's best wear resistance and strength
- Suitable for use with all aluminium and non-ferrous alloys

### DA1000 Wear Resistance





Comparison of Surface Roughness of Nose Radius Cutting Edge





Insert: TPGW 160308
Cutting Conditions: $v_c$ = 1000 m/min, f = 0,15 mm/rev, $a_p$ = 0,2 mm, Wet

### Wear Resistance in Turning Applications




Insert: TPGN160304
Cutting Conditions: $v_c$ = 800 m/min, f = 0,12 mm/rev, $a_p$ = 0,5 mm, wet

### Wear Resistance in Milling Applications





Insert: SNEW1204 ADFR-NF
Cutting Conditions: $v_c$ = 2000 m/min, f = 0,15 mm/rev, $a_p$ = 3,0 mm, wet


## Application Examples

### H1 + NAG Type Breakers

**ADC12 Aluminium Wheel**

Excellent adhesion resistance.
Longer tool life.








Insert: VCGT160408 NAG (H1)
Cutting Conditions: $v_c$ = 2000 m/min, f = 0,25 mm/rev, $a_p$ = 2,0 mm, wet

### DA1000

**Copper Alloy Bush**

Stable surface roughness with no edge breakage (3,2S).
Tool life improved to 3x that of conventional models.






Insert: TPGN160308 NF (DA1000)
Cutting Conditions: $v_c$ = 300 m/min, f = 0,07 mm/rev, $a_p$ = 0,08 mm, wet


## Grades

| Category | Application Range: High Precision / Finish-Light Cut / Medium Cut | Work Material: P General Steel | M Stainless Steel | K Cast Iron | S Heat Resistant Steel | H Hardened Steel | N Non-Ferrous Metal |
|---|---|---|---|---|---|---|---|
| Coated Carbide (PVD) | ACZ150 | ◎ | ◎ | | | | ○ |
| | AC5015S | ○ | ◎ | ○ | ◎ | | |
| | AC5025S | ○ | ◎ | ○ | ◎ | | |
| | AC530U | ◎ | ◎ | ○ | ○ | | ○ |
| | AC1030U | ◎ | ◎ | ○ | ○ | | ○ |
| Cermet/Coated Cermet | T1000A | ◎ | ○ | ◎ | | | ○ |
| | T1500A/T1500Z | ◎ | ○ | ○ | | | ○ |
| Carbide | H1 | ○ | ○ | ○ | | | ◎ |
| | EH510 | ○ | ○ | ○ | ◎ | | ○ |
| CBN (SUMIBORON) | BN1000/BN2000 | | | ◎ | ○ | ◎ | |
| | BN7000 | | | | | | |
| SUMIDIA | DA1000 | | | | | | ◎ |


◎ Preferred Choice ○ Suitable

## Chipbreakers


M-Class Finishing to Light Cut




G-Class Chipbreaker (Groove Design)





G-Class Chipbreaker (3D Design)




## Recommended Cutting Conditions

| Work Material / Grade | P Free Cutting Steel | | P Carbon Steel | | M Stainless Steel | | S Heat Resistant Steel | | H Hardened Steel | | N Aluminium | | N Brass | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) |
| ACZ150 | 50–200 | 0,02–0,10 | 50–150 | 0,01–0,08 | 50–150 | 0,01–0,05 | | | | | 70–300 | 0,05–0,20 | 70–300 | 0,05–0,20 |
| AC5015S | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | 50–200 | 0,02–0,10 | 30–100 | 0,02–0,10 | | | | | 70–300 | 0,05–0,20 |
| AC5 25S | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | 50–200 | 0,02–0,10 | 30–100 | 0,02–0,10 | | | | | 70–300 | 0,05–0,20 |
| AC530U | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | 50–200 | 0,02–0,10 | | | | | | | 70–300 | 0,05–0,20 |
| AC1030U | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | 50–150 | 0,02–0,10 | | | | | | | 70–300 | 0,05–0,20 |
| T1000A | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | 50–150 | 0,02–0,10 | | | | | 70–300 | 0,05–0,20 | 70–300 | 0,05–0,20 |
| T1500A | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | 50–150 | 0,02–0,10 | | | | | 70–300 | 0,05–0,20 | 70–300 | 0,05–0,20 |
| T1500Z | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | 50–150 | 0,02–0,10 | | | | | 70–300 | 0,05–0,20 | 70–300 | 0,05–0,20 |
| BN1000 | | | | | | | | | 120–300 | 0,03–0,15 | | | | |
| BN2000 | | | | | | | | | 50–200 | 0,03–0,20 | | | | |
| BN7000 | | | | | | | 50–200 | 0,05–0,20 | | | | | | |
| DA1000 | | | | | | | | | | | 70–300 | 0,02–0,10 | 70–300 | 0,02–0,10 |

## Application Range





ABSOTECH

### AC1030U


Employs a new PVD coating, with a special tough carbide substate.
Achieving excellent machined surface quality with a high-quality cutting edge that reduces adhesion and micro-chipping.

## AC1030U Performance




| | |
|---|---|
| Material: | X5CrNiS18-10, 1.4301 |
| Insert: | DCGT11T302RFY (AC1030U) |
| Cutting Data: | $v_c$ = 100 m/min, f = 0,05 mm/rev, $a_p$ = 0,1 mm, wet (Oil) |

Wear Resistance






Roughness




## Application Examples


### STKM12C-EC, Pipe







| | |
|---|---|
| Insert | CCGT060201LFX (AC1030U) |
| Cutting Data: | $v_c$ = 196 m/min, f = 0,04 mm/rev, $a_p$ = 0,4 mm, wet |


### C45, Stator Shaft







| | |
|---|---|
| Insert | VCGT110302RFX (AC1030U) |
| Cutting Data: | $v_c$ = 195 m/min, f = 0,12 mm/rev, $a_p$ = 0,175-0,25 mm, wet |


### X5CrNiS18-10, 1.4301, Valve Body







| | |
|---|---|
| Insert: | VCGT110301RFY (AC1030U) |
| Cutting Data: | $v_c$ = 31,5 m/min, f = 0,025 mm/rev, $a_p$ = 0,2 mm, wet |

### X6Cr17, Sensor Housing






| | |
|---|---|
| Insert: | DCGT11T304M NFC (AC1030U) |
| Cutting Data: | $v_c$ = 50 m/min, f = 0,06 mm/rev, $a_p$ = 0,2 mm, wet |

# New Grades for Milling

New New

## ACU2500 / XCU2500 / XCK2000


### Features of ACU2500

- Utilizing ABSOTECH, a new coating with excellent wear and chipping resistance.
- Adopts a carbide substrate with excellent fracture resistance and wear resistance, realising stable long tool life with various work material grades. Our 1st recommended grade for milling.

### Features of XCU2500 / XCK2000

- Uses the revolutionary ABSOTECH X coating, combining the wear resistance of conventional CVD coatings and fracture resistance equivalent to that of PVD coatings.
- Superb long tool life in machining of steel, cast iron, and stainless steel.

**ABSOTECH PVD**




New Super Multi-Layered Structure


Higher hardness and twice the conventional wear resistance due to a fine crystal structure AlTiCrBN-based nano-layered coating.

High Adhesion Strength

Coating adhesion signi-ficantly increased. Twice or more the conventional chipping resistance.

Applicable Grades: ACU2500, ACP3000, ACK3000

**ABSOTECH X CVD**




Pure cubic crystal AlTiN with high Al content:

With proprietary structural control technology, differently composed layers of AlTiN are stacked at the nanometre level.
With a high-Al composition containing over 80% Al on average, it also maintains a cubic crystalline structure to achieve excellent thermal resistance and high hardness.
Vastly improved wear resistance.


Special Surface Treatment:

Proprietary surface treatment introduces high compression stress to the coating, suppressing the development of cracks.
Greatly improved fracture and thermal crack resistance.


Applicable Grades: XCU2500, XCK2000

## Application Range


### P Steel





### M Stainless Steel




### K Cast Iron




### S Exotic Alloy



# Grades

B











| | | |
|---|---|---|
| Coated Grades | **Coating Series** | B2 |
| | **CVD / PVD Series** | B3–4 |
| Coated and Uncoated | **Cermet** | B5 |
| Uncoated Carbide | **“Igetalloy”** | B6 |
| CBN Grades | **“SUMIBORON”** | B7–8 |
| PCD Grades | **“SUMIDIA”** | B9 |
| | **“SUMIDIA” Binderless** | B10 |
| Chart | **Grades Comparison Chart** | B11–14 |

# Coated Carbide

## ABSOTECH X : Revolutionary coating technology that realises superb tool life.




### CVD

Pure cubic crystal AlTiN with high Al content:

With proprietary structural control technology, differently composed layers of AlTiN are stacked at the nanometre level. With a high-Al composition containing over 80% Al on average, it also maintains a cubic crystalline structure to achieve excellent thermal resistance and high hardness. Vastly improved wear resistance.

Special Surface Treatment:

Proprietary surface treatment introduces high compression stress to the coating, suppressing the development of cracks. Greatly improved fracture and thermal crack resistance.

Realises extremely long tool life for general machining through high-efficiency machining, using revolutionary technology combining wear resistance and fracture resistance.

[ABSOTECH X] For CVD Milling

Applicable Grades

For Milling: **XCU2500, XCK2000**

## ABSOTECH : New coating technology that realises absolute stability.

### CVD



Special Surface Treatment:
Chipping resistance and adhesion resistance are significantly improved by special surface treatment applied to suit the application.

High Strength Alumina Layer:
Significantly improves the coating strength by controlling crystal growth direction.

High Hardness Micro-Grain TiCN Layer:
Significantly improves the coating hardness by using a fine and uniform crystal structure.


High Adhesion Technology:
Significantly improves adhesion strength through a smooth interface between the coating and carbide substrate.

- Suppresses abnormal damage such as chipping and adhesion. Stable machining is achieved in various situations.
- Next-level high strength and high hardness coating is achieved. Achieves long, stable tool life even in high-efficiency machining.

Applicable Grades

| | | |
|---|---|---|
| For Turning: | Steel | AC8015P, AC8020P, AC8025P, AC8035P |
| | Stainless Steel | AC6020M, AC6030M |
| | Cast Iron | AC4010K, AC4015K |
| For Milling: | | ACP2000, ACK2000 |

### PVD




The Proprietary Super Multi-layered Coating Structure:
Advanced nanotechnology enables nanometre level thickness (1 nanometre is one billion of a meter) Hardness, thermal resistance and toughness are significantly improved by alternately layering one thousand layers of super thin films.

High Adhesion Technology:
Significantly improves adhesion strength through advanced control technology at the interface of the coating and carbide substrate.

- Optimised coating composition according to application. Achieves stable machining regardless of the work material.
- Significantly improves chipping resistance by improving coating adhesion strength. Stable machining is realised even under high load conditions.


Applicable Grades

| | | |
|---|---|---|
| For Turning: | Stainless Steel | AC6040M |
| | Exotic Alloy | AC5005S, AC5015S, AC5025S |
| | Small Lathes | AC1030U |
| For Milling: | | **ACU2500**, ACP3000, ACK3000 |

### Brilliant Coat — PVD

Brilliant Coat provides excellent lubricity for higher quality machining.

- PVD coating with excellent wear resistance and lubricity.
- Suppresses reactions with work material and realises beautiful machined surfaces.


Brilliant Coat


Conventional Coating

Work Material: STKM13A
Insert: CNMG120408NLU
Cutting Conditions: $v_c$: 100 m/min
f: 0,15 mm/rev
$a_p$: 1,0 mm, wet

Applicable Grades


| | | |
|---|---|---|
| For steel turning | | T1500Z, T2500Z |

### AURORA Coat (DLC : Diamond Like Carbon) — PVD

Using our proprietary PVD process tech nology, we have developed a hydrogen-free DLC coating that is extremely hard and smooth.

Comparison of Cutting Edge Adhesion After Cutting ADC12


AURORA Coat



Uncoated

Work Material: STKM13A
Cutting Conditions: $v_c$: 100 m/min
f: 0,15 mm/rev
$a_p$: 1,0 mm, wet

- Second only to diamond in terms of hardness, this smooth coating has a low coefficient of friction and provides excellent adhesion resistance to deliver better-quality machined surfaces.
- Can be used for high-speed, high-efficiency cutting of aluminium alloys, copper alloys, resins, and more.

Applicable Grades

| | |
|---|---|
| For Milling | DL1000, DL2000 |
| For Endmilling | DL1000, DL1200 |
| For Drilling | DL1300, DL1500 |

## Characteristic Values

### For Turning (CVD)

| Class | Grade | Hardness (HRA) | TRS (GPa) | Coating Type | Coating Thickness (μm) | Characteristics | Old Grades |
|---|---|---|---|---|---|---|---|
| P | AC8015P | 91,0 | 2,3 | Absotech | 14 | For high-speed and high-efficiency machining of steel. Crystal orientation control technology is used to drastically suppress the advancement of crater wear, achieving long, stable tool life during high-speed and high-feed cutting. | AC810P |
| P | New AC8020P | 90,5 | 2,2 | Absotech | 18 | Our 1st recommended grade for mill-scale work on forged material. Alumina coating with even higher strength balances outstanding stability and wear resistance in mill-scale work. | AC820P |
| P | AC8025P | 90,1 | 2,3 | Absotech | 12 | A P20 grade that drastically reduces the occurrence of abnormal damage and achieves long and stable tool life by employing a special carbide substrate and the new Absotech Platinum coating. | AC820P |
| P | AC8035P | 89,4 | 2,6 | Absotech | 9 | For interrupted machining of steel. Coating layer tensile stress removal technology greatly improves fracture resistance and achieves long, stable tool life during heavy interrupted cutting. | AC830P |
| M | AC6020M | 90,1 | 2,3 | Absotech | 5 | An M20 grade that maintains wear resistance in stainless steel machining while drastically reducing the occurrence of abnormal damage by employing a special carbide substrate and the new Absotech Platinum coating. | AC610M |
| M | AC6030M | 89,5 | 2,7 | Absotech | 5 | The first recommended grade for general machining of stainless steel that drastically reduces the occurrence of abnormal damage in stainless steel machining and achieves long and stable tool life by employing a new coating: Absotech Platinum. | AC630M |
| M | AC630M | 89,5 | 2,7 | Super FF Coat | 5 | A general purpose grade featuring improved wear and fracture resistance during stainless steel cutting. Utilises a special tough carbide substrate with a thin Super FF Coat. | AC304 |
| K | AC4010K | 91,1 | 2,5 | Absotech | 20 | 1st recommended grade for turning grey cast iron. For high-speed cast iron milling. New thick coating realizes stable long tool life even with ultra-high-speed machining of grey cast iron at $v_c$ = 700 m/min. | AC405K |
| K | AC4015K | 91,1 | 2,5 | Absotech | 16 | 1st recommended grade for turning ductile cast iron. New high-adhesion, high-strength coating realises high wear resistance and chipping resistance for stable long tool life over a wide range of cutting conditions. | AC415K |
| K | AC420K | 91,1 | 2,5 | Super FF Coat | 12 | A new, extremely versatile grade that can be used for rough, interrupted cutting of ductile and grey cast iron. Employs special, ultra-hard carbide substrate and Super FF Coat to provide stability and long tool life. | AC700G |

### For Milling (CVD)

| Class | Grade | Hardness (HRA) | TRS (GPa) | Coating Type | Coating Thickness (μm) | Characteristics | Old Grades |
|---|---|---|---|---|---|---|---|
| P | ACP100 | 89,3 | 3,1 | Super FF Coat | 6 | A grade that employs a tough carbide substrate and thin-layer Super FF Coat to provide superior thermal crack and wear resistance in high-speed milling of steel. | AC230 |
| P | ACP2000 | 89,5 | 3,2 | Absotech | 10 | For high-speed machining of steel. Stable long tool life with high-speed machining is realized by adopting a tough carbide substrate and a new coating with excellent thermal crack resistance. | ACP100 |
| P | New XCU2500 | 89,5 | 3,2 | AbsotechX | 6 | General purpose grade for a wide variety of materials such as steel, cast iron and stainless steel. New coating combining wear and fracture resistance realises long tool life in medium-speed to high-speed machining. | |
| M | ACM200 | 89,8 | 3,4 | Super FF Coat | 6 | A grade ideal for hardened steel machining that provides excellent wear and heat resistance by employing a newly-developed ultra-hard carbide and Super FF Coat. | AC230 |
| K | ACK100 | 92,0 | 2,4 | Super FF Coat | 6 | A grade that employs a high-strength carbide substrate and Super FF Coat to provide excellent wear resistance in high-speed milling. | — |
| K | ACK200 | 91,7 | 2,5 | Super FF Coat | 6 | A grade that employs a tough carbide substrate and thin-layer Super FF Coat to provide superior thermal crack and wear resistance for high-speed milling. | AC211 |
| K | ACK2000 | 91,7 | 3,1 | Absotech | 10 | For high-speed cast iron milling. Stable long tool life with high-speed machining is realized by adopting a tough carbide substrate and a new coating with excellent thermal resistance. | ACK100 ACK200 |
| K | New XCK2000 | 91,7 | 2,5 | AbsotechX | 6 | For high-speed cast iron milling. Along with a high-hardness carbide substrate, the new coating combining wear and fracture resistance realises superb long tool life in medium-speed to high-speed machining. | – |

## Characteristic Values

### For Turning (PVD)

| Class | Grade | Hardness (HRA) | TRS (GPa) | Coating Type | Coating Thickness (μm) | Characteristics | Old Grades |
|---|---|---|---|---|---|---|---|
| P | **T1500Z** (Cermet) | 92,0 | 2,2 | Brilliant Coat* | 3 | For finishing of steel.<br>Adopts Brilliant Coat for excellent lubricity and higher machined surface quality. | T2000Z |
| P | New **T2500Z** (Cermet) | 91,8 | 2,4 | Brilliant Coat* | 3 | For finishing of steel.<br>The use of Brilliant Coat with excellent lubricity and a tough cermet substrate realises excellent machined surface quality and superb stability. | T3000Z |
| P | **AC530U** | 91,4 | 3,3 | Super ZX Coat | 3 | For interrupted and general steel cutting.<br>Utilizing the super multi-layered PVD coating of nanometre thick TiAlN and AlCrN layers, coupled with a fine-grained super tough substrate for excellent fracture resistance. | ACZ310 |
| M | **AC6040M** | 91,6 | 3,8 | Absotech | 3 | The first recommended grade for interrupted machining of stainless steel that drastically improves the reliability in unstable machining thanks to the excellent adhesion and peel-off resistance of the new Absotech Bronze PVD coating, as well as the improved fracture resistance of the exclusive ultra-hard carbide substrate. | AC530U |
| M | **AC530U** | 91,4 | 3,3 | Super ZX Coat | 3 | Heavy interrupted machining and stainless steel machining.<br>Utilizing the super multi-layered PVD coating of nanometre thick TiAlN and AlCrN layers, coupled with a fine-grained super tough substrate for excellent fracture resistance. | ACZ310 |
| S | New **AC5005S** | 93,1 | 2,8 | Absotech | 5 | Grade for high-speed and high-efficiency machining of exotic alloys.<br>The use of a dedicated carbide substrate with great high-temperature strength realises excellent wear resistance in high-speed, high-efficiency machining. | — |
| S | **AC5015S** | 92,7 | 3,2 | Absotech | 5 | The first recommended grade for turning exotic alloy.<br>Adopts a carbide substrate with excellent thermal resistance and a new coating with excellent wear resistance and chipping resistance, realizing stable long tool life over a wide range of cutting conditions. | AC510U |
| S | **AC5025S** | 91,8 | 3,6 | Absotech | 5 | For partially interrupted to interrupted machining of exotic alloy.<br>Adopts a carbide substrate with excellent fracture resistance and a new coating with excellent wear resistance and chipping resistance, realizing stable long tool life with unstable cutting conditions. | AC520U |
| H | **AC503U** | 93,2 | 1,7 | Super ZX Coat | 3 | For hardenend steel.<br>Utilizing the super multi-layered PVD coating of nanometre thick TiAlN and AlCrN layers, coupled with an ultra-hard substrate for excellent wear resistance. | — |
| Small Product Machining | **ACZ150** | 91,4 | 3,3 | ZX Coat | 1 | For small tools, and high-precision finishing to general finishing applications.<br>TiN ultra-thin coating and fine-grained, super tough substrate combine to give good edge sharpness and superior cut finish. | — |
| Small Product Machining | **AC1030U** | 91,6 | 3,8 | Absotech | 2 | For precision machining that supports a wide range of work materials.<br>Employs the new "Absotech Bronze" coating with excellent adhesion and peel-off resistance to deliver excellent machined surface quality with improvements in cutting edge quality and superb stability. | — |

### For Milling (PVD)

| Class | Grade | Hardness (HRA) | TRS (GPa) | Main Coating Components | Coating Thickness (μm) | Characteristics | Old Grades |
|---|---|---|---|---|---|---|---|
| P | **ACU2500** | 91,6 | 3,8 | Absotech | 3 | General purpose grade supporting steel, stainless steel and cast iron machining.<br>Adopts a carbide substrate with excellent fracture resistance and wear resistance, plus a new coating with wear and chipping resistance, realizing stable long tool life with various work material grades. | — |
| P | **ACP200** | 89,5 | 3,2 | Super ZX Coat | 3 | For general machining of general and die steel.<br>Employs PVD coating consisting of multiple nanometre-thin layers. A general grade that achieves a good balance between fracture resistance and wear resistance when combined with an exclusive tough substrate. | ACZ330 |
| P | **ACP300** | 89,3 | 3,1 | Super ZX Coat | 3 | For interrupted machining and stainless steel machining.<br>Employs PVD coating consisting of multiple nanometre-thin layers.Provides excellent fracture resistance when combined with an ultra-tough substrate. | ACZ350 |
| P | **ACP3000** | 89,5 | 3,2 | Absotech | 3 | 1st recommended grade for milling steel. Carbide substrate with excellent thermal crack resistance, plus a new coating with excellent wear and chipping resistance, realizes stable long tool life over a wide range of cutting conditions. | ACP200<br>ACP300 |
| M | **ACM100** | 91,4 | 3,3 | Super ZX Coat | 3 | A grade that provides excellent wear resistance by employing an ultra-hard fine-grained carbide and New Super ZX Coating. | ACZ310 |
| M | **ACM300** | 89,8 | 3,4 | Super ZX Coat | 3 | The first recommended grade for stainless steel machining that achieves a good balance between wear resistance and fracture resistance by employing a newly-developed ultra-hard carbide and New Super ZX Coating. | — |
| K | **ACK300** | 91,4 | 3,3 | Super ZX Coat | 3 | General-purpose grade with an excellent balance of wear and fracture resistance. | ACZ310 |
| K | **ACK3000** | 91,7 | 3,1 | Absotech | 3 | 1st recommended grade for milling cast iron. Adopts a high thermal conductivity carbide substrate and a new coating with excellent wear and chipping resistance, realizing stable long tool life over a wide range of cast iron machining operations. | ACK300 |
| N | **DL1000** | 92,9 | 2,1 | AURORA Coat (DLC Coat) | 0,5 | For milling non-ferrous metal, utilizing DLC coat with a low coefficient of friction and excellent adhesion resistance. | — |
| N | **DL2000** | 91,6 | 3,8 | AURORA Coat (DLC Coat) | 0,5 | For milling non-ferrous metal, utilizing DLC coat with a low coefficient of friction and excellent adhesion resistance. | — |

*There may be minor differences in the colour tone/lustre of Brilliant Coat grades due to the interference of light. Such differences have no effect on performance.



**Various grades and expanded lineup of catalogue items meet a wide range of finishing needs.**

Lineup includes wear-resistant T1000A, general purpose T1500A, general purpose coated cermet T1500Z and tough T2500A.
Significantly expanded lineup of catalogue items for a wide variety of finishing applications.

## Characteristics

### Uncoated Cermet

**T1000A** High Speed Finishing Grade

High speed finishing grade with excellent wear resistance.
Improved wear and fracture resistance.
Solid solution hard phase reduces reaction with steel.
Perfect for high-speed continuous finishing of steel, cast iron and powdered metal.



### Coated Cermet

**T1500Z** New General Purpose Grade

General purpose coated cermet grade that employs new Brillant Coat* PVD coating with excellent lubricity.
Excellent wear resistance provides long tool life.
Reduces adhesion of work material for beautiful finished surfaces.



### Uncoated Cermet

**T1500A**

A general purpose grade that provides both wear and fracture resistance with higher-quality surface finish.
Mixing hard phases of different functionality, grain size and composition improves balance of wear and fracture resistance.
Improved cutting edge treatment technology provides beautiful finished machined surfaces.



### Coated Cermet

**T2500Z**

Tough grade with excellent fracture resistance and thermal crack resistance.
Fine, uniform grain structure greatly improves toughness
Improves thermal crack resistance due to the high thermal conductivity and realises long stable tool life.
Uses Brilliant Coat, with excellent lubricity to realise excellent machined surface quality.



## Characteristic Values

### For Turning

| Class | Grade | Hardness (HRA) | TRS (GPa) | Coating Type | Coating Thickness (μm) | Characteristics | Old Grades |
|---|---|---|---|---|---|---|---|
| P | T1000A | 93,3 | 1,8 | — | — | Uncoated cermet grade with excellent wear resistance that provides good cost efficiency. Demonstrates excellent wear resistance in continuous finishing applications, and stable finishing of cast iron and sintered alloy as well as steel. | T110A |
| | T1500A | 92,0 | 2,2 | — | — | A general purpose grade that employs a substrate with improved balance of fracture and wear resistance to deliver superior finished surfaces in a wide variety of cutting conditions. | T1200A |
| | T2500A | 91,8 | 2,4 | — | — | For interrupted machining of steel. Fine, uniform grain structure greatly improves toughness, realizing long tool life and excellent surface finish even with interrupted cutting. | — |
| | T1500Z | 92,0 | 2,2 | PVD Brilliant Coat* | 3 | Brilliant Coat's* new PVD coating gives excellent lubricity for higher quality machining. General-purpose coated cermet grade that can maintain high-quality machined surfaces and also gives excellent wear resistance. | T2000Z |
| | T2500Z New | 91,8 | 2,4 | PVD Brilliant Coat* | 3 | For finishing of steel. The use of Brilliant Coat with excellent lubricity and a tough cermet substrate realises excellent machined surface quality and superb stability. | T3000Z |
| K | T1000A | 93,3 | 1,8 | — | — | Exclusive uncoated cermet grade with excellent cost efficiency suitable for cast iron finishing, which requires high hardness. | T110A |

### For Milling

| Class | Grade | Hardness (HRA) | TRS (GPa) | Coating Type | Coating Thickness (μm) | Characteristics | Old Grades |
|---|---|---|---|---|---|---|---|
| P | T1500A | 92,0 | 2,2 | — | — | A general-purpose grade that employs a substrate with an improved balance between fracture and wear resistance to deliver superior finished surfaces in a wide variety of cutting conditions. | T1200A |
| | T250A | 91,4 | 2,1 | — | — | Tough cermet grade with enhanced crack advancement resistance. | — |
| M | T2500A | 91,8 | 2,2 | — | — | For finishing of steel and stainless steel. Fine, uniform grain structure greatly improves toughness, realizing long tool life and excellent surface finishing. | T250A |
| | T4500A | 91,0 | 2,3 | — | — | For finishing of steel and stainless steel. Tough grade with excellent fracture resistance and reduced thermal cracking. | — |


*There may be minor differences in the colour tone/lustre of Brilliant Coat grades due to the interference of light. Such differences have no effect on performance.

# WC (Tungsten Carbide)
# „Igetalloy“


**Igetalloy carbides have a solid history and a big variety of grades to suit many different applications. They are widely used and appreciated for their superior performance.**

The Igetalloy line-up consists of carbide cutting tools that are available in a variety of different structures and compositions, each differing in terms of WC grain size and containing varying amounts of CO binder and TiC, TaC, and other double carbide components. The wide selection enables excellent wear resistance and toughness with a variety of work materials and cutting conditions.


● For Steel




● For Stainless Steel




● For Cast Iron




## Characteristic Values

| Application | Grade | Hardness (HRA) | TRS (GPa) | Young's Modulus (GPa) | Thermal Conductivity (W/m·°C) | Compressive Strength (GPa) | Linear-Thermal Expansion Coefficient (X $10^{-6}$/°C) |
|---|---|---|---|---|---|---|---|
| P | **ST10P** | 92,1 | 1,9 | 470 | 25 | 4,9 | 6,2 |
| | **ST20E** | 91,8 | 1,9 | 550 | 42 | 4,8 | 5,2 |
| | **A30** | 91,3 | 2,1 | 520 | — | — | 5,2 |
| | **A30N** | 91,2 | 2,2 | 520 | — | — | — |
| | **ST40E** | 90,4 | 2,6 | — | 75 | — | — |
| M | **EH510** | 92,6 | 2,6 | — | — | — | — |
| | **EH520** | 91,7 | 3,0 | — | — | — | — |
| | **A30** | 91,3 | 2,1 | 520 | — | — | 5,2 |
| | **A30N** | 91,0 | 2,4 | — | — | — | — |
| K | **BL130** | 94,3 | 2,9 | — | — | — | — |
| | **H2** | 93,2 | 1,8 | 600 | 105 | 6,1 | 4,4 |
| | **H1** | 92,9 | 2,1 | 650 | 109 | 6,1 | 4,7 |
| | **EH510** | 92,6 | 2,6 | — | — | — | — |
| | **H10E** | 92,3 | 2,0 | — | 67 | — | — |
| | **EH520** | 91,7 | 3,0 | — | — | — | — |
| | **G10E** | 91,1 | 2,2 | 620 | 105 | 5,7 | — |
| N | **H1** | 92,9 | 2,1 | 650 | 109 | 6,1 | 4,7 |
| | **H20** | 91,6 | 3,8 | — | — | — | — |
| S | **EH510** | 92,6 | 2,6 | — | — | — | — |
| | **EH520** | 91,7 | 3,0 | — | — | — | — |

# SUMIBORON






**High hardness and heat resistance for cutting high hardness steel and hard cast iron. Long tool life with high-speed finishing of grey cast iron.**


In 1977, Sumitomo Electric Hardmetal successfully developed a revolutionary CBN sintered tool - SUMIBORON. The main component in SUMIBORON is Cubic Boron Nitride with a special ceramic binder sintered under super high pressure and temperature. As compared to other conventional tool materials, CBN has higher hardness and excellent heat resistance.

With these distinct characteristics, SUMIBORON can perform machining of hardened steel, high hardness cast iron and exotic metals where previously only grinding was done. Furthermore, excellent efficiency and longer tool life can also be achieved from high speed machining of cast irons.

## Characteristics

| Classifications | Structure | CBN Content | Hardness (GPa) | Grades | Application | Characteristics |
|---|---|---|---|---|---|---|
| Purely CBN particles, firmly bonded |  | High | 54 | NCB100 | Cast Iron, Titanium Alloy, Pure Titanium, Co-Cr-Alloy, Cemented Carbide, Cermet | Containing no binder, the nano-to sub-micron CBN particles have a directly bonded structure. The high hardness and thermal conductivity make it highly efficient with a long tool life when machining exotic alloys such as titanium alloys and Co-Cr alloys. |
| Mainly CBN grains fused together |  | | | BN7000<br>BN7500<br>BN7115<br>BNC8125<br>BNS8125<br>BNS800 | Carbide, Chilled cast iron, Ni-Hard cast iron,Heat-resistant alloy, Cast iron<br>Sintered ferrous alloy | High carbon content. Structure consists of strongly fused CBN grains.<br>Suited to cutting cast iron, heat-resistant alloy, ultra-hard alloy, and other hard materials. |
| Mainly CBN grains held together with a binder |  | Low | 27 | BN1000, BN2000, BN350<br>BNX10, BNX20, BNX25<br>BN500, New<br>BNC2115, New BNC2125,<br>BN2010, BN2020<br>BNC300, BNC100, BNC160<br>BNC200, BNC500 | Alloy steel, Case hardened steel, Carbon tool steels, Bearing steel, Die steel, Ductile cast iron | CBN grains are fused together strongly with a special ceramic binder.<br>Strong CBN binding force gives superior wear resistance and toughness when cutting hardened steel and cast iron. |

## Grade Range Map




* Dedicated for Ductile Cast Iron.


## Characteristic Values

| Class | Grade | Binder | Carbon Content (%) | Grain Size (μm) | Hardness HV (GPa) | TRS (GPa) | Main Coating Components | Coating Thickness (μm) | Characteristics |
|---|---|---|---|---|---|---|---|---|---|
| | New **BNC2115** | TiN | 60–65 | 3 | 31–33 | 1,3–1,4 | TiAlSiN super multilayered coating | 3 | Maintains excellent surface roughness thanks to coating with high notch wear resistance and tough CBN substrate |
| | New **BNC2125** | TiN | 65–70 | 4 | 33–35 | 1,5–1,6 | TiAlSiN super multilayered coating | 3 | Along with a tough CBN substrate, the coating combines wear resistance and toughness to achieve even more stable machining. |
| H | **BNC2010** | TiCN | 50–55 | 2 | 30–32 | 1,1–1,2 | TiCN multi-layered | 2 | Improves the wear resistance of coating and substrate and stably achieves excellent surface roughness. |
| | **BNC2020** | TiN | 70–75 | 5 | 34–36 | 1,4–1,5 | TiAlN multi-layered | 2 | Provides long tool life in general and high-efficincy cutting thanks to tough substrate coated with a highly wear-resistant and highly adhesive layer. |
| | **BNC100** | TiN | 40–45 | 1 | 29–32 | 1,0–1,1 | TiAlN | 3 | Highly wear resistant coating makes this grade suited for high speed finishing. |
| | **BNC160** | TiN | 60–65 | 3 | 31–33 | 1,2–1,3 | TiAlN/TiCN | 3 | Stable, high precision finishing of hardened steel. |
| | **BNC200** | TiN | 65–70 | 4 | 33–35 | 1,4–1,5 | TiAlN/TiCN | 3 | Tough substrate with high wear resistant coating provide longer tool life. |
| | **BNC300** | TiN | 60–65 | 1 | 33–35 | 1,5–1,6 | TiAlN | 1 | Suited for finishing when there is a combination of continuous and interrupted cutting. |
| | **BNX10** | TiCN | 40–45 | 3 | 27–31 | 0,9–1,0 | – | – | Optimum wear resistance.<br>Suited to continuous, high-speed cutting. |
| | **BN1000** | TiCN | 40–45 | 1 | 27–31 | 0,9–1,0 | – | – | Ultimate wear and fracture resistance. Suited to high-speed cutting. |
| | **BNX20** | TiN | 55–60 | 3 | 31–33 | 1,0–1,1 | – | – | Crater resistant grade, suitable for high efficiency cutting under high temperature conditions. |
| | **BNX25** | TiN | 65–70 | 4 | 29–31 | 1,0–1,1 | – | – | Excellent fracture resistance during high speed cutting.<br>Suited to high speed interrupted cutting of hardened steel. |
| | **BN2000** | TiN | 50–55 | 2 | 31–34 | 1,1–1,2 | – | – | A general purpose grade for hardened steel that provides a high degree of fracture and wear resistance. |
| | **BN350** | TiN | 60–65 | 1 | 33–35 | 1,5–1,6 | – | – | High cutting edge strength. suited to heavy interrupted cutting. |
| Sintered Components | New **BN7115** | Co Compound | 90–95 | 1 | 41–44 | 2,2–2,3 | – | – | Grade balancing ultimate cutting edge sharpness with fracture resistance, suitable for finishing of sintered alloy. |
| | **BN7500** | Co Compound | 90–95 | 1 | 41–44 | 2,0–2,1 | – | – | Maintains optimum cutting edge sharpness.<br>Suited for finishing of sintered alloy. |
| | **BN7000** | Co Compound | 90–95 | 2 | 41–44 | 1,8–1,9 | – | – | Improved wear and fracture resistance in rough cutting of sintered components. |
| K | New **BNC8115** | Al Alloy | 85–90 | 8 | 39–42 | 0,95–1,15 | TiAlN | 2 | Grade with 100% solid CBN structure, using PVD coating with excellent wear resistance to enable roughing operations. |
| | New **BNS8125** | Al Alloy | 85–90 | 8 | 39–42 | 0,95–1,15 | – | – | Grade with 100% solid CBN structure that exhibits excellent wear and fracture resistance. |
| | **BN7000** | Co Compound | 90–95 | 2 | 41–44 | 1,8–1,9 | – | – | Improved wear and fracture resistance in rough cutting of cast iron and exotic alloy. |
| | **BNS800** | Al Alloy | 85–90 | 8 | 39–42 | 0,9–1,1 | – | – | 100% solid CBN structure with good thermal impact resistance. |
| | **BNC500** | TiC | 60–65 | 4 | 32–34 | 1,1–1,2 | TiAlN | 3 | Substrate with excellent wear resistance and coating makes this grade suited for hard-to-cut cast iron. |
| S | **NCB100** | – | 100 | –0,5 | 51–54 | 1,8–1,9 | - | – | Achieves high-efficiency, improved machining accuracy and long tool life in machining of exotic alloys such as titanium alloy and Co-Cr alloys. |

# SUMIDIA







**Excellent wear resistance, longer tool life, and high-speed, high-efficiency, high-precision cutting of non-ferrous metals and non-metals.**





SUMIDIA is a polycrystalline diamond material made from sintered diamond powder that was first created using our proprietary technology in 1978.
SUMIDIA's superior wear resistance achieves longer tool life, high speed, high efficiency and high precision in non-metal cutting and non-ferrous metal applications including aluminium, copper, magnesium and zinc alloys.

SUMIDIA Binderless uses nano-polycrystalline diamond for the cutting edge, demonstrating excellent wear resistance and fracture resistance.
In particular, it achieves extended tool life and machining accuracy superior to conventional polycrystalline diamond when machining hard brittle materials such as cemented carbides.

## Features

Diamond particles on the order of sub-microns to several dozen microns, sintered at high density.

Structure

| SUMIDIA Binderless | SUMIDIA | | |
|---|---|---|---|
| NPD10 | DA1000 | DA150 | DA90 |
|   Diamond particles |   |   |   Black areas in image are diamond particles. |

## Grade Range Map

| Class | Series | Finishing – Light Cutting | | Medium Cutting | Rough – Heavy Cutting |
|---|---|---|---|---|---|
| Brittle Materials | Classification | 01 | 10 | 20 | 30 |
| | SUMIDIA Binderless | NPD10 | | | |
| | SUMIDIA | | DA90 | | |
| N | Classification | N01 | N02 | N20 | N30 |
| | SUMIDIA | DA1000 | | | |
| | | | DA150 | | |
| | | DA90 | | | |

## Characteristic Values

| Class | Grade | Binder | Carbon Content (%) | Grain Size (μm) | Hardness HV (GPa) | TRS (GPa) | Characteristics |
|---|---|---|---|---|---|---|---|
| Brittle Materials | NPD10 | Co | 100 | <=0,05 | 120–130 | ≈ 3,15 | 100% diamond that directly binds nano-order diamond particles with high strength. Demonstrates optimum wear and fracture resistance as well as the best edge sharpness. |
| N | DA1000 | Co | 90–95 | –0,5 | 110–120 | ≈ 2,60 | High density sintered material made of ultra-fine diamond particles that demonstrates optimum wear and fracture resistance, and edge sharpness. |
| | DA150 | Co | 85–90 | 5 | 100–120 | ≈ 1,95 | Sintered material made of fine diamond particles that provides a good balance of workability and wear resistance. |
| | DA90 | Co | 90–95 | 50 | 50–65 | ≈ 1,10 | Coarse sintered diamond particles, with high diamond content for excellent wear resistance. |

# SUMIDIA Binderless





SUMIDIA Binderless Series uses nano-polycrystalline diamond for the cutting edge and demonstrates excellent wear and fracture resistance compared to conventional sintered diamond tools.
In particular, SUMIDIA Binderless Series allows for improvements in tool life and machining precision that go far beyond conventional diamond tools in the machining of hard brittle materials, such as carbide.

### Excellent for High Precision Machining of Carbide

Nano-polycrystalline diamond with excellent wear resistance achieves high precision machining of carbide.

### Maintains Superior Dimensional Tolerances Over Many Hours

Greatly reduces the number of tool replacemets compared to conventional diamond tools and increases work efficiency while reducing total costs.


### Suitable for Hard Brittle Material Machining

Hard brittle materials (such as ceramics) that could only be ground before can now be cut.

## Characteristics

### Comparison of Structure

Nano-Polycrystalline Diamond SEM Structure





Diamond Particles (30–50 nm)

Conventional PCD SEM Structure




Diamond Particles (1–10 μm)

### Hardness





### Application (Carbide Machining)

Hardness < 88HRA




Hardness ≥ 88HRA




### Recommended Cutting Conditions (Carbide Machining)

Coolant: Dry  Min. - **Optimum** - Max.

| Work Material | | | | Cutting Conditions | | |
|---|---|---|---|---|---|---|
| Classification | | Hardness (HRA) | SEH Grade | Cutting Speed $v_c$ (m/min) | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm/rev) |
| VM<br>VC | 70<br>60<br>50 | 83–87 | G7<br>G6 | 5–**20**–30 | 0,03–**0,10**–0,20 | 0,03–**0,10**–0,20 |
| VM<br>VC | 40 | ≥ 88 | G5<br>G2 | 5–**15**–30 | 0,03–**0,05**–0,07 | 0,03–**0,10**–0,20 |

## Coated Carbide (CVD)

| Appli-cation | Class | Grade | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | MOLDINO | Sandvik | Kennametal | SECO Tools | WALTER | ISCAR | Taegu Tec | NTK |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Turning | P | P05 | **AC8015P** | UE6105<br>MC6115 | T9105<br>T9205 | CA510<br>CA5505 | HG8010 | GC4305<br>GC4205 | KCP05<br>KCP05B | TP0501<br>TP0500 | WPP05S<br>WPP05<br>WPP01 | IC8005<br>IC8150<br>IC9015 | TT8105 | |
| | | P10 | **AC8020P** New<br>**AC8015P** | MC6115<br>MC6015<br>UE6110 | T9105<br>T9115<br>T9205<br>T9215 | CA510<br>CA515<br>CA5515 | HG8010 | GC4415<br>GC4305<br>GC4215<br>GC4315 | KCP10<br>KCP10B | TP1501<br>TP1500 | WPP10S<br>WPP10 | IC8150<br>IC8080<br>IC9015<br>IC9150 | TT8115 | CP7 |
| | | P20 | **AC8020P** New<br>**AC8025P** | MC6025<br>UE6020 | T9115<br>T9125<br>T9215<br>T9225 | CA025P<br>CA525 | GM25<br>HG8025<br>GM8020 | GC4425<br>GC4325<br>GC4225 | KCP25<br>KCP25B | TP2501<br>TP2500 | WPP20S<br>WPP20 | IC8150<br>IC8250<br>IC9015<br>IC9150 | TT5100<br>TT8125 | CP7 |
| | | P30 | **AC8035P**<br>**AC6030M**<br>**AC630M** | MC6035<br>UE6035 | T9125<br>T9135<br>T6130 | CA025P<br>CA525<br>CA530 | GM25 | GC4325<br>GC4335<br>GC4235 | KCP30<br>KCP30B | TP3500 | WPP30S<br>WPP30 | IC8080<br>IC9350 | TT7100<br>TT8135 | |
| | | P40 | **AC8035P**<br>**AC6030M**<br>**AC630M** | MC6035 | T9135<br>T9235<br>T6130 | CA530<br>CA5535 | GX30<br>GM8035 | GC4335<br>GC4235<br>GC30 | KCP40<br>KCP40B | TP3501<br>TP3500 | | IC9350 | TT7100 | |
| | M<br>S | M10<br>S10 | **AC6020M** | MC7015<br>US905<br>US7020 | T9115<br>T9215 | CA6515 | HS9105 | GC2015<br>GC1515<br>S05F | KCM15 | TM1501 | | IC9250<br>IC520M | TT9215<br>TT3005 | |
| | | M20<br>S20 | **AC6020M**<br>**AC6030M**<br>**AC630M** | MC7025<br>US7020 | T6120<br>T9125<br>T9215 | CA6525 | HG8025 | GC2025<br>GC1515 | KCM25 | TP2501<br>TM2000<br>TM2501 | | IC9025<br>IC9325<br>IC4050 | TT5100<br>TT9225 | |
| | | M30 | **AC6030M**<br>**AC630M**<br>**AC8035P** | MC7025<br>US735 | T6130 | CA6535 | GM8035<br>GX30<br>GM25 | GC2035<br>GC235 | KCM35 | TP3500<br>TM3501<br>TM4000 | | IC9350<br>IC4050<br>IC635 | TT9235 | |
| | | M40 | **AC6040M**<br>**AC630M** | US735 | | | | GC235<br>GC2035 | | TM4000 | | | TT7800 | |
| | K | K05 | **AC4010K** | MC5005<br>UC5105<br>UC5115 | T5105 | CA310<br>CA4505<br>CA4010 | HX3505 | GC3205<br>GC3210 | KCK05 | TK0501<br>TK1001 | WAK10<br>WKK10S | IC5005 | TT7005<br>TT7505 | CP1 |
| | | K10 | **AC4010K**<br>**AC4015K** | MC5005<br>MC5015<br>MC5020<br>UC5105<br>UC5115 | T515<br>T5105<br>T5115 | CA315<br>CA4505<br>CA4515<br>CA4115 | HX3305<br>HX3515<br>HG8010 | GC3210 | KCK15 | TK1000<br>TK1001 | WAK10<br>WAK20<br>WKK10S<br>WKK20S | IC5100<br>IC9150<br>IC4100 | TT7015 | CP1 |
| | | K20 | **AC4015K**<br>**AC420K**<br>**AC425K**<br>**AC8025P** | MC5015<br>UC5115<br>UE6110 | T515<br>T5125<br>T9125 | CA320<br>CA4515<br>CA4120<br>CA4115 | HX3315<br>GM8020 | GC3225 | KCK15<br>KCK20 | K2001 | WAK20<br>WAK30<br>WKK20S | IC9150<br>IC5100<br>IC4100 | TT7015 | |
| Milling | P | P10 | **XCU2500** New<br>**ACP2000**<br>**ACP100** | FH7020<br>F7030<br>MV1020 | T3130<br>T3030 | | | GC4220<br>GC4330 | KCPM20 | MP1501<br>MP1500<br>MP2501<br>MP2500 | WKP25<br>WKP25S<br>WPP35G<br>WKP35S | IC4100<br>IC5400<br>IC9015<br>IC8080<br>IC9080 | TT7080<br>TT7515<br>TT9300 | |
| | | P20 | **XCU2500** New<br>**ACP2000, ACP100** | F7030 | | | | GC4330<br>GC4340 | KCPM20<br>KCPK30 | MP2501<br>MP2500 | WKP25<br>WKP25S | IC8080<br>IC9080 | TT7400 | |
| | | P30 | **XCU2500**<br>**ACP2000, ACP100** | F7030 | | | | GC4340 | KCPK30<br>KCMP30 | | | IC9250<br>IC4050 | TT7800<br>TT8525 | |
| | M<br>S | M10 | **XCU2500** New<br>**ACM100** | | | | | | | | | | | |
| | | M20 | **XCU2500**<br>**ACM200** | F7030 | T3130 | CA6535 | GX2160<br>AX2040 | GC2040 | | MS2500 | WKP35S | | TT7800 | |
| | | M30 | **XCU2500**<br>**ACM200** | F7030 | | | | | KC994M | | | IC5820 | TT7800 | |
| | K | K10 | **XCK2000** New<br>**ACK2000**<br>**ACK200** | | | | | | KCK15 | | | IC5100 | TT7515 | |
| | | K20 | **XCK2000** New<br>**XCU2500**<br>**ACK2000**<br>**ACK200** | MV1020<br>MC5020<br>F5010<br>F5020 | T1115 | CA420M | GX2120 | GC3330<br>GC3220<br>GC3225<br>GC3020<br>GC3040 | KC915M<br>KC930M<br>KC935M | MK1500 | WAK15<br>WKP25S | IC5100<br>DT7150<br>IC4010<br>IC4050<br>IC4100 | TT6800<br>TT7080 | |

## Coated Carbide (PVD)

| Appli-cation | Class | Grade | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | MOLDINO | Sandvik | Kennametal | SECO Tools | WALTER | ISCAR | Taegu Tec | NTK |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Turning | P | P10 | **ACZ150**<br>**AC1030U** New<br>**AC5005S**<br>**AC5015S**<br>**AC5025S** | VP15TF<br>MS6015 | AH710<br>AH110<br>AH120<br>AH725 | PR915<br>PR1005<br>PR930<br>PR1215<br>PR1225<br>PR1705 | | GC1525 | KCU10<br>KC5510 | TS2000 | WSM10 | IC507<br>IC807<br>IC907 | | TM1<br>VM1<br>DT4<br>DM4 |
| | | P20 | **AC1030U**<br>**AC5025S**<br>**AC530U** | VP15TF<br>VP20RT | AH120<br>AH725<br>AH3135 | PR1225<br>PR1425 | IP2000 | GC15<br>GC1125 | KCU25 | | | IC807<br>IC808<br>IC810 | TT9080 | TM1<br>TM4<br>VM1<br>QM3<br>DM4 |
| | | P30 | **AC1030U**<br>**AC530U** | VP15TF<br>VP20RT | AH120<br>AH725<br>SH730<br>AH730 | PR1425<br>PR1525<br>PR1535 | IP3000<br>CY250 | GC1125 | | | | IC328<br>IC928 | TT8020<br>TT9030 | QM3 |
| | | P40 | **AC1030U** | | | PR660 | IP3000 | GC4335<br>GC4235 | | | | IC830 | TT8020 | |

# Grade Comparison Chart



## ■ Coated Carbide (PVD)

| Appli-cation | Class | Grade | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | Mitsubishi-Hitachi | Sandvik | Kennametal | SECO Tools | WALTER | ISCAR | Taegu Tec | NTK |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Turning | M | M10<br>S10 | New<br>**AC5005S**<br>**AC5015S**<br>**AC5025S**<br>**ACZ150** | MP9005<br>MP9015<br>VP15TF<br>VP05RT<br>VP10RT | AH110<br>AH710<br>AH725<br>AH905<br>AH8005 | PR005S<br>PR015S<br>PR915<br>PR1025<br>PR1215<br>PR1225<br>PR1305<br>PR1310 | IP050S<br>IP100S<br>JP9105<br>JP9115 | H5D6<br>GC1105<br>GC1115 | KCS10<br>KCS10B<br>KC5510<br>KCU10 | TH1000<br>TS2000 | WSM01<br>WSM10<br>WSM10S | IC804<br>IC807<br>IC808<br>IC907<br>IC908 | TT5080<br>TT3010<br>TT8010 | TM1<br>VM1<br>DT4<br>DM4<br>ZM3<br>ST4 |
| | M<br>S | M20<br>S20 | **AC1030U**<br>**AC5015S**<br>**AC5025S** | MP9015<br>MP9025<br>VP15TF<br>VP20RT<br>VP20MF<br>UP20M<br>MS9025 | AH630<br>AH120<br>AH725<br>AH8015 | PR015S<br>PR915<br>PR930<br>PR1025<br>PR1125<br>PR1215<br>PR1225<br>PR1325 | IP100S<br>HS9115 | GC15<br>GC1115<br>GC1125 | KC5525<br>KCU25<br>KC5025 | TS2500 | WSM20<br>WSM20S | IC330<br>IC806<br>IC808<br>IC830<br>IC908<br>IC928 | TT9080<br>TT9020<br>TT3020 | DT4<br>DM4<br>ZM3<br>QM3<br>TM4<br>ST4 |
| | | M30 | **AC5025S**<br>**AC6040M**<br>**AC530U**<br>**AC1030U** | MP7035<br>VP15TF<br>VP20MF<br>MS9025 | AH630<br>AH645<br>AH725 | PR1125<br>PR1525<br>PR1535 | | GC1125 | | | WSM30<br>WSM30S | IC328<br>IC330<br>IC830<br>IC840<br>IC882 | TT8020<br>TT8080<br>TT9080 | QM3<br>TM4<br>DT4<br>DM4 |
| | | M40 | **AC6040M**<br>**AC530U**<br>**AC1030U** | MP7035<br>VP15TF<br>MS6015 | AH645 | PR1125<br>PR1535 | GX30 | | | | | IC830<br>IC928 | TT8020<br>TT8080 | |
| | K | K10 | **ACZ150**<br>**AC1030U**<br>**AC5015S** | VP10RT | AH110<br>AH120 | PR905 | HX3305<br>HG3305<br>HG3315<br>HX3515<br>HG8010<br>TH315 | GC15 | | | | IC810 | TT6080 | |
| | | K20 | **ACZ150**<br>**AC1030U**<br>**AC5015S**<br>**AC5025S** | VP10RT<br>VP20RT<br>VP15TF | AH120 | PR905 | | | | | | | TT6080 | DM4<br>QM3 |
| | | K30 | **AC1030U**<br>**AC530U** | VP15TF<br>VP20RT | AH110<br>AH120<br>AH725 | | | | | | | IC830<br>IC908<br>IC910<br>IC928 | | |
| Milling | P | P10 | **ACU2500**<br>**ACP200** | VP15TF<br>MP6120 | AH110<br>AH120<br>AH710<br>AH725 | PR1225 | PN215<br>PN15M<br>JP4105<br>JP4115<br>JP4120<br>CY9020 | GC1010 | KC505M<br>KC510M<br>KC515M | F25M | | IC807<br>IC903 | TT2510<br>TT7080 | DT4<br>DM4 |
| | | P20 | **ACP3000**<br>**ACU2500**<br>**ACP200**<br>**ACP300** | VP15TF<br>VP20RT<br>MP6120<br>MP6130<br>UP20M | AH9030<br>AH120<br>AH725<br>AH3035<br>AH3225 | PR1525<br>PR1225<br>PR1230<br>PR830 | JP4120<br>CY150<br>CY1230<br>JS4045 | GC1010<br>GC1025 | KC522M<br>KC525M<br>KCSM30<br>SP6519 | MP3000<br>F30M<br>F32M<br>F40M | WSM20<br>WSM20S | IC808<br>IC810<br>IC908<br>IC910 | TT7080<br>TT9030<br>TT9080 | TM4<br>DT4<br>DM4 |
| | | P30 | **ACP3000**<br>**ACU2500**<br>**ACP200**<br>**ACP300** | VP15TF<br>VP30RT<br>MP6130<br>UP20M | AH3035<br>AH3135<br>AH3225<br>AH120<br>AH130<br>AH140<br>AH725 | PR1525<br>PR1230<br>PR830 | JS4045<br>JS4060<br>CY25<br>CY150<br>CY250<br>CY250V<br>PTH30E | GC1030<br>GC1130<br>GC2030 | KC725M<br>KC735M<br>KC525M<br>KC530M<br>KCPM40<br>KCSM30<br>SP6519 | F40M<br>T60M<br>MP3000 | WSM35<br>WSM35S<br>WSP45<br>WSP45S | IC328<br>IC330<br>IC830<br>IC928 | TT8080<br>TT8020 | DM4<br>TM4<br>ZM3 |
| | | P40 | **ACP3000**<br>**ACU2500**<br>**ACP300** | VP30RT | AH140 | | JS4060<br>JM4160<br>PTH40H | | KC725M<br>KC735M<br>KCPM40 | | WSP45<br>WSP45S | IC830<br>IC845<br>IC928 | TT8020<br>TT8080<br>TT8525B | |
| | M | M10<br>S10 | **ACM100**<br>**ACU2500**<br>**ACK300**<br>**ACP300** | MP9120<br>VP15TF | AH110<br>AH120<br>AH330<br>AH725<br>AH8005<br>AH8015 | PR1025<br>PR1225 | CY9020<br>JP4120<br>PN08M<br>PN15M<br>PN208<br>PN215 | GC1010<br>GC1025<br>GC1030<br>GC1130 | KC515M<br>SP4019<br>SP6519 | | | IC808<br>IC908 | | DT4<br>DM4<br>ZM3 |
| | | M20 | **ACM300**<br>**ACU2500**<br>**ACP300** | MP7030<br>MP7130<br>MP9120<br>MP9130<br>UP20M<br>VP15TF<br>VP20RT | AH120<br>AH130<br>AH330<br>AH725<br>AH3225<br>AH8015 | PR1210<br>PR1225<br>PR1525<br>PR830 | JP4120<br>CY150<br>JS1025 | S30T | KC522M<br>KC525M<br>SP4019<br>SP6519<br>X700 | F25M<br>F30M<br>T32M<br>MP3000<br>MS2050<br>MM4500 | WSM35<br>WSM35S | IC328<br>IC330<br>IC808<br>IC830<br>IC840<br>IC908<br>IC928 | TT9080<br>TT9030 | DT4<br>DM4<br>ZM3 |
| | | M30 | **ACM300** | MP7030<br>MP7130<br>MP7140<br>MP9130<br>VP15TF | AH130<br>AH140<br>AH330<br>AH725<br>AH3135 | PR1525<br>PR1535<br>PR830 | JM4160<br>PTH30E<br>JS1025 | GC2030<br>GC1040<br>S40T | KC522M<br>KC525M<br>KC725M<br>KCPM40<br>KCSM30 | F30M<br>F32M<br>F40M<br>MP2050<br>MS2050 | WSM35<br>WSM35S<br>WSP45<br>WSP45S | IC328<br>IC330<br>IC830<br>IC840<br>IC882 | TT8020<br>TT8080<br>TT9080 | DT4<br>DM4<br>ZM3 |
| | | M40 | **ACM300** | MP7140<br>MP9140<br>VP30RT | AH140 | PR1535 | JM4160<br>PTH40H | | KC725M<br>KCPM40<br>KCSM40 | | WSP45<br>WSP45S | IC328<br>IC330<br>IC882 | TT8020<br>TT8080 | |
| | K | K05 | **ACK3000** | MP8010 | AH110<br>AH710 | | TH303<br>TH308<br>ATH80D | GC1010 | SP4019 | MH1000 | | | | |
| | | K10 | **ACK3000**<br>**ACU2500** | MP8010 | AH110<br>AH120 | PR1210 | ATH10E<br>TH315 | GC1010<br>GC1020 | KC514M<br>SP4019 | MH1000 | | IC810<br>IC910 | TT7080<br>TT7515 | |
| | | K20 | **ACK3000**<br>**ACU2500**<br>**ACK300** | MP8010<br>VP15TF | AH110<br>AH120<br>AH330<br>GH330 | PR1210<br>PR1510 | JP4120<br>PTH13S<br>CY100H<br>CY9020 | GC1020<br>GC1025 | KC514M<br>KC524M<br>KCK20<br>SP6519 | MK2050<br>MK3000 | WKK25S | IC808<br>IC810<br>IC830<br>IC908 | TT6080<br>TT7515 | DM4 |
| | | K30 | **ACK3000**<br>**ACU2500**<br>**ACK300** | VP15TF<br>VP20RT | AH725<br>AH120<br>AH330<br>GH110<br>GH130<br>GH330 | PR1510<br>PR1210 | JS4045<br>CY150<br>CY250 | GC1025<br>GC1030<br>GC1130 | KC520M<br>KC522M<br>KC524M | MK2050 | | IC830<br>IC810<br>IC910<br>IC928 | TT6080 | |

## Cermet

| Appli-cation | Class | | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | MOLDINO | Sandvik | Kennametal | SECO Tools | WALTER | ISCAR | Taegu Tec |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Turning | P | P10 | **T1500Z*<br>T1000A<br>T1500A** | AP25N*<br>NX2525<br>VP25N* | GT720*<br>GT9530*<br>GT9535*<br>J9530*<br>NS520 | TN30<br>TN6020<br>TN610<br>TN620<br>PV710*<br>PV720*<br>CCX* | CZ25*<br>CH550 | CT5015 | KT125<br>HTX<br>KT1120 | | | IC20N<br>IC30N<br>IC520N | PV3030<br>PV3010<br>CT3000 |
| | | P20 | **T1500Z*** New<br>**T2500Z***<br>**T3000Z***<br>**T1500A**<br>**T2500A** | AP25N*<br>NX2525<br>NX3035<br>MP3025* | AT9530*<br>NS9530<br>GT9530*<br>J9530* | TN90<br>TN620<br>TN6020<br>PV720*<br>CCX* | CZ25*<br>CH550 | GC1525* | KT6215<br>KT315*<br>KT175<br>KT5020* | CM<br>CMP<br>C15M<br>TP1020 | | IC20N<br>IC30N<br>IC520N<br>IC530N | CT7000 |
| | | P30 | **T2500Z*** New<br>**T3000Z***<br>**T2500A** | MX2525<br>MP3025*<br>VP45N | NS9530<br>GT9530*<br>AT9530* | TN620<br>PV720*<br>PV730* | | | | | | | |
| | K | K10 | **T1000A** | AP25N*<br>VP25N*<br>NX2525 | GT720*<br>GT9530*<br>NS9530<br>J9530*<br>NS520 | TN610<br>PV7005*<br>PV7010*<br>CCX* | CH550 | CT5015 | KT125<br>HTX | | | | PV3030<br>CT3000 |
| Milling | P | P30 | **T2500A<br>T250A<br>T4500A** | NX2525<br>MX3030<br>NX4545<br>VP45N* | NS540<br>NS740 | TN60<br>TN90<br>TN100M<br>TN620M | MZ1000*<br>MZ2000*<br>MZ3000*<br>CH7030<br>CH7035 | CT530 | KT530M*<br>KTPK20* | C15M | | IC30N | |

* denotes coated cermet

## Uncoated Carbide

| Class | Grade | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | MOLDINO | NTK | Sandvik | Kennametal | SECO Tools | ISCAR | Taegu Tec |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| P | P10 | **ST10P** | | TH10 | | WS10 | | S1P | | | | |
| | P20 | **ST20E** | UTi20T | KS20 | | EX35 | | SMA | K125M | | IC70<br>IC50M | UF10 |
| | P30 | **A30N** | UTi20T | KS15F<br>UX30 | PW30 | EX35<br>EX40 | | SM30 | | | IC54<br>IC28 | P30 |
| | P40 | **ST40E** | | TX40 | | EX45 | | S6 | | | IC54<br>IC28 | |
| M | M10 | **EH510** | | TH10 | | EX35<br>WA10B | KM1 | H10A | KU10<br>K313<br>K68<br>KYSM10 | 890 | IC07<br>IC08<br>IC20 | |
| | M20 | **EH520** | UTi20T | KS20 | | EX35 | | H13A | K313<br>K68 | HX<br>883 | IC07<br>IC08<br>IC20 | UF10 |
| | M30 | **A30<br>A30N** | UTi20T | UX30 | | | | H10F<br>SM30 | | | IC28 | |
| K | K01 | **H2<br>H1** | HTi05T | KS05F | | WH01<br>WH05 | | | KU10<br>K68<br>K313<br>K115M | | IS8 | |
| | K10 | **H1<br>EH510** | HTi10 | TH10 | KW10<br>GW15 | WH10 | KM1 | H13A | KU10<br>K313<br>K68<br>K115M<br>K110M<br>KY3500 | 890 | IC20<br>IS8 | K10 |
| | K20 | **G10E, H10E<br>EH520** | UTi20T | KS15F<br>KS20 | GW25 | WH20 | KM3 | H13A | KMF<br>KY3500<br>KYHS10 | 890<br>883<br>HX | IC20<br>IS8 | |
| | K30 | **G10E, H10E** | UTi20T | | | WH30 | | | KY3500 | 883 | | |
| S | S10<br>S20 | **EH510<br>EH520** | RT9005<br>RT9010<br>MT9015<br>TF15 | TH10<br>KS05F<br>KS15F<br>KS20 | SW05<br>SW10<br>SW25<br>KW10<br>GW15 | WH10 | | H10A<br>H10F<br>H13A | KU10<br>K313<br>K68<br>KMF<br>K110M<br>K1025<br>KYHS10 | HX<br>H25 | IC20<br>IC07<br>IC08<br>IC28 | K10 |
| Fine-grained Carbide | | **A1** | | UM | | NM25 | | N6F<br>H10F | | 883 | IC08 | |

# Grade Comparision Chart



## CBN

| Class | Grade | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | NTK | Chukyo | Sandvik | Kennametal | SECO Tools | ISCAR |
|---|---|---|---|---|---|---|---|---|---|---|---|
| K | K01 | **NCB100**<br>**BNC500***<br>**BN7000**<br>**BN500** | MB710<br>MB5015 | BX930<br>BX870<br>BX910 | KBN475<br>KBN60M | B30<br>B16 | | CB7525<br>CB7925 | KB1340 | | IB50<br>IB85 |
| | K10 | **BN7000**<br>**BN500** | MB710<br>MB730<br>MB5015<br>MB4020 | BX470<br>BX480<br>BX950 | KBN60M<br>KBN900 | B23<br>B16 | HB55<br>HB56<br>HB569<br>HB580<br>HB57 | CB7925 | | CBN200<br>CBN300<br>CBN300P<br>CBN400C | IB55<br>IB90 |
| | K20 | **BN700**<br>**BN7000**<br>**BNS800** | MB730<br>MB4020<br>MB4120<br>MBS140 | BX470<br>BX480<br>BXC90<br>BX90S | KBN900 | | HB56<br>HB569<br>HB580<br>HB57 | | | | |
| | K30 | **BNC8115** New<br>**BNS8125** | MBA4120<br>MBS140<br>BC5030 | BX90S<br>BXC90 | | | HB57 | | KB5630 | CBN500 | |
| S | S01 | **NCB100**<br>**BN7000** | MB730<br>MB4020<br>MB4120 | BX940<br>BX950<br>BX470<br>BX480 | | | HB55<br>HB580<br>HB52 | | KB5630<br>KB1340 | | IB85<br>IB05S<br>IB10S |
| H | H01 | **BNC2010** New<br>**BNC2115**<br>**BN1000**<br>**BN2000** | BC8105<br>BC8110<br>MBC010<br>MB810<br>MB8110 | BXA10<br>BXM10<br>BX310 | KBN05M<br>KBN25M<br>KBN510 | B5K<br>B52 | HB55<br>HB550<br>HB580<br>HB590 | CB7105 | KB5610 | CH0550<br>CBN10<br>CBN100<br>CBN60K | IB05H<br>IB50<br>IB10HC |
| | H10 | **BNC2010**<br>**BNC2020** New<br>**BNC2115** New<br>**BNC2125**<br>**BN2000** | BC8110<br>BC8120<br>MBC020<br>MB8025<br>MB8110<br>MB825 | BXA10<br>BXM10<br>BX330<br>BX530 | KBN05M<br>KBN25M<br>KBN525 | B5K<br>B6K<br>B52<br>B36 | HB55<br>HB59<br>HB550<br>HB580<br>HB52 | CB7015<br>CB7115<br>CB20 | KBH20<br>KB5610<br>KB5625 | CBN10<br>CBN150<br>CBN100<br>CBN060K<br>CBN160C | IB10H<br>IB55<br>IB25HA |
| | H20 | **BNC2020** New<br>**BNC2125**<br>**BNX20** | BC8120<br>BC8020<br>MBC020<br>MB8025<br>MB8120 | BXA20<br>BXM20<br>BX360 | KBN30M<br>KBN35M<br>KBN900 | B36<br>B40<br>B6K | HB57<br>HB59<br>HB590<br>HB580 | CB7025<br>CB7125<br>CB50 | KBH20<br>KB5625<br>KB5630 | CH2540<br>CBN150<br>CBN160C | IB20H<br>IB20HC<br>IB25H<br>IB25HC |
| | H30 | **BNC300**<br>**BN350**<br>**BNX25** | MB835<br>MB8130<br>BC8130 | BXM20<br>BXA20<br>BXC50<br>BX380 | KBN30M<br>KBN35M<br>KBN900 | B40 | HB57<br>HB580 | CB7525<br>CB7135 | KB5630 | CH3515 | IB90 |


## PCD

| Class | Grade | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | NTK | Chukyo | Sandvik | Kennametal | SECO Tools | ISCAR |
|---|---|---|---|---|---|---|---|---|---|---|---|
| N | N01 | **DA90**<br>**DA1000** | MD205 | DX180<br>DX160 | KPD001 | PD1 | | CD05<br>CD10 | KD1400 | | ID5 |
| | N10 | **DA150**<br>**DA1000** | MD205<br>MD220 | DX140 | KPD001<br>KPD010<br>KPD230 | PD2 | HD100<br>HD30<br>HD60 | CD1810 | KD1400<br>KD1425 | PCD05<br>PCD10 | ID5 |
| | N20 | **DA1000**<br>**DA2200** | MD220<br>MD230 | DX120<br>DX110 | KPD230 | PD2 | HD100<br>HD30<br>HD50 | | KD1400<br>KD1425 | PCD05<br>PCD20 | |
| | N30 | **DA1000**<br>**DA2200** | MD2030<br>MD230 | DX110 | | | HD30<br>HD50<br>HD700<br>HC100 | | KD1400 | PCD05<br>PCD30<br>PCD30M | |

# Indexable Inserts for Turning

## Negative / Positive Inserts

**C1–C96**






ISO **Inserts Identi ication Table** ..... C2–3
General-purpose Chipbreaker for M-class Positive Inserts **NGU** New ..... C4–5
Chipbreaker for Low Carbon and General Steel Turning **NFE / NFB** ..... C6
Chipbreaker for Hardened Steel Turning **NGH** ..... C7
Chipbreaker for Exotic Alloys and Stainless Steel Turning **NEG / NEF** ..... C8–9
Chipbreaker for Stainless Steel Turning **NEM** ..... C10
Positive M Class Chipbreaker **NFB / NLB** ..... C11
Chipbreaker for Steel Turning **(M) NSI** ..... C12
Comparison Chart **Chipbreaker** ..... C13
Selection **Chipbreaker Application Table** ..... C14–19

Negative Inserts **C / 80° Diamond Type (With Hole)** ..... C20–28
**D / 55° Diamond Type (With Hole)** ..... C29–36
**S / Square Type (With Hole)** ..... C37–44
**S / Square Type (Without Hole)** ..... C45
**T / Triangle Type** ..... C46–54
**T-REX Insert** ..... C52
**V / 35° Diamond Type (With Hole)** ..... C55–57
**W / Polygon Type (With Hole)** ..... C58–62

Positive Inserts **C / 80° Diamond Type (With Hole)** ..... C63–69
**D / 55° Diamond Type (With Hole)** ..... C70–73
**R / Round Type (With Hole)** ..... C74
**S / Square Type (With Hole)** ..... C75–78
**S / Square Type (Without Hole)** ..... C79
**T / Triangle Type (With Hole)** ..... C80–87
**T / Triangle Type (Without Hole)** ..... C86-89
**V / 35° Diamond Type (With Hole)** ..... C90-93
**W / Polygon Type (With Hole)** ..... C94–95


**Stock marking chart**

- ● : Euro stock item
- ○ : Japan stock item
- ▲ : To be replaced by new item

[—] : We cannot produce

**Note:**
Stocking policy may change without prior notice, please consult our sales representative for actual stock situation.

# Inserts Identification Table



**C N M G**

① **Insert Shape** — Chart 1

② **Relief Angle** — Chart 2

③ **Tolerance** — Chart 3

④ **Insert Type** — Chart 4

## Chart 1: Insert Shape

| Symbol | Insert Shape | | Angle |
|---|---|---|---|
| **C** | | Diamond | 80° |
| D | | | 55° |
| E | | | 75° |
| F | | | 50° |
| V | | | 35° |
| R | | Round | — |
| S | | Square | 90° |
| T | | Triangle | 60° |
| W | | Trigon | 80° |
| A | | Parallelogram | 85° |
| B | | | 82° |
| K | | | 55° |
| H | | Hexagonal | 120° |
| O | | Octogonal | 135° |
| P | | Pentagonal | 108° |
| L | | Rectangular | 90° |
| M | | Rhombic | 86° |


## Chart 2: Relief Angle

| Symbol | Relief Angle |
|---|---|
| A | 3° |
| B | 5° |
| C | 7° |
| D | 15° |
| E | 20° |
| F | 25° |
| G | 30° |
| **N** | 0° |
| P* | 11° |
| O | Others |

* Inserts with a 10° relief angle are sometimes considered as "P"

## Chart 3: Tolerance (mm)

| Symbol | Nose Height | Inscribed Circle | Thickness |
|---|---|---|---|
| A | ± 0,005 | ± 0,025 | ± 0,025 |
| F | ± 0,005 | ± 0,013 | ± 0,025 |
| C | ± 0,013 | ± 0,025 | ± 0,025 |
| H | ± 0,013 | ± 0,013 | ± 0,025 |
| E | ± 0,025 | ± 0,025 | ± 0,025 |
| G | ± 0,025 | ± 0,025 | ± 0,13 |
| J* | ± 0,005 | ±0,05 – ±0,15 | ± 0,025 |
| K* | ± 0,013 | ±0,05 – ±0,15 | ± 0,025 |
| L* | ± 0,025 | ±0,05 – ±0,15 | ± 0,025 |
| **M*** | ±0,08 – ±0,2 | ±0,05 – ±0,15 | ± 0,13 |
| N* | ±0,08 – ±0,2 | ±0,05 – ±0,15 | ± 0,025 |
| U* | ±0,13 – ±0,38 | ±0,08 – ±0,25 | ± 0,13 |



The height "m" on sharp corner.

## Chart 4: Insert Hole or Breaker

| Symbol | Hole | Hole Style | Chip Breaker | Shape | Symbol | Hole | Hole Style | Chip Breaker | Shape |
|---|---|---|---|---|---|---|---|---|---|
| N | No Hole | — | Nil | | A | With Hole | Straight Hole | Nil | |
| R | | | One Face | | M | | | One Face | |
| F | | | Both Faces | | **G** | | | Both Faces | |
| W | With Hole | Straight hole with top end counter-sink (40°–60°) | Nil | | B | With Hole | Straight hole with top end counter-sink (70°–90°) | Nil | |
| T | | | One Face | | H | | | One Face | |
| Q | With Hole | Straight hole with top end counter-sink (40°–60°) | Nil | | C | With Hole | Straight hole with top end counter-sink (70°–90°) | Nil | |
| U | | | Both Faces | | J | | | Both Faces | |
| | | | | | X | — | — | — | Special |

### ● Tolerance of Nose Height (M-Class)

| Inscribed Circle | Triangle | Square | 80° Diamond | 55° Diamond | 35° Diamond | Round |
|---|---|---|---|---|---|---|
| 6,35 | ± 0,08 | ± 0,08 | ± 0,08 | ± 0,11 | — | — |
| 9,525 | ± 0,08 | ± 0,08 | ± 0,08 | ± 0,11 | ± 0,16 | |
| 12,70 | ± 0,13 | ± 0,13 | ± 0,13 | ± 0,15 | | |
| 15,875 | ± 0,15 | ± 0,15 | ± 0,15 | ± 0,18 | | |
| 19,05 | ± 0,15 | ± 0,15 | ± 0,15 | ± 0,18 | | |
| 25,40 | ± 0,18 | ± 0,18 | ± 0,18 | | | |
| 31,75 | — | ± 0,20 | | | | |

### ● Tolerance of Inscribed Circle (M-Class)

| Inscribed Circle | Triangle | Square | 80° Diamond | 55° Diamond | 35° Diamond | Round |
|---|---|---|---|---|---|---|
| 6,35 | ± 0,05 | ± 0,05 | ± 0,05 | ± 0,05 | — | — |
| 9,525 | ± 0,05 | ± 0,05 | ± 0,05 | ± 0,05 | ± 0,05 | ± 0,05 |
| 12,70 | ± 0,08 | ± 0,08 | ± 0,08 | ± 0,08 | — | ± 0,08 |
| 15,875 | ± 0,10 | ± 0,10 | ± 0,10 | ± 0,10 | — | ± 0,10 |
| 19,05 | ± 0,10 | ± 0,10 | ± 0,10 | ± 0,10 | — | ± 0,10 |
| 25,40 | ± 0,13 | ± 0,13 | ± 0,13 | — | — | ± 0,10 |
| 31,75 | — | ± 0,15 | — | — | — | ± 0,12 |

# Inserts Identification Table

**12 04 08 N - GE**

⑤ **Insert Size** — Chart 5

⑥ **Thickness** — Chart 6

⑦ **Corner Radius** — Chart 7

⑧ **Feed Direction** — Chart 8

⑨ **Chip Breaker** — Chart 9

**Picture of insert shown as example**
(ISO Cat, No,)



## Chart 5: Cutting Edge Length (mm)

| Shape | Symbol | Cutting Edge | Inscribed Circle |
|---|---|---|---|
| C | 03 | 3,55 | 3,50 |
| | 04 | 4,97 | 4,30 |
| | 06 | 6,4 | 6,35 |
| | 08 | 8,0 | 7,94 |
| | 09 | 9,7 | 9,525 |
| | **12** | 12,9 | 12,70 |
| | 16 | 16,1 | 15,875 |
| | 19 | 19,3 | 19,05 |
| | 25 | 25,8 | 25,4 |
| S | 06 | 6,35 | 6,35 |
| | S7 | 7,14 | 7,14 |
| | 07 | 7,94 | 7,94 |
| | 09 | 9,525 | 9,525 |
| | 12 | 12,70 | 12,70 |
| | 15 | 15,875 | 15,875 |
| | 19 | 19,05 | 19,05 |
| | 25 | 25,40 | 25,40 |
| | 31 | 31,75 | 31,75 |
| D | 07 | 7,7 | 6,35 |
| | 09 | 9,7 | 7,94 |
| | 11 | 11,6 | 9,525 |
| | 15 | 15,5 | 12,70 |
| | 19 | 19,4 | 15,875 |
| V | 08 | 8,3 | 4,76 |
| | 09 | 9,7 | 5,56 |
| | 11 | 11,1 | 6,35 |
| | 16 | 16,6 | 9,525 |
| | 22 | 22,1 | 12,7 |
| T | 06 | 6,9 | 3,97 |
| | 08 | 8,2 | 4,76 |
| | 09 | 9,6 | 5,56 |
| | 11 | 11,0 | 6,35 |
| | 13 | 13,7 | 7,94 |
| | 16 | 16,5 | 9,525 |
| | 22 | 22,0 | 12,70 |
| | 27 | 27,5 | 15,875 |
| | 33 | 33,0 | 19,05 |

| Shape | Symbol | Cutting Edge Neg. | Cutting Edge Pos. | Inscribed Circle Neg. | Inscribed Circle Pos. |
|---|---|---|---|---|---|
| W | 03 | 3,8 | | 5,56 | |
| | 04 | 4,3 | | 6,35 | |
| | 05 | 5,4 | | 7,94 | |
| | 06 | 6,5 | | 9,525 | |
| | 08 | 8,7 | | 12,70 | |
| | 10 | 10,9 | | 15,875 | |
| | 11 | | 4,3 | | 6,35 |
| | 16 | | 6,5 | | 9,525 |
| R | 08 | 8,0 | | 8,0 | |
| | 10 | 10,0 | | 10,0 | |
| | 12 | 12,0 | | 12,0 | |
| | 12 | 12,70 | | 12,70 | |
| | 15 | 15,875 | | 15,875 | |
| | 16 | 16,0 | | 16,0 | |
| | 19 | 19,05 | | 19,05 | |
| | 20 | 20,0 | | 20,0 | |
| | 24 | 24,0 | | 24,0 | |
| | 25 | 25,0 | | 25,0 | |
| | 25 | 25,40 | | 25,40 | |
| | 32 | 32,0 | | 32,0 | |

## Chart 6: Thickness

| Symbol | Thickness (mm) |
|---|---|
| X1 | * |
| 01 | 1,59 |
| 02 | 2,38 |
| T2 | 2,78 |
| 03 | 3,18 |
| T3 | 3,97 |
| **04** | 4,76 |
| 05 | 5,56 |
| 06 | 6,35 |
| 07 | 7,94 |
| 09 | 9,52 |

(*):
CCET03X1 Insert thickness: 1,40
CCET04X1 Insert thickness: 1,80

## Chart 7: Nose Radius

| Symbol | Nose Radius (mm) |
|---|---|
| 00 | Sharp Point |
| 003 | 0,03 |
| 008 | 0,08 |
| 01 | 0,1 |
| 015 | 0,15 |
| 018 | 0,18 |
| 02 | 0,2 |
| 0,35 | 0,35 |
| 04 | 0,4 |
| **08** | 0,8 |
| **10** | 1,0 |
| 12 | 1,2 |
| 16 | 1,6 |
| 20 | 2,0 |
| 24 | 2,4 |
| 32 | 3,2 |
| M0 | Round Insert (Metric) |
| 00 | Round Insert (Imperial) |

An "M" after the nose radius indicates a negative tolerance
Example:
CCG T09T302 **M** NSI AC520U

## Chart 8: Feed Direction

| Symbol | Direction |
|---|---|
| R | Right-hand |
| L | Left-hand |
| **N** | Neutral |

## Chart 9: Chip Breaker

| Symbol | Process | Bumpy Type | Standard | Handed |
|---|---|---|---|---|
| F | Fine Finishing to Finishing | FA, FL, FE, FB, FC FK, FP | | FT, FX, FZ FY, FW |
| S L | Light Cut | SE, SEW, SI, SC, SF, SP, SU, SX LU, LUW, LB | | SD SDW ST |
| G U | General | **GE**, GU, GUW UG, UP US, UX | GZ UZ | UM |
| M | Rough | MP, MU, MX, ME | MC | MM HM |
| H | Heavy | HG, HP, HF | HU HW | |

| Other Specials | |
|---|---|
| Wide Chipbreaker | W |
| For Countersink | C |
| For Round insert | RD, RP, RX, RH |
| For Exotic Alloy | EF, EG, EX, EM |
| For Aluminium | AW, AG, AX, AY, LD, GD, |
| For Hardened Steel | FV, LV, GH |
| For Carburized Layer Removal | SV |
| For Stainless Steel | EF, EG, EM |

# Chipbreaker
# NGU Type

New

## For positive Inserts



## ■ General Features

Superb versatility handles processes from roughing to finishing.
Stable machining is realised across a range of conditioins through excellent cutting edge sharpness and strength.
Item range covers a wide variety of applications.

C

D

K

R


S

T

V

W

## NGU-Chipbreaker for Positive Inserts



### Excellent chip control performance

- Wide chip pocket for various cutting conditions

### Less Vibration


- Improved chip control in a wide application field

### Suppresses chip jamming at high feed rates for ideal chip control



- Wide restraining face enables consistent chip control for light to medium cutting.

- Discharges chips well under high feed conditions and suppresses build-up




- Achieves stable machining with both versatility and low resistance




New

# Chipbreaker NGU-Type


## Improved Fracture Resistance

The two step rake angle geometry ensures outstanding sharpness and hardness.


Corner **A-A** Cross Section





CCMT 09T3_ _ Type




Edge **B-B** Cross Section





CCMT 09T3_ _ Type




## Application Range


Enhanced application range over conventional products.





## Application Examples

### 24CrMo5, Automotive Parts

Improves chip entanglement for improved machining efficiency.








**NGU** Conventional

Insert: CPMT 090308 NGU (AC8025P)
Cutting Conditions: $v_c$ = 200 m/min, f = 0,2 mm/rev,
$a_p$ = 2,0 mm, wet, internal taper boring

### 15CrMo5, Fastening Parts

Strong cutting edge design realizes 1,5 times the tool life.






**NGU** Competitor B

Insert: CCMT 09T308 NGU (AC8025P)
Cutting Conditions: $v_c$ = 190 m/min, f = 0,25 mm/rev,
$a_p$ = 1,0 mm, wet, internal boring

# Negative M Class Chipbreakers for Low Carbon and General Steel Turning






## General Features

The high performance NFE type, which ensures stable chip control in a wide range of feed rate, has been added to the chipbreaker series for low carbon steel and general steel turning.
Extensive product lines are available to meet various machining requirements.
A positive insert execution of chipbreaker NFB is also available.

## Application Range





## NFE Chipbreaker for Finishing

Supports general purpose machining to high speed machining.


The arc-shaped main breaker ensures stable chip control in a wide feed rate range.

The two step chipbreakers enable stable chip control at a low feed rate of f = 0,1 mm/rev.

The sub-breaker controls cutting chips in profiling.



Cross-section of chipbreaker





### Performance

| | |
|---|---|
| Work Material: | Pipe steel (H240LA, 1.0480) |
| Insert: | CNMG 120408 NFE (AC8025P) |
| Cutting Conditions: | $v_c$=200 m/min, f=0,4 mm/rev, $a_p$=0,2 mm, dry |

Excellent chip control under low depth of cut and high feed rate condition



NFE Type (AC8025P)




Conventional

### Application Examples

| | |
|---|---|
| Work Material: | Deep-draw steel (SPHC440) |
| Facing Insert: | CNMG 120408 NFE (AC8025P) |
| Cutting Conditions: | $v_c$ = 200 m/min, f = 0,15 mm/rev, $a_p$ = 0,2–0,5 mm, wet |

Stable chip curling and breaking in facing of gummy steel.



NFE Type (AC8025P)



Competitor

| | |
|---|---|
| Work Material: | C53E,1.1210, Ø20-100 |
| Exter. Turning+Facing Ins.: | DNMG 150412 NFE (AC8025P) |
| Cutting Conditions: | $v_c$=180 m/min, f=0,25 mm/rev (radius), 0,45 mm/rev (straight section), $a_p$ = 0,3 mm, wet |

Stable chip control even at a variable feed rate in shallow cutting.



NFE Type (AC8025P)



Conventional

## NFB Chipbreaker for Low Feed Finishing


Supports low feed machining.

Smooth chipbreaker geometry with a high rake reduces cutting resistance.

The variable rake angle in nose radius makes effective strain on chips and improves the breaking performance.



Cross-section of chipbreaker




### Application Example

| | |
|---|---|
| Work Material: | Pipe steel (STKM13C) |
| Internal Turning Insert: | DNMG 150404 NFB (T3000Z) |
| Cutting Conditions: | $v_c$ = 352 m/min, f = 0,03–0,2 mm/rev, $a_p$ = 0,7 mm, wet |

Small chip curling and control



NFB Type (T3000Z)




Competitor

# Chipbreaker
# NGH Type



## General Features


Enables medium roughing of hardened steel in combination with coating and grade AC503U.
Reduces heat generation and enables deep cutting ($a_p$ = 1–3 mm) of hardened steel by using a wide neutral ground chipbreaker (rake angle: 4°) and sharp edge.
Discharges chips smoothly.





## Negative Insert for Rough Cutting NGH Type Chipbreaker

### Performance




### Application Examples

**NGH** Type Chipbreaker



Only minor wear occured after 40 min cutting



Stable chip forming

Without Chipbreaker



Major wear occured after 20 min cutting



| | |
|---|---|
| Work Material: | X155CrVMo12-1 (61HRC) |
| Insert: | TNGG 160404 NGH (AC503U) |
| Cutting Conditions: | $v_c$ = 50 m/min, f = 0,05 mm/rev, $a_p$ = 3,0 mm, dry |

## Recommended Cutting Conditions

| Application Range | Cutting Speed $v_c$ (m/min) | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm) | Recommended Chipbreaker |
|---|---|---|---|---|
| Finishing | 40–100 | 0,02–0,10 | <1 | Without chipbreaker |
| Medium Roughing | 20–60 | 0,02–0,05 | 1–3 | NGH Type |

Work Material: Hardened steel (50–62 HRC), X155CrVMo12-1, X40CrVMo5-1, S6-5-2, High-speed powder and high speed steel

# Chipbreaker
# NEG Type / NEF Type


**For Exotic Alloys and Stainless Steel Turning**



## ■ General Features

NEG/NEF type chipbreaker for exotic alloy machining can be used for Titanium alloys, heat-resistant alloys and a variety of other exotic alloys.
They deliver excellent wear resistance and superior chip management. These chipbreakers can solve quality problems caused by the unstable tool life and poor chip control provided by conventional chipbreakers for exotic alloys.

## ■ Application Range





## NEG Chipbreaker for Roughing

Provides excellent wear resistance and chip control from general-purpose machining to roughing applications. Reduces damage to insert and eliminates trouble from chips specific to exotic alloys. Also demonstrates very high versatility.


Crater wear advancement is prevented by the round bumps, whilst maintaining excellent control.

The cutting edge maintains the strength slowing the progress of crater wear.



Excellent chip management and wear prevention is delivered by the special rake face design.

Cross Section of Chipbreaker




## ● Cutting Performance – NEG Type

### Heat Resistant Alloy

Chipbreaker type: NEG (AC510U)




Suppresses the chipping of peripheral cutting edge and notch wear. Excellent chip management.

Work Material: Inconel 718

Insert: CNMG120412

Cutting Data:
$v_c$ = 40 m/min
$a_p$ = 2,5 mm
f = 0,2 mm/rev
wet
$T_c$ = 7 min

Conventional tool (S10)



Notch wear / poor chip control

### Titanium Alloy

Chipbreaker type: NEG (AC510U)




Suppresses crater wear and flank wear. Excellent chip management.

Work Material: Ti-6Al-4V

Insert: CNMG120412

Cutting Data:
$v_c$ = 65 m/min
$a_p$ = 2,5 mm
f = 0,2 mm/rev
wet
$T_c$ = 8 min


Conventional tool (S10)



Crater wear / flank wear / poor chip control


## ● Application Example – NEG Type

Inconel 718, machine component




Insert: CNMG120408 NEG (AC520U)
Cutting Data: $v_c$ = 50 m/min, $a_p$ = 1,5 mm, f = 0,3 mm/rev, wet


Pure Titanium (Ti grade 3), machine component





Insert: CNMG120408 NEG (EH510)
Cutting Data: $v_c$=80–100 m/min, $a_p$=1,0 mm, f=0,25 mm/rev, wet

# Chipbreaker
# NEG Type / NEF Type

## ■ Material Application Range








## NEF Chipbreaker for Finishing

The NEF chipbreaker reduces chip curl diameter in finishing applications.
Provides extremely good chip management not fluctuated by the material in use.


Main chipbreaker that enables good chip control even at low depths of cut.

Sharp edge with 20° rake angle reduces wear.



The grooves on the rake face reduce heat and assist chip flow away from the workpiece.


Cross Section of Chipbreaker




## ● Cutting Performance – NEF Type

### Heat Resistant Alloy

Chipbreaker type: NEF (AC510U)



Improvements in chip control and chip removal management based on small curled chips.

Work Material: Inconel 718

Insert: CNMG120408

Cutting Data:
$v_c$ = 55 m/min
$a_p$ = 0,3 mm
f = 0,15 mm/rev
wet
$T_c$ = 8 min

| Conventional tool (S10) | Competitor's product (S10) |
|---|---|
|  |  |

There is a problem in the length and the diameter of chips.

### Titanium Alloy

Chipbreaker type: NEF (AC510U)



Improvements in chip control and chip removal management based on small curled chips.

Work Material: Ti-6Al-4V

Insert: CNMG120408


Cutting Data:
$v_c$ = 80 m/min
$a_p$ = 0,5 mm
f = 0,2 mm/rev
wet
$T_c$ = 25 min

| Conventional tool (S10) | Competitor's product (S10) |
|---|---|
|  |  |

There is a problem in the length and the diameter of chips.

## ● Application Example – NEF Type

Inconel 718, shaft component



Great improvement in chip management. Keeps workpieces free of damage. It is possible to omit final polishing process.




**NEF (AC510U)**



Conventional tool

Insert: CNMG120408 NEF (AC510U)
Cutting Data: $v_c$= 45 m/min, $a_p$= 0,25 mm, f = 0,1 mm/rev, wet

Duplex stainless steel cover



Improvements in chip management. Suppress damage to finished surface with no entanglement of chips.




**NEF (AC510U)**




Conventional tool

Insert: CNMG120408 NEF (AC510U)
Cutting Data: $v_c$= 55 m/min, $a_p$ = 0,3 mm, f = 0,125 mm/rev, wet


## Application Range









## NEM Chipbreaker for Rough Cutting


The NEM chipbreaker achieves excellent fracture and crater resistance and ensures extremely stable machining.





## Reduction of Damage

| | Reduction of Boundary Damage | | Reduction of Crater Wear | |
|---|---|---|---|---|
| | Cutting Edge | Boundary Wear Comparison | Cross Section | Crater Wear Comparison |
| Conventional Geometry |  |  |  |  |
| NEM Type |  |  |  |  |
| | The NEM chipbreaker has no changing points on the cutting edge, so boundary damage is reduced. | | The NEM chipbreaker smoothly evacuates chips thanks to its large radius rake face design, so crater wear is reduced. | |


## Application Example





Reduces breakage out of the cutting edge and ensures stable machining.

| | |
|---|---|
| Work Material: | X5CrMo17 12 2 |
| Insert: | SNMG190616NEM (AC6030M) |
| Cutting Conditions: | $v_c$ = 70 m/min, f = 0,5 mm/rev, $a_p$ = 3,0–8,0 mm, wet |







Reduces crater wear and provides long tool life.

| | |
|---|---|
| Work Material: | X5CrNiS18 10 |
| Insert: | SNMG120408NEM (AC6030M) |
| Cutting Conditions: | $v_c$ =100 m/min, f = 0,32 mm/rev, $a_p$ = 2,0–2,5 mm, wet |

# Chipbreaker
# NFB Type / NLB Type

## ■ Application Range








## NFB Chipbreaker for Finishing


## NLB Chipbreaker for Light Cutting


The NFB type for finishing and the NLB type for light cutting have been added to the chipbreaker series for low carbon and general steel machining in addition to the already present NLU type for finishing and NSU type for light cutting.
The NFB and NLB type chipbreakers improve chip control in finishing of low carbon and general steel.



Cross Section of Chipbreaker







Cross Section of Chipbreaker

## ● Performance

### Chip Control

Achieves stable chip control at small cutting depth and low feed.




NFB Type Chipbreaker (T1500A)




Competitor's Product

| | |
|---|---|
| Work Material: | Pipe (H240LA), Ø 30 Boring |
| Insert: | TPMT 110304 NFB (T1500A) |
| Cutting Conditions: | $v_c$ = 100 m/min, f = 0,12 mm/rev, $a_p$ = 0,1 mm, wet |

### Comparison of Surface Roughness of Finished Surfaces



NFB Type Chipbreaker (T1500A)



Competitor's Product

| | |
|---|---|
| Work Material: | Pipe (H240LA), Ø 100 Boring |
| Insert: | TPMT 110304 NFB (T1500A) |
| Cutting Conditions: | $v_c$ = 200 m/min, f = 0,07 mm/rev, $a_p$ = 0,1 mm, wet |

## ● Performance

### Chip Control ①


Achieves stable chip control in light cutting.


NLB Type Chipbreaker (T1500A)


Competitor's Product

| | |
|---|---|
| Work Material: | Pipe (H240LA), Ø 30 Boring |
| Insert: | TPMT 110304 NLB (T1500A) |
| Cutting Conditions: | $v_c$ = 200 m/min, f = 0,15 mm/rev, $a_p$ = 0,5 mm, wet |


### Chip Control ②


Doubles the tool life by improving chip control and reducing blemishes on machined surfaces.

NLB Type Chipbreaker (T1500A)




Competitor's Product




| | |
|---|---|
| Work Material: | Hub (C45) |
| Insert: | VBMT 160408 NLB (T1500A) |
| Cutting Conditions: | $v_c$ = 240 m/min, f =0 ,25–0,28 mm/rev, $a_p$ = 0,6 mm, wet |


# (M)NSI Type

Nose radius with minus tolerance (**M**)


Example: DCGT 11T304**M** NSI



## Application Range





## Cutting Performance




Work Material: X5CrNiMo17122
Insert: DCGT11T304M NSI, Cutting Conditions: $v_c$ = 100m/min

## Application Examples


Inconel 718, machine component external turning




1,5 x higher tool life. Improved chip management.

Insert: DCGT11T302M NSI (AC510U)
Cutting Conditions: $v_c$ = 35 m/min, f = 0,08 mm/rev, $a_p$ = 0,8 mm, wet


X5CrNi1810, Shaft component external turning & facing




Improved chip management. Suppressing cutting edge adhesion to ensure a stable, long tool life.

Insert: DCGT11T304M NSI (AC520U)
Cutting Conditions: $v_c$ = 100 m/min, f = 0,08 mm/rev, $a_p$ = 0,5 mm, wet

– Sharp designed cutting edge with low-cutting force
– Better chip control in wide range DOC for bar feeder machine
– Combination of high rake edge design and G-class precision offers superior cutting performance
– Suitable for medical parts and high precision machining



## Negative Type

| Class | Application | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | NTK | Sandvik | Kennametal | SECO Tools | WALTER | ISCAR |
|---|---|---|---|---|---|---|---|---|---|---|---|
| P | Fine Finishing | **FA** | FH,FP | TF | GP | | QF | FF | FF1 | | SF |
| | | **FL, FB** | FS,FY | NS,ZF | XP,XF,VF | WM | | | FF2 | FP5 | |
| | Finishing | **LU, FE** | SA,SY | NM | XQ,CQ,PP | TF1 | LC | FN | | NF3 | |
| | | **SU** | SH | TS,TSF | HQ | UL,WV | XF,MF | CT | MF2 | | NF |
| | Wiper Edge | **LUW** | | AFW, FW | WP,WF | | WL,WP | | W-FF2 | | |
| | | **SEW** | SW | ASW, SW | WQ | | WF,WMX | FW | W-MF2 | NF | WF |
| | Finishing to Light Cut | **SE, SX** | LP | AS,ZM | CJ,XS | ZW1,WR | PF,KF | LF, 33 | | MP3,NS6 | F3P, TF |
| | Medium Cut | **GU** □UG□ | MA,MV | TM,TQ | HS,PS | ZP | XM,QM | P,MG | M3 | MU5 | GN |
| | | **GE, UX** | MH,MP | DM,AM | CS,GS,PQ,PT | Z5 | PM,SM,KM | MN, MP1 | | MP5,NM4,NM6 | RF, LF |
| | Wiper Edge | **GUW** | MW | | WE | | WM | MW, RW | W-M3 | NM | WG |
| | Roughing | **MU, ME** | GH, RP | TH, S | HT,GT,PH | G | PR,XMR,KR | RP | M5,MR7 | NM7,NM9,RP5 | M3P,NR |
| | | **MX, MP** | HAS,MT | CH | | | | RN | MR6 | | |
| | Heavy Cut | **HG** | HL,HZ,HX | THS,TRS | PX,Standard | | QR | RM,MR | R4,R5,M6 | NR6,NRF | NM |
| | | **HP** | HH,HXD,HR | 65 | | | HR,SR | RH | R7,MR7 | NR8 | TNM |
| | | **HU, HW** | HV | | | | | | | | |
| | | **HF** | HCS | TUS | | | MR | | RR9 | NRR | R3P |
| M | Finishing | **SU, EF** | LM,SH | SS | MQ,GU | ZF1 | MF | FP,FS,LF | MF2 | NF4,FM5 | F3M |
| | Light to Medium Cut | **EX, EG** | GM,MS | SF,SA | MS, MU | ZP | 23 | MS | MF1,M1 | MM5 | TF,VL |
| | | **GU** | MM | SM | | | MM, SMR | MP | MF3,M3 | NM4,MS3 | M3M,PP |
| | Roughing | **HM** | ES,1M,2M | S | | | | UP | MF4, MF5 | NR4, RM5 | |
| | | **EM, MU** | GH,RM,HM | SH | TK | | MR, MRR | | M5,MR3 | HU5 | MR,R3M |
| K | Light Cut | **UZ** | LK,MA,MK, | CM,CF | Standard | | KF | UN | M5 | NM5 | GN |
| | Medium Cut | **GZ** □UX□ | GH,RK,GK | Standard,CH,33 | ZS,GC,KG,KH | | KM,KR | | MR7 | RK5, RK7 | |
| N | Finishing | **AX** | | P | AH | | | MS | | | |
| S | Finishing | **EF** | LS,FJ | HRF | | | SF, SGF | | | NFT | F3S |
| | Medium Cut | **EG, EX** | MJ,MS | HMM,SA | SQ | | SM, SMC | | M1 | NMT,NMS | VL |
| | Roughing | **MU** | GJ,RS | | SG,SX | | SMR | | MR3,MR4 | NRT,HU5 | |
| H | Finishing | FV, GH | | HP* | | | | | | | |
| | Light Cut | LV | BF | HF* | HH*,HL* | | | | | | |
| | Carburized Layer Removal | SV | BM | HM* | HD* | | | | | | |

* CBN/PCD tool breaker


## Positive Type

| Class | Application | Sumitomo Electric | Mitsubishi | Tungaloy | Kyocera | NTK | Sandvik | Kennametal | SECO Tools | WALTER | ISCAR |
|---|---|---|---|---|---|---|---|---|---|---|---|
| P | Finishing | **FC** | FJ,AM | 01, JRP,JTS | CF,GF,VF | AM3,AZ7,FG | UM | | GT-F1 | FM4 | |
| | | **FB, LU** (FP, FK) | FP,FM,FV,SQ | PSF,PF,23 | GP,XP,MQ,PP | ZR | PF,UF,MF,KF | 11,UF,MF,KF,XF | FF1 | PF4 | PF |
| | Wiper Edge | **LUW** | SW | | WP | | WF | FW | W-F1 | PF | WF |
| | | **SDW** | | | | | WK,WM | MW | W-F2 | | WG |
| | Finishing to Light Cut | **SI** | SMG | JS,CM,PSS | CK,SKS | YL,1L | | | | | |
| | | **LB** | LP,LM,SV,MQ | PSS,PS,24 | XQ | AM2 | | LF | | | |
| | Light to Medium Cut | **SC** | | | GQ,SK,standard | AF1,CL | | MP | MF2 | | |
| | | **SU, GU** | SV,MQ | PS,TSF,TM | HQ,XQ,GK | AZ8,AM2,AM5 | PM,UM,XM | | F1 | MP4,MM4,FK6 | SM,14 |
| | Medium Cut | **MU** | MV,MM,MK | PM | | | PR,UR,NMC | MF | F2,M3,M5 | RP4,RM4 | 19 |
| M | Finishing | **FC** | FM,FV | PSF,PF,SS,JSS | | AZ7 | MF,XF | 11,UF | FF1 | FM4 | PF |
| | Finishing to Light Cut | **SI** | SMG | | | YL,1L,CL | UF | LF,FP | | | |
| | | **LB** | LM | | MQ | | | | F1 | | |
| | Light to Medium Cut | **SU,GU** | SV | | HQ | AM5 | MM | MP | MF2 | MM4,PS5 | SM |
| | Medium Cut | **MU** | NM,MV | PM | | | UM,MR,XR,UR | MF | F2,M3,M5 | PM5,RM4 | |
| K | Finishing | **FC** | | CF | | | KF,XF | 11,UF | | FK6 | |
| | Light to Medium Cut | **MU** | MK | | | AF1,FM | KM,UM,XR | FP,LF,MF,MP | M5 | MK4,RK4 | |
| N | Finishing | **AG,AW,AY** | AZ | AL,PP | AH,AP | | AL | HP | AL | PM2 | AS,AF |
| | Finishing to Light Cut | **LD, GD** | | | | | | | | | |
| S | Finishing | **FC,SI** | FS | PSS | PP,MQ | | WF,MF | | MF2,R2,R3 | | |
| | Light to Medium Cut | **SU,GU** | LS,MS | PS,PM | HQ,GK | | UM,PM | | | FV4,MV4 | |
| H | Finishing | **FV** | | HP* | | | | | | | |
| | Light Cut | **LV** | BF* | | | | | | | | |

# Chipbreaker Application

Bumpy Breaker | Standard Breaker | Handed Breaker
Break Master (CBN/PCD) | For Chamfering

## Negative Type — Finishing to Medium Cutting




### Fine Finishing

**N-FB** — P M K N S H
Better chipcontrol under low feed conditions with sharp edge shape.
0,80 | 27° | α= 0° | CNMG1204○○NFB
C D R S T V W

**N-FA** — P M K N S H
Profile breaker perfect for fine finishing
1,0 | 20° | α= 0° | CNMG1204○○NFA
C D R S T V W

**N-FL** — P M K N S H
Optimal breaker for chip management on iron sheeting
1,0 | 10° | α= 0° | CNMG1204○○NFL
C D R S T V W

**N-FE** — P M K N S H
Good chipcontrol from low to high feed rate
1,40 | 0,70 | 20° | α= 0° | CNMG1204○○NFE
C D R S T V W

### Finishing

**N-LU** — P M K N S H
Effective chip management for fluctuating cut depths and copying
1,5 | 1,0 | 10° | α= 0° | CNMG1204○○NLU
C D R S T V W

**N-SP** — P M K N S H
Shows excellent cutting performance in finishing to light cutting
1,3 | 13° | α= 0° | CNMG1204○○NSP
C D R S T V W

**N-SU** — P M K N S H
Effective in high-speed fine finishing
1,3 | 13° | α= 0° | CNMG1204○○NSU
C D R S T V W

**N-SE** — P M K N S H
Finishing breaker reduces tool wear on rake face. Effective even for high efficiency machining.
0,1 | 1,5 | 17° | 5° | α= 0° | CNMG1204○○NSE
C D R S T V W

**N-EF** — P M K N S H
Chipbreaker for exotic alloy finishing with excellent chip management
1,2 | 20° | α= 0° | CNMG1204○○NEF
C D R S T V W

**NLU-W** — P M K N S H
High performance finishing breaker with wiper edge
Wiper
1,5 | 1,0 | 10° | α= 0° | CNMG1204○○NLUW
C D R S T V W

**NSE-W** — P M K N S H
New high feed finishing breaker with wiper edge
Wiper
0,13 | 1,9 | 17° | 5° | α= 0° | CNMG1204○○NSEW
C D R S T V W

**L/R-FX** — P M K N S H
Parallel breaker with superior sharp edge
1,5 | 14° | α= 0° | TNGG1604○○L/RFX
C D R S T V W

**L/R-FY** — P M K N S H
Wide type breaker with sharp edge
2,5 | 15° | α= 0° | TNGG1604○○L/RFY
C D R S T V W

**L/R-FT** — P M K N S H
Arc-shaped ground type finishing breaker
0,15 | 1,35 | α= 0° | TNGG1103○○L/RFT
C D R S T V W

### Light to Medium

**N-SJ** — P M K N S H
Standard breaker with excellent cutting edge strength
0,18 | 1,2 | α= 0° | SNMG1204○○NSJ
C D R S T V W


**L/R-ST** — P M K N S H
Arc-shaped ground type breaker for light cutting
0,15 | 1,65 | α= 0° | TNGG1603○○L/RST
C D R S T V W

**N-EX** — P M K N S H
Standard breaker designed especially for use with exotic alloys
2,0 | 16° | α= 0° | CNMG1204○○NEX
C D R S T V W

**N-UP** — P M K N S H
Double positive edge for optimal stainless steel cutting
2,1 | 10° | α= 0° | CNMG1204○○NUP
C D R S T V W

**N-SX** — P M K N S H
Perform copying and raise steps
1,35 | 0,2 | 15° | 3° | α= 0° | CNMG1204○○NSX
C D R S T V W

## Chipbreaker Application Range (Insert IC up to Ø 12,7 mm)




Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

# Chipbreaker Application

## Negative Type — Medium to Rough Cutting

### Medium

**N-GU** — P M K N S H
Features low cutting resistance and excellent wear resistance
0,25 | 2,05 | 25° | 7°
α= 0° | CNMG1204○○NGU
C D R S T V W

**N-GE** — P M K N S H
A versatile breaker with excellent rake surface wear in high efficiency cutting
2,0 | 0,25 | 23° | 3°
α= 0° | CNMG1204○○NGE
C D R S T V W

**N-UX** — P M K N S H
Extremely reliable and versatile breaker with strong cutting edge
2,0 | 0,25 | 15°
α= 0° | CNMG1204○○NUX
C D R S T V W

**N-UG** — P M K N S H
Popular and versatile breaker
1,7 | 0,2 | 21° | 4°
α= 0° | CNMG1204○○NUG
C D R S T V W

**N-EG** — P M K N S H
General-purpose chipbreaker for exotic alloys with good chip control and wear resistance
1,75 | 0,09 | 30°
α= 0° | CNMG1204○○NEG
C D R S T V W

**NGU-W** — P M K N S H
Finishing breaker with wiper edge for high efficiency medium finishing
Wiper
2,5 | 0,3 | 23°
α= 0° | CNMG1204○○NGUW
C D R S T V W

**L/R-UM** — P M K N S H
General-purpose ground type medium cutting breaker
2,0 | 0,15 | 14°
α= 0° | SNMG1204○○L/RUM
C D R S T V W

### Medium to Rough

**N-EM** — P M K N S H
Achieves excellent fracture and crater resistance
2,5 | 0,05
α= 0° | CNMG1204○○NEM
C D R S T V W

**N-MU** — P M K N S H
Economical, double-sided breaker with low cutting resistance for high feed cutting
2,5 | 0,3 | 20° | 4°
α= 0° | CNMG1204○○NMU
C D R S T V W

**N-ME** — P M K N S H
Chipbreaker for rough cutting that supports high-feed cutting with reduced rake face wear
0,3 | 2,4 | 4°
α= 0° | CNMG1204○○NME
C D R S T V W


**N-MX** — P M K N S H
Strong cutting edge for interrupted cutting
2,3 | 0,2 | 0,4 | 20° | 15°
α= 0° | CNMG1204○○NMX
C D R S T V W

**N-UZ** — P M K N S H
Standard breaker with stable cutting performance
1,9 | 0,3 | 14° | 4°
α= 0° | CNMG1204○○NUZ
C D R S T V W

**N-GZ** — P M K N S H
Extremely reliable standard breaker with strong cutting edge
1,9 | 0,25 | 16°
α= 0° | CNMG1204○○NGZ
C D R S T V W

**L/R-HM** — P M K N S H
Wide, M class, handed breaker with low cutting resistance for medium to rough cutting.
2,7 | 15° | 0,2 | 25°
α= 0° | TNMG1604○○L/RHM
C D R S T V W

## Chipbreaker Application Range (Insert IC up to Ø 12,7 mm)




Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

# Chipbreaker Application

Bumpy Breaker | Standard Breaker | Handed Breaker
SUMIBORON Break Master | For Chamfering

## Negative Type — Rough Cutting

### Rough to Heavy

**N-HG** — P M K N S H
Excellent chip management for heavy cutting
0,4 | 22°
α= 0°
CNMM1606○○NHG
C D R S T W

**N-MP** — P M K N S H
Single-sided breaker with low cutting resistance for rough cutting
0,3 | 22°
α= 0°
CNMM1606○○NMP
C D R S T W

**N-HP** — P M K N S H
Strongest cutting edge for heavy cutting
0,3~0,6 | 22°
α= 0°
CNMM1606○○NHP
C D R S T W

**N-HU** — P M K N S H
Strong edges and excellent chip management for heavy cutting
3,2 | 0,6 | 0,25 | -15° | 16°
α= 0°
SNMM2507○○NHU
C D R S T W

**N-HW** — P M K N S H
Two step breaker with excellent chip evacuation for heavy cutting
6,3 | 0,3 | 0,75 | 17° | -15°
α= 0°
SNMM3109○○NHW
C D R S T W

**N-HF** — P M K N S H
Strong edge chipbreaker for heavy cutting with excellent chip evacuation even in high-feed cutting
4,5 | 0,2 | 0,4 | 20° | 15°
α= 0°
SNMM1906○○NHF
C D R S T W


## Negative Type — For Hardened Steel

### Finishing


**N-GH** — P M K N S H
For cutting hardened steel with low cutting force and excellent chip control
3,5 | 3°
α= 0°
CNGG1204○○NGH
C D R S T W

## Chipbreaker Application Range


Rough to Heavy (IC Ø15,875 to 19,05 mm)




Rough to Heavy (IC Ø25,4 mm)




Rough to Heavy (IC Ø31 mm)




Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

Bumpy Breaker | Standard Breaker | Handed Breaker | Break Master (CBN/PCD)

## Positive Type — Medium to Rough Cutting

### Finish to Light

**N-FB** — P M K N S H
Finishing chipbreaker for soft steel providing excellent chip control and surface finish quality
0,5 | 20°
α= 5° 7° 11°
CCMT09T3○○NFB
C D R S T V W

**N-LU** — P M K N S H
Chip management significantly improved in fine finishing
0,8 | 15°
α= 5° 7° 11°
CCMT09T3○○NLU
C D R S T V W

**NLU-W** — P M K N S H
High performance finishing breaker with wiper edge
Wiper
1,5 | 10°
α= 7° 11°
CCMT09T3○○NLUW
C D R S T V W

**N-FP** — P M K N S H
Provides good chip control in fine finishing
1,40 | 10°
α= 7°
CCMT09T3○○NFP
C D R S T V W

**N-FK** — P M K N S H
Finishing breaker with sharp edge and good chip control
1,1
α= 11°
TPMT1604○○NFK
C D R S T V W

### Light to Medium

**N-LB** — P M K N S H
Light-cutting breaker with sharp edge and good chip control
0,8 | 15°
α= 5° 7° 11°
CCMT09T3○○NLB
C D R S T V W

**N-SU** — P M K N S H
General-purpose breaker with sharp edge
1,45 | 8°
α= 5° 7° 11°
TPMT1103○○NSU
C D R S T V W

**N-US** — P M K N S H
Breaker for small diameter boring bars
1,95 | 10°
α= 11°
CPMH0903○○NSU
C D R S T V W

**N-UG** — P M K N S H — New
1st recommendation General-purpose breaker
0,2 | 1,6 | 5° | 15°
α= 5° 7° 11°
CCMT09T3○○NUG
C D R S T V W

**N-MU** — P M K N S H
Long lifetime breaker with low cutting resistance
0,35 | 0,1 | 1,8 | 4° | 20°
α= 7° 11°
TPMT1604○○NMU
C D R S T V W

**N-SF** — P M K N S H
Very reliable breaker with sharp edge
0,2 | 1,6 | 14°
α= 11°
TPMT1604○○NSF
C D R S T V W

## Positive Type — G Class with Ground Chipbreaker

### Finish to Light

**L/R-FW** — P M K N S H
Wide dimple breaker with sharp edge
0,90 | 15° (20°)
α= 5° 11°
TPMT1102○○L/RFW
C D R S T V W

**L/R-FX** — P M K N S H
Parallel breaker with sharp edge
0,9 | 15°
α= 5° 7° 11°
TPGT1103○○L/RFX
C D R S T V W

**L/R-FY** — P M K N S H
Wide breaker with sharp edge
1,5 | 15°
α= 5° 7° 11°
TPGT1103○○L/RFY
C D R S T V W

**L/R-FYS** — P M K N S H
Breaker for fine cutting with sharp edge
0,5 | 15°
α= 5° 7°
CCGT04X1○○L/RFYS
C D R S T V W


**L/R-W** — P M K N S H
Wide type finishing breaker
0,15 | 1,0 | 10°
α= 5° 11°
TPGR1103○○L/RW
C D R S T V W

**L/R-SD** — P M K N S H
Stepped parallel ground type
0,9
α= 7° 11°
TPGT1103○○L/RNSD
C D R S T V W


**L/R-SDW** — P M K N S H
Parallel ground type with high performance wiper edge
Wiper
0,9
α= 11°
TPGX1103○○L/RSDW
C D R S T V W

## Chipbreaker Application Range


M Class Finishing to Light Cutting




M Class Light to Medium Cutting




G Class with Ground Chipbreaker




Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

# Chipbreaker Application


Bumpy Breaker | Standard Breaker | Handed Breaker | SUMIBORON Break Master

## Positive Type — G Class

### Finish to Light

**N-FC*** — P M K N S H

Peripheral grinding 3D breaker with good chip control and sharp edge





α= 7° 11°

CCGT09T3○○NFC

C D R S T V W

**N-SI*** — P M K N S H

Sharper-edge breaker for a wide range of cutting applications from finishing to light cutting





α= 7°

CCGT09T3○○NSI

C D R S T V W

**N-SC*** — P M K N S H

Two step breaker for light cutting




α= 7°

TCGT1103○○NSC

C D R S T V W


* Remarks:
N-FC, N-SI and N-SC have minus tolerance indicated by "M" after the nose radius.
Example:
DCGT 11T302 **M** NSI AC520U

## Positive Type — Round Inserts

### Round

**N-RX** — P M K N S H

Round, bumpy type insert with excellent chip management





α= 7°

RCMX1606MON-RX

C D R S T V W

**N-RP** — P M K N S H

Standard breaker for copying




α= 7°

RCMX1606MON-RP


C D R S T V W

## Positive Type — For Al - Alloy Machining

### Finishing

**N-AG** — P M K N S H

Al breaker for mirror finish and anti-adhesion





α= 7°

CCGT09T3○○NAG

C D R S T V W

**N-AW** — P M K N S H

Finishing Al breaker with sharp edge





α= 7°

VCGT1604○○NAW

C D R S T V W

**R/L-AY** — P M K N S H

Al breaker for excellent machined surface quality





α= 5° 7° 11°

CCGT09T3○○_AY

C D R S T V W

## Chipbreaker Application Range




Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

Bumpy Breaker | Standard Breaker | Handed Breaker


## SUMIBORON Insert — CBN

### Finish to Light

**N-LV**

P M K N S H

Significantly improved chip control during hardened steel finishing




Break Master


α= 0° 7°

C D R S T V W

**N-FV**

P M K N S H

Significantly improved chip control during hardened steel finishing




Break Master

α= 0° 7°


C D R S T V W

### Carburized Layer Removal

**N-SV**

P M K N S H

Significantly improved chip management with carburized layer removal




Break Master

α= 0°

C D R S T V W


## SUMIDIA Insert — PCD

### Finish to Light

**N-LD**

P M K N S H

Ideal for finishing of Al by utilizing a special cutting edge shape




Break Master

α= 7° 11°


NF-CCMT0602○○NLD

C D R S T V W

**N-GD**

P M K N S H

Ideal for finishing to general machining of Al by utilizing a special cutting edge shape




Break Master

α= 7° 11°


NF-CCMT0602○○NGD

C D R S T V W

**L/R-DM**

P M K N S H

Perfect for highspeed finishing of aluminium alloy




Break Master


α= 7° 11°

NU-CCMT09T3○○L/R-DM


C D R S T V W

## Chipbreaker Application Range


SUMIBORON (Heavy Steel Machining) (IC up to Ø 12,7 mm)




SUMIBORON (Carburized Layer Removal) (IC up to Ø 12,7 mm)





SUMIDIA (For Aluminium Alloy Machining)





Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

80° Diamond Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN__ | L | IC | S | $D_1$ |
| 0903.. | 9,7 | 9,525 | 3,18 | 3,81 |
| 0904.. | 9,7 | 9,525 | 3,18 | 3,81 |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |


⇨ D12, D18
D41


⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# CNMG ●●●●●● ■-■■

● M-Class, Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Coated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Fine Finishing | NFB | CNMG 090304 NFB | 0,4 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 090308 NFB | 0,8 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 090404 NFB | 0,4 | | | | | | | ○ | ○ | | ○ | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 090408 NFB | 0,8 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 120402 NFB | 0,2 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | CNMG 120404 NFB | 0,4 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | CNMG 120408 NFB | 0,8 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Fine Finishing | NFA | CNMG 120402 NFA | 0,2 | | | | | | | | | | | | | | | | | | ● | ● | ● | | ● | | | | |
| | | CNMG 120404 NFA | 0,4 | | | | | | | | | | | | | | | | | | ● | ○ | ● | ● | ● | | | | |
| | | CNMG 120408 NFA | 0,8 | | | | | | | | | | | | | | | | | | ● | ○ | ● | ● | ● | | | | |
| Fine Finishing | NFL | CNMG 090308 NFL | 0,8 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 120404 NFL | 0,4 | | | ○ | | | | | ○ | | | | | ○ | ○ | ○ | | | ● | ○ | ● | | ● | | | | |
| | | CNMG 120408 NFL | 0,8 | | | ○ | | | | | | | | | | ○ | ○ | ○ | | | ● | ● | ● | ● | ● | | | | |
| Fine Finishing | NFE | CNMG 090304 NFE | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 090308 NFE | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 090404 NFE | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 090408 NFE | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 120402 NFE | 0,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | CNMG 120404 NFE | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | CNMG 120408 NFE | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | CNMG 120412 NFE | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Finishing | NLU | CNMG 090304 NLU | 0,4 | ○ | ○ | ○ | | | ○ | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 090308 NLU | 0,8 | ○ | ○ | ○ | | | ○ | | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | CNMG 120402 NLU | 0,2 | | | | | | ○ | | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | CNMG 120404 NLU | 0,4 | ● | ● | ● | ○ | | ○ | | ○ | | | | | | | | | | ● | ○ | ● | ○ | ○ | | | | |
| | | CNMG 120408 NLU | 0,8 | ● | ● | ● | ○ | | ○ | | ○ | | | | | | | | | | ● | ○ | ● | ○ | ○ | | | | |
| | | CNMG 120412 NLU | 1,2 | ● | ● | ● | ○ | | ○ | | | | | | | | | | | | ● | ○ | ● | | ○ | | | | |
| | NLU-W | CNMG 120404 NLU-W | 0,4 | ● | ● | ● | | ● | ○ | | ○ | | | | | | | | | | ● | ● | ● | | | | | | |
| | | CNMG 120408 NLU-W | 0,8 | ● | ● | ● | | ● | ○ | | ● | ● | | | | | | | | | ● | ● | ● | | ○ | | | | |
| | | CNMG 120412 NLU-W | 1,2 | ● | ● | ● | | | ○ | | | ● | | | | | | | | | ○ | ○ | | | ○ | | | | |
| Finishing | NEF | CNMG 090404 NEF | 0,4 | | | | | ○ | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | CNMG 090408 NEF | 0,8 | | | | | ○ | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | CNMG 120404 NEF | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | | ● | ● | |
| | | CNMG 120408 NEF | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | | ● | ● | |
| | | CNMG 120412 NEF | 1,2 | ○ | ● | ● | ○ | ○ | ● | ○ | | | | | | ● | ● | ● | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

**80° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN_ _ | L | IC | S | $D_1$ |
| 0903.. | 9,7 | 9,525 | 3,18 | 3,81 |
| 0904.. | 9,7 | 9,525 | 3,18 | 3,81 |
| 09T3.. | 9,7 | 9,525 | 3,97 | 3,81 |
| 1204.. | 12,9 | 12,7 | 4,46 | 5,16 |
| 1606.. | 16,1 | 15,875 | 6,35 | 6,35 |
| | | | | |



⇨ D12, D18
D41







⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC8025P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NSU | **CNMG 090304 NSU** | 0,4 | ○ | ● | ● | | ● | | | ● | | | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | **CNMG 090308 NSU** | 0,8 | ● | ○ | ○ | | ● | | | ● | | | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | **CNMG 09T304 NSU** | 0,4 | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 09T308 NSU** | 0,8 | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 090404 NSU** | 0,4 | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | **CNMG 090408 NSU** | 0,8 | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | **CNMG 090412 NSU** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | **CNMG 120402 NSU** | 0,2 | | | | | ● | ● | ● | | | | | ○ | ● | ● | ● | | | ○ | ○ | ○ | ○ | ○ | | | | | |
| | | **CNMG 120404 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | | | | ○ | ● | ● | ● | | | ● | ○ | ● | ● | ● | | | | | |
| | | **CNMG 120408 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | | | | ○ | ● | ● | ● | | | ● | ○ | ● | ● | ● | | | | | |
| | | **CNMG 120412 NSU** | 1,2 | ● | ● | ● | ○ | ● | ● | ● | ● | | | | | ● | ● | ● | | | ● | ○ | ● | ● | ● | | | | | |
| Finishing |  NSE / NSE-W | **CNMG 120404 NSE** | 0,4 | ● | ● | ● | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | | |
| | | **CNMG 120408 NSE** | 0,8 | ● | ● | ● | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | | |
| | | **CNMG 120412 NSE** | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 090404 NSE-W** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 090408 NSE-W** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120404 NSE-W** | 0,4 | ● | ○ | ○ | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | | |
| | | **CNMG 120408 NSE-W** | 0,8 | ● | ● | ● | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | | |
| | | **CNMG 120412 NSE-W** | 1,2 | ○ | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | |
| Finishing |  NSX | **CNMG 120404 NSX** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **CNMG 120408 NSX** | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | | |
| | | **CNMG 120412 NSX** | 1,2 | ● | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NGU / NGU-W | **CNMG 090304 NGU** | 0,4 | ○ | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNMG 090308 NGU** | 0,8 | ○ | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNMG 090404 NGU** | 0,4 | | | ○ | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | **CNMG 090408 NGU** | 0,8 | | | ○ | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | **CNMG 090412 NGU** | 1,2 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | **CNMG 120404 NGU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | ○ | | | | | |
| | | **CNMG 120408 NGU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | ○ | | | | | |
| | | **CNMG 120412 NGU** | 1,2 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | ○ | | | | | | | | | | |
| | | **CNMG 120416 NGU** | 1,6 | ○ | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNMG 160608 NGU** | 0,8 | ● | ● | ● | ○ | ● | ○ | ○ | ● | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNMG 160612 NGU** | 1,2 | ● | ● | ● | ● | ● | ○ | ○ | ● | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNMG 160616 NGU** | 1,6 | ● | ● | ● | ○ | | ○ | ○ | ● | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNMG 120408 NGU-W** | 0,8 | ● | ● | ● | | | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120412 NGU-W** | 1,2 | ● | ● | ● | | | ● | | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | **CNMG 160612 NGU-W** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan


80° Diamond Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN__ | L | IC | S | $D_1$ |
| 0903.. | 9,7 | 9,525 | 3,18 | 3,81 |
| 0904.. | 9,7 | 9,525 | 3,18 | 3,81 |
| 09T3.. | 9,7 | 9,525 | 3,97 | 3,81 |
| 1204.. | 12,9 | 12,7 | 4,46 | 5,16 |
| 1606.. | 16,1 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,3 | 19,05 | 6,35 | 7,94 |



⇨ D12, D18
D41







⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated PM | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated PM | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Medium Cut |  NGE | **CNMG 120404 NGE** | 0,4 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120408 NGE** | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120412 NGE** | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120416 NGE** | 1,6 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 160608 NGE** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 160612 NGE** | 1,2 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 160616 NGE** | 1,6 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 190612 NGE** | 1,2 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 190616 NGE** | 1,6 | ○ | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NUG | **CNMG 090304 NUG** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 090308 NUG** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 090404 NUG** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 090408 NUG** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 09T304 NUG** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 09T308 NUG** | 0,8 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120404 NUG** | 0,4 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120408 NUG** | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120412 NUG** | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 120416 NUG** | 1,6 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 160608 NUG** | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 160612 NUG** | 1,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 160616 NUG** | 1,6 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 190608 NUG** | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 190612 NUG** | 1,2 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 190616 NUG** | 1,6 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NEG | **CNMG 090408 NEG** | 0,8 | | | | | ○ | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 090412 NEG** | 1,2 | | | | | ○ | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 120404 NEG** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | ● | |
| | | **CNMG 120408 NEG** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | ● | ● | |
| | | **CNMG 120412 NEG** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ● | | | | | | | | ● | ● | |
| | | **CNMG 160608 NEG** | 0,8 | ○ | ● | ● | ○ | ○ | ○ | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 160612 NEG** | 1,2 | ○ | ● | ● | ○ | ● | ● | | ● | | | | | ○ | ○ | ● | | | | | | | | ● | ● | |
| | | **CNMG 160616 NEG** | 1,6 | ○ | ○ | | ○ | ○ | | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 190612 NEG** | 1,2 | ○ | ○ | ○ | ○ | ● | ● | | | | | | | ○ | ○ | ○ | | | | | | | | ○ | ○ | |
| | | **CNMG 190616 NEG** | 1,6 | ○ | ○ | ○ | ○ | ○ | ● | | ○ | | | | | ● | ● | ○ | | | | | | | | ○ | ○ | |
| Medium Cut |  NEX | **CNMG 120404 NEX** | 0,4 | | | | | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | | | | | | | | |
| | | **CNMG 120408 NEX** | 0,8 | | | | | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | | | | | | | | |
| | | **CNMG 120412 NEX** | 1,2 | | | | | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | | | |
| | | **CNMG 160612 NEX** | 1,2 | | | | | | | | | | | | | ○ | ○ | ● | | | | | | | | | | |
| | | **CNMG 190612 NEX** | 1,2 | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

80° Diamond Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN_ _ | L | IC | S | $D_1$ |
| 1204.. | 12,9 | 12,7 | 4,46 | 5,16 |
| 1606.. | 16,1 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,3 | 19,05 | 6,35 | 7,94 |
| 2509.. | 25,8 | 25,4 | 9,52 | 9,2 |
| | | | | |
| | | | | |





⇨ D12, D18
D41

⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T150Z | **T250Z** | T300Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Medium Cut |  NUP | **CNMG 120404 NUP** | 0,4 | | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | | | | | ○ | | | |
| | | **CNMG 120408 NUP** | 0,8 | | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | | | | | ○ | | | |
| | | **CNMG 120412 NUP** | 1,2 | | ● | ● | ● | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | ○ | | | |
| | | **CNMG 160612 NUP** | 1,2 | | | | ● | ● | | | ● | | | | | | | | | | | | | | | | | |
| | | **CNMG 190612 NUP** | 1,2 | | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| Medium Cut |  NEM | **CNMG 120408 NEM** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 120412 NEM** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 120416 NEM** | 1,6 | ○ | ○ | ● | ○ | ○ | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 160608 NEM** | 0,8 | ○ | ○ | ● | ○ | ○ | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 160612 NEM** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 160616 NEM** | 1,6 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 190612 NEM** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 190616 NEM** | 1,6 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 190624 NEM** | 2,4 | ○ | ○ | ○ | ○ | ○ | | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 250924 NEM** | 2,4 | ○ | ○ | | ○ | | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | |


● = Euro stock
○ = Stock item in Japan

80° Diamond Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN__ | L | IC | S | $D_1$ |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,16 |
| 1606.. | 16,1 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,3 | 19,05 | 6,35 | 7,94 |
| 2509.. | 25,8 | 25,4 | 9,52 | 9,2 |
| | | | | |
| | | | | |






⇨ D12, D18 D41


⇨ E8

P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

# CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  NMU | CNMG 120408 NMU | 0,8 | ● | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | ○ | | | | | | ○ | | | |
| | | CNMG 120412 NMU | 1,2 | ● | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | ○ | | | | | | | | | |
| | | CNMG 120416 NMU | 1,6 | ● | ● | ● | ○ | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | |
| | | CNMG 160608 NMU | 0,8 | ● | ● | ● | ● | ● | ● | | ● | | | | | ● | ○ | ○ | | | | | | | | | | | |
| | | CNMG 160612 NMU | 1,2 | ● | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | | | | | | | | | | |
| | | CNMG 160616 NMU | 1,6 | ● | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | | | | | | | | | | |
| | | CNMG 190608 NMU | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 190612 NMU | 1,2 | ● | ● | ● | ● | ● | ● | | ● | | | | | ○ | ○ | ● | | | | | | | | | | | |
| | | CNMG 190616 NMU | 1,6 | ● | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | | | | | | | | | | |
| | | CNMG 190624 NMU | 2,4 | ○ | ○ | ○ | ○ | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | CNMG 250924 NMU | 2,4 | ○ | ○ | ○ | ● | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| Roughing |  NME | CNMG 120408 NME | 0,8 | ● | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 120412 NME | 1,2 | ● | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 120416 NME | 1,6 | ● | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 160608 NME | 0,8 | ○ | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 160612 NME | 1,2 | ● | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 160616 NME | 1,6 | ● | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 190612 NME | 1,2 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 190616 NME | 1,6 | ● | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 190624 NME | 2,4 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | CNMG 250924 NME | 2,4 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| Roughing |  NUX | CNMG 090304 NUX | 0,4 | | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 090308 NUX | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 120404 NUX | 0,4 | ○ | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 120408 NUX | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 120412 NUX | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 120416 NUX | 1,6 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 160608 NUX | 0,8 | ● | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 160612 NUX | 1,2 | ● | ● | ● | ● | | | | ● | | | ● | | | | | | | | | | | | | | | |
| | | CNMG 160616 NUX | 1,6 | ● | ● | ● | ○ | | | | ● | | | ● | | | | | | | | | | | | | | | |
| | | CNMG 190608 NUX | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 190612 NUX | 1,2 | ○ | ○ | ○ | ○ | | | | ● | | | | | | | | | | | | | | | | | | |
| | | CNMG 190616 NUX | 1,6 | ○ | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NMX | CNMG 120408 NMX | 0,8 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 120412 NMX | 1,2 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 120416 NMX | 1,6 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 160608 NMX | 0,8 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 160612 NMX | 1,2 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 160616 NMX | 1,6 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 190612 NMX | 1,2 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | CNMG 190616 NMX | 1,6 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |



● = Euro stock
○ = Stock item in Japan


# C DIAMOND TYPE
INSERTS FOR TURNING

**80° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN_ _ | L | IC | S | $D_1$ |
| 0904.. | 9,7 | 9,525 | 3,18 | 3,81 |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,16 |
| 1606.. | 16,1 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,3 | 19,05 | 6,35 | 7,94 |
| | | | | |
| | | | | |






- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  NGZ | **CNMG 090408 NGZ** | 0,8 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | **CNMG 090412 NGZ** | 1,2 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | **CNMG 120404 NGZ** | 0,4 | | | | | | | | | ● | ● | ○ | | | | | | | | | | | | | | |
| | | **CNMG 120408 NGZ** | 0,8 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | |
| | | **CNMG 120412 NGZ** | 1,2 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | |
| | | **CNMG 120416 NGZ** | 1,6 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | |
| | | **CNMG 160608 NGZ** | 0,8 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **CNMG 160612 NGZ** | 1,2 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | **CNMG 160616 NGZ** | 1,6 | | | | | | | | | ○ | ● | ○ | | | | | | | | | | | | | | |
| | | **CNMG 190612 NGZ** | 1,2 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | **CNMG 190616 NGZ** | 1,6 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| Roughing |  NUZ | **CNMG 120404 NUZ** | 0,4 | | | ○ | ○ | | | | | ● | ○ | ○ | | | | | | | | | | | | | | |
| | | **CNMG 120408 NUZ** | 0,8 | | ○ | ○ | ○ | | | | | ● | ● | ● | | ○ | ○ | ○ | | | | | | | | ○ | | |
| | | **CNMG 120412 NUZ** | 1,2 | | | ○ | ○ | | | | | ● | ● | ● | | ○ | ○ | ○ | | | | | | | | | | |
| | | **CNMG 120416 NUZ** | 1,6 | | | ○ | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | |
| | | **CNMG 160608 NUZ** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 160612 NUZ** | 1,2 | | | ○ | ○ | | | | | ● | ● | ● | | | | | | | | | | | | | | |
| | | **CNMG 160616 NUZ** | 1,6 | | | ○ | ○ | | | | | ● | ● | ● | | | | | | | | | | | | | | |
| | | **CNMG 190608 NUZ** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMG 190612 NUZ** | 1,2 | | | ○ | ○ | | | | | ○ | ○ | ● | | | | | | | | | | | | | | |
| | | **CNMG 190616 NUZ** | 1,6 | | | ○ | ○ | | | | | ○ | ● | ● | | | | | | | | | | | | | | |


● = Euro stock
○ = Stock item in Japan

80° Diamond Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN__ | L | IC | S | $D_1$ |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,16 |
| 1606.. | 16,1 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,3 | 19,05 | 6,35 | 7,94 |
| 2507.. | 25,8 | 25,4 | 7,94 | 9,2 |
| 2509.. | 25,8 | 25,4 | 9,52 | 9,2 |
| | | | | |








- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# CNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Heavy Roughing |  NMP | **CNMM 120408 NMP** | 0,8 | ● | ● | ● | ● | | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 120412 NMP** | 1,2 | ● | ● | ● | ● | | ● | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 120416 NMP** | 1,6 | ○ | ● | ● | ● | | ● | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 160608 NMP** | 0,8 | | | ● | ● | | ○ | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 160612 NMP** | 1,2 | ● | ● | ● | ● | | ○ | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 160616 NMP** | 1,6 | ● | ● | ● | ● | | ○ | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 160624 NMP** | 2,4 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190608 NMP** | 0,8 | | | ● | ● | | ○ | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 190612 NMP** | 1,2 | ○ | ● | ● | ● | | ● | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 190616 NMP** | 1,6 | ● | ● | ● | ● | | ● | ○ | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 190624 NMP** | 2,4 | ○ | ● | ● | ● | | ○ | ○ | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | | | |
| | | **CNMM 250724 NMP** | 2,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 250924 NMP** | 2,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NMH | **CNMM 160612 NMH** | 1,2 | ● | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 160616 NMH** | 1,6 | ● | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190612 NMH** | 1,2 | ● | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190616 NMH** | 1,6 | ● | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190624 NMH** | 2,4 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 250924 NMH** | 2,4 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHG | **CNMM 120408 NHG** | 0,8 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 120412 NHG** | 1,2 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 120416 NHG** | 1,6 | | | ○ | | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 160608 NHG** | 0,8 | ● | | | | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 160612 NHG** | 1,2 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 160616 NHG** | 1,6 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 160624 NHG** | 2,4 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190612 NHG** | 1,2 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190616 NHG** | 1,6 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190624 NHG** | 2,4 | ● | ● | ● | ● | | | | ○ | | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHP | **CNMM 120408 NHP** | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 120412 NHP** | 1,2 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 120416 NHP** | 1,6 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 160608 NHP** | 0,8 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 160612 NHP** | 1,2 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 160616 NHP** | 1,6 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190608 NHP** | 0,8 | | | ○ | ● | | | | ○ | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190612 NHP** | 1,2 | | | ● | ● | | | | ○ | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190616 NHP** | 1,6 | | | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190624 NHP** | 2,4 | | ● | ● | ● | | | | ○ | | | | | | | | | | | | | | | | | | | |

Feed rate (mm/rev)

● = Euro stock
○ = Stock item in Japan


# C DIAMOND TYPE
INSERTS FOR TURNING

**80° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN_ _ | L | IC | S | $D_1$ |
| 1906.. | 19,3 | 19,05 | 6,35 | 7,94 |
| 2509.. | 25,8 | 25,4 | 9,52 | 9,2 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |




⇨ D12, D18


⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## CNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Heavy Roughing |  | **CNMM 190616 NHU** | 1,6 | | | | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **CNMM 190624 NHU** | 2,4 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 250924 NHU** | 2,4 | | | | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **CNMM 250924 NHW** | 2,4 | | | | | | | | ● | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  | **CNMM 190616 NHF** | 1,6 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 190624 NHF** | 2,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 250924 NHF** | 2,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNMM 250932 NHF** | 3,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |


● = Euro stock
○ = Stock item in Japan

80° Diamond Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN__ | L | IC | S | $D_1$ |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,16 |
| 1606.. | 16,1 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,3 | 19,05 | 6,35 | 7,94 |
| | | | | |
| | | | | |
| | | | | |




⇨ D12, D18


⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel





## CNMA / CNGA / CNMX

● Flat and One Side Handed Inserts

| Application | Shape | ISO Cat. No. | RE | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Roughing |  | **CNMA 120404** | 0,4 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | ● | | | | |
| | | **CNMA 120408** | 0,8 | | | | | | | | | ● | ● | ● | | ○ | ○ | ○ | | | | | | | ● | | | | |
| | | **CNMA 120412** | 1,2 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | | |
| | | **CNMA 120416** | 1,6 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | | |
| | | **CNMA 160608** | 0,8 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **CNMA 160612** | 1,2 | | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | |
| | | **CNMA 160616** | 1,6 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | | |
| | | **CNMA 190612** | 1,2 | | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | |
| | | **CNMA 190616** | 1,6 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | |
| Medium Cut |  | **CNGA 120402** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **CNGA 120404** | 0,4 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **CNGA 120408** | 0,8 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| Heavy Roughing |  | **CNMX 120408 L** | 0,8 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| |  | **CNMX 120408 R** | 0,8 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |

## CNGG ●●●●●● ■-■■


● G-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |   NSU | **CNGG 120402 NSU** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **CNGG 120404 NSU** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **CNGG 120408 NSU** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | | ○ | ○ | | | | |
| Finishing |   NGH | **CNGG 120402 NGH** | 0,2 | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | | | |
| | | **CNGG 120404 NGH** | 0,4 | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | | | |
| | | **CNGG 120408 NGH** | 0,8 | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | | | |
| Finishing |   NEF | **CNGG 120402 NEF** | 0,2 | | | | | | | | ○ | | | | | | ○ | ○ | | | | | | | | ○ | | | |
| | | **CNGG 120404 NEF** | 0,4 | | | | | | | | ○ | | | | | | ○ | ○ | | | | | | | | ○ | | | |
| | | **CNGG 120408 NEF** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| For Aluminum |   L/RAX | **CNGG 120402 LAX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **CNGG 120404 LAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **CNGG 120408 LAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **CNGG 120402 RAX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **CNGG 120404 RAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **CNGG 120408 RAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Stock item in Japan

# D DIAMOND TYPE
INSERTS FOR TURNING

**55° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN_ _ | L | IC | S | $D_1$ |
| 1104.. | 11,6 | 9,525 | 4,76 | 3,81 |
| 1504.. | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,5 | 12,7 | 6,35 | 5,16 |
| | | | | |
| | | | | |
| | | | | |








⇨ D13, D19
D41

⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## DNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Fine Finishing |  NFB | **DNMG 110404 NFB** | 0,4 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **DNMG 110408 NFB** | 0,8 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **DNMG 150404 NFB** | 0,4 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150408 NFB** | 0,8 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150604 NFB** | 0,4 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150608 NFB** | 0,8 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Fine Finishing |  NFA | **DNMG 150404 NFA** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150408 NFA** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150604 NFA** | 0,4 | | | | | | | | | | | | | | | | | | ● | ○ | | ● | ● | | | | |
| | | **DNMG 150608 NFA** | 0,8 | | | | | | | | | | | | | | | | | | ● | | | ● | ● | | | | |
| Fine Finishing |  NFL | **DNMG 150404 NFL** | 0,4 | | | | | | | | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150408 NFL** | 0,8 | | | ○ | | | | | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150412 NFL** | 1,2 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150604 NFL** | 0,4 | | | | | | | | | | | | | | | | | | ● | | ● | | | | | | |
| | | **DNMG 150608 NFL** | 0,8 | | | | | | | | | | | | | | | | | | ● | | ● | | | | | | |
| Fine Finishing |  NFE | **DNMG 110404 NFE** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **DNMG 110408 NFE** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **DNMG 110412 NFE** | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **DNMG 150402 NFE** | 0,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150404 NFE** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150408 NFE** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150412 NFE** | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150602 NFE** | 0,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150604 NFE** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150608 NFE** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150612 NFE** | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Finishing |  NLU | **DNMG 110404 NLU** | 0,4 | ● | ● | ● | | | ○ | | ○ | | | | | | | | | | ● | | | | ○ | | | | |
| | | **DNMG 110408 NLU** | 0,8 | ● | ○ | ○ | | | ○ | | ○ | | | | | | | | | | ● | | | | ○ | | | | |
| | | **DNMG 150402 NLU** | 0,2 | ○ | ○ | ○ | | | ○ | | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150404 NLU** | 0,4 | ○ | ○ | ○ | ○ | | ○ | | ○ | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150408 NLU** | 0,8 | ○ | ○ | ○ | ○ | | ○ | | ○ | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150412 NLU** | 1,2 | ○ | ○ | ○ | ○ | | ○ | | ○ | | | | | | | | | ○ | ○ | ○ | ○ | | ○ | | | | |
| | | **DNMG 150604 NLU** | 0,4 | ● | ● | ● | | | | | | | | | | | | | | | ● | | | | | | | | |
| | | **DNMG 150608 NLU** | 0,8 | ● | ● | ● | | | | | | | | | | | | | | | ● | | | | | | | | |
| | | **DNMG 150612 NLU** | 1,2 | ● | ● | ● | | | | | | | | | | | | | | | ● | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

**55° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN__ | L | IC | S | $D_1$ |
| 1104.. | 11,6 | 9,525 | 4,76 | 3,81 |
| 1504.. | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,5 | 12,7 | 6,35 | 5,16 |
| | | | | |
| | | | | |
| | | | | |








⇨ D13, D19 D41 ⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## DNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Coated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NEF | **DNMG 110404 NEF** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 110408 NEF** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 110412 NEF** | 1,2 | ○ | ○ | ○ | ○ | ○ | ● | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 150404 NEF** | 0,4 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | | | | | ○ | ○ | ○ | | | | | | | | ● | ● | | |
| | | **DNMG 150408 NEF** | 0,8 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | | | | | ○ | ○ | ○ | | | | | | | | | ● | | |
| | | **DNMG 150412 NEF** | 1,2 | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 150604 NEF** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | ● | ● | | |
| | | **DNMG 150608 NEF** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | ● | ● | | |
| | | **DNMG 150612 NEF** | 1,2 | ○ | ● | ● | ○ | ● | ● | ○ | | | | | | ● | ● | ● | | | | | | | | | | | |
| Finishing |  NSU | **DNMG 110404 NSU** | 0,4 | ● | ● | ● | ○ | ● | ○ | ○ | ● | | | | | | ● | ● | | | | | | | | | | | |
| | | **DNMG 110408 NSU** | 0,8 | ● | ● | ● | ○ | ● | ○ | ○ | ● | | | | | | ● | ● | | | | | | | | | | | |
| | | **DNMG 110412 NSU** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150402 NSU** | 0,2 | | | | | | ○ | | ○ | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150404 NSU** | 0,4 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150408 NSU** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | | | | | |
| | | **DNMG 150412 NSU** | 1,2 | ○ | ○ | ○ | | | ○ | | ○ | | | | | | ○ | ○ | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **DNMG 150604 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | ● | ● | | | ● | ○ | | ● | ● | | | | |
| | | **DNMG 150608 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | ● | ● | | | ● | ○ | | ● | ● | | | | |
| | | **DNMG 150612 NSU** | 1,2 | ● | ● | ● | ● | | | | ● | | | | | | ● | ● | | | ● | | | ● | ● | | | | |
| Finishing |  NSE | **DNMG 110408 NSE** | 0,8 | ● | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150404 NSE** | 0,4 | ● | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **DNMG 150408 NSE** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **DNMG 150412 NSE** | 1,2 | ● | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **DNMG 150604 NSE** | 0,4 | ● | ● | ● | | | | | | | | | | | | | | | | | | ○ | | | | | |
| | | **DNMG 150608 NSE** | 0,8 | ● | ● | ● | | | | | | | | | | | | | | | | | | ○ | | | | | |
| | | **DNMG 150612 NSE** | 1,2 | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Finishing |  NSX | **DNMG 150404 NSX** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | |
| | | **DNMG 150408 NSX** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **DNMG 150412 NSX** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150604 NSX** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **DNMG 150608 NSX** | 0,8 | ● | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| Medium Cut |  NGU | **DNMG 110404 NGU** | 0,4 | ● | ● | ● | ○ | ● | ● | ○ | ● | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 110408 NGU** | 0,8 | ● | ● | ● | ● | ● | ● | ○ | ● | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 110412 NGU** | 1,2 | ● | ● | ● | ○ | ● | | | ● | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150404 NGU** | 0,4 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | ○ | | | | |
| | | **DNMG 150408 NGU** | 0,8 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | ○ | | | | |
| | | **DNMG 150412 NGU** | 1,2 | ○ | ○ | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | ○ | | | | |
| | | **DNMG 150416 NGU** | 1,6 | | | ○ | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150604 NGU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150608 NGU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150612 NGU** | 1,2 | ● | ● | ● | ○ | ● | ● | ○ | ● | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150616 NGU** | 1,6 | | | ○ | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# D DIAMOND TYPE
## INSERTS FOR TURNING

**55° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN_ _ | L | IC | S | $D_1$ |
| 1104.. | 11,6 | 9,525 | 4,76 | 3,81 |
| 1504.. | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,5 | 12,7 | 6,35 | 5,16 |
| | | | | |
| | | | | |
| | | | | |







⇨ D13, D19 D41 ⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# DNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated M | Carbide Coated M | Carbide Coated P/M | Carbide Coated K | Carbide Coated K | Carbide Coated K | Carbide Coated H | Carbide Coated S | Carbide Coated S | Carbide Coated S | Carbide Coated P/M | Carbide Coated P/M | Cermet Coated P | Cermet Coated P | Cermet Coated P | Cermet Uncoated P | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | AC8020P | AC825P | AC835P | AC6020M | AC6030M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Medium Cut |  NGE | **DNMG 110408 NGE** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 110412 NGE** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150404 NGE** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150408 NGE** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150412 NGE** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150416 NGE** | 1,6 | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150604 NGE** | 0,4 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150608 NGE** | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150612 NGE** | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150616 NGE** | 1,6 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NUG | **DNMG 110404 NUG** | 0,4 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 110408 NUG** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150404 NUG** | 0,4 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150408 NUG** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150412 NUG** | 1,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150604 NUG** | 0,4 | ● | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150608 NUG** | 0,8 | ● | | ● | ○ | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150612 NUG** | 1,2 | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150616 NUG** | 1,6 | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NEG | **DNMG 110408 NEG** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 110412 NEG** | 1,2 | ○ | ● | ● | ○ | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150404 NEG** | 0,4 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | ○ | ○ | ○ | | | | | | | | | ○ | |
| | | **DNMG 150408 NEG** | 0,8 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | | | | ○ | ○ | ○ | | | | | | | | ● | | |
| | | **DNMG 150412 NEG** | 1,2 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | | | | ○ | ○ | ○ | | | | | | | | ● | | |
| | | **DNMG 150604 NEG** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | ○ | | | | ○ | ○ | ○ | | | | | | | | ○ | | |
| | | **DNMG 150608 NEG** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | ● | ● | ● | | | | | | | | ● | ● | |
| | | **DNMG 150612 NEG** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | ● | ● | ● | | | | | | | | ● | ● | |
| Medium Cut |  NEX | **DNMG 110404 NEX** | 0,4 | | | | | | ● | | ● | | | | | ● | ● | | | | | | | | | | |
| | | **DNMG 110408 NEX** | 0,8 | | | | | | ● | | ● | | | | | ● | ● | | | | | | | | | | |
| | | **DNMG 150404 NEX** | 0,4 | | | | | ○ | ○ | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150408 NEX** | 0,8 | | | | | ○ | ○ | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150412 NEX** | 1,2 | | | | | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150604 NEX** | 0,4 | | | | | ● | ● | ● | ● | | | | | ● | ● | | | | | | | | | | |
| | | **DNMG 150608 NEX** | 0,8 | | | | | ● | ● | ● | ● | | | | | ● | ● | | | | | | | | | | |
| | | **DNMG 150612 NEX** | 1,2 | | | | | ● | ○ | ○ | ● | | | | | ● | ● | | | | | | | | | | |


● = Euro stock
○ = Stock item in Japan

# D DIAMOND TYPE
INSERTS FOR TURNING

**55° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN__ | L | IC | S | $D_1$ |
| 1504.. | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,5 | 12,7 | 6,35 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |








⇨ D13, D19 D41 ⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## DNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Medium Cut |   | **DNMG 150404 NUP** | 0,4 | | | | | | ○ | ○ | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 150408 NUP** | 0,8 | | | | | | ○ | ○ | ○ | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | **DNMG 150412 NUP** | 1,2 | | | | | | ○ | | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 150604 NUP** | 0,4 | | ● | ● | ● | ● | ● | ● | ● | | | | | | ● | ● | | | | | | | | | | | |
| | | **DNMG 150608 NUP** | 0,8 | | ● | ● | ● | ● | ● | ● | ● | | | | | | ● | ● | | | | | | | | | | | |
| | | **DNMG 150612 NUP** | 1,2 | | | | ● | ● | | | ● | | | | | | ● | ● | | | | | | | | | | | |
| Medium Cut |   | **DNMG 150404 LUM** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **DNMG 150408 LUM** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **DNMG 150404 RUM** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **DNMG 150408 RUM** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| Roughing |   | **DNMG 150404 NMU** | 0,4 | | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150408 NMU** | 0,8 | ○ | ○ | ○ | ○ | | ○ | | ○ | | | | | ● | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 150412 NMU** | 1,2 | ○ | ○ | ○ | ○ | | ○ | | | | | | | ● | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 150416 NMU** | 1,6 | | | ○ | ○ | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **DNMG 150608 NMU** | 0,8 | ● | ● | ● | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150612 NMU** | 1,2 | ● | ● | ● | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | |
| | | **DNMG 150616 NMU** | 1,6 | ● | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| Roughing |   | **DNMG 150408 NEM** | 0,8 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150412 NEM** | 1,2 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150416 NEM** | 1,6 | | | ○ | ○ | ○ | ○ | ○ | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150608 NEM** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150612 NEM** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DNMG 150616 NEM** | 1,6 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |   | **DNMG 150408 NME** | 0,8 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150412 NME** | 1,2 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150416 NME** | 1,6 | | | ○ | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150608 NME** | 0,8 | ● | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150612 NME** | 1,2 | ● | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMG 150616 NME** | 1,6 | ● | ● | ● | ○ | | | | | ○ | ● | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# D DIAMOND TYPE
INSERTS FOR TURNING

**55° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN_ _ | L | IC | S | $D_1$ |
| 1104.. | 11,6 | 9,525 | 4,76 | 3,81 |
| 1504.. | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,5 | 12,7 | 6,35 | 5,16 |
| | | | | |
| | | | | |
| | | | | |








⇨ D13, D19
D41

⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## DNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | AC8020P | AC8025P | AC8035P | M | AC6030M | AC6040M | PM | AC630M | K | AC4010K | AC4015K | AC420K | H | AC503U | S | AC5005S | AC5015S | AC5025S | PM | AC1030U | AC530U | Cermet Coated P | T1500Z | T2500Z | T3000Z | Uncoated P | T1000A | T1500A | Carbide Uncoated K | G10E | S | EH510 | EH520 | N | H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Roughing |  L/RHM | DNMG 150404 LHM | 0,4 | | | ○ | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150408 LHM | 0,8 | | | ○ | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150404 RHM | 0,4 | ○ | ○ | ○ | ○ | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150408 RHM | 0,8 | ○ | ○ | ○ | ○ | | ○ | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NUX | DNMG 110408 NUX | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150404 NUX | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150408 NUX | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150412 NUX | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150604 NUX | 0,4 | ○ | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150608 NUX | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150612 NUX | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150616 NUX | 1,6 | | | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NMX | DNMG 150408 NMX | 0,8 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150412 NMX | 1,2 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150608 NMX | 0,8 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150612 NMX | 1,2 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NGZ | DNMG 110408 NGZ | 0,8 | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 110412 NGZ | 1,2 | | | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150404 NGZ | 0,4 | | | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150408 NGZ | 0,8 | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150412 NGZ | 1,2 | | | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150608 NGZ | 0,8 | | | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150612 NGZ | 1,2 | | | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NUZ | DNMG 150404 NUZ | 0,4 | | | ○ | | | | | | | | ○ | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | DNMG 150408 NUZ | 0,8 | | | ○ | ○ | | | | | | | ○ | ○ | ○ | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | DNMG 150412 NUZ | 1,2 | | | ○ | ○ | | | | | | | ○ | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | DNMG 150608 NUZ | 0,8 | | | ○ | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | DNMG 150612 NUZ | 1,2 | | | ○ | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

**55° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN__ | L | IC | S | $D_1$ |
| 1504.. | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,5 | 12,7 | 6,35 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |






⇨ D13, D19 ⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## DNMM ●●●●●● ■-■■


● M-Class One Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Heavy Roughing |  NMP | **DNMM 150404 NMP** | 0,4 | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150408 NMP** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150412 NMP** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150416 NMP** | 1,6 | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150604 NMP** | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150608 NMP** | 0,8 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **DNMM 150612 NMP** | 1,2 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **DNMM 150616 NMP** | 1,6 | ○ | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHG | **DNMM 150608 NHG** | 0,8 | ● | | | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **DNMM 150612 NHG** | 1,2 | ● | ● | ● | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **DNMM 150616 NHG** | 1,6 | ● | ● | ● | | | | | ● | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHP | **DNMM 150404 NHP** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150408 NHP** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150412 NHP** | 1,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150416 NHP** | 1,6 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150604 NHP** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150608 NHP** | 0,8 | | | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150612 NHP** | 1,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMM 150616 NHP** | 1,6 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# D DIAMOND TYPE
INSERTS FOR TURNING

**55° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN_ _ | L | IC | S | $D_1$ |
| 1104.. | 11,6 | 9,525 | 4,76 | 3,81 |
| 1504.. | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,5 | 12,7 | 6,35 | 5,16 |
| | | | | |
| | | | | |
| | | | | |





⇨ D13, D19 ⇨ E9


- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# DNMA / DNMX

Flat Inserts and One Side Handed Inserts

●M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | Carbide Coated P **AC8020P** | Carbide Coated P AC8025P | Carbide Coated P AC8035P | Carbide Coated M AC6020M | Carbide Coated M AC6030M | Carbide Coated M AC6040M | Carbide Coated P/M AC630M | Carbide Coated K AC4010K | Carbide Coated K AC4015K | Carbide Coated K AC420K | Carbide Coated H AC503U | Carbide Coated S **AC5005S** | Carbide Coated S AC5015S | Carbide Coated S AC5025S | Carbide Coated P/M AC1030U | Carbide Coated P/M AC530U | Cermet Coated P T1500Z | Cermet Coated P **T2500Z** | Cermet Coated P T3000Z | Cermet Coated P T1000A | Cermet Uncoated P T1500A | Carbide Uncoated K G10E | Carbide Uncoated S EH510 | Carbide Uncoated S EH520 | Carbide Uncoated N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Roughing |  | **DNMA 150404** | 0,4 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMA 150408** | 0,8 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMA 150412** | 1,2 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNMA 150608** | 0,8 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | | |
| | | **DNMA 150612** | 1,2 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | |
| |  | **DNMX 150608 L** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| |  | **DNMX 150608 R** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Finishing |   | **DNMX 110404 NSE-W** | 0,4 | ● | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMX 110408 NSE-W** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMX 110412 NSE-W** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMX 150404 NSE-W** | 0,4 | ○ | ○ | ○ | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | |
| | | **DNMX 150408 NSE-W** | 0,8 | ○ | ○ | ○ | | | | | | | | | | | | | | | | ○ | ○ | | | | | | |
| | | **DNMX 150412 NSE-W** | 1,2 | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMX 150604 NSE-W** | 0,4 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMX 150608 NSE-W** | 0,8 | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNMX 150612 NSE-W** | 1,2 | ● | | | | | | | | | | | | | | | | | | | | | | | | | |








(Note) The cutting point position of the SDW type does not follow the ISO standard.
Wenn using on a boring holder with a 93° approach angle, there is a need to revise the cutting point position (refer to right table) relative to using standard inserts.


| r | Compensation (mm) X (Diam. change) | Z |
|---|---|---|
| 0,4 | -0,14 (Ø: -0,28) | -0,02 |
| 0,8 | -0,14 (Ø: -0,28) | -0,02 |
| 1,2 | -0,1 (Ø: -0,2) | -0,03 |

● = Euro stock
○ = Stock item in Japan

**55° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN__ | L | IC | S | $D_1$ |
| 1104.. | 11,6 | 9,525 | 4,76 | 3,81 |
| 1504.. | 15,5 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |




⇨ D13, D19 ⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel








## DNGA ●●●●●●

● G-Class One Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | AC8020P | AC8025P | AC8035P | M AC6020M | AC6030M | AC6040M | P/M AC630M | K AC4010K | AC4015K | AC420K | H AC503U | S AC5005S | AC5015S | AC5025S | P/M AC1030U | AC530U | Cermet Coated P T1500Z | T2500Z | T3000Z | Cermet Uncoated P T1000A | T1500A | Carbide Uncoated K G10E | S EH510 | EH520 | N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Medium Cut |  | **DNGA 150402** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **DNGA 150404** | 0,4 | | | | | | | | | | | | ○ | | ○ | ○ | | | | | | | | | | | |
| | | **DNGA 150408** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | ○ | | | | | |

## DNGG ●●●●●● ■-■■


● G-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | AC8020P | AC8025P | AC8035P | M AC6020M | AC6030M | AC6040M | P/M AC630M | K AC4010K | AC4015K | AC420K | H AC503U | S AC5005S | AC5015S | AC5025S | P/M AC1030U | AC530U | Cermet Coated P T1500Z | T2500Z | T3000Z | Cermet Uncoated P T1000A | T1500A | Carbide Uncoated K G10E | S EH510 | EH520 | N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  NEF | **DNGG 150404 NEF** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | ○ | |
| | | **DNGG 150408 NEF** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| Finishing |  NSU | **DNGG 150402 NSU** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | | ○ | ○ | | | | |
| | | **DNGG 150404 NSU** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | | ○ | ○ | | | | |
| | | **DNGG 150408 NSU** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | | ○ | ○ | | | | |
| Medium Cut |  L/RUM | **DNGG 110404 LUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DNGG 110408 LUM** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DNGG 150404 LUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DNGG 150408 LUM** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DNGG 110404 RUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | |
| | | **DNGG 110408 RUM** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DNGG 150404 RUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DNGG 150408 RUM** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| Finishing |  NGH | **DNGG 150402 NGH** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **DNGG 150404 NGH** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **DNGG 150408 NGH** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| For Aluminum |  L/RAX | **DNGG 150402 LAX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **DNGG 150404 LAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **DNGG 150408 LAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **DNGG 150402 RAX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **DNGG 150404 RAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **DNGG 150408 RAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Stock item in Japan

# S SQUARE TYPE
INSERTS FOR TURNING

**90° Square Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 1204.. | 12,7 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |








➪ D14, D20~21
D41


➪ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## SNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | | Cermet Uncoated P | Carbide Uncoated K | | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC515S | AC525S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Fine Finishing |  NFB | **SNMG 120404 NFB** | 0,4 | | | | | | | ❍ | | | | | | | | | | | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | |
| | | **SNMG 120408 NFB** | 0,8 | | | | | | | ❍ | | | | | | | | | | | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | |
| Fine Finishing |  NFL | **SNMG 120408 NFL** | 0,8 | | | ❍ | | | | | | | | | | | | | | | ❍ | ❍ | ❍ | | ❍ | | | | | |
| Fine Finishing |  NFE | **SNMG 120404 NFE** | 0,4 | ❍ | ❍ | ❍ | ❍ | | ❍ | ❍ | | | | | | | | | | | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | |
| | | **SNMG 120408 NFE** | 0,8 | ❍ | ❍ | ❍ | ❍ | | ❍ | ❍ | | | | | | | | | | | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | |
| | | **SNMG 120412 NFE** | 1,2 | ❍ | ❍ | ❍ | ❍ | | ❍ | ❍ | | | | | | | | | | | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | |
| Finishing |  NLU | **SNMG 120408 NLU** | 0,8 | ❍ | ❍ | ❍ | | | ❍ | | ❍ | | | | | | | | | | ❍ | ❍ | ❍ | | ❍ | | | | | |
| | | **SNMG 120412 NLU** | 1,2 | ❍ | ● | ● | | | ❍ | | ❍ | | | | | | | | | | ❍ | ❍ | ❍ | | | | | | | |
| Finishing |  NSU | **SNMG 120408 NSU** | 0,8 | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | | ● | ● | ● | | | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | |
| | | **SNMG 120412 NSU** | 1,2 | | | | | | | | | | | | | | | ● | | | | | | | | | | | | |
| Finishing |  NSE | **SNMG 120408 NSE** | 0,8 | ❍ | ❍ | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 120412 NSE** | 1,2 | ● | ● | ● | ❍ | | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
❍ = Stock item in Japan

90° Square Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 0903.. | 9,525 | 9,525 | 3,18 | 3,81 |
| 1204.. | 12,7 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,875 | 15,875 | 6,35 | 6,35 |
| | | | | |
| | | | | |
| | | | | |







⇨ D14, D20~21
D41


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# SNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | Carbide Coated K | Carbide Coated S | Carbide Coated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NEF | **SNMG 120404 NEF** | 0,4 | ○ | ○ | ○ | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 120408 NEF** | 0,8 | ○ | ● | ● | ○ | ○ | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| Finishing |  NSJ | **SNMG 090304 NSJ** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **SNMG 120404 NSJ** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| Finishing |  NSX | **SNMG 120404 NSX** | 0,4 | | | | | | | | | | | | | | | | | | | ○ | ○ | | ○ | | | | |
| | | **SNMG 120408 NSX** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **SNMG 120412 NSX** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NGU | **SNMG 090304 NGU** | 0,4 | | | ● | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 090308 NGU** | 0,8 | ○ | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | ○ | | | | ○ | | | | |
| | | **SNMG 120404 NGU** | 0,4 | ● | ● | ● | ○ | ○ | ● | ○ | ○ | ○ | ○ | | | ○ | ○ | ○ | | | ○ | ○ | ○ | | ○ | | | | |
| | | **SNMG 120408 NGU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | | ○ | | | | |
| | | **SNMG 120412 NGU** | 1,2 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 120416 NGU** | 1,6 | ● | ● | ● | ○ | ● | | | ● | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 150608 NGU** | 0,8 | ○ | ○ | ○ | ○ | | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 150612 NGU** | 1,2 | ○ | ○ | ○ | ○ | | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 150616 NGU** | 1,6 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| Medium Cut |  NGE | **SNMG 120408 NGE** | 0,8 | ○ | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 120412 NGE** | 1,2 | ○ | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 120416 NGE** | 1,6 | ○ | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 150608 NGE** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 150612 NGE** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 150616 NGE** | 1,6 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# S SQUARE TYPE
INSERTS FOR TURNING

## 90° Square Type
0° Relief
With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 0903.. | 9,525 | 9,525 | 3,18 | 3,81 |
| 1204.. | 12,7 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,875 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,05 | 19,05 | 6,35 | 7,94 |
| 2509.. | 25,4 | 25,4 | 9,52 | 9,2 |
| | | | | |







⇨ D14, D20~21
D41


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## SNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | AC8015P | AC8020P | AC8025P | AC8035P | Carbide Coated M | AC6020M | AC6030M | AC6040M | Carbide Coated P/M | AC630M | Carbide Coated K | AC4010K | AC4015K | AC420K | Carbide Coated H | AC503U | Carbide Coated S | AC5005S | AC5015S | AC5025S | Carbide Coated P/M | AC1030U | AC530U | Cermet Coated P | T1500Z | T2500Z | T3000Z | Cermet Uncoated P | T1000A | T1500A | Carbide Uncoated K | G10E | Carbide Uncoated S | EH510 | EH520 | Carbide Uncoated N | H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Medium Cut |  NUG | SNMG 090308 NUG | 0,8 | | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 120408 NUG | 0,8 | | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 120412 NUG | 1,2 | | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 120416 NUG | 1,6 | ● | | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 150612 NUG | 1,2 | | | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 190612 NUG | 1,2 | | | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 190616 NUG | 1,6 | | | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 250924 NUG | 2,4 | | | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  L/RUM | SNMG 120404 LUM | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ | | | | | | | |
| | | SNMG 120408 LUM | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ | | | | | | | |
| | | SNMG 120412 LUM | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ | | | | | | | |
| | | SNMG 120404 RUM | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ | | | | | | | |
| | | SNMG 120408 RUM | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ | | | | | | | |
| Medium Cut |  NEG | SNMG 120404 NEG | 0,4 | ○ | ● | ● | ○ | ○ | ○ | ● | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | SNMG 120408 NEG | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | ● | ● | | | |
| | | SNMG 120412 NEG | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | ● | ● | | | |
| | | SNMG 150608 NEG | 0,8 | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | SNMG 150612 NEG | 1,2 | ○ | ○ | ○ | ○ | ● | ● | | ○ | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | | | | |
| | | SNMG 150616 NEG | 1,6 | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | SNMG 190612 NEG | 1,2 | ○ | ○ | ○ | ○ | ○ | ● | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | | | |
| | | SNMG 190616 NEG | 1,6 | ○ | ○ | ○ | ○ | ○ | ● | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | | | |
| Medium Cut |  NEX | SNMG 120404 NEX | 0,4 | | | | | ○ | ● | ● | ○ | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | |
| | | SNMG 120408 NEX | 0,8 | | | | | ● | ● | ● | ● | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | |
| | | SNMG 120412 NEX | 1,2 | | | | | ● | ● | ● | ● | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | |
| | | SNMG 150612 NEX | 1,2 | | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | SNMG 190612 NEX | 1,2 | | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | SNMG 190616 NEX | 1,6 | | | | | | | | | | | | | | | | | | | ● | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NUP | SNMG 120404 NUP | 0,4 | | ● | ● | ● | | ● | | ● | | | | | | | | | | | ● | ● | | | | | | | | | | | | | | | | |
| | | SNMG 120408 NUP | 0,8 | | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | ● | ● | ○ | | | | | | | | | | | | ○ | | | | | |
| | | SNMG 120412 NUP | 1,2 | | | | | ● | ● | ● | ● | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

90° Square Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN__ | L | IC | S | $D_1$ |
| 0903.. | 9,525 | 9,525 | 3,18 | 3,81 |
| 1204.. | 12,7 | 12,7 | 4,46 | 5,16 |
| 1506.. | 15,875 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,05 | 19,05 | 6,35 | 7,94 |
| 2509.. | 25,4 | 25,4 | 9,52 | 9,2 |
| | | | | |






⇨ D14, D20~21
D41


⇨ E10

P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

# SNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  NUX | **SNMG 090308 NUX** | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 120404 NUX** | 0,4 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 120408 NUX** | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 120412 NUX** | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 120416 NUX** | 1,6 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 190612 NUX** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMG 190616 NUX** | 1,6 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NMU | **SNMG 120408 NMU** | 0,8 | ● | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | ○ | | | | | | | | | |
| | | **SNMG 120412 NMU** | 1,2 | ○ | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | ○ | | | | | | | | | |
| | | **SNMG 120416 NMU** | 1,6 | ● | ○ | ○ | ○ | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMG 150608 NMU** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | ● | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 150612 NMU** | 1,2 | ● | ○ | ○ | ● | ● | ● | | ● | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | **SNMG 150616 NMU** | 1,6 | ● | ● | ● | ● | ● | ● | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 190612 NMU** | 1,2 | ● | ● | ● | ● | ● | ● | | ● | | | | | ○ | ○ | ● | | | | | | | | | | | |
| | | **SNMG 190616 NMU** | 1,6 | ● | ● | ● | ● | ● | ● | | ● | | | | | ○ | ○ | ● | | | | | | | | | | | |
| | | **SNMG 190624 NMU** | 2,4 | ○ | ○ | ○ | ○ | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 250924 NMU** | 2,4 | ○ | ○ | ○ | ● | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| Roughing |  NEM | **SNMG 120408 NEM** | 0,8 | ○ | ● | ● | ○ | ○ | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 120412 NEM** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 150608 NEM** | 0,8 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 150612 NEM** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 150616 NEM** | 1,6 | ○ | ○ | ○ | | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 190612 NEM** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 190616 NEM** | 1,6 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 190624 NEM** | 2,4 | ○ | ○ | ○ | ○ | ○ | | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMG 250924 NEM** | 2,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| Roughing |  NME | **SNMG 120408 NME** | 0,8 | ○ | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 120412 NME** | 1,2 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 120416 NME** | 1,6 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 150608 NME** | 0,8 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 150612 NME** | 1,2 | ○ | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 150616 NME** | 1,6 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 190612 NME** | 1,2 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 190616 NME** | 1,6 | ○ | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 190624 NME** | 2,4 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMG 250924 NME** | 2,4 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# S SQUARE TYPE
INSERTS FOR TURNING

**90° Square Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 1204.. | 12,7 | 12,7 | 4,46 | 5,16 |
| 1506.. | 15,875 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,05 | 19,05 | 6,35 | 7,94 |
| | | | | |
| | | | | |
| | | | | |






⇨ D14, D20~21
D41


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## SNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated M | Carbide Coated M | Carbide Coated P/M | Carbide Coated K | Carbide Coated K | Carbide Coated K | Carbide Coated H | Carbide Coated S | Carbide Coated S | Carbide Coated S | Carbide Coated P/M | Carbide Coated P/M | Cermet Coated P | Cermet Coated P | Cermet Coated P | Cermet Uncoated P | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  L/RHM | SNMG 120408 LHM | 0,8 | ○ | ○ | ○ | ○ | | ● | | | | | | | | | | | | | | | | | | |
| | | SNMG 120408 RHM | 0,8 | ○ | ○ | ○ | ○ | | ● | ○ | | | | | | | | | | | | | | | | | |
| Roughing |  NMX | SNMG 120408 NMX | 0,8 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 120412 NMX | 1,2 | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 120416 NMX | 1,6 | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 150612 NMX | 1,2 | | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 150616 NMX | 1,6 | | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 190612 NMX | 1,2 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 190616 NMX | 1,6 | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NGZ | SNMG 120408 NGZ | 0,8 | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | |
| | | SNMG 120412 NGZ | 1,2 | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | |
| | | SNMG 120416 NGZ | 1,6 | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | |
| | | SNMG 150612 NGZ | 1,2 | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | SNMG 150616 NGZ | 1,6 | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | |
| | | SNMG 190612 NGZ | 1,2 | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | SNMG 190616 NGZ | 1,6 | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| Roughing |  NUZ | SNMG 120408 NUZ | 0,8 | | | ○ | ○ | | | | ○ | ○ | ● | | ○ | ○ | ○ | | | | | | | | ○ | | |
| | | SNMG 120412 NUZ | 1,2 | | | ○ | ○ | | | | ○ | ○ | ● | | ○ | ○ | ○ | | | | | | | | | | |
| | | SNMG 120416 NUZ | 1,6 | | | ○ | ○ | | | | ● | ○ | ○ | | | | | | | | | | | | | | |
| | | SNMG 150612 NUZ | 1,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | SNMG 150616 NUZ | 1,6 | | | | | | | | | | ● | | | | | | | | | | | | | | |
| | | SNMG 190612 NUZ | 1,2 | | | ○ | ○ | | | | ○ | ○ | ● | | | | | | | | | | | | | | |
| | | SNMG 190616 NUZ | 1,6 | | | ○ | ○ | | | | ○ | ○ | ● | | | | | | | | | | | | | | |


● = Euro stock
○ = Stock item in Japan

90° Square Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 1204.. | 12,7 | 12,7 | 4,46 | 5,16 |
| 1506.. | 15,875 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,05 | 19,05 | 6,35 | 7,94 |
| 2507.. | 25,4 | 25,4 | 7,94 | 9,2 |
| 2509.. | 25,4 | 25,4 | 9,52 | 9,2 |
| 3109.. | 31,75 | 31,75 | 9,52 | 8,8 |






⇨ D14, D20~21


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# SNMM ●●●●●● ■-■■


● M-Class One Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Heavy Roughing |  NMP | **SNMM 120408 NMP** | 0,8 | ○ | ● | ● | ● | | ● | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMM 120412 NMP** | 1,2 | ○ | ○ | ○ | ● | | ● | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMM 120416 NMP** | 1,6 | ○ | ● | ● | ○ | | ● | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMM 120420 NMP** | 2,0 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 150612 NMP** | 1,2 | ○ | ● | ● | ● | | ○ | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 150616 NMP** | 1,6 | ● | ● | ● | ● | | ○ | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190612 NMP** | 1,2 | ○ | ● | ● | ● | | ● | | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMM 190616 NMP** | 1,6 | ● | ● | ● | ● | | ● | ○ | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **SNMM 190624 NMP** | 2,4 | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 250724 NMP** | 2,4 | ○ | ○ | ○ | ● | | ○ | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SNMM 250924 NMP** | 2,4 | ○ | ○ | ○ | | | ○ | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SNMM 310924 NMP** | 2,4 | ○ | ○ | ○ | | | ○ | | ○ | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NMH | **SNMM 190612 NMH** | 1,2 | ● | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190616 NMH** | 1,6 | ● | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 250724 NMH** | 2,4 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 250924 NMH** | 2,4 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHG | **SNMM 120408 NHG** | 0,8 | ● | ○ | ○ | ○ | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 120412 NHG** | 1,2 | ○ | ● | ● | ○ | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 120416 NHG** | 1,6 | ○ | ○ | ○ | | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 150612 NHG** | 1,2 | | | | | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 150616 NHG** | 1,6 | ○ | ● | ● | | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190612 NHG** | 1,2 | ○ | ○ | ○ | ● | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190616 NHG** | 1,6 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190624 NHG** | 2,4 | ○ | ● | ● | ● | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190616 NHGS** | 1,6 | | | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHP | **SNMM 120408 NHP** | 0,8 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 120412 NHP** | 1,2 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 120416 NHP** | 1,6 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 150612 NHP** | 1,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190612 NHP** | 1,2 | | | ● | ● | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190616 NHP** | 1,6 | | | ● | ● | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190624 NHP** | 2,4 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 250724 NHP** | 2,4 | ○ | ● | ● | ● | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SNMM 250924 NHP** | 2,4 | ○ | ○ | ○ | ● | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SNMM 310924 NHP** | 2,4 | ○ | ● | ● | | | | | ○ | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# S SQUARE TYPE
INSERTS FOR TURNING

**90° Square Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 1906.. | 19,05 | 19,05 | 6,35 | 7,94 |
| 2507.. | 25,4 | 25,4 | 7,94 | 9,2 |
| 2509.. | 25,4 | 25,4 | 9,52 | 9,2 |
| 3109.. | 31,75 | 31,75 | 9,52 | 8,8 |
| | | | | |
| | | | | |




➪ D14, D20~21


➪ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## SNMM ●●●●●● ■-■■


● M-Class One Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Heavy Roughing |  | **SNMM 190616 NHU** | 1,6 | | | | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **SNMM 250724 NHU** | 2,4 | ○ | ● | ● | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **SNMM 250924 NHU** | 2,4 | ○ | ○ | ○ | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **SNMM 310924 NHU** | 2,4 | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190616 NHW** | 1,6 | | | | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **SNMM 250724 NHW** | 2,4 | ○ | ● | ● | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **SNMM 250924 NHW** | 2,4 | ○ | ● | ● | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **SNMM 310924 NHW** | 2,4 | ○ | ○ | ○ | | | | | ○ | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  | **SNMM 190616 NHF** | 1,6 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 190624 NHF** | 2,4 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 250724 NHF** | 2,4 | | | ○ | ○ | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **SNMM 250732 NHF** | 3,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 250924 NHF** | 2,4 | | | ○ | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **SNMM 250932 NHF** | 3,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **SNMM 310924 NHF** | 2,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# S SQUARE TYPE
INSERTS FOR TURNING

**90° Square Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 0903.. | 9,525 | 9,525 | 3,18 | 3,81 |
| 1204.. | 12,7 | 12,7 | 4,76 | 5,16 |
| 1506.. | 15,875 | 15,875 | 6,35 | 6,35 |
| 1906.. | 19,05 | 19,05 | 6,35 | 7,94 |
| | | | | |
| | | | | |


⇨ D14, D20-21
D25


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel




## SNMA/SNGA ●●●●●●

● G/M-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | Carbide Coated | | | | | | | | | | | | | | | | | Cermet Coated | | | Cermet Uncoated | | Carbide Uncoated | | | |
| | | | | P | | | | M | | | P M | K | | | H | S | | | P M | | P | | | | | K | S | | N |
| Roughing |  | **SNMA 120404** | 0,4 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMA 120408** | 0,8 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | ○ | | | |
| | | **SNMA 120412** | 1,2 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | | |
| | | **SNMA 120416** | 1,6 | | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | |
| | | **SNMA 120420** | 2,0 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMA 150612** | 1,2 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | **SNMA 150616** | 1,6 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **SNMA 190612** | 1,2 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | |
| | | **SNMA 190616** | 1,6 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | |
| Medium Cut |  | **SNGA 120404** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **SNGA 120408** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **SNGA 120412** | 1,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | | |

## SNGG ●●●●●● ■-■■


● G-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | Carbide Coated | | | | | | | | | | | | | | | | | Cermet Coated | | | Cermet Uncoated | | Carbide Uncoated | | | |
| | | | | P | | | | M | | | P M | K | | | H | S | | | P M | | P | | | | | K | S | | N |
| Light Cutting |  | **SNGG 090304 LST** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **SNGG 090308 LST** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **SNGG 090304 RST** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **SNGG 090308 RST** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| Medium Cut |  | **SNGG 120404 LUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ● | | | | |
| | | **SNGG 120408 LUM** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | ○ | ● | | | | |
| | | **SNGG 120404 RUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **SNGG 120408 RUM** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | ● | ● | | | | |
| For Aluminum |  | **SNGG 120404 LAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **SNGG 120404 RAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **SNGG 120408 RAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Stock item in Japan

# S SQUARE TYPE
INSERTS FOR TURNING

## 90° Square Type
0° Relief
Without Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 1204.. | 12,7 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |


⇨ D14, D20-21
D25


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## SN_N ●●●●●●

● G/M-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated M | Carbide Coated M | Carbide Coated P/M | Carbide Coated K | Carbide Coated K | Carbide Coated K | Carbide Coated H | Carbide Coated S | Carbide Coated S | Carbide Coated S | Carbide Coated P/M | Carbide Coated P/M | Cermet Coated P | Cermet Coated P | Cermet Coated P | Cermet Uncoated P | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Medium Cut | | **SNGN 120408** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| Medium Cut | | **SNMN 120408** | 0,8 | | | | | | | | | ○ | ○ | | | | ○ | ○ | ○ | | | | | ○ | ○ | | | | |
| | | **SNMN 120412** | 1,2 | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **SNMN 120416** | 1,6 | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

60° Triangle Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |










⇨ D15, D22~23
D42

⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# TNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | Carbide Coated M: AC6020M | AC6030M | AC6040M | Carbide Coated P,M: AC630M | Carbide Coated K: AC4010K | AC4015K | AC420K | Carbide Coated H: AC503U | Carbide Coated S: AC5005S | AC5015S | AC5025S | Carbide Coated P,M: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | Carbide Uncoated S: EH510 | EH520 | Carbide Uncoated N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Fine Finishing |  NFB | **TNMG 160402 NFB** | 0,2 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 160404 NFB** | 0,4 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 160408 NFB** | 0,8 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Fine Finishing |  NFA | **TNMG 160402 NFA** | 0,2 | | | | | | | | | | | | | | | | | | ● | ○ | ○ | | ● | | | | |
| | | **TNMG 160404 NFA** | 0,4 | | | | | | | | | | | | | | | | | | ● | ○ | ● | ● | ● | | | | |
| | | **TNMG 160408 NFA** | 0,8 | | | | | | | | | | | | | | | | | | ● | ○ | ● | ● | ● | | | | |
| Fine Finishing |  NFL | **TNMG 160404 NFL** | 0,4 | | | ○ | | | | | ○ | | | | | | | | | | ● | ● | ● | ○ | ● | | | | |
| | | **TNMG 160408 NFL** | 0,8 | | | ○ | | | | | ○ | | | | | | | | | | ● | ○ | ● | ● | ● | | | | |
| Fine Finishing |  NFE | **TNMG 160402 NFE** | 0,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 160404 NFE** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 160408 NFE** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 160412 NFE** | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | | | | |
| Finishing |  NLU | **TNMG 160402 NLU** | 0,2 | | | | | | ○ | | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | |
| | | **TNMG 160404 NLU** | 0,4 | ● | ● | ● | ○ | | ○ | | ○ | | | | | | | | | | ● | ● | ● | ● | ● | | | | |
| | | **TNMG 160408 NLU** | 0,8 | ● | ● | ● | ○ | | ○ | | ○ | | | | | | | | | | ● | ○ | ● | ● | ● | | | | |
| | | **TNMG 160412 NLU** | 1,2 | ● | ● | ● | ○ | | ○ | | ○ | | | | | | | | | | ● | ● | ● | ● | | | | | |
| Finishing |  NEF | **TNMG 160404 NEF** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | ○ | ○ | | |
| | | **TNMG 160408 NEF** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | ○ | ○ | | |
| Finishing |  NSU | **TNMG 160402 NSU** | 0,2 | | | | | ● | ● | ● | ○ | | | | | ○ | ○ | ○ | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 160404 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | ● | ○ | ● | ● | ● | | | | |
| | | **TNMG 160408 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | ● | ● | ● | ● | ● | | | | |
| | | **TNMG 160412 NSU** | 1,2 | ● | ● | ● | | | ● | | | | | | | ○ | ○ | ○ | | | ● | ● | ● | | ● | | | | |

● = Euro stock
○ = Stock item in Japan

# T TRIANGLE TYPE
## INSERTS FOR TURNING

**60° Triangle Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN_ _ | L | IC | S | $D_1$ |
| 1603.. | 16,5 | 9,525 | 3,18 | 3,81 |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| 2204.. | 22,0 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |







➪ D15, D22~23
D42

➪ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# TNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | AC8015P | AC8020P | AC8025P | AC8035P | Carbide Coated M | AC6020M | AC6030M | AC6040M | Carbide Coated P/M | AC630M | Carbide Coated K | AC4010K | AC4015K | AC420K | Carbide Coated H | AC503U | Carbide Coated S | AC5005S | AC5015S | AC5025S | Carbide Coated P/M | AC1030U | AC530U | Cermet Coated P | T1500Z | T2500Z | T3000Z | Cermet Uncoated P | T1000A | T1500A | Carbide Uncoated K | G10E | Carbide Uncoated S | EH510 | EH520 | Carbide Uncoated N | H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  NSE | TNMG 160404 NSE | 0,4 | | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | | | | | | | |
| | | TNMG 160408 NSE | 0,8 | | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | | | | | |
| | | TNMG 160412 NSE | 1,2 | | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220404 NSE | 0,4 | | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220408 NSE | 0,8 | | ● | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220412 NSE | 1,2 | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Finishing |  NSX | TNMG 160304 NSX | 0,4 | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 160308 NSX | 0,8 | | ○ | ○ | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 160404 NSX | 0,4 | | ● | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | | | | |
| | | TNMG 160408 NSX | 0,8 | | ○ | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | | | | |
| | | TNMG 220404 NSX | 0,4 | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220408 NSX | 0,8 | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220412 NSX | 1,2 | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NGU | TNMG 160404 NGU | 0,4 | | ● | ● | ● | ● | | ● | ● | ● | | ● | | ○ | ○ | | | | | ○ | ○ | ○ | | | | ○ | ○ | | | | ○ | | | | | | | |
| | | TNMG 160408 NGU | 0,8 | | ● | ● | ● | ● | | ● | ● | ● | | ● | | ○ | ○ | | | | | ○ | ○ | ○ | | | ○ | ○ | ○ | | | | ○ | | | | | | | |
| | | TNMG 160412 NGU | 1,2 | | ● | ● | ● | ● | | ● | ● | ● | | ● | | ○ | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | TNMG 160416 NGU | 1,6 | | ○ | ● | ● | ● | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220404 NGU | 0,4 | | | | ○ | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220408 NGU | 0,8 | | ● | ● | ● | ○ | | | | | | ● | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220412 NGU | 1,2 | | ● | ○ | ○ | ● | | | | | | ● | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NGE | TNMG 160404 NGE | 0,4 | | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 160408 NGE | 0,8 | | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 160412 NGE | 1,2 | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220408 NGE | 0,8 | | ○ | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | TNMG 220412 NGE | 1,2 | | ○ | ○ | ○ | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

60° Triangle Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| 2204.. | 22,0 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |








⇨ D15, D22~23 D42

⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# TNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Coated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Medium Cut |  NUG | **TNMG 160404 NUG** | 0,4 | ● | | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 160408 NUG** | 0,8 | ● | | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 160412 NUG** | 1,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 160416 NUG** | 1,6 | ● | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220408 NUG** | 0,8 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220412 NUG** | 1,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  L/RUM | **TNMG 160404 LUM** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 160408 LUM** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 220404 LUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TNMG 220408 LUM** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TNMG 160404 RUM** | 0,4 | ● | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 160408 RUM** | 0,8 | ● | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNMG 220404 RUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TNMG 220408 RUM** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| Medium Cut |  NEG | **TNMG 160404 NEG** | 0,4 | ○ | ● | ● | ○ | ○ | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **TNMG 160408 NEG** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | | ● | ● | |
| | | **TNMG 160412 NEG** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | | ● | | |
| Medium Cut |  NEX | **TNMG 160404 NEX** | 0,4 | | | | | ● | ● | ● | ● | | | | | ○ | ○ | ● | | | | | | | | | | | |
| | | **TNMG 160408 NEX** | 0,8 | | | | | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | | | | | | | | | |
| | | **TNMG 160412 NEX** | 1,2 | | | | | ● | ● | ● | ● | | | | | ● | ● | ○ | | | | | | | | | | | |
| Medium Cut |  NUP | **TNMG 160404 NUP** | 0,4 | | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ○ | | ○ | | | | | | ○ | | |
| | | **TNMG 160408 NUP** | 0,8 | | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ○ | | | | | | | | ○ | | | |
| | | **TNMG 160412 NUP** | 1,2 | | | | | | ● | ● | ● | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | **TNMG 220408 NUP** | 0,8 | | ● | ● | ● | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# T TRIANGLE TYPE
## INSERTS FOR TURNING

**60° Triangle Type** — 0° Relief / With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN_ _ | L | IC | S | $D_1$ |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| 2204.. | 22,0 | 12,7 | 4,76 | 5,16 |
| 2706.. | 27,5 | 15,875 | 6,35 | 6,35 |
| 3309.. | 33,0 | 19,05 | 9,52 | 7,93 |
| | | | | |
| | | | | |








➪ D15, D22~23 D42

➪ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# TNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | AC8020P | AC8025P | AC8035P | Carbide Coated M | AC6020M | AC6030M | AC6040M | Carbide Coated P/M | AC630M | Carbide Coated K | AC4010K | AC4015K | AC420K | Carbide Coated H | AC503U | Carbide Coated S | AC5005S | AC5015S | AC5025S | Carbide Coated P/M | AC1030U | AC530U | Cermet Coated P | T1500Z | T2500Z | T3000Z | Cermet Uncoated P | T1000A | T1500A | Carbide Uncoated K | G10E | Carbide Uncoated S | EH510 | EH520 | Carbide Uncoated N | H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Roughing |  NUX | **TNMG 160404 NUX** | 0,4 | ○ | ● | ● | ○ | | | | | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 160408 NUX** | 0,8 | ● | ● | ● | ● | | | | | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 160412 NUX** | 1,2 | ● | ● | ● | ○ | | | | | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220408 NUX** | 0,8 | ○ | ○ | ○ | ○ | | | | | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220412 NUX** | 1,2 | ○ | ● | ● | ○ | | | | | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NMU | **TNMG 160408 NMU** | 0,8 | ● | ● | ● | ● | ● | ● | | ● | | | | | | | | ○ | ○ | ○ | | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 160412 NMU** | 1,2 | ● | ● | ● | ○ | ● | ● | | ● | | | | | | | | ○ | ○ | ○ | | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 220408 NMU** | 0,8 | ● | ● | ● | ● | ● | | | ● | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | | | |
| | | **TNMG 220412 NMU** | 1,2 | ● | ● | ● | ● | ● | | | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220416 NMU** | 1,6 | ● | ● | ● | ● | ● | | | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 270612 NMU** | 1,2 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 270616 NMU** | 1,6 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NEM | **TNMG 160408 NEM** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | | | | ○ | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 160412 NEM** | 1,2 | ○ | | ○ | ○ | ○ | ● | ● | | | | | | | | | ○ | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 330924 NEM** | 2,4 | | | ○ | ○ | | ○ | ○ | | | | | | | | | ○ | | ○ | ○ | | | | | | | | | | | | | | | |
| Roughing |  NME | **TNMG 160408 NME** | 0,8 | ○ | ● | ● | ○ | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 160412 NME** | 1,2 | ● | ● | ● | ○ | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220408 NME** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220412 NME** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220416 NME** | 1,6 | ○ | ○ | ○ | ○ | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NMX | **TNMG 160408 NMX** | 0,8 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 160412 NMX** | 1,2 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220408 NMX** | 0,8 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 220412 NMX** | 1,2 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |

Depth of cut (mm) / Feed rate (mm/rev)

● = Euro stock
○ = Stock item in Japan

**60° Triangle Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| 2204.. | 22,0 | 12,7 | 4,76 | 5,16 |
| 2706.. | 27,5 | 15,875 | 6,35 | 6,35 |
| | | | | |
| | | | | |
| | | | | |






⇨ D15, D22~23 D42

⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## TNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  NGZ | **TNMG 160404 NGZ** | 0,4 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | **TNMG 160408 NGZ** | 0,8 | | | | | | | | | ● | ● | ● | | | | | | | | | | | | | | |
| | | **TNMG 160412 NGZ** | 1,2 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | |
| | | **TNMG 220408 NGZ** | 0,8 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 220412 NGZ** | 1,2 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 220416 NGZ** | 1,6 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| Roughing |  L/RHM | **TNMG 160404 LHM** | 0,4 | ○ | ○ | ○ | ○ | | ● | | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TNMG 160408 LHM** | 0,8 | ○ | ○ | ○ | ○ | | ● | | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TNMG 220404 LHM** | 0,4 | ○ | ○ | ○ | ○ | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **TNMG 220408 LHM** | 0,8 | ○ | ○ | ○ | ○ | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **TNMG 160404 RHM** | 0,4 | ● | ○ | ○ | ○ | | ● | | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TNMG 160408 RHM** | 0,8 | ○ | ○ | ○ | ○ | | ● | | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TNMG 220404 RHM** | 0,4 | ○ | ○ | ○ | ○ | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **TNMG 220408 RHM** | 0,8 | ○ | ○ | ○ | ○ | | | | ○ | | | | | | | | | | | | | | | | | |
| Roughing |  NUZ | **TNMG 160404 NUZ** | 0,4 | | | ○ | | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 160408 NUZ** | 0,8 | | | ○ | ○ | | | | | ● | ● | ● | | | | | | | | | | | | | | |
| | | **TNMG 160412 NUZ** | 1,2 | | | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 160416 NUZ** | 1,6 | | | ○ | | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 160420 NUZ** | 2,0 | | | ○ | | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 220408 NUZ** | 0,8 | | | ○ | ● | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | **TNMG 220412 NUZ** | 1,2 | | | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 220416 NUZ** | 1,6 | | | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMG 270608 NUZ** | 0,8 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 270612 NUZ** | 1,2 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMG 270616 NUZ** | 1,6 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# T TRIANGLE TYPE
INSERTS FOR TURNING

**60° Triangle Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN_ _ | L | IC | S | $D_1$ |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| 2204.. | 22,0 | 12,7 | 4,76 | 5,16 |
| 2706.. | 27,5 | 15,875 | 6,35 | 6,35 |






⇨D22-23 ⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## TNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Heavy Roughing |  NMP | **TNMM 160404 NMP** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 160408 NMP** | 0,8 | | | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **TNMM 160412 NMP** | 1,2 | | | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **TNMM 220408 NMP** | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 220412 NMP** | 1,2 | ● | | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **TNMM 220416 NMP** | 1,6 | | | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **TNMM 270612 NMP** | 1,2 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 270616 NMP** | 1,6 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHG | **TNMM 160408 NHG** | 0,8 | | | | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **TNMM 160412 NHG** | 1,2 | ● | | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 220408 NHG** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 220412 NHG** | 1,2 | | | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **TNMM 220416 NHG** | 1,6 | | | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHP | **TNMM 160408 NHP** | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 160412 NHP** | 1,2 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 220408 NHP** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 220412 NHP** | 1,2 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 220416 NHP** | 1,6 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 270612 NHP** | 1,2 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNMM 270616 NHP** | 1,6 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |


## TNMN ●●●●●●

● M-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Medium Cut |  | **TNMN 160408** | 0,8 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMN 160412** | 1,2 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TNMN 160416** | 1,6 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

60° Triangle Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| 2204.. | 22,0 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |



⇨ D15, D22~23 ⇨ E12


- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## TNMA ●●●●●●

● G/M-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  | **TNMA 160404** | 0,4 | | | | | | | | | ○ | ○ | ● | | | ○ | ○ | | | | | | | | ○ | | | |
| | | **TNMA 160408** | 0,8 | | | | | | | | | ○ | ○ | ● | | | ○ | ○ | | | | | | | | ● | | | |
| | | **TNMA 160412** | 1,2 | | | | | | | | | ○ | ○ | ● | | | ○ | ○ | | | | | | | | | | | |
| | | **TNMA 160416** | 1,6 | | | | | | | | | ○ | ● | | | | | | | | | | | | | | | | |
| | | **TNMA 160420** | 2,0 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **TNMA 220408** | 0,8 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | ○ | | | |
| | | **TNMA 220412** | 1,2 | | | | | | | | | ○ | ● | | | | | | | | | | | | | | | | |
| | | **TNMA 220416** | 1,6 | | | | | | | | | ○ | ● | ○ | | | | | | | | | | | | | | | |










⇨ D11 ⇨ E11

## TRM ●●●●●● -■■


● M-Class Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Fine Finishing |  -FL | **TRM 551704 -FL** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | **TRM 551708 -FL** | 0,8 | | | ○ | | | | | | | | | | | | | | | | | ○ | | | | | | |
| Finishing |  -LU | **TRM 551704 -LU** | 0,4 | ● | | ○ | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | **TRM 551708 -LU** | 0,8 | ● | | ○ | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | **TRM 551712 -LU** | 1,2 | | | ○ | | | | | | | | | | | | | | | | | ○ | | | | | | |
| |    -SU | **TRM 551704 -SU** | 0,4 | | | ○ | | | | | ● | | | | | | | | | | | | ○ | | | | | | |
| | | **TRM 551708 -SU** | 0,8 | | | ○ | | | | | ● | | | | | | | | | | | | ○ | | | | | | |
| | | **TRM 551712 -SU** | 1,2 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| Light Cut |    -GU | **TRM 551704 -GU** | 0,4 | | | ○ | | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **TRM 551708 -GU** | 0,8 | | | ○ | | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **TRM 551712 -GU** | 1,2 | | | ○ | | | | | ○ | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# T TRIANGLE TYPE
## INSERTS FOR TURNING

**60° Triangle Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN_ _ | L | IC | S | $D_1$ |
| 1103.. | 11,0 | 6,35 | 3,18 | 2,26 |
| 1603.. | 16,5 | 9,525 | 3,18 | 3,81 |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| | | | | |
| | | | | |
| | | | | |








⇨ D15, D22~23 ⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# TNGG ●●●●●● ■-■■


● G-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  L/RFT | **TNGG 110302 LFT** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 110304 LFT** | 0,4 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 110302 RFT** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 110304 RFT** | 0,4 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| Light Cutting |  L/RST | **TNGG 160302 LST** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160304 LST** | 0,4 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160308 LST** | 0,8 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160402 LST** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160404 LST** | 0,4 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160408 LST** | 0,8 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160412 LST** | 1,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TNGG 160302 RST** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160304 RST** | 0,4 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160308 RST** | 0,8 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160402 RST** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160404 RST** | 0,4 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160408 RST** | 0,8 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160412 RST** | 1,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| Finishing |  NSU | **TNGG 160402 NSU** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ● | ● | ○ | ○ | | | | |
| | | **TNGG 160404 NSU** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNGG 160408 NSU** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Finishing |  L/RFY | **TNGG 160401 LFY** | 0,1 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TNGG 160402 LFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNGG 160404 LFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNGG 160408 LFY** | 0,8 | | | | | | | | | | | | | | | | ○ | | ○ | | | ○ | ○ | | | | |
| | | **TNGG 160412 LFY** | 1,2 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **TNGG 160401 RFY** | 0,1 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TNGG 160402 RFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNGG 160404 RFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNGG 160408 RFY** | 0,8 | | | | | | | | | | | | | | | | ○ | | ○ | | | ○ | ○ | | | | |
| | | **TNGG 160412 RFY** | 1,2 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| Finishing |  L/RFX | **TNGG 160402 LFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNGG 160404 LFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNGG 160408 LFX** | 0,8 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TNGG 160402 RFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | ● | ○ | ○ | ○ | | | | |
| | | **TNGG 160404 RFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TNGG 160408 RFX** | 0,8 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |



● = Euro stock
○ = Stock item in Japan

60° Triangle Type | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| 1103.. | 11,0 | 6,35 | 3,18 | 2,26 |
| 1604.. | 16,5 | 9,525 | 4,76 | 3,81 |
| 2204.. | 22,0 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |






⇨ D15, D22~23 ⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel




## TNGG ●●●●●● ■-■■

● G-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | AC8020P | AC8025P | AC8035P | M AC6020M | AC6030M | AC6040M | PM AC630M | K AC4010K | AC4015K | AC420K | H AC503U | S AC5005S | AC5015S | AC5025S | PM AC1030U | AC530U | Cermet Coated P T1500Z | T2500Z | T3000Z | Uncoated P T1000A | T1500A | Carbide Uncoated K G10E | S EH510 | EH520 | N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Medium Cut |   | **TNGG 160402 LUM** | 0,2 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ● | | | | |
| | | **TNGG 160404 LUM** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ● | ● | | | | |
| | | **TNGG 160408 LUM** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ● | | | | | |
| | | **TNGG 160412 LUM** | 1,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 220404 LUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 220408 LUM** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 160402 RUM** | 0,2 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ● | ● | | | | |
| | | **TNGG 160404 RUM** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ● | ● | | | | ○ |
| | | **TNGG 160408 RUM** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | | ● | | | | |
| | | **TNGG 160412 RUM** | 1,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 220404 RUM** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TNGG 220408 RUM** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| Finishing |   | **TNGG 160402 NGH** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **TNGG 160404 NGH** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **TNGG 160408 NGH** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| For Aluminum |   | **TNGG 160402 LAX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TNGG 160404 LAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TNGG 160408 LAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TNGG 160402 RAX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TNGG 160404 RAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TNGG 160408 RAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

## TNGA ●●●●●●


● G-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | AC8020P | AC8025P | AC8035P | M AC6020M | AC6030M | AC6040M | PM AC630M | K AC4010K | AC4015K | AC420K | H AC503U | S AC5005S | AC5015S | AC5025S | PM AC1030U | AC530U | Cermet Coated P T1500Z | T2500Z | T3000Z | Uncoated P T1000A | T1500A | Carbide Uncoated K G10E | S EH510 | EH520 | N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Medium Cut |  | **TNGA 110308** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | | | | | |
| | | **TNGA 160402** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **TNGA 160404** | 0,4 | | | | | | | | | | | | ○ | | ○ | ○ | | | | | | ○ | | | | | |
| | | **TNGA 160408** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | ○ | ○ | ○ | | | ○ |

● = Euro stock
○ = Stock item in Japan

# V DIAMOND TYPE
## INSERTS FOR TURNING

**35° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VN__ | L | IC | S | $D_1$ |
| 1604.. | 16,6 | 9,525 | 4,76 | 3,81 |



⇨ D16

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel







## VNMA ●●●●●●

● M-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | T1000A | T1500A | Cermet Uncoated K: G10E | Carbide Uncoated S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Roughing |  | **VNMA 160404** | 0,4 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **VNMA 160408** | 0,8 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | **VNMA 160412** | 1,2 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |

## VNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | T1000A | T1500A | Cermet Uncoated K: G10E | Carbide Uncoated S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Fine Finishing |  NFB | **VNMG 160404 NFB** | 0,4 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VNMG 160408 NFB** | 0,8 | | | | | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Fine Finishing |  NFA | **VNMG 160404 NFA** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VNMG 160408 NFA** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Fine Finishing |  NFL | **VNMG 160404 NFL** | 0,4 | | | ○ | | | | | ○ | | | | | | | | | | ● | ● | ● | ● | ● | | | | |
| | | **VNMG 160408 NFL** | 0,8 | | ● | ● | | | | | ○ | | | | | | | | | | ● | ● | ● | ● | ● | | | | |
| Fine Finishing |  NFE | **VNMG 160402 NFE** | 0,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VNMG 160404 NFE** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VNMG 160408 NFE** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VNMG 160412 NFE** | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Finishing |  NLU | **VNMG 160402 NLU** | 0,2 | | | | | | ○ | | ○ | | | | | | | | | | ● | ● | ● | ○ | ● | | | | |
| | | **VNMG 160404 NLU** | 0,4 | ● | ● | ● | | | ○ | | ○ | | | | | | | | | | ● | ○ | ● | ● | ● | | | | |
| | | **VNMG 160408 NLU** | 0,8 | ● | ● | ● | | | ○ | | ○ | | | | | | | | | | ● | ○ | ○ | ● | ● | | | | |
| | | **VNMG 160412 NLU** | 1,2 | ● | ○ | | | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NEF | **VNMG 160402 NEF** | 0,2 | ○ | ○ | ○ | ○ | ● | ● | | ○ | | | | | ○ | ○ | ○ | | | | | | | | ○ | | | |
| | | **VNMG 160404 NEF** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | ○ | ● | | |
| | | **VNMG 160408 NEF** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | ● | ● | | |


● = Euro stock
○ = Stock item in Japan

# V DIAMOND TYPE
## INSERTS FOR TURNING

**35° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VN__ | L | IC | S | $D_1$ |
| 1604.. | 16,6 | 9,525 | 4,76 | 3,81 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |



⇨ D16

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## VNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated PM | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated PM | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing | NSU | **VNMG 160402 NSU** | 0,2 | | | | | | ● | ● | ○ | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | | ○ | | | | |
| | | **VNMG 160404 NSU** | 0,4 | ● | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VNMG 160408 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ○ | | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| Medium Cut | NSE | **VNMG 160404 NSE** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **VNMG 160408 NSE** | 0,8 | ● | ● | ● | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| Medium Cut | NSX | **VNMG 160404 NSX** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **VNMG 160408 NSX** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| Medium Cut | NGU | **VNMG 160404 NGU** | 0,4 | ● | ● | ● | ○ | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | | ○ | ○ | | | ○ | | | | |
| | | **VNMG 160408 NGU** | 0,8 | ● | ● | ● | ○ | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | ○ | | | | |
| | | **VNMG 160412 NGU** | 1,2 | ○ | ● | ● | ○ | | | ● | | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | | |
| Medium Cut | NGE | **VNMG 160404 NGE** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **VNMG 160408 NGE** | 0,8 | ○ | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **VNMG 160412 NGE** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut | NUG | **VNMG 160404 NUG** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **VNMG 160408 NUG** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **VNMG 160412 NUG** | 1,2 | ● | | | | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut | NEG | **VNMG 160404 NEG** | 0,4 | ○ | ○ | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **VNMG 160408 NEG** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | ○ | ○ | | |
| | | **VNMG 160412 NEG** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| Medium Cut | NEX | **VNMG 160404 NEX** | 0,4 | | | | | ● | ● | ● | ● | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | **VNMG 160408 NEX** | 0,8 | | | | | ● | ● | ○ | ● | | | | | ● | ● | ● | | ○ | | | | | | | | | |

Depth of cut (mm) / Feed rate (mm/rev)

● = Euro stock
○ = Stock item in Japan

# V DIAMOND TYPE
## INSERTS FOR TURNING

**35° Diamond Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VN_ _ | L | IC | S | $D_1$ |
| 1604.. | 16,6 | 9,525 | 4,76 | 3,81 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |



⇨ D16

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## VNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | T1000A | Cermet Uncoated P: T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Medium Cut | NUP | **VNMG 160404 NUP** | 0,4 | | ● | ● | ● | ● | ● | | ● | | | | | | ● | | | | | | | | | ○ | | | |
| | | **VNMG 160408 NUP** | 0,8 | | ● | ● | ● | ● | ● | ○ | ● | | | | | | ● | ● | | | | | | | | ○ | | | |
| Medium Cut | NUX | **VNMG 160404 NUX** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **VNMG 160408 NUX** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **VNMG 160412 NUX** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut | NGZ | **VNMG 160404 NGZ** | 0,4 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **VNMG 160408 NGZ** | 0,8 | | | | | | | | | ● | ● | ○ | | | | | | | | | | | | | | | |
| | | **VNMG 160412 NGZ** | 1,2 | | | | | | | | | ● | ○ | ● | | | | | | | | | | | | | | | |
| Medium Cut | NUZ | **VNMG 160404 NUZ** | 0,4 | | | ○ | ○ | | | | | ○ | ○ | ● | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **VNMG 160408 NUZ** | 0,8 | | | ○ | ○ | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **VNMG 160412 NUZ** | 1,2 | | | ○ | ○ | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | |

## VNGG ●●●●●● ■-■■


● G-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | T1000A | Cermet Uncoated P: T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing | NSU | **VNGG 160402 NSU** | 0,2 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VNGG 160404 NSU** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VNGG 160408 NSU** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Medium Cut | NEF | **VNGG 160402 NEF** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| | | **VNGG 160404 NEF** | 0,4 | | | | | | | | ○ | | | | | | ○ | ○ | | | | | | | | | | | |
| Medium Cut | L/RAX | **VNGG 160402 LAX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **VNGG 160404 LAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **VNGG 160408 LAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **VNGG 160402 RAX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **VNGG 160404 RAX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **VNGG 160408 RAX** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Stock item in Japan

# W TRIGON TYPE
## INSERTS FOR TURNING

**80° Trigon Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WN_ _ | L | IC | S | $D_1$ |
| 0604.. | 6,5 | 9,525 | 4,76 | 3,81 |
| 0804.. | 8,7 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |








⇨ D17, D24 D42


⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## WNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P,M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P,M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Fine Finishing |  NFB  Feed rate (mm/rev) | **WNMG 060404 NFB** | 0,4 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **WNMG 060408 NFB** | 0,8 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **WNMG 080402 NFB** | 0,2 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **WNMG 080404 NFB** | 0,4 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **WNMG 080408 NFB** | 0,8 | | | | | | | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Fine Finishing |  NFA  Feed rate (mm/rev) | **WNMG 080402 NFA** | 0,2 | | | | | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **WNMG 080404 NFA** | 0,4 | | | | | | | | | | | | | | | | | | ● | ○ | | | ● | | | | |
| | | **WNMG 080408 NFA** | 0,8 | | | | | | | | | | | | | | | | | | ● | ○ | | | ● | | | | |
| Fine Finishing |  NFL  Feed rate (mm/rev) | **WNMG 080404 NFL** | 0,4 | | | ○ | | | | | ○ | | | | | | | | | | ● | ○ | ● | | | | | | |
| | | **WNMG 080408 NFL** | 0,8 | | | ○ | | | | | ○ | | | | | | | | | | ● | ● | ● | | ● | | | | |
| Fine Finishing |  NFE  Feed rate (mm/rev) | **WNMG 060404 NFE** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **WNMG 060408 NFE** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **WNMG 080402 NFE** | 0,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **WNMG 080404 NFE** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **WNMG 080408 NFE** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **WNMG 080412 NFE** | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Finishing |  NLU  Feed rate (mm/rev) | **WNMG 060404 NLU** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | | | | | | | |
| | | **WNMG 060408 NLU** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | | | | | | | |
| | | **WNMG 060412 NLU** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080404 NLU** | 0,4 | ● | ● | ● | ○ | | ○ | | ○ | | | | | | | | | | ● | ○ | | | | | | | |
| | | **WNMG 080408 NLU** | 0,8 | ● | ● | ● | ○ | | ○ | | ○ | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| | | **WNMG 080412 NLU** | 1,2 | ○ | ● | ● | ○ | | ○ | | ○ | | | | | | | | | | ● | ○ | | | | | | | |
| Finishing |  NLU-W  Feed rate (mm/rev) | **WNMG 060404 NLU-W** | 0,4 | ● | ● | ● | | | ○ | | ● | | | | | | | | | | ● | ○ | | | ● | | | | |
| | | **WNMG 060408 NLU-W** | 0,8 | ● | ● | ● | | ● | ○ | | ● | | | | | | | | | | ● | ● | | | ● | | | | |
| | | **WNMG 080404 NLU-W** | 0,4 | ● | ● | ● | | ● | ○ | | ● | | ● | | | | | | | | ● | ○ | ● | | ● | | | | |
| | | **WNMG 080408 NLU-W** | 0,8 | ● | ● | ● | | ● | ○ | | ● | ● | ● | | | | | | | | ● | ● | ● | | ● | | | | |
| | | **WNMG 080412 NLU-W** | 1,2 | ● | ○ | | | | ○ | | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |

● = Euro stock
○ = Stock item in Japan

# W TRIGON TYPE
## INSERTS FOR TURNING

**80° Trigon Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WN_ _ | L | IC | S | $D_1$ |
| 0604.. | 6,5 | 9,525 | 4,76 | 3,81 |
| 06T3.. | 6,5 | 9,525 | 3,97 | 3,81 |
| 0804.. | 8,7 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |








⇨ D17, D24
D42

⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## WNMG ●●●●●● ■-■■


●

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Coated K | Carbide Coated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NEF | **WNMG 060404 NEF** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **WNMG 060408 NEF** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **WNMG 080404 NEF** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | | ● | ● | |
| | | **WNMG 080408 NEF** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ● | ● | ● | | | | | | | | | ● | ● | |
| Finishing |  NSU | **WNMG 060404 NSU** | 0,4 | ● | ● | ● | ○ | ● | ○ | ○ | ● | | | | | | ● | ● | | | | ○ | | | | | | | |
| | | **WNMG 060408 NSU** | 0,8 | ● | ● | ● | ○ | ● | ○ | | ● | | | | | | ● | ● | | | | ○ | | | | | | | |
| | | **WNMG 060412 NSU** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 06T304 NSU** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 06T308 NSU** | 0,8 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080404 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ○ | ○ | ● | | ○ | ● | ● | ○ | ● | ● | | | | |
| | | **WNMG 080408 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | ● | ○ | ● | | ● | | | | |
| | | **WNMG 080412 NSU** | 1,2 | ● | ● | ● | ● | | ● | ● | ○ | | | | | ○ | ○ | ○ | | ○ | ○ | ● | ○ | ○ | ○ | | | | |
| Finishing |  NSE / NSE-W | **WNMG 080404 NSE** | 0,4 | ● | ● | ● | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **WNMG 080408 NSE** | 0,8 | ● | ● | ● | ○ | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **WNMG 080412 NSE** | 1,2 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 060404 NSE-W** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 060408 NSE-W** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080404 NSE-W** | 0,4 | ● | ● | ● | | | | | | | | | | | | | | | ○ | ○ | | | | | | | |
| | | **WNMG 080408 NSE-W** | 0,8 | ● | ● | ● | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **WNMG 080412 NSE-W** | 1,2 | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Finishing |  | **WNMG 080404 NSX** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **WNMG 080408 NSX** | 0,8 | ● | ○ | ○ | ● | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **WNMG 080412 NSX** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NGU / NGU-W | **WNMG 060404 NGU** | 0,4 | ● | ● | ● | ○ | ● | ○ | ○ | ● | ○ | ○ | | | | | | | | ○ | ○ | | | | | | | |
| | | **WNMG 060408 NGU** | 0,8 | ● | ● | ● | ○ | ● | ○ | ○ | ● | ○ | ○ | | | | | | | | ○ | ○ | | | | | | | |
| | | **WNMG 060412 NGU** | 1,2 | ● | ● | ● | ○ | ● | ○ | | ● | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **WNMG 080404 NGU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | | ○ | ○ | | | ○ | | | | |
| | | **WNMG 080408 NGU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | ○ | | | | |
| | | **WNMG 080412 NGU** | 1,2 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **WNMG 060408 NGU-W** | 0,8 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080408 NGU-W** | 0,8 | ● | ● | ● | | | | | ● | ● | | | | | | | | | | | | | | | | | |
| | | **WNMG 080412 NGU-W** | 1,2 | ● | ● | ● | | | | | ● | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# W TRIGON TYPE
## INSERTS FOR TURNING

**80° Trigon Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WN_ _ | L | IC | S | $D_1$ |
| 0604.. | 6,5 | 9,525 | 4,76 | 3,81 |
| 06T3.. | 6,5 | 9,525 | 3,97 | 3,81 |
| 0804.. | 8,7 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |









⇨ D17, D24 D42 ⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## WNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Medium Cut |  NGE | **WNMG 060408 NGE** | 0,8 | ● | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 060412 NGE** | 1,2 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080404 NGE** | 0,4 | ○ | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080408 NGE** | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080412 NGE** | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080416 NGE** | 1,6 | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NUG | **WNMG 060404 NUG** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 060408 NUG** | 0,8 | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 06T304 NUG** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 06T308 NUG** | 0,8 | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080404 NUG** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080408 NUG** | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080412 NUG** | 1,2 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| Medium Cut |  NEG | **WNMG 060408 NEG** | 0,8 | ○ | ● | ● | ○ | ○ | ○ | ○ | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **WNMG 060412 NEG** | 1,2 | ○ | ○ | ○ | | ○ | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **WNMG 080404 NEG** | 0,4 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **WNMG 080408 NEG** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | ● | ● | |
| | | **WNMG 080412 NEG** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | ● | | |
| Medium Cut |  NEX | **WNMG 060404 NEX** | 0,4 | | | | | ● | | | ● | | | | | | ● | ● | | | | | | | | | | |
| | | **WNMG 060408 NEX** | 0,8 | | | | | ● | | | ● | | | | | | ● | ● | | | | | | | | | | |
| | | **WNMG 080404 NEX** | 0,4 | | | | | ● | ● | ● | ● | | | | | ● | ● | ○ | | | | | | | | | | |
| | | **WNMG 080408 NEX** | 0,8 | | | | | ● | ● | ● | ● | | | | | ● | ● | ● | | ○ | | | | | | | | |
| | | **WNMG 080412 NEX** | 1,2 | | | | | ● | ● | ● | ● | | | | | ○ | ○ | ● | | | | | | | | | | |
| Medium Cut |  NUP | **WNMG 080408 NUP** | 0,8 | | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | | | | | | | | | |
| | | **WNMG 080412 NUP** | 1,2 | | ● | ● | | | ● | ● | ● | | | | | ○ | ○ | ○ | | | | | | | | | | |
| Medium Cut |  NEM | **WNMG 080408 NEM** | 0,8 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **WNMG 080412 NEM** | 1,2 | ○ | ● | ● | ○ | ● | ● | ● | | | | | | ○ | ○ | ○ | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# W TRIGON TYPE
## INSERTS FOR TURNING

**80° Trigon Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WN_ _ | L | IC | S | $D_1$ |
| 0604.. | 6,5 | 9,525 | 4,76 | 3,81 |
| 0804.. | 8,7 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |









⇨ D17, D24 D42 ⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# WNMG ●●●●●● ■-■■


● M-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | Carbide Coated P **AC8020P** | Carbide Coated P AC8025P | Carbide Coated P AC8035P | Carbide Coated M AC6020M | Carbide Coated M AC6030M | Carbide Coated M AC6040M | Carbide Coated P/M AC630M | Carbide Coated K AC4010K | Carbide Coated K AC4015K | Carbide Coated K AC420K | Carbide Coated H AC503U | Carbide Coated S **AC5005S** | Carbide Coated S AC5015S | Carbide Coated S AC5025S | Carbide Coated P/M AC1030U | Carbide Coated P/M AC530U | Cermet Coated P T1500Z | Cermet Coated P **T2500Z** | Cermet Coated P T3000Z | Cermet Uncoated P T1000A | Cermet Uncoated P T1500A | Carbide Uncoated K G10E | Carbide Uncoated S EH510 | Carbide Uncoated S EH520 | Carbide Uncoated N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Roughing |  NUX | **WNMG 080404 NUX** | 0,4 | ○ | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080408 NUX** | 0,8 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080412 NUX** | 1,2 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NMU | **WNMG 060408 NMU** | 0,8 | ● | | ○ | ● | ● | | | | | | | | | | ● | ● | | | | | | | | | | |
| | | **WNMG 060412 NMU** | 1,2 | ● | | | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080408 NMU** | 0,8 | ● | ● | ● | ● | ● | ● | | ● | | | | | ○ | ○ | ● | | ○ | | | | | | | | | |
| | | **WNMG 080412 NMU** | 1,2 | ● | ● | ● | ● | ● | ● | | ● | | | | | ○ | ○ | ● | | ○ | | | | | | | | | |
| | | **WNMG 080416 NMU** | 1,6 | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NME | **WNMG 060408 NME** | 0,8 | ○ | ○ | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **WNMG 060412 NME** | 1,2 | ○ | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **WNMG 080408 NME** | 0,8 | ● | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **WNMG 080412 NME** | 1,2 | ● | ● | ● | ● | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **WNMG 080416 NME** | 1,6 | ● | ● | ● | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| Roughing |  NMX | **WNMG 080408 NMX** | 0,8 | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **WNMG 080412 NMX** | 1,2 | | ○ | ○ | ● | | | | | | | | | | | | | | | | | | | | | | |
| Roughing |  NGZ | **WNMG 060408 NGZ** | 0,8 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | |
| | | **WNMG 060412 NGZ** | 1,2 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **WNMG 080404 NGZ** | 0,4 | | | | | | | | | ○ | ○ | ● | | | | | | | | | | | | | | | |
| | | **WNMG 080408 NGZ** | 0,8 | | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | |
| | | **WNMG 080412 NGZ** | 1,2 | | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | |
| Roughing |  NUZ | **WNMG 080404 NUZ** | 0,4 | | | ○ | | | | | | ○ | ○ | ● | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **WNMG 080408 NUZ** | 0,8 | | | ○ | ○ | | | | | ○ | ● | ● | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **WNMG 080412 NUZ** | 1,2 | | | ○ | ○ | | | | | ● | ○ | ● | | ○ | ○ | ○ | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

# W TRIGON TYPE
INSERTS FOR TURNING

**80° Trigon Type** | 0° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WN_ _ | L | IC | S | $D_1$ |
| 0804.. | 8,7 | 12,7 | 4,76 | 5,16 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |





⇨ D17, D24 ⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## WNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | M | | | PM | K | | | H | S | | | | PM | Cermet Coated P | | | | | Carbide Uncoated K | S | | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Heavy Roughing |  NMP | **WNMM 080408 NMP** | 0,8 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **WNMM 080412 NMP** | 1,2 | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | | |
| Heavy Roughing |  NHG | **WNMM 080408 NHG** | 0,8 | | | | | | | | ● | | | | | | | | | | | | | | | | | | |
| | | **WNMM 080412 NHG** | 1,2 | ● | | | | | | | ● | | | | | | | | | | | | | | | | | | |


## WNMA ●●●●●●

● M-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | M | | | PM | K | | | H | S | | | | PM | Cermet Coated P | | | | | Carbide Uncoated K | S | | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  | **WNMA 080408** | 0,8 | | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | |
| | | **WNMA 080412** | 1,2 | | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | |
| | | **WNMA 080416** | 1,6 | | | | | | | | | ○ | ● | ● | | | | | | | | | | | | | | | |

## WNGG ●●●●●● ■-■■


● G-Class Double Sided Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | M | | | PM | K | | | H | S | | | | PM | Cermet Coated P | | | | | Carbide Uncoated K | S | | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NSU | **WNGG 080404 NSU** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |


● = Euro stock
○ = Stock item in Japan

# C DIAMOND TYPE
INSERTS FOR TURNING

**80° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CC_ _ | L | IC | S | $D_1$ |
| 03X1.. | 3,55 | 3,5 | 1,4 | 1,9 |
| 04X1.. | 4,37 | 4,3 | 1,8 | 2,3 |
| 0602.. | 6,4 | 6,35 | 2,38 | 2,8 |
| 09T3.. | 9,7 | 9,525 | 3,97 | 4,4 |
| | | | | |
| | | | | |




⇨ D31 ⇨ E14

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## CCET ●●●●●● ●-■■

● E-Class


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  L/RFY | **CCET 03X1003 LFY** | 0,03 | | | | | | | | | | | | | | | | | ○ | | | | ○ | ○ | | | | |
| | | **CCET 03X101 LFY** | 0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **CCET 03X102 LFY** | 0,2 | | | | | | | | | | | | | | | | | ○ | | | | ○ | ○ | | | | |
| | | **CCET 03X104 LFY** | 0,4 | | | | | | | | | | | | | | | | | ○ | | | | ○ | ○ | | | | |
| | | **CCET 04X1003 LFY** | 0,03 | | | | | | | | | | | | | | | | | ○ | | | | ○ | ○ | | | | |
| | | **CCET 04X101 LFY** | 0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **CCET 04X102 LFY** | 0,2 | | | | | | | | | | | | | | | | | ○ | | | | ○ | ○ | | | | |
| | | **CCET 04X104 LFY** | 0,4 | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | | |
| | | **CCET 060201 LFY** | 0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 060202 LFY** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 09T301 LFY** | 0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 09T302 LFY** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 03X1003 RFY** | 0,03 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 03X101 RFY** | 0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 03X102 RFY** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 03X104 RFY** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 04X1003 RFY** | 0,03 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 04X101 RFY** | 0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 04X102 RFY** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 04X104 RFY** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 060201 RFY** | 0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 060202 RFY** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 09T301 RFY** | 0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **CCET 09T302 RFY** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |



● = Euro stock
○ = Japan stock

80° Diamond Type | 7° Relief | With Insert Hole

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CC__ | L | IC | S | $D_1$ |
| 03X1.. | 3,55 | 3,5 | 1,4 | 1,9 |
| 04X1.. | 4,37 | 4,3 | 1,8 | 2,3 |
| 0602.. | 6,4 | 6,35 | 2,38 | 2,8 |
| 09T3.. | 9,7 | 9,525 | 3,97 | 4,4 |
| | | | | |
| | | | | |









➪ D31 ➪ E14

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# CCGT ●●●●●● ●-■■

● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | AC8020P | AC8025P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NFC | **CCGT 060201M NFC** | <0,1 | | | | | | | | | | | | | | | ● | ● | | | | ❍ | ❍ | | | | |
| | | **CCGT 060202M NFC** | <0,2 | | | | | | | | | | | | | | | ● | ● | | | | ❍ | ❍ | | | | |
| | | **CCGT 060204M NFC** | <0,4 | | | | | | | | | | | | | | | ● | ● | | | | ❍ | ❍ | | | | |
| | | **CCGT 09T301M NFC** | <0,1 | | | | | | | | | | | | | | | ● | ● | | | | ❍ | ❍ | | | | |
| | | **CCGT 09T302M NFC** | <0,2 | | | | | | | | | | | | | | | ● | ● | | | | ❍ | | | | | |
| | | **CCGT 09T304M NFC** | <0,4 | | | | | | | | | | | | | | | ● | ● | | | | ❍ | ❍ | | | | |
| Finishing |  L/R**FX** | **CCGT 0602003 LFX** | 0,03 | | | | | | | | | | | | | | | ❍ | ❍ | | | | ❍ | | | | | |
| | | **CCGT 060201 LFX** | 0,1 | | | | | | | | | | | | | | | ❍ | ❍ | ● | | | | ● | | | | |
| | | **CCGT 060202 LFX** | 0,2 | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **CCGT 060204 LFX** | 0,4 | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **CCGT 09T3003 LFX** | 0,03 | | | | | | | | | | | | | | | ❍ | ❍ | | | | | | | | | |
| | | **CCGT 09T301 LFX** | 0,1 | | | | | | | | | | | | | | | ❍ | ❍ | ● | | | | ❍ | | | | |
| | | **CCGT 09T302 LFX** | 0,2 | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **CCGT 09T304 LFX** | 0,4 | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **CCGT 09T308 LFX** | 0,8 | | | | | | | | | | | | | | | ❍ | ❍ | | | | | | | | | |
| | | **CCGT 0602003 RFX** | 0,03 | | | | | | | | | | | | | | | ❍ | ❍ | | | | ❍ | | | | | |
| | | **CCGT 060201 RFX** | 0,1 | | | | | | | | | | | | | | | ❍ | ❍ | | | | | ❍ | | | | |
| | | **CCGT 060202 RFX** | 0,2 | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **CCGT 060204 RFX** | 0,4 | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **CCGT 09T3003 RFX** | 0,03 | | | | | | | | | | | | | | | ● | ❍ | | | | | | | | | |
| | | **CCGT 09T301 RFX** | 0,1 | | | | | | | | | | | | | | | ● | ● | ● | | | | ● | | | | |
| | | **CCGT 09T302 RFX** | 0,2 | | | | | | | | | | | | | | | ● | ● | ● | | | ❍ | ● | | | | |
| | | **CCGT 09T304 RFX** | 0,4 | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **CCGT 09T308 RFX** | 0,8 | | | | | | | | | | | | | | | ❍ | ❍ | | | | | | | | | |
| Finishing |  L/R**FYS** | **CCGT 03X1003 LFYS** | 0,03 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 03X101 LFYS** | 0,1 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 03X102 LFYS** | 0,2 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 03X104 LFYS** | 0,4 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 04X1003 LFYS** | 0,03 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 04X101 LFYS** | 0,1 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 04X102 LFYS** | 0,2 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 04X104 LFYS** | 0,4 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 03X1003 RFYS** | 0,03 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 03X101 RFYS** | 0,1 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 03X102 RFYS** | 0,2 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 03X104 RFYS** | 0,4 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 04X1003 RFYS** | 0,03 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 04X101 RFYS** | 0,1 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 04X102 RFYS** | 0,2 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | | **CCGT 04X104 RFYS** | 0,4 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |












● = Euro stock
❍ = Japan stock

# C DIAMOND TYPE
INSERTS FOR TURNING

**80° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CC_ _ | L | IC | S | $D_1$ |
| 03X1.. | 3,55 | 3,5 | 1,4 | 1,9 |
| 04X1.. | 4,37 | 4,3 | 1,8 | 2,3 |
| 0602.. | 6,4 | 6,35 | 2,38 | 2,8 |
| 0903.. | 9,7 | 9,525 | 3,18 | 4,4 |
| 09T3.. | 9,7 | 9,525 | 3,97 | 4,4 |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,5 |








➪ E14

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## CCGT ●●●●●● ●-■■

● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | AC8020P | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC515S | AC525S | AC1030U | AC530U | T150Z | T250Z | T300Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  L/RFY | CCGT 03X101 LFY | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | CCGT 03X102 LFY | 0,2 | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | | | |
| | | CCGT 03X104 LFY | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | CCGT 04X101 LFY | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | CCGT 04X102 LFY | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | CCGT 04X104 LFY | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | CCGT 03X101 RFY | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | CCGT 03X102 RFY | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | CCGT 03X104 RFY | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | CCGT 04X101 RFY | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | ○ | | | | | |
| | | CCGT 04X102 RFY | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | ○ | | | | | |
| | | CCGT 04X104 RFY | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| Light Cut |  NAG | CCGT 060202 NAG | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | CCGT 060204 NAG | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | CCGT 09T302 NAG | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | CCGT 09T304 NAG | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | CCGT 09T308 NAG | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | CCGT 120404 NAG | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | CCGT 120408 NAG | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| Light cut |  NSI | CCGT 09T301M NSI | <0,1 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | ○ | ○ | | | | |
| | | CCGT 09T302M NSI | <0,2 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | ○ | ○ | | | | |
| | | CCGT 09T304M NSI | <0,4 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | ○ | ○ | | | | |
| Light cut |  NSC | CCGT 0602003 NSC | 0,03 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | | | | |
| | | CCGT 09T3003 NSC | 0,03 | | | | | | | | | | | | | | | | ● | ○ | ○ | | | ○ | ○ | | | | |
| | | CCGT 060201M NSC | <0,1 | | | | | | | | | | | | | | | | ○ | ○ | ● | ○ | | | ● | | | | |
| | | CCGT 060202M NSC | <0,2 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | ● | ● | | | | |
| | | CCGT 060204M NSC | <0,4 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | | ● | | | | |
| | | CCGT 080201M NSC | <0,1 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | CCGT 080202M NSC | <0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | CCGT 090301M NSC | <0,1 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | CCGT 090302M NSC | <0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | CCGT 09T301M NSC | <0,1 | | | | | | | | | | | | | | | | ● | ○ | ● | ○ | | | ● | | | | |
| | | CCGT 09T302M NSC | <0,2 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | ● | ● | | | | |
| | | CCGT 09T304M NSC | <0,4 | | | | | | | | | | | | | | | | ● | ● | ● | | | | ● | | | | |
| | | CCGT 09T308M NSC | <0,8 | | | | | | | | | | | | | | | | ● | ● | ● | | | | ● | | | | |
| For Aluminum |  L/RAY | CCGT 060202 LAY | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 060204 LAY | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 09T301 LAY | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 09T302 LAY | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 09T304 LAY | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 060201 RAY | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 060202 RAY | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 060204 RAY | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 09T301 RAY | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 09T302 RAY | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | CCGT 09T304 RAY | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Japan stock

80° Diamond Type | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CC__ | L | IC | S | $D_1$ |
| 0602.. | 6,4 | 6,35 | 2,38 | 2,8 |
| 09T3.. | 9,7 | 9,525 | 3,97 | 4,4 |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,5 |
| | | | | |
| | | | | |
| | | | | |










➪ D31 ➪ E14

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# CCMT ●●●●●● ●-■■


● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NFB | **CCMT 060202 NFB** | 0,2 | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | ● | | | | |
| |  | **CCMT 060204 NFB** | 0,4 | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | ● | | | | |
| | | **CCMT 09T302 NFB** | 0,2 | | | | | | | | | | | | | | | | ○ | | ● | | | ○ | | | | |
| | | **CCMT 09T304 NFB** | 0,4 | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | ● | | | | |
| | | **CCMT 09T308 NFB** | 0,8 | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | | | | | |
| Finishing – Light Cut |  NFP | **CCMT 060202 NFP** | 0,2 | | | | | | | | | | | | | | | | | ● | ● | | ● | ● | ● | | | | |
| |  | **CCMT 060204 NFP** | 0,4 | | | | | | | | | | | | | | | | | ● | ● | | ● | ● | ● | | | | |
| | | **CCMT 060208 NFP** | 0,8 | ● | | | | | | | | | | | | | | | | ● | ● | | ● | ● | ● | | | | |
| | | **CCMT 09T302 NFP** | 0,2 | | | | | | | | | | | | | | | | | | ● | | ● | ● | ● | | | | |
| | | **CCMT 09T304 NFP** | 0,4 | | | | | | | | | | | | | | | | | ● | ● | | ● | ● | ● | | | | |
| | | **CCMT 09T308 NFP** | 0,8 | | | | | | | | | | | | | | | | | | ● | | ● | ● | ● | | | | |
| | | **CCMT 120404 NFP** | 0,4 | | | | | | | | | | | | | | | | | | ● | | | | ● | | | | |
| | | **CCMT 120408 NFP** | 0,8 | | | | | | | | | | | | | | | | | | ● | | | | ● | | | | |
| Finishing |  NLU | **CCMT 060202 NLU** | 0,2 | | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | ● | ○ | ○ | ● | ○ | ○ | | | | |
| |  | **CCMT 060204 NLU** | 0,4 | | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | ● | ○ | ● | ● | ○ | ○ | | | | |
| | | **CCMT 09T302 NLU** | 0,2 | | | | | ● | | | | | | | | | | | | ● | | | ● | | | | | | |
| | | **CCMT 09T304 NLU** | 0,4 | | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | ● | ○ | ● | ● | ○ | ○ | | | | |
| | | **CCMT 09T308 NLU** | 0,8 | | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | ● | ○ | ○ | ● | ○ | ○ | | | | |
| |  NLU-W | **CCMT 09T304 NLU-W** | 0,4 | | ● | ● | ● | ● | | | ● | | | | | | | | | ● | ● | ● | ● | | ○ | | | | |
| |  | **CCMT 09T308 NLU-W** | 0,8 | | ● | ● | ● | ● | | | ● | | | | | | | | | ● | ● | ● | ● | | ○ | | | | |
| Light Cut |  NLB | **CCMT 060202 NLB** | 0,2 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| |  | **CCMT 060204 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ● | ● | | ● | | | | |
| | | **CCMT 060208 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ● | ○ | | | | | | | | | | | ● | ○ | | | | | | | |
| | | **CCMT 09T302 NLB** | 0,2 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| | | **CCMT 09T304 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ● | ● | | ● | | | | |
| | | **CCMT 09T308 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| Light Cut |  NSU | **CCMT 060202 NSU** | 0,2 | | ● | ● | ● | ● | ● | ● | ● | | | | | ○ | ● | ● | | ● | ● | ● | ● | ● | ● | | | | |
| |  | **CCMT 060204 NSU** | 0,4 | | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ● | ● | ● | ● | ● | ● | | | | |
| | | **CCMT 060208 NSU** | 0,8 | | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ○ | ○ | | ● | ● | ● | ● | ● | ● | | | | |
| | | **CCMT 09T302 NSU** | 0,2 | | ○ | ● | ● | ○ | ● | ● | ● | ○ | | | | ○ | | | | ● | ● | ○ | ● | ● | ● | | | | |
| | | **CCMT 09T304 NSU** | 0,4 | | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ● | ● | ● | ● | ● | ● | | | | |
| | | **CCMT 09T308 NSU** | 0,8 | | ● | ● | ● | ● | ● | ● | ● | ● | | | | ● | ● | ● | | ● | ● | ● | ● | ● | ● | | | | |
| | | **CCMT 120404 NSU** | 0,4 | | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | ● | | | | | | | | | |
| | | **CCMT 120408 NSU** | 0,8 | | ● | ● | ● | ● | ● | | ● | | | | | ● | ○ | ○ | | ● | | | | | | | | | |


● = Euro stock
○ = Japan stock

# C DIAMOND TYPE
INSERTS FOR TURNING

**80° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| C_ _ _ | L | IC | S | $D_1$ |
| 0602.. | 6,4 | 6,35 | 2,38 | 2,8 |
| 0803.. | 8,0 | 7,94 | 3,18 | 3,4 |
| 0903.. | 9,7 | 9,525 | 3,18 | 4,4 |
| 09T3.. | 9,7 | 9,525 | 3,97 | 4,4 |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,5 |
| | | | | |









⇨ E15

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## CCMT/-W ●●●●●● ●-■■

● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | AC8020P | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | T2500Z | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Light Cut |  NUS | CCMT 09T308 NUS | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Light Cut |  NSC | CCMT 060204 NSC | 0,4 | | | ❍ | | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 080304 NSC | 0,4 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 090308 NSC | 0,8 | | | ❍ | | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 120408 NSC | 0,8 | | | ❍ | | | | | | | | | | | | | | | | | | | | | | | | |
| Light Cut |  NSK | CCMT 060204 NSK | 0,4 | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 060208 NSK | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 09T304 NSK | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 09T308 NSK | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 120404 NSK | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 120408 NSK | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | CCMT 120412 NSK | 1,2 | | | | | | | | | | ● | | | | | | | | | | | | | | | | | |
| Roughing – Light Cut |  NGU | CCMT 060204 NGU New | 0,4 | ● | ● | ● | ● | ● | ● | ● | | | ● | | | | ● | ❍ | | | ● | ❍ | | | ❍ | | | | | |
| | | CCMT 060208 NGU New | 0,8 | ● | ● | ● | ❍ | ❍ | ● | ● | | | | | | | | ❍ | | | ❍ | ❍ | | | ❍ | | | | | |
| | | CCMT 09T304 NGU New | 0,4 | ● | ● | ● | ● | ● | ● | ● | | | | | | | ● | ● | | | ● | ● | | | ❍ | | | | | |
| | | CCMT 09T308 NGU New | 0,8 | ● | ● | ● | ● | ● | ● | ● | | ● | ● | | | | | ● | | | ● | ❍ | | | ❍ | | | | | |
| | | CCMT 120408 NGU New | 0,8 | ● | ● | ● | ● | ● | ● | | | ● | ● | | | | | | | | | | | | | | | | | |
| Roughing |  NMU | CCMT 09T304 NMU | 0,4 | ● | ● | ● | ● | ● | ● | | ● | ❍ | ● | ● | | | | | | | | | | | | | | | | |
| | | CCMT 09T308 NMU | 0,8 | ● | ● | ● | ● | ● | ● | | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| Roughing |  | CCMW 060204 | 0,4 | | | | | | | | | ❍ | ❍ | ❍ | | | | | | | | | | | | | | | | |
| | | CCMW 09T304 | 0,4 | | | | | | | | | ❍ | ❍ | ❍ | | | | | | | | | | | | | | | | |
| | | CCMW 09T308 | 0,8 | | | | | | | | | ❍ | ● | ❍ | | | | | | | | | | | | | | | | |

● = Euro stock
❍ = Japan stock

**80° Diamond Type** | 11° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CP_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,0 | 7,94 | 2,38 | 3,4 |
| 0903.. | 9,7 | 9,525 | 3,18 | 4,4 |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,5 |
| | | | | |
| | | | | |
| | | | | |




➪ E15

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel





## CPGT ●●●●●● NSD

● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing ~ Light Cut |  NSD | **CPGT 080202 NSD** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | | | | ● | ● | | | | |
| | | **CPGT 080204 NSD** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | ● | | ○ | ● | ● | | | | |
| | | **CPGT 080208 NSD** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | ○ | | ○ | ○ | ○ | | | | |
| | | **CPGT 090302 NSD** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | | | | ○ | ○ | | | | |
| | | **CPGT 090304 NSD** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | ○ | | ○ | ● | ● | | | | |
| | | **CPGT 090308 NSD** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | ○ | | ○ | ○ | ○ | | | | |
| | | **CPGT 120402 NSD** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | | | | ○ | ○ | | | | |
| | | **CPGT 120404 NSD** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | ○ | ○ | | | | |
| | | **CPGT 120408 NSD** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | ○ | ○ | | | | |

## CPMT ●●●●●● ●-■■


● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NFB | **CPMT 080204 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| | | **CPMT 090304 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| | | **CPMT 090308 NFB** | 0,8 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| Finishing |  NLU | **CPMT 080204 NLU** | 0,4 | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **CPMT 090304 NLU** | 0,4 | ○ | ○ | ○ | | | ○ | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **CPMT 090308 NLU** | 0,8 | ○ | ○ | ○ | | | ○ | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| |  NLU-W | **CPMT 090304 NLU-W** | 0,4 | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **CPMT 090308 NLU-W** | 0,8 | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| Light Cut |  NLB | **CPMT 080204 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **CPMT 090304 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ● | ○ | | | | | | | | | | | ○ | ○ | ○ | | | | | | |
| | | **CPMT 090308 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ● | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |

● = Euro stock
○ = Japan stock

# C DIAMOND TYPE
INSERTS FOR TURNING

**80° Diamond Type** | 11° Relief With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CP_ _ | L | IC | S | $D_1$ |
| 0602.. | 6,4 | 6,35 | 2,38 | 2,8 |
| 0802.. | 8,0 | 7,94 | 2,38 | 3,4 |
| 0903.. | 9,7 | 9,525 | 3,18 | 4,4 |
| 09T3.. | 9,7 | 9,525 | 3,97 | 4,4 |
| 1204.. | 12,9 | 12,7 | 4,76 | 5,5 |
| 1604.. | 16,1 | 15,875 | 4,76 | 6,5 |







⇨ E15

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## CPMT/-H ●●●●●● ●-■■

● M-Class


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated M | Carbide Coated M | Carbide Coated P/M | Carbide Coated K | Carbide Coated K | Carbide Coated K | Carbide Coated H | Carbide Coated S | Carbide Coated S | Carbide Coated S | Carbide Coated P/M | Carbide Coated P/M | Cermet Coated P | Cermet Coated P | Cermet Coated P | Cermet Coated P | Cermet Coated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | AC8020P | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T150Z | T250Z | T300Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Light Cut |  NSU | **CPMT 080204 NSU** | 0,4 | ○ | ○ | ○ | ○ | | | | ○ | | | | | ○ | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **CPMT 080208 NSU** | 0,8 | ○ | ○ | ○ | ○ | | | | ○ | | | | | ○ | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **CPMT 090304 NSU** | 0,4 | ○ | ○ | ○ | ○ | ○ | ○ | | ○ | | | | | ○ | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **CPMT 090308 NSU** | 0,8 | ○ | ● | ● | ○ | ○ | ○ | | ○ | | | | | ○ | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| Light Cut |  NUS | **CPMT 060204 NUS** | 0,4 | | | | ● | | | | ○ | | | | | | | | | | | | | | | ○ | | | |
| | | **CPMT 080308 NUS** | 0,8 | | | | ● | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **CPMT 09T308 NUS** | 0,8 | | | | ● | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **CPMH 120408 NUS** | 0,8 | | | | ● | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **CPMH 160408 NUS** | 0,8 | | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| Light–Medium Cut |  NGU | **CPMT 090304 NGU** New | 0,4 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **CPMT 090308 NGU** New | 0,8 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| Light–Medium Cut |  NMU | **CPMT 080204 NMU** | 0,4 | ○ | ○ | ○ | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **CPMT 080208 NMU** | 0,8 | ○ | ○ | ○ | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **CPMT 090304 NMU** | 0,4 | ○ | ○ | ○ | | ○ | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **CPMT 090308 NMU** | 0,8 | ○ | ○ | ○ | | ○ | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

**55° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DC__ | L | IC | S | $D_1$ |
| 0702.. | 7,7 | 6,35 | 2,38 | 2,8 |
| 11T3.. | 11,6 | 9,525 | 3,97 | 4,4 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |







➪ D32–33 ➪ E16–17


- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## DCGT ●●●●●● ●-■■


● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |   NFC | **DCGT 070201M NFC** | <0,1 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | ○ | ○ | | | | |
| | | **DCGT 070202M NFC** | <0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | | ○ | | | | |
| | | **DCGT 070204M NFC** | <0,4 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | ○ | ○ | | | | |
| | | **DCGT 11T301M NFC** | <0,1 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | ○ | ○ | | | | |
| | | **DCGT 11T302M NFC** | <0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | ○ | ○ | | | | |
| | | **DCGT 11T304M NFC** | <0,4 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | ○ | ○ | | | | |
| Finishing |   L/R**FX** | **DCGT 0702003 LFX** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **DCGT 070201 LFX** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | | ○ | | | | |
| | | **DCGT 070202 LFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | ● | ● | | | | |
| | | **DCGT 070204 LFX** | 0,4 | | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **DCGT 11T3003 LFX** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **DCGT 11T301 LFX** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | | ● | | | | |
| | | **DCGT 11T302 LFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ● | ● | | | ● | ● | | | | |
| | | **DCGT 11T304 LFX** | 0,4 | | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **DCGT 0702003 RFX** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **DCGT 070201 RFX** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | ● | ● | | | | |
| | | **DCGT 070202 RFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ● | ● | | | | ● | | | | |
| | | **DCGT 070204 RFX** | 0,4 | | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| | | **DCGT 11T3003 RFX** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **DCGT 11T301 RFX** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ● | ● | ● | | | ● | ● | | | | |
| | | **DCGT 11T302 RFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ● | ● | | | ● | ● | | | | |
| | | **DCGT 11T304 RFX** | 0,4 | | | | | | | | | | | | | | | | ● | ● | ● | | | ● | ● | | | | |
| Finishing |   L/R**FYS** | **DCGT 0702003 LFYS** | 0,03 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 070201 LFYS** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 070202 LFYS** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 070204 LFYS** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 11T3003 LFYS** | 0,03 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 11T301 LFYS** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 11T302 LFYS** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 11T304 LFYS** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 0702003 RFYS** | 0,03 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 070201 RFYS** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 070202 RFYS** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 070204 RFYS** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 11T3003 RFYS** | 0,03 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 11T301 RFYS** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 11T302 RFYS** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **DCGT 11T304 RFYS** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |


● = Euro stock
○ = Japan stock

# D DIAMOND TYPE
INSERTS FOR TURNING

**55° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DC_ _ | L | IC | S | $D_1$ |
| 0702.. | 7,7 | 6,35 | 2,38 | 2,8 |
| 11T3.. | 11,6 | 9,525 | 3,97 | 4,4 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |







⇨ D32–33 ⇨ E16–17

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## DCGT ●●●●●● ●-■■

● G-Class


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | Carbide Coated P **AC8020P** | Carbide Coated P AC8025P | Carbide Coated P AC8035P | Carbide Coated M AC6020M | Carbide Coated M AC6030M | Carbide Coated M AC6040M | Carbide Coated P/M AC630M | Carbide Coated K AC4010K | Carbide Coated K AC4015K | Carbide Coated K AC420K | Carbide Coated H AC503U | Carbide Coated S **AC5005S** | Carbide Coated S AC5015S | Carbide Coated S AC5025S | Carbide Coated P/M AC1030U | Carbide Coated P/M AC530U | Cermet Coated P T150Z | Cermet Coated P **T250Z** | Cermet Coated P T300Z | Cermet Uncoated P T1000A | Cermet Uncoated P T1500A | Carbide Uncoated K G10E | Carbide Uncoated S EH510 | Carbide Uncoated S EH520 | Carbide Uncoated N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  LFY | **DCGT 0702003 LFY** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 070201 LFY** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 070202 LFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 070204 LFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 11T3003 LFY** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 11T301 LFY** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 11T302 LFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **DCGT 11T304 LFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | ● | ○ | | | | |
| Finishing |  RFY | **DCGT 0702003 RFY** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 070201 RFY** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 070202 RFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 070204 RFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **DCGT 11T3003 RFY** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **DCGT 11T301 RFY** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **DCGT 11T302 RFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | ○ | | | | |
| | | **DCGT 11T304 RFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | ● | ○ | | | | |
| Finishing ~ Light Cut |  L/RSD | **DCGT 070202 LSD** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **DCGT 070204 LSD** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **DCGT 11T304 LSD** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **DCGT 11T308 LSD** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **DCGT 070202 RSD** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **DCGT 070204 RSD** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | | | | | |
| | | **DCGT 11T304 RSD** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **DCGT 11T308 RSD** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| Light Cut |  NAG | **DCGT 070202 NAG** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **DCGT 070204 NAG** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **DCGT 11T302 NAG** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **DCGT 11T304 NAG** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **DCGT 11T308 NAG** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |

● = Euro stock
○ = Japan stock

**55° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DC__ | L | IC | S | $D_1$ |
| 0702.. | 7,7 | 6,35 | 2,38 | 2,8 |
| 0902.. | 9,7 | 7,94 | 2,38 | 3,4 |
| 1103.. | 11,6 | 9,525 | 3,18 | 4,4 |
| 11T3.. | 11,6 | 9,525 | 3,97 | 4,4 |
| | | | | |
| | | | | |







➪ D32–33 ➪ E16–17

P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

# DCGT/-W ●●●●●● ●-■■


● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Light Cut |  NSI | **DCGT 070201M NSI** | <0,1 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | ○ | ○ | | | | |
| | | **DCGT 070202M NSI** | <0,2 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | ○ | ○ | | | | |
| | | **DCGT 070204M NSI** | <0,4 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | ○ | ○ | | | | |
| | | **DCGT 11T301M NSI** | <0,1 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | | ○ | | | | |
| | | **DCGT 11T302M NSI** | <0,2 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | ○ | ○ | | | | |
| | | **DCGT 11T304M NSI** | <0,4 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | ○ | ○ | | | | |
| | | **DCGT 11T308M NSI** | <0,8 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ○ | | | | | | | |
| Light cut |  NSC | **DCGT 0702003 NSC** | 0,03 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **DCGT 11T3003 NSC** | 0,03 | | | | | | | | | | | | | | | | ○ | ○ | ● | | | ○ | ○ | | | | |
| | | **DCGT 070201M NSC** | <0,1 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | ○ | ● | | | | |
| | | **DCGT 070202M NSC** | <0,2 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | | ● | | | | |
| | | **DCGT 070204M NSC** | <0,4 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | ● | ● | | | | |
| | | **DCGT 090201M NSC** | <0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DCGT 090202M NSC** | <0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DCGT 110301M NSC** | <0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **DCGT 110302M NSC** | <0,2 | | | | | | | | | | | | | | | | | | | | | ● | ● | | | | |
| | | **DCGT 11T301M NSC** | <0,1 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | ○ | ● | | | | |
| | | **DCGT 11T302M NSC** | <0,2 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | ● | ● | | | | |
| | | **DCGT 11T304M NSC** | <0,4 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | ● | ● | | | | |
| | | **DCGT 11T308M NSC** | <0,8 | | | | | | | | | | | | | | | | ● | ● | ● | ○ | | ● | ● | | | | |
| For Aluminum |  L/RAY | **DCGT 11T301 LAY** | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | ○ | ○ |
| | | **DCGT 11T302 LAY** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ | ○ |
| | | **DCGT 11T304 LAY** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ | ○ |
| | | **DCGT 070202 RAY** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ | ○ |
| | | **DCGT 070204 RAY** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ | ○ |
| | | **DCGT 11T301 RAY** | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | ○ | ○ |
| | | **DCGT 11T302 RAY** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ | ○ |
| | | **DCGT 11T304 RAY** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ | ○ |
| Light Cut |  | **DCGW 070202** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **DCGW 070204** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **DCGW 070208** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **DCGW 11T302** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **DCGW 11T304** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **DCGW 11T308** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |


● = Euro stock
○ = Japan stock

# D DIAMOND TYPE
INSERTS FOR TURNING

**55° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DC_ _ | L | IC | S | $D_1$ |
| 0702.. | 7,7 | 6,35 | 2,38 | 2,8 |
| 11T3.. | 11,6 | 9,525 | 3,97 | 4,4 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |



⇨ D32–33 ⇨ E16–17

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## DCM_ ●●●●●● ●-■■

● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | AC8020P | AC8025P | AC8035P | M AC6020M | AC6030M | AC6040M | PM AC630M | K AC4010K | AC4015K | AC420K | H AC503U | S AC5005S | AC5015S | AC5025S | PM AC1030U | AC530U | Cermet Coated P T150Z | T250Z | T300Z | Uncoated T1000A | T1500A | Carbide Uncoated K G10E | S EH510 | EH520 | N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing | NFB | DCMT 070202 NFB | 0,2 | | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | | | | |
| | | DCMT 070204 NFB | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | | | | |
| | | DCMT 070208 NFB | 0,8 | | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | | | | |
| | | DCMT 11T302 NFB | 0,2 | | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | | | | |
| | | DCMT 11T304 NFB | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | | | | |
| | | DCMT 11T308 NFB | 0,8 | | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | | | | |
| Finishing | NFP | DCMT 070202 NFP | 0,2 | | | | | | | | | | | | | | | | | ● | ● | | ● | | ● | | | | |
| | | DCMT 070204 NFP | 0,4 | | | | | | | | | | | | | | | | | ● | ● | | ● | ● | ● | | | | |
| | | DCMT 11T302 NFP | 0,2 | | | | | | | | | | | | | | | | | ● | ● | | ● | | ● | | | | |
| | | DCMT 11T304 NFP | 0,4 | | | | | | | | | | | | | | | | | ● | ● | | ● | ● | ● | | | | |
| | | DCMT 11T308 NFP | 0,8 | | | | | | | | | | | | | | | | | ● | ● | | ● | ● | ● | | | | |
| | | DCMT 11T312 NFP | 1,2 | | | | | | | | | | | | | | | | | | ● | | ● | | ● | | | | |
| Finishing | NLU | DCMT 070202 NLU | 0,2 | ● | ○ | ○ | | | ● | ● | ● | | | | | | | | | ● | ○ | ● | ● | ○ | | | | | |
| | | DCMT 070204 NLU | 0,4 | ● | ● | ● | | ● | ● | ● | ● | | | | | | | | | ● | ○ | ○ | ● | ○ | ○ | | | | |
| | | DCMT 11T302 NLU | 0,2 | ● | ● | ● | | ● | | ● | ● | | | | | | | | | ● | ○ | ● | ● | ○ | | | | | |
| | | DCMT 11T304 NLU | 0,4 | ● | ● | ● | | ● | ● | ● | ● | | | | | | | | | ● | ● | ● | ● | ○ | ○ | | | | |
| | | DCMT 11T308 NLU | 0,8 | ● | ● | ● | | ● | ● | ● | ● | | | | | | | | | ● | ○ | ● | ● | ○ | ○ | | | | |
| Light Cut | NLB | DCMT 070202 NLB | 0,2 | | ○ | ○ | ○ | ○ | ● | | | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| | | DCMT 070204 NLB | 0,4 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| | | DCMT 070208 NLB | 0,8 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ● | ● | | ○ | | | | |
| | | DCMT 11T302 NLB | 0,2 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| | | DCMT 11T304 NLB | 0,4 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ● | ● | | ● | | | | |
| | | DCMT 11T308 NLB | 0,8 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| Light Cut | NSU | DCMT 070202 NSU | 0,2 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ● | ● | ● | ○ | ● | ● | ● | | | | |
| | | DCMT 070204 NSU | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | | ● | ● | ● | ● | ○ | ● | ● | | | | |
| | | DCMT 070208 NSU | 0,8 | ● | ● | ● | ● | ● | ● | ○ | ● | | | | | ● | | | | ● | ● | ● | ○ | ○ | ○ | ○ | | | | |
| | | DCMT 11T302 NSU | 0,2 | ● | ● | ● | ○ | ● | ● | ● | ○ | | | | | ● | ● | ○ | | ● | ● | ● | ○ | ○ | ● | ● | | | | |
| | | DCMT 11T304 NSU | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | ● | ● | ● | | ● | ● | ● | ● | ● | ● | ● | | | | |
| | | DCMT 11T308 NSU | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | ● | ● | ● | | ● | ● | ● | ● | ● | ● | ● | | | | |
| Light Cut | NSK | DCMT 070204 NSK | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | DCMT 070208 NSK | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | DCMT 11T304 NSK | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | DCMT 11T308 NSK | 0,8 | ● | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | DCMT 11T312 NSK | 1,2 | | | ● | | | | | | | | | | | | | | | | | | | | | | | | |
| Roughing–Light Cut | NGU | DCMT 070204 NGU New | 0,4 | ● | ● | ● | ● | ● | ● | ○ | | | | | | | | | | | ● | ○ | | | ○ | | | | |
| | | DCMT 070208 NGU New | 0,8 | ● | ● | ● | ○ | ○ | ● | ○ | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | DCMT 11T302 NGU New | 0,2 | ● | ● | ● | ○ | ● | ● | ○ | | | | | | | | | | | ● | ○ | | | ○ | | | | |
| | | DCMT 11T304 NGU New | 0,4 | ● | ● | ● | ● | ● | ● | ● | | ● | ● | | | | ● | ● | | | ● | ● | | | ● | | | | |
| | | DCMT 11T308 NGU New | 0,8 | ● | ● | ● | ● | ● | ● | ● | | ● | ● | | | | ● | ● | | | ● | ● | | | ● | | | | |
| | | DCMT 11T312 NGU New | 1,2 | | | ○ | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| Roughing–Light Cut | NMU | DCMT 11T304 NMU | 0,4 | ● | ● | ● | ● | ● | ● | | ● | ○ | ● | ● | | | | | | | | | | | | | | | | |
| | | DCMT 11T308 NMU | 0,8 | ● | ● | ● | ● | ● | ● | | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| Roughing | | DCMW 070204 | 0,4 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | DCMW 070208 | 0,8 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | DCMW 11T304 | 0,4 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | DCMW 11T308 | 0,8 | | | | | | | | | ● | ● | | | | | | | | | | | | | | | | | |
| Finishing | | DCMX 11T308 NLUW | 0,8 | ● | | | | | | | ● | | | ● | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

Round Type Inserts | 7° Relief | With Insert Hole




| RC-- | L | IC | S | $D_1$ |
|---|---|---|---|---|
| 1003 | – | 10,0 | 3,18 | 3,6 |
| 10T3 | – | 10,0 | 3,97 | 3,6 |
| 12 | – | 12,0 | 4,76 | 4,2 |
| 16 | – | 16,0 | 6,35 | 5,2 |
| 20 | – | 20,0 | 6,35 | 6,5 |
| 25 | – | 25,0 | 7,94 | 7,2 |
| 32 | – | 32,0 | 9,52 | 9,5 |

(M0: IC is metric)





Lever lock holders for RCMX
⇨ D34–35

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## RCMT ●●●●M0 ●-■■

● M-Class Bumpy Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated PM | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated PM | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  NRX | **RCMT 1003M0 NRX** | – | ● | ● | ● | ○ | | | | ● | | | | | | | | | | | | | | | | | |
| | | **RCMT 10T3M0 NRX** | – | ● | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | | |
| | | **RCMT 1204M0 NRX** | – | ● | ● | ● | ● | | | | ● | | | | | | | ● | | | | | | | | | | |
| | | **RCMT 1606M0 NRX** | – | ● | ● | ● | ● | | | | ● | | | | | | | ● | | | | | | | | | | |
| | | **RCMT 2006M0 NRX** | – | ● | ● | ● | ● | | | | ● | | | | | | | ● | | | | | | | | | | |
| | | **RCMT 2507M0 NRX** | – | ○ | ○ | ○ | ○ | | | | ● | | | | | | | | | | | | | | | | | |
| Roughing |  NRH | **RCMT 1204M0 NRH** | – | ○ | ○ | ○ | ○ | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **RCMT 1606M0 NRH** | – | ○ | ● | ● | ○ | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **RCMT 2006M0 NRH** | – | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |

## RCMX ●●●●M0 ●-■■


● M-Class Grooved Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated PM | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated PM | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Roughing |  NRP | **RCMX 1003M0 NRP** | – | ○ | ● | ● | ● | | | | ● | ○ | ○ | | | | | | | | | | | | | | | |
| | | **RCMX 1204M0 NRP** | – | ○ | ● | ● | ● | | | | ○ | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **RCMX 1606M0 NRP** | – | ○ | ● | ● | ● | | | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | |
| | | **RCMX 2006M0 NRP** | – | ○ | ● | ● | ● | | | | ○ | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **RCMX 2507M0 NRP** | – | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **RCMX 3209M0 NRP** | – | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

# S SQUARE TYPE
INSERTS FOR TURNING

**90° Square Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SC_ _ | L | IC | S | $D_1$ |
| 0702.. | 7,94 | 7,94 | 2,38 | 3,4 |
| 0903.. | 9,525 | 9,525 | 3,18 | 4,4 |
| 09T3.. | 9,525 | 9,525 | 3,97 | 4,4 |
| 1204.. | 12,7 | 12,7 | 4,76 | 5,5 |
| | | | | |
| | | | | |





⇨ D36

"S ... SSKC" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## SCGT ●●●●●● ●-■■

● G-Class


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | **AC8020P** | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T150Z | **T250Z** | T300Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  L/RFX | **SCGT 09T302 LFX** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **SCGT 09T304 LFX** | 0,4 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **SCGT 120404 LFX** | 0,4 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **SCGT 09T302 RFX** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **SCGT 09T304 RFX** | 0,4 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **SCGT 120404 RFX** | 0,4 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| Light Cut |  NSC | **SCGT 070201M NSC** | <0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **SCGT 070202M NSC** | <0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **SCGT 090301M NSC** | <0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **SCGT 090302M NSC** | <0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **SCGT 09T301M NSC** | <0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **SCGT 09T302M NSC** | <0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |

Depth of cut (mm) 2 1 0 — 0,2 0,4 — Feed rate (mm/rev)

Depth of cut (mm) 2 1 0 — 0,1 0,2 0,3 — Feed rate (mm/rev)

● = Euro stock
○ = Japan stock

90° Square Type | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SC_ _ | L | IC | S | $D_1$ |
| 09T3.. | 9,525 | 9,525 | 3,97 | 4,4 |
| 1204.. | 12,7 | 12,7 | 4,76 | 5,5 |



⇨ D36

"S ... SSKC" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# SCMT/-W ●●●●●● ●-■■


● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing | NFB | **SCMT 09T304 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| | | **SCMT 09T308 NFB** | 0,8 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| Finishing | NFP | **SCMT 09T304 NFP** | 0,4 | | | | | | | | | | | | | | | | | | ● | | | ● | ● | | | | |
| | | **SCMT 09T308 NFP** | 0,8 | | | | | | | | | | | | | | | | | | ● | | | ● | ● | | | | |
| | | **SCMT 120404 NFP** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| Finishing | NLU | **SCMT 09T304 NLU** | 0,4 | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **SCMT 09T308 NLU** | 0,8 | ● | ○ | ○ | | ○ | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **SCMT 120412 NLU** | 1,2 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Light Cut | NLB | **SCMT 09T304 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **SCMT 09T308 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| Light Cut | NSU | **SCMT 09T304 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | | ● | | | | | ● | ● | ● | | ● | | | | | | | | | |
| | | **SCMT 09T308 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ○ | ● | | ● | | | ● | ● | ● | | ● | | | | | | | | | |
| | | **SCMT 120404 NSU** | 0,4 | ○ | ● | ● | ● | ● | | | ● | | | | | | | | | ● | | | | | | | | | |
| | | **SCMT 120408 NSU** | 0,8 | ● | ● | ● | ● | ● | | | ● | | | | | | | | | ● | | | | | | | | | |
| Light Cut | NSK | **SCMT 09T304 NSK** | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SCMT 09T308 NSK** | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SCMT 120404 NSK** | 0,4 | | | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **SCMT 120408 NSK** | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SCMT 120412 NSK** | 1,2 | | | ● | | | | | | | | | | | | | | | | | | | | | | | |
| Light-Medium Cut | NGU | **SCMT 09T304 NGU** New | 0,4 | ● | ● | ● | ○ | ○ | ● | ○ | | | | | | | ● | | | | | | | | | | | | |
| | | **SCMT 09T308 NGU** New | 0,8 | ● | ● | ● | ● | ○ | ● | ○ | | | ● | | | | ● | ● | | | | | | | | | | | |
| | | **SCMT 120408 NGU** New | 0,8 | ○ | ● | ● | ○ | | ● | | | | | | | | | | | | | | | | | | | | |
| Light-Medium Cut | NMU | **SCMT 09T308 NMU** | 0,8 | ○ | ● | ● | ● | ○ | ● | | ○ | ○ | ○ | ● | | | | | | | | | | | | | | | |
| | | **SCMT 120408 NMU** | 0,8 | ● | ● | ● | ● | | | | ○ | ○ | ○ | ● | | | | | | | | | | | | | | | |
| | | **SCMT 120412 NMU** | 1,2 | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **SCMW 09T308** | 0,8 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | **SCMW 120408** | 0,8 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | **SCMW 120412** | 1,2 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | |


● = Euro stock
○ = Japan stock

# S SQUARE TYPE
INSERTS FOR TURNING

**90° Square Type** | 11° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SP_ _ | L | IC | S | $D_1$ |
| 0602.. | 6,35 | 6,35 | 2,38 | 2,8 |
| 0703.. | 7,94 | 7,94 | 3,18 | 3,4 |
| 0903.. | 9,525 | 9,525 | 3,18 | 3,4 |
| 09T3.. | 9,525 | 9,525 | 3,97 | 4,4 |
| 1204.. | 12,7 | 12,7 | 4,76 | 5,5 |
| 1504.. | 15,875 | 15,875 | 4,76 | 6,5 |










➪ E18

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## SPMT/-H ●●●●●● ●-■■

● M-Class


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | AC8020P | AC8025P | AC8035P | M AC6020M | AC6030M | AC6040M | P/M AC630M | K AC4010K | AC4015K | AC420K | H AC503U | S AC5005S | AC5015S | AC5025S | P/M AC1030U | AC530U | Cermet Coated P T150Z | T250Z | T300Z | Cermet Uncoated P T1000A | T1500A | Carbide Uncoated K G10E | S EH510 | EH520 | N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  NFB | **SPMT 090304 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| | | **SPMT 090308 NFB** | 0,8 | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| Finishing |  NLU | **SPMT 090304 NLU** | 0,4 | ○ | ○ | ○ | | ○ | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | |
| | | **SPMT 090308 NLU** | 0,8 | ○ | ○ | ○ | | ○ | | ○ | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | |
| Finishing |  NFK | **SPMT 090304 NFK** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| Light Cut |  NUS | **SPMT 060204 NUS** | 0,4 | | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SPMT 070308 NUS** | 0,8 | | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SPMT 09T308 NUS** | 0,8 | | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| Light Cut |  NUS | **SPMH 090308 NUS** | 0,8 | | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SPMH 120408 NUS** | 0,8 | | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **SPMH 150408 NUS** | 0,8 | | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| Light - Medium Cut |  NLB | **SPMT 090304 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **SPMT 090308 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| Light - Medium Cut |  NSF | **SPMT 090304 NSF** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SPMT 090308 NSF** | 0,8 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

**90° Square Type** | 11° Relief / With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SP_ _ | L | IC | S | $D_1$ |
| 0703.. | 7,94 | 7,94 | 3,18 | 3,4 |
| 0903.. | 9,525 | 9,525 | 3,18 | 3,4 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |




⇨ E18

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## SPGW ●●●●●●

● G-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | M | | | P/M | K | | | H | S | | | P/M | Cermet Coated P | | | | Carbide Uncoated K | S | | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Light Cut |  | **SPGW 090304 T** | 0,4 | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **SPGW 070304** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **SPGW 090304** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |

## SPGT ●●●●●● ●-■■


● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | M | | | P/M | K | | | H | S | | | P/M | Cermet Coated P | | | | Carbide Uncoated K | S | | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing - Light Cut |   **L/RSD** | **SPGT 090302 LSD** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **SPGT 090304 LSD** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | | ○ | | | | | |
| | | **SPGT 090308 LSD** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **SPGT 090302 RSD** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **SPGT 090304 RSD** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **SPGT 090308 RSD** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |

● = Euro stock
○ = Japan stock

# S SQUARE TYPE
INSERTS FOR TURNING

**90° Square Type** | 11° Relief | Without Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SP_ _ | L | IC | S | $D_1$ |
| 0903.. | 9,525 | 9,525 | 3,18 | - |
| 1203.. | 12,7 | 12,7 | 3,18 | - |
| 1504.. | 15,875 | 15,875 | 4,76 | - |






"S… CSKP…09/12" - Type
(➪ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel



## SPMR ●●●●●● ●-■■

● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | AC8020P | AC8025P | AC8035P | M AC6020M | AC6030M | AC6040M | PM AC630M | K AC4010K | AC4015K | AC420K | H AC503U | S AC5005S | AC5015S | AC5025S | PM AC1030U | AC530U | Cermet Coated P T1500Z | T2500Z | T3000Z | Cermet Uncoated P T1000A | T1500A | Carbide Uncoated K G10E | S EH510 | EH520 | N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  NFK | **SPMR 090304 NFK** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ● | | | | |
| | | **SPMR 090308 NFK** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **SPMR 120304 NFK** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **SPMR 120308 NFK** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| Light- Medium Cut |  NSF | **SPMR 090304 NSF** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SPMR 090308 NSF** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SPMR 120304 NSF** | 0,4 | | | ● | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SPMR 120308 NSF** | 0,8 | ● | | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **SPMR 120312 NSF** | 1,2 | ● | | ● | | | | | | | | | | | | | | | | | | | | | | | |
| |  NUJ | **SPMR 090304 NUJ** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **SPMR 090308 NUJ** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **SPMR 120304 NUJ** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **SPMR 120308 NUJ** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |


## SP_N ●●●●●●

● G/M-Class No Chipbreaker


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P AC8015P | AC8020P | AC8025P | AC8035P | M AC6020M | AC6030M | AC6040M | PM AC630M | K AC4010K | AC4015K | AC420K | H AC503U | S AC5005S | AC5015S | AC5025S | PM AC1030U | AC530U | Cermet Coated P T1500Z | T2500Z | T3000Z | Cermet Uncoated P T1000A | T1500A | Carbide Uncoated K G10E | S EH510 | EH520 | N H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Medium Cut |  | **SPGN 090304** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ● | | | | |
| | | **SPGN 090308** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | ○ | | | | | | ○ |
| | | **SPGN 090308T** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **SPGN 120304** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **SPGN 120308** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | |
| Medium Cut |  | **SPMN 090304** | 0,4 | | | | | | | | | ○ | ○ | | | | | | | | | | | ○ | ○ | | | | |
| | | **SPMN 090308** | 0,8 | | | | | | | | | ○ | ○ | | | | | | | | | | | ○ | ○ | | | | |
| | | **SPMN 120304** | 0,4 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | | |
| | | **SPMN 120308** | 0,8 | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | ○ | ○ | | | | |
| | | **SPMN 120312** | 1,2 | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | | ○ | | | | ○ | ○ | | | | |
| | | **SPMN 150408** | 0,8 | | | | | | | | | | | | | ○ | | | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

60° Triangle Type | 5° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TB_ _ | L | IC | S | $D_1$ |
| 0601.. | 6,9 | 3,97 | 1,59 | 2,2 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |








⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## TBGT ●●●●●● ●-■■

● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  L/RFW | **TBGT 060102 LFW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **TBGT 060104 LFW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **TBGT 060102 RFW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **TBGT 060104 RFW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| Finishing |  L/RFX | **TBGT 060102 LFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ○ | | | | | | | | | |
| | | **TBGT 060104 LFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ● | ○ | | | | | | | | | |
| | | **TBGT 060102 RFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ○ | | | | | | | | | |
| | | **TBGT 060104 RFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ● | ○ | | | | | | | | | |
| Finishing |  L/RFY | **TBGT 060101 LFY** | 0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **TBGT 060102 LFY** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **TBGT 060104 LFY** | 0,4 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | | | | | |
| | | **TBGT 060101 RFY** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TBGT 060102 RFY** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | ○ | ○ | | | | |
| | | **TBGT 060104 RFY** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | ○ | ○ | | | | |
| Finishing-Light Cut |  L/RW | **TBGT 060102 LW** | 0,2 | | | | | | | | | | | | | | | | ● | ○ | ○ | | ○ | ○ | ● | | | | |
| | | **TBGT 060104 LW** | 0,4 | | | | | | | | | | | | | | | | ● | ○ | ○ | | ○ | ○ | ● | | | | |
| | | **TBGT 060102 RW** | 0,2 | | | | | | | | | | | | | | | | ● | ○ | ○ | | | ○ | ● | ○ | | | |
| | | **TBGT 060104 RW** | 0,4 | | | | | | | | | | | | | | | | ● | ○ | ○ | | | ○ | ● | | | | |
| For Aluminum |  L/RAY | **TBGT 060101 LAY** | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TBGT 060101 RAY** | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

## TBGW ●●●●●●


● G-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Light Cut |  | **TBGW 060102** | 0,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TBGW 060204** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |

● = Euro stock
○ = Japan stock

# T TRIANGLE TYPE
INSERTS FOR TURNING

**60° Triangle Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TC_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,2 | 4,76 | 2,38 | 2,3 |
| 0902.. | 9,62 | 5,56 | 2,38 | 2,5 |
| 1102.. | 11,0 | 6,35 | 2,38 | 2,8 |
| 16T3.. | 16,5 | 9,525 | 3,97 | 4,3 |
| | | | | |
| | | | | |








➪ D37 ➪ E19

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


## TCGT ●●●●●● ●-■■

● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | P/M: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | P/M: AC1030U | AC530U | Cermet Coated P: T150Z | T250Z | T300Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  L/RFX | **TCGT 090201 LFX** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 090202 LFX** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **TCGT 110201 LFX** | 0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **TCGT 110202 LFX** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 110301 LFX** | 0,1 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TCGT 110302 LFX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TCGT 110304 LFX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TCGT 090201 RFX** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 090202 RFX** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 110201 RFX** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 110202 RFX** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **TCGT 110301 RFX** | 0,1 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TCGT 110302 RFX** | 0,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TCGT 110304 RFX** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| Finishing |  L/RFY | **TCGT 090201 LFY** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 090202 LFY** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **TCGT 110201 LFY** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 110202 LFY** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **TCGT 090201 RFY** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 090202 RFY** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 110201 RFY** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TCGT 110202 RFY** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| Light cut |  NSI | **TCGT 110204M NSI** | <0,4 | | | | | | | | ● | | | | | ● | ● | | ● | ● | ○ | | | ○ | | | | |
| Light Cut |  NAG | **TCGT 110202 NAG** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **TCGT 110204 NAG** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **TCGT 16T304 NAG** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **TCGT 16T308 NAG** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| Light Cut |  NSC | **TCGT 080201M NSC** | <0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **TCGT 080202M NSC** | <0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **TCGT 090201M NSC** | <0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **TCGT 090202M NSC** | <0,2 | | | | | | | | | | | | | | | | ○ | ○ | | | | ● | ● | | | | |
| | | **TCGT 110201M NSC** | <0,1 | | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **TCGT 110202M NSC** | <0,2 | | | | | | | | | | | | | | | | ● | ● | | | | ● | ● | | | | |
| | | **TCGT 110204M NSC** | <0,4 | | | | | | | | | | | | | | | | ● | ● | | | | | ● | | | | |
| | | **TCGT 110301M NSC** | <0,1 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TCGT 110302M NSC** | <0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |

● = Euro stock
○ = Japan stock

**60° Triangle Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TC__ | L | IC | S | $D_1$ |
| 0902.. | 9,6 | 5,56 | 2,38 | 2,5 |
| 1102.. | 11,0 | 6,35 | 2,38 | 2,8 |
| 16T3.. | 16,5 | 9,525 | 3,97 | 4,3 |
| | | | | |
| | | | | |
| | | | | |









⇨ D37 ⇨ E19

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## TCMT/-W ●●●●●● ●-■■


● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated PM | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated PM | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | | | Carbide Uncoated S | | | Carbide Uncoated N | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NFB | **TCMT 110204 NFB** | 0,4 | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ○ | ● | | | | | |
| | | **TCMT 110208 NFB** | 0,8 | | | | | | | | | | | | | | | | ○ | ● | ● | ● | | ● | | | | | |
| Finishing |  NFP | **TCMT 090202 NFP** | 0,2 | | | | | | | | | | | | | | | | | | | | | ● | | | | | |
| | | **TCMT 090204 NFP** | 0,4 | | | | | | | | | | | | | | | | | | | | | ● | | | | | |
| | | **TCMT 090208 NFP** | 0,8 | | | | | | | | | | | | | | | | | | | | | ● | | | | | |
| | | **TCMT 110202 NFP** | 0,2 | | | | | | | | | | | | | | | | | | ● | | | ● | | | | | |
| | | **TCMT 110204 NFP** | 0,4 | | | | | | | | | | | | | | | | | | ● | | ● | ● | | | | | |
| | | **TCMT 110208 NFP** | 0,8 | | | | | | | | | | | | | | | | | | ● | | ● | ● | | | | | |
| | | **TCMT 16T304 NFP** | 0,4 | | | | | | | | | | | | | | | | | | ● | | ● | ● | | | | | |
| | | **TCMT 16T308 NFP** | 0,8 | | | | | | | | | | | | | | | | | | ● | | ● | ● | | | | | |
| Finishing |  NLU | **TCMT 110204 NLU** | 0,4 | ○ | ● | ● | | | ○ | | | | | | | | | | ● | ○ | ○ | ○ | ○ | ○ | | | | | |
| | | **TCMT 110208 NLU** | 0,8 | ○ | ○ | ○ | | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | | |
| Light Cut |  NLB | **TCMT 110204 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **TCMT 110208 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| Light Cut |  NSU | **TCMT 110204 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ○ | ○ | ○ | ● | ● | ● | ● | | | | | | | | |
| | | **TCMT 110208 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ○ | ○ | ○ | ● | | | | | | | | | | | |
| | | **TCMT 16T304 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | | ● | | | | | ○ | | | ● | | | | | | | | | | | |
| | | **TCMT 16T308 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ○ | ● | | ● | | | ○ | | | ● | | | | | | | | | | | |
| Light Cut |  NSK | **TCMT 110204 NSK** | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TCMT 110208 NSK** | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TCMT 16T304 NSK** | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TCMT 16T308 NSK** | 0,8 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TCMT 16T312 NSK** | 1,2 | | | ● | | | | | | ● | | | | | | | | | | | | | | | | | | |
| Light Cut |  | **TCMW 110204** | 0,4 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **TCMW 110208** | 0,8 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **TCMW 16T304** | 0,4 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **TCMW 16T308** | 0,8 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **TCMW 16T312** | 1,2 | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

# T TRIANGLE TYPE
INSERTS FOR TURNING

**60° Triangle Type** | 11° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TP_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,2 | 4,76 | 2,38 | 2,4 |
| 0902.. | 9,6 | 5,56 | 2,38 | 2,8 |
| 1103.. | 11,0 | 6,35 | 3,18 | 3,4 |
| 1603.. | 16,5 | 9,525 | 3,18 | 4,4 |
| | | | | |
| | | | | |






⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## TPGT ●●●●●● ●-■■


● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated P | Carbide Coated M | Carbide Coated M | Carbide Coated M | Carbide Coated P/M | Carbide Coated K | Carbide Coated K | Carbide Coated H | Carbide Coated S | Carbide Coated P/M | Cermet Coated P | Cermet Coated P | Cermet Coated P | Cermet Coated P | Cermet Uncoated P | Cermet Uncoated P | Carbide Uncoated K | Carbide Uncoated S | Carbide Uncoated S | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC815P | AC8020P | AC825P | AC835P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | AC5005S | AC5015S | AC5025S | AC1030U | AC530U | T150Z | T250Z | T300Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  | **TPGT 110302M NFC** | <0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | ○ | ○ | | | | |
| | | **TPGT 110304M NFC** | <0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | ○ | ○ | | | | |
| Finishing |  | **TPGT 080202 LFW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 080204 LFW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | |
| | | **TPGT 110202 LFW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 110204 LFW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 080202 RFW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 080204 RFW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 110202 RFW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 110204 RFW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| Finishing |  | **TPGT 080202 LFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **TPGT 080204 LFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **TPGT 090204 LFX** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TPGT 110202 LFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| | | **TPGT 110204 LFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| | | **TPGT 110208 LFX** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| | | **TPGT 110302 LFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | | | | | | |
| | | **TPGT 110304 LFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | | | | | | |
| | | **TPGT 110308 LFX** | 0,8 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 160304 LFX** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 160308 LFX** | 0,8 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| Finishing |  | **TPGT 080202 RFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **TPGT 080204 RFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 110202 RFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| | | **TPGT 110204 RFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| | | **TPGT 110208 RFX** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | | | |
| | | **TPGT 110302 RFX** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | | | | | | |
| | | **TPGT 110304 RFX** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ● | ● | | | | | | | | | |
| | | **TPGT 110308 RFX** | 0,8 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 160304 RFX** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 160308 RFX** | 0,8 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |



● = Euro stock
○ = Japan stock

**60° Triangle Type** | 11° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TP_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,2 | 4,76 | 2,38 | 2,4 |
| 0902.. | 9,6 | 5,56 | 2,38 | 2,8 |
| 1102.. | 11,0 | 6,35 | 2,38 | 2,8 |
| 1103.. | 11,0 | 6,35 | 3,18 | 3,4 |
| 1603.. | 16,5 | 9,525 | 3,18 | 4,4 |





⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## TPGT/-W ●●●●●● ●-■■


● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing | | **TPGT 0802003 LFY** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 080201 LFY** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 080202 LFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | ○ | ○ | | | | |
| | | **TPGT 080204 LFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | ○ | ○ | | | | |
| | | **TPGT 090201 LFY** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 090202 LFY** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | ○ | | | | |
| | | **TPGT 090204 LFY** | 0,4 | | | | | | | | | | | | | | ○ | | ○ | | | | | | | | | | |
| | | **TPGT 110202 LFY** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TPGT 110204 LFY** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TPGT 110208 LFY** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPGT 1103003 LFY** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 110301 LFY** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **TPGT 110302 LFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TPGT 110304 LFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TGPT 110308 LFY** | 0,8 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | ○ | | | | |
| | | **TPGT 160302 LFY** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 160304 LFY** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 160308 LFY** | 0,8 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| |  L/RFY | **TPGT 0802003 RFY** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 080201 RFY** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 080202 RFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | ○ | ○ | | | | |
| | | **TPGT 080204 RFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | ○ | ○ | | | | |
| | | **TPGT 090201 RFY** | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 090202 RFY** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 090204 RFY** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 110202 RFY** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TPGT 110204 RFY** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TPGT 110208 RFY** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPGT 1103003 RFY** | 0,03 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | |
| | | **TPGT 110301 RFY** | 0,1 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | | | | |
| | | **TPGT 110302 RFY** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 110304 RFY** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 110308 RFY** | 0,8 | | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | ○ | | | | |
| | | **TPGT 160302 RFY** | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 160304 RFY** | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| | | **TPGT 160308 RFY** | 0,8 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| For Aluminum |  L/RAY | **TPGT 110202 LAY** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TPGT 110302 LAY** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TPGT 110304 LAY** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TPGT 110302 RAY** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | **TPGT 110304 RAY** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| Light Cut |  | **TPGW 080202** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TPGW 110302** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **TPGW 110304** | 0,4 | | | | | | | | | | | | ○ | | ○ | ○ | | | | | | ○ | ○ | ● | | | |
| | | **TPGW 110308** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | ○ | ○ | | | | |
| | | **TPGW 160404** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | | | | | | ● | | | |

● = Euro stock
○ = Japan stock

## 60° Triangle Type

11° Relief
With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TP_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,2 | 4,76 | 2,38 | 2,4 |
| 1103.. | 11,0 | 6,35 | 3,18 | 3,4 |
| 1604.. | 16,5 | 9,525 | 4,76 | 4,4 |
| | | | | |
| | | | | |
| | | | | |







⇨ E20


- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# TPGT/-X ●●●●●● ●-■■

● G-Class Handed Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC015P | **AC8020P** | AC025P | AC035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T150Z | **T250Z** | T300Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing-Light Cutting |  L/R**W** | **TPGT 080202 LW** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | | ○ | | | ● | | | | |
| | | **TPGT 080204 LW** | 0,4 | | | | | | | | | | | | | | | | ● | ● | | ○ | ○ | | ● | ○ | | | |
| | | **TPGT 110302 LW** | 0,2 | | | | | | | | | | | | | | | | ● | ● | | | | | ● | | | | |
| | | **TPGT 110304 LW** | 0,4 | | | | | | | | | | | | | | | | ● | ● | | | | | ● | | | | |
| | | **TPGT 160402 LW** | 0,2 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **TPGT 160404 LW** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **TPGT 080202 RW** | 0,2 | | | | | | | | | | | | | | | | ○ | | | ○ | | | ● | ○ | | | |
| | | **TPGT 080204 RW** | 0,4 | | | | | | | | | | | | | | | | ● | ● | | | | | ● | | | | |
| | | **TPGT 110302 RW** | 0,2 | | | | | | | | | | | | | | | | ● | ● | | | | | ● | | | | |
| | | **TPGT 110304 RW** | 0,4 | | | | | | | | | | | | | | | | ● | ● | | | | | ● | | | | |
| | | **TPGT 160404 RW** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| Finishing-Light Cutting |  L/R**SD** | **TPGT 110302 LSD** | 0,2 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ○ | | | |
| | | **TPGT 110304 LSD** | 0,4 | | | | | | | | | | | | | | ○ | ○ | ○ | ● | ○ | ○ | ○ | ○ | ● | ○ | | | |
| | | **TPGT 110308 LSD** | 0,8 | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **TPGT 160402 LSD** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | | ● | | | | |
| | | **TPGT 160404 LSD** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | ○ | ○ | ○ | ○ | ● | | | | |
| | | **TPGT 160408 LSD** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 110302 RSD** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | ● | | | | |
| | | **TPGT 110304 RSD** | 0,4 | | | | | | | | | | | | | | | | ○ | ● | ○ | | ○ | ○ | ● | | | | |
| | | **TPGT 110308 RSD** | 0,8 | | | | | | | | | | | | | | | | ○ | | ○ | | | ○ | ○ | | | | |
| | | **TPGT 160402 RSD** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **TPGT 160404 RSD** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ● | | | | |
| | | **TPGT 160408 RSD** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ● | | | | |
| Finishing-Light Cutting |  L/R**SDW** | **TPGX 110304 L-SDW** | 0,4 | | | | | | | | | | | | | | | | | | | ● | ● | | | | | | |
| | | **TPGX 110308 L-SDW** | 0,8 | | | | | | | | | | | | | | | | | | | ○ | ● | | | | | | |
| | | **TPGX 160404 L-SDW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **TPGX 160408 L-SDW** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **TPGX 110304 R-SDW** | 0,4 | | | | | | | | | | | | | | | | | | | ○ | ● | | | | | | |
| | | **TPGX 110308 R-SDW** | 0,8 | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | | |
| | | **TPGX 160404 R-SDW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **TPGX 160408 R-SDW** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |








(Note) The cutting point position of the SDW type does not follow the ISO standard.
Wenn using on a boring holder with a 93° approach angle, there is a need to revise the cutting point position (refer to right table) relative to using standard inserts.

| RE | Compensation (mm) | | |
|---|---|---|---|
| | X (Diam. change) | | Z |
| 0,4 | +0,12 | (Ø : +0,24) | -0,02 |
| 0,8 | +0,12 | (Ø : +0,24) | -0,02 |

● = Euro stock
○ = Japan stock

60° Triangle Type | 11° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TP_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,2 | 4,76 | 2,38 | 2,4 |
| 0902.. | 9,6 | 5,56 | 2,38 | 2,8 |
| 1103.. | 11,0 | 6,35 | 3,18 | 3,4 |
| 1603.. | 16,5 | 9,525 | 3,18 | 4,4 |
| 1604.. | 16,5 | 9,525 | 4,76 | 4,4 |



⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# TPMT ●●●●●● ●-■■


● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Uncoated K | | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing | NFB | **TPMT 080202 NFB** | 0,2 | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 080204 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 090202 NFB** | 0,2 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 090204 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | | ○ | ○ | | | | | |
| | | **TPMT 110302 NFB** | 0,2 | | | | | | | | | | | | | | | | | ○ | | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 110304 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 110308 NFB** | 0,8 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 160304 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 160308 NFB** | 0,8 | | | | | | | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | | |
| | | **TPMT 160404 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 160408 NFB** | 0,8 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | | |
| Light Cut | NLB | **TPMT 080202 NLB** | 0,2 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **TPMT 080204 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **TPMT 090202 NLB** | 0,2 | | ○ | ○ | ○ | ○ | ● | ○ | | | | | | | | | | | ○ | ○ | ○ | | | | | | | |
| | | **TPMT 090204 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | | ○ | ○ | | ○ | | | | | |
| | | **TPMT 110302 NLB** | 0,2 | | ○ | ○ | ○ | ○ | | ● | | | | | | | | | | | | ○ | ○ | | | | | | | |
| | | **TPMT 110304 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **TPMT 110308 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ● | | | | | | | | | | | | | ○ | | | ○ | | | | | |
| | | **TPMT 160304 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **TPMT 160308 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **TPMT 160404 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **TPMT 160408 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| Finishing | NFK | **TPMT 110304 NFK** | 0,4 | | | | | | | | | | | | | | | | | | | | | ● | ● | | | | | |
| | | **TPMT 110308 NFK** | 0,8 | | | | | | | | | | | | | | | | | | | | | ● | ● | | | | | |
| | | **TPMT 160404 NFK** | 0,4 | | | | | | | | | | | | | | | | | | | | | ● | ● | | | | | |
| | | **TPMT 160408 NFK** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ● | | | | | |
| Finishing | NLU | **TPMT 080202 NLU** | 0,2 | | | | | | ● | ● | | | | | | | | | | ○ | | | | ○ | ○ | | | | | |
| | | **TPMT 080204 NLU** | 0,4 | ● | | | | | ● | ○ | ● | | | | | | | | | ○ | | ● | ● | ○ | ○ | | | | | |
| | | **TPMT 090202 NLU** | 0,2 | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | | |
| | | **TPMT 090204 NLU** | 0,4 | ○ | ○ | ○ | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | | | | | |
| | | **TPMT 110302 NLU** | 0,2 | | | | | | | ● | | | | | | | | | | | ○ | ○ | | ○ | ○ | | | | | |
| | | **TPMT 110304 NLU** | 0,4 | ● | ○ | ○ | | | ● | ● | | | | | | | | | | ● | ○ | ○ | ● | ○ | ○ | | | | | |
| | | **TPMT 110308 NLU** | 0,8 | ● | ○ | ○ | | | ● | ● | ● | | | | | | | | | ● | ○ | ○ | ● | ○ | ○ | | | | | |

Depth of cut (mm) / Feed rate (mm/rev)

● = Euro stock
○ = Japan stock

**60° Triangle Type** | 11° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TP_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,2 | 4,76 | 2,38 | 2,4 |
| 1103.. | 11,0 | 6,35 | 3,18 | 3,4 |
| 1604.. | 16,5 | 9,525 | 4,76 | 4,4 |
| | | | | |
| | | | | |
| | | | | |






➪ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# TPMT ●●●●●● ●-■■

● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Light Cut |  NSU | **TPMT 080202 NSU** | 0,2 | | | | | ○ | ● | ● | | | | | | ○ | | | | ○ | | | | ○ | ○ | | | | |
| | | **TPMT 080204 NSU** | 0,4 | | | | | ○ | ● | ● | ○ | | | | | ○ | | | | ○ | | | | ○ | ○ | | | | |
| | | **TPMT 110302 NSU** | 0,2 | ○ | ○ | ○ | ○ | ○ | ● | ● | ○ | | | | | ○ | | | | ○ | ○ | ○ | | ○ | ○ | | | | |
| | | **TPMT 110304 NSU** | 0,4 | ● | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | | | | ● | ○ | ○ | ○ | ○ | ● | | | | |
| | | **TPMT 110308 NSU** | 0,8 | ● | ● | ● | ○ | ● | ● | ● | ● | | | | | ○ | | | | ● | ○ | ○ | ○ | ○ | ● | | | | |
| | | **TPMT 160404 NSU** | 0,4 | ● | ○ | ○ | ○ | ● | ○ | | ● | | | | | ○ | | | | ● | ○ | ○ | ○ | ○ | ● | | | | |
| | | **TPMT 160408 NSU** | 0,8 | ● | ○ | ○ | ○ | ● | ○ | | ● | | | | | ○ | | | | ● | ○ | ○ | ○ | ○ | ● | | | | |
| Light -Medium Cut |  NGU | **TPMT 110304 NGU** New | 0,4 | ○ | ● | ● | ○ | ○ | ● | ○ | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **TPMT 110308 NGU** New | 0,8 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **TPMT 160404 NGU** New | 0,4 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **TPMT 160408 NGU** New | 0,8 | ● | ○ | ○ | ○ | ○ | ● | ○ | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| Light -Medium Cut |  NMU | **TPMT 110304 NMU** | 0,4 | ○ | ○ | ○ | | ○ | ● | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TPMT 110308 NMU** | 0,8 | ○ | ○ | ○ | | ○ | ● | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | **TPMT 160404 NMU** | 0,4 | ○ | ○ | ○ | | ○ | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **TPMT 160408 NMU** | 0,8 | ○ | ○ | ○ | | ○ | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | |


# TPMT/H ●●●●●● NSF

● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Light -Medium Cut |  NSF | **TPMH 110304 NSF** | 0,4 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMH 110308 NSF** | 0,8 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMT 160404 NSF** | 0,4 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMT 160408 NSF** | 0,8 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

60° Triangle Type | 5°/11° Relief | Without Insert Hole






| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TP/TB_ | L | IC | S | $D_1$ |
| 0601.. | 6,9 | 3,97 | 1,59 | - |
| 0902.. | 9,6 | 5,56 | 2,38 | - |
| 1103.. | 11,0 | 6,35 | 3,18 | - |
| 1603.. | 16,5 | 9,525 | 3,18 | - |
| 2204.. | 22,0 | 12,7 | 4,75 | - |



P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

## TPGR ●●●●●● ●-■

● G-Class Handed Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | M | | | P/M | K | | | H | S | | | P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Uncoated K | S | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing-Light Cut |  L-**W** | **TPGR 090202 LW** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPGR 090204 LW** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPGR 090208 LW** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPGR 110302 LW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGR 110304 LW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ● | | | | |
| | | **TPGR 110308 LW** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGR 160302 LW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGR 160304 LW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ● | | | | |
| | | **TPGR 160308 LW** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ● | | | | |
| Finishing-Light Cut |  R-**W** | **TPGR 090202 RW** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPGR 090204 RW** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPGR 090208 RW** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPGR 110302 RW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGR 110304 RW** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **TPGR 160302 RW** | 0,2 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | |
| | | **TPGR 160304 RW** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ● | | | | |
| | | **TPGR 160308 RW** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ● | | | | |

## TBG_ ●●●●●● ●-■

● G-Class No Chipbreaker/ Handed Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | M | | | P/M | K | | | H | S | | | P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Uncoated K | S | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing - Light-Cut |  | **TBGN 060104** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| |  | **TBGR 060104 LW** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |

## TPGN ●●●●●●


● G-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | M | | | P/M | K | | | H | S | | | P/M | Cermet Coated P | | | | Cermet Uncoated P | | Carbide Uncoated K | S | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Light Cut |  | **TPGN 090202** | 0,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | | **TPGN 090208** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ○ | | | ○ |
| | | **TPGN 110302** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | |
| | | **TPGN 110304** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | | | | ○ | ○ | | | ○ |
| | | **TPGN 110308** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | |
| | | **TPGN 160302** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | ● | | |
| | | **TPGN 160304** | 0,4 | | | | | | | | | | | | | | ○ | ○ | | | | | | ○ | ○ | ○ | | |
| | | **TPGN 160308** | 0,8 | | | | | | | | | | | | | | ○ | ○ | | | | | | ○ | ○ | | | |
| | | **TPGN 160312** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | ○ | | |
| | | **TPGN 220404** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ○ | | |

● = Euro stock
○ = Japan stock

# T TRIANGLE TYPE
INSERTS FOR TURNING

**60° Triangle Type** | 11°/20° Relief | Without Insert Hole







| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TP_ _ | L | IC | S | $D_1$ |
| 0902.. | 9,6 | 5,56 | 2,38 | - |
| 1103.. | 11,0 | 6,35 | 3,18 | - |
| 1603.. | 16,5 | 9,525 | 3,18 | - |
| 2204.. | 22,0 | 12,7 | 4,76 | - |
| | | | | |
| | | | | |



- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## TPMR ●●●●●● ●-■■

● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |   NFK | **TPMR 090204 NFK** | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **TPMR 110302 NFK** | 0,2 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **TPMR 110304 NFK** | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | ○ | ● | | | | |
| | | **TPMR 110308 NFK** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **TPMR 160304 NFK** | 0,2 | | | | | | | | | | | | | | | | | | ○ | ○ | | | ● | | | | |
| | | **TPMR 160308 NFK** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | ● | | | | |
| | | **TPMR 160312 NFK** | 1,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| Light-Medium Cut |   NSF | **TPMR 110304 NSF** | 0,4 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMR 110308 NSF** | 0,8 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMR 160304 NSF** | 0,4 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMR 160308 NSF** | 0,8 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMR 160312 NSF** | 1,2 | | ● | ● | ● | | | | | | | | | | | | | | | | | | | | | | |
| Light-Medium Cut |   NUJ | **TPMR 110304 NUJ** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMR 110308 NUJ** | 0,8 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMR 160304 NUJ** | 0,4 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPMR 160308 NUJ** | 0,8 | | | ○ | ● | | | | | | | | | | | | | | | | | | | | | | |

## TPMN ●●●●●

● M-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Medium Cut |  | **TPMN 110304** | 0,4 | | | | | | | | | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **TPMN 110308** | 0,8 | | | | | | | | | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **TPMN 160304** | 0,4 | | | | | | | | | ○ | ○ | | | ○ | ○ | ○ | | | | | | | | | | | |
| | | **TPMN 160308** | 0,8 | | | | | | | | | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | ○ | ○ | | | | |
| | | **TPMN 160312** | 1,2 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **TPMN 220404** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | | **TPMN 220408** | 0,8 | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | ○ | ○ | | | | |
| | | **TPMN 220412** | 1,2 | | | | | | | | | | | | | ○ | ○ | ○ | | | | | | | | | | | |


## TEGN ●●●●●●

● E-Class No Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | PM: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | PM: AC1030U | AC530U | Cermet Coated P: T1500Z | T2500Z | T3000Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Light-Medium Cut |  | **TEGN 160308** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ○ | | | | |

● = Euro stock
○ = Japan stock

**35° Diamond Type** | 5° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VB_ _ | L | IC | S | $D_1$ |
| 1102.. | 11,0 | 6,35 | 2,38 | 2,38 |
| 1103.. | 11,1 | 6,35 | 3,18 | 2,8 |
| 1604.. | 16,6 | 9,525 | 4,76 | 4,4 |
| | | | | |
| | | | | |
| | | | | |










⇨ D38 ⇨ E21–22


- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## VBMT/-W ●●●●●● ●-■■


● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | | Cermet Uncoated P | Carbide Uncoated K | | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  NFB | **VBMT 110302 NFB** | 0,2 | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| | | **VBMT 110304 NFB** | 0,4 | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| | | **VBMT 110308 NFB** | 0,8 | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | ○ | | | | |
| | | **VBMT 160404 NFB** | 0,4 | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | ● | | | | |
| | | **VBMT 160408 NFB** | 0,8 | | | | | | | | | | | | | | | | ○ | ● | ● | ● | ● | ● | | | | |
| Finishing |  NFP | **VBMT 110202 NFP** | 0,2 | | | | | | | | | | | | | | | | ● | | | ● | ● | ● | | | | |
| | | **VBMT 110204 NFP** | 0,4 | | | | | | | | | | | | | | | | | | | ● | ● | ● | | | | |
| | | **VBMT 160404 NFP** | 0,4 | | | | | | | | | | | | | | | | ● | | | ● | ● | ● | | | | |
| | | **VBMT 160408 NFP** | 0,8 | | | | | | | | | | | | | | | | ● | | | ● | ● | ● | | | | |
| Finishing |  NLU | **VBMT 110302 NLU** | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | ○ | ○ | | ○ | | | | |
| | | **VBMT 110304 NLU** | 0,4 | ○ | ● | ● | | ● | | ● | ○ | | | | | | | | ○ | ○ | ○ | ○ | | ○ | | | | |
| | | **VBMT 110308 NLU** | 0,8 | ○ | ○ | ○ | ● | ● | ○ | ● | ○ | | | | | | | | | | | | | | | | | |
| | | **VBMT 160404 NLU** | 0,4 | ● | ○ | ○ | | | ○ | ● | ○ | | | | | | | | ● | ○ | ○ | ○ | ○ | ○ | | | | |
| | | **VBMT 160408 NLU** | 0,8 | ● | ● | ● | | | ○ | ● | ○ | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | | | | |
| Light Cut |  NLB | **VBMT 110302 NLB** | 0,2 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **VBMT 110304 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **VBMT 110308 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | |
| | | **VBMT 160404 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ● | ● | | | | | | | | | | ● | ● | ● | | ● | | | | |
| | | **VBMT 160408 NLB** | 0,8 | | ○ | ● | ○ | ○ | ● | ○ | | | | | | | | | | ● | ● | ● | | ● | | | | |
| | | **VBMT 160412 NLB** | 1,2 | | ○ | ○ | ○ | ○ | ● | | | | | | | | | | | ● | ○ | ● | | ● | | | | |
| Light Cut |  NSU | **VBMT 110204 NSU** | 0,4 | ● | | | | ● | | | ● | | | | | | | | ● | | | | | | | | | |
| | | **VBMT 110208 NSU** | 0,8 | ● | ● | ● | | ● | | | ● | | | | | | | | ● | | | | | | | | | |
| | | **VBMT 110302 NSU** | 0,2 | | | | | | | | | | | | | ○ | | | ○ | | | | | | | | | |
| | | **VBMT 110304 NSU** | 0,4 | ● | ● | ● | | ● | | ● | ● | | | | | ○ | | | ● | | ○ | ○ | | | | | | |
| | | **VBMT 110308 NSU** | 0,8 | ● | ● | ● | | ● | ● | ○ | ● | | | | | ○ | | | ● | | | | | | | | | |
| | | **VBMT 160404 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | | |
| | | **VBMT 160408 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | | | | | |
| | | **VBMT 160412 NSU** | 1,2 | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| Light Cut |  NSK | **VBMT 110204 NSK** | 0,4 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **VBMT 110208 NSK** | 0,8 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **VBMT 160404 NSK** | 0,4 | ● | | ● | ● | | | | | | | | | | ● | ● | | | | | | | | | | |
| | | **VBMT 160406 NSK** | 0,6 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **VBMT 160408 NSK** | 0,8 | ● | | ● | ● | | | | | | | | | | ● | ● | | | | | | | | | | |
| | | **VBMT 160412 NSK** | 1,2 | ● | ● | ● | ● | | | | | ● | | | | | | | | | | | | | | | | |
| Light - Medium Cut |  NGU | **VBMT 110304 NGU** New | 0,4 | ○ | ○ | ○ | ○ | ○ | ● | ○ | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **VBMT 110308 NGU** New | 0,8 | ● | ○ | ○ | ○ | ● | ○ | ○ | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **VBMT 160404 NGU** New | 0,4 | ● | ● | ● | ○ | ● | ● | ○ | | | ● | | | | ● | ● | | ● | ● | | | ○ | | | | |
| | | **VBMT 160408 NGU** New | 0,8 | ● | ● | ● | ● | ● | ● | ○ | | ● | ● | | | | | ● | | ● | ○ | | | ○ | | | | |
| Light - Medium Cut |  NMU | **VBMT 160408 NMU** | 0,8 | ● | | | | | | | ● | | | | | | | | | | | | | | | | | |
| Light Cut |  | **VBMW 160404** | 0,4 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | |
| | | **VBMW 160408** | 0,8 | | | | | | | | | ○ | ○ | | | | | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

# V DIAMOND TYPE
## INSERTS FOR TURNING

**35° Diamond Type** | 5° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VB_ _ | L | IC | S | $D_1$ |
| 1103.. | 11,1 | 6,35 | 3,18 | 2,8 |
| 1604.. | 16,6 | 9,525 | 4,76 | 4,4 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |









⇨ D38 ⇨ E21–22

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# VBGT ●●●●●● ●-■■

● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | M: AC6020M | AC6030M | AC6040M | P/M: AC630M | K: AC4010K | AC4015K | AC420K | H: AC503U | S: AC5005S | AC5015S | AC5025S | P/M: AC1030U | AC530U | Cermet Coated P: T150Z | T250Z | T300Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | S: EH510 | EH520 | N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  L/RFX   | VBGT 110301 LFX | 0,1 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | | | | | |
| | | VBGT 110302 LFX | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | | | | | | |
| | | VBGT 110304 LFX | 0,4 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | | | | | |
| | | VBGT 160402 LFX | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | |
| | | VBGT 160404 LFX | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | |
| | | VBGT 110301 RFX | 0,1 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | | | | | |
| | | VBGT 110302 RFX | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | | | | | |
| | | VBGT 110304 RFX | 0,4 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | | | | | |
| | | VBGT 160402 RFX | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | |
| | | VBGT 160404 RFX | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | |
| Finishing |  L/RFYS   | VBGT 1103003 LFYS | 0,03 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 110301 LFYS | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 110302 LFYS | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 110304 LFYS | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 110308 LFYS | 0,8 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 1103003 RFYS | 0,03 | | | | | | | | | | | | | | ○ | | ○ | | | | | | | | | | | |
| | | VBGT 110301 RFYS | 0,1 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 110302 RFYS | 0,2 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 110304 RFYS | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 110308 RFYS | 0,8 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| Finishing |  L/RFY   | VBGT 110301 LFY | 0,1 | | | | | | | | | | | | | | | | ○ | | ○ | | | ○ | ○ | | | | | |
| | | VBGT 110302 LFY | 0,2 | | | | | | | | | | | | | | | | ○ | ○ | ○ | | | ○ | ○ | | | | | |
| | | VBGT 110304 LFY | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| | | VBGT 110301 RFY | 0,1 | | | | | | | | | | | | | | | | | | ○ | | | ○ | ○ | | | | | |
| | | VBGT 110302 RFY | 0,2 | | | | | | | | | | | | | | | | ○ | | ○ | | | ○ | ○ | | | | | |
| | | VBGT 110304 RFY | 0,4 | | | | | | | | | | | | | | | | ○ | | | | | | | | | | | |
| Light Cut |  NSI   | VBGT 110301M NSI | <0,1 | | | | | | | | | | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | VBGT 110302M NSI | <0,2 | | | | | | | | | | | | | | ● | ● | ○ | ○ | | | | | | | | | | |
| | | VBGT 110304M NSI | <0,4 | | | | | | | | | | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | VBGT 110308M NSI | <0,8 | | | | | | | | | | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | VBGT 160401M NSI | <0,1 | | | | | | | | | | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | VBGT 160402M NSI | <0,2 | | | | | | | | | | | | | | ● | ● | ○ | ○ | | | | | | | | | | |
| | | VBGT 160404M NSI | <0,4 | | | | | | | | | | | | | | ● | ● | ○ | | | | | | | | | | | |
| | | VBGT 160408M NSI | <0,8 | | | | | | | | | | | | | | ● | ● | ○ | | | | | | | | | | | |
| For Aluminum |  L/RAY   | VBGT 110301 LAY | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 110302 LAY | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 110304 LAY | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 160402 LAY | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 160404 LAY | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 110301 RAY | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 110302 RAY | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 110304 RAY | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 160402 RAY | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | VBGT 160404 RAY | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Japan stock

**35° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VC_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,3 | 4,76 | 2,38 | 2,3 |
| 1103.. | 11,1 | 6,35 | 3,18 | 2,8 |
| 1604.. | 16,6 | 9,525 | 4,76 | 4,4 |
| 2205.. | 20,2 | 12,7 | 5,56 | 5,5 |
| | | | | |
| | | | | |



⇨ D39

"S...- SV...C" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## VCGT ●●●●●● ●-■■


● G-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC8035P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | **T1500Z** | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing | NFC | **VCGT 080204M NFC** | <0,4 | | | | | | | | | | | | | | ❍ | ❍ | ❍ | ❍ | | | | | | | | | |
| | | **VCGT 110301M NFC** | <0,1 | | | | | | | | | | | | | | ❍ | ❍ | ● | ● | | | | ❍ | ❍ | | | | |
| | | **VCGT 110302M NFC** | <0,2 | | | | | | | | | | | | | | ❍ | ❍ | ● | ● | | | | ❍ | ❍ | | | | |
| | | **VCGT 110304M NFC** | <0,4 | | | | | | | | | | | | | | ❍ | ❍ | ● | ● | | | | ❍ | ❍ | | | | |
| Finishing | L/RFX | **VCGT 110301 LFX** | 0,1 | | | | | | | | | | | | | | ❍ | ❍ | ● | ● | | | | ❍ | ● | | | | |
| | | **VCGT 110302 LFX** | 0,2 | | | | | | | | | | | | | | ❍ | ❍ | ● | ● | | | | ❍ | ● | | | | |
| | | **VCGT 110304 LFX** | 0,4 | | | | | | | | | | | | | | | | ● | ● | | | | | | | | | |
| | | **VCGT 110301 RFX** | 0,1 | | | | | | | | | | | | | | ❍ | ❍ | ● | ● | | | | ❍ | ● | | | | |
| | | **VCGT 110302 RFX** | 0,2 | | | | | | | | | | | | | | ❍ | ❍ | ● | ● | | | | ❍ | ● | | | | |
| | | **VCGT 110304 RFX** | 0,4 | | | | | | | | | | | | | | | | ❍ | ❍ | | | | | | | | | |
| Finishing | L/RFY | **VCGT 110301 LFY** | 0,1 | | | | | | | | | | | | | | ❍ | ❍ | ❍ | | | | | | | | | | |
| | | **VCGT 110302 LFY** | 0,2 | | | | | | | | | | | | | | ❍ | ❍ | ❍ | | | | | | | | | | |
| | | **VCGT 110304 LFY** | 0,4 | | | | | | | | | | | | | | | | ❍ | ❍ | | | | | | | | | |
| | | **VCGT 110301 RFY** | 0,1 | | | | | | | | | | | | | | ❍ | ❍ | ❍ | ❍ | | | | | | | | | |
| | | **VCGT 110302 RFY** | 0,2 | | | | | | | | | | | | | | ❍ | ❍ | ❍ | ❍ | | | | | | | | | |
| | | **VCGT 110304 RFY** | 0,4 | | | | | | | | | | | | | | | | ❍ | ❍ | | | | | | | | | |
| Light Cut | NAG | **VCGT 110302 NAG** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **VCGT 110304 NAG** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **VCGT 160408 NAG** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **VCGT 160412 NAG** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ● |
| | | **VCGT 220530 NAG** | 3,0 | | | | | | | | | | | | | | | | | | | | | | | | | | ❍ |
| Light Cut | NSI | **VCGT 110301M NSI** | <0,1 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ❍ | | ❍ | ❍ | | | | |
| | | **VCGT 110302M NSI** | <0,2 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ❍ | | ❍ | ❍ | | | | |
| | | **VCGT 110304M NSI** | <0,4 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ❍ | | | ❍ | | | | |
| | | **VCGT 110308M NSI** | <0,8 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ❍ | | ❍ | ❍ | | | | |
| | | **VCGT 160401M NSI** | <0,1 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ❍ | | ❍ | ❍ | | | | |
| | | **VCGT 160402M NSI** | <0,2 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ❍ | | ❍ | ❍ | | | | |
| | | **VCGT 160404M NSI** | <0,4 | | | | | | | | ● | | | | | | ● | ● | ● | ● | ● | ❍ | | ● | ❍ | | | | |
| | | **VCGT 160408M NSI** | <0,8 | | | | | | | | | | | | | | ● | ● | ❍ | ❍ | | | | | | | | | |

● = Euro stock
❍ = Japan stock

# V DIAMOND TYPE
## INSERTS FOR TURNING

**35° Diamond Type** | 7° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VC_ _ | L | IC | S | $D_1$ |
| 0802.. | 8,3 | 4,76 | 2,38 | 2,3 |
| 1103.. | 11,1 | 6,35 | 3,18 | 2,8 |
| 1604.. | 16,6 | 9,525 | 4,76 | 4,4 |
| | | | | |
| | | | | |
| | | | | |









⇨ D39

"S…- SV…C" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel


# VCMT ●●●●●● ●-■■

● M-Class


| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8015P | AC8020P | AC8025P | AC8035P | Carbide Coated M: AC6020M | AC6030M | AC6040M | Carbide Coated P/M: AC630M | Carbide Coated K: AC4010K | AC4015K | AC420K | Carbide Coated H: AC503U | Carbide Coated S: AC5005S | AC5015S | AC5025S | Carbide Coated P/M: AC1030U | AC530U | Cermet Coated P: T150Z | T250Z | T300Z | Cermet Uncoated P: T1000A | T1500A | Carbide Uncoated K: G10E | Carbide Uncoated S: EH510 | EH520 | Carbide Uncoated N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Finishing |  NFB  | **VCMT 080202 NFB** | 0,2 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | | | | | |
| | | **VCMT 080204 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | | | | | |
| | | **VCMT 160404 NFB** | 0,4 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | | | | | |
| | | **VCMT 160408 NFB** | 0,8 | | | | | | | | | | | | | | | | | ○ | ● | ○ | ○ | ○ | | | | | |
| Finishing |  NLU  | **VCMT 160404 NLU** | 0,4 | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | | |
| | | **VCMT 160408 NLU** | 0,8 | ○ | ○ | ○ | | ○ | | ○ | | | | | | | | | | | ○ | ○ | ○ | ○ | ○ | | | | | |
| Light Cut |  NLB  | **VCMT 080202 NLB** | 0,2 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **VCMT 080204 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | ○ | | | | | |
| | | **VCMT 160404 NLB** | 0,4 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | | | | | | |
| | | **VCMT 160408 NLB** | 0,8 | | ○ | ○ | ○ | ○ | ○ | ○ | | | | | | | | | | | ○ | ○ | ○ | | | | | | | |
| Light Cut |  NSU  | **VCMT 080204 NSU** | 0,4 | | | | | ○ | ○ | ● | ○ | | | | | ○ | | | | ○ | | | | | | | | | |
| | | **VCMT 110302 NSU** | 0,2 | | | | | ● | ● | | ● | | | | | ○ | | | | | | | | | | | | | |
| | | **VCMT 110304 NSU** | 0,4 | | ○ | ○ | | ● | ● | ○ | ○ | | | | | ○ | | | | | | | | | | | | | |
| | | **VCMT 110308 NSU** | 0,8 | | ○ | ○ | | ● | ● | ○ | ○ | | | | | ○ | | | | | | | | | | | | | |
| | | **VCMT 160404 NSU** | 0,4 | ● | ● | ● | ● | ● | ● | ○ | ● | | | | | ● | ● | ● | | ● | | | | | | | | | |
| | | **VCMT 160408 NSU** | 0,8 | ● | ● | ● | ● | ● | ● | ○ | ● | | | | | ○ | ○ | ○ | | ● | | | | | | | | | |
| Light Cut |  NSK  | **VCMT 160404 NSK** | 0,4 | | ● | ● | ● | | | | | | | | | | | ● | | | | | | | | | | | |
| | | **VCMT 160408 NSK** | 0,8 | | ● | ● | ● | | | | | | | | | | ● | ● | | | | | | | | | | | |
| Light - Medium Cut |  NGU  | **VCMT 160404 NGU** New | 0,4 | ● | ● | ● | ○ | ○ | ● | ○ | | | ● | | | | ● | ○ | | | | | | | | | | | |
| | | **VCMT 160408 NGU** New | 0,8 | ● | ● | ● | ○ | ○ | ● | ○ | | | | | | | | ○ | | | | | | | | | | | |

● = Euro stock
○ = Japan stock

80° Trigon Type | 5° Relief | With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WB_ _ | L | IC | S | $D_1$ |
| 0601.. | 3,2 | 3,97 | 1,59 | 2,2 |
| 0802.. | 4,6 | 4,76 | 2,38 | 2,4 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |






⇨ E23

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

# WBGT ●●●●●● ●-■■


● G-Class Handed Chipbreaker

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P | | | Carbide Coated M | | | Carbide Coated P/M | Carbide Coated K | | | Carbide Coated H | Carbide Coated S | | | Carbide Coated P/M | Cermet Coated P | | | Cermet Uncoated P | | Carbide Uncoated K | | Carbide Uncoated S | | Carbide Uncoated N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | AC8015P | **AC8020P** | AC8025P | AC6020M | AC6030M | AC6040M | AC630M | AC4010K | AC4015K | AC420K | AC503U | **AC5005S** | AC5015S | AC5025S | AC1030U | AC530U | T1500Z | **T2500Z** | T3000Z | T1000A | T1500A | G10E | EH510 | EH520 | H1 |
| Finishing |  L/RFW  | **WBGT 060102 LFW** | 0,2 | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **WBGT 060104 LFW** | 0,4 | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **WBGT 080202 LFW** | 0,2 | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **WBGT 080204 LFW** | 0,4 | | | | | | | | | | | | | | | | | ○ | ○ | | | ○ | | | | |
| | | **WBGT 060102 RFW** | 0,2 | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **WBGT 060104 RFW** | 0,4 | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **WBGT 080202 RFW** | 0,2 | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| | | **WBGT 080204 RFW** | 0,4 | | | | | | | | | | | | | | | | | ○ | | | | ○ | | | | |
| Finishing |  L/RFX  | **WBGT 060102 LFX** | 0,2 | | | | | | | | | | | | ○ | ○ | | ● | ● | | | | | | | | | |
| | | **WBGT 060104 LFX** | 0,4 | | | | | | | | | | | | ○ | ○ | | ● | ● | | | | | | | | | |
| | | **WBGT 080202 LFX** | 0,2 | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **WBGT 080204 LFX** | 0,4 | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **WBGT 060102 RFX** | 0,2 | | | | | | | | | | | | | | | ● | ● | | | | | | | | | |
| | | **WBGT 060104 RFX** | 0,4 | | | | | | | | | | | | | | | ● | ● | | | | | | | | | |
| | | **WBGT 080202 RFX** | 0,2 | | | | | | | | | | | | | | | ○ | ○ | | | | | | | | | |
| | | **WBGT 080204 RFX** | 0,4 | | | | | | | | | | | | | | | ○ | | | | | | | | | | |
| Finishing |  L/RFY  | **WBGT 0601003 LFY** | 0,03 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **WBGT 060101 LFY** | 0,1 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **WBGT 060102 LFY** | 0,2 | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **WBGT 060104 LFY** | 0,4 | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **WBGT 080201 LFY** | 0,1 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **WBGT 080202 LFY** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **WBGT 080204 LFY** | 0,4 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **WBGT 060101 RFY** | 0,1 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | **WBGT 060102 RFY** | 0,2 | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **WBGT 060104 RFY** | 0,4 | | | | | | | | | | | | | | | ○ | ○ | | | | ○ | ○ | | | | |
| | | **WBGT 080201 RFY** | 0,1 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **WBGT 080202 RFY** | 0,2 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| | | **WBGT 080204 RFY** | 0,4 | | | | | | | | | | | | | | | | | | | | ○ | ○ | | | | |
| Finishing ~ Light Cut |  L/RW  | **WBGT 060102 LW** | 0,2 | | | | | | | | | | | | | | | ● | ● | | | | ○ | ● | | | | |
| | | **WBGT 060104 LW** | 0,4 | | | | | | | | | | | | | | | ● | ● | | | | ○ | ● | | | | |
| | | **WBGT 060102 RW** | 0,2 | | | | | | | | | | | | | | | ● | ● | | | | ○ | ● | | | | |
| | | **WBGT 060104 RW** | 0,4 | | | | | | | | | | | | | | | ● | ● | | | | ○ | ● | | | | |


● = Euro stock
○ = Japan stock

# W TRIGON TYPE
INSERTS FOR TURNING

**80° Trigon Type** | 11° Relief | With Insert Hole





| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WP_ _ | L | IC | S | $D_1$ |
| 1102.. | 4,3 | 6,35 | 2,38 | 2,8 |
| 1603.. | 6,5 | 9,525 | 3,18 | 4,4 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |



- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

## WPMT ●●●●●● NLB

● M-Class

| Application | Shape | ISO Cat. No. | RE | Carbide Coated P: AC8020P | Carbide Coated P: AC8025P | Carbide Coated P: AC8035P | Carbide Coated M: AC6020M | Carbide Coated M: AC6030M | Carbide Coated M: AC6040M | Carbide Coated P/M: AC630M | Carbide Coated K: AC4010K | Carbide Coated K: AC4015K | Carbide Coated K: AC420K | Carbide Coated H: AC503U | Carbide Coated S: AC5005S | Carbide Coated S: AC5015S | Carbide Coated S: AC5025S | Carbide Coated P/M: AC1030U | Carbide Coated P/M: AC530U | Cermet Coated P: T150Z | Cermet Coated P: T250Z | Cermet Coated P: T300Z | Cermet Uncoated P: T1000A | Cermet Uncoated P: T1500A | Carbide Uncoated K: G10E | Carbide Uncoated S: EH510 | Carbide Uncoated S: EH520 | Carbide Uncoated N: H1 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Light Cut |  NLB | **WPMT 110204 NLB** | 0,4 | ❍ | ❍ | ❍ | ❍ | | | | | | | | | | | | | ❍ | ❍ | ❍ | | | | | | |
| | | **WPMT 160308 NLB** | 0,8 | ❍ | ❍ | ❍ | ❍ | | | | | | | | | | | | | ❍ | ❍ | ❍ | | | | | | |



● = Euro stock
○ = Japan stock

# External Holders

D

D1–D46








Selection
ISO
Turning Holder Series ..... D2–7
Turning Holder Identification Table ..... D8
Calculation of The Cutting Edge Position ..... D9

T-REX Tool Holders
SumiTurn T-REX Tool Holders ..... D10–11

For High Performance Turning
**D Type Double Clamp Holders**
DC Type Holders ..... D12
DD Type Holders ..... D13
DS Type Holders ..... D14
DT Type Holders ..... D15
DV Type Holders ..... D16
DW Type Holders ..... D17

For General Turning
**P Type Lever Lock and**
**M Type Top & Hole Clamp Holders**
PC Type Holders ..... D18
PD Type Holders ..... D19
PS Type Holders ..... D20–21
PT / MT Type Holders ..... D22–23
PW / MW Type Holders ..... D24


For Solid CBN Inserts
C Type Clamp On Holders ..... D25–26
X Type Dimple Lock Holders ..... D27

Selection
Special for Back Facing
Small Product Turning
**Mini Holders Series** ..... D28–29
SBT Type Mini Holders ..... D30
PC / SC Type Mini Holders ..... D31
PD / SD Type Mini Holders ..... D32–33
PR Type Holders ..... D34
SR Type Holders ..... D35
SS Type Mini Holders ..... D36
ST Type Mini Holders ..... D37
SV Type Copying Holders ..... D38–39

**Polygon-Shank Holders** ..... D40


For High Performance Turning
**D Type Double Clamp Holders**
PSC**DC Type Holders ..... D41
PSC**DD Type Holders ..... D41
PSC**DS Type Holders ..... D41
PSC**DT Type Holders ..... D42
PSC**DW Type Holders ..... D42







For General Turning
**S Type Screw Clamp**
PSC**SC Type Holders ..... D43
PSC**SD Type Holders ..... D43
PSC**SS Type Holders ..... D43
PSC**ST Type Holders ..... D44
PSC**SV Type Holders ..... D44–45

| Application | For Neg. Inserts | For Pos. Inserts | Special Type for Hardened Steel |
|---|---|---|---|
| General Turning | **P Type Lever Lock Type**<br><br>⇨ D18–D22 | **P Type Lever Lock Type**<br><br>⇨ D31, D32 | **D Type Double Lock Type**<br><br>⇨ D12–D17 ⇨ D41–D42 |
| | **M Type Double Lock Type**<br><br>⇨ D23–D24 | **S Type Screw On Type**<br><br>D31–D33<br>⇨ D35–D37 ⇨D43–D45 | **C Type Top Clamp Type**<br><br>⇨ D25–D26 |
| Copying | **T-REX**<br><br>⇨D10–D11 | **S Type Screw On Type**<br><br>⇨D38–D39 ⇨D43–D45 | **D Type Double Lock Type**<br><br>⇨ D13, D16 ⇨ D41 |
| Parting-Off Grooving | **GNDS, GNDM, GNDMS Type General Grooving**<br><br>⇨F18, F22, F24 ⇨ F46-F49 | **GNDL, GNDLS Type Deep Grooving**<br><br>⇨ F18, F28 ⇨ F46-F49 | **GNDF, GNDFS Type Axial Grooving**<br><br>⇨ F34, F36 ⇨ F46-F49 |
| | **SCT and GWC Type**<br><br>⇨ F50-F54 ⇨ F51 | **Sumi Grip and Sumi Grip Jr.**<br><br>⇨ F55–F60 | **GWB Type Hard Grooving**<br><br>⇨ M54 ⇨ M55 |
| Threading | **SSTE and SSTI Type**<br>Pitch<br>{0,5–3 mm<br>48–8 Threads/inch<br><br>⇨ F62-F69 | **THE Type**<br>Pitch<br>{0,8–3 mm<br>24–10 Threads/inch<br><br>⇨ Stock in Jp. | **BNGG-TT Type Hard Threading**<br>Pitch<br>1–3 mm<br><br>⇨ M56 |

PSC Available in Polygon-Shank-Design



## External Turning



| Usage / Type | Cut - Off | Back Turning | Copying | General Turning | Grooving | Grooving & Cut-Off |
|---|---|---|---|---|---|---|
| | SCT Type | SBT Type | SV Type | P / S Type | GWC Type | GND Type |
| Cutting Edge Style |  |  |  |  |  |  |



## Holder Selection for Autolathe

| | Offset - 0 mm Type Holders | Offset - 0,5 mm Type Holders |
|---|---|---|
| Tooling |  |  |
| Features | Program correction is not necessary. | The position of cutting edge can be put in near guide bush through a program correction. |
| Holder Types | SDJC-X, SDAC-X<br>SDLC-X, SCAC-X<br>SVJC-X<br>(⇨ Stock in Japan) | PDJC, SDJC, SDAC<br>PCLC, SCAC<br>STAC, SVLC |







# External Tool Holder Series

Lever Lock System


































Double Lock (D)





D Type "Double Clamp" Holders
for high performance machining

## ■ TOOLING SELECTION

| Application | | | General Turning & Facing | | General Turning & Copying | | | General Turning | |
|---|---|---|---|---|---|---|---|---|---|
| Insert Type / System | | | 80° Diamond Type | | 55° Diamond Type | | T-REX 55° | 90° Square Type | |
| Screw Lock System | S Type Mini Holder |  |  **SCLC** ⇨ D31 |  **SCAC** ⇨ D31 |  **SDJC** ⇨ D32<br>**SDHC** ⇨ D32 |  **SDAC** ⇨ D33 | – | – |  **SSBC** ⇨ D36 |
| | | | – | – |  **SDNC** ⇨ D33 | – | – | – | – |
| Lever Lock System | P Type (* Side Lever Lock Type) |  |  **PCLC** (*) ⇨ D31 | – |  **PDJC** (*) ⇨ D32 | – | – |  **PSBN** ⇨ D20 |  **PSDN** ⇨ D20 |
| | | |  **PCBN** ⇨ D18 |  **PCLN** ⇨ D18 |  **PDJN** ⇨ D19 | – | – |  **PSKN** ⇨ D21 |  **PSSN** ⇨ D21 |
| Top-On Clamp System | C & M Type |  |  **CCLN** ⇨ D25 | – | – | – | – |  **CSBN** ⇨ D25 |  **CSKN** ⇨ D25 |
| Double Lock (D) Dimple Lock (X) | D & X Type |  |  **DCLN** ⇨ D12 |  **XCLN** ⇨ D27 |  **DDJN** ⇨ D13 | – |  **DTR** ⇨ D11 |  **XSBN** ⇨ D27 | – |
| | | | – | – |  **DDHN** ⇨ D13 |  **DDNN** ⇨ D13 | – |  **DSBN** ⇨ D14 |  **DSDN** ⇨ D14 |

Top-On Clamp System



Screw Lock System



## TOOLING SELECTION











| Application | | General Turning | | | Copying | | General Turning | Special Turning | |
|---|---|---|---|---|---|---|---|---|---|
| Insert Type / System | | 60° Triangle Type | | | 35° Diamond Type | | 80° Trigon Type | Round and Special Purpose Inserts | |
| Screw Lock System | S Type Mini Holder | STAC ⇨ D37 | STGC ⇨ D37 | – | SVJB ⇨ D38<br>SVLC ⇨ D39 | SVVB ⇨ D38 | – | SRDC ⇨ D35 | SRSC ⇨ D35 |
| | | – | – | – | SVPB ⇨ D38<br>SVPC ⇨ D39 | – | – | SBT ⇨ D30 | – |
| Lever Lock System | P Type | PTGN ⇨ D22 | PTFN ⇨ D22 | PTTN ⇨ D22 | – | – | PWLN ⇨ D24 | PRDC ⇨ D34 | PRGC ⇨ D34 |
| | | – | – | – | – | – | – | – | – |
| Top-On Clamp System | C & M Type | MTJN ⇨ D23 | MTXN ⇨ D23 | – | – | – | MWLN ⇨ D24 | CRDN ⇨ D26 | CRSN ⇨ D26 |
| Double Lock (D) Dimple Lock (X) | D & X Type | DTJN ⇨ D15 | DTFN ⇨ D15 | – | DVJN ⇨ D16 | – | DWLN ⇨ D17 | – | – |
| | | DTGN ⇨ D15 | – | – | DVQN ⇨ D16 | DVVN ⇨ D16 | – | – | – |

Polygon - Shank Holder - Produced According to ISO 26623-1



Negative Insert Type

## ■ TOOLING SELECTION

| Application | | | General Turning & Facing | | General Turning & Copying | | | General Turning | |
|---|---|---|---|---|---|---|---|---|---|
| Insert Type / System | | | 80° Diamond Type | | 55° Diamond Type | | T-REX 55° | 90° Square Type | |
| Screw Lock System | S Type Mini Holder |  |  **SCLC** ⇨ D43 | – |  **SDJC** ⇨ D43 | – | – | – |  **SSBC** ⇨ D43 |
| | | | – | – |  **SDHC** ⇨ D43 | – | – SRSCR | – | – |
| Double Lock (D) | D Type |  |  **DCLN** ⇨ D41 | – |  **DDJN** ⇨ D41 | – | – | – | – |
| | | | – | – |  **DDHN** ⇨ D41 | – | – |  **DSBN** ⇨ D41 | – |

## ■ Classification System for Polygon - Shank Holder

**PSC 40 - S C L C R 27 050 - 09**

- **PSC** — Polygon Shank
- **40** — Size (ø*D*)
- **S** — Clamping System: D: Double Clamp; S: Screw Clamp
- **C** — Insert Shape
- **L** — Holder Style
- **C** — Seat Clearance Angle: N = 0°; C = 7°; P = 11°
- **R** — Feed Direction: R: Right Hand; L: Left Hand; N: Neutral
- **27** — Size (*f*)
- **050** — Holder Length ($L_1$)
- **09** — Insert Cutting Edge Length



Positive Insert Type

## TOOLING SELECTION

| Application | | General Turning | | | Copying | | General Turning | Special Turning | |
|---|---|---|---|---|---|---|---|---|---|
| Insert Type / System | | 60° Triangle Type | | | 35° Diamond Type | | 80° Trigon Type | Round and Special Purpose Inserts | |
| Screw Lock System | S Type Mini Holder | **STJC** ⇨ D44 | – | – | **SVJB** ⇨ D44<br>**SVHB** ⇨ D44 | **SVJC** ⇨ D45<br>**SVHC** ⇨ D45 | – | – | – |
| | | – | – | – | **SVVB** ⇨ D44 | **SVVC** ⇨ D45 | – | – | – |
| Double Lock (D) | D Type | **DTJN** ⇨ D42 | – | – | – | – | **DWLN** ⇨ D42 | – | – |
| | | – | – | – | – | – | – | – | – |

## Classification System for Polygon - Shank Holder

**P S C 5 0 - S T J C R 3 5 0 6 0 - 1 6**


- **P S C** — Polygon Shank
- **5 0** — Size (ø*D*)
- **S** — Clamping System: D: Double Clamp; S: Screw Clamp
- **T** — Insert Shape
- **J** — Holder Style
- **C** — Seat Clearance Angle: N = 0°; C = 7°; P = 11°
- **R** — Feed Direction: R: Right Hand; L: Left Hand; N: Neutral
- **3 5** — Size (*f*)
- **0 6 0** — Holder Length ($L_1$)
- **1 6** — Insert Cutting Edge Length

# ISO Holders Identification

## ■ Catalogue Classification System for Tool Holders

| D | T | F | N | R | 25 | 25 | M | 16 | E |
|---|---|---|---|---|---|---|---|---|---|
| Clamping System Chart 1 | Insert Shape Chart 2 | Holder Style Chart 3 | Seat Clearance Angle Chart 4 | Feed Direction Chart 5 | Shank Height Chart 6 | Shank Width Chart 7 | Shank Length Chart 8 | Insert Size Chart 9 | For D-Type Euro-Inserts D□□□1506○○ |

**DTFNR2525M16**



Clamping: Double clamp system
Shape: Triangular insert with 91° approach angle
Shank: H = 25mm, W = 25mm, L = 150mm

External Holders

Chart 1






| Clamping System | | | | | |
|---|---|---|---|---|---|
| Symbol | Clamp Types | Example of Structure | Symbol | Clamp Types | Example of Structure |
| C | Top Clamp |  | M | Top & Hole Clamp Type |  |
| D | Double Clamp |  | P | Lever Lock Type (Insert is Supported by 1 face) |  |
| E | Pin Lock Type (Insert is supported by 1 face) |  | S | Screw Clamp Type |  |

Chart 2

| Insert Shape | | | | | |
|---|---|---|---|---|---|
| Symbol | Insert Shape | | Symbol | Insert Shape | |
| A | Parallelogram 85° | | M | Rhombic 86° | |
| B | Parallelogram 82° | | O | Octagonal | |
| C | Diamond 80° | | P | Pentagonal | |
| D | Diamond 55° | | R | Round | |
| E | Diamond 75° | | S | Square | |
| F | Diamond 50° | | T | Triangular | |
| H | Hexagonal | | V | Diamond 35° | |
| K | Parallelogram 55° | | W | Trigon | |
| L | Rectangular | | | | |

Chart 4

| Seat Clearance Angle | | |
|---|---|---|
| Symbol | Relief Angle | |
| A | 3° | |
| B | 5° | |
| C | 7° | |
| D | 15° | |
| E | 20° | |
| F | 25° | |
| G | 30° | |
| N | 0° | |
| P | 11° | |
| O | Special Angle | |

Chart 5




| Feed Direction | | | | | |
|---|---|---|---|---|---|
| Symbol | Right Hand Feed | Symbol | Neutral Feed | Symbol | Left Hand Feed |
| R |  | N |  | L |  |

Chart 3










| Holder Style | | | | | |
|---|---|---|---|---|---|
| Symbol | Shape | Offset | Symbol | Shape | Offset |
| A |  | Nil | L |  | With Offset |
| B |  | Nil | N |  | Nil |
| D |  | Nil | R |  | With Offset |
| E |  | Nil | S |  | With Offset |
| F |  | With Offset | T |  | With Offset |
| G |  | With Offset | U |  | With Offset |
| J |  | With Offset | W |  | With Offset |
| K |  | With Offset | Y |  | With Offset |

Chart 6

| Shank Height | |
|---|---|
| Symbol | Height (mm) |
| 12 | 12 |
| 16 | 16 |
| 20 | 20 |
| 25 | 25 |
| 32 | 32 |
| 40 | 40 |
| 50 | 50 |
| 00 | Round shank, Shank Diamater is Shown for Round Shank, |

2 digits are used for each dimension in mm.

Chart 7

| Shank Width | |
|---|---|
| Symbol | Width (mm) |
| 12 | 12 |
| 16 | 16 |
| 20 | 20 |
| 25 | 25 |
| 32 | 32 |
| 40 | 40 |
| 50 | 50 |

Chart 8

| Shank Length | |
|---|---|
| Symbol | Length (mm) |
| F | 80 |
| H | 100 |
| K | 125 |
| M | 150 |
| N | 160 |
| P | 170 |
| Q | 180 |
| S | 250 |
| T | 300 |
| U | 350 |

For some Products, a Hypen is used Instead of an alphabet.

Chart 9

| Cutting Edge | |
|---|---|
| Symbol | Length (mm) |

Eg. for Triangle Inserts:





























| | |
|---|---|
| 06 | 6,9 |
| 08 | 8,2 |
| 09 | 9,6 |
| 11 | 11,0 |
| 16 | 16,5 |
| 22 | 22,0 |
| 27 | 27,5 |
| 33 | 33,0 |

For Round Inserts:

| | |
|---|---|
| 10 | 10 |
| 12 | 12 |
| 16 | 16 |
| 20 | 20 |
| 25 | 25 |
| 32 | 32 |



## ■ Cutting Edge Dimensions by Corner Radius

(This table shows X and Y dimensions based on 0° approach angle cutting edge inclination)

| Holders | | | Dimensions(mm) | | | Holders | | | Dimensions(mm) | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| Symbol | Shapes | Corner Shapes | RE | X | Y | Symbol | Shapes | Corner Shapes | RE | X | Y |
| A |  |  | 0,4 | 0,291 | – | K |  |  | 0,4 | 0,024 | 0,089 |
| | | | 0,8 | 0,581 | – | | | | 0,8 | 0,048 | 0,178 |
| | | | 1,2 | 0,872 | – | | | | 1,2 | 0,072 | 0,268 |
| | | | 1,6 | 1,162 | – | | | | 1,6 | 0,096 | 0,357 |
| | | | 2,4 | 1,743 | – | | | | 2,4 | 0,143 | 0,535 |
| B |  |  | 0,4 | 0,089 | 0,024 | L |  |  | 0,4 | 0,040 | 0,040 |
| | | | 0,8 | 0,178 | 0,048 | | | | 0,8 | 0,079 | 0,079 |
| | | | 1,2 | 0,268 | 0,072 | | | | 1,2 | 0,119 | 0,119 |
| | | | 1,6 | 0,357 | 0,096 | | | | 1,6 | 0,159 | 0,159 |
| | | | 2,4 | 0,535 | 0,143 | | | | 2,4 | 0,238 | 0,238 |
| D |  |  | 0,4 | 0,164 | 0,164 | N |  |  | 0,4 | 0,463 | 0,263 |
| | | | 0,8 | 0,329 | 0,329 | | | | 0,8 | 0,925 | 0,471 |
| | | | 1,2 | 0,493 | 0,493 | | | | 1,2 | 1,388 | 0,707 |
| | | | 1,6 | 0,658 | 0,658 | | | | 1,6 | 1,850 | 0,943 |
| | | | 2,4 | 0,986 | 0,986 | | | | 2,4 | 2,776 | 1,414 |
| E |  |  | 0,4 | 0,396 | 0,229 | S |  |  | 0,4 | 0,164 | 0,164 |
| | | | 0,8 | 0,793 | 0,458 | | | | 0,8 | 0,329 | 0,329 |
| | | | 1,2 | 1,190 | 0,687 | | | | 1,2 | 0,493 | 0,493 |
| | | | 1,6 | 1,587 | 0,916 | | | | 1,6 | 0,658 | 0,658 |
| | | | 2,4 | 2,381 | 1,374 | | | | 2,4 | 0,986 | 0,986 |
| F |  |  | 0,4 | – | 0,291 | T |  |  | 0,4 | 0,396 | 0,229 |
| | | | 0,8 | – | 0,581 | | | | 0,8 | 0,793 | 0,458 |
| | | | 1,2 | – | 0,872 | | | | 1,2 | 1,190 | 0,687 |
| | | | 1,6 | – | 1,162 | | | | 1,6 | 1,587 | 0,916 |
| | | | 2,4 | – | 1,743 | | | | 2,4 | 2,381 | 1,374 |
| G |  |  | 0,4 | 0,291 | – | U |  |  | 0,4 | 0,253 | 0,058 |
| | | | 0,8 | 0,581 | – | | | | 0,8 | 0,506 | 0,116 |
| | | | 1,2 | 0,872 | – | | | | 1,2 | 0,759 | 0,175 |
| | | | 1,6 | 1,162 | – | | | | 1,6 | 1,013 | 0,233 |
| | | | 2,4 | 1,743 | – | | | | 2,4 | 1,519 | 0,350 |
| J |  |  | 0,4 | 0,344 | 0,033 | Y |  |  | 0,4 | 0,002 | 0,033 |
| | | | 0,8 | 0,687 | 0,079 | | | | 0,8 | 0,005 | 0,066 |
| | | | 1,2 | 1,031 | 0,118 | | | | 1,2 | 0,008 | 0,099 |
| | | | 1,6 | 1,375 | 0,157 | | | | 1,6 | 0,011 | 0,132 |
| | | | 2,4 | 2,062 | 0,236 | | | | 2,4 | 0,017 | 0,198 |

### ● Calculation of the Nose Radius Dimensions

(Unit in mm)

| Insert Shape | | Calculation |
|---|---|---|
|  | Triangle | $B = \frac{3}{2}A - RE$ |
|  | Square | $B=(\sqrt{2}-1) \times (\frac{A}{2}-RE)$ |
|  | Rhombic | $B=\{\frac{1}{Sin(\theta/2)}-1\} \times (\frac{A}{2}-RE)$ |

### Figures of „A“ and „RE“ to calculate Figure „B“

| I.C. size (inch) | | „øA“ dimensions (mm) |
|---|---|---|
| – | 5/32 | 3,9688 |
| – | 6/32 | 4,7625 |
| – | 7/32 | 5,5562 |
| 2/8 | 8/32 | 6,3500 |
| – | (0) | 7,9375 |
| 3/8 | – | 9,5250 |
| 4/8 | – | 12,7000 |
| 5/8 | – | 15,8750 |
| 6/8 | – | 19,0500 |
| 8/8 | – | 25,4000 |

| Nose symbol | Size (inch) | „RE“ dimension (mm) |
|---|---|---|
| 02 | (0) | 0,203 |
| 04 | 1/64 | 0,397 |
| 08 | 2/64 | 0,794 |
| 12 | 3/64 | 1,191 |
| 16 | 4/64 | 1,588 |
| 24 | 6/64 | 2,389 |

# T-REX Tool Holders







SumiTurn T-REX

● T-REX clamping for maximum rigidity 50 % more cutting edges than a DNMG Insert





## ■ Advantages

● T-REX Inserts for Maximum Economy


With 6 cutting edges and a 55 degree included angle - T-Rex is the intelligent alternative to profile turning with a traditional 4 edge DNMG insert.

● Biting Performance from T-REX Teeth

The double clamp tool holder and powerful teeth of T-REX lock the insert to eliminate movement, dramatically improving tool life, machining accuracy, and cutting edge security.





● Application Range





## ■ Application Examples

● 20Cr4 Shaft




33 % cost saving





Insert: TRM551708-GU, AC2000
Cutting data: $v_c$= 150 m/min, f = 0,25 mm/rev, $a_p$ < 2,0 mm, wet

● 25CrMo4 Gear




1,3 times long tool life




Insert: TRM551708-LU, AC900G
Cutting data: $v_c$= 220 m/min, f = 0,2–0,3 mm/rev, $a_p$ < 1,0 mm, wet


## ■ Recommendations

● Depth of Cut




Max. $a_p$ = 2,5 mm


● Approach Angle




(*) Angle of major cutting edge

C-Type: 95,5°
Q-Type: 107,5°

● Insert Clamping





Recommended Tightening Torque (N·m)


● = Euro stock
○ = Japan stock

SumiTurn


## External Turning & Copying

### DTR55C
Profiling






### Spare Parts




### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Screw | Shim | Screw | Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | |
| DTR 55C-R/L 2020-K17 | ● | ● | 20 | 20 | 20 | 125 | 35 | 25 | TRCP3 | S-SP4-20 | BX0520 3,5-4,5 Nm | TRW5505 | BFTX0307N 2,0 Nm | TSW040 | TRX10(*) |
| DTR 55C-R/L 2525-M17 | ● | ● | 25 | 25 | 25 | 150 | 35 | 32 | | | | | | | |


(*) Note: Wrench (TRX) for shim clamp screw is not included.

### DTR55Q
Profiling






### Spare Parts



### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Screw | Shim | Screw | Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | |
| DTR 55Q-R/L 2020-K17 | ● | ● | 20 | 20 | 20 | 125 | 35 | 28,5 | TRCP3 | S-SP4-20 | BX0520 3,5-4,5 Nm | TRW5505 | BFTX0307N 2,0 Nm | TSW040 | TRX10(*) |
| DTR 55Q-R/L 2525-M17 | ● | ● | 25 | 25 | 25 | 150 | 35 | 32 | | | | | | | |

(*) Note: Wrench (TRX) for shim clamp screw is not included.

### Inserts

| Applic. | Shape | Ordering No. | RE | Coated Carbide AC8015P | Coated Carbide AC8025P | Coated Carbide AC630M | Coated Cermet T3000Z |
|---|---|---|---|---|---|---|---|
| Fine Finishing |  FL | TRM 551704-FL | 0,4 | | ❍ | | ❍ |
| | | 551708-FL | 0,8 | | ❍ | | ❍ |
| Finishing |  LU | TRM 551704-LU | 0,4 | ● | ❍ | | ❍ |
| | | 551708-LU | 0,8 | ● | ❍ | | ❍ |
| | | 551712-LU | 1,2 | | ❍ | | ❍ |
| |  SU | TRM 551704-SU | 0,4 | | ❍ | ● | ❍ |
| | | 551708-SU | 0,8 | | ❍ | ● | ❍ |
| | | 551712-SU | 1,2 | | ❍ | | |
| Light Cut |  GU | TRM 551704-GU | 0,4 | | ❍ | ● | |
| | | 551708-GU | 0,8 | | ❍ | ● | |
| | | 551712-GU | 1,2 | | ❍ | ❍ | |




Application P Steel
M Stainless steel




## Characteristics

Insert is clamping firmly for improved fracture resistance.
High indexing accuracy improves machining accuracy.
Insert can be changed from below the holder.
Suitable for high efficiency machining and interrupted cutting in hardened steel.



## Clamp Mechanism


Secured in two directions and supported by two faces.




Insert can be changed from below the holder.

## Index Accuracy Comparison (Length Wise)

### D Type Tool Holders




### Lever Lock




## General Turning and Facing



## Inserts


Eg.




N-GU

❶ CNMG 120408 N-GU
❷ CNMG 160608 N-GU
❸ CNMM 190612 N-HG
❹ CNMM 250924 N-HU

**DCLN**






## Spare Parts

## Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| DCLN R/L 2020 K12 | ● | ● | 20 | 20 | 20 | 125 | 32 | 25 | SCP2 | | 5,0 (N·m) | CNS1204 | BFTX0409N 3,4 (N·m) | TRX15(*) | LH040 LH025 | ❶ |
| DCLN R/L 2525 M12 | ● | ● | 25 | 25 | 25 | 150 | 32 | 32 | | | | | | | | |
| DCLN R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 32 | 32 | SCP3 | | 5,0 (N·m) | CNS1606 | BFTX0509N 5,0 (N·m) | TRX20(*) | LH040 LH025 | ❷ |
| DCLN R/L 3232 P16 | ● | ● | 32 | 32 | 32 | 170 | 32 | 40 | | | | | | | | |
| DCLN R/L 3232 P19 | ● | ● | 32 | 32 | 32 | 170 | 42 | 40 | SCP5 | | 5,0 (N·m) | CNS1906 | BFTX0511N 5,0 (N·m) | TRX20(*) | LH040 LH025 | ❸ |
| DCLN R/L 4040 S19 | ● | ● | 40 | 40 | 40 | 250 | 42 | 50 | | | | | | | | |
| DCLN R/L 4040 S25 | ❍ | ● | 40 | 40 | 40 | 250 | 53 | 50 | SCP6 | | 6,0 (N·m) | CNS2509 | BFTX0615N 7,5 (N·m) | TRD25(*) | LH060 | ❹ |

(*) Note: Wrench (TRX / TRD) for shim clamp screw is not included.




● = Euro stock
○ = Japan stock


(N·m) Recommended Tightening Torque (N·m)

## General Turning and Copying



### DDJN






#### Inserts

Eg.



N-GU

❶ DNMG 150408 N-GU
❷ DNMG 150608 N-GU


#### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| DDJN R/L 2020 K15 | ❍ | ● | 20 | 20 | 20 | 125 | 38 | 25 | SCP2 | | 5,0 (N·m) | DNS1504 | BFTX0409N 3,4 (N·m) | TRX15(*) | LH040 | ❶ |
| DDJN R/L 2020 K15E | ● | ● | 20 | 20 | 20 | 125 | 38 | 25 | | | | DNS1506 | | | | ❷ |
| DDJN R/L 2525 M15 | ❍ | | 25 | 25 | 25 | 150 | 38 | 32 | | | | DNS1504 | | | | ❶ |
| DDJN R/L 2525 M15E | ● | ● | 25 | 25 | 25 | 150 | 38 | 32 | | | | DNS1506 | | | | ❷ |

(*) Note: Wrench (TRX) for shim clamp screw is not included.

### DDHN






#### Inserts

Eg.



N-GU

❷ DNMG 150608 N-GU


#### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| DDHN R/L 2020 K15E | ● | ● | 20 | 20 | 20 | 125 | 35 | 25 | SCP2 | | 5,0 (N·m) | DNS1506 | BFTX0409N 3,4 (N·m) | TRX15(*) | LH040 | ❷ |
| DDHN R/L 2525 M15E | ● | ● | 25 | 25 | 25 | 150 | 35 | 32 | | | | | | | | |

(*) Note: Wrench (TRX) for shim clamp screw is not included.

### DDNN






#### Inserts

Eg.



N-GU

❷ DNMG 150608 N-GU

#### Holders

Above figures show right hand tools.


| Cat. No. | Stock | Dimensions (mm) | | | | | | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | LH | WF | | | | | | | | |
| DDNN N 2020 K15E | ● | 20 | 20 | 20 | 125 | 40 | 10,5 | SCP2 | | 5,0 (N·m) | DNS1506 | BFTX0409N 3,4 (N·m) | TRX15(*) | LH040 | ❷ |
| DDNN N 2525 M15E | ● | 25 | 25 | 25 | 150 | 40 | 13,0 | | | | | | | | |


(*) Note: Wrench (TRX) for shim clamp screw is not included.

General Turning and Facing



## DSBN






### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF |
| DSBN R/L 2525 M12 | | ❍ | 25 | 25 | 25 | 150 | 36 | 22 |
| DSBN R/L 3232 P19 | ● | ● | 32 | 32 | 32 | 170 | 45 | 27 |
| DSBN R/L 4040 S2507 | ❍ | ❍ | 40 | 40 | 40 | 250 | 58 | 35 |
| DSBN R/L 4040 S2509 | ❍ | ❍ | 40 | 40 | 40 | 250 | 58 | 35 |

### Inserts

Eg.



N-UZ, N-HU


❶ SNMG 190612 N-UZ
❷ SNMM 250724 N-HU
❸ SNMM 250924 N-HU


### Spare Parts

| Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|
| SCP2 | | 5,0 (N·m) | SNS1204 | BFTX0409N | TRX15(*) | LH040, LH025 | |
| SCP5 | | 5,0 (N·m) | SNS1906 | BFTX0511N 5,0 (N·m) | TRX20(*) | LH040, LH025 | ❶ |
| SCP6 | | 6,0 (N·m) | SNS2507 | BFTX0615N | TRD25(*) | LH060 | ❷ |
| | | | SNS2509 | 7,5 (N·m) | | | ❸ |

(*) Note: Wrench (TRX / TRD) for shim clamp screw is not included.

## DSDN






### Holders

Above figures show right hand tools.

| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | LH | WF |
| DSDN N 3232 P19 | ● | 32 | 32 | 32 | 170 | 50 | 16 |
| DSDN N 4040 S2507 | | 40 | 40 | 40 | 250 | 63 | 20 |
| DSDN N 4040 S2509 | | 40 | 40 | 40 | 250 | 63 | 20 |

### Inserts

Eg.



N-UZ, N-HU

❶ SNMG 190612 N-UZ
❷ SNMM 250724 N-HU
❸ SNMM 250924 N-HU

### Spare Parts

| Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|
| SCP5 | | 5,0 (N·m) | SNS1906 | BFTX0511N 5,0 (N·m) | TRX20(*) | LH040, LH025 | ❶ |
| SCP6 | | 6,0 (N·m) | SNS2507 | BFTX0615N | TRD25(*) | LH060 | ❷ |
| | | | SNS2509 | 7,5 (N·m) | | | ❸ |

(*) Note: Wrench (TRX / TRD) for shim clamp screw is not included.





● = Euro stock
○ = Japan stock


(N·m) Recommended Tightening Torque (N·m)


# External Tool Holders
# D Type (Double Clamp)



## General Turning and Facing

## DTJN






### Inserts


Eg.



N-GU

❶ TNMG 160408 N-GU

### Spare Parts




### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| DTJN R/L 2020 K16 | ● | | 20 | 20 | 20 | 125 | 31 | 25 | SCP1 | | 5,0 N·m | TNS1604 | BFTX0307N 2,0 N·m | TRX10(*) | LH040 | ❶ |
| DTJN R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 31 | 32 | | | | | | | | |

(*) Note: Wrench (TRX) for shim clamp screw is not included.

## DTGN






### Inserts


Eg.



N-GU

❶ TNMG 160408 N-GU

### Spare Parts




### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| DTGN R/L 2020 K16 | ❍ | | 20 | 20 | 20 | 125 | 31 | 25 | SCP1 | | 5,0 N·m | TNS1604 | BFTX0307N 2,0 N·m | TRX10(*) | LH040 | ❶ |
| DTGN R/L 2525 M16 | ● | | 25 | 25 | 25 | 150 | 31 | 32 | | | | | | | | |

(*) Note: Wrench (TRX) for shim clamp screw is not included.

## DTFN






### Inserts


Eg.



N-GU

❶ TNMG 160408 N-GU

### Spare Parts



### Holders

Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| DTFN R/L 2020 K16 | ❍ | ❍ | 20 | 20 | 20 | 125 | 30 | 25 | SCP1 | | 5,0 N·m | TNS1604 | BFTX0307N 2,0 N·m | TRX10(*) | LH040 | ❶ |
| DTFN R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 30 | 32 | | | | | | | | |


(*) Note: Wrench (TRX) for shim clamp screw is not included.

General Turning and Copying



## DVJN






### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF |
| DVJN R/L 2020 K16 | ● | ● | 20 | 20 | 20 | 125 | 35 | 25 |
| DVJN R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 35 | 32 |

### Inserts


Eg.



❶ VNMG 160408 N-GU

N-GU


### Spare Parts




| Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|
| SCP4 | | 5,0 (N·m) | VNS1604 | BFTX0307N 2,0 (N·m) | TRX10(*) | LH040 LH025 | ❶ |

(*) Note: Wrench (TRX) for shim clamp screw is not included.

## DVQN






### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF |
| DVQN R/L 2020 K16 | ● | ● | 20 | 20 | 20 | 125 | 35 | 25 |
| DVQN R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 35 | 32 |

### Inserts


Eg.



❶ VNMG 160408 N-GU

N-GU


### Spare Parts




| Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|
| SCP4 | | 5,0 (N·m) | VNS1604 | BFTX0307N 2,0 (N·m) | TRX10(*) | LH040 LH025 | ❶ |

(*) Note: Wrench (TRX) for shim clamp screw is not included.

## DVVN






### Holders

Above figures show right hand tools.

| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | LH | WF |
| DVVN N 2020 K16 | ● | 20 | 20 | 20 | 125 | 37 | 10,0 |
| DVVN N 2525 M16 | ● | 25 | 25 | 25 | 150 | 37 | 12,5 |

### Inserts


Eg.



❶ VNMG 160408 N-GU

N-GU

### Spare Parts



| Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|
| SCP4 | | 5,0 (N·m) | VNS1604 | BFTX0307N 2,0 (N·m) | TRX10(*) | LH040 LH025 | ❶ |

(*) Note: Wrench (TRX) for shim clamp screw is not included.






● = Euro stock


(N·m) Recommended Tightening Torque (N·m)

## General Turning and Facing



**DWLN**






## Inserts




## Spare Parts

## Holders

Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| DWLN R/L 2020 K08 | ● | ● | 20 | 20 | 20 | 125 | 32 | 25 | SCP2 | | | WNS0804 | BFTX0409N | TRX15(*) | LH040 | ❶ |
| DWLN R/L 2525 M08 | ● | ● | 25 | 25 | 25 | 150 | 32 | 32 | | | 5,0 N·m | | 3,4 N·m | | LH025 | |


(*) Note: Wrench (TRX) for shim clamp screw is not included.

General Turning and Facing




## PCBN






### Inserts





### Holders


Above figures show right hand tools.

### Spare Parts


| Cat. No. | Stock | | Dimensions (mm) | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | |
| PCBN R/L 2020 K12 | ● | ❍ | 20 | 20 | 20 | 125 | 27 | 17 | LCL4SD | LCS42BS-SD | LSC42SD | LSP4SD | LH030 | ❶ |
| PCBN R/L 2525 M12 | ● | ● | 25 | 25 | 25 | 150 | 27,7 | 22 | | | | | | |
| PCBN R/L 3225 P12 | | ● | 32 | 32 | 25 | 170 | 27,7 | 22 | | | | | | |
| PCBN R/L 2525 M16 | | ● | 25 | 25 | 25 | 150 | 31,7 | 22 | LCL5SD | LCS5B-SD | LSC53SD | LSP5SD | LH030 | ❷ |
| PCBN R/L 3225 P16 | | | 32 | 32 | 25 | 170 | 31,7 | 22 | | | | | | |
| PCBN R/L 3232 P19 | ● | ● | 32 | 32 | 32 | 170 | 37,9 | 27 | LCL6SD | LCS6B-SD | LSC63SD | LSP6SD | LH040 | ❸ |

## PCLN






### Inserts




### Holders

Above figures show right hand tools.

### Spare Parts

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | |
| PCLN R/L 1616 H09 | ● | ● | 16 | 16 | 16 | 100 | 25,7 | 20 | LCL3SD | LCS3TB-SD | LSC32SD | LSP3SD | LH025 | ❶ |
| PCLN R/L 2020 K09 | ● | | 20 | 20 | 20 | 125 | 27 | 25 | | | | | | |
| PCLN R/L 2525 M09 | | | 25 | 25 | 25 | 150 | 27 | 32 | | | | | | |
| PCLN R/L 1616 H12 | ● | ● | 16 | 16 | 16 | 100 | 26,1 | 20 | LCL4SD | LCS 4CA / LCS42BS-SD | LSC42SD | LSP4SD | LH030 | ❷ |
| PCLN R/L 2020 K12 | ● | ❍ | 20 | 20 | 20 | 125 | 27,4 | 25 | | | | | | |
| PCLN R/L 2525 M12 | ● | ● | 25 | 25 | 25 | 150 | 28 | 32 | | | | | | |
| PCLN R/L 3225 P12 | ● | ● | 32 | 32 | 25 | 170 | 28 | 32 | | | | | | |
| PCLN R/L 2525 M16 | ● | | 25 | 25 | 25 | 150 | 32,6 | 32 | LCL5SD | LCS5B-SD | LSC53SD | LSP5SD | LH030 | ❸ |
| PCLN R/L 3225 P16 | ● | | 32 | 32 | 25 | 170 | 32,6 | 32 | | | | | | |
| PCLN R/L 3232 P16 | ● | ● | 32 | 32 | 32 | 170 | 32,6 | 40 | | | | | | |
| PCLN R/L 2525 M19 | ● | ● | 25 | 25 | 25 | 150 | 37 | 32 | LCL6SD | LCS6B-SD | LSC63SD | LSP6SD | LH040 | ❹ |
| PCLN R/L 3225 P19 | ❍ | | 32 | 32 | 32 | 170 | 38 | 32 | | | | | | |
| PCLN R/L 3232 P19 | | | 32 | 32 | 32 | 170 | 38 | 40 | | | | | | |
| PCLN R/L 4040 S19 | | | 40 | 40 | 40 | 250 | 37,8 | 50 | | | | | | |







● = Euro stock
○ = Japan stock

# External Tool Holders
# P Type (Lever Lock)




## General Turning and Facing




Above figures show right hand tools.

## Inserts




## Spare Parts


## Holders


| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | |
| PDJN R/L 1616 H11 | ● | | 16 | 16 | 16 | 100 | 30 | 20 | | LCL3D-SD | LCS3TB-SD | LSD32SD | LSP3SD | LH025 | ❶ |
| PDJN R/L 2020 K11 | ● | ● | 20 | 20 | 20 | 125 | 30 | 25 | | | | | | | |
| PDLN R/L 2525 M11 | ● | ● | 25 | 25 | 25 | 150 | 30 | 32 | | | | | | | |
| PDJN R/L 2020 K15 | ● | ● | 20 | 20 | 20 | 125 | 34,7 | 25 | | LCL4D-SD | LCS5DB-SD | LSD42SD | LSP4SD | LH030 | ❷ |
| PDJN R/L 2525 M15 | ● | ● | 25 | 25 | 25 | 150 | 34,7 | 32 | | | | | | | |
| PDJN R/L 3225 P15 | ● | ● | 32 | 32 | 25 | 170 | 34,7 | 32 | | | | | | | |

## General Turning and Chamfering



## PSBN







### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | |
| PSBN R/L 2020 K12 | ● | | 20 | 20 | 20 | 125 | 27,5 | 17 | LCL4SD | LCS42BS-SD | LSS42SD | LSP4SD | LH030 | ❶ |
| PSBN R/L 2525 M12 | ● | ● | 25 | 25 | 25 | 150 | 27,5 | 22 | | | | | | |
| PSBN R/L 2525 M15 | | ● | 25 | 25 | 25 | 150 | 32 | 22 | LCL5SD | LCS5B-SD | LSS53SD | LSP5SD | LH030 | ❷ |
| PSBN R/L 3225 P15 | ● | ● | 32 | 32 | 25 | 170 | 32 | 22 | | | | | | |
| PSBN R/L 3232 P19 | ● | ● | 32 | 32 | 32 | 170 | 39,2 | 27 | LCL6SD | LCS6B-SD | LSS63SD | LSP6SD | LH040 | ❸ |

### Inserts

Eg.




❶ SNMG 120408 N-GU
❷ SNMG 150612 N-GU
❸ SNMM 190612 N-HG


N-GU N-HG

### Spare Parts



## PSDN







### Holders

| Cat. No. | Stock | Dimensions (mm) | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | LH | WF | | | | | | |
| PSDN N 1616 H09 | ● | 16 | 16 | 16 | 100 | 21 | 8,3 | LCL3SD | LCS 3TB-SD | LSS32SD | LSP3SD | LH025 | ❶ |
| PSDN N 2020 K12 | ● | 20 | 20 | 20 | 125 | 27,6 | 10,3 | LCL4SD | LCS42BS-SD | LSS42SD | LSP4SD | LH030 | ❷ |
| PSDN N 2525 M12 | ● | 25 | 25 | 25 | 150 | 27,6 | 12,8 | | | | | | |
| PSDN N 3225 P12 | ● | 32 | 32 | 25 | 170 | 27,6 | 12,8 | | | | | | |
| PSDN N 3225 P19 | | 32 | 32 | 25 | 170 | 40,6 | 13 | LCL6SD | LCS6B-SD | LSS63SD | LSP6SD | LH040 | ❸ |
| PSDN N 3232 P19 | ● | 32 | 32 | 32 | 170 | 40,6 | 16,5 | | | | | | |

### Inserts

Eg.



❶ SNMG 090308 N-UG
❷ SNMG 120408 N-GU
❸ SNMM 190612 N-HG

N-GU N-HG

### Spare Parts






● = Euro stock




## General Turning and Facing

**PSKN**




### Inserts





### Spare Parts

### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | |
| PSKN R/L 2020 K12 | ● | | 20 | 20 | 20 | 125 | 22,7 | 17 | | LCL4SD | LCS42BS-SD | LSS42SD | LSP4SD | LH030 | ❶ |
| PSKN R/L 2525 M12 | ● | ● | 25 | 25 | 25 | 150 | 22,7 | 32 | | | | | | | |
| PSKN R/L 2525 M15 | | | 25 | 25 | 25 | 150 | 32 | 32 | | LCL5SD | LCS5B-SD | LSS53SD | LSP5SD | LH030 | ❷ |
| PSKN R/L 3225 P15 | | | 32 | 32 | 25 | 170 | 32 | 32 | | | | | | | |
| PSKN R/L 3232 P19 | | | 32 | 32 | 32 | 170 | 33,7 | 40 | | LCL6SD | LCS6B-SD | LSS63SD | LSP6SD | LH040 | ❸ |

**PSSN**




### Inserts




### Spare Parts

### Holders


Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LF2 | LH | WF | | | | | | | |
| PSSN R/L 2020 K12 | ● | ● | 20 | 20 | 20 | 125 | 116,7 | 29,3 | 25 | | LCL4SD | LCS42BS-SD | LSS42SD | LSP4SD | LH030 | ❶ |
| PSSN R/L 2525 M12 | ● | ● | 25 | 25 | 25 | 150 | 141,7 | 29,3 | 32 | | | | | | | |
| PSSN R/L 3225 P12 | ● | | 32 | 32 | 25 | 170 | 161,7 | 29,3 | 32 | | | | | | | |
| PSSN R/L 2525 M15 | ● | ● | 25 | 25 | 25 | 150 | 139,8 | 32 | 32 | | LCL5SD | LCS5B-SD | LSS53SD | LSP5SD | LH030 | ❷ |
| PSSN R/L 3225 P15 | | | 32 | 32 | 25 | 170 | 159,8 | 32 | 32 | | | | | | | |
| PSSN R/L 3232 P15 | ● | | 32 | 32 | 32 | 170 | 159,8 | 32 | 40 | | | | | | | |
| PSSN R/L 3232 P19 | ● | ● | 32 | 32 | 32 | 170 | 157,5 | 40,2 | 40 | | LCL6SD | LCS6B-SD | LSS63SD | LSP6SD | LH040 | ❸ |

## General Turning and Facing




## PTGN






### Inserts




### Spare Parts





### Holders

Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | |
| PTGN R/L 1616 H16 | ● | | 16 | 16 | 16 | 100 | 20 | 20 | LCL3SD | LCS3TB-SD | LST317SD | LSP3SD | LH025 | ❶ |
| PTGN R/L 2020 K16 | ● | ● | 20 | 20 | 20 | 125 | 20 | 25 | | | | | | |
| PTGN R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 22,2 | 32 | | | | | | |
| PTGN R/L 2525 M22 | ● | ● | 25 | 25 | 25 | 150 | 28,7 | 32 | LCL4SD | LCS42BS-SD | LST42SD | LSP4SD | LH030 | ❷ |
| PTGN R/L 3225 P22 | ● | | 32 | 32 | 25 | 170 | 28,7 | 32 | | | | | | |
| PTGN R/L 3232 P22 | | | 32 | 32 | 32 | 170 | 28,7 | 32 | | | | | | |

## PTFN






### Inserts




### Spare Parts





### Holders

Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | |
| PTFN R/L 1616 H16 | | | 16 | 16 | 16 | 100 | 19,7 | 20 | LCL3SD | LCS3TB-SD | LST317SD | LSP3SD | LH025 | ❶ |
| PTFN R/L 2020 K16 | ● | ● | 20 | 20 | 20 | 125 | 20,2 | 25 | | | | | | |
| PTFN R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 20,2 | 32 | | | | | | |
| PTFN R/L 2525 M22 | ● | | 25 | 25 | 25 | 150 | 25,2 | 32 | LCL4SD | LCS42BS-SD | LST42SD | LSP4SD | LH030 | ❷ |
| PTFN R/L 3225 P22 | ● | | 32 | 32 | 25 | 170 | 25,2 | 32 | | | | | | |

## PTTN






### Inserts




### Spare Parts



### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | |
| PTTN R/L 2020 K16 | ❍ | | 20 | 20 | 20 | 125 | 25,9 | 17 | LCL3SD | LCS3TB-SD | LST317SD | LSP3SD | LH025 | ❶ |
| PTTN R/L 2525 M16 | ● | | 25 | 25 | 25 | 150 | 25,9 | 22 | | | | | | |
| PTTN R/L 3225 P22 | | | 31 | 32 | 25 | 170 | 31,9 | 22 | LCL4SD | LCS42BS-SD | LST42SD | LSP4SD | LH030 | ❷ |




● = Euro stock
○ = Japan stock

Recommended Tightening Torque (N·m)


## General Turning and Copying



### MTJN




#### Inserts





#### Spare Parts

#### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Wedge | Shim pin | Shim | Clamp bold | Nut | Ring | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| MTJN R/L 2020-33 (K16) | ● | ● | 20 | 20 | 20 | 125 | 37 | 25 | MMW30 | MP317 / MP320 | STW323 | BHA0525 4,0 Nm | CPM32N | ER04 | LH030 | ❶ |
| MTJN R/L 2525-33 (M16) | ● | ● | 25 | 25 | 25 | 150 | 37 | 32 | | | | | | | | |
| MTJN R/L 2525-43 (M22) | ● | ● | 25 | 25 | 25 | 150 | 37 | 32 | MMW40 | MP420 | STW434 | BHA0625 4,5 Nm | CPM43N | ER05 | LH030 LH040 | ❷ |
| MTJN R/L 3225-43 (P22) | ❍ | ❍ | 32 | 32 | 25 | 170 | 37 | 32 | | | | | | | | |

### MTXN




#### Inserts





#### Spare Parts

#### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Wedge | Shim pin | Shim | Clamp bold | Nut | Ring | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| MTXN R/L 2020-33 (K16) | ❍ | ❍ | 20 | 20 | 20 | 125 | 32 | 25 | MMW30 | MP317 / MP320 | STW323 | BHA0525 4,0 Nm | CPM32N | ER04 | LH030 | ❶ |
| MTXN R/L 2525-33 (M16) | ❍ | ❍ | 25 | 25 | 25 | 150 | 32 | 32 | | | | | | | | |
| MTXN R/L 2525-43 (M22) | | | 25 | 25 | 25 | 150 | 38 | 32 | MMW40 | MP420 | STW434 | BHA0625 4,5 Nm | CPM43N | ER05 | LH030, 040 | ❷ |




## General Turning and Facing

**MWLN**




### Inserts

Eg.



N-GU N-HG

❶ WNMG 080408 N-GU
❷ WNMM 080412 N-HG

### Spare Parts


### Holders

Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | H | HF | B | LF | LH | WF | Wedge | Shim pin | Shim | Clamp bold | Nut | Ring | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| MWLN R/L 2020-43 (K08) | ● | ● | 20 | 20 | 20 | 125 | 32 | 25 | MWW40 | MP416 | SWW433 | BHA0625 | CPM43S | ER04 | LH030 LH040 | ❶,❷ |
| MWLN R/L 2525-43 (M08) | ● | ● | 25 | 25 | 25 | 150 | 32 | 32 | | MP420 | | 4,5 (N·m) | CPM43N | | | |
| MWLN R/L 3225-43 (P08) | ❍ | ❍ | 32 | 32 | 25 | 170 | 32 | 32 | | | | | | | | |

## P Type Lever Lock Holders

**PWLN**




### Inserts

Eg.



N-SU

❶ WNMG 060408 N-SU

### Spare Parts

### Holders

Above figures show right hand tools.

| Cat. No.. | Stock R | Stock L | H | HF | B | LF | LH | WF | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| PWLN R/L 2020 K06 (PWLN R/L 2020-33) | ● | ❍ | 20 | 20 | 20 | 125 | 27 | 25 | LCL3SD | LCS3TB-SD | LSW317 | LSP3SD | LH025 | ❶ |
| PWLN R/L 2525 M06 | ● | | 25 | 25 | 25 | 150 | 27 | 32 | | | | | | |





● = Euro stock
❍ = Japan stock

(N·m) Recommended Tightening Torque (N·m)

## C Type Top Clamp Holders



### CCLN




Fig.1






Fig.2



#### Inserts



❶ CNGN0903**
❷ CNGN1203**
❸ CNGN1204**

#### Spare Parts

#### Holders

Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | H | HF | B | LF | LH | WF | WF2 | Fig. | Clamp | Insert protector | Clamp bolt | Shim | Shim pin | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| CCLN R/L 2525 M09 | | | 25 | 25 | 25 | 150 | 25 | 32 | 7 | 1 | CCM8UL | CBC0903 | WB8-22T | SCN0903 | SPP3 | LT27 | | ❶ |
| CCLN R/L 2525 M12-03 | | | 25 | 25 | 25 | 150 | 30 | 32 | 7 | 1 | | CBC4 | | SCND433 | | | | ❷ |
| CCLN R/L 2525 M12-04 | | | 25 | 25 | 25 | 150 | 30 | 32 | 7 | 2 | CCM8-LONG | CBC4 | WB8-30 | SCND433 | SPP3 | LH040 | | ❸ |

### CSBN




Fig.1






Fig.2



#### Inserts



❶ SNGN0903**
❷ SNGN1203**
❸ SNGN1204**

#### Spare Parts

#### Holders

Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | H | HF | B | LF | LH | WF | WF2 | Fig. | Clamp | Insert protector | Clamp bolt | Shim | Shim pin | Spring | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| CSBN R/L 2525 N09 | | | 25 | 25 | 25 | 160 | 30 | 21,5 | - | 1 | CCM8UL | CBS13 | WB8-22T | SSN0903 | - | - | LH040 | ❶ |
| CSBN R/L 2525 N12-03 | | | 25 | 25 | 25 | 160 | 35 | 21,5 | - | 1 | | CBS14 | | SSND423 | | | | ❷ |
| CSBN R/L 2525 N12-04 | | | 25 | 25 | 25 | 160 | 33 | 21,5 | - | 2 | DC-R/L 1 | CBD 4 R/L | BH 0830 R/L | SSND423 | SPP3 | DSP5 | LH040 | ❸ |

### CSKN




Fig.1






Fig.2



#### Inserts



❶ SNGN0903**
❷ SNGN1203**
❸ SNGN1204**

#### Spare Parts

#### Holders


Above figures show right hand tools.


| Cat. No. | Stock R | Stock L | H | HF | B | LF | LH | WF | WF2 | Fig. | Clamp | Insert protector | Clamp bolt | Shim | Shim pin | Spring | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| CSKN R/L 2525 N09 | | | 25 | 25 | 25 | 160 | 25 | 32 | 7 | 1 | CCM8UL | CBS13 | WB8-22T | SSN0903 | - | - | LH040 | ❶ |
| CSKN R/L 2525 N12-03 | | | 25 | 25 | 25 | 160 | 25 | 32 | 7 | 1 | | CBS14 | | SSND423 | | | | ❷ |
| CSKN R/L 2525 N12-04 | | | 25 | 25 | 25 | 160 | 21 | 32 | 7 | 2 | DC-R/L 1 | CBD 4 R/L | BH 0830 R/L | SSND423 | SPP3 | DSP5 | LH040 | ❸ |

## C Type Top Clamp Holders



### CRDN






#### Inserts




❶ RNGN0903**
❷ RNGN1203**
❸ RNGN1204**


#### Spare Parts

#### Holders

| Cat. No. | Stock | Dimensions (mm) | | | | | | | Clamp | Double screw | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | LH | WF | CDX | | | | | | |
| CRDNN 2525 M09 | ● | 25 | 25 | 25 | 150 | 35 | - | 15 | CCM8-LONG | WB8-22T | SRND32 | SPP3 | LT27 | ❶ |
| CRDNN 2525 M12-03 | | 25 | 25 | 25 | 150 | 35 | - | 20 | | | SRND42 | | | ❷ |
| CRDNN 2525 M12-04 | ● | 25 | 25 | 25 | 150 | 35 | - | 20 | | | | | | ❸ |

### CRSN






#### Inserts



❶ RNGN0903**
❷ RNGN1203**
❸ RNGN1204**

#### Spare Parts

#### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Clamp | Double screw | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | WF2 | | | | | | |
| CRSN R/L 2525 M09 | ● | ● | 25 | 25 | 25 | 150 | 30 | 32 | 7 | CCM8-LONG | WB8-22T | SRND32 | SPP3 | LT27 | ❶ |
| CRSN R/L 2525 M12-03 | | | 25 | 25 | 25 | 150 | 30 | 32 | 7 | | | SRND42 | | | ❷ |
| CRSN R/L 2525 M12-04 | ● | ● | 25 | 25 | 25 | 150 | 30 | 32 | 7 | | | | | | ❸ |







● = Euro stock

## X Type Dimple Lock Holders



**XSBN**







### Inserts



❶ SNGX1204**

### Spare Parts





### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Clamp | Clamp bolt | Shim | Shim pin | Spring | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | | | | | | | | |
| XSBN R/L 2525 N12 | | | 25 | 25 | 25 | 160 | 38 | 21,5 | DSLX8 | BH0825 | SSND423 | SPP3 | GSP10 | LH050 | | ❶ |

**XCLN**







### Inserts



❶ CNGX1204**

### Spare Parts




### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Clamp | Clamp bolt | Shim | Shim pin | Spring | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | WF2 | | | | | | | | |
| XCLN R/L 2525 N12 | | | 25 | 25 | 25 | 150 | 33 | 32 | 7 | DSLX8 | BH0825 | SCND433 | SPP3 | GSP10 | LH050 | | ❶ |

# External Mini Holders










**Back-Turning Tool Holder SBT Type**

Sharp cutting edges with good surface finish.
Max. reach of insert 8,0 mm, edge width 2,5 mm




**Cut-off Tool Holder SCT Type**


Easy insert change by just loosening the screw from the back.
Max. cut-off dia. Ø 5 mm, Ø 12 mm, Ø 16 mm



PDJCR type
lever lock holder



# External Mini Holders



In 1984, Sumitomo Electric Hardmetal first released the Mini Tool Holder series for the machining of small components in small NC autolathes.
A full range of insert grades comprising of the Cermet T1500A, SUMIBORON BN2000, SUMIDIA DA1000 and especially AC530U, was also introduced to meet a variety of machining requirements.

## Grade Selection

| Category | Application Range | | | Work Material | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| | | | | P | M | K | S | H | N |
| | High Precision | Finish-Light Cut | Medium Cut | General Steel | Stainless Steel | Cast Iron | Heat Resistant Alloy | Hardenend Steel | Non-Ferrous Metal |
| Coated Carbide (PVD) | ACZ150 | ACZ150 | | ◎ | ◎ | | | | ○ |
| | AC5015S | AC5015S | | ○ | ◎ | ○ | ◎ | | |
| | AC5025S | AC5025S | | ○ | ◎ | ○ | ◎ | | |
| | AC530U | AC530U | | ◎ | ◎ | ○ | ○ | | ○ |
| | AC1030U | AC1030U | | ◎ | ◎ | ○ | ○ | | ○ |
| Cermet/Coated Cermet | T1000A | T1000A | | ◎ | ○ | ◎ | | | ○ |
| | T1500A / T1500Z | T1500A / T1500Z | | ◎ | ○ | ○ | | | ○ |
| Carbide | BL130 | BL130 | | ○ | ○ | ○ | | | ○ |
| | H1 | H1 | | ○ | ○ | ○ | | | ◎ |
| | EH510 | EH510 | | ○ | ○ | ○ | ◎ | | ○ |
| CBN (SUMIBORON) | BN1000 / BN2000 | BN1000 / BN2000 | | | | | | ◎ | |
| | BN7000 | BN7000 | | | | ◎ | ○ | | |
| SUMIDIA | DA1000 | DA1000 | | | | | | | ◎ |

◎ Preferred Choice ○ Suitable

## Recommended Cutting Conditions


| Work Material / Grade | P Free Cutting Steel | | P Carbon Steel | | M Stainless Steel | | S Heat Resistant Alloy | | H Hardened Steel | | N Aluminium | | N Brass | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) | $v_c$ (m/min) | f (mm/rev) |
| ACZ150 | 50–200 | 0,02–0,10 | 50–150 | 0,01–0,08 | 50–150 | 0,01–0,05 | | | | | 70–300 | 0,05–0,20 | 70–300 | 0,05–0,20 |
| AC5015S | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | *50–200 | *0,02–0,10 | | | | | | | 70–300 | 0,05–0,20 |
| AC5025S | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | *50–200 | *0,02–0,10 | 30–100 | 0,02–0,10 | | | | | 70–300 | 0,05–0,20 |
| AC530U | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | *50–200 | *0,02–0,10 | 30–100 | 0,02–0,10 | | | | | 70–300 | 0,05–0,20 |
| AC1030U | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | *50–200 | *0,02–0,10 | | | | | | | 70–300 | 0,05–0,20 |
| T1000A | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | *50–150 | *0,02–0,10 | | | | | 70–300 | 0,05–0,20 | 70–300 | 0,05–0,20 |
| T1500A | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | *50–150 | *0,02–0,10 | | | | | 70–300 | 0,05–0,20 | 70–300 | 0,05–0,20 |
| T1500Z | 50–200 | 0,02–0,15 | 50–200 | 0,02–0,10 | *50–150 | *0,02–0,10 | | | | | 70–300 | 0,05–0,20 | 70–300 | 0,05–0,20 |
| BN1000 | | | | | | | | | 120–300 | 0,03–0,15 | | | | |
| BN2000 | | | | | | | | | 50–200 | 0,03–0,20 | | | | |
| BN7000 | | | | | | | 50–200 | 0,05–0,20 | | | | | | |
| DA1000 | | | | | | | | | | | 70–300 | 0,02–0,10 | 70–300 | 0,02–0,10 |


* Please use maximal possible C/speed

# SBT Type


## Special Mini Holders for Back Facing






SBT35 R1010:




## Holders

Above figures show right hand tools.

| Cat. No. | Stock | Dimensions (mm) | | | | | | | Screw | (N·m) | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | WF | | | | | | | |
| SBT 35-R 1010 | ● | 10 | 10 | 10 | 120 | 7,5 | | | BFTX0307N | **2,0** | TRX10 | | BTR 35_ _ |
| SBT 35-R 1212 | ● | 12 | 12 | 12 | 120 | 9,5 | | | | | | | |
| SBT 35-R 1616 | ● | 16 | 16 | 16 | 120 | 13,5 | | | | | | | |

## Spare Parts






## Inserts

Coated carbide  Uncoated Cermet


**BTR**



| Cat. No. | Stock | | | Dimensions (mm) | | | |
|---|---|---|---|---|---|---|---|
| | AC1030U | AC530U | T1500A | L | CDX | CW | RE |
| BTR 3505 | ❍ | ❍ | ❍ | 15 | 3,5 | 2,5 | 0,05 |
| BTR 3515 | ❍ | ❍ | ❍ | 15 | 3,5 | 2,5 | 0,15 |




Sharp cutting edge with 15° rake angle



Wide groove breaker for smooth chip evacuation

● Surface roughness comparision



**BTR 3505**



P10 des Wettbewerbs

Work Material: C45
Insert: BTR3505 (ACZ310)
Cutting Data: $v_c$ = 80 m/min, f = 0,04 mm/rev
$a_p$ = 3,0 mm, wet

## Recommended Cutting Data (SBT type)

| Work Material | Tooling | $v_c$ (m/min) | f (mm/rev) |
|---|---|---|---|
| General steel | Grooving | 50–150 | 0,02–0,05 |
| | Back facing | | 0,02–0,10 |
| Free-cutting steel | Grooving | 50–150 | 0,02–0,10 |
| | Back facing | | 0,02–0,15 |
| Stainless steel | Grooving | 50–150 | 0,02–0,04 |
| | Back facing | | 0,02–0,06 |





● = Euro stock
○ = Japan stock


(N·m) Recommended Tightening Torque (N·m)


# External Mini Tool Holders
# PC/SC Type




## P Type Lever Lock Holders

**PCLC**







PCLC R/L0810-K06:




### Inserts

Eg.



❶ CCGT 060202 R-FX
❷ CCMT 09T304 N-SU

R-FX N-SU

### Spare Parts

| Lever pin | Clamp screw | Side pin | Wrench | Insert |
|---|---|---|---|---|
| LCL 06 | BTT 0407 | LP 07 | TH 020 | ❶ |
| LCL 09 | BTT 0411 | LP 06 | TH 020 | ❷ |


### Holders


Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | H | HF | B | LF | WF |
|---|---|---|---|---|---|---|---|
| PCLC R/L 0810 K06 | | | 8 | 8 | 10 | 125 | 10,5 |
| PCLC R/L 1010 K06 | ● | ○ | 10 | 10 | 10 | 125 | 10,5 |
| PCLC R/L 1212 K09 | ● | ● | 12 | 12 | 12 | 150 | 12,5 |
| PCLC R/L 1616 K09 | ● | | 16 | 16 | 16 | 150 | 16,5 |

## S Type Screw Lock Holders


**SCLC**






### Inserts

Eg.



❶ CCGT 060202 R-FX
❷ CCMT 09T304 N-SU
❸ CCMT 120408 N-SU

R-FX N-SU

### Spare Parts


| Screw | N·m | Wrench | | Insert |
|---|---|---|---|---|
| BFTX02506N | 1,5 | TRX08 | | ❶ |
| BFTX0409N | 3,4 | TRX15 | | ❷ |
| BFTX0511N | 5,0 | TRX20 | | ❸ |


### Holders

Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | H | HF | B | LF | WF |
|---|---|---|---|---|---|---|---|
| SCLC R/L 0808 D06 | | | 8 | 8 | 8 | 60 | 10 |
| SCLC R/L 1010 E06 | ● | ● | 10 | 10 | 10 | 70 | 12 |
| SCLC R/L 1212 F09 | ● | ● | 12 | 12 | 12 | 80 | 16 |
| SCLC R/L 1616 H09 | ● | ● | 16 | 16 | 16 | 100 | 20 |
| SCLC R/L 2020 H09 | ● | | 20 | 20 | 20 | 100 | 25 |
| SCLC R/L 2020 K09 | ● | ● | 20 | 20 | 20 | 125 | 25 |
| SCLC R/L 2020 K12 | ● | ● | 20 | 20 | 20 | 125 | 25 |
| SCLC R/L 2525 M12 | ● | ● | 20 | 25 | 25 | 150 | 32 |


**SCAC**






### Inserts

Eg.



❶ CCGT 060202 R-FX
❷ CCMT 09T304 N-SU

R-FX N-SU


### Spare Parts

| Screw | N·m | Wrench | | Insert |
|---|---|---|---|---|
| BFTX02506N | 1,5 | TRX08 | | ❶ |
| BFTX0409N | 3,4 | TRX15 | | ❷ |

### Holders


Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | H | HF | B | LF | WF |
|---|---|---|---|---|---|---|---|
| SCAC R/L 0808 D06 | | | 8 | 8 | 8 | 60 | 8,5 |
| SCAC R/L 1010 E06 | ● | | 10 | 10 | 10 | 70 | 10,5 |
| SCAC R/L 1212 F09 | ● | | 12 | 12 | 12 | 80 | 12,5 |




## P Type Lever Lock Holders

**PDJC**





PDJC R/L0810-K07:




### Inserts

Eg.



❶ DCGT 070202 R-FX
❷ DCMT 11T304 N-SU

R-FX N-SU

### Spare Parts

### Holders


Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Lever pin | Clamp screw | Side pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | | | | | | | |
| PDJC R/L 0810 K07 | ● | | 8 | 8 | 10 | 125 | 10,5 | | | LCL 06 | BTT 0407 | LP 04 | TH 020 | ❶ |
| PDJC R/L 1010 K07 | ● | ● | 10 | 10 | 10 | 125 | 10,5 | | | | | | | |
| PDJC R/L 1212 M11 | ● | ● | 12 | 12 | 12 | 150 | 12,5 | | | LCL 09 | | LP 07 | | ❷ |
| PDJC R/L 1616 M11 | ● | ○ | 16 | 16 | 16 | 150 | 16,5 | | | | BTT 0411 | | | |


## S Type Screw Lock Holders

**SDJ/HC**

**SDJC** R/L





**SDHC** R/L




### Inserts

Eg.



❶ DCGT 070202 R-FX
❷ DCMT 11T304 N-SU

R-FX N-SU

### Spare Parts

### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Screw | N·m | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | | | | | | | |
| SDJC R/L 1010 E07 | ● | | 10 | 10 | 10 | 70 | 12 | | | BFTX02506N | 1,5 | TRX08 | | ❶ |
| SDJC R/L 1212 F07 | ● | ● | 12 | 12 | 12 | 80 | 16 | | | | | | | |
| SDJC R/L 1616 H07 | ● | ● | 16 | 16 | 16 | 100 | 20 | | | | | | | |
| SDJC R/L 2020 K07 | ● | ● | 20 | 20 | 20 | 125 | 25 | | | | | | | |
| SDJC R/L 1212 F11 | ● | ● | 12 | 12 | 12 | 80 | 16 | | | BFTX0409N | 3,4 | TRX15 | | ❷ |
| SDJC R/L 1616 H11 | ● | ● | 16 | 16 | 16 | 100 | 20 | | | | | | | |
| SDJC R/L 2020 K11 | ● | ● | 20 | 20 | 20 | 125 | 25 | | | | | | | |
| SDJC R/L 2525 M11 | ● | ● | 25 | 25 | 25 | 150 | 32 | | | | | | | |
| | | | | | | | | | | | | | | |
| SDHC R/L 1616 H11 | ● | ● | 16 | 16 | 16 | 100 | 20 | | | BFTX0409N | 3,4 | TRX15 | | ❷ |
| SDHC R/L 2020 K11 | ● | ● | 20 | 20 | 20 | 125 | 25 | | | | | | | |
| SDHC R/L 2525 M11 | ● | ● | 25 | 25 | 25 | 150 | 32 | | | | | | | |





● = Euro stock
○ = Japan stock


N·m Recommended Tightening Torque (N·m)

# External Mini Tool Holders
# SD Type




## S Type Screw Lock Holders

**SDAC**




### Inserts

Eg.



❶ DCGT 070202 R-FX
❷ DCMT 11T304 N-SU

R-FX N-SU


### Spare Parts

### Holders

Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Screw | N·m | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | | | | | | | |
| SDAC R/L 0808 D07 | | | 8 | 8 | 8 | 60 | 8,5 | | | BFTX02506N | 1,5 | TRX08 | | ❶ |
| SDAC R/L 1010 E07 | ● | | 10 | 10 | 10 | 70 | 10,5 | | | | | | | |
| SDAC R/L 1212 F11 | ● | ● | 12 | 12 | 12 | 80 | 12,5 | | | BFTX0409N | 3,4 | TRX15 | | ❷ |

**SDNC**




### Inserts

Eg.



❶ DCGT 070202 R-FX
❷ DCMT 11T304 N-SU

R-FX N-SU

### Spare Parts

### Holders


| Cat. No. | Stock | Dimensions (mm) | | | | | | | Screw | N·m | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | WF | | | | | | | |
| SDNCN 0808 D07 | ● | 8 | 8 | 8 | 60 | 4,2 | | | BFTX02506N | 1,5 | TRX08 | | ❶ |
| SDNCN 1010 E07 | ● | 10 | 10 | 10 | 70 | 5,2 | | | | | | | |
| SDNCN 1212 F07 | ● | 12 | 12 | 12 | 80 | 6,2 | | | | | | | |
| SDNCN 1616 H07 | | 16 | 16 | 16 | 100 | 8,2 | | | | | | | |
| SDNCN 2020 K07 | ● | 20 | 20 | 20 | 125 | 10,2 | | | | | | | |
| SDNCN 1212 F11 | ● | 12 | 12 | 12 | 80 | 6,5 | | | BFTX0409N | 3,4 | TRX15 | | ❷ |
| SDNCN 1616 H11 | ● | 16 | 16 | 16 | 100 | 8,5 | | | | | | | |
| SDNCN 2020 K11 | ● | 20 | 20 | 20 | 125 | 10,5 | | | | | | | |
| SDNCN 2525 M11 | ● | 25 | 25 | 25 | 150 | 13 | | | | | | | |


# External Holders for 7° RC_ _ pos. Inserts

## P Type Lever Lock Holders



## PRDCN






### Inserts

Eg.



N-RP


❶ RCOO1003M0 N–RO
❷ RCOO1204M0 N–RO
❸ RCOO1606M0 N–RO
❹ RCOO2006M0 N–RO


### Spare Parts

### Holders

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | Lever pin | Clamp screw | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | LH | WF | E1 | IC | | | | | | |
| PRDC N 2020 M10 | ● | 20 | 20 | 20 | 150 | 22 | 15,0 | 1,0 | 10 | LCL10 | LCS10 | LSR10 | LSP10 | LH020 | ❶ |
| PRDC N 2525 M10 | ● | 25 | 25 | 25 | 150 | 22 | 17,5 | 1,0 | 10 | | | | | | |
| PRDC N 2525 M12 | ● | 25 | 25 | 25 | 150 | 24 | 18,5 | 1,2 | 12 | LCL12 | LCS12 | LSR12 | LSP10 | LH025 | ❷ |
| PRDC N 3225 Q12 | ● | 32 | 32 | 25 | 180 | 24 | 18,5 | 1,2 | 12 | | | | | | |
| PRDC N 3225 Q16 | ● | 32 | 32 | 25 | 180 | 28 | 20,5 | 1,5 | 16 | LCL16 | LCS16 | LSR16 | LSP16 | LH025 | ❸ |
| PRDC N 3232 Q20 | ● | 32 | 32 | 32 | 180 | 32 | 26,5 | 1,7 | 20 | LCL20 | LCS20 | LSR20 | LSP20 | LH030 | ❹ |

## PRGC






### Inserts

Eg.



N-RP

❶ RCOO 1003M0 N–RO
❷ RCOO 1204M0 N–RO
❸ RCOO 1606M0 N–RO
❹ RCOO 2006M0 N–RO

### Spare Parts

### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Lever pin | Clamp screw | Shim | Shim pin | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | E1 | IC | | | | | | |
| PRGC R/L 2020 K10 | ● | | 20 | 20 | 20 | 125 | 25 | 1,5 | 10 | LCL10 | LCS10 | LSR10 | LSP10 | LH020 | ❶ |
| PRGC R/L 2525 M10 | ● | ● | 25 | 25 | 25 | 150 | 32 | 1,5 | 10 | | | | | | |
| PRGC R/L 2020 K12 | | | 20 | 20 | 20 | 125 | 25 | 2,5 | 12 | LCL12 | LCS12 | LSR12 | LSP10 | LH025 | ❷ |
| PRGC R/L 2525 M12 | ○ | ● | 25 | 25 | 25 | 150 | 32 | 2,5 | 12 | | | | | | |
| PRGC R/L 3225 P12 | | | 32 | 32 | 25 | 170 | 32 | 2,5 | 12 | | | | | | |
| PRGC R/L 2525 M16 | ● | | 25 | 25 | 25 | 150 | 32 | 3,0 | 16 | LCL16 | LCS16 | LSR16 | LSP16 | LH025 | ❸ |
| PRGC R/L 3225 P16 | ● | | 32 | 32 | 25 | 170 | 32 | 3,0 | 16 | | | | | | |
| PRGC R/L 3232 P20 | ● | | 32 | 32 | 32 | 170 | 40 | 4,0 | 20 | LCL20 | LCS20 | LSR20 | LSP20 | LH030 | ❹ |






● = Euro stock
○ = Japan stock


Recommended Tightening Torque (N·m)

## S Type Screw Lock Holders



### SRDCN







#### Inserts





#### Spare Parts





#### Holders

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | Screw | Shim | Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | LH | WF | E1 | IC | | | | | | |
| SRDC N 2020 K10T3 | ● | 20 | 20 | 20 | 125 | 25 | 15,0 | 1,0 | 10 | BFTX03510-SD 2,0 Nm | SRNS 103-SD | BW 0508F-SD | TRX 15 IP-35 | LH 035 | ❶ |
| SRDC N 2525 M10T3 | ● | 25 | 25 | 25 | 150 | 25 | 17,5 | 1,0 | 10 | | | | | | |
| SRDC N 2525 M12 | ● | 25 | 25 | 25 | 150 | 28 | 18,5 | 1,2 | 12 | BFTX03512-SD 2,0 Nm | SRNS 123-SD | | | | ❷ |
| SRDC N 3225 P12 | ● | 32 | 32 | 25 | 170 | 28 | 18,5 | 1,2 | 12 | | | | | | |
| SRDC N 2525 M16 | | 25 | 25 | 25 | 150 | 35 | 20,5 | 1,5 | 16 | BFTX0517-SD 5,0 Nm | SRNS 164-SD | BW 0810F-SD | LT 20 IP | LH 050 | ❸ |
| SRDC N 3225 P16 | ● | 32 | 32 | 25 | 170 | 35 | 20,5 | 1,5 | 16 | | | | | | |
| SRDC N 3232 P20 | ● | 32 | 32 | 32 | 170 | 40 | 26,0 | 1,7 | 20 | BFTX0618-SD 7,5 Nm | SRNS 204-SD | BW 0912F-SD | LT 25 IP | LH 060 | ❹ |

### SRSC







#### Inserts





#### Spare Parts





#### Holders


| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Screw | Shim | Screw | Wrench | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | E1 | IC | | | | | | |
| SRSC R/L 2020 K10T3 | ● | ● | 20 | 20 | 20 | 125 | 25 | 1,5 | 10 | BFTX 03510-SD 2,0 Nm | SRNS 103-SD | BW 0508F-SD | TRX 15 IP-35 | LH 035 | ❶ |
| SRSC R/L 2525 M10T3 | ● | ● | 25 | 25 | 25 | 150 | 32 | 1,5 | 10 | | | | | | |
| SRSC R/L 2525 M12 | ● | | 25 | 25 | 25 | 150 | 32 | 2,5 | 12 | BFTX 03512-SD 2,0 Nm | SRNS 123-SD | | | | ❷ |
| SRSC R/L 3225 P12 | ● | ● | 32 | 32 | 25 | 170 | 32 | 2,5 | 12 | | | | | | |
| SRSC R/L 3225 P16 | ● | ● | 32 | 32 | 25 | 170 | 32 | 3,0 | 16 | BFTX 0517-SD 5,0 Nm | SRNS 164-SD | BW 0810F-SD | LT 20 IP | LH 050 | ❸ |
| SRSC R/L 3232 P20 | ● | ● | 32 | 32 | 32 | 170 | 40 | 4,0 | 20 | BFTX 0618-SD 7,5 Nm | SRNS 204-SD | BW 0912F-SD | LT 25 IP | LH 060 | ❹ |



## S Type Screw Lock Holders


**SSBC**






## Inserts

Eg.



SUMIDIA N-SU

❶ SCMT 070202
❷ SCMT 09T304 N-SU
❸ SCMT 120408 N-SU

## Spare Parts

## Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Screw | N·m | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | | | | | | | |
| SSBC R/L 1010 E07 | | | 10 | 10 | 10 | 70 | 9 | | | BFTX0307N | 2,0 | TRX10 | | ❶ |
| SSBC R/L 1212 F09 | | | 12 | 12 | 12 | 80 | 11 | | | BFTX0409N | 3,4 | TRX15 | | ❷ |
| SSBC R/L 1616 H09 | ● | ● | 16 | 16 | 16 | 100 | 13 | | | | | | | |
| SSBC R/L 2020 K12 | | | 20 | 20 | 20 | 125 | 17 | | | BFTX0511N | 5,0 | TRX20 | | ❸ |
| SSBC R/L 2525 M12 | | | 25 | 25 | 25 | 150 | 22 | | | | | | | |





● = Euro stock


N·m Recommended Tightening Torque (N·m)

# External Mini Tool Holders
# ST Type



## S Type Screw Lock Holders

## STAC




### ■ Inserts

Eg.







❶ TCMT 090202 N-FP
❷ TCMT 110204 N-SU


### ■ Spare Parts

### ■ Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Screw | N·m | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | | | | | | | |
| STAC R/L 0808 D09 | | | 8 | 8 | 8 | 60 | 8,5 | | | BFTX02205N | 1,1 | TRX06 | | ❶ |
| STAC R/L 1212 F11 | ● | | 12 | 12 | 12 | 80 | 12,5 | | | BFTX02506N | 1,5 | TRX08 | | ❷ |
| | | | | | | | | | | | | | | |

## STGC




### ■ Inserts

Eg.








❶ TCMT 090202 N-FP
❷ TCMT 110204 N-SU
❸ TCMT 16T308 N-SU

### ■ Spare Parts

### ■ Holders


Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Screw | N·m | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | | | | | | | |
| STGC R/L 0808 D09 | | | 8 | 8 | 8 | 60 | 10 | | | BFTX02205N | 1,1 | TRX06 | | ❶ |
| STGC R/L 1010 E09 | ● | | 10 | 10 | 10 | 70 | 12 | | | | | | | |
| STGC R/L 1212 F11 | ● | | 12 | 12 | 12 | 80 | 16 | | | BFTX02506N | 1,5 | TRX08 | | ❷ |
| STGC R/L 1616 H11 | ● | ● | 16 | 16 | 16 | 100 | 20 | | | | | | | |
| STGC R/L 1616 H16 | ● | ● | 16 | 16 | 16 | 100 | 20 | | | BFTX0409N | 3,4 | TRX15 | | ❸ |
| STGC R/L 2020 K16 | ● | ● | 20 | 20 | 20 | 125 | 25 | | | | | | | |
| STGC R/L 2525 M16 | | | 25 | 25 | 25 | 150 | 32 | | | | | | | |




## S Type Screw Lock Holders

### SVJB







#### Inserts




#### Spare Parts





#### Holders

Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Stopper | Nut | Shim | Wrench | Scew | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | WF2 | | | | | | | |
| SVJB R/L 1212 F11 | ● | ● | 12 | 12 | 12 | 80 | 25 | 16 | 4,5 | - | - | - | - | BFTX02508NV 1,5 (N·m) | TRX08 | ❶ |
| SVJB R/L 1616 H11 | ● | ● | 16 | 16 | 16 | 100 | 25 | 20 | 4,5 | | | | | | | |
| SVJB R/L 2020 K16 | ● | ● | 20 | 20 | 20 | 125 | 41 | 25 | 5,0 | VP20 | | | | | | |
| SVJB R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 41 | 32 | 7,0 | VP25 | CPV33N | SVP32 | LH025 | BFTX03508 2,0 (N·m) | TRX10 | ❷ |
| SVJB R/L 3225 P16 | ● | ● | 32 | 32 | 25 | 170 | 41 | 32 | 7,0 | VP32 | | | | | | |

### SVPB







#### Inserts




#### Spare Parts





#### Holders

Above figures show right hand tools.


| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Stopper | Nut | Shim | Wrench | Scew | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | WF2 | | | | | | | |
| SVPB R/L 1212 F11 | ● | | 12 | 12 | 12 | 80 | 25 | 16 | 4,5 | - | - | - | - | BFTX02508NV 1,5 (N·m) | TRX08 | ❶ |
| SVPB R/L 1616 H11 | ● | ● | 16 | 16 | 16 | 100 | 25 | 20 | 4,5 | | | | | | | |
| SVPB R/L 2020 K16 | ● | ● | 20 | 20 | 20 | 125 | 36 | 25 | 5,0 | VP20 | | | | | | |
| SVPB R/L 2525 M16 | ● | ● | 25 | 25 | 25 | 150 | 36 | 32 | 7,0 | VP25 | CPV33N | SVP32 | LH025 | BFTX03508 2,0 (N·m) | TRX10 | ❷ |
| SVPB R/L 3225 P16 | ● | ● | 32 | 32 | 25 | 170 | 36 | 32 | 7,0 | VP32 | | | | | | |

### SVVB







#### Inserts




#### Spare Parts



#### Holders

| Cat. No. | Stock | Dimensions (mm) | | | | | | Stopper | Nut | Shim | Wrench | Scew | Wrench | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | H | HF | B | LF | LH | WF | | | | | | | |
| SVVB M 1212 F11 | ● | 12 | 12 | 12 | 80 | - | 6 | - | - | - | - | BFTX02508NV 1,5 (N·m) | TRX08 | ❶ |
| SVVB N 1616 H11 | ● | 16 | 16 | 16 | 100 | - | 8 | | | | | | | |
| SVVB N 2020 K16 | ● | 20 | 20 | 20 | 125 | - | 10 | VP20 | | | | | | |
| SVVB N 2525 M16 | ● | 25 | 25 | 25 | 150 | - | 12,5 | VP25 | CPV33N | SVP32 | LH025 | BFTX03508 2,0 (N·m) | TRX10 | ❷ |
| SVVB N 3225 P16 | ● | 32 | 32 | 25 | 170 | - | 12,5 | VP32 | | | | | | |





● = Euro stock
○ = Japan stock

(N·m) Recommended Tightening Torque (N·m)


# External Mini Tool Holders
# SV Type




## S Type Screw Lock Holders



### SVLC






### Inserts

Eg.



❶ VCGT 110302 R-FX

R-FX


### Spare Parts


### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Screw | | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | WF | | | | | | | |
| SVLC R/L 1010 H11 | ● | ● | 10 | 10 | 10 | 100 | 10,5 | | | BFTX02508NV | 1,5 | TRX08 | | ❶ |
| SVLC R/L 1212 H11 | ● | ● | 12 | 12 | 12 | 100 | 12,5 | | | | | | | |
| SVLC R/L 1616 H11 | ● | ● | 16 | 16 | 16 | 100 | 16,5 | | | | | | | |
| SVLC R/L 2020 K11 | ❍ | ❍ | 20 | 20 | 20 | 125 | 20,5 | | | | | | | |
| SVLC R/L 2525 M11 | ● | ❍ | 25 | 25 | 25 | 150 | 25,5 | | | | | | | |

### SVPC






### Inserts

Eg.



❶ VCGT 110302 R-FX

R-FX

### Spare Parts

### Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Screw | | Wrench | | Insert |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | HF | B | LF | LH | WF | WF2 | | | | | |
| SVPC R/L 1010 H11 | ❍ | ❍ | 10 | 10 | 10 | 100 | - | 14,5 | 4,5 | | | | | |
| SVPC R/L 1212 H11 | ● | ● | 12 | 12 | 12 | 100 | - | 16,5 | 4,5 | BFTX02508NV | 1,5 | TRX08 | | ❶ |
| SVPC R/L 1616 H11 | ● | ● | 16 | 16 | 16 | 100 | - | 20,5 | 4,5 | | | | | |

# Polygon - Shank Holder





## Features

The Sumitomo polygon shank holders enable an extremely high stiffness connection between machine and tool. The conical polygon can take high bending and torque moments based on the combination of the face contact to the spindle.
This self-guiding coupling system offers high precision and a repeatability of ± 2 µm in X, Y and Z axis.
While using this easy and quick coupling system it is possible to gain higher machine utilization time as the set-up and tool change times are reduced.
The compact design and the high stiffness connection to the spindle offer a versatile use e.g. on multi-task machines, machining centers and turning-milling centers.

## Characteristics

- original SUMITOMO D-type double clamping system
- compact design
- monoblock system - no additional interfaces
- precise positioning; self-guiding with high repeatability
- high stiffness supported by face contact of holder
- carbide shims to prevent holders from damage
- simple tool holder change and low-maintenance operation
- internal coolant supply directly to the cutting edge
- Polygon shank and insert seat hardened for long holder life

Polygon - shank holder - produced according to ISO 26623-1

Negative Insert Type



Positive Insert Type



## Classification System for Polygon - Shank Holder

**P S C 4 0 - D C L N R 2 7 0 5 0 - 1 2**

| | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| Polygon Shank | Size (DCSFMS) | Clamping System D: Double Clamp S: Screw Clamp | Insert Shape | Holder Style | Seat Clearance Angle N = 0° C = 7° P = 11° | Feed Direction R: Right Hand L: Left Hand N: Neutral | Size (WF) | Holder Length (LF) | Insert Cutting Edge Length |





● = Euro stock

Recommended Tightening Torque (N·m)

## General Turning, Copying and Facing

### DCLN







Right hand shown.

■ Inserts



CNMG1204_ _ NGE
(Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | Applicable Insert | Clamp Set | N·m | Shim | Shim Screw | Shim Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | LF | WF | DCSFMS | | | | | | | |
| PSC40 DCLN R/L 27050-12 | ● | ● | 50 | 27 | 40 | CN□□ 1204 | SCP-2 | 5,0 | CNS1204 | BFTX0409N | TRX15 (*) | LH040 |
| PSC50 DCLN R/L 35060-12 | ● | ● | 60 | 35 | 50 | | | | | | | |

### DDJN







Right hand shown.

■ Inserts



DNMG1506_ _ NGE
(Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | Applicable Insert | Clamp Set | N·m | Shim | Shim Screw | Shim Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | LF | WF | DCSFMS | | | | | | | |
| PSC40 DDJN R/L 27055-15 | ● | ● | 55 | 27 | 40 | DN□□ 1506 | SCP-2 | 5,0 | DNS1506 | BFTX0409N | TRX15 (*) | LH040 |
| PSC50 DDJN R/L 35060-15 | ● | ● | 60 | 35 | 50 | | | | | | | |

### DDHN







Right hand shown.

■ Inserts



DNMG1506_ _ NGE
(Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | Applicable Insert | Clamp Set | N·m | Shim | Shim Screw | Shim Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | LF | WF | DCSFMS | | | | | | | |
| PSC40 DDHN R/L 27055-15 | ● | ● | 55 | 27 | 40 | DN□□ 1506 | SCP-2 | 5,0 | DNS1506 | BFTX0409N | TRX15 (*) | LH040 |
| PSC50 DDHN R/L 35060-15 | | ● | 60 | 35 | 50 | | | | | | | |

### DSBN







Right hand shown.

■ Inserts



SNMG1204_ _ NGE
(Representative example)

■ Spare Parts




■ Holders


| Cat. No. | Stock | | Dimensions (mm) | | | Applicable Insert | Clamp Set | N·m | Shim | Shim Screw | Shim Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | LF | WF | DCSFMS | | | | | | | |
| PSC40 DSBN R/L 22050-12 | | ● | 50 | 22 | 40 | SN□□ 1204 | SCP-2 | 5,0 | SNS1204 | BFTX0409N | TRX15 (*) | LH040 |
| PSC50 DSBN R/L 27060-12 | ● | | 60 | 27 | 50 | | | | | | | |

(*) Item is sold separately.

## General Turning and Facing

### DTJN







Right hand shown.

■ Inserts



TNMG1604_ _ NGE
(Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | Applicable Insert | Clamp Set | N·m | Shim | Shim Screw | Shim Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | LF | WF | DCSFMS | | | | | | | |
| PSC40 DTJN R/L 27050-16 | | ● | 50 | 27 | 40 | TN□□ 1604 | SCP-1 | 5,0 | TNS1604 | BFTX0307N | TRX15 (*) | LH040 |
| PSC50 DTJN R/L 35060-16 | ● | | 60 | 35 | 50 | | | | | | | |

### DWLN







Right hand shown.

■ Inserts



WNMG0804_ _ NSE
(Representative example)

■ Spare Parts



■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | Applicable Insert | Clamp Set | N·m | Shim | Shim Screw | Shim Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | LF | WF | DCSFMS | | | | | | | |
| PSC40 DWLN R/L 27050-06 | ● | ● | 50 | 27 | 40 | WN□□ 06 | SCP-1 | 5,0 | WNS0604 | BFTX0307N | TRX15 (*) | LH040 |
| PSC50 DWLN R/L 35060-06 | ● | | 60 | 35 | 50 | | | | | | | |
| PSC40 DWLN R/L 27050-08 | ● | ● | 50 | 27 | 40 | WN□□ 08 | SCP-2 | 5,0 | WNS0804 | BFTX0409N | TRX15 (*) | LH040 |
| PSC50 DWLN R/L 35060-08 | ● | | 60 | 35 | 50 | | | | | | | |

(*) Item is sold separately.





● = Euro stock

N·m Recommended Tightening Torque (N·m)

## General Turning, Copying and Facing

### SCLC






Right hand shown.

■ Inserts



CCMT09T3_ _ NSU
(Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | $L_1$ | f | DCSFMS | | | | | | | |
| PSC40 SCLC R/L 27050-09 | ● | ● | | 50 | 27 | 40 | CC□□ 09T3 | CCS09T3 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SCLC R/L 35060-09 | ● | ● | | 60 | 35 | 50 | | | | | | | |

### SDJC







Right hand shown.

■ Inserts



DCMT11T3_ _ NMU
(Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SDJC R/L 27050-11 | ● | ● | | 50 | 27 | 40 | DC□□ 11T3 | DCS11T3 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SDJC R/L 35060-11 | ● | | | 60 | 35 | 50 | | | | | | | |

### SDHC







Right hand shown.

■ Inserts



DCMT11T3_ _ NMU
(Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SDHC R/L 27050-11 | ● | ● | | 50 | 27 | 40 | DC□□ 11T3 | DCS11T3 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SDHC R/L 35060-11 | ● | ● | | 60 | 35 | 50 | | | | | | | |

### SSBC







Right hand shown.

■ Inserts



SCMT1204_ _ NMU
(Representative example)

■ Spare Parts




■ Holders


| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SSBC R/L 22050-12 | | | | 50 | 22 | 40 | SC□□ 1204 | SCS1204 | KGBS1221 | KSS1221 | 4,5 | LT15K | LH045K* |
| PSC50 SSBC R/L 27060-12 | ● | | | 60 | 27 | 50 | | | | | | | |

(*) Item is sold separately.

## General Turning, Copying and Facing

### STJC






Right hand shown.

■ Inserts



TCMT16T3_ _ NSU (Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 STJC R/L 27050-16 | ● | | | 50 | 27 | 40 | TC□□ 16T3 | TCS16T3 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 STJC R/L 35060-16 | | | | 60 | 35 | 50 | | | | | | | |

### SVJB






Right hand shown.

■ Inserts



VBMT1604_ _ NSU (Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SVJB R/L 27050-16 | ● | ● | | 50 | 27 | 40 | VB□□ 1604 | VCS1604 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SVJB R/L 35060-16 | | ● | | 60 | 35 | 50 | | | | | | | |

### SVVB







Right hand shown.

■ Inserts



VBMT1604_ _ NSU (Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SVVB N 00050-16 | | | ● | 50 | | 40 | VB□□ 1604 | VCS1604 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SVVB N 00060-16 | | | | 60 | | 50 | | | | | | | |

### SVHB






Right hand shown.

■ Inserts



VBMT1604_ _ NSU (Representative example)

■ Spare Parts



■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SVHB R/L 27050-16 | ● | ● | | 50 | 27 | 40 | VB□□ 1604 | VCS1604 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SVHB R/L 35060-16 | ● | | | 60 | 35 | 50 | | | | | | | |

(*) Item is sold separately.







● = Euro stock

N·m Recommended Tightening Torque (N·m)

## General Turning, Copying and Facing

### SVJC






Right hand shown.

■ Inserts



VCMT1604_ _ NSU
(Representative example)


■ Spare Parts




■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SVJC R/L 27050-16 | | ● | | 50 | 27 | 40 | VC□□ 1604 | VCS1604 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SVJC R/L 35060-16 | ● | ● | | 60 | 35 | 50 | | | | | | | |

### SVVC






Right hand shown.

■ Inserts



VCMT1604_ _ NSU
(Representative example)

■ Spare Parts




■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SVVC N 00050-16 | | | | 50 | | 40 | VC□□ 1604 | VCS1604 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SVVC N 00060-16 | | | | 60 | | 50 | | | | | | | |

### SVHC






Right hand shown.

■ Inserts



VCMT1604_ _ NSU
(Representative example)

■ Spare Parts



■ Holders

| Cat. No. | Stock | | | Dimensions (mm) | | | Applicable Insert | Shim | Shim Screw | Insert Screw | N·m | Wrench | Shim Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | N | LF | WF | DCSFMS | | | | | | | |
| PSC40 SVHC R/L 27050-16 | ● | ● | | 50 | 27 | 40 | VC□□ 1604 | VCS1604 | KGBS1111 | KSS1111 | 3,5 | LT15K | LH035K* |
| PSC50 SVHC R/L 35060-16 | | | | 60 | 35 | 50 | | | | | | | |

(*) Item is sold separately.

# Boring Bars

E

E1–E24






Selection — Boring Tool Selection Table ..... E2–4
ISO — Boring Tool Identification Table ..... E5
Features — Boring Tool Series ..... E6–7

Boring Bars for Negative Insert Type :

CN_ _: **D…DCLN / S…PCLN** ..... E8
DN_ _: **D…DDUN / S…PDUN** ..... E9
SN_ _: **S…PSKN** ..... E10
**SumiTurn T-Rex** **S…DTR** ..... E11
TN_ _: **D…DTFN / S…PTFN** ..... E12
WN_ _: **D…DWLN / S…WMLN** ..... E13

Boring Bars for Positive Insert Type :

**X-Bar** for CC_ _: **B/D…SCLC** ..... E14
CC_ _: **S … SCLC** ..... E14
CP_ _: **S/C…SCLP** ..... E15
**X-Bar** for DC_ _: **B/D…SDUC / SDQC** ..... E16–17
DC_ _: **S … SDQC / SDUC** ..... E16–17
SP_ _: **S/C…SSKP** ..... E18
TC_ _: **S … STFC** ..... E19
**X-Bar** for TP_ _: **B/D…STUP** ..... E20
TP_ _: **S/C…STUP** ..... E20
**X-Bar** for VB_ _: **D … SVUB / SVZB** ..... E21
VB_ _: **S … SVQB / SVUB / SVZB** ..... E22
WB_ _: **S/C…SWUB** ..... E23

Very Small Dia. Boring — **BXBR…R(-NB)** ..... E24

# Boring Tools Selection

## According to Applications / Bore Diameter

## ■ BORING TOOLS

Coloured boxes indicate available size.

| Application | Type | Boring Depth (L/D) Shank: Steel | Carbide | X - Bar (Steel) | Applicable Insert | Tooling | Min. Bore Diameter (mm) (Min. cutting diameter is shown when not matched in this table.) |
|---|---|---|---|---|---|---|---|
| Very Small Dia. Boring | BXBR ⇨ E24 | | –5 | | Special boring bar | | ○ 2 ○ 2,5 ○ 3 ○ 3,5 ○ 4 ○ 4,5 ○ 5 |
| | DABB ⇨M57 | | –2 | | Sumidia brazed | | ● 3 ● 4 ● 5 ● 7 |
| Stop Boring | BSME ⇨M48–M50 | | –4 | | Sumiboron brazed | | ● 2,5 ● 3 ● 3,5 ● 4 ● 4,5 ● 5 |
| | SEXC ⇨M48,49,51 | | –3 | | Sumiboron insert | | ● 4 ● 5 ● 6 |
| | BNBB ⇨M52 | | –5 | | Sumiboron brazed | | ● 3,5 ● 4,5 ● 5,5 ● 6,5 ● 8,5 |
| | BNB ⇨M53 | | –4 | | Sumiboron insert | | ● 10 ● 12 ● 14 ● 16 ● 18 ● 22 |
| | S/C-SWUB ⇨ E23 | –3 | –8 | | Trigon Type 5° Pos. | | ● 5,5 |
| | S-STFC ⇨ E19 | –3 | | | Triangle Type 5° & 11° Pos. | | ● 13 ● 16 ● 20 ● 22 ● 25 ● 32 ● 40 ● 50 |
| | B/D-STUP ⇨ E20 | | | –6 | | | ● 10 ● 12 ● 14 ● 16 ● 18 ● 20 ● 22 ● 25 ● 40 |
| | S-STUP(B) ⇨ E20 | –3 | | | | | ● 8 ● 10 ● 12 ● 16 ● 18 ● 20 ● 22 ● 25 |
| | C-STUP ⇨ E20 | | –8 | | | | ● 8 ● 10 ● 12 ● 14 ● 16 ● 18 ● 20 ● 22 |
| | CTFP ⇨ Stock in Japan | –3 | | | Triangle 11° Pos. | | ○ 16 ○ 20 ○ 25 ○ 32 |
| | D-DTFN ⇨ E12 | –3 | | –6 | Triangle Neg. Type | | ● 32 ● 40 ● 50 |
| | S-PTFN ⇨ E12 | | | | | | ● 32 ● 40 ● 50 |
| Bottom Facing | BNZ ⇨M53 | | –5 | | Sumiboron insert | | ● 8 ● 9 ● 11 ● 12 ● 16 ● 20 |
| | S-SCLP ⇨ E15 | –3 | | | 80 ° Diamond 11° Pos. Type | | ● 12 ● 16 ● 18 ● 20 ● 25 ● 28 |
| | B-SCLP ⇨ Stock in Japan | | | –6 | | | ○ 14 ○ 16 ○ 18 ○ 20 |
| | C-SCLP ⇨ E15 | | –8 | | | | ● 12 ● 16 ● 18 |
| | B/D-SCLC ⇨ E14 | | | –6 | | | ● 10 ● 12 ● 14 ● 16 ● 18 ● 20 ● 22 ● 32 ● 40 |
| | S-SCLC ⇨ E14 | –3 | | | 80 ° Diamond 7° Pos. Type | | ● 13 ● 16 ● 18 ● 20 ● 25 ● 32 ● 40 ● 50 |
| | C-SCLC ⇨ Stock in Japan | | –8 | | | | ○ 5 ○ 6 ○ 7 ○ 8 ○ 10 ○ 12 ○ 13 ○ 14 ○ 16 ○ 20 ○ 22 |
| | D-DCLN ⇨ E8 | | | –6 | 80 ° Diamond Neg. Type | | ● 32 ● 40 ● 50 |
| | S-PCLN ⇨ E8 | –3 | | | | | ● 25 ● 30 ● 32 ● 40 ● 50 ● 63 |
| | D-DWLN ⇨ E13 | | | –6 | Trigon Neg. Type | | ● 32 ● 40 ● 50 |
| | S-MWLN ⇨ E13 | –3 | | | | | ● 32 ● 40 ● 50 |

2 2,5 3 3,5 4 4,5 5 6 7 8 10 12 13 14 16 18 20 22 25 28 35 44 54 70

Boring Bars



● = Eurostock
○ = Japanstock


































## ■ BORING TOOLS

Coloured boxes indicate available size.

| Application | Type | Boring Depth (L/D) Shank: Steel | Carbide | X-Bar (Steel) | Applicable Insert | Tooling | Min. Bore Diameter (mm) 6 | 8 | 10 | 12 | 13 | 14 | 16 | 18 | 20 | 22 | 25 | 28 | 32 | 34 | 35 | 40 | 44 | 50 | 54 | 70 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Copying | B/D-SDUC ⇨ E16 | | | –6 | 55 ° Diamond 7° Pos. Type | | | | | | ● | | ● | | ● | | ● | | ● | | | ● | | | | |
| | S-SDUC ⇨E16 | –3 | | | | | | | | | ● | | ● | | ● | | ● | | ● | | | ● | | | | |
| | C-SDUC ⇨ Stock in Japan | | –8 | | | | | | | | ❍ | | ❍ | | ❍ | | ❍ | | | | | | | | | |
| | B/D-SDQC ⇨ E17 | | | –6 | | | | | | | ● | | ● | | ● | | ● | | ● | | | ● | | | | |
| | S-SDQC ⇨E17 | –3 | | | | | | | | | ● | | ● | | ● | | ● | | ● | | | | | | | |
| | D-SVUB ⇨ E21 | | | –6 | 35 ° Diamond Type 5° & 7° Pos. | | | | | | | | | | | ● | | ● 27 | | | ● | ● | | | | |
| | S-SVUB ⇨ E22 | –3 | | | | | | | | | | | | | | ● | | ● 27 | | | ● | ● | | | | |
| | S-SVQB ⇨ E22 | –3 | | | | | | | | | | | | | | ● | | ● 27 | | | ● | ● | | | | |
| | B/C-SVQB ⇨ Stock in Japan | | –8 | –6 | | | | | | | | | | | ❍ | | ❍ | | | | | | | | | |
| | D-SVZB ⇨ E21 | | | –6 | | | | | | | | | | | | ● | | ● 27 | | | ● | ● | | | | |
| | S-SVZB ⇨ E22 | | | | | | | | | | | | | | | ● | | ● 27 | | | ● | ● | | | | |
| | D-DDUN ⇨ E9 | | | –6 | 55 ° Diamond Neg. Type | | | | | | | | | | | | | | ● | | | ● | | | | |
| | S-PDUN ⇨ E9 | –3 | | | | | | | | | | | | | | | | | ● | | | ● | | ● | | ❍ 63 |
| Through Boring | S-SSKP ⇨ E18 | –3 | | | 55 ° Diamond Neg. Type | | | | | | | | ● | | ● | | ● | ● | | | | | | | | |
| | C-SSKP ⇨ E18 | | –8 | | | | | | | | | | ● | | ● | | | | | | | | | | | |
| | SSKC ⇨ Stock in Japan | –3 | | | Square Type 7° Pos. | | | | | | | | | | ❍ | | ❍ | | ❍ | | | ❍ | | | | |
| | CSKP ⇨ Stock in Japan | –3 | | | Square Type 11° Pos. | | | | | | | | | | ❍ | | ❍ | | | | | | | | | |
| | S-PSKN ⇨ E10 | –3 | | | Square Neg. Type | | | | | | | | | | | | | | ● | | | ● | | ● | | ● 63 |
| Grooving | GNDI ⇨ F12/F38 | | | | | | | | | | | | | | | | | | ● | | | ● | | ● | | |
| | GNDIS ⇨ F12/F40 | | | | | | | | | | | ❍ | ❍ | | ❍ | | ❍ | | | | | | | | | |
| | | | | | | | 6 | 8 | 10 | 12 | 13 | 14 | 16 | 18 | 20 | 22 | 25 | 28 | 32 | 34 | 35 | 40 | 44 | 50 | 54 | 70 |


# Boring Tool Series

## ■ TOOLING SELECTION

| Application | | Stop Boring | | Bottom Facing | | Trough Boring | Copying | | |
|---|---|---|---|---|---|---|---|---|---|
| Insert Type / System | | Triangle | Poligon / Others | 80° Diamond | | Square | 55° T-REX | 55° Diamond | 35° Diamond |
| Screw Lock | Steel |  S-STFC ⇨E19 S-STUP(B)⇨E20 |  S-SWUB ⇨ E23 |  S-SCLC ⇨ E14 |  S-SCLP ⇨ E15 |  S-SSKP ⇨ E18 | – |  S-SDUC ⇨E16 S-SDQC ⇨E17 |  S-SVUB (S-SVQB S-SVZB) ⇨ E22 |
| | Anti-vibration |  B-STUP ⇨ E20 | – |  B-SCLC ⇨ E14 | – | | – |  B-SDUC ⇨E16 B-SDQC ⇨E17 | – |
| | Anti-vibration with Oil Hole |  D-STUP ⇨ E20 | – |  D-SCLC ⇨ E14 | | | – |  D-SDUC ⇨E16 D-SDQC ⇨E17 |  D-SVUB ⇨E21 D-SVZB ⇨E21 |
| | Carbide |  C-STUP (C-STUB) ⇨ E20 |  C-SWUB ⇨ E23 | – |  C-SCLP ⇨ E15 |  C-SSKP ⇨ E18 | – | – | – |
| Lever Lock | Steel |  S-PTFN ⇨ E12 | – |  S-PCLN ⇨ E8 | – |  S-PSKN ⇨ E10 | – |  S-PDUN ⇨ E9 | – |
| Top Clamp | Anti-vibration with Oil Hole |  D-DTFN ⇨ E12 |  D-DWLN ⇨E13 |  D-DCLN ⇨ E8 | | | – |  D-DDUN ⇨E9 | – |
| | Steel | – |  S-MWLN ⇨ E13 | – | – | – |  S-DTR ⇨ E11 | – | – |
| CBN | Carbide |  BNB ⇨ M53 |  BNBB ⇨ M52 |  BNZ ⇨ M53 | | | | | |
| | |  BSME ⇨ M48 |  SEXC ⇨ M51 | | | | | | |
| | Carbide | | | | |  BXBR ⇨ E24 | | | |



## ■ Catalogue Classification System For Boring Holders




※ This code may only be included in some of the catalogue nos.






### ① Chart 1

| Shank Material | |
|---|---|
| S | Steel |
| B | Steel with Anti-vibration Mechanism without Oil Hole |
| C | Carbide |
| D | Steel with Anti-vibration Mechanism with Oil Hole |
| E | Carbide with Oil Hole |

### ② Chart 2

| Shank Length | | | |
|---|---|---|---|
| Symbol | Length (mm) | Symbol | Length (mm) |
| F | 80 | P | 170 |
| G | 90 | Q | 180 |
| H | 100 | R | 200 |
| J | 110 | S | 250 |
| K | 125 | T | 300 |
| L | 140 | U | 350 |
| M | 150 | V | 400 |
| N | 160 | W | 450 |













### ③ Chart 3

| Clamping System | | | | | |
|---|---|---|---|---|---|
| Symbol | System | Structure | Symbol | System | Structure |
| C | Top Clamp |  | M | Top & Hole Clamp Type |  |
| D | Double Clamp |  | P | Lever Lock Type (Insert is Supported by 1 face) |  |
| E | Pin Lock Type (Insert is supported by 1 face) |  | S | Screw Clamp Type |  |

### ④ Chart 4

| Insert Shape | | | |
|---|---|---|---|
| Symbol | Insert Shape | Symbol | Insert Shape |
| A | Parallellogram 85° | M | Rhombic 86° |
| B | Parallelogram 82° | O | Octagonal |
| C | Diamond 80° | P | Pentagonal |
| D | Diamond 55° | R | Round |
| E | Diamond 75° | S | Square |
| F | Diamond 50° | T | Triangular |
| H | Hexagonal | V | Diamond 35° |
| K | Parallelogram 55° | W | Trigon |
| L | Rectangular | | |

### ⑤ Chart 5

| Holder Style | | | | | |
|---|---|---|---|---|---|
| Symbol | Shape | Offset | Symbol | Shape | Offset |
| A |  | Nil | N |  | Nil |
| B |  | Nil | Q |  | With Offset |
| D |  | Nil | R |  | With Offset |
| E |  | Nil | S |  | With Offset |
| F |  | With Offset | T |  | With Offset |
| G |  | With Offset | U |  | With Offset |
| J |  | With Offset | W |  | With Offset |
| K |  | With Offset | Y |  | With Offset |
| L |  | With Offset | Z |  | With Offset |

### ⑥ Chart 6

| Seat Clearance Angle | |
|---|---|
| Symbol | Relief Angle |
| A | 3° |
| B | 5° |
| C | 7° |
| D | 15° |
| E | 20° |
| F | 25° |
| G | 30° |
| N | 0° |
| P | 11° |
| O | Special Angle |

# Boring Tool Series



## General Features

Since being the first in 1976 to introduce indexable boring bars, Sumitomo Electric has been continuously developing a comprehensive range which includes the SEC-Small Hole boring bar series, high rigidity boring head series, with either steel / carbide shanks, and the latest anti-vibration mechanism - SumiTurn X-Bar series coupled with a wide variety of insert grades and chipbreakers, cover a whole range of process requirements.


## Features

- Wide selection for various boring operations
- Minimum bore diameter from ø 5,5 mm onwards
- New anti-vibration boring bars, SumiTurn X-Bar.
- High rigidity head-design for small boring bars
- Wide selection of grades and chipbreakers available for various processes and work materials




## Series SumiTurn X Bar

**Good Chip Evacuation from new head design**







**Chatter Killer System - Eliminates Vibration**






- New negative type "X Bar" with high performance double clamping system



## Application Guide


- Carbide shank
  Rigid shank for long high precision bores
- Anti-Vibration Steel Shank
  Low cost solution for long precision bores - eliminates chatter - improves productivity and surface finish
- Steel shank



# Boring Tool Series

## Recommended Over Hang Length / Shank Diameter (L/D)





## Grades

| Tool Material | | Process: High Precision | Process: Finish–Light Cut | Process: Medium Cut | Work Material: P General Steel | Work Material: M Stainless Steel | Work Material: K Cast Iron | Work Material: S Heat Resistant Alloy | Work Material: H Hardened Steel | Work Material: N Non-Ferrous Metal | Work Material: Sintered Alloy |
|---|---|---|---|---|---|---|---|---|---|---|---|
| Coated Carbide | CVD | | AC8015P, AC8020P (New), AC8025P, AC8035P, AC6020M, AC6030M, AC4010K, AC4015K, AC420K | | ◎ | ○ | ○ | | | | |
| | PVD | | ACZ150, AC5015S, AC5025S, AC530U, AC1030U, AC6040M | | ◎ | ◎ | ◎ | ◎ | | ○ | |
| Cermet Coated Cermet | | | T1000A, T1500A/T1500Z, T2500Z | | ◎ | ○ | ◎ | | | ○ | ○ |
| Carbide | | | G10E | | | | ◎ | | | ○ | |
| SumiBoron | | | BN1000, BN2000, BNC2010, BNC2115 (New), BNC2020, BNC2125 (New), BN7000, BN7115 | | | | ◎ | ○ | ◎ | | ○ ◎ |
| SumiDia | | | DA1000, DA150 | | | | | | | ◎ | |


◎ Preferred choice ○ Suitable

## Recommended Chip Breakers


● M-Class Finish-Light-Cut





● M-Class Light-Medium-Cut




● G-Class Ground Typ




● G-Class Breaker




# D...DCLN / S...PCLN Type

For Negative CN _ _ - Inserts ( α = 0°)




SumiTurn X Bar




**D-DCLN**

Bottom facing



Anti-vibration D type with oil hole





Insert (eg.)



N-GU

## Spare Parts



## Holders


Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | øD$_{min}$ | Dimensions (mm) ød | h | $\ell_1$ | $\ell_2$ | f | γ | Insert (eg.) | Clamp | Spring | Clamp bolt | Shim | Shim screw | Wrench | Wrench | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| D25T - DCLN R/L 1204-32 | ● | ● | 32 | 25 | 23 | 300 | 26 | 17 | -12° | CN□□1204○○ | SCP-2 | | | CNS1203B | BFTX0307N | TRX10(*) | LH040 | LH025 |
| D32T - DCLN R/L 1204-40 | ● | ● | 40 | 32 | 30 | 300 | 26 | 22 | -10° | | | | | CNS1204B | BFTX0409N (Nm) 3,4 | TRX15(*) | | |
| D40U - DCLN R/L 1204-50 | ● | ● | 50 | 40 | 37 | 350 | 26 | 27 | -10° | | | | | | | | | |

(*) Note: Wrench (TRX type) for shim screw is not included.


Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.


## Holders



Tool holders (P type) with lever-lock system

**S - PCLN** R/L






| Cat. No. | Stock R | Stock L | øD$_{min}$ | Dimensions (mm) d | h | $l_1$ | $l_2$ | f | γ | |
|---|---|---|---|---|---|---|---|---|---|---|
| S20S - PCLN R/L09 | ● | ● | 25 | 20 | 18 | 250 | 29 | 13 | -11° | CN_ _ 0903_ _ |
| S25T - PCLN R/L09 | ● | | 30 | 25 | 23 | 300 | 33 | 17 | -10° | |
| S25T - PCLN R/L12 | ● | ● | 32 | 25 | 23 | 300 | 42 | 17 | -10° | CN_ _ 1204_ _ |
| S32U - PCLN R/L12 | ● | ● | 40 | 32 | 30 | 350 | 49 | 22 | -11° | |
| S40V - PCLN R/L12 | ● | ● | 50 | 40 | 37 | 400 | 56 | 27 | -10° | |
| S32U - PCLN R/L16 | | | 40 | 32 | 30 | 350 | 56 | 22 | -11° | CN_ _ 1606_ _ |
| S40V - PCLN R/L16 | ● | ● | 50 | 40 | 37 | 400 | 56 | 27 | -10° | |
| S50W - PCLN R/L16 | | | 63 | 50 | 47 | 450 | 56 | 35 | -11° | |
| S50W - PCLN R/L19 | | | 63 | 50 | 47 | 450 | 63 | 35 | -11° | CN_ _ 1906_ _ |

All figures show right hand tools.

## Applicable Inserts

## Spare Parts

| Holder | Carbides, Cermets: Double sided | Carbides, Cermets: One sided | CBN, PCD | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | |
|---|---|---|---|---|---|---|---|---|---|
| **S - PCLN R/L** |  |  |  |  |  |  |  |  | |
| S.....09 | CNMG 0903_ _ NGU | - | - | LCL3C-SD | LCS3B-SD | - | - | LH020 | |
| S25T.....12 | CNMG 1204_ _ NGU | CNMM 1204_ _ NMP | CNGA 1204_ _ | LCL4C-SD | LCS4B-SD | - | - | LH025 | |
| S32U.....12 | CNMG 1204_ _ NGU | CNMM 1204_ _ NMP | CNGA 1204_ _ | LCL4T-SD | LCS41BS-SD | LSC42SD | LSP4SD | LH030 | |
| S40V.....12 | CNMG 1204_ _ NGU | CNMM 1204_ _ NMP | CNGA 1204_ _ | LCL4SD | LCS42BS-SD | LSC42SD | LSP4SD | LH030 | |
| S.....16 | CNMG 1606_ _ NGU | CNMM 1606_ _ NMP | - | LCL5SD | LCS5B-SD | LSC53SD | LSP5SD | LH030 | |
| S.....19 | CNMG 1906_ _ NGU | CNMM 1906_ _ NMP | - | LCL5C-SD | LCS6B-SD | LSC63SD | LSP6SD | LH040 | |






● = Euro stock
❍ = Japan stock

(Nm) Recommended Tightening Torque (N·m)


# Boring Bars
# D...DDUN / S...PDUN Type




SumiTurn X Bar



**D-DDUN**
Copying



Anti-vibration D type
with oil hole





Insert (eg.)



N-GU

## Spare Parts



## Holders


Above figures show right hand tools.

| Cat. No.. | Stock R | Stock L | øD min | Dimensions (mm) ød | h | $\ell_1$ | $\ell_2$ | f | γ | Insert (eg.) | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| D32T - DDUN R/L 1104-40 | ● | ○ | 40 | 32 | 30 | 300 | 26 | 22 | -10° | DN□□1104○○ | SCP-1 | | | DNS1104B | BFTX0307N | TRX10 (*) | LH040 | LH025 |
| D32T - DDUN R/L 1506-40 | ● | ● | 40 | 32 | 30 | 300 | 26 | 22 | -12° | DN□□1506○○ | SCP-2 | | | DNS1506B | BFTX0409N (3,4) | TRX15 (*) | | |
| D40U - DDUN R/L 1506-50 | ● | ● | 50 | 40 | 37 | 350 | 26 | 27 | -12° | | | | | | | | | |

(*) Note: Wrench (TRX type) for shim screw is not included.


Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.


## Holders



Tool holders (P type)
with lever-lock system

**S - PDUN** R/L






| Cat. No. | Stock R | Stock L | Dimensions (mm) øD min | d | h | $l_1$ | $l_2$ | f | γ | |
|---|---|---|---|---|---|---|---|---|---|---|
| S25T - PDUN R/L 11 | ● | ● | 32 | 25 | 23 | 300 | 35 | 17 | -11° | DN_ _ 1104_ _ |
| | | | | | | | | | | |
| S32U - PDUN R/L 15 04 | ● | ● | 40 | 32 | 30 | 350 | 40 | 22 | -11° | DN_ _ 1504_ _ |
| S40V - PDUN R/L 15 | ● | ● | 50 | 40 | 37 | 400 | 56 | 27 | -11° | DN_ _ 1506_ _ |
| S50W - PDUN R/L 15 | | | 63 | 50 | 47 | 450 | 63 | 35 | -10° | |


All figures show right hand tools.

## Applicable Inserts



| Holder | Carbides, Cermets: Double sided | Carbides, Cermets: One sided | CBN, PCD |
|---|---|---|---|
| S - PDUN R/L |  |  |  |
| S25T ....11 | DNMG 1104_ _ NGU | - | DNGA 1104_ _ |
| S32U ....15 04 | DNMG 1504_ _ NGU | DNMM 1504_ _ NMP | DNGA 1504_ _ |
| S40V ....15 | DNMG 1506_ _ NGU | DNMM 1506_ _ NMP | DNGA 1506_ _ |
| S50W....15 | DNMG 1506_ _ NGU | DNMM 1506_ _ NMP | DNGA 1506_ _ |

## Spare Parts

| Lever pin | Clamp bolt | Shim | Shim pin | Wrench | |
|---|---|---|---|---|---|
|  |  |  |  |  | |
| LCL3DB-SD | LCS3DB-SD | – | – | LH020 | |
| LCL4D-SD | LCS5DB-SD | LSD42SD | LSP4SD | LH030 | |
| LCL4D-SD | LCS5DB-SD | LSD42SD | LSP4SD | LH030 | |
| LCL4D-SD | LCS5DB-SD | LSD42SD | LSP4SD | LH030 | |



## Holders

| | Tool holders (P type) with lever-lock system | Cat. No. | Stock | | Dimensions (mm) | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | R | L | øD$_{min}$ | d | h | $l_1$ | $l_2$ | f | γ | |
| **S - PSKN** R/L  |  | S25T - PSKN R/L 12 | ● | | 32 | 25 | 23 | 300 | 42 | 17 | -11° | SN_ _ 1204_ _ |
| | | S32U - PSKN R/L 12 | ● | | 40 | 32 | 30 | 350 | 45 | 22 | -10° | |
| | | S40V - PSKN R/L 12 | ● | ● | 50 | 40 | 37 | 400 | 50 | 27 | -10° | |
| | | | | | | | | | | | | |
| | | S40V - PSKN R/L 15 | ● | | 63 | 40 | 47 | 400 | 60 | 35 | -10° | SN_ _ 1506_ _ |
| | | S50W - PSKN R/L 15 | | | 63 | 50 | 47 | 450 | 60 | 35 | -10° | |
| | | | | | | | | | | | | |
| | | S50W - PSKN R/L 19 | | | 63 | 50 | 47 | 450 | 60 | 35 | -9° | SN_ _ 1906_ _ |
| | | | | | | | | | | | | |

All figures show right hand tools.

## Applicable Inserts

| Holder | Carbides, Cermets | | CBN |
|---|---|---|---|
| | Double sided | One sided | |
| **S - PSKN R/L**  |  |  | |
| S25T....12 | SNMG 0903_ _ NGU | - | - |
| S32U....12 | SNMG 1204_ _ NGU | SNMM 1204_ _ NMP | SNGA 1204_ _ |
| S40V....12 | SNMG 1204_ _ NGU | SNMM 1204_ _ NMP | SNGA 1204_ _ |
| S....15 | SNMG 1506_ _ NGU | SNMM 1506_ _ NMP | - |
| S....19 | SNMG 1906_ _ NGU | SNMM 1906_ _ NMP | - |

## Spare Parts

| Lever pin | Clamp bolt | Shim | Shim pin | Wrench | |
|---|---|---|---|---|---|
|  |  |  |  |  | |
| LCL4C-SD | LCS4B-SD | – | – | LH025 | |
| LCL4T-SD | LCS41BS-SD | LSS42SD | LSP4SD | LH030 | |
| LCL4SD | LCS42BS-SD | LSS42SD | LSP4SD | LH030 | |
| LCL5SD | LCS5B-SD | LSS53SD | LSP5SD | LH030 | |
| LCL5C-SD | LCS6B-SD | LSS63SD | LSP6SD | LH040 | |




● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)


# Boring Bars
# "T-REX" Type


## Internal Turning & Copying

SumiTurn T-REX




## S-DTR
Profiling






## Spare Parts



## Holders

Above figures show right hand tools.

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | | Clamp | Spring | Screw | Shim | Screw | Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | øDmin | ød | h | ℓ1 | ℓ2 | f | γ | e | | | | | | | |
| S32S-DTR55C R/L-17 | ● | | 44 | 32 | 30 | 250 | 40 | 22 | -12° | 7 | TRCP3 | S-SP4-20 | BX0520 | TRW5505 | BFTX0307N (Nm) 2,0 | TSW040 | TRX10(*) |
| S40T-DTR55C R/L-17 | ● | ❍ | 50 | 40 | 37 | 300 | 40 | 25 | -10° | 6,2 | | | | | | | |

(*) Note: Wrench (TRX10) for shim is not included.


## Advantages

● T-REX Inserts for Maximum Economy

With 6 cutting edges and a 55 degree included angle - T-Rex is the intelligent alternative to profile turning with a traditional 4 edge DNMG insert.


## Inserts

| Applic. | Shape | Cat. No. | r | Coated Carbide AC8015P | Coated Carbide AC8025P | Coated Carbide AC630M | Coated Cermet T3000Z |
|---|---|---|---|---|---|---|---|
| Fine Finishing |  FL | TRM 551704-FL | 0,4 | | ❍ | | ❍ |
| | | 551708-FL | 0,8 | | ❍ | | ❍ |
| Finishing |  LU | TRM 551704-LU | 0,4 | ● | ❍ | | ❍ |
| | | 551708-LU | 0,8 | ● | ❍ | | ❍ |
| | | 551712-LU | 1,2 | | ❍ | | ❍ |
| |  SU | TRM 551704-SU | 0,4 | | ❍ | ● | ❍ |
| | | 551708-SU | 0,8 | | ❍ | ● | ❍ |
| | | 551712-SU | 1,2 | | ❍ | | |
| Light Cut |  GU | TRM 551704-GU | 0,4 | | ❍ | ● | |
| | | 551708-GU | 0,8 | | ❍ | ● | |
| | | 551712-GU | 1,2 | | ❍ | | |





Application P Steel
M Stainless steel







**D-DTFN**
Stop boring



Anti-vibration D type with oil hole





Insert (eg.)



N-GU

## Spare Parts




## Holders

Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) ød | h | ℓ1 | ℓ2 | f | γ | Insert (eg.) | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| D25T - DTFN R/L 1604-32 | ● | ● | 32 | 25 | 23 | 300 | 21 | 17 | -12° | TN□□1604○○ | SCP-1 | | | TNS1603B / TNS1604B | BFTX0307N (Nm) 2,0 | TRX10 (*) | LH040 | LH025 |
| D32T - DTFN R/L 1604-40 | ● | ● | 40 | 32 | 30 | 300 | 26 | 22 | -10° | | | | | | | | | |
| D40U - DTFN R/L 1604-50 | ● | ● | 50 | 40 | 37 | 350 | 26 | 27 | -10° | | | | | | | | | |

(*) Note: Wrench (TRX type) for shim screw is not included.


## Holders




Tool holders (P type) with lever-lock system



**S - PTFN** R/L






| Cat. No. | Stock R | Stock L | Dimensions (mm) øDmin | d | h | l1 | l2 | f | γ | |
|---|---|---|---|---|---|---|---|---|---|---|
| S20S - PTFN R/L 11 | | | 25 | 20 | 18 | 250 | 30 | 13 | -12° | TN_ _ 1103_ _ |
| S25T - PTFN R/L 16 | ● | ● | 32 | 25 | 23 | 300 | 43,3 | 17 | -13° | TN_ _ 1604_ _ |
| S32U - PTFN R/L 16 | ● | ● | 40 | 32 | 30 | 350 | 49,6 | 27 | -12° | |
| S40V - PTFN R/L 16 | ● | | 50 | 40 | 37 | 400 | 49,5 | 27 | -11° | |
| S50W - PTFN R/L 16 | | | 63 | 50 | 47 | 450 | 56 | 35 | -10° | |
| S40V - PTFN R/L 22 | ● | | 50 | 40 | 37 | 400 | 59 | 27 | -11° | TN_ _ 2204_ _ |
| S50W - PTFN R/L 22 | | | 63 | 50 | 47 | 450 | 66 | 35 | -10° | |

All figures show right hand tools.

## Applicable Inserts

## Spare Parts

| Holder | Carbides, Cermets Double sided | Carbides, Cermets One sided | CBN | Lever pin | Clamp bolt | Shim | Shim pin | Wrench | |
|---|---|---|---|---|---|---|---|---|---|
| S - PTFN R/L |  |  |  |  |  |  |  |  | |
| S....11 | - | - | - | LCL3T-SD | LCS3B-SD | – | – | LH020 | |
| S....16 | TNMG 1604_ _ NGU | TNMM 1604_ _ NMP | TNGA 1604_ _ | LCL3SD | LCS3TB-SD | LST317SD | LSP3SD | LH025 | |
| S....22 | TNMG 2204_ _ NGU | TNMM 2204_ _ NMP | TNGA 2204_ _ | LCL4SD | LCS42BS-SD | LST42SD | LSP4SD | LH030 | |




● = Euro stock

(Nm) Recommended Tightening Torque (N·m)


# Boring Bars
# D...DWLN / S...MWLN Type




**D-DWLN**
Bottom facing



Anti-vibration D type
with oil hole




SumiTurn X Bar




Insert (eg.)



N-GU

## Spare Parts




## Holders

Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | øD$_{min}$ | Dimensions (mm) ød | h | $\ell_1$ | $\ell_2$ | f | γ | Insert (eg.) | Clamp | Spring | Clamp bolt | Shim | Shim Screw | Wrench | Wrench | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| D25T - DWLN R/L 0804-32 | ● | ● | 32 | 25 | 23 | 300 | 26 | 17 | -12° | WN□□0804○○ | SCP-2 | | | WNS0803B | BFTX0307N | TRX10 (*) | LH040 | LH025 |
| D32T - DWLN R/L 0804-40 | ● | ● | 40 | 32 | 30 | 300 | 26 | 22 | -10° | | | | | WNS0804B | BFTX0409N (Nm) 3,4 | TRX15 (*) | | |
| D40U - DWLN R/L 0804-50 | ● | ● | 50 | 40 | 37 | 350 | 26 | 27 | -10° | | | | | | | | | |

(*) Note: Wrench (TRX type) for shim screw is not included.


## Holders




Tool holders (M type)
with wedge clamp system



**S - MWLN** R/L






| Cat. No. | Stock R | Stock L | øD$_{min}$ | d | h | $l_1$ | $l_2$ | f | γ | |
|---|---|---|---|---|---|---|---|---|---|---|
| S25R - MWLN R/L 08 | ● | ● | 32 | 25 | 23 | 200 | 28 | 17 | -15° | WNMG 0804_ _ |
| S32S - MWLN R/L 08 | ● | ● | 40 | 32 | 30 | 250 | 28 | 22 | -14° | |
| S40T - MWLN R/L 08 | ● | ● | 50 | 40 | 37 | 300 | 28 | 27 | -12° | |

All figures show right hand tools.

## Applicable Inserts

| Holder | Carbides, Cermets: Double sided | Carbides, Cermets: One sided | |
|---|---|---|---|
| S - MWLN R/L |  |  | |
| S....08 | WNMG 0804_ _ NGU | WNMM 0804_ _ NMP | |


## Spare Parts

| Clamp | Double screw | Pin | Shim | Wrench | |
|---|---|---|---|---|---|
|  |  |  |  |  | |
| HE060011W | WB 6-16 | HE060011P | HE060011E | LH025, LH030 | |




SumiTurn X Bar


**B/D-SCLC**
Bottom facing



***B* Type** (Fig.1)
Min. Bore Dia.




***D* Type** (Fig.2)




Insert (ex.)



## Spare Parts





## Holders

| Steel shank | Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) ød | h | ℓ1 | f | ℓ2 | γ | Fig. | Insert (ex.) | Screw | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Anti-vibration B type | B08H - SCLC R/L 0602-10 | ● | ● | 10 | 8 | 7 | 100 | 5,5 | 19 | -13° | 1. | CC□T 0602○○ | BFTX02505N (N·m) 1,1 | TRX08 |
| | B10K - SCLC R/L 0602-12 | ● | ● | 12 | 10 | 9 | 125 | 6 | 21 | -12° | | | BFTX02506N | |
| Anti-vibration D type with oil hole | D12M - SCLC R/L 0602-14 | ● | ● | 14 | 12 | 11 | 150 | 7 | 25 | -10° | 2. | CC□T 09T3○○ | BFTX0407N | TRX15 |
| | D16R - SCLC R/L 09T3-18 | ● | ● | 18 | 16 | 15 | 200 | 11 | 30 | -8° | | | BFTX0409N | |
| | D20S - SCLC R/L 09T3-22 | ● | ● | 22 | 20 | 18 | 250 | 13 | 30 | -7° | | | | |
| | D25T - SCLC R/L 1204-32 | ● | ● | 32 | 25 | 23 | 300 | 17 | 38 | -6° | | CC□T 1204○○ | BFTX0511N (N·m) 5,0 | TRX20 |
| | D32T - SCLC R/L 1204-40 | ● | ● | 40 | 32 | 30 | 300 | 20 | 53 | -6° | | | | |

All figures show right hand tools.


Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.


## Holders



Tool holders (S type)
with screw-lock system

**S - SCLC** R/L






| Cat. No. | Stock R | Stock L | Dimensions (mm) øDmin | d | h | l1 | l2 | f | γ | |
|---|---|---|---|---|---|---|---|---|---|---|
| S10K - SCLC R/L 06 | | | 13 | 10 | 9 | 125 | 9 | 7 | -12° | CC_ _ 0602_ _ |
| S12M - SCLC R/L 06 | | | 16 | 12 | 11 | 150 | 11 | 9 | -10° | |
| S16R - SCLC R/L 06 | ● | ● | 20 | 16 | 15 | 200 | 15 | 11 | -8° | |
| | | | | | | | | | | |
| S16R - SCLC R/L 09 | | | 20 | 16 | 15 | 200 | 15 | 11 | -8° | CC_ _ 09T3_ _ |
| S20S - SCLC R/L 09 | | | 25 | 20 | 18 | 250 | 20 | 13 | -7° | |
| | | | | | | | | | | |
| S25T - SCLC R/L 12 | | | 32 | 25 | 23 | 300 | 20 | 17 | -6° | CC_ _ 1204_ _ |
| S32U - SCLC R/L 12 | ● | ● | 40 | 32 | 30 | 350 | 25 | 22 | -10° | |
| S40V - SCLC R/L 12 | ● | ● | 50 | 40 | 37 | 400 | 25 | 27 | -8° | |

All figures show right hand tools.

## Applicable Inserts

| Holder | Carbides, Cermets | | | Screw | (N·m) | Wrench | | | |
|---|---|---|---|---|---|---|---|---|---|
| S - SCLC R/L |  |  | |  | |  | | | |
| S.....06 | CCMT 0602_ _ NFP | CCGW 0602_ _ | - | BFTX02505N | 1,1 | TRX08 | | | |
| S16R.....09 | CCMT 09T3_ _ NFP | CCGW 09T3_ _ | - | BFTX0407N | 3,0 | TRX15 | | | |
| S20S.....09 | CCMT 09T3_ _ NFP | CCGW 09T3_ _ | - | BFTX0409N | 3,4 | TRX15 | | | |
| S.....12 | CCMT 1204_ _ NFP | CCGW 1204_ _ | - | BFTX0511N | 5,0 | TRX20 | | | |

## Spare Parts









● = Euro stock
❍ = Japan stock

(N·m) Recommended Tightening Torque (N·m)



## Holders

|  | Tool holders (S type) with screw-lock system | Cat. No. | Stock | | Dimensions (mm) | | | | | | |  |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | R | L | øD$_{min}$ | d | h | $l_1$ | $l_2$ | f | γ | |
| **S - SCLP** R/L<br>Steel shank<br> |  | S10K - SCLP R/L 08 | ● | ● | 12 | 10 | 9 | 125 | 12 | 6 | -5° | CP_ T 0802_ _ |
| | | S12M - SCLP R/L 08 | ● | ● | 16 | 12 | 11 | 150 | 15 | 8 | -3° | |
| | | S16R - SCLP R/L 09 | | ● | 20 | 16 | 15 | 200 | 18 | 10 | -3° | CP_ T 0903_ _ |
| | | S20S - SCLP R/L 09 | ● | ● | 25 | 20 | 18 | 250 | 18 | 12,5 | 0 | |
| | | S25T - SCLP R/L 12 | ❍ | ❍ | 28 | 25 | 22 | 300 | 17,4 | 14 | -3° | CP_ T 1204_ _ |
| **C - SCLP** R/L<br>Carbide shank<br> |  | C10Q - SCLP R/L 08 | ● | | 12 | 10 | 9 | 180 | 15 | 6 | -5° | CP_ T 0802_ _ |
| | | C12R - SCLP R/L 08 | | | 16 | 12 | 11 | 200 | 15 | 8 | -2° | |
| | | C16S - SCLP R/L 09 | ● | | 20 | 16 | 15 | 250 | 15 | 10 | -2° | CP_ T 0903_ _ |

All figures show right hand tools.

## Applicable Inserts


| Holder | Carbides, Cermets | CBN | |
|---|---|---|---|
| **S/C-SCLP** R/L |  |  | |
| S/C 10.....08 | CPGT 0802_ _ NSD | CPMW 0802_ _ | |
| S/C 12.....08 | CPGT 0802_ _ NSD | CPMW 0802_ _ | |
| S/C 16.....09 | CPGT 0903_ _ NSD | CPMW 0903_ _ | |
| S 20.....09 | CPGT 0903_ _ NSD | CPMW 0903_ _ | |
| S 25.....12 | CPGT 1204_ _ NSD | - | |

## Spare Parts

| Screw | N·m | Wrench | | | |
|---|---|---|---|---|---|
|  | |  | | | |
| BFTX 0305 A | - | TRX 10 | | | |
| BFTX 0305 A | - | TRX 10 | | | |
| BFTX 0407 A | 3,4 | TRX 15 | | | |
| BFTX 0407 A | 3,4 | TRX 15 | | | |
| BFTX 0509 A | 5,0 | TRX 20 | | | |


# B/D/S...SDUC Type

For Positive DC_ _- Inserts ( α = 7°)




SumiTurn X Bar

**B/D-SDUC**
Copying




***B Type*** (Fig.1)

Min. Bore Dia.





***D Type*** (Fig.2)




Insert (ex.)



## ■ Spare Parts




## ■ Holders

| Steel shank | Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) ød | h | ℓ1 | f | e | γ | Fig. | Insert (ex.) | Screw | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Anti-vibration B type | B10M - SDUC R/L 0702-13 | ● | ● | 13 | 10 | 9 | 150 | 7 | 2,5 | -8° | 1. | DC□T 0702○○ | BFTX02506N 1,5 (N·m) | TRX08 |
| Anti-vibration D type with oil hole | D12M - SDUC R/L 0702-16 | ● | ● | 16 | 12 | 11 | 150 | 9 | 3,5 | -8° | 2. | | | |
| | D16R - SDUC R/L 0702-20 | ● | ● | 20 | 16 | 15 | 200 | 11 | 4,0 | -6° | | | | |
| | D20S - SDUC R/L 11T3-25 | ● | ● | 25 | 20 | 18 | 250 | 13 | 4,5 | -6° | | DC□T 11T3○○ | BFTX0409N 3,4 (N·m) | TRX15 |
| | D25S - SDUC R/L 11T3-32 | ● | ● | 32 | 25 | 22 | 250 | 17 | 7,0 | -6° | | | | |
| | D32T - SDUC R/L 11T3-40 | ● | ● | 40 | 32 | 30 | 300 | 22 | 8,0 | -6° | | | | |

All figures show right hand tools.


Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.


## ■ Holders



Tool holders (S type)
with screw-lock system

**S - SDUC** R/L






| Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) d | h | l1 | f | e | γ | |
|---|---|---|---|---|---|---|---|---|---|---|
| S10K - SDUC R/L 07 | ● | ● | 13 | 10 | 9 | 125 | 7 | 2,5 | -8° | DC_ _ 0702_ _ |
| S12M - SDUC R/L 07 | ● | ● | 16 | 12 | 11 | 150 | 9 | 3,5 | -8° | |
| S16R - SDUC R/L 07 | ● | ● | 20 | 16 | 15 | 200 | 11 | 4 | -6° | |
| | | | | | | | | | | |
| S20S - SDUC R/L 11 | ● | ● | 25 | 20 | 18 | 250 | 13 | 4,5 | -6° | DC_ _ 11T3_ _ |
| S25T - SDUC R/L 11 | ● | ● | 32 | 25 | 22 | 300 | 17 | 7,5 | -6° | |
| S32U - SDUC R/L 11 | ● | ● | 40 | 32 | 30 | 350 | 22 | 11 | -6° | |

All figures show right hand tools.

## ■ Applicable Inserts

## ■ Spare Parts

| Holder | Carbides, Cermets | | CBN, PCD | Screw | (N·m) | Wrench | | | |
|---|---|---|---|---|---|---|---|---|---|
| S - SDUC R/L<br>S - SDQC R/L |  |  |  |  | |  | | | |
| S10K.....07 | DCMT 0702_ _ NFP | DCMT 0702_ _ NSK | DCGW 0702_ _ | BFTX02506N | 1,5 | TRX08 | | | |
| S12M.....07 | DCMT 0702_ _ NFP | DCMT 0702_ _ NSK | DCGW 0702_ _ | BFTX02506N | 1,5 | TRX08 | | | |
| S16R.....07 | DCMT 0702_ _ NFP | DCMT 0702_ _ NSK | DCGW 0702_ _ | BFTX02506N | 1,5 | TRX08 | | | |
| S.....11 | DCMT 11T3_ _ NFP | DCMT 11T3_ _ NSK | DCGW 11T3_ _ | BFTX0409N | 3,4 | TRX15 | | | |

● = Euro stock


(N·m) Recommended Tightening Torque (N·m)

# Boring Bars
# B/D/S...SDQC Type




SumiTurn X Bar


**B/D-SDQC**
Copying



***B Type*** (Fig.1)
Min. Bore Dia.




***D Type*** (Fig.2)




Insert (ex.)



## ■ Spare Parts





## ■ Holders

| Steel shank | Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) ød | h | ℓ1 | f | e | γ | Fig. | Insert (ex.) | Screw | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Anti-vibration B type | B10M - SDQC R/L 0702-13 | ● | ● | 13 | 10 | 9 | 150 | 7 | 2,5 | -8° | 1. | DC□T 0702○○ | BFTX02506N 1,5 | TRX08 |
| Anti-vibration D type with oil hole | D12M - SDQC R/L 0702-16 | ● | ● | 16 | 12 | 11 | 150 | 9 | 3,5 | -8° | 2. | | | |
| | D16R - SDQC R/L 0702-20 | ● | ● | 20 | 16 | 15 | 200 | 11 | 4,0 | -6° | | | | |
| | D20S - SDQC R/L 11T3-25 | ● | ● | 25 | 20 | 18 | 250 | 13 | 4,5 | -6° | | DC□T 11T3○○ | BFTX0409N 3,4 | TRX15 |
| | D25S - SDQC R/L 11T3-32 | ● | ● | 32 | 25 | 22 | 250 | 17 | 7,0 | -6° | | | | |
| | D32T - SDQC R/L 11T3-40 | ● | ● | 40 | 32 | 30 | 300 | 22 | 7,0 | -10° | | | | |

All figures show right hand tools.


Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.


## ■ Holders



Tool holders (S type)
with screw-lock system

**S - SDQC** R/L







| Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) d | h | l1 | f | e | γ | |
|---|---|---|---|---|---|---|---|---|---|---|
| S10K - SDQC R/L-07 | ● | ● | 13 | 10 | 9 | 125 | 7 | 2,5 | -8° | DC_ _ 0702_ _ |
| S12M - SDQC R/L-07 | ● | ● | 16 | 12 | 11 | 150 | 9 | 3,5 | -8° | |
| S16R - SDQC R/L-07 | ● | ● | 20 | 16 | 15 | 200 | 11 | 4 | -6° | |
| | | | | | | | | | | |
| S20S - SDQC R/L-11 | ● | ● | 25 | 20 | 18 | 250 | 13 | 4,5 | -6° | DC_ _ 11T3_ _ |
| S25T - SDQC R/L-11 | ● | ● | 32 | 25 | 22 | 300 | 17 | 7 | -6° | |

All figures show right hand tools.



## ■ Applicable Inserts

## ■ Spare Parts

| Holder | Carbides, Cermets | | CBN, PCD | Screw | N·m | Wrench | | | |
|---|---|---|---|---|---|---|---|---|---|
| S - SDUC R/L<br>S - SDQC R/L |  |  |  |  | |  | | | |
| S10K.....07 | DCMT 0702_ _ NFP | DCMT 0702_ _ NSK | DCGW 0702_ _ | BFTX02506N | 1,5 | TRX08 | | | |
| S12M.....07 | DCMT 0702_ _ NFP | DCMT 0702_ _ NSK | DCGW 0702_ _ | BFTX02506N | 1,5 | TRX08 | | | |
| S16R.....07 | DCMT 0702_ _ NFP | DCMT 0702_ _ NSK | DCGW 0702_ _ | BFTX02506N | 1,5 | TRX08 | | | |
| S.....11 | DCMT 11T3_ _ NFP | DCMT 11T3_ _ NSK | DCGW 11T3_ _ | BFTX0409N | 3,4 | TRX15 | | | |



## Holders

| | Tool holders (S type) with screw-lock system | Cat. No. | Stock R | Stock L | Dimensions (mm) øD$_{min}$ | d | h | $l_1$ | $l_2$ | f | γ | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| **S - SSKP** R/L<br>Steel shank |  | S12M - SSKP R/L 09 | | ❍ | 16 | 12 | 11 | 150 | 9 | 8 | -6° | SP_ T 0903_ _ |
| | | S16R - SSKP R/L 09 | ● | ● | 20 | 16 | 15 | 200 | 6,8 | 10 | -4° | |
| | | S20S - SSKP R/L 09 | ● | ❍ | 25 | 20 | 18 | 250 | 8,5 | 12,5 | -2° | |
| | | S25T - SSKP R/L 09 | ● | | 28 | 25 | 22 | 300 | 5 | 14 | 0 | |
| **C - SSKP** R/L<br>Carbide shank |  | C12R - SSKP R/L 09 | ● | | 16 | 12 | 11 | 200 | 25 | 8 | -6° | SP_ T 0903 _ _ |
| | | C16S - SSKP R/L 09 | ● | | 20 | 16 | 15 | 250 | 30 | 10 | -4° | |

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.
SPGT figure shows left hand tool.

## Applicable Inserts

## Spare Parts

| Holder | Carbides, Cermets | CBN | | Screw | N·m | Wrench | | | |
|---|---|---|---|---|---|---|---|---|---|
| **S/C-SSKP** R/L |  |  | |  | |  | | | |
| S/C 12.....09 | SPGT 0903_ _ L/R-SD | SPGW 0903_ _ | | BFTX 0307 A | 2,0 | TRX 10 | | | |
| S/C 16.....09 | | | | | | | | | |
| S 20.....09 | | | | | | | | | |
| S 25.....09 | | | | | | | | | |




● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

# Boring Bars
# S ...STFC Type





## Holders



Tool holders (S type)
with screw-lock system

**S - STFC** R/L






| Cat. No. | Stock R | Stock L | Dimensions (mm) øDmin | d | h | l1 | l2 | f | γ | |
|---|---|---|---|---|---|---|---|---|---|---|
| S10K - STFC R/L 09 | ● | ● | 13 | 10 | 9 | 125 | - | 10,5 | -12° | TC_ _ 0902_ _ |
| S12M - STFC R/L 11 | ● | ● | 16 | 12 | 11 | 150 | 10 | 9 | -10° | TC_ _ 1102_ _ |
| S16R - STFC R/L 11 | ● | ● | 20 | 16 | 15 | 200 | 12 | 11 | -6° | |
| S20S - STFC R/L 11 | ● | ● | 25 | 20 | 18 | 250 | 14 | 13 | -3° | |
| S25T - STFC R/L 16 | ● | | 32 | 25 | 23 | 300 | 18 | 17 | -6° | TC_ _ 16T3_ _ |
| S32U - STFC R/L 16 | ● | | 40 | 32 | 30 | 350 | 20 | 22 | -10° | |
| S40V - STFC R/L 16 | | | 50 | 40 | 37 | 400 | 25 | 27 | -8° | |

All figures show right hand tools.

## Applicable Inserts

| Holder | Carbides, Cermets | | CBN, PCD |
|---|---|---|---|
| **S - STFC R/L** |  |  |  |
| S.....09 | TCMT 0902_ _ NFP | - | TCGW 0902_ _ |
| S.....11 | TCMT 1102_ _ NFP | TCMT 1102_ _ NSK | TCGW 1102_ _ |
| S.....16 | TCMT 16T3_ _ NFP | TCMT 16T3_ _ NSK | TCGW 16T3_ _ |


## Spare Parts

| Screw | N·m | Wrench |
|---|---|---|
|  | |  |
| BFTX02205N | 0,5 | TRX06 |
| BFTX02506N | 1,5 | TRX08 |
| BFTX0409N | 3,4 | TRX15 |




SumiTurn X Bar


**B/D-STUP**
Stop boring



***B Type*** (Fig.1)
Min. Bore Dia.




***D Type*** (Fig.2)




Insert (ex.)



## Spare Parts





## Holders

| Steel shank | Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) ød | h | ℓ1 | f | ℓ2 | γ | Fig. | Insert (ex.) | Screw | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Anti-vibration B type | B08H - STUP R/L 0802-10 | ● | ● | 10 | 8 | 7 | 100 | 5 | 13 | -10° | 1. | TP□T 0802○○ | BFTX0204A ⓒ0,5 | TRX06 |
| | B10K - STUP R/L 1103-12 | ● | ● | 12 | 10 | 9 | 125 | 6 | 15 | -8° | | | | |
| Anti-vibration D type with oil hole | D12M - STUP R/L 1103-14 | ● | ● | 14 | 12 | 11 | 150 | 7 | 17 | -7° | 2. | TP□T 1103○○ | BFTX0306A (N·m) 2,0 | TRX10 |
| | D16R - STUP R/L 1103-18 | ● | ● | 18 | 16 | 15 | 200 | 9 | 18 | -4° | | | | |
| | D20S - STUP R/L 1103-22 | ● | ● | 22 | 20 | 18 | 250 | 11 | 18 | -3° | | | BFTX0307A ⓒ2,0 | |
| | D25T - STUP R/L 1604-28 | ● | ● | 28 | 25 | 22 | 300 | 14 | 18 | -2° | | TP□T 1604○○ | BFTX0410A (N·m) 3,4 | TRX15 |
| | D32T - STUP R/L 1604-40 | ● | ● | 40 | 32 | 30 | 300 | 20 | 13 | -2° | | | | |

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

## Holders



Tool holders (S type)
with screw-lock system

| | Cat. No. | Stock R | Stock L | Dimensions (mm) øDmin | d | h | l1 | l2 | f | γ | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| **S - STUP/B** R/L<br>Steel shank | S08H - STUB R/L 06-01 | ● | ● | 8 | 8 | 7 | 100 | 30 | 4 | -12° | TB_T 0601_ _ |
| | S08H - STUP R/L 08-02 | ● | ● | 10 | 8 | 7 | 100 | 13 | 5 | -10° | TP_T 0802_ _ |
| | S10K - STUP R/L 11-03 | ● | | 12 | 10 | 9 | 125 | 15 | 6 | -8° | TP_T 1103_ _ |
| | S12M - STUP R/L 11-03 | ● | ● | 16 | 12 | 11 | 150 | 17 | 8 | -6° | |
| | S16R - STUP R/L 11-03 | | | 20 | 16 | 15 | 200 | 18 | 10 | -2° | |
| | S20S - STUP R/L 16 | | | 25 | 20 | 18 | 250 | 18 | 12,5 | -3° | TP_T 1604_ _ |
| | S25T - STUP R/L 16 | | ● | 28 | 25 | 22 | 300 | 18 | 14 | -2° | |
| **C - STUP/B** R/L<br>Carbide shank | C08M - STUB R/L 06 | ● | ● | 8 | 8 | 7 | 150 | 50 | 4 | -12° | TB_T 0601_ _ |
| | C08M - STUP R/L 08 | ● | ● | 10 | 8 | 7 | 150 | 18 | 5 | -10° | TP_T 0802_ _ |
| | C10Q - STUP R/L 11 | ● | ● | 12 | 10 | 9 | 180 | 19 | 6 | -8° | TP_T 1103_ _ |
| | C12R - STUP R/L 11 | | ● | 16 | 12 | 11 | 200 | 25 | 8 | -6° | |
| | C16S - STUP R/L 11 | ● | | 20 | 16 | 15 | 250 | 30 | 10 | -4° | |

## Applicable Inserts

| Holder | Carbides, Cermets | CBN, PCD |
|---|---|---|
| S/C-STU_ R/L |  |  |
| S/C 08.....06-01 | TBGT 0601_ _L/R-W | - |
| S/C 08.....08-02 | TPGT 0802_ _L/R-W | TPMW 0802_ _ |
| S/C 10.....11-03 | TPGT 1103_ _L/R-W | TPGW 1103_ _ |
| S/C 12/16.....11-03 | TPGT 1103_ _L/R-W | TPGW 1103_ _ |
| S 20/25.....16 | TPGT 1604_ _L/R-W | TPGW 1604_ _ |

## Spare Parts

| Screw | (N·m) | Wrench |
|---|---|---|
|  | |  |
| BFTX 0204 A | 0,5 | TRX 06 |
| BFTX 0204 A | 0,5 | TRX 06 |
| BFTX 0306 A | 2,0 | TRX 10 |
| BFTX 0307 A | 2,0 | TRX 10 |
| BFTX 0410 A | 3,4 | TRX 15 |

● = Euro stock

(N·m) Recommended Tightening Torque (N·m)

SumiTurn X Bar



Anti-vibration D type with oil hole

**D-SVUB**
Copying




Fig.1






Fig.2




Insert (ex.)



## Spare Parts

## Holders

Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) ød | h | ℓ1 | f | e | γ | Fig. | Insert (ex.) | Pin | Clamp screw | Shim | Screw | Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| D16R - SVUB R/L 1103-22 | ● | ● | 22 | 16 | 15 | 200 | 13 | 5 | -7° | 1. | VB□□1103○○ | – | – | – | BFTX02508NV | TRX08 | – |
| D20S - SVUB R/L 1103-27 | ● | ● | 27 | 20 | 18 | 250 | 15 | 5 | -5° | | | | | | | | |
| D25T - SVUB R/L 1604-35 | ● | ● | 35 | 25 | 23 | 300 | 20,5 | 9 | -7,5° | 2. | VB□□1604○○ | VP32B | BH03504 | SVP32 | BFTX03508 (M+) 2,0 | TRX10 | LH020 |
| D32T - SVUB R/L 1604-40 | ● | ● | 40 | 32 | 30 | 300 | 22 | 9 | -7,5° | | | | | | | | |

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

SumiTurn X Bar



Anti-vibration D type with oil hole

**D-SVZB**
Copying




Fig.1






Fig.2




Insert (ex.)



## Spare Parts




## Holders

Above figures show right hand tools.

| Cat. No. | Stock R | Stock L | øDmin | Dimensions (mm) ød | h | ℓ1 | f | e | γ | Fig. | Insert (ex.) | Pin | Clamp screw | Shim | Screw | Wrench | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| D16R - SVZB R/L 1103-22 | ● | ● | 22 | 16 | 15 | 200 | 13 | 5 | -7 | 1. | VB□□1103○○ | – | – | – | BFTX02508NV | TRX08 | – |
| D20S - SVZB R/L 1103-27 | ● | ● | 27 | 20 | 18 | 250 | 15 | 5 | -5 | | | | | | | | |
| D25T - SVZB R/L 1604-35 | ● | ● | 35 | 25 | 23 | 300 | 20,5 | 9 | -7,5 | 2. | VB□□1604○○ | VP32B | BH03504 | SVP32 | BFTX03508 (M+) 2,0 | TRX10 | LH020 |
| D32T - SVZB R/L 1604-40 | ● | ● | 40 | 32 | 30 | 300 | 22 | 9 | -7,5 | | | | | | | | |



## Holders

| | Tool holders (S type) with screw-lock system | Cat. No. | Stock R | Stock L | Dimensions (mm) øD$_{min}$ | d | h | $l_1$ | f | γ | e | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| **S - SVQB** R/L |  | S16R - SVQB R/L 11 | ● | ● | 22 | 16 | 15 | 200 | 13 | -6,5° | | VB_ _ 1102_ _ |
| | | S20S - SVQB R/L 11 | ● | ● | 27 | 20 | 18 | 250 | 15 | -6,5° | | |
| | | S25T - SVQB R/L 16 | ● | ● | 35 | 25 | 23 | 300 | 20,5 | -6,5° | | VB_ _ 1604_ _ |
| | | S32U - SVQB R/L 16 | ● | ● | 40 | 32 | 30 | 350 | 22 | -6,5° | | |
| | | S40V - SVQB R/L 16 | | | 50 | 40 | 37 | 400 | 27 | -6,5° | | |
| **S - SVUB** R/L |  | S16R - SVUB R/L 11 | ● | ● | 22 | 16 | 15 | 200 | 13 | -7,5° | | VB_ _ 1102_ _ |
| | | S20S - SVUB R/L 11 | ● | ● | 27 | 20 | 18 | 250 | 15 | -7,5° | | |
| | | S25T - SVUB R/L 16 | ● | ● | 35 | 25 | 23 | 300 | 20,5 | -7,5° | | VB_ _ 1604_ _ |
| | | S32U - SVUB R/L 16 | ● | ● | 40 | 32 | 30 | 350 | 22 | -7,5° | | |
| | | S40V - SVUB R/L 16 | | | 50 | 40 | 37 | 400 | 27 | -7,5° | | |
| **S - SVZB** R/L |  | S16R - SVZB R/L 11 | ● | ● | 22 | 16 | 15 | 200 | 13 | -7,5° | 5 | VB_ _ 1102_ _ |
| | | S20S - SVZB R/L 11 | ● | ● | 27 | 20 | 18 | 250 | 15 | -7,5° | 5 | |
| | | S25T - SVZB R/L 16 | ● | ● | 35 | 25 | 23 | 300 | 20,5 | -7,5° | 9 | VB_ _ 1604_ _ |
| | | S32U - SVZB R/L 16 | ● | ● | 40 | 32 | 30 | 350 | 22 | -7,5° | 9 | |

All figures show right hand tools.

## Applicable Inserts

| Holder | Carbides, Cermets | | CBN |
|---|---|---|---|
| |  |  |  |
| S16R | VBMT 1102_ _ NFP | VBMT 1102_ _ NSK | - |
| S20S | VBMT 1102_ _ NFP | VBMT 1102_ _ NSK | - |
| S25T | VBMT 1604_ _ NFP | VBMT 1604_ _ NSK | VBGW 1604_ _ |
| S32U | VBMT 1604_ _ NFP | VBMT 1604_ _ NSK | VBGW 1604_ _ |
| S40V | VBMT 1604_ _ NFP | VBMT 1604_ _ NSK | VBGW 1604_ _ |

## Spare Parts

| Pin | Clamp bolt | Shim | Screw | Wrench | Wrench |
|---|---|---|---|---|---|
|  |  |  |  |  |  |
| - | - | - | BFTX02506N (1,5) | TRX08 | - |
| - | - | - | | TRX08 | - |
| - | - | - | BFTX03508 (2,0) | TRX10 | - |
| VP32B | BH03504 | SVP32 | | TRX10 | LH020 |
| VP40B | BH03504 | SVP32 | | TRX10 | LH020 |









● = Euro stock

(N·m) Recommended Tightening Torque (N·m)

# Boring Bars
# S/C...SWUB Type



## Holders

|  | Tool holders (S type) with screw-lock system | Cat. No. | Stock | | Dimensions (mm) | | | | | | |  |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | R | L | $øD_{min}$ | d | h | $l_1$ | $l_2$ | f | γ | |
| **S - SWUB** R/L<br>Steel shank<br> |  | S08H - SWUB R/L 06-01 | ● | ● | 5,5 | 8 | 7 | 100 | 18 | 3 | -12° | WBGT 0601_ _ |
| **C - SWUB** R/L<br>Carbide shank<br> |  | C08K - SWUB R/L 06 | | ● | 5,5 | 8 | 7 | 125 | 30 | 3 | -12° | WBGT 0601_ _ |

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

## Applicable Inserts

| Holder | Carbides, Cermets | CBN | |
|---|---|---|---|
| **S/C-SWUB**R/L |  | | |
| S/C 08.....R 06 | WBGT 0601_ _ LW | - | |
| S/C 08.....L 06 | WBGT 0601_ _ RW | - | |

## Spare Parts

| Screw | N·m | Wrench | | | |
|---|---|---|---|---|---|
|  | |  | | | |
| BFTX 0203 N | 0,5 | TRX 06 | | | |
| BFTX 0203 N | 0,5 | TRX 06 | | | |

# BXBR Type






## Characteristics

SumiSmall

- Economical, two-cornered insert.
- Maximum boring depth 5D (5 times the shank diameter)
- Usable at any desired overhang.
- Shank size = min. bore diameter for easy selection. (Available from ø 2 mm to ø 5 mm in 0,5 mm increments.)
- KBMX Type cutting edge used, no breaker versions also available in stock.

## Small Hole Finishing









Figure shows tool with breaker.

## Solid Carbide Bar


| | Cat. No. | Stock | | DMIN | Dimensions (mm) | | | | | | | | Applicable Sleeve |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | ACZ150 | AC530U | | DCON | H | LF | WF | LH | CDX | E1 | RE | |
| With Breaker | BXBR 02005 R | ❍ | | **2,0** | 2,0 | 1,8 | 50 | 0,80 | 6,0 | 10,0 | 0,20 | 0,05 | HBX 2016 |
| | 02020 R | ❍ | | **2,0** | 2,0 | 1,8 | 50 | 0,80 | 6,0 | 10,0 | 0,20 | 0,20 | HBX 2016 |
| | BXBR 02505 R | ❍ | | **2,5** | 2,5 | 2,2 | 50 | 1,05 | 7,5 | 12,5 | 0,20 | 0,05 | HBX 2516 |
| | 02520 R | ❍ | | **2,5** | 2,5 | 2,2 | 50 | 1,05 | 7,5 | 12,5 | 0,20 | 0,20 | HBX 2516 |
| | BXBR 03005 R | ❍ | | **3,0** | 3,0 | 2,7 | 50 | 1,30 | 9,0 | 15,0 | 0,25 | 0,05 | HBX 3016 |
| | 03020 R | ❍ | | **3,0** | 3,0 | 2,7 | 50 | 1,30 | 9,0 | 15,0 | 0,25 | 0,20 | HBX 3016 |
| | BXBR 03505 R | ❍ | | **3,5** | 3,5 | 3,1 | 60 | 1,55 | 10,5 | 17,5 | 0,25 | 0,05 | HBX 3516 |
| | 03520 R | ❍ | | **3,5** | 3,5 | 3,1 | 60 | 1,55 | 10,5 | 17,5 | 0,25 | 0,20 | HBX 3516 |
| | BXBR 04005 R | ❍ | | **4,0** | 4,0 | 3,6 | 60 | 1,80 | 12,0 | 20,0 | 0,35 | 0,05 | HBX 4016 |
| | 04020 R | ❍ | | **4,0** | 4,0 | 3,6 | 60 | 1,80 | 12,0 | 20,0 | 0,35 | 0,20 | HBX 4016 |
| | BXBR 04505 R | ❍ | | **4,5** | 4,5 | 4,1 | 70 | 2,05 | 13,5 | 22,5 | 0,35 | 0,05 | HBX 4516 |
| | 04520 R | ❍ | | **4,5** | 4,5 | 4,1 | 70 | 2,05 | 13,5 | 22,5 | 0,35 | 0,20 | HBX 4516 |
| | BXBR 05005 R | ❍ | | **5,0** | 5,0 | 4,5 | 70 | 2,30 | 15,0 | 25,0 | 0,40 | 0,05 | HBX 5016 |
| | 05020 R | ❍ | | **5,0** | 5,0 | 4,5 | 70 | 2,30 | 15,0 | 25,0 | 0,40 | 0,20 | HBX 5016 |
| No Breaker | BXBR 02005 R-NB | | | **2,0** | 2,0 | 1,8 | 50 | 0,80 | 6,0 | 10,0 | 0,20 | 0,05 | HBX 2016 |
| | 02020 R-NB | ❍ | | **2,0** | 2,0 | 1,8 | 50 | 0,80 | 6,0 | 10,0 | 0,20 | 0,20 | HBX 2016 |
| | BXBR 02505 R-NB | | | **2,5** | 2,5 | 2,2 | 50 | 1,05 | 7,5 | 12,5 | 0,20 | 0,05 | HBX 2516 |
| | 02520 R-NB | ❍ | | **2,5** | 2,5 | 2,2 | 50 | 1,05 | 7,5 | 12,5 | 0,20 | 0,20 | HBX 2516 |
| | BXBR 03005 R-NB | ❍ | | **3,0** | 3,0 | 2,7 | 50 | 1,30 | 9,0 | 15,0 | 0,25 | 0,05 | HBX 3016 |
| | 03020 R-NB | ❍ | | **3,0** | 3,0 | 2,7 | 50 | 1,30 | 9,0 | 15,0 | 0,25 | 0,20 | HBX 3016 |
| | BXBR 03505 R-NB | | | **3,5** | 3,5 | 3,1 | 60 | 1,55 | 10,5 | 17,5 | 0,25 | 0,05 | HBX 3516 |
| | 03520 R-NB | ❍ | | **3,5** | 3,5 | 3,1 | 60 | 1,55 | 10,5 | 17,5 | 0,25 | 0,20 | HBX 3516 |
| | BXBR 04005 R-NB | ❍ | | **4,0** | 4,0 | 3,6 | 60 | 1,80 | 12,0 | 20,0 | 0,35 | 0,05 | HBX 4016 |
| | 04020 R-NB | ❍ | | **4,0** | 4,0 | 3,6 | 60 | 1,80 | 12,0 | 20,0 | 0,35 | 0,20 | HBX 4016 |
| | BXBR 04505 R-NB | ❍ | | **4,5** | 4,5 | 4,1 | 70 | 2,05 | 13,5 | 22,5 | 0,35 | 0,05 | HBX 4516 |
| | 04520 R-NB | ❍ | | **4,5** | 4,5 | 4,1 | 70 | 2,05 | 13,5 | 22,5 | 0,35 | 0,20 | HBX 4516 |
| | BXBR 05005 R-NB | ❍ | | **5,0** | 5,0 | 4,5 | 70 | 2,30 | 15,0 | 25,0 | 0,40 | 0,05 | HBX 5016 |
| | 05020 R-NB | ❍ | | **5,0** | 5,0 | 4,5 | 70 | 2,30 | 15,0 | 25,0 | 0,40 | 0,20 | HBX 5016 |

## Adaptor Sleeve (Optional)




| Cat. No. | Stock | DCB (mm) | Applicable Bar |
|---|---|---|---|
| HBX 2016 | ❍ | 2,0 | BXBR 020○○ R(-NB) |
| HBX 2516 | ❍ | 2,5 | BXBR 025○○ R(-NB) |
| HBX 3016 | ❍ | 3,0 | BXBR 030○○ R(-NB) |
| HBX 3516 | ❍ | 3,5 | BXBR 035○○ R(-NB) |
| HBX 4016 | ❍ | 4,0 | BXBR 040○○ R(-NB) |
| HBX 4516 | ❍ | 4,5 | BXBR 045○○ R(-NB) |
| HBX 5016 | ❍ | 5,0 | BXBR 050○○ R(-NB) |

## Spare Parts (For sleeve)

| Screw | (N·m) | Setting Screw | Wrench |
|---|---|---|---|
|  | |  |  |
| BFTX 0409 N | **3,4** | BT 06035 T | TRD 15 |

* BXBR bars can be used with HBB type sleeves. Commercially available sleeves may also be used.



❍ = Japan stock

(N·m) Recommended Tightening Torque (N·m)

# Grooving & Parting-Off Threading Holders

**F1–F70**






| | | |
|---|---|---|
| GND Type Grooving Tools Selection Guide | **GND** | F 2–17 |
| External Grooving, for Small Lathes | **GNDM / GNDL** | F18 |
| Internal Grooving, for Small Lathes | **GNDM-J / GNDL-J** | F20 |
| For Shallow Grooves | **GNDS** | F22 |
| External Multi Purpose/L-Styled Holder | **GNDM / GNDMS** | F24 |
| External Multi Purpose Grooving/Internal Coolant | **GNDM JE** | F26 |
| External Deep Grooving and Cut-Off | **GNDL / GNDLS** | F28 |
| External Deep Grooving and Cut-Off/Internal Coolant | **GNDL JE** | F30 |
| Necking | **GNDN** | F32 |
| Face Grooving/L-Styled Holder | **GNDF / GNDFS** | F34 |
| Internal Grooving/L-Styled Holder | **GNDI / GNDIS** | F38 |
| Internal Grooving for Small Diameters | **SSH**-Series | F42–44 |
| ISO-PSC Polygon Modular Grooving System Holders | **PSC-GNDCM** | F46 |
| ISO-PSC Polygon Modular Grooving System Inserts | **PSC-GNDCF** | F48 |
| ”SumiTurn B-Groove” Holders | **GWC / GWCS** | F50 |
| ”SumiTurn B-Groove” Inserts | **PSC /GWCI /TGA-BF** | F51 |
| ”SumiTurn B-Groove” Inserts | **TGA** R/L **(E)** | F52 |
| ”SumiTurn B-Groove” Inserts | **TGA** R/L **R**, **TGA** R/L **T** | F53 |
| Parting-Off Mini Holders | **SCT** | F54 |
| Sumi-Grip | | F55 |
| ”Sumi-Grip Jr.” Steel Type | **STFH / STFS** R/L | F56 |
| Sumi-Grip Jr. Inserts | **WCF** (NTL) | F57 |
| ”Sumi-Grip” Carbide Blade Type | **WCFH / WCFS** R/L | F58 |
| Sumi-Grip Inserts | **WCF** (NTL) | F60 |
| Threading Tools | **SSTE / SSTI** | F62-69 |
| Inserts for External Threading Holders | **SSTE** | F64 |
| Inserts for Internal Threading Holders | **SSTI** | F65 |

# GND Series







New

New series of internal coolant-type holders for small lathes


## Characteristics


- Wide range of application processes
  Applicable for grooving, turning, copying, facing, boring and cut-off.
- Achieving stable tool life
  An array of chipbreakers improves the efficiency in chip control in various applications and prevents unexpected damages caused by chip blockade.
- Achieving smooth cutting and high efficiency machining
  Holders utilizing one-piece body construction made of special steel, reduce vibration by 30 % during machining as compared to conventional types.
- Achieving high precision grooving widths with moulded inserts
  Grooving insert width tolerance of ±0,03 mm over the entire range

## Cutting Performance

### Eliminates Vibration

Reduces vibration up to 30 % compared to conventional grades thanks to its high-rigidity design.









**GND** Type — Conventional Tool

| | |
|---|---|
| Work Material: | 15CrMo5 |
| Holder: | GNDL R2525M 220 |
| Insert: | GCM N2002 GG |
| Cutting Conditions: | $v_c$ = 100 m/min, f = 0,10 mm/rev, $a_p$ = 20 mm, wet |

### Ensures both, high rigidity and good chip evacuation

Internal





**GND** Type — Comp. A — Comp. B

| | |
|---|---|
| Work Material: | 15CrMo5 |
| Holder: | GNDI R2532 T306 |
| Insert: | GCM N3002 GG |
| Cutting Conditions: | $v_c$ = 100 m/min, f = 0,05 mm/rev, $a_p$ = 3,0 mm, wet |

## Application Examples

### Substantially improved machining efficiency!

High rigidity holder enables high load machining at high feed rate.




| | |
|---|---|
| Work Material: | 42CrMo4 |
| Holder: | GNDL R2525M 320 |
| Insert: | GCM N3002 GG (AC530U) |
| Cutting Conditions: | $v_c$ = 130 m/min, f = 0,30 mm/rev, wet |

### Stable and long tool life ensures reliable functionality even on automatic production lines!

Reduction of chattering prevents unexpected breakage.




**GND** Type — Competitor

| | |
|---|---|
| Work Material: | C53 |
| Holder: | GNDM L2525M 618 |
| Insert: | GCM N6030 RG (AC530U) |
| Cutting Conditions: | $v_c$ = 130 m/min, f = 0,30 mm/rev, wet |


## Internal Coolant Grooving Tool Holder GNDM-J(E) / GNDL-J(E) Type and Grade-Expansion


New Expansion




- Newly developed 2-hole coolant design optimizes cooling of the insert and improves chip removal, extending tool life and allowing for improved speeds and feeds in production.
- Grooving width range from 2,0 to 6,0 mm
- Introducing new holders for small lathes with grooving width of 2,0 to 3,0 mm
- Achieves both high efficiency in high speed machining and extension of tool life due to internal coolant supply to the cutting edge.
- Improves chip control by applying direct coolant from cutting edge side.
- 4 more grades **AC8025P, AC8035P, AC5015S and AC5025S** available.
- The new grades expand the application in steel materials in direction of high speed with the grade **AC8025P** and for more toughness with the grade **AC8035P**.
- In the area for machining heat-resistance alloys and exotic alloys as Inconel and Hastelloy, we recommend the grade **AC5025S** as the first choice and the grade **AC5015S** for high-speed machining in continues cut.

## Wear Resistance




## Chip Control



Coolant Pressure: 7 MPA



Coolant Pressure: 1 MPA



External Coolant

| | |
|---|---|
| Work Material: | Ti-6Al-4V |
| Holder: | GNDM R2525K 312JE |
| Insert: | GCM N3002 GG (AC530U) |
| Cutting Conditions: | $v_c$ = 60 m/min, f = 0,1 mm/rev, $a_p$ = 5,0 mm, wet |


## **CF** Type Chipbreaker for Cut-Off




- Lead angle of 10°/15° for improved sharpness in cut-off machining.
- Asymmetrical chipbreaker design provides excellent chip control even in difficult to machine conditions.



10°/15°



GCMN20003 CF 10



GCMN20003 CF 15














Competitor

| | |
|---|---|
| Work Material: | St42-3 |
| Holder: | GNDM R2525M 220 |
| Insert: | GCM N3002 CF-10,15 (AC1030U) |
| Cutting Conditions: | n = 2000 $min^{-1}$, f = 0,08 mm/rev, wet |

## Inserts - Chipbreaker Series

Achieving stability and longer tool life. A variety of chipbreakers ensures outstanding chip control performance in many different types of applications.

| Grooving / Turning | | Grooving / Cut-Off | | | Cut-Off | | Profiling | Necking | Non Ferrous Metals |
|---|---|---|---|---|---|---|---|---|---|
| General Type | Low Feed Type | General Type | Low Feed Type | Low Cutting ForceType | Cut-Off Type | Low Cutting ForceType | General Type | General Type | General Type |
| MG | ML | GG | GL | GF | CG | CF | RG | RN | GA |
|  |  |  |  |  |  |  |  |  |  |
| Cross Section of Cutting Edge | | | | | | | | | |
|   |   |   |   |   |   |   |   |   |   |
| Grooving Width (mm) | | | | | | | | | |
| 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 | 1,25 1,5 2,0<br>3,0 4,0 5,0<br>6,0 7,0 8,0 |
| Grade | | | | | | | | | |
| AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>*AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>*AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>AC1030U T2500A<br>H10 | AC8025P AC8035P<br>AC830P AC425K<br>AC5015S AC5025S<br>AC520U AC530U<br>AC1030U T2500A<br>H10 |

Stock

* Only use with GNDIS

## Recommended Cutting Conditions

| Work Material | P Carbon Steel / Alloy Steel | | | | M Stainless Steel | | | K Cast Iron | | | S Exotic Alloy | | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Grade | AC830P AC8025P AC8035P | AC520U | AC530U AC1030U | T2500A | AC830P | AC520U AC5015S AC5025S | AC530U AC1030U | AC425K | AC520U | AC530U AC1030U | AC520U AC5015S AC5025S | AC530U AC1030U | H10 |
| Cutting Speed (m/min) | 80–200 | 80–200 | 50–200 | 50–200 | 70–150 | 70–150 | 50–150 | 80–200 | 60–200 | 50–200 | 20–80 | 20–60 | 150–300 |

Please see cutting data page 13

## Excellent Chip Control

### Grooving



**GND** Type
(**GG** Type Chipbreaker)



Conventional Tool

| | |
|---|---|
| Work Material: | 15CrMo5 |
| Holder: | GNDL R2525M 320 |
| Insert: | GCM N3002 GG |
| Cutting Conditions: | $v_c$=100 m/min, f=0,15 mm/rev, $a_p$=12,0 mm, wet |

### Turning



**GND** Type
(**ML** Type Chipbreaker)



Conventional Tool

| | |
|---|---|
| Work Material: | 15CrMo5 |
| Holder: | GNDM R2525M 312 |
| Insert: | GCM N3002 ML |
| Cutting Conditions: | $v_c$=100 m/min, f=0,10 mm/rev, $a_p$=0,5 mm, wet |

### Cut-Off




**GND** Type
(**CG** Type Chipbreaker)



Conventional Tool

| | |
|---|---|
| Work Material: | X5CrMo17122 (Ø 30 mm) |
| Holder: | GNDL R2525M 220 |
| Insert: | GCM R2002 CG 05 |
| Cutting Conditions: | $v_c$ = 100 m/min, f = 0,15 mm/rev, wet |

### Profiling




**GND** Type
(**RG** Type Chipbreaker)




Conventional Tool

| | |
|---|---|
| Work Material: | 15CrMo5 |
| Holder: | GNDM R2525M 312 |
| Insert: | GCM N3015 RG |
| Cutting Conditions: | $v_c$=100 m/min, f=0,15 mm/rev, $a_p$=0,1 mm, wet |

## Chipbreaker Selection




## Grade Selection

New


| Cutting Process | P Steel | M Stainless Steel | K Cast Iron | S Exotic Alloy | N Non Ferrous Metals |
|---|---|---|---|---|---|
| Continuous, high speed ↕ Interrupted, unstable | AC8025P CVD<br>AC8035P (AC830P) CVD<br>AC5025S (AC520U) PVD<br>1st Recommendation AC530U/AC1030U PVD<br>Good machined surface T2500A Uncoated Cermet | AC8035P (AC830P) CVD<br>AC5015S PVD<br>1st Recommendation AC5025S (AC520U) PVD<br>AC530U AC1030U PVD | 1st Recommendation AC425K CVD<br>AC8025P CVD<br>AC5015S PVD<br>AC5025S (AC520U) PVD<br>AC530U AC1030U PVD | AC5015S PVD<br>1st Recommendation AC5025S (AC520U) PVD<br>AC530U AC1030U PVD | 1st Recommendation H10 Uncoated Carbide |

Only AC520U and AC1030U are stocked for inserts of GNDIS holders.

# GND Series

## For External Machining (For Small Lathes)

### Turning / Profiling





Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA





Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA

### Grooving / Cut-Off





Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA




Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA


## ■ Series for External Machining for Small Lathes Series

| Type | Shank Size Height | Shank Size Width | Cutting Width (mm) 1,25 | 1,5 | 2 | 3 | 4 | 5 | 6 | 7 | 8 | Series | Max. Grooving Depth (mm) 5 10 15 20 25 30 | Ref. Page | Applicable Chipbreaker MG | ML | GG | GL | GF | CG | CF | RG | RN | GA |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| For Small Lathes | 10 | 10 | 1,25 | 1,5 | | | | | | | | GNDL | 10 | 18 | | | | | ◎ | | | | | |
| | | | | | 2 | | | | | | | GNDL | 10 | 18 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDL | 10 | 18 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | ◎ |
| | 12 | 12 | 1,25 | 1,5 | | | | | | | | GNDL | 12 | 18 | | | | | ◎ | | | | | |
| | | | | | 2 | | | | | | | GNDL | 12,5 | 18 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | 2 | | | | | | | GNDL-J | 12,5 | 20 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDL | 12,5 | 18 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | ◎ |
| | | | | | | 3 | | | | | | GNDL-J | 12,5 | 20 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | ◎ |
| | 16 | 16 | 1,25 | | | | | | | | | GNDM | 8 | 18 | | | | | ◎ | | | | | |
| | | | 1,25 | 1,5 | | | | | | | | GNDL | 12,5 | 18 | | | | | ◎ | | | | | |
| | | | | 1,5 | | | | | | | | GNDM | 10 | 18 | | | | | ◎ | | | | | |
| | | | | | 2 | | | | | | | GNDM | 12 | 18 | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | 2 | | | | | | | GNDM-J | 12 | 20 | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | 2 | | | | | | | GNDL | 16 | 18 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | 2 | | | | | | | GNDL-J | 16 | 20 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDM | 12 | 18 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDM-J | 12 | 20 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDL | 16 | 18 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDL-J | 16 | 20 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| | 20 | 12 | | | 2 | | | | | | | GNDM | 17 | 18 | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | 2 | | | | | | | GNDM-J | 17 | 20 | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | 2 | | | | | | | GNDL | 21 | 18 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | 2 | | | | | | | GNDL-J | 21 | 20 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDM | 17 | 18 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDM-J | 17 | 20 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDL | 21 | 18 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| | | | | | | 3 | | | | | | GNDL-J | 21 | 20 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |

Stock ◎ 1st Recommendation ○ 2nd Recommendation


## For External Machining (Straight Type)

### Turning / Profiling





| Grooving Width (mm) | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker: MG ML GG GL GF CG CF RG RN GA




| Grooving Width (mm) | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |


Chipbreaker: MG ML GG GL GF CG CF RG RN GA




| Grooving Width (mm) | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |


Chipbreaker: MG ML GG GL GF CG CF RG RN GA

### Grooving / Cut-Off




| Grooving Width (mm) | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker: MG ML GG GL GF CG CF RG RN GA




| Grooving Width (mm) | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker: MG ML GG GL GF CG CF RG RN GA

## ■ Series for External Machining (Straight Type)


| Type | Shank Size Height | Shank Size Width | Cutting Width (mm) | Series | Max. Grooving Depth (mm) | Ref. Page | Applicable Chipbreaker MG | ML | GG | GL | GF | CG | CF | RG | RN | GA |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Straight Type | 20 | 20 | 1,25 1,5 | GNDM | 10 | 24 | | | | | ◎ | | | | | |
| | | | 1,25 1,5 | GNDL | 16 | 28 | | | | | ◎ | | | | | |
| | | | 2 | GNDS | 6 | 22 | | ◎ | ○ | ○ | ○ | ○ | ○ | | ◎ | ○ |
| | | | 2 | GNDM | 10 | 24 | | ◎ | ○ | ○ | ○ | ○ | ○ | | ◎ | ○ |
| | | | 2 | GNDM-JE | 10 | 26 | | ◎ | ○ | ○ | ○ | ○ | ○ | | ◎ | ○ |
| | | | 2 | GNDL | 20 | 28 | | ○ | ○ | ○ | ○ | ○ | ○ | | ◎ | ○ |
| | | | 2 | GNDL-JE | 20 | 30 | | ○ | ○ | ○ | ○ | ○ | ○ | | ◎ | ○ |
| | | | 3 | GNDS | 6 | 22 | ◎ | ◎ | ○ | ○ | ○ | ○ | ○ | ◎ | ○ | ○ |
| | | | 3 | GNDM | 12 | 24 | ◎ | ◎ | ○ | ○ | ○ | ○ | ○ | ◎ | ○ | ○ |
| | | | 3 | GNDM-JE | 12 | 26 | ◎ | ◎ | ○ | ○ | ○ | ○ | ○ | ◎ | ○ | ○ |
| | | | 3 | GNDL | 20 | 28 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ◎ | ○ | ○ |
| | | | 3 | GNDL-JE | 20 | 30 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ◎ | ○ | ○ |
| | 25 | 25 | 4 | GNDS | 10 | 22 | ◎ | ◎ | ○ | ○ | ○ | ○ | | ◎ | ○ | ○ |
| | | | 4 | GNDM | 18 | 24 | ◎ | ◎ | ○ | ○ | ○ | ○ | | ◎ | ○ | ○ |
| | | | 4 | GNDM-JE | 18 | 26 | ◎ | ◎ | ○ | ○ | ○ | ○ | | ◎ | ○ | ○ |
| | | | 4 | GNDL | 25 | 28 | ○ | ○ | ○ | ○ | ○ | ○ | | ◎ | ○ | ○ |
| | | | 4 | GNDL-JE | 25 | 30 | ○ | ○ | ○ | ○ | ○ | ○ | | ◎ | ○ | ○ |
| | | | 5 6 | GNDS | 10 | 22 | ◎ | ◎ | ○ | ○ | ○ | | | ◎ | ○ | ○ |
| | | | 5 6 | GNDM | 18 | 24 | ◎ | ◎ | ○ | ○ | ○ | | | ◎ | ○ | ○ |
| | | | 5 6 | GNDM-JE | 18 | 26 | ◎ | ◎ | ○ | ○ | ○ | | | ◎ | ○ | ○ |
| | | | 5 6 | GNDL | 25 | 28 | ○ | ○ | ○ | ○ | ○ | | | ◎ | ○ | ○ |
| | | | 5 6 | GNDL-JE | 25 | 30 | ○ | ○ | ○ | ○ | ○ | | | ◎ | ○ | ○ |
| | | | 7 8 | GNDM | 18 | 24 | ◎ | ◎ | ○ | ○ | ○ | | | ◎ | | |
| | | | 7 8 | GNDL | 25 | 28 | ○ | ○ | ○ | ○ | ○ | | | ◎ | | |
| | 32 | 25* | 3 | GNDM | 12 | 24 | ◎ | ◎ | ○ | ○ | ○ | ○ | ○ | ◎ | ○ | ○ |
| | | | 3 | GNDL | 20 | 28 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ◎ | ○ | ○ |
| | | | 4 | GNDM | 18 | 24 | ◎ | ◎ | ○ | ○ | ○ | ○ | | ◎ | ○ | ○ |
| | | | 4 | GNDL | 25 | 28 | ○ | ○ | ○ | ○ | ○ | ○ | | ◎ | ○ | ○ |
| | 32 | 32 | 5 6 | GNDM | 18 | 24 | ◎ | ◎ | ○ | ○ | ○ | | | ◎ | ○ | ○ |
| | | | 5 6 | GNDL | 25 | 28 | ○ | ○ | ○ | ○ | ○ | | | ◎ | ○ | ○ |
| | | | 7 8 | GNDM | 18 | 24 | ◎ | ◎ | ○ | ○ | ○ | | | ◎ | | |
| | | | 7 8 | GNDL | 25 | 28 | ○ | ○ | ○ | ○ | ○ | | | ◎ | | |

Stock　　* Make to order item (32x25mm)　　◎ 1st Recommendation　　○ 2nd Recommendation

# GND Series

## For External Machining (L Type)

### Turning / Profiling





Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA

### Grooving / Cut-Off




Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA

## ■ Series for External Machining (L Type)

| Type | Shank Size Height | Shank Size Width | Cutting Width (mm) | Series | Max. Grooving Depth (mm) | Ref. Page | Applicable Chipbreaker MG | ML | GG | GL | GF | CG | CF | RG | RN | GA |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| L Type | 20 | 20 | 2 | GNDLS | 16 | F28 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | 3 | GNDMS | 10 | F24 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | ◎ |
| | | | 3 | GNDLS | 16 | F28 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | ◎ |
| | | | 4 | GNDMS | 12 | F24 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ○ | ◎ |
| | | | 5 | GNDMS | 12 | F24 | ◎ | ◎ | ◎ | ◎ | ◎ | | | ◎ | ○ | ◎ |
| | 25 | 25 | 2 | GNDLS | 18 | F28 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ◎ |
| | | | 3 | GNDMS | 12 | F24 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | ◎ |
| | | | 3 | GNDLS | 18 | F28 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | ◎ |
| | | | 4 | GNDMS | 14 | F24 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | ◎ | ○ | ◎ |
| | | | 4 | GNDLS | 23 | F28 | ○ | ○ | ◎ | ◎ | ◎ | ◎ | | ◎ | ○ | ◎ |
| | | | 5 6 | GNDMS | 14 | F24 | ◎ | ◎ | ◎ | ◎ | ◎ | | | ◎ | ○ | ◎ |
| | | | 5 6 | GNDLS | 23 | F28 | ○ | ○ | ◎ | ◎ | ◎ | | | ◎ | ○ | ◎ |

Cutting Width (mm): 1,25 1,5 2 3 4 5 6 7 8


Max. Grooving Depth (mm): 5 10 15 20 25 30

■ Stock

◎ 1st Recommendation ○ 2nd Recommendation

## Cassettes for Radial Machining

### Grooving




Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA

## ■ Radial Grooving Cassettes

| Type | Applicable Holders | Cutting Width (mm) | Series | Max. Grooving Depth (mm) | Ref. Page | Applicable Chipbreaker MG | ML | GG | GL | GF | CG | CF | RG | RN | GA |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Cassette | GND00 | 2 | GNDCM | 12 | F46 | | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| | | 3 | GNDCM | 12 | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | ◎ |
| | GND90 | 4 | GNDCM | 18 | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | ○ | ◎ |
| | | 5 6 | GNDCM | 18 | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | | ○ | ◎ |

Cutting Width (mm): 1.25 1.5 2 3 4 5 6 7 8


Max. Grooving Depth (mm): 5 10 15 20 25 30

■ Stock

◎ 1st Recommendation ○ 2nd Recommendation


## For Face Machining

### Grooving / Turning / Profiling




| Grooving Width (mm) | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker: MG ML GG GL GF CG CF RG RN GA




| Grooving Width (mm) | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker: MG ML GG GL GF CG CF RG RN GA

## ■ Series for Face Machining


| Type | Shank Size Height | Shank Size Width | Cutting Width (mm) | Series | Max. Grooving Depth (mm) | Bore (mm) | Ref. Page | Applicable Chipbreaker |
|---|---|---|---|---|---|---|---|---|
| Straight Type | 20 | 20 | 3 | GNDF | 12 | ø35 ø45 | F34 | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 3 | | 12 | ø40 ø55 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 3 | | 18 | ø50 ø70 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 3 | | 18 | ø65 ø100 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 3 | | 18 | ø90 ø150 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 3 | | 18 | ø140 ø200 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 3 | | 18 | ø180 ø300 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 4 | GNDF | 18 | ø40 ø55 | F34 | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 4 | | 23 | ø50 ø70 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 4 | | 23 | ø65 ø90 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 4 | | 23 | ø85 ø130 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 4 | | 23 | ø125 ø200 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 4 | | 23 | ø180 ø300 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 4 | | 23 | ø280 ø1.000 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | 25 | 25 | 4 | | 23 | | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 5 | GNDF | 23 | ø50 ø70 | F34 | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 5 | | 23 | ø65 ø90 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 5 | | 23 | ø85 ø130 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 5 | | 23 | ø125 ø200 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 5 | | 23 | ø180 ø300 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 5 | | 23 | ø280 ø1.000 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | GNDF | 23 | ø50 ø75 | F34 | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | | 23 | ø70 ø110 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | | 23 | ø100 ø200 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | | 23 | ø180 ø300 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | | 23 | ø280 ø1.000 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| L Type | 20 | 20 | 6 | GNDFS | 20 | ø70 ø100 | F36 | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | | 20 | ø100 ø200 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | | 20 | ø180 ø300 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | | 20 | ø280 ø1.000 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 6 | | 20 | ø450~ | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | 25 | 25 | 8 | GNDFS | 20 | ø70 ø100 | F36 | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 8 | | 20 | ø100 ø200 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 8 | | 20 | ø180 ø300 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 8 | | 20 | ø280 ø1.000 | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |
| | | | 8 | | 20 | ø450~ | | ◎ ◎ ◎ ◎ ◎ ○ ○ ○ ○ ○ |

Stock  Make to order item  ◎ 1st Recommendation  ○ 2nd Recommendation

# GND Series

## For Necking

**GNDN**
Straight Type



Shank Size
Height x Width
20 mm x 20 mm
25 mm x 25 mm

F32

Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA

### ■ Series for Necking

| Type | Shank Size | | Cutting Width (mm) 2 | 3 | 4 | 5 | 6 | Series | Max. Grooving Depth (mm) 5 10 15 20 25 30 | Min. Bore (mm) | Ref. Page | Applicable Chipbreaker MG | ML | GG | GL | GF | CG | CF | RG | RN | GA |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Straight Type | 20 | 20 | 2 | | | | | GNDN | 2,0 | ø20 | F32 | | | | | | | | | ◯ | |
| | | | | 3 | | | | | 2,5 | ø20 | | | | | | | | | | ◯ | |
| | 25 | 25 | | | 4 | | | | 3,0 | ø30 | | | | | | | | | | ◯ | |
| | | | | | | 5 | | | 3,5 | ø30 | | | | | | | | | | ◯ | |
| | | | | | | | 6 | | 4,0 | ø30 | | | | | | | | | | ◯ | |

Min. Bore, 45°, Max. Groov. Depth


Stock

## Tips for Necking

### Notes for Undercutting

Recommended Chipbreaker: **RN**

Distance between Workpiece and Necking





| Edge Width CW (mm) | Depth of Necking APMX (mm) | Distance between Workpiece and Necking APMX2 (mm) |
|---|---|---|
| 2,0 | 1,50 | 0,64 |
| 3,0 | 2,00 | 0,79 |
| 4,0 | 3,00 | 1,29 |
| 5,0 | 3,50 | 1,44 |
| 6,0 | 4,00 | 1,59 |

The recommended cutting conditions for necking are the same as grooving with RN type chipbreaker and edge width.
To prevent interference with the work material, do not use the holder for less than the minimum cutting diameter (DMIN) as specified for GNGN type holders.

Chip Shape







| | |
|---|---|
| Work Material: | 34CrMo4 |
| Holder: | GNDN R2020K 325-020 |
| Insert: | GCM N3015 RN |
| Cutting Conditions: | $v_c$ = 100m/min, f = 0,1mm/rev |
| | Depth of Necking = 1,0mm, wet |

## Cassettes for Face Machining

### Face Grooving / Turning / Profiling




Grooving Width (mm)

| | | |
|---|---|---|
| 1,25 | 1,5 | 2,0 |
| 3,0 | 4,0 | 5,0 |
| 6,0 | 7,0 | 8,0 |

Chipbreaker

MG ML GG GL GF CG CF RG RN GA

## ■ Face Grooving Cassettes


| Type | Cutting Width (mm) 3 | 4 | 5 | 6 | 7 | 8 | Series | Max. Grooving Depth (mm) 5 10 15 20 25 30 | Bore (mm) 50 100 150 200 250 300 1.000 | Ref. Page | Applicable Chipbreaker MG | ML | GG | GL | GF | CG | CF | RG | RN | GA |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Straight Type | 3 | | | | | | GNDCF R/L | 12 | ø40 ø55 | F48 | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | 3 | | | | | | | 15 | ø50 ø75 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | 3 | | | | | | | 15 | ø65 ø100 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | 3 | | | | | | | 18 | ø90 ø150 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | 3 | | | | | | | 18 | ø140 ø200 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | 4 | | | | | | 18 | ø40 ø55 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | 4 | | | | | | 18 | ø50 ø70 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | 4 | | | | | | 18 | ø65 ø90 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | 4 | | | | | | 18 | ø85 ø130 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | 4 | | | | | | 18 | ø125 ø200 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | 4 | | | | | | 18 | ø180 ø300 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | 5 | | | | | 18 | ø50 ø70 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | 5 | | | | | 18 | ø65 ø90 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | 5 | | | | | 18 | ø85 ø130 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | 5 | | | | | 18 | ø125 ø200 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | 5 | | | | | 18 | ø180 ø300 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | | 6 | | | | 18 | ø50 ø75 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | | 6 | | | | 18 | ø70 ø110 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | | 6 | | | | 18 | ø100 ø200 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | | 6 | | | | 18 | ø180 ø300 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |
| | | | | 6 | | | | 18 | ø280 ø1.000 | | ◎ | ○ | ◎ | ○ | ○ | | | | ○ | ◎ |

Stock  Make to order item  ◎ 1st Recommendation  ○ 2nd Recommendation

# GND Series


## For Internal Machining (≥ Ø 14 mm)

### Grooving / Turning / Copying




## For Internal Machining (≥ Ø 32 mm)

### Grooving / Turning / Copying




## ■ Series for Internal Machining (≥ Ø 14 mm)

| Type | Shank Size ØDs(mm) | Cutting Width (mm) 1,5 | 2 | 3 | Series | Max. Grooving Depth (mm) 5 10 15 20 25 30 | Min. Bore (mm) | Ref. Page | Applicable Chipbreaker ML | GF |
|---|---|---|---|---|---|---|---|---|---|---|
| Straight Type | ø12 | 1,5 | | | GNDIS | 2,6 | ø14 | F40 | | ◎ |
| | | 1,5 | | | | 3,6 | ø14 | | | ◎ |
| | | | 2 | 3 | | 2,6 | ø14 | | ◎ | ◎ |
| | | | 2 | 3 | | 3,6 | ø14 | | ◎ | ◎ |
| | ø16 | 1,5 | | | GNDIS | 3,6 | ø16 | | | ◎ |
| | | 1,5 | | | | 4,6 | ø20 | | | ◎ |
| | | | 2 | 3 | | 3,6 | ø16 | | ◎ | ◎ |
| | | | 2 | 3 | | 4,6 | ø20 | | ◎ | ◎ |
| | ø20 | 1,5 | | | GNDIS | 6,6 | ø25 | | | ◎ |
| | | | 2 | 3 | | 6,6 | ø25 | | ◎ | ◎ |

















Stock  GNDIS type: use smaller GXM type inserts  ◎ 1st Recommendation

## ■ Series for Internal Machining (≥ Ø 32 mm)

| Type | Shank Size ØDs(mm) | Cutting Width (mm) 2 | 3 | 4 | 5 | 6 | Series | Max. Grooving Depth (mm) 5 10 15 20 25 30 | Min. Bore (mm) | Ref. Page | Applicable Chipbreaker MG | ML | GG | GL | GF | CG | CF | RG | RN | GA |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Straight Type | ø25 | 2 | | | | | GNDI | 6 | ø32 | F38 | | ◎ | ○ | ◎ | ◎ | | | | ◎ | ◎ |
| | | | 3 | 4 | 5 | | | 6 | ø32 | | ○ | ◎ | ○ | ◎ | ◎ | | | | ◎ | ◎ |
| | ø32 | 2 | | | | | | 6 | ø32 | | | ◎ | ○ | ◎ | ◎ | | | | ◎ | ◎ |
| | | | 3 | 4 | 5 | | | 10 | ø40 | | ○ | ◎ | ○ | ◎ | ◎ | | | | ◎ | ◎ |
| | ø40 | | 3 | 4 | 5 | 6 | | 11 | ø50 | | ○ | ◎ | ○ | ◎ | ◎ | | | | ◎ | ◎ |

Stock  ◎ 1st Recommendation  ○ 2nd Recommendation

## Chipbreaker Selection Guide

| Groov. Width (mm) | Recommended Cutting Conditions | | Nose Radius (mm) | Chipbreaker |
|---|---|---|---|---|
| | Grooving | Turning | | |
| 1,25 |  | | 0,05 |  |
| 1,5 |  | | 0,05 |  |
| 2,0 |  |  | 0,03<br>0,2<br>0,4<br>1,0 |  |
| 3,0 |  |  | 0,03<br>0,2<br>0,4<br>1,5 |  |
| 4,0 |  |  | 0,2<br>0,4<br>0,8<br>2,0 |  |
| 5,0 |  |  | 0,2<br>0,4<br>0,8<br>2,5 |  |
| 6,0 |  |  | 0,2<br>0,4<br>0,8<br>3,0 |  |
| 7,0 |  |  | 0,2<br>0,4<br>0,8<br>3,5 |  |
| 8,0 |  |  | 0,2<br>0,4<br>0,8<br>4,0 |  |

## Recommended Cutting Conditions

| Work Material | P | | | | | M | | | K | | | | S | | N |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Carbon Steel, Alloy Steel | | | | | Stainless Steel | | | Cast Iron | | | | Exotic Alloy | | |
| Grade | AC8025P | AC8035P AC830P | AC5015S AC520U | AC5025S AC530U AC1030U | T2500A | AC8035P AC830P | AC5015S AC520U | AC5025S AC530U AC1030U | AC8025P | AC425K | AC5015S AC520U | AC5025S AC530U AC1030U | AC5015S AC520U | AC5025S AC530U AC1030U | H10 |
| Cutting Speed (m/min) | 80–250 | 80–200 | 80–200 | 50–200 | 50–200 | 70–150 | 70–150 | 50–150 | 80–200 | 80–200 | 60–200 | 50–200 | 20–80 | 20–60 | 150–300 |

# GND Series

## ■ Identification Details – Holders

**GND M R 25 25 (M) - (T) 3 12 (J/JE) (- 035)**

| ① Series Symbol | ② Application | ③ Holder Design | ④ Shank Height / Diameter | ⑤ Shank Width/ Work Diameter | ⑥ Shank Length | ⑦ Type | ⑧ Insert Width | ⑨ Max. Grooving Depth | ⑩ Coolant Supply | ⑪ Min. Machining Diameter |
|---|---|---|---|---|---|---|---|---|---|---|
| GND | Chart 2 | Chart 3 | Chart 4 | Chart 5 | Chart 6 | Internal Grooving | Chart 7 | Chart 8 | **JE**: Internal Coolant (Screw Connection European Standard)<br>**J**: Internal Coolant (Screw Connection Japanese Standard) | (mm) |

### ② Application

| Symbol | Application | |
|---|---|---|
| S | External Multi-Purpose | Grooving/Cut Off/ Turning/Profiling |
| **M** | External Multi-Purpose | Grooving/Cut Off/ Turning/Profiling |
| L | External Grooving | Grooving/Cut Off |
| MS | External L-Styled (Side Cut) Multi-Purpose | Grooving/Turning/Profiling |
| LS | External L-Styled (Side Cut) Deep Grooving | Grooving |
| N | Necking | Necking |
| I | Internal Grooving | Grooving/Turning/ Profiling |
| IS | Internal Grooving | Grooving/Turning/ Profiling |
| F | Face Grooving | Grooving/Turning/ Profiling |
| FS | L-Shaped Tools for Facing | Grooving/Turning/ Profiling |
| CM | Cassette for Polygon Holder | Radial Grooving |
| CF | Cassette for Polygon Holder | Face Grooving |

### ③ Holder Design

| Symbol | Direction |
|---|---|
| **R** | Right |
| L | Left |

### ④ Shank Height / Diameter

| Application | Symbol | Height (mm) |
|---|---|---|
| External/ Face Grooving (Shank Height) | 10 | 10 |
| | 12 | 12 |
| | 16 | 16 |
| | 20 | 20 |
| | **25** | 25 |
| Internal Grooving (Shank Diameter) | 25 | 25 |
| | 32 | 32 |
| | 40 | 40 |

### ⑤ Shank Width / Work Diameter

| Application | Symbol | Width (mm) |
|---|---|---|
| External/ Face Grooving (Shank Width) | 10 | 10 |
| | 12 | 12 |
| | 16 | 16 |
| | 20 | 20 |
| | **25** | 25 |
| Internal Grooving (Shank Diameter) | 32 | 32 |
| | 40 | 40 |
| | 50 | 50 |

### ⑥ Shank Length

| Symbol | Length (mm) |
|---|---|
| JX | 120 |
| K | 125 |
| **M** | 150 |
| P | 170 |

### ⑧ Insert Width

| Symbol | Groov. Width (mm) |
|---|---|
| 1,25 | 1,25 |
| 1,5 | 1,5 |
| 2 | 2,0 |
| **3** | 3,0 |
| 4 | 4,0 |
| 5 | 5,0 |
| 6 | 6,0 |
| 7 | 7,0 |
| 8 | 8,0 |

### ⑨ Max. Grooving Depth

| Symbol | Groov. Depth (mm) | Symbol | Groov. Depth (mm) |
|---|---|---|---|
| 06 | 6,0 | 20 | 20,0 |
| 08 | 8,0 | 23 | 23,0 |
| 10 | 10,0 | 25 | 25,0 |
| 11 | 11,0 | | |
| **12** | 12,0 | | |
| 12,5 | 12,5 | | |
| 14 | 14,0 | | |
| 16 | 16,0 | | |
| 18 | 18,0 | | |

To ensure maximum rigidity, use the multi-purpose type holder to machine the maximum grooving depth.


## ■ Identification Details – Inserts

**G C M N 30 02 (S) - G G - (05)**

| ① Series Symbol | ② Front Relief Angle | ③ Tolerance | ④ Insert Design | ⑤ Insert Width | ⑥ Nose Radius | ⑦ Applicable Holder | ⑧ Chipbreaker | ⑨ Front Cutt. Edge Angle |
|---|---|---|---|---|---|---|---|---|
| **G**rooving | **C**: 7°<br>X: Special | G Class<br>**M** Class | Symbol / Direction<br>**N** Neutral<br>R Right Hand<br>L Left Hand | Symbol / Groov. Width (mm)<br>125 / 1,25<br>150 / 1,5<br>20 / 2,0<br>**30** / 3,0<br>40 / 4,0<br>50 / 5,0<br>60 / 6,0<br>70 / 7,0<br>80 / 8,0 | Symbol / R (mm)<br>005 / 0,05<br>**02** / 0,2<br>04 / 0,4<br>08 / 0,8<br>15 / 1,5<br>20 / 2,0<br>25 / 2,5<br>30 / 3,0 | Symbol / Holder<br>S / GNDIS | Symbol / Application<br>MG Multi-Purpose: General Feed<br>ML Multi-Purpose: Low Feed<br>**GG** Grooving: General Feed<br>GL Grooving: Low Feed<br>GF Grooving: Low Cutting Forces<br>CG Cut-Off<br>CF Cut-Off: Low Cutting Forces<br>RG Copying: General Feed<br>RN Multi-Purpose: General Feed<br>GA Multi-Purpose: General Feed | PSI<br>**05** : 5°<br>10 : 10°<br>15 : 15° |

## Key Points for Face Machining


### Holder Selection




Select a holder so that the outer diameter of the first groove to be machined comes within the range of maximum and minimum grooving diameter of the holder.

### Precautions for Groove Expansion

Recommended Chipbreaker: **MG, ML, GG, GL, GF**





If the first groove meets the range of the effective grooving diameter during groove expansion, the grooving diameter will not be limited for the second and later passes.

### Precautions for Turning

Recommended Chipbreaker: **MG, ML**

Considering the rigidity of the holder, we recommend machining from the outside to the inside.




If machining is performed toward the outside, the wall thickness remaining on the principal force side will become thinner, which reduces the rigidity of the holder.


- If the first groove meets the range of the effective grooving diameter in face turning, the grooving diameter will not be limited for the second and later passes.
- Select the chipbreaker of the lower limit side of the recommended cutting conditions and straight chips before evacuation. (In face grooving, broken chips easily get stuck in grooves, which causes problems.)
- When breaking chips, step feed is required.

## Key Points for Internal Machining

### Precautions for Internal Machining

Recommended Chipbreaker: **ML, GL**

If the prepared hole diameter is small, use an ML or GL low-feed chipbreaker, each of which reduces chip curl diameter, to ensure adequate chip evacuation.



GCMN 3004 MG



GCMN 3002 ML



GCMN 3002 GG



GCMN 3002 GL


| | |
|---|---|
| Work Material: | 15CrMo5 (Ø 25 mm) |
| Holder: | GNDI R2532 T306 |
| Insert: | GCM N300□-□□ |
| Cutting Conditions: | $v_c$=100 m/min, f=0,10 mm/rev, $a_p$=3,0 mm, wet |

Internal Machining



GCMN 3002 GG

External Machining



GCMN 3002 GG

⚠ Chip shapes differ between internal and external machining even under the same cutting conditions.


| | |
|---|---|
| Work Material: | 15CrMo5 |
| Holder: | GNDL R2525M 320 |
| Insert: | GCM N3002 GG |
| Cutting Conditions: | $v_c$=100 m/min, f=0,10 mm/rev, $a_p$=5 mm, wet |

## Precautions for Grooving Tool Holders GND Series


### ■ Notes on how to Attach Inserts

① Remove any foreign particles or oil from the insert seat before attaching the insert.
② Ensure the seat location is clean and free of damage.
③ Slide the insert level over its seat.
④ Push the insert with its opposite end (the holder side) firmly against the insert stop end.
⑤ The recommended tightening torque is 5 N·m. Tightening above the recommended torque may damage the insert or the holder which could cause injury and other accidents.

③ Attach insert on the seat flat.




④ Push insert fully into place.





### ■ Notes on how to Apply Holders

① Remove any foreign particles or oil from the tool post before attaching the holder.
② Ensure the seat location is clean and free of damage.
③ Attach the holder so that the insert is perpendicular to the workpiece.
④ Set holder with shortest possible overhang.
⑤ When grooving or turning, adjust the center height of the cutting edge to as close ±0 mm as possible. (Within ±0,1 mm is recommended)
⑥ Incorrect center height adjustment may cause chattering. (In cut-off applications, adjust the center height of the cutting edge to a value from 0,0 to +0,2 mm). A lower center height will result in larger nip at the center.


③ Attach at right angle to work-piece.



④ Set with short over-hang





⑥ Center height ad-justment in cut-off applications





### ■ Notes on Setting Coolant Supply Nozzle

Set the coolant supply nozzle so that coolant can be supplied from the top of the upper clamp unit.



### ■ Maximum Depth of Cut


Maximum depth of cut when pulling up with RG chipbreaker





| Grooving Width (mm) | Max. Depth of Cut (mm) |
|---|---|
| CW | E1 |
| 3,0 | 0,15 |
| 4,0 | 0,20 |
| 5,0 | 0,25 |
| 6,0 | 0,30 |
| 7,0 | 0,35 |
| 8,0 | 0,40 |

## Key Points of Internal Coolant-Type Holders for Small Lathes

The insert for internal coolant-type 12 mm and 16 mm holders for small lathes can be replaced from either the top or bottom.





GNDL R/L1212JX-_ _ _ ._ J




GNDM R/L1616JX-_ _ _J
GNDL R/L1616JX-_ _ _J

## Key Points for Connecting Hoses and Connectors

### ■ Connecting Hoses and Connectors




Apply sealant such as commercial sealing tape to the piping connection parts.
GNDM-JE type holders have a plug (XP02-E) mounted on the holder back end at shipping. (see fig.1)
When piping from the holder back end, mount a grub screw (BT0505-E) on the bottom of the holder for use. (see fig. 2)

Fig. 1 Piping from bottom







Fig. 2 Piping from back end





### ■ Connecting Hoses and Connectors (for Small Lathes)





Apply sealant such as commercial sealing tape to the piping connection parts.
Refer to the figur below for mounting the plug during piping.

Piping from side (when shipped)





Piping from rear




* The plug will protrude a few millimeters when mounted to the side.

Hoseless coolant support products (when shipped)





*1 The plug will protrude a few millimeters when mounted to the side.
*2 A plug is attached when shipped. Remove this plug before supplying coolant without a hose.

## Holder with Hoseless Coolant Support

Direct coolant supply from the tool post is possible without a hose

Connector for Hoseless Coolant Supply

Remove the plug before supplying coolant without a hose.




# GNDM / GNDL Type

Expansion

## External General-Purpose Type for Small Lathes (Grooving, Turning, Profiling)

**GNDM**

External Grooving (Small Tools)



External

Cut-Off

Fig. 1







Fig. 2




Above figures show right hand tools.

Use the multi-purpose profiling insert for turning (wide grooves).

### ■ Spare Parts



### ■ Holders


| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Max. Cutt-Off Dia (mm) | Fig. | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | WF2 | CW | CDX | | | | | | |
| GNDM R/L 1616 JX 1.2508 | ● | ● | 16 | 16 | 120 | (16) | 16 | 26 | 0 | 1,25 | 8,0 | 16 | 1 | GCM N125005 GF | BX0515 | 4,0 | LH040 |
| GNDM R/L 1616 JX 1.510 | ● | ● | 16 | 16 | 120 | (16) | 16 | 26 | 0 | 1,50 | 10,0 | 20 | | GCM N150005 GF | | | |
| GNDM R/L 1616 JX 212 | ● | ● | 16 | 16 | 120 | (16) | 16 | 30 | 0 | 2,00 | 12,0 | 24 | | GCM □20○○-□□ | | | |
| GNDM R/L 1616 JX 312 | ● | ● | 16 | 16 | 120 | (16) | 16 | 30 | 0 | 3,00 | 12,0 | 24 | | GCM □30○○-□□ | | | |
| GNDM R/L 2012 JX 217 New | ❍ | ❍ | 20 | 12 | 120 | (12) | 20 | 26,5 | 0 | 2,00 | 17,0 | 34 | 2 | GCM □20○○-□□ | BFTX0414 | 3,0 | LT15-10 |
| GNDM R/L 2012 JX 317 New | ❍ | ❍ | 20 | 12 | 120 | (12) | 20 | 26,5 | 0 | 3,00 | 17,0 | 34 | | GCM □30○○-□□ | | | |

Select holders and inserts with the same grooving width (CW).

## External Grooving / Cut-Off for Small Lathes

**GNDL**

External Grooving (Small Tools)



External

Cut-Off

Fig. 1





Fig. 2







Fig. 3




Above figures show right hand tools.

### ■ Spare Parts




### ■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Max. Cutt-Off Dia (mm) | Fig. | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | HBH | LH | LH2 | WF2 | CW | CDX | | | | | | |
| GNDL R/L 1010 JX 1.2510 | ● | ● | 10 | 10 | 120 | (10) | 10 | 2,0 | 18 | 18,3 | 0 | 1,25 | 10,0 | 20 | 1 | GCM N125005 GF | BFTX0412N | 3,0 | LT15-10 |
| GNDL R/L 1010 JX 1.510 | ● | ● | 10 | 10 | 120 | (10) | 10 | 2,0 | 18 | 18,3 | 0 | 1,50 | 10,0 | 20 | | GCM N150005 GF | | | |
| GNDL R/L 1010 JX 210 | ● | ● | 10 | 10 | 120 | (10) | 10 | 2,0 | 22 | 22,3 | 0 | 2,00 | 10,0 | 20 | | GCM □20○○-□□ | | | |
| GNDL R/L 1010 JX 310 | ● | ● | 10 | 10 | 120 | (10) | 10 | 2,0 | 22 | 22,3 | 0 | 3,00 | 10,0 | 20 | | GCM □30○○-□□ | | | |
| GNDL R/L 1212 JX 1.2512 | ● | ● | 12 | 12 | 120 | (12) | 12 | 2,0 | 19 | 19,3 | 0 | 1,25 | 12,0 | 24 | 1 | GCM N125005 GF | BFTX0412N | 3,0 | LT15-10 |
| GNDL R/L 1212 JX 1.512 | ● | ● | 12 | 12 | 120 | (12) | 12 | 2,0 | 19 | 19,3 | 0 | 1,50 | 12,0 | 24 | | GCM N150005 GF | | | |
| GNDL R/L 1212 JX 212.5 | ● | ● | 12 | 12 | 120 | (12) | 12 | 2,0 | 22 | 22,3 | 0 | 2,00 | 12,5 | 25 | | GCM □20○○-□□ | | | |
| GNDL R/L 1212 JX 312.5 | ● | ● | 12 | 12 | 120 | (12) | 12 | 2,0 | 22 | 22,3 | 0 | 3,00 | 12,5 | 25 | | GCM □30○○-□□ | | | |
| GNDL R/L 1616 JX 1.2512.5 | ❍ | ● | 16 | 16 | 120 | (16) | 16 | – | 28 | – | 0 | 1,25 | 12,5 | 25 | 2 | GCM N125005 GF | BFTX0515 | 4,0 | LH040 |
| GNDL R/L 1616 JX 1.512.5 | ● | ● | 16 | 16 | 120 | (16) | 16 | – | 28 | – | 0 | 1,50 | 12,5 | 25 | | GCM N150005 GF | | | |
| GNDL R/L 1616 JX 216 | ● | ● | 16 | 16 | 120 | (16) | 16 | – | 32 | – | 0 | 2,00 | 16,0 | 32 | | GCM □20○○-□□ | | | |
| GNDL R/L 1616 JX 316 | ● | ● | 16 | 16 | 120 | (16) | 16 | – | 32 | – | 0 | 3,00 | 16,0 | 32 | | GCM □30○○-□□ | | | |
| GNDL R/L 2012 JX 221 New | ❍ | ❍ | 20 | 12 | 120 | (12) | 20 | – | 30,5 | – | 0 | 2,00 | 21,0 | 42 | 3 | GCM □20○○-□□ | BFTX0414 | 3,0 | LT15-10 |
| GNDL R/L 2012 JX 321 New | ❍ | ❍ | 20 | 12 | 120 | (12) | 20 | – | 30,5 | – | 0 | 3,00 | 21,0 | 42 | | GCM □30○○-□□ | | | |

Select holders and inserts with the same grooving width (CW).





● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

## Inserts for GNDM / GNDL (Small Tools)

Coated Carbide | Cermet | Carbide

Fig. 1





Fig. 2





Fig. 3





Fig. 4




### ● Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |

### ● External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |

### ● Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |

### ● Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |

### ● Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| GCM N125005 GF | – | – | – | – | – | ● | – | 1,25 | ±0,03 | 0,05 | 17,4 | 3,2 | 1 |
| N150005 GF | – | – | – | – | – | ● | – | 1,5 | ±0,03 | 0,05 | 17,4 | 3,7 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |

### ● Cut-Off Machining (Handed Edge)

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | AC1030U | PSI | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM R2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 4 |
| L2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | |
| GCM R3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| L3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| GCM R4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| L4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| GCM R20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | 4 |
| L20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| GCM R20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |

GCM R: Right hand GCM L: Left hand


Combine the insert with a holder such that the width of cut (CW) matches.

# GNDM-J/GNDL-J Type

New

## Holder with Internal Coolant

## External Multi-Purpose Type for Small Lathes (Grooving, Turning, Profiling)




External

Cut-Off

Internal Coolant

Use the multi-purpose profiling insert for turning (wide grooves).

Fig. 1







Fig. 2




Above figures show right hand tools.

### Spare Parts





### Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Max. Cutt-Off Dia (mm) | Fig. | Applicable Insert | Screw / Cap Screw | N·m | Plug | Wrench for Upper Surface | Wrench for Lower Surface |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | WF2 | CW | CDX | | | | | | | | |
| GNDM R/L 1616 JX 212 J | ❍ | ❍ | 16 | 16 | 120 | (16) | 16 | 30,0 | 0 | 2,0 | 12,0 | 24 | 1 | GC□ □20○○-□□ | CP-M5-20-1 | 5,0 | XP02 | LH040 | LH025 |
| GNDM R/L 1616 JX 312 J | ❍ | ❍ | 16 | 16 | 120 | (16) | 16 | 30,0 | 0 | 3,0 | 12,0 | 24 | | GC□ □30○○-□□ | | | | | |
| GNDM R/L 2012 JX 217 J | ❍ | ❍ | 20 | 12 | 120 | (12) | 20 | 26,5 | 0 | 2,0 | 17,0 | 34 | 2 | GC□ □20○○-□□ | BFTX0414 | 3,0 | XP02 | LT15-10 | |
| GNDM R/L 2012 JX 317 J | ❍ | ❍ | 20 | 12 | 120 | (12) | 20 | 26,5 | 0 | 3,0 | 17,0 | 34 | | GC□ □30○○-□□ | | | | | |

Select holders and inserts with the same grooving width (CW).

Grooving & Parting-Off

## External Grooving / Cut-Off for Small Lathes




External

Cut-Off

Internal Coolant

Fig. 1





Fig. 2







Fig. 3




Above figures show right hand tools.

### Spare Parts




### Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Max. Cutt-Off Dia (mm) | Fig. | Applicable Insert | Screw / Cap Screw | N·m | Plug | Wrench for Upper Surface | Wrench for Lower Surface |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | HBH | LH | LH2 | WF2 | CW | CDX | | | | | | | | |
| GNDL R/L 1212 JX 212.5 J | ❍ | ❍ | 12 | 12 | 120 | (12) | 12 | 2,0 | 22,0 | 22,3 | 0 | 2,0 | 12,5 | 25 | 1 | GCM □20○○-□□ | BFTX0415T8R | 1,5 | XP02 | LT08-06 | |
| GNDL R/L 1212 JX 312.5 J | ❍ | ❍ | 12 | 12 | 120 | (12) | 12 | 2,0 | 22,0 | 22,3 | 0 | 3,0 | 12,5 | 25 | | GC□ □30○○-□□ | | | | | |
| GNDL R/L 1616 JX 216 J | ❍ | ❍ | 16 | 16 | 120 | (16) | 16 | – | 32,0 | – | 0 | 2,0 | 16,0 | 32 | 2 | GC□ □20○○-□□ | CP-M5-20-1 | 5,0 | XP02 | LH040 | LH025 |
| GNDL R/L 1616 JX 316 J | ❍ | ❍ | 16 | 16 | 120 | (16) | 16 | – | 32,0 | – | 0 | 3,0 | 16,0 | 32 | | GC□ □30○○-□□ | | | | | |
| GNDL R/L 2012 JX 221 J | ❍ | ❍ | 20 | 12 | 120 | (12) | 20 | – | 30,5 | – | 0 | 2,0 | 21,0 | 42 | 3 | GCM □20○○-□□ | BFTX0414 | 3,0 | XP02 | LT15-10 | |
| GNDL R/L 2012 JX 321 J | ❍ | ❍ | 20 | 12 | 120 | (12) | 20 | – | 30,5 | – | 0 | 3,0 | 21,0 | 42 | | GCM □30○○-□□ | | | | | |

Select holders and inserts with the same grooving width (CW).

### Parts (Hoses and Connectors)

See page 21



● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

## Inserts for GNDM-J / GNDL-J (Small Tools)

Coated Carbide | Cermet | Carbide

Fig. 1





Fig. 2





Fig. 3





Fig. 4




### ● Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ● | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |

### ● External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |

### ● Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |

### ● Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |

### ● Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| GCM N125005 GF | – | – | – | – | – | ● | – | 1,25 | ±0,03 | 0,05 | 17,4 | 3,2 | 1 |
| N150005 GF | – | – | – | – | – | ● | – | 1,5 | ±0,03 | 0,05 | 17,4 | 3,7 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |

### ● Cut-Off Machining (Handed Edge)

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | AC1030U | PSI | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM R2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 4 |
| L2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | |
| GCM R3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| L3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| GCM R4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| L4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| GCM R20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | 4 |
| L20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| GCM R20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |


GCM R: Right hand GCM L: Left hand

Combine the insert with a holder such that the width of cut (CW) matches.

## Parts (Hoses and Connectors)

### ● Parts Hoses

Fig. 1




| Cat. No. | Stock | L (mm) | Screw Standard | Screw Standard | Fig. |
|---|---|---|---|---|---|
| J-HOSE-G1/8-G1/8-200-E | ● | 200 | G1/8 | G1/8 | 1 |
| J-HOSE-G1/8-G1/8-300-E | ● | 300 | G1/8 | G1/8 | 1 |

Hoses are sold separately.

### ● Parts (Connector) on Holder Side

Fig. 1






Fig. 2




| Cat. No. | Stock | Screw Standard | Screw Standard | Fig. |
|---|---|---|---|---|
| J-G1/8-R1/8-00 | ❍ | G1/8 | R1/8 | 1 |
| J-G1/8-R1/8-90 | ❍ | G1/8 | R1/8 | 2 |

Connectors are sold separately.

### ● Parts (Connector) on Machine Side

Fig. 1





Fig. 2






Fig. 3





| Cat. No. | Stock | Screw Standard | Screw Standard | Fig. |
|---|---|---|---|---|
| J-G1/8-G1/8-00-E | ● | G1/8 | G1/8 | 1 |
| J-G1/8-G1/8F-90-E | ● | G1/8 | G1/8 | 2 |
| J-G1/8-G1/8-90-E | ● | G1/8 | G1/8 | 3 |


Connectors are sold separately.

# GNDS Type

## External Multi-Purpose Shallow Grooves Type (Grooving, Turning, Profiling)




External




Use the multi-purpose profiling insert for turning (wide grooves).

Above figures show right hand tools.

## Spare Parts




## Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | CW | CDX | | | | |
| GNDS R/L 2020 K 206 | ● | ● | 20 | 20 | 125 | 20 | 20 | 30 | 2,0 | 6 | GCM □20○○-□□ | BX0520 | 5,0 | LH040 |
| GNDS R/L 2020 K 306 | ● | ● | 20 | 20 | 125 | 20 | 20 | 30 | 3,0 | 6 | GCM □30○○-□□ | | | |
| GNDS R/L 2020 K 410 | ● | ● | 20 | 20 | 125 | 20 | 20 | 34 | 4,0 | 10 | GCM □40○○-□□ | | | |
| GNDS R/L 2020 K 510 | ● | ● | 20 | 20 | 125 | 20 | 20 | 34 | 5,0 | 10 | GCM N50○○-□□ | | | |
| GNDS R/L 2020 K 610 | ● | ● | 20 | 20 | 125 | 20 | 20 | 34 | 6,0 | 10 | GCM N60○○-□□ | | | |
| GNDS R/L 2525 M 206 | ● | ● | 25 | 25 | 150 | 25 | 25 | 30 | 2,0 | 6 | GCM □20○○-□□ | | | |
| GNDS R/L 2525 M 306 | ● | ● | 25 | 25 | 150 | 25 | 25 | 30 | 3,0 | 6 | GCM □30○○-□□ | | | |
| GNDS R/L 2525 M 410 | ● | ● | 25 | 25 | 150 | 25 | 25 | 34 | 4,0 | 10 | GCM □40○○-□□ | | | |
| GNDS R/L 2525 M 510 | ● | ● | 25 | 25 | 150 | 25 | 25 | 34 | 5,0 | 10 | GCM N50○○-□□ | | | |
| GNDS R/L 2525 M 610 | ● | ● | 25 | 25 | 150 | 25 | 25 | 34 | 6,0 | 10 | GCM N60○○-□□ | | | |

Select holders and inserts with the same grooving width (CW).





● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

# Grooving Tool Holders
# GNDS Type

## Inserts for GNDS

Coated Carbide | Cermet | Carbide

Fig. 1





Fig. 2





Fig. 3





Fig. 4




### ● Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |

### ● External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |
| N4020 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 4,0 | ±0,03 | 2,0 | 26,4 | 4,0 | |
| N5025 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 27,2 | 4,1 | |
| N6030 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 27,5 | 4,5 | |

### ● Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

### ● Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | | | | | | | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | | | | | | | | | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | | | | | | | | | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |
| N4004 GA | ❍ | | | | | | | | | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | | | | | | | | | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | | | | | | | | | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

### ● Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |

### ● Cut-Off Machining (Handed Edge)

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | AC1030U | | PSI | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM R2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 4 |
| L2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | |
| GCM R3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| L3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| GCM R4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| L4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| GCM R20003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | 4 |
| L20003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| GCM R20003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |


GCM R: Right hand GCM L: Left hand

Combine the insert with a holder such that the width of cut (CW) matches.

# GNDM / GNDMS Type

## External Multi-Purpose Type (Grooving, Turning, Profiling)


**GNDM**
External Grooving



External

Cut-Off

Use for multi-purpose or profiling insert for turning (wide grooves).




Above figures show right hand tools.

### Spare Parts





### Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Max. Cutt-Off Dia (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | CW | CDX | | | | | |
| GNDM R/L 2020 K 1.2510 | ● | ● | 20 | 20 | 125 | 20 | 20 | 34,0 | 1,25 | 10 | 20 | GCM N125005 GF | BX0520 | 5,0 | LH040 |
| GNDM R/L 2020 K 1.510 | ● | ● | 20 | 20 | 125 | 20 | 20 | 34,0 | 1,50 | 10 | 20 | GCM N150005 GF | | | |
| GNDM R/L 2020 K 210 | ● | ● | 20 | 20 | 125 | 20 | 20 | 33,6 | 2,00 | 10 | 20 | GCM □20○○-□□ | | | |
| GNDM R/L 2020 K 312 | ● | ● | 20 | 20 | 125 | 20 | 20 | 36,6 | 3,00 | 12 | 24 | GCM □30○○-□□ | | | |
| GNDM R/L 2020 K 418 | ● | ● | 20 | 20 | 125 | 20 | 20 | 45,0 | 4,00 | 18 | 36 | GCM □40○○-□□ | | | |
| GNDM R/L 2020 K 518 | ● | ● | 20 | 20 | 125 | 20 | 20 | 45,0 | 5,00 | 18 | 36 | GCM N50○○-□□ | | | |
| GNDM R/L 2020 K 618 | ● | ● | 20 | 20 | 125 | 20 | 20 | 45,0 | 6,00 | 18 | 36 | GCM N60○○-□□ | | | |
| GNDM R/L 2525 M 1.2510 | ● | ● | 25 | 25 | 150 | 25 | 25 | 36,0 | 1,25 | 10 | 20 | GCM N125005 GF | | | |
| GNDM R/L 2525 M 1.510 | ● | ● | 25 | 25 | 150 | 25 | 25 | 36,0 | 1,50 | 10 | 20 | GCM N150005 GF | | | |
| GNDM R/L 2525 M 210 | ● | ● | 25 | 25 | 150 | 25 | 25 | 33,6 | 2,00 | 10 | 20 | GCM N20○○-□□ | | | |
| GNDM R/L 2525 M 312 | ● | ● | 25 | 25 | 150 | 25 | 25 | 36,6 | 3,00 | 12 | 24 | GCM □30○○-□□ | | | |
| GNDM R/L 2525 M 418 | ● | ● | 25 | 25 | 150 | 25 | 25 | 45,0 | 4,00 | 18 | 36 | GCM □40○○-□□ | | | |
| GNDM R/L 2525 M 518 | ● | ● | 25 | 25 | 150 | 25 | 25 | 45,0 | 5,00 | 18 | 36 | GCM N50○○-□□ | | | |
| GNDM R/L 2525 M 618 | ● | ● | 25 | 25 | 150 | 25 | 25 | 45,0 | 6,00 | 18 | 36 | GCM N60○○-□□ | | | |
| GNDM R/L 3225 P 312 | | | 32 | 25 | 170 | 25 | 32 | 36,6 | 3,00 | 12 | 24 | GCM □30○○-□□ | | | |
| GNDM R/L 3225 P 418 | | | 32 | 25 | 170 | 25 | 32 | 45,0 | 4,00 | 18 | 36 | GCM □40○○-□□ | | | |
| GNDM R/L 3225 P 518 | | | 32 | 25 | 170 | 25 | 32 | 45,0 | 5,00 | 18 | 36 | GCM N50○○-□□ | | | |
| GNDM R/L 3225 P 618 | | | 32 | 25 | 170 | 25 | 32 | 45,0 | 6,00 | 18 | 36 | GCM N60○○-□□ | | | |
| GNDM R/L 3225 P 718 | | | 32 | 25 | 170 | 25 | 32 | 50,0 | 7,00 | 18 | 36 | GCM N70○○-□□ | BX0620 | 6,0 | LH050 |
| GNDM R/L 3225 P 818 | | | 32 | 25 | 170 | 25 | 32 | 50,0 | 8,00 | 18 | 36 | GCM N80○○-□□ | | | |
| GNDM R/L 3232 P 312 | ● | ● | 32 | 32 | 170 | 32 | 32 | 36,6 | 3,00 | 12 | 24 | GCM □30○○-□□ | BX0620 | 6,0 | LH050 |
| GNDM R/L 3232 P 418 | ● | ● | 32 | 32 | 170 | 32 | 32 | 45,0 | 4,00 | 18 | 36 | GCM □40○○-□□ | | | |
| GNDM R/L 3232 P 518 | ● | ● | 32 | 32 | 170 | 32 | 32 | 45,0 | 5,00 | 18 | 36 | GCM N50○○-□□ | | | |
| GNDM R/L 3232 P 618 | ● | ● | 32 | 32 | 170 | 32 | 32 | 45,0 | 6,00 | 18 | 36 | GCM N60○○-□□ | | | |
| GNDM R/L 3232 P 718 | ● | ● | 32 | 32 | 170 | 32 | 32 | 50,0 | 7,00 | 18 | 36 | GCM N70○○-□□ | | | |
| GNDM R/L 3232 P 818 | ● | ● | 32 | 32 | 170 | 32 | 32 | 50,0 | 8,00 | 18 | 36 | GCM N80○○-□□ | | | |

Select holders and inserts with the same grooving width (CW).


## External L-Styled (Side Cut) Multi-Purpose Type (Grooving, Turning, Profiling)

**GNDMS**
External Grooving



External

Use for multi-purpose or profiling insert for turning (wide grooves).




Above figures show right hand tools.

### Spare Parts




### Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | CW | CDX | | | | |
| GNDMS R/L 2020 K 310 | ● | ❍ | 20 | 20 | 125 | 32 | 20 | 25 | 3,0 | 10 | GCM □30○○-□□ | BX0520 | 5,0 | LH040 |
| GNDMS R/L 2020 K 412 | ● | ● | 20 | 20 | 125 | 34 | 20 | 25 | 4,0 | 12 | GCM □40○○-□□ | | | |
| GNDMS R/L 2020 K 512 | ● | ❍ | 20 | 20 | 125 | 34 | 20 | 25 | 5,0 | 12 | GCM N50○○-□□ | | | |
| GNDMS R/L 2525 M 312 | ● | ● | 25 | 25 | 150 | 39 | 25 | 25 | 3,0 | 12 | GCM □30○○-□□ | | | |
| GNDMS R/L 2525 M 414 | ● | ● | 25 | 25 | 150 | 41 | 25 | 25 | 4,0 | 14 | GCM □40○○-□□ | | | |
| GNDMS R/L 2525 M 514 | ● | ● | 25 | 25 | 150 | 41 | 25 | 25 | 5,0 | 14 | GCM N50○○-□□ | | | |
| GNDMS R/L 2525 M 614 | ● | ● | 25 | 25 | 150 | 41 | 25 | 25 | 6,0 | 14 | GCM N60○○-□□ | | | |

Select holders and inserts with the same grooving width (CW).





● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

## Inserts for GNDM / GNDMS

Coated Carbide  Cermet  Carbide

Fig. 1





Fig. 2





Fig. 3






Fig. 4




### Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| N7004 MG | ● | ● | | ❍ | ● | ● | | ❍ | – | 7,0 | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N7008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,04 | 0,8 | 28,8 | 5,5 | |
| N8004 MG | ● | ● | | ❍ | ● | ● | | ❍ | – | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| N8008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,04 | 0,8 | 28,8 | 6,0 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| N7004 ML | ● | ● | ● | ❍ | ● | ● | ❍ | ● | – | 7,0 | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N7008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,04 | 0,8 | 28,8 | 5,5 | |
| N8004 ML | ● | ● | ● | ❍ | ● | ● | ❍ | ● | – | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| N8008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,04 | 0,8 | 28,8 | 6,0 | |

### External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |
| N4020 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 4,0 | ±0,03 | 2,0 | 26,4 | 4,0 | |
| N5025 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 27,2 | 4,1 | |
| N6030 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 27,5 | 4,5 | |
| N7035 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 7,0 | ±0,04 | 3,5 | 29,1 | 5,5 | |
| N8040 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 8,0 | ±0,04 | 4,0 | 29,3 | 6,0 | |

### Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

### Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |
| N4004 GA | ❍ | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

### Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N7004 GG | ● | ❍ | ● | ● | ❍ | ● | – | | | 7,0 | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N8004 GG | ● | ● | ● | ● | ❍ | ● | – | | | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N7004 GL | ● | ❍ | ● | ● | ❍ | ● | – | | | 7,0 | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N8004 GL | ● | ❍ | ● | ● | ❍ | ● | – | | | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| GCM N125005 GF | – | – | – | – | – | ● | – | | | 1,25 | ±0,03 | 0,05 | 17,4 | 3,2 | 1 |
| N150005 GF | – | – | – | – | – | ● | – | | | 1,5 | ±0,03 | 0,05 | 17,4 | 3,7 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N7002 GF | ● | ● | ● | ● | ❍ | ● | – | | | 7,0 | ±0,04 | 0,2 | 28,8 | 5,5 | |
| N7004 GF | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N8002 GF | ● | ● | ● | ● | ❍ | ● | – | | | 8,0 | ±0,04 | 0,2 | 28,8 | 6,0 | |
| N8004 GF | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,04 | 0,4 | 28,8 | 6,0 | |

### Cut-Off Machining (Handed Edge)

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | AC1030U | PSI | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM R2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 4 |
| L2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | |
| GCM R3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| L3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| GCM R4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| L4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| GCM R20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| GCM R20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |


GCM R: Right hand  GCM L: Left hand

Combine the insert with a holder such that the width of cut (CW) matches.

# GNDM-JE Type



## External Multi-Purpose Type (Grooving, Turning, Profiling)





External

Internal Coolant

Cut-Off

Use for multi-purpose or profiling insert for turning (wide grooves).




Above figures show right hand tools.


## Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Max. Cutt-Off Dia (mm) | Applicable Insert | Cap Screw | N·m | Plug and Sealing | Grub Screw* | Span-ner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | CW | CDX | | | | | | | |
| GNDM R/L 2020 X 210 JE | ● | ● | 20 | 20 | 100 | 20 | 20 | 33,6 | 2,00 | 10 | 20 | GC□ □20○○-□□ | BX0520 | 6,0 | XP02-E | BT0505-E | LH040 |
| GNDM R/L 2020 X 312 JE | ● | ● | 20 | 20 | 100 | 20 | 20 | 36,6 | 3,00 | 12 | 24 | GC□ □30○○-□□ | | | | | |
| GNDM R/L 2020 X 418 JE | ● | ● | 20 | 20 | 110 | 20 | 20 | 45,0 | 4,00 | 18 | 36 | GC□ □40○○-□□ | | | | | |
| GNDM R/L 2020 X 518 JE | ● | ● | 20 | 20 | 110 | 20 | 20 | 45,0 | 5,00 | 18 | 36 | GC□ N50○○-□□ | | | | | |
| GNDM R/L 2020 X 618 JE | ● | ● | 20 | 20 | 110 | 20 | 20 | 45,0 | 6,00 | 18 | 36 | GC□ N60○○-□□ | | | | | |
| GNDM R/L 2525 X 210 JE | ● | ● | 25 | 25 | 100 | 25 | 25 | 33,6 | 2,00 | 10 | 20 | GC□ □20○○-□□ | | | | | |
| GNDM R/L 2525 X 312 JE | ● | ● | 25 | 25 | 100 | 25 | 25 | 36,6 | 3,00 | 12 | 24 | GC□ □30○○-□□ | | | | | |
| GNDM R/L 2525 X 418 JE | ● | ● | 25 | 25 | 110 | 25 | 25 | 45,0 | 4,00 | 18 | 36 | GC□ □40○○-□□ | | | | | |
| GNDM R/L 2525 X 518 JE | ● | ● | 25 | 25 | 110 | 25 | 25 | 45,0 | 5,00 | 18 | 36 | GC□ N50○○-□□ | | | | | |
| GNDM R/L 2525 X 618 JE | ● | ● | 25 | 25 | 110 | 25 | 25 | 45,0 | 6,00 | 18 | 36 | GC□ N60○○-□□ | | | | | |

Select holders and inserts with the same grooving width (CW).


*Grub screws are sold separately (M5x5)

## Spare Parts



## Parts (Hose)

Fig. 1




| Cat. No. | Stock | L (mm) | Srew Stan-dard | Srew Stan-dard | Fig. |
|---|---|---|---|---|---|
| J-HOSE-G1/8-G1/8-200-E | ● | 200 | G1/8 | G1/8 | 1 |
| J-HOSE-G1/8-G1/8-300-E | ● | 300 | G1/8 | G1/8 | 1 |

Hoses are sold separately.

## Parts (Connector)

Fig. 1





Fig. 2






Fig. 3




| Cat. No. | Stock | Srew Standard | Srew Standard | Fig. |
|---|---|---|---|---|
| J-G1/8-G1/8-00-E | ● | G1/8 | G1/8 | 1 |
| J-G1/8-G1/8F-90-E | ● | G1/8 | G1/8 | 2 |
| J-G1/8-G1/8-90-E | ● | G1/8 | G1/8 | 3 |

Connectors are sold separately.





● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

# Grooving Tool Holders
# GNDM-JE Type

## Inserts for GNDM-JE

Coated Carbide | Cermet | Carbide

Fig. 1





Fig. 2





Fig. 3






Fig. 4




### ● Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |

### ● External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |
| N4020 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 4,0 | ±0,03 | 2,0 | 26,4 | 4,0 | |
| N5025 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 27,2 | 4,1 | |
| N6030 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 27,5 | 4,5 | |

### ● Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

### ● Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | | | | | | | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | | | | | | | | | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | | | | | | | | | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |
| N4004 GA | ❍ | | | | | | | | | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | | | | | | | | | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | | | | | | | | | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

### ● Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |

### ● Cut-Off Machining (Handed Edge)

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | AC1030U | | PSI | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM R2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 4 |
| L2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | |
| GCM R3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| L3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| GCM R4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| L4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| GCM R20003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | 4 |
| L20003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| GCM R20003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |


GCM R: Right hand GCM L: Left hand

Combine the insert with a holder such that the width of cut (CW) matches.

# GNDL / GNDLS Type


## External Deep Grooving and Cut-Off

**GNDL**
External Grooving



External

Cut-Off




Above figures show right hand tools.

### Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Max. Cutt-Off Dia (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | CW | CDX | | | | | |
| GNDL R/L 2020 K 1.2516 | ● | ● | 20 | 20 | 125 | 20 | 20 | 38,0 | 1,25 | 16 | 32 | GCM N125005 GF | BX0520 | 5,0 | LH040 |
| GNDL R/L 2020 K 1.516 | ● | ● | 20 | 20 | 125 | 20 | 20 | 38,0 | 1,50 | 16 | 32 | GCM N150005 GF | | | |
| GNDL R/L 2020 K 220 | ● | ● | 20 | 20 | 125 | 20 | 20 | 44,5 | 2,00 | 20 | 40 | GCM □20○○-□□ | | | |
| GNDL R/L 2020 K 320 | ● | ● | 20 | 20 | 125 | 20 | 20 | 44,5 | 3,00 | 20(18) | 40 | GCM □30○○-□□ | | | |
| GNDL R/L 2020 K 425 | ● | ● | 20 | 20 | 125 | 20 | 20 | 50,0 | 4,00 | 25(23) | 50 | GCM □40○○-□□ | | | |
| GNDL R/L 2020 K 525 | ● | ● | 20 | 20 | 125 | 20 | 20 | 50,0 | 5,00 | 25(23) | 50 | GCM N50○○-□□ | | | |
| GNDL R/L 2020 K 625 | ● | ● | 20 | 20 | 125 | 20 | 20 | 50,0 | 6,00 | 25(23) | 50 | GCM N60○○-□□ | | | |
| GNDL R/L 2525 M 1.2516 | ● | ● | 25 | 25 | 150 | 25 | 25 | 40,0 | 1,25 | 16 | 32 | GCM N125005 GF | | | |
| GNDL R/L 2525 M 1.516 | ● | ● | 25 | 25 | 150 | 25 | 25 | 40,0 | 1,50 | 16 | 32 | GCM N150005 GF | | | |
| GNDL R/L 2525 M 220 | ● | ● | 25 | 25 | 150 | 25 | 25 | 44,5 | 2,00 | 20 | 40 | GCM □20○○-□□ | | | |
| GNDL R/L 2525 M 320 | ● | ● | 25 | 25 | 150 | 25 | 25 | 44,5 | 3,00 | 20(18) | 40 | GCM □30○○-□□ | | | |
| GNDL R/L 2525 M 425 | ● | ● | 25 | 25 | 150 | 25 | 25 | 50,0 | 4,00 | 25(23) | 50 | GCM □40○○-□□ | | | |
| GNDL R/L 2525 M 525 | ● | ● | 25 | 25 | 150 | 25 | 25 | 50,0 | 5,00 | 25(23) | 50 | GCM N50○○-□□ | | | |
| GNDL R/L 2525 M 625 | ● | ● | 25 | 25 | 150 | 25 | 25 | 50,0 | 6,00 | 25(23) | 50 | GCM N60○○-□□ | | | |
| GNDL R/L 3225 P 320 | | | 32 | 25 | 170 | 25 | 32 | 44,5 | 3,00 | 20(18) | 40 | GCM □30○○-□□ | | | |
| GNDL R/L 3225 P 425 | | | 32 | 25 | 170 | 25 | 32 | 50,0 | 4,00 | 25(23) | 50 | GCM □40○○-□□ | | | |
| GNDL R/L 3225 P 525 | | | 32 | 25 | 170 | 25 | 32 | 50,0 | 5,00 | 25(23) | 50 | GCM N50○○-□□ | | | |
| GNDL R/L 3225 P 625 | | | 32 | 25 | 170 | 25 | 32 | 50,0 | 6,00 | 25(23) | 50 | GCM N60○○-□□ | | | |
| GNDL R/L 3225 P 725 | | | 32 | 25 | 170 | 25 | 32 | 50,0 | 7,00 | 25(23) | 50 | GCM N70○○-□□ | BX0520 | 6,0 | LH050 |
| GNDL R/L 3225 P 825 | | | 32 | 25 | 170 | 25 | 32 | 50,0 | 8,00 | 25(23) | 50 | GCM N80○○-□□ | | | |
| GNDL R/L 3232 P 320 | ● | ● | 32 | 32 | 170 | 32 | 32 | 44,5 | 3,00 | 20(18) | 40 | GCM □30○○-□□ | BX0620 | 6,0 | LH050 |
| GNDL R/L 3232 P 425 | ● | ● | 32 | 32 | 170 | 32 | 32 | 50,0 | 4,00 | 25(23) | 50 | GCM □40○○-□□ | | | |
| GNDL R/L 3232 P 525 | ● | ● | 32 | 32 | 170 | 32 | 32 | 50,0 | 5,00 | 25(23) | 50 | GCM N50○○-□□ | | | |
| GNDL R/L 3232 P 625 | ● | ● | 32 | 32 | 170 | 32 | 32 | 50,0 | 6,00 | 25(23) | 50 | GCM N60○○-□□ | | | |
| GNDL R/L 3232 P 725 | ● | ● | 32 | 32 | 170 | 32 | 32 | 50,0 | 7,00 | 25(23) | 50 | GCM N70○○-□□ | | | |
| GNDL R/L 3232 P 825 | ● | ● | 32 | 32 | 170 | 32 | 32 | 50,0 | 8,00 | 25(23) | 50 | GCM N80○○-□□ | | | |


Select holders and inserts with the same grooving width (CW). Dimensions in parentheses are for applications that use copying inserts (RG type breakers).

### Spare Parts





## External L-Styled (Side Cut) Grooving

**GNDLS**
External Grooving



External




Above figures show right hand tools.

### Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | CW | CDX | | | | |
| GNDLS R/L 2020 K 216 | ● | ● | 20 | 20 | 125 | 38 | 20 | 25 | 2,0 | 16 | GCM □20○○-□□ | BX0520 | 5,0 | LH040 |
| GNDLS R/L 2020 K 316 | ❍ | ● | 20 | 20 | 125 | 38 | 20 | 25 | 3,0 | 16 | GCM □30○○-□□ | | | |
| GNDLS R/L 2525 M 218 | ● | ● | 25 | 25 | 150 | 45 | 25 | 25 | 2,0 | 18 | GCM □20○○-□□ | | | |
| GNDLS R/L 2525 M 318 | ● | ● | 25 | 25 | 150 | 45 | 25 | 25 | 3,0 | 18 | GCM □30○○-□□ | | | |
| GNDLS R/L 2525 M 423 | ● | ● | 25 | 25 | 150 | 50 | 25 | 25 | 4,0 | 23 | GCM □40○○-□□ | | | |
| GNDLS R/L 2525 M 523 | ❍ | ❍ | 25 | 25 | 150 | 50 | 25 | 25 | 5,0 | 23 | GCM N50○○-□□ | | | |
| GNDLS R/L 2525 M 623 | ● | ❍ | 25 | 25 | 150 | 50 | 25 | 25 | 6,0 | 23 | GCM N60○○-□□ | | | |

Select holders and inserts with the same grooving width (CW).

### Spare Parts






● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

## Inserts for GNDL / GNDLS

Coated Carbide  Cermet  Carbide

Fig. 1





Fig. 2





Fig. 3






Fig. 4




### Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| N7004 MG | ● | ● | | ❍ | ● | ● | | ❍ | – | 7,0 | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N7008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,04 | 0,8 | 28,8 | 5,5 | |
| N8004 MG | ● | ● | | ❍ | ● | ● | | ❍ | – | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| N8008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,04 | 0,8 | 28,8 | 6,0 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| N7004 ML | ● | ● | ● | ❍ | ● | ● | ❍ | ● | – | 7,0 | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N7008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,04 | 0,8 | 28,8 | 5,5 | |
| N8004 ML | ● | ● | ● | ❍ | ● | ● | ❍ | ● | – | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| N8008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,04 | 0,8 | 28,8 | 6,0 | |

### External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |
| N4020 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 4,0 | ±0,03 | 2,0 | 26,4 | 4,0 | |
| N5025 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 27,2 | 4,1 | |
| N6030 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 27,5 | 4,5 | |
| N7035 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 7,0 | ±0,04 | 3,5 | 29,1 | 5,5 | |
| N8040 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 8,0 | ±0,04 | 4,0 | 29,3 | 6,0 | |

### Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

### Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |
| N4004 GA | ❍ | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

Select holders and inserts with the same grooving width (CW).

### Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N7004 GG | ● | ❍ | ● | ● | ❍ | ● | – | | | 7,0 | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N8004 GG | ● | ● | ● | ● | ❍ | ● | – | | | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N7004 GL | ● | ❍ | ● | ● | ❍ | ● | – | | | 7,0 | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N8004 GL | ● | ❍ | ● | ● | ❍ | ● | – | | | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| GCM N125005 GF | – | – | – | – | – | ● | – | | | 1,25 | ±0,03 | 0,05 | 17,4 | 3,2 | 1 |
| N150005 GF | – | – | – | – | – | ● | – | | | 1,5 | ±0,03 | 0,05 | 17,4 | 3,7 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N7002 GF | ● | ● | ● | ● | ❍ | ● | – | | | 7,0 | ±0,04 | 0,2 | 28,8 | 5,5 | |
| N7004 GF | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,04 | 0,4 | 28,8 | 5,5 | |
| N8002 GF | ● | ● | ● | ● | ❍ | ● | – | | | 8,0 | ±0,04 | 0,2 | 28,8 | 6,0 | |
| N8004 GF | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,04 | 0,4 | 28,8 | 6,0 | |

### Cut-Off Machining (Handed Edge)

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | AC1030U | PSI | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM R2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 4 |
| L2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | |
| GCM R3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| L3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| GCM R4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| L4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| GCM R20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| GCM R20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |


GCM R: Right hand  GCM L: Left hand

Combine the insert with a holder such that the width of cut (CW) matches.

# GNDL-JE Type

## Holder with Internal Coolant


## External Deep Grooving and Cut-Off




External

Internal Coolant

Cut-Off




Above figures show right hand tools.


## Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Grooving Width (mm) | Max. Groov. Depth (mm) | Max. Cutt-Off Dia (mm) | Applicable Insert | Cap Screw | N·m | Plug and Sealing | Grub Screw* | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | CW | CDX | | | | | | | |
| GNDL R/L 2020 X 220 JE | ● | ● | 20 | 20 | 110 | 20 | 20 | 44,5 | 2,00 | 20 | 40 | GC□ □20○○-□□ | BX0520 | 6,0 | XP02-E | BT0505-E | LH040 |
| GNDL R/L 2020 X 320 JE | ● | ● | 20 | 20 | 110 | 20 | 20 | 44,5 | 3,00 | 20 | 40 | GC□ □30○○-□□ | | | | | |
| GNDL R/L 2020 X 425 JE | ● | ● | 20 | 20 | 115 | 20 | 20 | 50,0 | 4,00 | 25 | 50 | GC□ □40○○-□□ | | | | | |
| GNDL R/L 2020 X 525 JE | ● | ● | 20 | 20 | 115 | 20 | 20 | 50,0 | 5,00 | 25 | 50 | GC□ N50○○-□□ | | | | | |
| GNDL R/L 2020 X 625 JE | ● | ● | 20 | 20 | 115 | 20 | 20 | 50,0 | 6,00 | 25 | 50 | GC□ N60○○-□□ | | | | | |
| GNDL R/L 2525 X 220 JE | ● | ● | 25 | 25 | 110 | 25 | 25 | 44,5 | 2,00 | 20 | 40 | GC□ □20○○-□□ | | | | | |
| GNDL R/L 2525 X 320 JE | ● | ● | 25 | 25 | 110 | 25 | 25 | 44,5 | 3,00 | 20 | 40 | GC□ □30○○-□□ | | | | | |
| GNDL R/L 2525 X 425 JE | ● | ● | 25 | 25 | 115 | 25 | 25 | 50,0 | 4,00 | 25 | 50 | GC□ □40○○-□□ | | | | | |
| GNDL R/L 2525 X 525 JE | ● | ● | 25 | 25 | 115 | 25 | 25 | 50,0 | 5,00 | 25 | 50 | GC□ N50○○-□□ | | | | | |
| GNDL R/L 2525 X 625 JE | ● | ● | 25 | 25 | 115 | 25 | 25 | 50,0 | 6,00 | 25 | 50 | GC□ N60○○-□□ | | | | | |

Select holders and inserts with the same grooving width (CW).


*Grub screws are sold separately (M5x5)

## Spare Parts



## Parts (Hose)

Fig. 1




| Cat. No. | Stock | L (mm) | Srew Standard | Srew Standard | Fig. |
|---|---|---|---|---|---|
| J-HOSE-G1/8-G1/8-200-E | ● | 200 | G1/8 | G1/8 | 1 |
| J-HOSE-G1/8-G1/8-300-E | ● | 300 | G1/8 | G1/8 | 1 |

Hoses are sold separately.

## Parts (Connector)

Fig. 1





Fig. 2






Fig. 3




| Cat. No. | Stock | Srew Standard | Srew Standard | Fig. |
|---|---|---|---|---|
| J-G1/8-G1/8-00-E | ● | G1/8 | G1/8 | 1 |
| J-G1/8-G1/8F-90-E | ● | G1/8 | G1/8 | 2 |
| J-G1/8-G1/8-90-E | ● | G1/8 | G1/8 | 3 |

Connectors are sold separately.





● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

## Inserts for GNDL-JE

Coated Carbide  Cermet  Carbide


Fig. 1




Fig. 2





Fig. 3



Fig. 4



### Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |

### External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |
| N4020 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 4,0 | ±0,03 | 2,0 | 26,4 | 4,0 | |
| N5025 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 27,2 | 4,1 | |
| N6030 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 27,5 | 4,5 | |

### Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

### Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | | | | | | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | | | | | | | | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | | | | | | | | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |
| N4004 GA | ❍ | | | | | | | | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | | | | | | | | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | | | | | | | | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

### Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | | | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | | | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | | | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | | | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | | | ±0,03 | 0,4 | 26,4 | 4,5 | |

### Cut-Off Machining (Handed Edge)

Dimensions (mm)


| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | AC1030U | | PSI | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM R2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 4 |
| L2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | |
| GCM R3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| L3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| GCM R4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| L4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| GCM R20003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | 4 |
| L20003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 10 | – | – | ● | ● | – | – | ● | | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| GCM R20003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 15 | – | – | ● | ● | – | – | ● | | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |

GCM R: Right hand  GCM L: Left hand

Combine the insert with a holder such that the width of cut (CW) matches.


# GNDN Type


## Necking










Above figures show right hand tools.

## Spare Parts





## Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | Min. Bore (mm) | Groov. Width (mm) | APMX | APMX2 | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | WF2 | DMIN | CW | | | | | | |
| GNDN R/L2020 K 215-020 | ❍ | ❍ | 20 | 20 | 125 | 23 | 20 | 30 | 3,0 | 20 | 2,0 | 1,5 | 0,64 | GCM N2010 RN | BX0520 | 5,0 | LH040 |
| GNDN R/L2020 K 320-020 | ❍ | ❍ | 20 | 20 | 125 | 23 | 20 | 30 | 3,0 | 20 | 3,0 | 2,0 | 0,79 | GCM N3015 RN | | | |
| GNDN R/L2020 K 430-030 | ❍ | ❍ | 20 | 20 | 125 | 24 | 20 | 32 | 4,0 | 30 | 4,0 | 3,0 | 1,29 | GCM N4020 RN | | | |
| GNDN R/L2020 K 535-030 | ❍ | ❍ | 20 | 20 | 125 | 25 | 20 | 35 | 5,0 | 30 | 5,0 | 3,5 | 1,44 | GCM N5025 RN | | | |
| GNDN R/L2020 K 640-030 | ❍ | ❍ | 20 | 20 | 125 | 25 | 20 | 35 | 5,0 | 30 | 6,0 | 4,0 | 1,59 | GCM N6030 RN | | | |
| GNDN R/L2525 M 215-020 | ❍ | ❍ | 25 | 25 | 150 | 28 | 25 | 30 | 3,0 | 20 | 2,0 | 1,5 | 0,64 | GCM N2010 RN | BX0520 | 5,0 | LH040 |
| GNDN R/L2525 M 320-020 | ❍ | ❍ | 25 | 25 | 150 | 28 | 25 | 30 | 3,0 | 20 | 3,0 | 2,0 | 0,79 | GCM N3015 RN | | | |
| GNDN R/L2525 M 430-030 | ❍ | ❍ | 25 | 25 | 150 | 29 | 25 | 32 | 4,0 | 30 | 4,0 | 3,0 | 1,29 | GCM N4020 RN | | | |
| GNDN R/L2525 M 535-030 | ❍ | ❍ | 25 | 25 | 150 | 30 | 25 | 35 | 5,0 | 30 | 5,0 | 3,5 | 1,44 | GCM N5025 RN | | | |
| GNDN R/L2525 M 640-030 | ❍ | ❍ | 25 | 25 | 150 | 30 | 25 | 35 | 5,0 | 30 | 6,0 | 4,0 | 1,59 | GCM N6030 RN | | | |

Select holders and inserts with the same grooving width (CW).





● = Euro stock
○ = Japan stock


– Not available

N·m Recommended Tightening Torque (N·m)

## ■ Inserts for GNDN

Coated Carbide  Cermet

Fig. 2




### ● Profiling / Radius Grooving / Necking

Dimensions (mm)


| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tole-rance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

Select holders and inserts with the same grooving width (CW).


# GNDF Type


## Face Grooving

**GNDF**
Face Grooving



Face




Work diameters in the stock indicate external diameters of face grooving.

Use for multi-purpose or profiling insert for turning (wide grooves).

Above figures show right hand tools.

## Holders

## Spare Parts

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Work Dia. (mm) | Groov. Width (mm) | Max. Cut-off Dia. (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | DC | CW | CDX | | | | |
| GNDF R/L 2020 K 312-035 | ● | ● | 20 | 20 | 125 | 20 | 20 | 35,6 | 35–45 | 3,0 | 12 | GCM N30OO-□□ | BX0520 | 5,0 | LH040 |
| GNDF R/L 2020 K 312-040 | ● | ● | 20 | 20 | 125 | 20 | 20 | 35,6 | 40–55 | 3,0 | 12 | | | | |
| GNDF R/L 2020 K 318-050 | ● | ● | 20 | 20 | 125 | 20 | 20 | 41,6 | 50–70 | 3,0 | 18 | | | | |
| GNDF R/L 2020 K 318-065 | ● | ● | 20 | 20 | 125 | 20 | 20 | 41,6 | 65–100 | 3,0 | 18 | | | | |
| GNDF R/L 2020 K 318-090 | ● | ● | 20 | 20 | 125 | 20 | 20 | 41,6 | 90–150 | 3,0 | 18 | | | | |
| GNDF R/L 2020 K 318-140 | ● | ● | 20 | 20 | 125 | 20 | 20 | 41,6 | 140–200 | 3,0 | 18 | | | | |
| GNDF R/L 2020 K 318-180 | ● | ● | 20 | 20 | 125 | 20 | 20 | 41,6 | 180–300 | 3,0 | 18 | | | | |
| GNDF R/L 2020 K 418-040 | ● | ● | 20 | 20 | 125 | 20 | 20 | 41,6 | 40–55 | 4,0 | 18 | GCM N40OO-□□ | BX0520 | 5,0 | LH040 |
| GNDF R/L 2020 K 423-050 | ● | ● | 20 | 20 | 125 | 20 | 20 | 46,6 | 50–70 | 4,0 | 23 | | | | |
| GNDF R/L 2020 K 423-065 | ● | ● | 20 | 20 | 125 | 20 | 20 | 46,6 | 65–90 | 4,0 | 23 | | | | |
| GNDF R/L 2020 K 423-085 | ● | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 85–130 | 4,0 | 23 | | | | |
| GNDF R/L 2020 K 423-125 | ❍ | ● | 20 | 20 | 125 | 20 | 20 | 46,6 | 125–200 | 4,0 | 23 | | | | |
| GNDF R/L 2020 K 423-180 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 180–300 | 4,0 | 23 | | | | |
| GNDF R/L 2020 K 423-280 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 280–1000 | 4,0 | 23 | | | | |
| GNDF R/L 2020 K 523-050 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 50–70 | 5,0 | 23 | GCM N50OO-□□ | BX0520 | 5,0 | LH040 |
| GNDF R/L 2020 K 523-065 | ❍ | ● | 20 | 20 | 125 | 20 | 20 | 46,6 | 65–90 | 5,0 | 23 | | | | |
| GNDF R/L 2020 K 523-085 | ● | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 85–130 | 5,0 | 23 | | | | |
| GNDF R/L 2020 K 523-125 | ● | ● | 20 | 20 | 125 | 20 | 20 | 46,6 | 125–200 | 5,0 | 23 | | | | |
| GNDF R/L 2020 K 523-180 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 180–300 | 5,0 | 23 | | | | |
| GNDF R/L 2020 K 523-280 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 280–1000 | 5,0 | 23 | | | | |
| GNDF R/L 2020 K 623-050 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 50–75 | 6,0 | 23 | GCM N60OO-□□ | BX0520 | 5,0 | LH040 |
| GNDF R/L 2020 K 623-070 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 70–110 | 6,0 | 23 | | | | |
| GNDF R/L 2020 K 623-100 | ❍ | ● | 20 | 20 | 125 | 20 | 20 | 46,6 | 100–200 | 6,0 | 23 | | | | |
| GNDF R/L 2020 K 623-180 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 180–300 | 6,0 | 23 | | | | |
| GNDF R/L 2020 K 623-280 | ❍ | ❍ | 20 | 20 | 125 | 20 | 20 | 46,6 | 280–1000 | 6,0 | 23 | | | | |
| GNDF R/L 2525 M 312-035 | ● | ● | 25 | 25 | 150 | 25 | 25 | 35,6 | 35–45 | 3,0 | 12 | GCM N30OO-□□ | BX0520 | 5,0 | LH040 |
| GNDF R/L 2525 M 312-040 | ● | ● | 25 | 25 | 150 | 25 | 25 | 35,6 | 40–55 | 3,0 | 12 | | | | |
| GNDF R/L 2525 M 318-050 | ● | ● | 25 | 25 | 150 | 25 | 25 | 41,6 | 50–70 | 3,0 | 18 | | | | |
| GNDF R/L 2525 M 318-065 | ● | ● | 25 | 25 | 150 | 25 | 25 | 41,6 | 65–100 | 3,0 | 18 | | | | |
| GNDF R/L 2525 M 318-090 | ● | ● | 25 | 25 | 150 | 25 | 25 | 41,6 | 90–150 | 3,0 | 18 | | | | |
| GNDF R/L 2525 M 318-140 | ● | ● | 25 | 25 | 150 | 25 | 25 | 41,6 | 140–200 | 3,0 | 18 | | | | |
| GNDF R/L 2525 M 318-180 | ● | ● | 25 | 25 | 150 | 25 | 25 | 41,6 | 180–300 | 3,0 | 18 | | | | |
| GNDF R/L 2525 M 418-040 | ● | ● | 25 | 25 | 150 | 25 | 25 | 41,6 | 40–55 | 4,0 | 18 | GCM N40OO-□□ | BX0520 | 5,0 | LH040 |
| GNDF R/L 2525 M 423-050 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 50–70 | 4,0 | 23 | | | | |
| GNDF R/L 2525 M 423-065 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 65–90 | 4,0 | 23 | | | | |
| GNDF R/L 2525 M 423-085 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 85–130 | 4,0 | 23 | | | | |
| GNDF R/L 2525 M 423-125 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 125–200 | 4,0 | 23 | | | | |
| GNDF R/L 2525 M 423-180 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 180–300 | 4,0 | 23 | | | | |
| GNDF R/L 2525 M 423-280 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 280–1000 | 4,0 | 23 | | | | |
| GNDF R/L 2525 M 523-050 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 50–70 | 5,0 | 23 | GCM N50OO-□□ | BX0520 | 5,0 | LH040 |
| GNDF R/L 2525 M 523-065 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 65–90 | 5,0 | 23 | | | | |
| GNDF R/L 2525 M 523-085 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 85–130 | 5,0 | 23 | | | | |
| GNDF R/L 2525 M 523-125 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 125–200 | 5,0 | 23 | | | | |
| GNDF R/L 2525 M 523-180 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 180–300 | 5,0 | 23 | | | | |
| GNDF R/L 2525 M 523-280 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 280–1000 | 5,0 | 23 | | | | |
| GNDF R/L 2525 M 623-050 | ● | ❍ | 25 | 25 | 150 | 25 | 25 | 46,6 | 50–75 | 6,0 | 23 | GCM N60OO-□□ | BX0520 | 5,0 | LH040 |
| GNDF R/L 2525 M 623-070 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 70–110 | 6,0 | 23 | | | | |
| GNDF R/L 2525 M 623-100 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 100–200 | 6,0 | 23 | | | | |
| GNDF R/L 2525 M 623-180 | ❍ | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 180–300 | 6,0 | 23 | | | | |
| GNDF R/L 2525 M 623-280 | ● | ● | 25 | 25 | 150 | 25 | 25 | 46,6 | 280–1000 | 6,0 | 23 | | | | |

Select holders and inserts with the same grooving width (CW).





● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

# Grooving Tool Holders
# GNDF Type

## Inserts for GNDF

Coated Carbide | Cermet | Carbide

Fig. 1





Fig. 2






Fig. 3




### ● Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |

### ● Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |
| N4020 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 4,0 | ±0,03 | 2,0 | 26,4 | 4,0 | |
| N5025 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 27,2 | 4,1 | |
| N6030 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 27,5 | 4,5 | |

### ● Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|
| GCG N3002 GA | ❍ | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | 3 |
| N4004 GA | ❍ | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

### ● Grooving / Cut-Off Machining

Dimensions (mm)


| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 GG | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N3002 GL | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |

Combine the insert with a holder such that the width of cut (CW) matches.

# GNDFS Type


## Face Grooving L-Styled (Non-Adjustable Type)


**GNDFS**
Face Grooving



Face

Use the multi-purpose copying inserts for turning (wide grooves).




Above figures show right hand tools.

## ■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | Work Dia. (mm) | Min. Bore Ø Inner (mm) | Groov. Width (mm) | Max. Groov. Depth (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | LH | DC | | CW | CDX | | | | |
| GNDFS R/L2525M 620 070 | | | 25 | 25 | 150 | 47 | 25 | 25 | 70–100 | 58 | 6,0 | 20 | GC□ N60○○-□□ | BX0520 | 5,0 | LH040 |
| GNDFS R/L2525M 620 100 | | | 25 | 25 | 150 | 47 | 25 | 25 | 100–200 | 88 | 6,0 | 20 | | | | |
| GNDFS R/L2525M 620 180 | | | 25 | 25 | 150 | 47 | 25 | 25 | 180–300 | 168 | 6,0 | 20 | | | | |
| GNDFS R/L2525M 620 280 | | | 25 | 25 | 150 | 47 | 25 | 25 | 280–1000 | 268 | 6,0 | 20 | | | | |
| GNDFS R/L2525M 620 450 | | | 25 | 25 | 150 | 47 | 25 | 25 | >450 | 438 | 6,0 | 20 | | | | |
| GNDFS R/L3232P 620 070 | | | 32 | 32 | 170 | 54 | 32 | 25 | 70–100 | 58 | 6,0 | 20 | GC□ N60○○-□□ | BX0620 | 6,0 | LH050 |
| GNDFS R/L3232P 620 100 | | | 32 | 32 | 170 | 54 | 32 | 25 | 100–200 | 88 | 6,0 | 20 | | | | |
| GNDFS R/L3232P 620 180 | | | 32 | 32 | 170 | 54 | 32 | 25 | 180–300 | 168 | 6,0 | 20 | | | | |
| GNDFS R/L3232P 620 280 | | | 32 | 32 | 170 | 54 | 32 | 25 | 280–1000 | 268 | 6,0 | 20 | | | | |
| GNDFS R/L3232P 620 450 | | | 32 | 32 | 170 | 54 | 32 | 25 | >450 | 438 | 6,0 | 20 | | | | |
| GNDFS R/L2525M 820 070 | | | 25 | 25 | 150 | 47 | 25 | 30 | 70–100 | 54 | 8,0 | 20 | GCM N80○○-□□ | BX0620 | 6,0 | LH050 |
| GNDFS R/L2525M 820 100 | | | 25 | 25 | 150 | 47 | 25 | 30 | 100–200 | 84 | 8,0 | 20 | | | | |
| GNDFS R/L2525M 820 180 | | | 25 | 25 | 150 | 47 | 25 | 30 | 180–300 | 164 | 8,0 | 20 | | | | |
| GNDFS R/L2525M 820 280 | | | 25 | 25 | 150 | 47 | 25 | 30 | 280–1000 | 264 | 8,0 | 20 | | | | |
| GNDFS R/L2525M 820 450 | | | 25 | 25 | 150 | 47 | 25 | 30 | >450 | 434 | 8,0 | 20 | | | | |
| GNDFS R/L3232P 820 070 | | | 32 | 32 | 170 | 54 | 32 | 30 | 70–100 | 54 | 8,0 | 20 | GCM N80○○-□□ | BX0620 | 6,0 | LH050 |
| GNDFS R/L3232P 820 100 | | | 32 | 32 | 170 | 54 | 32 | 30 | 100–200 | 84 | 8,0 | 20 | | | | |
| GNDFS R/L3232P 820 180 | | | 32 | 32 | 170 | 54 | 32 | 30 | 180–300 | 164 | 8,0 | 20 | | | | |
| GNDFS R/L3232P 820 280 | | | 32 | 32 | 170 | 54 | 32 | 30 | 280–1000 | 264 | 8,0 | 20 | | | | |
| GNDFS R/L3232P 820 450 | | | 32 | 32 | 170 | 54 | 32 | 30 | >450 | 434 | 8,0 | 20 | | | | |

Select holders and inserts with the same grooving width (CW).

## ■ Spare Parts








● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

## Inserts for GNDFS

Coated Carbide  Cermet  Carbide

Fig. 1





Fig. 2






Fig. 3




### ● Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tole-rance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | 1 |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| N8004 MG | ● | ● | | ❍ | ● | ● | | ❍ | – | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| N8008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,04 | 0,8 | 28,8 | 6,0 | |
| GCM N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | 1 |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| N8004 ML | ● | ● | ● | ❍ | ● | ● | ❍ | ● | – | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| N8008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,04 | 0,8 | 28,8 | 6,0 | |

### ● Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tole-rance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N6030 RN | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | 2 |

### ● Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | CW Cutting Width | CW Tole-rance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|
| GCG N6004 GA | ❍ | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | 3 |

### ● Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tole-rance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N6002 GG | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | 1 |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N8004 GG | ● | ● | ● | ● | ❍ | ● | – | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| GCM N6002 GL | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | 1 |
| N6004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N8004 GL | ● | ❍ | ● | ● | ❍ | ● | – | 8,0 | ±0,04 | 0,4 | 28,8 | 6,0 | |
| GCM N6002 GF | ● | ● | ● | ● | ● | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | 1 |
| N6004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N8002 GF | ● | ● | ● | ● | ❍ | ● | – | 8,0 | ±0,04 | 0,2 | 28,8 | 6,0 | |
| N8004 GF | ● | ● | ● | ● | ❍ | ● | – | | ±0,04 | 0,4 | 28,8 | 6,0 | |

Combine the insert with a holder such that the width of cut (CW) matches.

# GNDI Type


## Internal Grooving








Use for multi-purpose or profiling insert for turning (wide grooves).




Above figures show right hand tools.

## ■ Spare Parts



## ■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | Min. Bore (mm) | Groov. Width (mm) | Max. Groov. Depth (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | DCON | H | LF | WF | DMIN | CW | CDX | | | | |
| GNDI R/L 2532 T 206 | ● | ● | 25 | 23 | 200 | 16 | 32 | 2,0 | 6 | GCM N20OO-□□ | BH0516 | 5,0 | LH030 |
| GNDI R/L 3240 T 210 | ● | ● | 32 | 30 | 250 | 26 | 40 | 2,0 | 10 | GCM N20OO-□□ | BH0616 | 6,0 | LH040 |
| GNDI R/L 2532 T 306 | ● | ● | 25 | 23 | 200 | 16 | 32 | 3,0 | 6 | GCM N30OO-□□ | BH0516 | 5,0 | LH030 |
| GNDI R/L 3240 T 310 | ● | ● | 32 | 30 | 250 | 26 | 40 | 3,0 | 10 | GCM N30OO-□□ | BH0616 | 6,0 | LH040 |
| GNDI R/L 4050 T 311 | ● | ● | 40 | 38 | 300 | 31 | 50 | 3,0 | 11 | GCM N30OO-□□ | | | |
| GNDI R/L 2532 T 406 | ● | ● | 25 | 23 | 200 | 19 | 32 | 4,0 | 6 | GCM N40OO-□□ | BH0516 | 5,0 | LH030 |
| GNDI R/L 3240 T 410 | ● | ● | 32 | 30 | 250 | 26 | 40 | 4,0 | 10 | GCM N40OO-□□ | BH0616 | 6,0 | LH040 |
| GNDI R/L 4050 T 411 | ● | ● | 40 | 38 | 300 | 31 | 50 | 4,0 | 11 | GCM N40OO-□□ | | | |
| GNDI R/L 2532 T 506 | ● | ○ | 25 | 23 | 200 | 19 | 32 | 5,0 | 6 | GCM N50OO-□□ | BH0516 | 5,0 | LH030 |
| GNDI R/L 3240 T 510 | ● | ● | 32 | 30 | 250 | 26 | 40 | 5,0 | 10 | GCM N50OO-□□ | BH0616 | 6,0 | LH040 |
| GNDI R/L 4050 T 511 | ● | ● | 40 | 38 | 300 | 31 | 50 | 5,0 | 11 | GCM N50OO-□□ | | | |
| GNDI R/L 4050 T 611 | ● | ● | 40 | 38 | 300 | 31 | 50 | 6,0 | 11 | GCM N60OO-□□ | BH0616 | 6,0 | LH040 |

Select holders and inserts with the same grooving width (CW).





● = Euro stock
○ = Japan stock

– Not available

N·m Recommended Tightening Torque (N·m)

# Grooving Tool Holders
# GNDI Type

## GNDI Inserts

Coated Carbide | Cermet | Carbide

Fig. 1





Fig. 2






Fig. 3




### ● Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |

### ● External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |
| N4020 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 4,0 | ±0,03 | 2,0 | 26,4 | 4,0 | |
| N5025 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 27,2 | 4,1 | |
| N6030 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 27,5 | 4,5 | |

### ● Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

### ● Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | | | | | | | | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | | | | | | | | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | | | | | | | | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |
| N4004 GA | ❍ | | | | | | | | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | | | | | | | | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | | | | | | | | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

### ● Grooving / Cut-Off Machining

Dimensions (mm)


| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |

Combine the insert with a holder such that the width of cut (CW) matches.


# GNDIS Type

## Internal Grooving

**GNDIS**
Internal Grooving



Internal




Above figures show right hand tools.

## ■ Spare Parts






## ■ Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | Min. Bore (mm) | Groov. Width (mm) | Max. Groov. Depth (mm) | Applicable Insert | Cap Screw | N·m | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | DCON | H | LF | LH | WF | DMIN | CW | CDX | | | | |
| GNDIS R/L 1214 T 1526 | ❍ | ❍ | 12 | 11 | 150 | 30 | 9,0 | 14 | 1,5 | 2,6 | GXM N150005S GF | | | |
| GNDIS R/L 1214 T 1536 | ❍ | ❍ | 12 | 11 | 150 | 30 | 10,0 | 14 | 1,5 | 3,6 | GXM N150005S GF | BFTX0409N | 3,4 | LT15 |
| GNDIS R/L 1616 T 1536 | ❍ | ❍ | 16 | 15 | 160 | 35 | 11,5 | 16 | 1,5 | 3,6 | GXM N150005S GF | | | |
| GNDIS R/L 1620 T 1546 | ❍ | ❍ | 16 | 15 | 160 | 40 | 14,5 | 20 | 1,5 | 4,6 | GXM N150005S GF | BFTX0511N | 5,0 | LT20 |
| GNDIS R/L 2025 T 1566 | ❍ | ❍ | 20 | 19 | 180 | 40 | 19,0 | 25 | 1,5 | 6,6 | GXM N150005S GF | | | |
| GNDIS R/L 1214 T 2026 | ❍ | ❍ | 12 | 11 | 150 | 30 | 9,0 | 14 | 2,0 | 2,6 | GXM N2002S-□□ | | | |
| GNDIS R/L 1214 T 2036 | ❍ | ❍ | 12 | 11 | 150 | 30 | 10,0 | 14 | 2,0 | 3,6 | GXM N2002S-□□ | BFTX0409N | 3,4 | LT15 |
| GNDIS R/L 1616 T 2036 | ❍ | ❍ | 16 | 15 | 160 | 35 | 11,5 | 16 | 2,0 | 3,6 | GXM N2002S-□□ | | | |
| GNDIS R/L 1620 T 2046 | ❍ | ❍ | 16 | 15 | 160 | 40 | 14,5 | 20 | 2,0 | 4,6 | GXM N2002S-□□ | BFTX0511N | 5,0 | LT20 |
| GNDIS R/L 2025 T 2066 | ❍ | ❍ | 20 | 19 | 180 | 40 | 19,0 | 25 | 2,0 | 6,6 | GXM N2002S-□□ | | | |
| GNDIS R/L 1214 T 3026 | ❍ | ❍ | 12 | 11 | 150 | 30 | 9,0 | 14 | 3,0 | 2,6 | GXM N3002S-□□ | | | |
| GNDIS R/L 1214 T 3036 | ❍ | ❍ | 12 | 11 | 150 | 30 | 10,0 | 14 | 3,0 | 3,6 | GXM N3002S-□□ | BFTX0409N | 3,4 | LT15 |
| GNDIS R/L 1616 T 3036 | ❍ | ❍ | 16 | 15 | 160 | 35 | 11,5 | 16 | 3,0 | 3,6 | GXM N3002S-□□ | | | |
| GNDIS R/L 1620 T 3046 | ❍ | ❍ | 16 | 15 | 160 | 40 | 14,5 | 20 | 3,0 | 4,6 | GXM N3002S-□□ | BFTX0511N | 5,0 | LT20 |
| GNDIS R/L 2025 T 3066 | ❍ | ❍ | 20 | 19 | 180 | 40 | 19,0 | 25 | 3,0 | 6,6 | GXM N3002S-□□ | | | |

Select holders and inserts with the same grooving width (CW).

Only GXM inserts can be used.





○ = Japan stock


– Not available

N·m Recommended Tightening Torque (N·m)

## Inserts for GNDIS

Coated Carbide

Fig. 1




### Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC520U | AC1030U | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|
| GXM N2002S ML | ❍ | ❍ | 2,0 | ±0,03 | 0,2 | 11,1 | 3,1 | 1 |
| N3002S ML | ❍ | ❍ | 3,0 | ±0,03 | 0,2 | 11,1 | 3,1 | |

Select holders and inserts with the same grooving width (CW).

### Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC520U | AC1030U | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|
| GXM N150005S GF | – | ❍ | 1,5 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2002S GF | ❍ | ❍ | 2,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3002S GF | ❍ | ❍ | 3,0 | ±0,03 | 0,4 | 21,1 | 3,8 | |

GCM and GCG inserts are not compatible.

## Recommended Cutting Conditions

| Work Material | P Carbon Steel / Alloy Steel | | M Stainless Steel | | K Cast Iron | | S Exotic Alloy | |
|---|---|---|---|---|---|---|---|---|
| Grade | AC520U | AC1030U | AC520U | AC1030U | AC520U | AC1030U | AC520U | AC1030U |
| Cutting Speed (m/min) | 80–200 | 50–200 | 70–150 | 50–150 | 60–200 | 50–200 | 20–80 | 20–60 |

## Grooving / Cut-Off Machining / Necking

| Chipbreaker | | Feed Rate (mm/rev) ML | Feed Rate (mm/rev) GF |
|---|---|---|---|
| Width of Cut CW (mm) | 1,5 | – | 0,02–0,10 |
| | 2,0 | 0,03–0,12 | 0,03–0,12 |
| | 3,0 | 0,05–0,15 | 0,05–0,15 |

## Traversing

| Chipbreaker | | ML Feed Rate (mm/rev) | ML Depth of Cut (mm) |
|---|---|---|---|
| Width of Cut CW (mm) | 2,0 | 0,03–0,12 | 0,2–0,8 |
| | 3,0 | 0,05–0,15 | 0,3–1,2 |


# SSH Series

New





## Features

Tough carbide body for stable machining.
Internal coolant supply for outstanding chip evacuation.
Adopts AC1030U for excellent machined surface quality.
In addition to grooving applications, we have a lineup of 12 items for circlip groove machining.




## Application Range




| | |
|---|---|
| Width of Cut: | 0,74 mm – 3,00 mm |
| Min. Bore Diameter: | Ø 8,0 mm |
| Max. Groove Depth: | to 4,0 mm |
| Holder: | Carbide body (internal coolant supply) |
| Insert: | Grade AC1030U |



## Chip Control




**SSH** Series

Stable and smooth evacuation of curled chips even on small diameters.





Competitor


Evacuation from grooves is poor, inviting sudden breakage.

| | | | |
|---|---|---|---|
| Work Material: | C45 | Cutting Conditions: | $v_c$ = 50 m/min, f = 0,02 mm/rev, $a_p$ = 1,0 mm, wet (oil-based) |
| Cutting Diameter: | Ø 13 mm | | |

## Chatter Resistance





**SSH** Series





Competitor

| | | | |
|---|---|---|---|
| Work Material: | C45 | Cutting Conditions: | $v_c$ = 100 m/min, f = 0,01, 0,02, 0,03 mm/rev, $a_p$ = 0,2 mm, wet (oil-based) |
| Cutting Diameter: | Ø 13 mm | | |

## Machined Surface Quality




**SSH** Series




Competitor

| | | | |
|---|---|---|---|
| Work Material: | 42CrMo4 | Cutting Conditions: | $v_c$ = 180 m/min, f = 0,02 mm/rev, $a_p$ = 0,2 mm, wet (oil-based) |
| Cutting Diameter: | Ø 30 mm | | |

**SSH**
Internal Grooving




Fig. 1






Fig. 2




## ■ Holder

Dimensions (mm)

## ■ Parts

| Cat. No. | Stock | DCON | DN | H | LF* | LHD | DMIN | CW | Fig. | Applicable Insert | Flat Screw | | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | | | | | | | | N·m | TRX08IP / LT15IP |
| E08D SSHM N125 08 | ❍ | 8 | 6 | 7 | 60 | 12,5 | 8 | 0,74–2,00 | 1 | SSH_ R/L 08 . . . | BFTX02608IPS | 1,2 | TRX08IP |
| E08E SSHM N210 08 | ❍ | 8 | 6 | 7 | 70 | 21,0 | 8 | 0,74–2,00 | 1 | | | | |
| E12E SSHM N125 08 | ❍ | 12 | 6 | 11 | 70 | 12,5 | 8 | 0,74–2,00 | 1 | | BFTX02608IPS | 1,2 | TRX08IP |
| E12F SSHM N210 08 | ❍ | 12 | 6 | 11 | 80 | 21,0 | 8 | 0,74–2,00 | 1 | | | | |
| E12G SSHM N300 08 | ❍ | 12 | 6 | 11 | 90 | 30,0 | 8 | 0,74–2,00 | 1 | | | | |
| E12H SSHM N420 08 | ❍ | 12 | 6 | 11 | 100 | 42,0 | 8 | 0,74–2,00 | 1 | | | | |
| E12X SSHM N195 14 | ❍ | 12 | 9 | 11 | 75 | 19,5 | 14 | 0,74–3,00 | 2 | SSH_ R/L 14 . . . | BFTX0412IPS | 5,0 | LT15IP |
| E12H SSHM N340 14 | ❍ | 12 | 9 | 11 | 100 | 34,0 | 14 | 0,74–3,00 | 2 | | | | |
| E12J SSHM N450 14 | ❍ | 12 | 9 | 11 | 110 | 45,0 | 14 | 0,74–3,00 | 2 | | | | |
| E12X SSHM N640 14 | ❍ | 12 | 9 | 11 | 130 | 64,0 | 14 | 0,74–3,00 | 2 | | | | |
| E16F SSHM N195 14 | ❍ | 16 | 9 | 14 | 80 | 19,5 | 14 | 0,74–3,00 | 2 | | BFTX0412IPS | 5,0 | LT15IP |
| E16H SSHM N340 14 | ❍ | 16 | 9 | 14 | 100 | 34,0 | 14 | 0,74–3,00 | 2 | | | | |
| E16J SSHM N450 14 | ❍ | 16 | 9 | 14 | 110 | 45,0 | 14 | 0,74–3,00 | 2 | | | | |
| E16X SSHM N640 14 | ❍ | 16 | 9 | 14 | 130 | 64,0 | 14 | 0,74–3,00 | 2 | | | | |

* The LF dimensions above are dimensions with SSHG/SSHR type insert mounted. Refer to the insert stock table for WF dimensions.

## ■ Inserts (E08_ SSHM N_ _ _ -08 / E12_ SSHM N_ _ _ -08)

Dimensions (mm)

| Applications | Cat. No. | | AC1030U Coated Carbide R | AC1030U Coated Carbide L | CW | CDX | RE | WF3 | WF | S | E2 | Fig. | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Grooving | SSHG | R/L 0807400 | ❍ | ❍ | 0,74 | 1,0 | – | 3,2 | 4,80 | 3,6 | 0,4 | 1 | E08_SSHM N_ _ _ 08<br>E12_SSHM N_ _ _ 08 |
| | | R/L 0808400 | ❍ | ❍ | 0,84 | 1,0 | – | 3,2 | 4,80 | 3,6 | 0,4 | 1 | |
| | | R/L 0809400 | ❍ | ❍ | 0,94 | 1,0 | – | 3,2 | 4,80 | 3,6 | 0,4 | 1 | |
| | | R/L 0810000 | ❍ | ❍ | 1,00 | 1,0 | – | 3,2 | 4,80 | 3,1 | – | 1 | |
| | | R/L 0810010 | ❍ | ❍ | 1,00 | 1,0 | 0,10 | 3,2 | 4,80 | 3,1 | – | 2 | |
| | | R/L 0811900 | ❍ | ❍ | 1,19 | 1,0 | – | 3,2 | 4,80 | 3,1 | – | 1 | |
| | | R/L 0813900 | ❍ | ❍ | 1,39 | 1,0 | – | 3,2 | 4,80 | 3,0 | – | 1 | |
| | | R/L 0815000 | ❍ | ❍ | 1,50 | 1,0 | – | 3,2 | 4,80 | 3,0 | – | 1 | |
| | | R/L 0815010 | ❍ | ❍ | 1,50 | 1,0 | 0,10 | 3,2 | 4,80 | 3,0 | – | 2 | |
| | | R/L 0816900 | ❍ | ❍ | 1,69 | 1,0 | – | 3,2 | 4,80 | 3,0 | – | 1 | |
| | | R/L 0820000 | ❍ | ❍ | 2,00 | 1,0 | – | 3,2 | 4,80 | 3,0 | – | 1 | |
| | | R/L 0820010 | ❍ | ❍ | 2,00 | 1,0 | 0,10 | 3,2 | 4,80 | 3,0 | – | 2 | |
| | | R/L 0820020 | ❍ | ❍ | 2,00 | 1,0 | 0,20 | 3,2 | 4,80 | 3,0 | – | 2 | |
| Radius Grooving/ Profiling | SSHR | R/L 08080 | ❍ | ❍ | 0,80 | 1,0 | 0,40 | 3,2 | 4,80 | 3,1 | – | 3 | |
| | | R/L 08100 | ❍ | ❍ | 1,00 | 1,0 | 0,50 | 3,2 | 4,80 | 3,1 | – | 3 | |
| | | R/L 08120 | ❍ | ❍ | 1,20 | 1,0 | 0,60 | 3,2 | 4,80 | 3,1 | – | 3 | |
| | | R/L 08150 | ❍ | ❍ | 1,50 | 1,0 | 0,75 | 3,2 | 4,80 | 3,0 | – | 3 | |
| | | R/L 08180 | ❍ | ❍ | 1,80 | 1,0 | 0,90 | 3,2 | 4,80 | 3,0 | – | 3 | |
| | | R/L 08200 | ❍ | ❍ | 2,00 | 1,0 | 1,00 | 3,2 | 4,80 | 3,0 | – | 3 | |
| Chamfering | SSHC | R/L 08454502 | ❍ | ❍ | – | 1,4 | 0,20 | 1,8 | 4,65 | 3,6 | – | 4 | |

* Refer to the holder stock table for the DMIN dimensions above.

WF, WF3, E2: Cutting Edge Distance

Fig. 1 (For Grooving)





Fig. 2 (For Grooving)





Fig. 3 (For Radius Grooving/Profiling)





Fig. 4 (For Chamfering)





Fig. shows right hand (R) tools.

❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

New

## ■ Inserts (E12_ SSHM N_ _ _ -14 / E16_ SSHM N_ _ _ -14)

Dimensions (mm)

| Applica-tions | Cat. No. | AC1030U Coated Carbide R | AC1030U Coated Carbide L | CW | CDX | RE | WF3 | WF | S | E2 | Fig. | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Grooving | SSHG R/L 1407400 | ❍ | ❍ | 0,74 | 1,2 | – | 5,3 | 9,0 | 5,5 | 0,2 | 1 | E12_ SSHM N_ _ _ 14<br>E16_ SSHM N_ _ _ 14 |
| | R/L 1408400 | ❍ | ❍ | 0,84 | 1,3 | – | 5,3 | 9,0 | 5,5 | 0,2 | 1 | |
| | R/L 1409400 | ❍ | ❍ | 0,94 | 1,5 | – | 5,3 | 9,0 | 5,5 | 0,2 | 1 | |
| | R/L 1410000 | ❍ | ❍ | 1,00 | 1,6 | – | 5,3 | 9,0 | 5,5 | 0,2 | 1 | |
| | R/L 1410010 | ❍ | ❍ | 1,00 | 1,6 | 0,10 | 5,3 | 9,0 | 5,5 | 0,2 | 2 | |
| | R/L 1411900 | ❍ | ❍ | 1,19 | 4,0 | – | 5,3 | 9,0 | 5,2 | – | 1 | |
| | R/L 1413900 | ❍ | ❍ | 1,39 | 4,0 | – | 5,3 | 9,0 | 5,1 | – | 1 | |
| | R/L 1415000 | ❍ | ❍ | 1,50 | 4,0 | – | 5,3 | 9,0 | 5,1 | – | 1 | |
| | R/L 1415010 | ❍ | ❍ | 1,50 | 4,0 | 0,10 | 5,3 | 9,0 | 5,1 | – | 2 | |
| | R/L 1416900 | ❍ | ❍ | 1,69 | 4,0 | – | 5,3 | 9,0 | 5,1 | – | 1 | |
| | R/L 1420000 | ❍ | ❍ | 2,00 | 4,0 | – | 5,3 | 9,0 | 5,1 | – | 1 | |
| | R/L 1420010 | ❍ | ❍ | 2,00 | 4,0 | 0,10 | 5,3 | 9,0 | 5,1 | – | 2 | |
| | R/L 1420020 | ❍ | ❍ | 2,00 | 4,0 | 0,20 | 5,3 | 9,0 | 5,1 | – | 2 | |
| | R/L 1425000 | ❍ | ❍ | 2,50 | 4,0 | – | 5,3 | 9,0 | 5,1 | – | 1 | |
| | R/L 1425010 | ❍ | ❍ | 2,50 | 4,0 | 0,10 | 5,3 | 9,0 | 5,1 | – | 2 | |
| | R/L 1425020 | ❍ | ❍ | 2,50 | 4,0 | 0,20 | 5,3 | 9,0 | 5,1 | – | 2 | |
| | R/L 1430000 | ❍ | ❍ | 3,00 | 4,0 | – | 5,3 | 9,0 | 5,1 | – | 1 | |
| | R/L 1430010 | ❍ | ❍ | 3,00 | 4,0 | 0,10 | 5,3 | 9,0 | 5,1 | – | 2 | |
| | R/L 1430020 | ❍ | ❍ | 3,00 | 4,0 | 0,20 | 5,3 | 9,0 | 5,1 | – | 2 | |
| Radius Grooving/ Profiling | SSHR R/L 14100 | ❍ | ❍ | 1,00 | 1,6 | 0,50 | 5,3 | 9,0 | 5,2 | – | 3 | |
| | R/L 14120 | ❍ | ❍ | 1,20 | 4,0 | 0,60 | 5,3 | 9,0 | 5,2 | – | 3 | |
| | R/L 14150 | ❍ | ❍ | 1,50 | 4,0 | 0,75 | 5,3 | 9,0 | 5,1 | – | 3 | |
| | R/L 14180 | ❍ | ❍ | 1,80 | 4,0 | 0,90 | 5,3 | 9,0 | 5,1 | – | 3 | |
| | R/L 14200 | ❍ | ❍ | 2,00 | 4,0 | 1,00 | 5,3 | 9,0 | 5,1 | – | 3 | |
| | R/L 14220 | ❍ | ❍ | 2,20 | 4,0 | 1,10 | 5,3 | 9,0 | 5,1 | – | 3 | |
| | R/L 14250 | ❍ | ❍ | 2,50 | 4,0 | 1,25 | 5,3 | 9,0 | 5,1 | – | 3 | |
| | R/L 14300 | ❍ | ❍ | 3,00 | 4,0 | 1,50 | 5,3 | 9,0 | 5,1 | – | 3 | |

Fig. 1 (For Grooving)





Fig. 2 (For Grooving)





Fig. 3 (For Radius Grooving/Profiling)





Fig. shows right hand (R) tools.

* Refer to the holder stock table for the DMIN dimensions above.
WF, WF3, E2: Cutting Edge Distance

❍ = Japan stock

## ■ Recommended Cutting Conditions

| Work Material | P Carbon Steel/Alloy Steel | M Stainless Steel | S Cast Iron |
|---|---|---|---|
| Cutting Speed $v_c$ (m/min) | 20–200 | 15–80 | 20–160 |
| Feed Rate f (mm/rev) | 0,01–0,03 | 0,01–0,03 | 0,01–0,03 |







❍ = Japan stock

# GND Grooving System

**GNDCM**
External Grooving



External








## General Features

New grades and chipbreakers have been added to the already established GND grooving system with polygon shank and a flexible and economical cassette system for inserts. An array of chipbreakers improves the efficiency in chip control in various applications such as grooving, turning, profiling and cut-off.

## Advantages

- GND inserts for soft grooving from 2,0 - 6,0 mm width
- Expanded grade selection with 9 different chipbreakers for a wide application range
- Provides excellent chip control
- Achieves stable long tool life


## Cassette

| Cat. No. | R | L | CW (mm) | CDX (mm) | Inserts | Cap Screw | Tightening Torque (N·m) | Spanner |
|---|---|---|---|---|---|---|---|---|
| GNDCM R/L 212 | ● | ● | 2 | 12 | GCM □20○○-□□ | BX0512 | 5,0 | LH040 |
| GNDCM R/L 312 | ● | ● | 3 | | GCM □30○○-□□ | | | |
| GNDCM R/L 418 | ● | ● | 4 | 18 | GCM □40○○-□□ | | 6,0 | |
| GNDCM R/L 518 | ● | ● | 5 | | GCM □50○○-□□ | | | |
| GNDCM R/L 618 | ● | ● | 6 | | GCM □60○○-□□ | | | |

## Handling


ATTENTION

To fix the cassette on the holder, please clamp the cassette at first with the inner torx screw.




## Holder

PSC__GM**00**
(straight)




PSC__GM**90**
(L-style)




Note:
The right handed PSC40/50GM90R holder needs a left cassette.
The left handed PSC40/50GM90L holder needs a right cassette.

| Style | Cat. No. | R | L | DCSFMS (mm) | WF (mm) | LF (mm) | Cap Screw | Tightening Torque (N·m) | Spanner |
|---|---|---|---|---|---|---|---|---|---|
| Straight | PSC40GM00 R/L | ● | ● | 40 | 22 | **80*** | BFTX0619N | 7,5 | LT25 |
| | PSC50GM00 R/L | ● | ● | 50 | 27 | | | | |
| L-Style | PSC40GM90 R/L | ● | ● | 40 | **42*** | 52,5 | | | |
| | PSC50GM90 R/L | ● | ● | 50 | **47*** | 55,0 | | | |

* Dimension when using radial grooving cassettes.

## Identification Details - Polygon-Toolholder

| **PSC** | **40** | - | **G** | **M** | **00** | **R** |
|---|---|---|---|---|---|---|
| Polygonshank | Shank Diameter (DCSFMS) | | Series Symbol GND | Application External Multi-Purpose | Style 00 = Straight 90 = L-Style | Holder Design R = Right L = Left |

## Identification Details - Cassette

| **GND** | **C** | **M** | **L** | **3** | **12** |
|---|---|---|---|---|---|
| Series Symbol GND | Cassette | Application External Multi-Purpose | Holder Design R = Right L = Left | Grooving Width | Max. Grooving Depth |





● = Euro stock
○ = Japan stock

– Not available

Recommended Tightening Torque (N·m)

## Inserts for GNDCM

Coated Carbide | Cermet | Carbide

Fig. 1





Fig. 2





Fig. 3






Fig. 4




### Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| GCM N2002 ML | – | – | – | – | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |

### External Profiling / External Radius Grooving

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 1,5 | 21,1 | 3,8 | 2 |
| N4020 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 4,0 | ±0,03 | 2,0 | 26,4 | 4,0 | |
| N5025 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 2,5 | 27,2 | 4,1 | |
| N6030 RG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 3,0 | 27,5 | 4,5 | |

### Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2010 RN | – | – | – | – | ● | ● | ❍ | ❍ | – | 2,0 | ±0,03 | 1,0 | 21,7 | 3,6 | 2 |
| N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

### Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|
| GCG N2002 GA | ❍ | 2,0 | ±0,025 | 0,2 | 21,1 | 3,6 | 3 |
| N3002 GA | ❍ | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | |
| N4004 GA | ❍ | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

### Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N2002 GG | ● | ● | ● | ● | ● | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N3002 GG | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GL | ● | ● | ● | ● | ❍ | ● | – | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GL | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N2002 GF | – | – | ● | ● | | ● | ❍ | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 1 |
| N2004 GF | – | – | ● | ● | | ❍ | ❍ | | ±0,03 | 0,4 | 21,1 | 3,6 | |
| N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |

### Cut-Off Machining (Handed Edge)


Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | AC1030U | PSI | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM R2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | 4 |
| L2002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 2,0 | ±0,03 | 0,2 | 21,1 | 3,6 | |
| GCM R3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| L3002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 3,0 | ±0,03 | 0,2 | 21,3 | 3,8 | |
| GCM R4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| L4002 CG 05 | ● | ● | ● | ● | ❍ | ● | – | 5° | 4,0 | ±0,04 | 0,2 | 26,7 | 4,0 | |
| GCM R20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 10 | – | – | ● | ● | – | – | ● | 10° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| GCM R20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| L20003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 2,0 | ±0,08 | 0,03 | 22,4 | 3,6 | |
| GCM R30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |
| L30003 CF 15 | – | – | ● | ● | – | – | ● | 15° | 3,0 | ±0,08 | 0,03 | 22,4 | 3,8 | |


GCM R: Right hand GCM L: Left hand


Combine the insert with a holder such that the width of cut (CW) matches.


**GNDCF**
Face Grooving



Face







Above figures show right hand tools.







Work diameters in the stock indicate external diameters of face grooving.

## Cassette


| Cat. No. | R | L | CW (mm) | Diameter Range (mm) | DC (mm) | CDX (mm) | Inserts | Cap Screw | Tightening Torque (N·m) | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|
| GNDCF R/L 312-040 | ● | ● | 3 | 40–200 | 40–55 | 12 | GC□ N30OO-□□ | BX0512 | 5,0 | LH040 |
| GNDCF R/L 315-050 | ● | ● | | | 50–70 | 15 | | | | |
| GNDCF R/L 315-065 | ● | ● | | | 65–100 | 15 | | | | |
| GNDCF R/L 318-090 | ● | ❑ | | | 90–150 | 18 | | | | |
| GNDCF R/L 318-140 | ● | ❑ | | | 140–200 | 18 | | | | |
| GNDCF R/L 418-040 | ● | ● | 4 | 40–300 | 40–55 | 18 | GC□ N40OO-□□ | | 6,0 | |
| GNDCF R/L 418-050 | ● | ❑ | | | 50–70 | 18 | | | | |
| GNDCF R/L 418-065 | ● | ● | | | 65–90 | 18 | | | | |
| GNDCF R/L 418-085 | ● | ❑ | | | 85–130 | 18 | | | | |
| GNDCF R/L 418-125 | ❑ | ❑ | | | 125–200 | 18 | | | | |
| GNDCF R/L 418-180 | ● | ❑ | | | 180–300 | 18 | | | | |
| GNDCF R/L 518-050 | ❑ | ❑ | 5 | 50–300 | 50–70 | 18 | GC□ N50OO-□□ | | | |
| GNDCF R/L 518-065 | ❑ | ❑ | | | 65–90 | 18 | | | | |
| GNDCF R/L 518-085 | ❑ | ❑ | | | 85–130 | 18 | | | | |
| GNDCF R/L 518-125 | ● | ❑ | | | 125–200 | 18 | | | | |
| GNDCF R/L 518-180 | ❑ | ❑ | | | 180–300 | 18 | | | | |
| GNDCF R/L 618-050 | ❑ | ❑ | 6 | 50–1000 | 50–75 | 18 | GC□ N60OO-□□ | | | |
| GNDCF R/L 618-070 | ❑ | ❑ | | | 70–110 | 18 | | | | |
| GNDCF R/L 618-100 | ❑ | ❑ | | | 100–200 | 18 | | | | |
| GNDCF R/L 618-180 | ❑ | ❑ | | | 180–300 | 18 | | | | |
| GNDCF R/L 618-280 | ❑ | ❑ | | | 280–1000 | 18 | | | | |

## Holder

PSC__GM**00**
(straight)




PSC__GM**90**
(L-style)




Note:
The **right** handed PSC40/50GM90R holder needs a **left** cassette.
The **left** handed PSC40/50GM90L holder needs a **right** cassette.

| Style | Cat. No. | R | L | DCSFMS (mm) | WF (mm) | LF (mm) | Cap Screw | Tightening Torque (N·m) | Spanner |
|---|---|---|---|---|---|---|---|---|---|
| Straight | PSC40GM00 R/L | ● | ● | 40 | 22 | **81*** | BFTX0619N | 7,5 | LT25 |
| | PSC50GM00 R/L | ● | ● | 50 | 27 | | | | |
| L-Style | PSC40GM90 R/L | ● | ● | 40 | **43*** | 52,5 | | | |
| | PSC50GM90 R/L | ● | ● | 50 | **48*** | 55,0 | | | |

* Dimension when using face grooving cassettes.

## Identification Details - Polygon-Toolholder

| PSC | 40 | - | G | M | 00 | R |
|---|---|---|---|---|---|---|
| Polygonshank | Shank Diameter (DCSFMS) | | Series Symbol GND | Application External Multi-Purpose | Style 00 = Straight 90 = L-Style | Holder Design R = Right L = Left |

## Identification Details - Cassette

| GND | C | F | L | 3 | 12 |
|---|---|---|---|---|---|
| Series Symbol GND | Cassette | Application Face Grooving | Holder Design R = Right L = Left | Grooving Width | Max. Grooving Depth |





● = Euro stock
○ = Japan stock
❑ = Delivery on request
Recommended Tightening Torque (N·m)

## Inserts for GNDCF

Coated Carbide  Cermet  Carbide

Fig. 1





Fig. 2






Fig. 3




### ● Grooving / Traversing

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 MG | ● | ● | | ❍ | ● | ● | | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 MG | ● | ● | | ❍ | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 MG | ● | ● | | ❍ | ● | ● | | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 MG | ● | ● | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |
| GCM N3002 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 ML | ● | ● | | ❍ | ● | ● | | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N4008 ML | ● | ● | | ❍ | ● | ● | | ❍ | ❍ | | ±0,03 | 0,8 | 26,4 | 4,0 | |
| N5004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N5008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,1 | |
| N6004 ML | ● | ● | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,4 | 26,4 | 4,5 | |
| N6008 ML | ● | ● | | ❍ | ● | ● | | ❍ | – | | ±0,03 | 0,8 | 26,4 | 4,5 | |

### ● Profiling / Radius Grooving / Necking

Dimensions (mm)

| Cat. No. | AC8025P | AC8035P | AC830P | AC425K | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3015 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 3,0 | ±0,03 | 1,5 | 22,6 | 3,8 | 2 |
| N4020 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 4,0 | ±0,03 | 2,0 | 28,2 | 4,0 | |
| N5025 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 5,0 | ±0,03 | 2,5 | 28,3 | 4,1 | |
| N6030 RN | ● | ● | ● | ❍ | ● | ● | ❍ | ❍ | – | 6,0 | ±0,03 | 3,0 | 28,3 | 4,5 | |

### ● Non-Ferrous Metals

Dimensions (mm)

| Cat. No. | H1 | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|
| GCM N3002 GA | ❍ | 3,0 | ±0,025 | 0,2 | 21,1 | 3,8 | 3 |
| N4004 GA | ❍ | 4,0 | ±0,025 | 0,4 | 26,4 | 4,0 | |
| N5004 GA | ❍ | 5,0 | ±0,025 | 0,4 | 26,4 | 4,1 | |
| N6004 GA | ❍ | 6,0 | ±0,025 | 0,4 | 26,4 | 4,5 | |

### ● Grooving / Cut-Off Machining

Dimensions (mm)

| Cat. No. | AC8035P | AC830P | AC5015S | AC5025S | AC520U | AC530U | T2500A | CW Cutting Width | CW Tolerance | RE | L | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GCM N3002 GG | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GG | ● | ● | ● | ● | ❍ | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GG | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GG | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GG | ● | ● | ● | ● | ❍ | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N3002 GL | ● | ● | ● | ● | ❍ | ● | – | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GL | ● | ● | ● | ● | ❍ | ● | – | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GL | ● | ● | ● | ● | ❍ | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GL | ● | ● | ● | ● | ❍ | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GL | ● | | ● | ● | | ❍ | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |
| GCM N3002 GF | ● | ● | ● | ● | ● | ● | ❍ | 3,0 | ±0,03 | 0,2 | 21,1 | 3,8 | 1 |
| N3004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 21,1 | 3,8 | |
| N4002 GF | ● | ● | ● | ● | ● | ● | ❍ | 4,0 | ±0,03 | 0,2 | 26,4 | 4,0 | |
| N4004 GF | ● | | ● | ● | | ● | ❍ | | ±0,03 | 0,4 | 26,4 | 4,0 | |
| N5002 GF | ● | ● | ● | ● | ● | ● | – | 5,0 | ±0,03 | 0,2 | 26,4 | 4,1 | |
| N5004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,1 | |
| N6002 GF | ● | ● | ● | ● | ● | ● | – | 6,0 | ±0,03 | 0,2 | 26,4 | 4,5 | |
| N6004 GF | ● | | ● | ● | | ● | – | | ±0,03 | 0,4 | 26,4 | 4,5 | |

Combine the insert with a holder such that the width of cut (CW) matches.



– Not available

# TGA-BF Type



## Characteristics

- Outstanding chip control when grooving
- Excellent chip control when finishing wide grooves using axial feed
- Grooving inserts from 1,5–4,5 mm wide
- Grade AC530U with Super ZX ultra hard coating for steels, stainless steels and cast iron increases productivity and extends tool life

## External Grooving

Figures show right hand tools.

**GWC**
External Grooving




Fig. 1





Fig. 2






Fig. 3




The rake angle R varies depending on the insert grade. For details, see the table at the lower part of page F47.


### Holders


Right handed tool holders are applicable with **right** handed inserts (TGA-R), left handed clamp plates (CCM_ _ L) and right handed screws 8WB_ _T)

### Spare Parts

| Cat. No. | Stock R | Stock L | H | B | LF | WF | HF | Fig. | Grooving Width CW (mm) | Maximum Grooving Depth (mm) | Applicable Insert Group No. | Screw | (N·m) | Wrench | Clamp | Screw | (N·m) | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GWC R/L 1010-3 | ❍ | ❍ | 10 | 10 | 125 | 10 | 10 | 2 | 0,33–2,80 | 0,8–2,5 | ❶ | BFTX 0409N | 3,4 | TRX15 | – | – | – | – |
| GWC R/L 1212-3 | ❍ | ❍ | 12 | 12 | 125 | 12 | 12 | 2 | 0,33–2,80 | 0,8–2,5 | ❶ | | | | | | | |
| GWC R/L 1616-3 | ● | ❍ | 16 | 16 | 125 | 16 | 16 | 3 | 0,33–2,80 | 0,8–2,5 | ❶ | | | | | | | |
| GWC R/L 2020-3 | ❍ | ❍ | 20 | 20 | 125 | 25 | 20 | 1 | 0,33–2,80 | 0,8–2,5 | ❶ | BFTX 0409N | 3,4 | TRX15 | CCM 6B -L/R | WB 6-20 -T/TL | 5,0 | LT20 |
| GWC R/L 2525-3 | ❍ | ● | 25 | 20 | 150 | 30 | 25 | 1 | 0,33–2,80 | 0,8–2,5 | ❶ | | | | | | | |
| GWC R/L 2020-15 | ● | ● | 20 | 20 | 125 | 25 | 20 | 1 | 1,25–1,45 | 2,0 | ❷ | BFTX 0511N | 5,0 | TRX20 | CCM 8U -L/R | WB 8-22 -T/TL | 5,0 | LT27 |
| GWC R/L 2020-25 | ● | ❍ | 20 | 20 | 125 | 25 | 20 | 1 | 1,50–2,30 | 3,5 | ❸ | | | | | | | |
| GWC R/L 2020-35 | ● | ● | 20 | 20 | 125 | 25 | 20 | 1 | 2,50–4,80 | 5,0 | ❹ | | | | | | | |
| GWC R/L 2525-15 | ● | ❍ | 25 | 25 | 150 | 30 | 25 | 1 | 1,25–1,45 | 2,0 | ❷ | | | | | | | |
| GWC R/L 2525-25 | ● | ● | 25 | 25 | 150 | 30 | 25 | 1 | 1,50–2,30 | 3,5 | ❸ | | | | | | | |
| GWC R/L 2525-35 | ● | ● | 25 | 25 | 150 | 30 | 25 | 1 | 2,50–4,80 | 5,0 | ❹ | | | | | | | |

**GWCS**
External Grooving






The rake angle R varies depending on the insert grade. For details, see the table at the lower part of page F47.

Figures show right hand tools.

### Holders

Right handed tool holders are applicable with **left** handed inserts (TGA-L), right handed clamp plates (CCM_ _R) and left handed screws (WB_ _TL)

### Spare Parts

| Cat. No. | Stock R | Stock L | H | B | LF | WF | HF | Grooving Width CW (mm) | Maximum Grooving Depth (mm) | Applicable Insert Group No. | Screw | (N·m) | Wrench | Clamp | Screw | (N·m) | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GWCS R/L 2020-3 | ❍ | | 20 | 20 | 125 | 25 | 20 | 0,33–2,80 | 0,8–2,5 | ❶ | BFTX 0409N | 3,4 | TRX15 | CCM 6B -L/R | WB 6-20 -T/TL | 5,0 | LT20 |
| GWCS R/L 2525-3 | | | 25 | 25 | 150 | 30 | 25 | 0,33–2,80 | 0,8–2,5 | ❶ | | | | | | | |
| GWCS R/L 2020-15 | ❍ | ❍ | 20 | 20 | 125 | 27 | 20 | 1,25–1,45 | 2,0 | ❷ | BFTX 0511N | 5,0 | TRX20 | CCM 8U -L/R | WB 8-22 -T/TL | 5,0 | LT27 |
| GWCS R/L 2020-25 | ❍ | ❍ | 20 | 20 | 125 | 27 | 20 | 1,50–2,30 | 3,5 | ❸ | | | | | | | |
| GWCS R/L 2020-35 | ❍ | ❍ | 20 | 20 | 125 | 27 | 20 | 2,50–4,80 | 5,0 | ❹ | | | | | | | |
| GWCS R/L 2525-15 | ❍ | ❍ | 25 | 25 | 150 | 32 | 25 | 1,25–1,45 | 2,0 | ❷ | | | | | | | |
| GWCS R/L 2525-25 | | ❍ | 25 | 25 | 150 | 32 | 25 | 1,50–2,30 | 3,5 | ❸ | | | | | | | |
| GWCS R/L 2525-35 | ❍ | ❍ | 25 | 25 | 150 | 32 | 25 | 2,50–4,80 | 5,0 | ❹ | | | | | | | |

● = Euro stock
○ = Japan stock

(N·m) Recommended Tightening Torque (N·m)

## ISO-PSC Polygon Modular



PSC

### Holder


| Cat. No. | R | L | Ø (mm) | F (mm) | L (mm) | Cap Screw | (N·m) | Spanner |
|---|---|---|---|---|---|---|---|---|
| PSC 40 GM00 R/L | ● | ● | 40 | 22 | 80,0 | BFTX0619N | 7,5 | LT25 |
| PSC 50 GM00 R/L | ● | ● | 50 | 27 | 80,0 | | | |
| PSC 40 GM90 R/L | ● | ● | 40 | 42 | 52,5 | | | |
| PSC 50 GM90 R/L | ● | ● | 50 | 47 | 55,0 | | | |


### Cassette

| Cat. No. | R | L | Grooving Width (mm) | Grooving Depth (mm) | Insert | Insert Screw | Spanner | Spring | Clamp Finger | Cap Screw | (N·m) | Spanner |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GWCCM R/L 25 | ● | ● | 1,5–2,3 | 3,9 | TGA□4□□□BF | BFTX0511N | TRX20 | SCP4A | | | 3,0 | LH030 |
| GWCCM R/L 35 | ● | ● | 2,5–4,5 | 5,4 | TGA□4□□□BF | **5,0** (N·m) | | | | | | |

## Internal Grooving

**GWCI**
Internal Grooving






The rake angle R varies depending on the insert grade. For details, see the table at the lower part of page F39.

Figures show right hand tools.

### Spare Parts





### Holders

Right handed tool holders are applicable with **left** handed inserts (TGA-L).

| Cat. No. | Stock R | Stock L | Dimensions (mm) DMIN | DCON | LF | H | HF | WF | Grooving width CW (mm) | Maximum Grooving Depth (mm) | Applicable Insert Group No. | Screw | (N·m) | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| GWCI R/L 325 | ❍ | ❍ | 35 | 25 | 100 | 23 | 11,5 | 17,5 | 0,33–2,80 | 0,8–2,0 | ❶ | BFTX0409N | 3,4 | TRX 15 |
| GWCI R/L 432 | ❍ | ❍ | 40 | 32 | 250 | 30 | 15,0 | 17,5 | 1,25–4,80 | 2,0–2,5 | ❷❸❹ | BFTX0511N | 5,0 | TRX 20 |

### Inserts




Notice:
Please note the cutting edge position E2, for grooving widths below 1,85 mm..

(Note 2) Figures show right hand tools.


| Cat. No. | Coated AC530U R | Coated AC530U L | Dimensions (mm) ( ) CDX: presents max. depth CW | CDX | RE | E2 | Fig. | Applicable holder & insert group |
|---|---|---|---|---|---|---|---|---|
| TGA R/L 4140BF01 | ❍ | ❍ | 1,40 | 2,5 (2,0-1,7) | 0,1 | 0,300 | 2 | ❷ |
| TGA R/L 4150BF | ● | ● | 1,50 | 3,9 External (3,5) Internal (2,5) | 0,2 | 0,250 | 2 | ❸ |
| TGA R/L 4165BF | ❍ | ❍ | 1,65 | | | 0,175 | | |
| TGA R/L 4175BF | ❍ | ❍ | 1,75 | | | 0,125 | | |
| TGA R/L 4185BF | ❍ | ❍ | 1,85 | | | 0,075 | | |
| TGA R/L 4200BF | ● | ● | 2,00 | | | 0 | 1 | |
| TGA R/L 4220BF | ❍ | ❍ | 2,20 | | | | | |
| TGA R/L 4230BF | ❍ | ❍ | 2,30 | | | | | |
| TGA R/L 4250BF | ● | ● | 2,50 | 5,4 External (5,0) Internal (2,5) | 0,3 | 0 | 1 | ❹ |
| TGA R/L 4265BF | ❍ | ❍ | 2,65 | | | | | |
| TGA R/L 4270BF | ❍ | ❍ | 2,70 | | | | | |
| TGA R/L 4280BF | ❍ | ❍ | 2,80 | | | | | |
| TGA R/L 4300BF | ● | ● | 3,00 | | | | | |
| TGA R/L 4320BF | ❍ | ❍ | 3,20 | | | | | |
| TGA R/L 4330BF | ❍ | ❍ | 3,30 | | | | | |
| TGA R/L 4350BF | ● | ● | 3,50 | | | | | |
| TGA R/L 4370BF | ❍ | ❍ | 3,70 | | | | | |
| TGA R/L 4390BF | ❍ | ❍ | 3,90 | | | | | |
| TGA R/L 4400BF | ● | ● | 4,00 | | 0,4 | | | |
| TGA R/L 4410BF | ❍ | ❍ | 4,10 | | | | | |
| TGA R/L 4420BF | | ❍ | 4,20 | | | | | |
| TGA R/L 4430BF | ❍ | ❍ | 4,30 | | | | | |
| TGA R/L 4440BF | ❍ | ❍ | 4,40 | | | | | |
| TGA R/L 4450BF | ● | ❍ | 4,50 | | | | | |

*) Please select applicable inserts for the holders by using matching group numbers.

### Recommended Cutting Conditions

#### Grooving

Feed direction





Wet condition is recommended.

| Work Material | | General Steel | | Stainless Steel | |
|---|---|---|---|---|---|
| Cutting speed (m/min) | | 50–180 | | 50–160 | |
| Groove width (mm) | | 1,5–2,3 | 2,5–3,3 | 3,5–4,5 | |
| Feed rate (mm/rev) | | 0,03–0,12 | 0,04–0,12 | 0,05–0,12 | |
| Depth of cut (mm) | Ext. | –3,5 | –5,0 | –5,0 | |
| | Int. | –2,5 | | | |

#### Axial Feed

Feed direction for axial feed




Wet condition is recommended.

| Work Material | General Steel | | Stainless Steel |
|---|---|---|---|
| Cutting speed (m/min) | 50–180 | | 50–160 |
| Feed rate (mm/rev) | 0,03–0,10 | 0,05–0,10 | 0,07–0,12 |
| Depth of cut (mm) | –0,3 | –0,5 | –0,7 |


### Rake Angle with a Holder Fitted (E)

| Grooving | AC530U | H1 | T2500Z T3000Z | T1500A | BN2000 | DA2200 |
|---|---|---|---|---|---|---|
| External GWC, GWCS | 10° | 20° | 10° | 5° | 0° | 10° |
| Internal GWCI | 1° | 11° | 1° | –4° | –9° | 1° |

# TGA Type

Expansion

## ■ Square Edged Grooving Insert




This figure shows right handed tools.

| Grade | | Cutting Edge | GAN |
|---|---|---|---|
| Coated Carbide | AC530U | Honing | 15° |
| Carbide | H1 | Sharp | 25° |
| Coated Cermet | T2500Z,T3000Z | Honing | 15° |
| Cermet | T1500A | Sharp | 10° |
| SUMIBORON | BN2000 | K-Land | 5° |
| SUMIDIA | DA2200 | Sharp | 15° |

* See page F47 for the rake angle with a holder fitted.

Dimensions (mm)

| Cat. No. (The part numbers of T1500A end with E) | AC530U | | H1 | | T2500Z | | T3000Z | | T1500A | | BN2000 | | DA2200 | | CW | Max. Groove Depth | | CDX | RE | IC | S | Insert /Holder Group No.* |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | R | L | R | L | R | L | R | L | R | L | R | L | | External | Internal | | | | | |
| TGA R/L 3033 (E) | ❍ | | ❍ | | ❍ | ❍ | | | | | – | – | – | – | 0,33 | 0,8 | 0,5 | 1,0 | 0,05 | 9,525 | 3,18 | ❶ |
| TGA R/L 3050 (E) | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | | | | – | – | – | – | 0,50 | 1,2 | 0,8 | 1,4 | | | | |
| TGA R/L 3075 (E) | ❍ | ❍ | ❍ | | ❍ | ❍ | | | | | | | | | 0,75 | 2,0 | 1,5 | 2,5 | 0,1 (T1500A 0,2) | | | |
| R/L 3095 (E) | ❍ | ❍ | | | ❍ | ❍ | | | | | | | | | 0,95 | | | | | | | |
| R/L 3100 (E) | ❍ | ❍ | ❍ | ❍ | ❍ | ❍ | ❍ | | ❍ | ❍ | | | | | 1,00 | | | | | | | |
| R/L 3110 (E) | ❍ | ❍ | | | ❍ | ❍ | | | | | | | | | 1,10 | | | | | | | |
| R/L 3125 (E) | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | | ❍ | ❍ | | | | | 1,25 | | | | | | | |
| R/L 3135 (E) | ❍ | ❍ | | | ❍ | ❍ | ❍ | | ❍ | | | | | | 1,35 | | | | | | | |
| R/L 3145 (E) | ❍ | ❍ | ❍ | | ❍ | ❍ | | | | | | | | | 1,45 | | | | | | | |
| R/L 3150 (E) | ❍ | ❍ | ❍ | | ❍ | ❍ | | | | | | | | | 1,50 | | | | | | | |
| R/L 3165 (E) | ❍ | ❍ | | | ❍ | ❍ | | | | | | | | | 1,65 | | | | | | | |
| R/L 3175 (E) | ❍ | ❍ | | | ❍ | ❍ | ❍ | | | | | | | | 1,75 | | | | | | | |
| R/L 3185 (E) | ❍ | ❍ | | | ❍ | ❍ | | | | | | | | | 1,85 | | | | | | | |
| TGA R/L 3200 (E) | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | 2,00 | 2,5 | 2,0 | 3,0 | | | | |
| R/L 3220 (E) | | ❍ | | | ❍ | ❍ | | | | | | | | | 2,20 | | | | | | | |
| R/L 3230 (E) | | | | | ❍ | ❍ | | | | | | | | | 2,30 | | | | | | | |
| R/L 3250 (E) | ❍ | | ❍ | | ❍ | ❍ | | | | | | | | | 2,50 | | | | | | | |
| R/L 3265 (E) | | | | | ❍ | ❍ | | | | | | | | | 2,65 | | | | | | | |
| R/L 3270 (E) | | | | | ❍ | ❍ | | | | | | | | | 2,70 | | | | | | | |
| R/L 3280 (E) | ❍ | | | | ❍ | ❍ | | | | | | | | | 2,80 | | | | | | | |
| TGA R/L 4125 (E) | ❍ | ❍ | | | ❍ | ❍ | | | | | ❑ | | ❍ | | 1,25 | 2,0 | 1,7 | 2,5 | 0,2 *2 | 12,70 | 4,76 | ❷ |
| R/L 4145 (E) | ❍ | ❍ | | | ❍ | ❍ | | | | | | | | | 1,45 | | | | | | | |
| TGA R/L 4150 (E) | ❍ | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | ❍ | | ❍ | | 1,50 | 3,5 | 2,5 | 3,9 | | | | ❸ |
| R/L 4165 (E) | | ❍ | | | ❍ | ❍ | | | | | | | | | 1,65 | | | | | | | |
| R/L 4175 (E) | | | | | ❍ | ❍ | | | | | | | | | 1,75 | | | | | | | |
| R/L 4185 (E) | | ❍ | ❍ | ❍ | ❍ | ❍ | | | | | | | | | 1,85 | | | | | | | |
| R/L 4200 (E) | ❍ | ❍ | | | ❍ | ❍ | | | | | ❍ | | ❍ | | 2,00 | | | | | | | |
| R/L 4220 (E) | | ❍ | | | ❍ | ❍ | | | | | | | | | 2,20 | | | | | | | |
| R/L 4230 (E) | ❍ | ❍ | | | ❍ | ❍ | | | | | | | | | 2,30 | | | | | | | |
| TGA R/L 4250 (E) | ❍ | | ❍ | | ❍ | ❍ | | | ❍ | | ❍ | | | | 2,50 | 5,0 *1 | 2,5 | 5,4 *1 | 0,3 *2 | | | ❹ |
| R/L 4265 (E) | ❍ | | ❍ | | ❍ | ❍ | | | | | | | | | 2,65 | | | | | | | |
| R/L 4270 (E) | | | | | ❍ | ❍ | | | | | | | | | 2,70 | | | | | | | |
| R/L 4280 (E) | ❍ | | | | ❍ | ❍ | | | | | | | | | 2,80 | | | | | | | |
| R/L 4300 (E) | ❍ | ❍ | | | ❍ | ❍ | | | ❍ | | ❍ | | ❍ | | 3,00 | | | | | | | |
| R/L 4320 (E) | | | | | ❍ | ❍ | | | | | | | | | 3,20 | | | | | | | |
| R/L 4330 (E) | ❍ | | | | ❍ | ❍ | | | | | | | | | 3,30 | | | | | | | |
| TGA R/L 4350 (E) | ❍ | | | | ❍ | ❍ | | | | | ❑ | | | | 3,50 | 5,0 | 2,5 | 5,4 | | | | |
| R/L 4370 (E) | | | | | ❍ | ❍ | | | | | | | | | 3,70 | | | | | | | |
| R/L 4390 (E) | | | | | ❍ | ❍ | | | | | | | | | 3,90 | | | | | | | |
| R/L 4400 (E) | ❍ | | | | ❍ | ❍ | | | | | ❍ | | ❑ | | 4,00 | | | | 0,4 *2 | | | |
| R/L 4410 (E) | | | | | ❍ | ❍ | | | | | | | | | 4,10 | | | | | | | |
| R/L 4420 (E) | | | | | ❍ | ❍ | | | | | | | | | 4,20 | | | | | | | |
| R/L 4430 (E) | | | | | ❍ | ❍ | | | | | | | | | 4,30 | | | | | | | |
| R/L 4440 (E) | | | | | ❍ | ❍ | | | | | | | | | 4,40 | | | | | | | |
| R/L 4450 (E) | | | ❍ | | ❍ | ❍ | | | | | | | | | 4,50 | | | | | | | |
| R/L 4480 (E) | | | | | ❍ | ❍ | | | | | | | | | 4,80 | | | | | | 5,00 | |

* See the group numbers of GWC, GWCS and GWCI types on page F46 and F47 to find applicable holders. Inserts and holders that have corresponding group numbers can be used together.

*1: CDX for SUMIBORON and SUMIDIA = 4,4, maximum groove depth 4,0 (2,5 during internal machining)
*2: RE for SUMIBORON = 0,2, RE for SUMIDIA = 0,1


Grooving & Parting-Off



❍ = Japan stock

❑ = Delivery on request

## Round Edged Grooving Insert




This figure shows right handed tools.

| Grade | | Cutting Edge | GAN |
|---|---|---|---|
| Coated Carbide | AC530U | Honing | 15° |
| Carbide | H1 | Sharp | 25° |
| Coated Cermet | T2500Z, T3000Z | Honing | 15° |
| Cermet | T1500A | Sharp | 10° |
| SUMIBORON | BN2000 | K-Land | 5° |
| SUMIDIA | DA2200 | Sharp | 15° |

* See page F47 for the rake angle with a holder fitted.

Dimensions (mm)

| Cat. No. | AC530U | | H1 | | T2500Z | | T3000Z | | T1500A | | BN2000 | | DA2200 | | CW | Max. Groove Depth | | CDX | RE | IC | S | Insert /Holder Group No.* |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | R | L | R | L | R | L | R | L | R | L | R | L | | External | Internal | | | | | |
| TGA R/L 4050 R | ❍ | ❍ | | | ❍ | | | | | | | | | | 1,00 | 2,0 | 1,7 | 2,5 | 0,50 | 12,70 | 4,76 | ❷ |
| TGA R/L 4075 R | ❍ | ❍ | | | ❍ | | | | | | | | | | 1,50 | 3,5 | 2,5 | 3,9 | 0,75 | | | ❸ |
| R/L 4100 R | ❍ | ❍ | | | ❍ | | | | | | | | | | 2,00 | | | | 1,00 | | | |
| TGA R/L 4125 R | ❍ | ❍ | | | ❍ | | | | | | | | | | 2,50 | 5,0 *1 | 2,5 | 5,4 *1 | 1,25 | | | ❹ |
| R/L 4150 R | ❍ | ❍ | | | ❍ | | ❍ | | | | | | ❑ | | 3,00 | | | | 1,50 | | | |
| R/L 4200 R | ❍ | | | | ❍ | | | | | | | | | | 4,00 | | | | 2,00 | | | |

* See the group numbers of GWC, GWCS and GWCI types on page F46 and F47 to find applicable holders. Inserts and holders that have corresponding group numbers can be used together.

*1 CDX for SUMIBORON and SUMIDIA = 4,4, maximum groove depth 4,0 (2,5 during internal machining)

## Recommended Cutting Conditions

| Work Material | P General Steel | | | M Stainless Steel | | | N Non-Ferrous Metal | | H Hardened Steel |
|---|---|---|---|---|---|---|---|---|---|
| Grade | AC530U | T2500Z, T3000Z | T1500A | AC530U | T2500Z, T3000Z | T1500A | H1 | DA2200 | BN2000 |
| Cutting Speed (m/min) | 50–200 | 100–180 | 100–180 | 50–200 | 80–150 | 80–120 | 200–300 | 200–300 | 80–120 |
| Feed Rate (mm/rev) | 0,02–0,10 | 0,05–0,10 | 0,05–0,08 | 0,02–0,10 | 0,05–0,08 | 0,05–0,08 | 0,05–0,15 | 0,05–0,15 | 0,03–0,07 |

## Insert Blanks

(Incomplete products. Machine them to meet your edge width, nose radius and rake angle requirements.)

Fig. 1






Fig. 2




This figure shows right handed tools.

Dimensions (mm)

| Cat. No. | KH03 | | H1 | | EH510 | | T1500A | | CW | CDX | IC | S | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | R | L | R | L | R | L | | | | | |
| TGA R/L 3 T18 | | | | | | | | | 1,85 | (3,4) | 9,525 | 3,18 | 1 |
| R/L 3 T23 | | | | | | | ❍ | ❍ | 2,35 | (3,4) | | | |
| R/L 3 T31 | ❍ | | | | | | | | 3,18 | – | | | 2 |
| TGA R/L 4 T22 | | | | | | | | | 2,20 | (4,8) | 12,70 | 4,76 | 1 |
| R/L 4 T37 | | | | | | | | | 3,75 | (6,2) | | | |
| R/L 4 T47 | ❍ | | | | | | ❍ | | 4,76 | – | | | 2 |


Note: CDX values in parentheses are for reference only.

## Notes for Machining an Insert

Make the cutting edge so that the rake angle, back taper, etc. as shown in fig. 3. When you have installed an insert into a holder, it becomes a cutting blade element as shown in fig. 4.


Suggested Shape

Fig. 3




Cutting blade element during holder installation

Fig. 4



# SCT Type









Fig. 1






Fig. 2




Above figures show right hand tools.

## Spare Parts


















## Holders

| Cat. No. | Stock | Dimensions (mm) H | B | LF | WF | HF | LH | Applicable inserts | Fig. | Screw | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|
| SCT R 1010 | ● | 10 | 10 | 120 | 10 | 10 | 15 | CT R05_ _ _ CT R12_ _ _ | 1 | BFTX0410T8L | TRX 08 |
| SCT R 1212 | ● | 12 | 12 | 120 | 12 | 12 | 15 | | | | |
| SCT R 1616 | ● | 16 | 16 | 120 | 16 | 16 | 15 | | | | |
| SCT R 101016 | ❍ | 10 | 10 | 120 | 10 | 10 | 18 | CT R16_ _ _ | 2 | | |
| SCT R 121216 | ❍ | 12 | 12 | 120 | 12 | 12 | 18 | | | | |
| SCT R 161616 | ❍ | 16 | 16 | 120 | 16 | 16 | 18 | | 1 | | |
| SCT L 1010 | ● | 10 | 10 | 120 | 10 | 10 | 15 | CT L05 _ _ _ CT L12 _ _ _ | 1 | BFTX0410T8R | |
| SCT L 1212 | ● | 12 | 12 | 120 | 12 | 12 | 15 | | | | |
| SCT L 1616 | ● | 16 | 16 | 120 | 16 | 16 | 15 | | | | |
| SCT L 101016 | ❍ | 10 | 10 | 120 | 10 | 10 | 18 | CT L16 _ _ _ | 2 | | |
| SCT L 121216 | ❍ | 12 | 12 | 120 | 12 | 12 | 18 | | | | |
| SCT L 161616 | ❍ | 16 | 16 | 120 | 16 | 16 | 18 | | 1 | | |

## Inserts

| | For Right Handed Holder (SCTR) | | | For Left Handed Holder (SCTL) | | |
|---|---|---|---|---|---|---|
| | CTR _ _ R | CTR _ _ N | CTR _ _ L | CTL _ _ R | CTL _ _ N | CTL _ _ L |
| Installation Conditions for Holder |   |  |   |   |  |   |
| Insert Shape and Dimensions |   |   |   |   |   |   |

| Cat. No. | AC1030U R | N | L | AC530U R | N | L | Max. Cut-Off Ø (mm) | CW | RE | L | S | Chip Breaker | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| CTR 050505 R/N/L | ❍ | | ❍ | ❍ | ❍ | ❍ | 5 | 0,5 | 0,05 | 19 | 7 | With Chip Breaker | SCT R1010 SCT R1212 SCT R1616 |
| 050500 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 5 | | 0 | | | | |
| CTR 121005 R/N/L | ❍ | ❍ | ❍ | ❍ | ❍ | ❍ | 12 | 1,0 | | | | | |
| 121505 R/N/L | ● | ● | ❍ | ❍ | ❍ | ❍ | 12 | 1,5 | 0,05 | | | | |
| 122005 R/N/L | ● | ● | | ❍ | ❍ | | 12 | 2,0 | | | | | |
| 121000 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 12 | 1,0 | | | | | |
| 121500 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 12 | 1,5 | 0 | | | | |
| 122000 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 12 | 2,0 | | | | | |
| CTR 161005 R/N/L | | | | | | | 16 | 1,0 | | 23,1 | 8,3 | | SCT R101016 SCT R121216 SCT R161616 |
| 161505 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 16 | 1,5 | 0,05 | | | | |
| 162005 R/N/L | ❍ | ❍ | ❍ | ❍ | ❍ | ❍ | 16 | 2,0 | | | | | |
| 161000 R/N/L | | | | | | | 16 | 1,0 | | | | | |
| 161500 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 16 | 1,5 | 0 | | | | |
| 162000 R/N/L | ❍ | ❍ | ❍ | ❍ | ❍ | ❍ | 16 | 2,0 | | | | | |
| CTR 050500 R/N/L NB | | | | | | | 5 | 0,5 | 0 | 19 | 7 | Without Chip Breaker | SCT R1010 SCT R1212 SCT R1616 |
| CTR 121000 R/N/L NB | ❍ | | | ❍ | | | 12 | 1,0 | | | | | |
| 121500 R/N/L NB | ❍ | | | ❍ | | | 12 | 1,5 | | | | | |
| 122000 R/N/L NB | ❍ | | | ❍ | | | 12 | 2,0 | | | | | |
| CTR 161000 R/N/L NB | | | | | | | 16 | 1,0 | | 23,1 | 8,3 | | SCT R101016 SCT R121216 SCT R161616 |
| 161500 R/N/L NB | | | | | | | 16 | 1,5 | | | | | |
| 162000 R/N/L NB | ❍ | | | ❍ | | | 16 | 2,0 | | | | | |
| CTL 050505 R/N/L | ❍ | | | ❍ | ❍ | | 5 | 0,5 | 0,05 | 19 | 7 | With Chip Breaker | SCT R1010 SCT R1212 SCT R1616 |
| 050500 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 5 | | 0 | | | | |
| CTL 121005 R/N/L | ❍ | ❍ | ● | ❍ | ❍ | ❍ | 12 | 1,0 | | | | | |
| 121505 R/N/L | ❍ | ❍ | ● | ❍ | ❍ | ❍ | 12 | 1,5 | 0,05 | | | | |
| 122005 R/N/L | ❍ | ● | | ❍ | ❍ | | 12 | 2,0 | | | | | |
| 121000 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 12 | 1,0 | | | | | |
| 121500 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 12 | 1,5 | 0 | | | | |
| 122000 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 12 | 2,0 | | | | | |
| CTL 161005 R/N/L | | | | | | | 16 | 1,0 | | 23,1 | 8,3 | | SCT R101016 SCT R121216 SCT R161616 |
| 161505 R/N/L | ❍ | ❍ | | | ❍ | | 16 | 1,5 | 0,05 | | | | |
| 162005 R/N/L | ❍ | ❍ | ❍ | ❍ | ❍ | ❍ | 16 | 2,0 | | | | | |
| 161000 R/N/L | | | | | | | 16 | 1,0 | | | | | |
| 161500 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 16 | 1,5 | 0 | | | | |
| 162000 R/N/L | ❍ | ❍ | | ❍ | ❍ | | 16 | 2,0 | | | | | |




Wide groove breaker for smooth chip evacuation

## Surface Finish Comparison




| | |
|---|---|
| Work Material: | X6Cr17 ( ø8 mm) |
| Insert: | CTR 121005 R, ( b =1,0 mm) |
| Cutting Data: | $v_c$ = 45 m/min |
| | f = 0,02 mm/rev, wet |





● = Euro stock
○ = Japan stock




## Characteristics

- Holders available in carbide (SumiGrip) and steel (SumiGrip JR).
- Capable on interrupted machining.
- Can be used for cut-off, grooving and chamfering applications.


## Type

- Tool block type
  STFH (steel) / WCFH (carbide)
- Shank type
  STFS (steel) / WCFS (carbide)


## Cut-Off





## Features of Design




## Twice the Insert Holding Force





## Low Vibration




Work Material: C45 (Ø 50 mm, 250 HB)
Insert: 3 mm width, coated carbide
Cutting Conditions: $v_c$ = 80 m/min, dry

## Wear Resistance




Work Material: C45 (hexagonal)
Insert: 3 mm width, coated carbide
Cutting Conditions: $v_c$ = 150 m/min, f = 0,15 mm/rev, wet (water soluble)

## GG Type/GF Type/CF Type Chipbreaker, Grade AC1030U

Utilizing grooving tool GND type chipbreaker series for excellent chip control.
Low cutting force chipbreaker GF type (neutral) or CF type (left or right handed) inserts, coupled with a carbide blade, enables stable machining and prevents chattering even when machining stainless steel.
Achieving stable and longer tool life with the new AC1030U grade.

| GG | GF | CF |
|---|---|---|
|  Neutral |  Neutral |  L/R handed |
| General purpose | Exotic alloy, Low cutting force | Exotic alloy, Low cutting force |

## Performance (Chipbreaker)

Chip Control Capability


GF


GG



Conventional


Work Material: X5CrMo17 12 2 (Ø 40 mm)
Cutting Conditions: $v_c$ = 100 m/min, f = 0,1 mm/rev, wet

# Sumi-Grip Jr.

## Cut-Off (Steel Holder/Tool Block Type)

**STFH**
Cut-Off






Above figures show right hand tools.

### Holders


| Cat. No. | Stock | Dimensions (mm) H | B | LF | HF | LF2 | CW | Max. Cut-Off Dia. | Applicable Inserts | Applicable Tool Blocks | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|
| STFH 26-2 | ● | 26 | 1,6 | 109 | 21,4 | 108 | 2,0 | 40 | WCF _ 2 _ | | |
| 26-3 | ● | 26 | 2,4 | 109 | 21,4 | 108 | 3,0 | 70 | WCF _ 3 _ | SBN 20-26 | |
| 26-4 | ● | 26 | 3,4 | 109 | 21,4 | 108 | 4,0 | 70 | WCF _ 4 _ | SBU 20-26 | |
| 26-5 | ● | 26 | 4,3 | 109 | 21,4 | 108 | 5,0 | 70 | WCF _ 5 _ | | |
| STFH 32-2 | ● | 32 | 1,6 | 149 | 25,0 | 148 | 2,0 | 40 | WCF _ 2 _ | SBN 20-32 | SL 4 |
| 32-3 | ● | 32 | 2,4 | 149 | 25,0 | 148 | 3,0 | 100 | WCF _ 3 _ | SBN 25-32 | |
| 32-4 | ● | 32 | 3,4 | 149 | 25,0 | 148 | 4,0 | 100 | WCF _ 4 _ | SBU 20-32 | |
| 32-5 | ● | 32 | 4,3 | 149 | 25,0 | 148 | 5,0 | 100 | WCF _ 5 _ | SBU 25-32 | |

### Parts



### Tool Blocks

SBN Type, One piece type





| Cat. No. | Stock | Dimensions (mm) H | Ha | Hb | Hc | L | Applicable Carbide Blades |
|---|---|---|---|---|---|---|---|
| SBN 20-26 | ● | 45 | 20 | 20 | 10,0 | 80 | STFH 26_ |
| SBN 20-32 | ● | 50 | 20 | 20 | 13,5 | 100 | STFH 32_ |
| SBN 25-26 | ❑ | 48 | 25 | 25 | 10,0 | 80 | STFH 26_ |
| SBN 25-32 | ● | 50 | 25 | 25 | 8,5 | 110 | STFH 32_ |

### Parts

| Clamp | Screw | Wrench |
|---|---|---|
|  |  |  |
| BWS 30 | WB 8-20 | LH 040 |

SBU Type, Separate type




| Cat. No. | Stock | Dimensions (mm) H | Ha | Hb | Hc | L | Applicable Carbide Blades |
|---|---|---|---|---|---|---|---|
| SBU 20-26 | ● | 45 | 20 | 20 | 10,0 | 80 | STFH 26_ |
| SBU 20-32 | ● | 50 | 20 | 20 | 13,5 | 100 | STFH 32_ |
| SBU 25-26 | ❑ | 48 | 25 | 25 | 10,0 | 80 | STFH 26_ |
| SBU 25-32 | ● | 50 | 25 | 25 | 8,5 | 110 | STFH 32_ |


| Wedge | | |
|---|---|---|
|  20-26 SBU 25-26 |  SBU20-32 |  SBU25-32 |
| BCS 15 | BCS 20 | BCS 25 |


| Screw | Wrench | |
|---|---|---|
|  |  | |
| BX 0622 | LH 050 | |

*Tool blocks selection guide see page F46

## Cut-Off (Steel Holder/Shank Type)

**STFS**
Cut-Off






### Holders

| Cat. No. | Stock R | L | Dimensions (mm) H | B | LF | WF | HF | LH | LH2 | CW | Max. Cut-Off Dia. | Applicable Inserts | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| STFS R/L 1010-2 | ❍ | | 10 | 10 | 86 | 10 | 10 | 17 | 17 | 2,0 | 28 | | |
| R/L 1212-2 | ● | ● | 12 | 12 | 110 | 12 | 12 | 18 | 18 | 2,0 | 30 | WCF _ 2 _ | |
| R/L 1616-2 | ● | ❍ | 16 | 16 | 110 | 16 | 16 | – | 19 | 2,0 | 32 | | |
| R/L 2020-2 | ● | ❍ | 20 | 20 | 125 | 20 | 20 | – | 24 | 2,0 | 40 | | |
| STFS R/L 1616-3 | ● | ❍ | 16 | 16 | 110 | 16 | 16 | 20 | 22 | 3,0 | 35 | | |
| R/L 2012-3 | ❍ | | 20 | 12 | 110 | 12 | 20 | – | 24 | 3,0 | 40 | WCF _ 3 _ | SL 4 |
| R/L 2020-3 | ● | ● | 20 | 20 | 125 | 20 | 20 | – | 30 | 3,0 | 50 | | |
| R/L 2525-3 | ● | ● | 25 | 25 | 150 | 25 | 25 | – | 30 | 3,0 | 50 | | |
| STFS R/L 2020-4 | ● | ● | 20 | 20 | 125 | 20 | 20 | – | 33 | 4,0 | 55 | WCF _ 4 _ | |
| R/L 2525-4 | ● | | 25 | 25 | 150 | 25 | 25 | – | 38 | 4,0 | 65 | | |
| STFS R/L 2020-5 | ❍ | | 20 | 20 | 125 | 20 | 20 | – | 35 | 5,0 | 60 | WCF _ 5 _ | |
| R/L 2525-5 | ❍ | ❍ | 25 | 25 | 150 | 25 | 25 | – | 40 | 5,0 | 70 | | |

### Parts









● = Euro stock
○ = Japan stock
❑ = Delivery on request

## Inserts


Neutral (N)




Right Handed (R)




Left Handed (L)




* WCF_2T: 2_RE=0,15

| External Appearance | Cat. No. | AC830P | AC225 | AC1030U | T1500A | A30 | G10E | CW | Applicable Holder | |
|---|---|---|---|---|---|---|---|---|---|---|
| WCF N _ GG<br>General purpose | WCF N2 GG | ● | | | | | | 2,0 | STFH _ _ 2 | STFS R/L _ _ _ _ 2 |
| | N3 GG | ● | | | | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | N4 GG | ● | | | | | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | N5 GG | ● | | | | | | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| WCF N _ GF<br>Exotic alloy<br>Low feed | WCF N2 GF | | | ❍ | | | | 2,0 | STFH _ _ 2 | STFS R/L _ _ _ _ 2 |
| | N3 GF | | | ❍ | | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | N4 GF | | | ❍ | | | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | N5 GF | | | ❍ | | | | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| WCF _ _ CF<br>Exotic alloy<br>Low feed | WCF R3 CF | | | ❍ | | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | L3 CF | | | ❍ | | | | 3,0 | | |
| | R4 CF | | | | | | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | L4 CF | | | ❍ | | | | 4,0 | | |
| WCF _ 2T<br>Small diameter<br>Low cutting force | WCF N2T | ● | | | | | | 2,0 | STFH _ _ 2 | STFS R/L _ _ _ _ 2 |
| | R2T | ● | | | | | | 2,0 | | |
| | L2T | ● | | | | | | 2,0 | | |
| WCF _ _<br>Without chip breaker<br>General steel | WCF N3 | ● | | | | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | R3 | ● | | | | | | 3,0 | | |
| | L3 | ● | | | | | | 3,0 | | |
| | WCF N4 | ● | | | | | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | R4 | ● | | | | | | 4,0 | | |
| | L4 | ● | | | | | | 4,0 | | |
| | WCF N5 | ● | | | | | | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| | R5 | ● | | | | | | 5,0 | | |
| | L5 | ● | | | | | | 5,0 | | |
| WCF _ _ A<br>Exotic alloy<br>Low feed | WCF N2A | | ● | | | | | 2,0 | STFH _ _ 2 | STFS R/L _ _ _ _ 2 |
| | WCF N3A | ● | ● | | ❍ | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | R3A | | ● | | | | | 3,0 | | |
| | L3A | | ● | | | | | 3,0 | | |
| | WCF N4A | ❍ | ● | | | ❍ | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | R4A | | ● | | | | | 4,0 | | |
| | L4A | | ● | | | | | 4,0 | | |
| | WCF N5A | | ● | | | | | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| | R5A | | ❍ | | | | | 5,0 | | |
| | L5A | ● | | | | | | 5,0 | | |
| WCF _ _ B<br>Cast iron<br>Light alloys<br><br>Note:<br>With the similar chip breaker style as for general steel (WCF _ _ ) but with smaller edge preparation. | WCF N3B | | | | | | ● | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | R3B | | | | | | ● | 3,0 | | |
| | L3B | | | | | | ● | 3,0 | | |
| | WCF N4B | | | | | | ● | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | R4B | | | | | | ❍ | 4,0 | | |
| | L4B | | | | | | | 4,0 | | |
| | WCF N5B | | | | | | ❍ | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| | R5B | | | | | | | 5,0 | | |
| | L5B | | | | | | | 5,0 | | |

## Recommended Cutting Conditions


| Work Material | | Cutting Speed (m/min) | | | | | |
|---|---|---|---|---|---|---|---|
| | | AC830P | AC225 | AC1030U | T1500A | A30 | G10 |
| Steel | General Steel | 80–200 | 80–200 | 50–200 | 80–200 | 50–120 | – |
| | Soft Steel | 100–230 | 100–230 | 50–230 | 100–230 | 70–150 | – |
| | Die Steel | 60–150 | 60–150 | 50–150 | 60–150 | 50–120 | – |
| Stainless Steel | | 70–150 | 70–150 | 50–150 | – | 70–130 | – |
| Cast Iron | | – | – | 50–200 | – | – | 50–120 |
| Non-Ferrous Metal | | – | – | 200–500 | – | – | 200–500 |

| Chip Breaker | | Feed Rate (mm/rev) | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | Neutral | | | | | | Left or Right Handed | | | | |
| | | GG | GF | Without Chip Breaker | T | A | B | Without Chip Breaker | CF | T | A | B |
| | | General Purpose | Exotic Alloy Low Cutting Force | General Steel | Small Diam. Low Cutting Force | Exotic Alloy Low Feed | Cast Iron Light Alloys | General Steel | Exotic Alloy Low Cutting Force | Small Diam. Low Cutting Force | Exotic Alloy Low Feed | Cast Iron Light Alloys |
| Groove Width W (mm) | **2,0** | 0,05–0,20 | 0,03–0,12 | – | 0,03–0,10 | 0,03–0,12 | – | – | – | 0,03–0,10 | – | – |
| | **3,0** | 0,08–0,25 | 0,04–0,15 | 0,08–0,25 | – | 0,04–0,15 | 0,05–0,15 | 0,08–0,25 | 0,08–0,12 | – | 0,04–0,15 | 0,05–0,15 |
| | **4,0** | 0,10–0,30 | 0,05–0,18 | 0,10–0,30 | – | 0,05–0,18 | 0,05–0,18 | 0,10–0,30 | 0,10–0,30 | – | 0,05–0,18 | 0,05–0,18 |
| | **5,0** | 0,10–0,35 | 0,05–0,20 | 0,10–0,30 | – | 0,05–0,20 | 0,06–0,20 | 0,10–0,20 | 0,10–0,30 | – | – | 0,06–0,20 |


# Sumi-Grip Series

## Cut-Off (Carbide Holder/Tool Block Type)


**WCFH**
Cut-Off



CW: 3 mm
4 mm
5 mm




CW: 2 mm




(WCFH 32-2)

Above figures show right hand tools.

### ■ Parts




### ■ Holders

| Cat. No. | Stock | Dimensions (mm) H | B | LF | HF | LF2 | CW | Max. Cut-Off Dia. | Applicable Inserts | Applicable Tool Blocks | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WCFH 26-2 | ● | 26 | 1,7 | 110 | 21,4 | 109,0 | 2,0 | 40 | WCF _ 2 _ | SBN 20-26 SBU 20-26 | SL 2 |
| 26-3 | ● | 26 | 2,4 | 110 | 21,4 | 108,5 | 3,0 | 70 | WCF _ 3 _ | | SL 1 |
| 26-4 | ● | 26 | 3,4 | 110 | 21,4 | 108,5 | 4,0 | 70 | WCF _ 4 _ | | |
| 26-5 | ● | 26 | 4,3 | 110 | 21,4 | 108,5 | 5,0 | 70 | WCF _ 5 _ | | |
| WCFH 32-2 | ● | 32 | 1,7 | 150 | 25,0 | 149,0 | 2,0 | 40 | WCF _ 2 _ | SBN 20-32 SBN 25-32 SBU 20-32 SBU 25-32 | SL 2 |
| 32-3 | ● | 32 | 2,4 | 150 | 25,0 | 148,5 | 3,0 | 100 | WCF _ 3 _ | | SL 1 |
| 32-4 | ● | 32 | 3,4 | 150 | 25,0 | 148,5 | 4,0 | 100 | WCF _ 4 _ | | |
| 32-5 | ● | 32 | 4,3 | 150 | 25,0 | 148,5 | 5,0 | 100 | WCF _ 5 _ | | |

See F48 for applicable inserts.

### ■ Tool Blocks

SBN Type, Mono-block Type





| Cat. No. | Stock | Dimensions (mm) H | Ha | Hb | Hc | L | Applicable Carbide Blades |
|---|---|---|---|---|---|---|---|
| SBN 20-26 | ● | 45 | 20 | 20 | 10,0 | 80 | WCFH 26_ |
| SBN 20-32 | ● | 50 | 20 | 20 | 13,5 | 100 | WCFH 32_ |
| SBN 25-26 | ❑ | 48 | 25 | 25 | 10,0 | 80 | WCFH 26_ |
| SBN 25-32 | ● | 50 | 25 | 25 | 8,5 | 110 | WCFH 32_ |

### ■ Parts

| Clamp | Screw | Wrench |
|---|---|---|
|  |  |  |
| BWS 30 | WB 8-20 | LH 040 |

SBU Type, Separate Type




| Cat. No. | Stock | Dimensions (mm) H | Ha | Hb | Hc | L | Applicable Carbide Blades |
|---|---|---|---|---|---|---|---|
| SBU 20-26 | ● | 45 | 20 | 20 | 10,0 | 80 | WCFH 26_ |
| SBU 20-32 | ● | 50 | 20 | 20 | 13,5 | 100 | WCFH 32_ |
| SBU 25-26 | ❑ | 48 | 25 | 25 | 10,0 | 80 | WCFH 26_ |
| SBU 25-32 | ● | 50 | 25 | 25 | 8,5 | 110 | WCFH 32_ |


| Wedge | | |
|---|---|---|
|   |   |   |
| BCS 15 | BCS 20 | BCS 25 |

| Screw | Wrench | |
|---|---|---|
|  |  | |
| BX 0622 | LH 050 | |

### ■ Tool Block Type Selection Guide

**Tool Block (Mono-Block Type)**


SBN Type



This tool block can be used for the machining tool post **A** shown on the right.


**Tool Block (Separate Type)**

SBU Type




This tool block can be used for the machining tool posts **A** and **B** shown on the right.
Since the clamp is large it has a large scope even when the holder has a long overhang.

**A** General Purpose Lathe, etc.
SBN Type, SBU Type




(Overhead clamp)

**B** Turret Type Tool Post, etc.
SBU Type




(Side clamp)





● = Euro stock
○ = Japan stock

❑ = Delivery on request

## Cut-Off (Carbide Holder/Shank Type)

**WCFS**
Cut-Off






Above figures show right hand tools.

### ■ Holders

| Cat. No. | | Stock R | Stock L | Dimensions (mm) H | B | LF | WF | HF | LH | CW | Max. Cut-Off Dia. | Applicable Blades | Applicable Inserts | Fig. | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Brazed Type | WCFS R/L 1010-2 | ● | | 10 | 10 | 86 | 10 | 10 | 10 | 2,0 | 28 | – | WCF _ 2 _ | 1 | SL 2 |
| | R/L 1212-2 | ● | | 12 | 12 | 110 | 12 | 12 | 18 | 2,0 | 30 | – | WCF _ 2 _ | 1 | |
| | R/L 1616-2 | ❍ | ❍ | 16 | 16 | 100 | 16 | 16 | 25 | 2,0 | 35 | – | WCF _ 2 _ | 2 | |
| | R/L 1616-3 | | | 16 | 16 | 100 | 16 | 16 | 25 | 3,0 | 35 | – | WCF _ 3 _ | 2 | SL 1 |
| Clamp Type | WCFS R/L 20-3 | ● | ● | 20 | 20 | 125 | 23 | 20 | 46 | 3,0 | 50 | WCFH17-3 | WCF _ 3 _ | 3 | SL 1 |
| | R/L 20-4 | ● | | 20 | 20 | 125 | 24 | 20 | 46 | 4,0 | 50 | WCFH17-4 | WCF _ 4 _ | 3 | |
| | R/L 20-5 | ❍ | | 20 | 20 | 125 | 25 | 20 | 46 | 5,0 | 50 | WCFH17-5 | WCF _ 5 _ | 3 | |
| | WCFS R/L 25-3 | ● | | 25 | 25 | 150 | 28 | 25 | 46 | 3,0 | 50 | WCFH17-3 | WCF _ 3 _ | 4 | |
| | R/L 25-4 | | ❍ | 25 | 25 | 150 | 29 | 25 | 46 | 4,0 | 50 | WCFH17-4 | WCF _ 4 _ | 4 | |
| | R/L 25-5 | | | 25 | 25 | 150 | 30 | 25 | 46 | 5,0 | 50 | WCFH17-5 | WCF _ 5 _ | 4 | |


See F48 for applicable inserts.

Blade included in holder.

### ■ Parts



### ■ Blades




| Cat. No. | Stock | Dimensions (mm) CW | Dimensions (mm) B | Applicable Blades |
|---|---|---|---|---|
| WCFH 17-3 | ● | 3 | 2,4 | WCFS R/L 20-3, 25-3 |
| WCFH 17-4 | ❍ | 4 | 3,4 | WCFS R/L 20-4, 25-4 |
| WCFH 17-5 | | 5 | 4,3 | WCFS R/L 20-5, 25-5 |

### ■ Parts





| Cap Screw | Wrench | Applicable Holders |
|---|---|---|
| BX0622 | LH050 | All clamp type holders. |


# Sumi-Grip Inserts

## Inserts


Neutral (N)




Right Handed (R)




Left Handed (L)




* WCF_2T: 2_RE=0,15

| External Appearance | Cat. No. | AC830P | AC225 | AC1030U | T1500A | A30 | G10E | CW | Applicable Holder | |
|---|---|---|---|---|---|---|---|---|---|---|
| WCF N _ GG<br>General purpose | WCF N2 GG | ● | | | | | | 2,0 | STFH _ _ 2 | STFS R/L _ _ _ _ 2 |
| | N3 GG | ● | | | | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | N4 GG | ● | | | | | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | N5 GG | ● | | | | | | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| WCF N _ GF<br>Exotic alloy<br>Low feed | WCF N2 GF | | | ❍ | | | | 2,0 | STFH _ _ 2 | STFS R/L _ _ _ _ 2 |
| | N3 GF | | | ❍ | | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | N4 GF | | | ❍ | | | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | N5 GF | | | ❍ | | | | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| WCF _ _ CF<br>Exotic alloy<br>Low feed | WCF R3 CF | | | ❍ | | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | L3 CF | | | ❍ | | | | 3,0 | | |
| | R4 CF | | | | | | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | L4 CF | | | ❍ | | | | 4,0 | | |
| WCF _ 2T<br>Small diameter<br>Low cutting force | WCF N2T | ● | | | | | | 2,0 | STFH _ _ 2 | STFS R/L _ _ _ _ 2 |
| | R2T | ● | | | | | | 2,0 | | |
| | L2T | ● | | | | | | 2,0 | | |
| WCF _ _<br>Without chip breaker<br>General steel | WCF N3 | ● | | | | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | R3 | ● | | | | | | 3,0 | | |
| | L3 | ● | | | | | | 3,0 | | |
| | WCF N4 | ● | | | | | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | R4 | ● | | | | | | 4,0 | | |
| | L4 | ● | | | | | | 4,0 | | |
| | WCF N5 | ● | | | | | | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| | R5 | ● | | | | | | 5,0 | | |
| | L5 | ● | | | | | | 5,0 | | |
| WCF _ _ A<br>Exotic alloy<br>Low feed | WCF N2A | | ● | | | | | 2,0 | STFH _ _ 2 | STFS R/L _ _ _ _ 2 |
| | WCF N3A | ● | ● | | ❍ | | | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | R3A | | ● | | | | | 3,0 | | |
| | L3A | | ● | | | | | 3,0 | | |
| | WCF N4A | ❍ | ● | | | ❍ | | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | R4A | | ● | | | | | 4,0 | | |
| | L4A | | ● | | | | | 4,0 | | |
| | WCF N5A | | ● | | | | | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| | R5A | | ❍ | | | | | 5,0 | | |
| | L5A | ● | | | | | | 5,0 | | |
| WCF _ _ B<br>Cast iron<br>Light alloys<br><br>Note:<br>With the similar chip breaker style as for general steel (WCF _ _ ) but with smaller edge preparation. | WCF N3B | | | | | | ● | 3,0 | STFH _ _ 3 | STFS R/L _ _ _ _ 3 |
| | R3B | | | | | | ● | 3,0 | | |
| | L3B | | | | | | ● | 3,0 | | |
| | WCF N4B | | | | | | ● | 4,0 | STFH _ _ 4 | STFS R/L _ _ _ _ 4 |
| | R4B | | | | | | ❍ | 4,0 | | |
| | L4B | | | | | | | 4,0 | | |
| | WCF N5B | | | | | | ❍ | 5,0 | STFH _ _ 5 | STFS R/L _ _ _ _ 5 |
| | R5B | | | | | | | 5,0 | | |
| | L5B | | | | | | | 5,0 | | |

## Recommended Cutting Conditions

| Work Material | | Cutting Speed (m/min) | | | | | |
|---|---|---|---|---|---|---|---|
| | | AC830P | AC225 | AC1030U | T1500A | A30 | G10 |
| Steel | General Steel | 80–200 | 80–200 | 50–200 | 80–200 | 50–120 | – |
| | Soft Steel | 100–230 | 100–230 | 50–230 | 100–230 | 70–150 | – |
| | Die Steel | 60–150 | 60–150 | 50–150 | 60–150 | 50–120 | – |
| Stainless Steel | | 70–150 | 70–150 | 50–150 | – | 70–130 | – |
| Cast Iron | | – | – | 50–200 | – | – | 50–120 |
| Non-Ferrous Metal | | – | – | 200–500 | – | – | 200–500 |

| Chip Breaker | | Feed Rate (mm/rev) | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | Neutral | | | | | | Left or Right Handed | | | | |
| | | GG | GF | Without Chip Breaker | T | A | B | Without Chip Breaker | CF | T | A | B |
| | | General Purpose | Exotic Alloy Low Cutting Force | General Steel | Small Diam. Low Cutting Force | Exotic Alloy Low Feed | Cast Iron Light Alloys | General Steel | Exotic Alloy Low Cutting Force | Small Diam. Low Cutting Force | Exotic Alloy Low Feed | Cast Iron Light Alloys |
| Groove Width W (mm) | **2,0** | 0,05–0,20 | 0,03–0,12 | – | 0,03–0,10 | 0,03–0,12 | – | – | – | 0,03–0,10 | – | – |
| | **3,0** | 0,08–0,25 | 0,04–0,15 | 0,08–0,25 | – | 0,04–0,15 | 0,05–0,15 | 0,08–0,25 | 0,08–0,12 | – | 0,04–0,15 | 0,05–0,15 |
| | **4,0** | 0,10–0,30 | 0,05–0,18 | 0,10–0,30 | – | 0,05–0,18 | 0,05–0,18 | 0,10–0,30 | 0,10–0,30 | – | 0,05–0,18 | 0,05–0,18 |
| | **5,0** | 0,10–0,35 | 0,05–0,20 | 0,10–0,30 | – | 0,05–0,20 | 0,06–0,20 | 0,10–0,20 | 0,10–0,30 | – | – | 0,06–0,20 |





● = Euro stock
○ = Japan stock

# SSTE / SSTI Type

New



## Features

- High-precision inserts with/without wiper flat for threading, supporting a wide range of applications from general industrial machinery to pipes and aerospace devices
- Stable chip control through use of a 3D molded chipbreaker.
- Ground cutting edge flank for improved cutting edge sharpness, resulting in high quality threads




Ground flanks around cutting edge

## Product Range

| Applications | Type | Wiper Flat | External/ Internal | Pitch (mm) | TPI (Threads/Inch) 48 36 32 28 27 24 20 19 18 16 14 13 12 11.5 11 10 8 | Insert Cat. No. Example: |
|---|---|---|---|---|---|---|
| General Industrial Use | 60° General-purpose Thread | No | External | 0.5 – 3.0 | 48 to 8 | 16ER A60-CB |
| | | | Internal | 0.5 – 3.0 | 48 to 8 | 16IR A60-CB |
| | 55° General-purpose Thread | | External | | 48 to 8 | 16ER A55-CB |
| | | | Internal | | 48 to 8 | 16IR A55-CB |
| | 60° ISO Metric Thread | Yes | External | 0.75 1.0 1.25 1.5 1.75 2.0 2.5 3.0 | | 16ER 075ISO-CB |
| | | | Internal | 0.75 1.0 1.25 1.5 1.75 2.0 2.5 3.0 | | 16IR 075ISO-CB |
| | 60° Unified Thread | | External | | | 16ER 32UN-CB |
| | | | Internal | | | 16IR 32UN-CB |
| Pipe Coupling for Gas, Water and Water Faucets | 55° Parallel Thread for Pipe/ Whitworth | | External | | | 16ER 36W-CB |
| | | | Internal | | | 16IR 28W-CB |
| | 60° American NPT | | External | | | 16ER 27NPT-CB |
| | | | Internal | | | 16IR 27NPT-CB |
| Steam, Gas and Water Supply Pipes | 55° Taper Thread for Pipe BSPT | | External | | | 16ER 28BSPT-CB |
| | | | Internal | | | 16IR 28BSPT-CB |
| | 60° American NPTF | | External | | | 16ER 27NPTF-CB |
| | | | Internal | | | 16IR 27NPTF-CB |
| For Aerospace Equipment | UNJ 60° | | External | | | 16ER 32UNJ-CB |
| | | | Internal | | | 16IR 32UNJ-CB |


## Application Examples

### Comparison of Cutting Force




Work Material: C45, M30×1,5
Cutting Conditions: $v_c$=150 m/min, wet, 8 passes Thread infeed method: Radial infeed

### Machined Surface Comparison




Work Material: C45, M30×1,5
Cutting Conditions: $v_c$=150 m/min, wet, 8 passes Thread infeed method: Radial infeed





● = Euro stock
○ = Japan stock

Recommended Tightening Torque (N·m)

## Screw-on for External Diameter

**SSTE**
External Threading






Fig.1




The values for dimensions LF and LH below are only for reference.
The actual value is the value below minus the PDY value for the corresponding insert on F65.

### Holder

Dimensions (mm)

| Cat. No. | Stock | Height H | Width B | Overall Length LF | Head LH | Cutting Edge Functional Width WF | Cutting Edge Height HF | Fig |
|---|---|---|---|---|---|---|---|---|
| SSTE R1616H16 | ● | 16 | 16 | 100 | 20,5 | 16 | 16 | 1 |
| SSTE R2020K16 | ● | 20 | 20 | 125 | 30,0 | 20 | 20 | 1 |
| SSTE R2525M16 | ● | 25 | 25 | 150 | 30,0 | 25 | 25 | 1 |

### Parts

| Screw | N·m | Shim Screw | Flat Washer | Shim | Wrench |
|---|---|---|---|---|---|
| BFTX0312N | 2,0 | BX0304*1 | PW3 | YE3 | TRX10 |

*1 Shim screw wrench is sold separately.

## Screw-on for Internal Diameter

**SSTI**
Internal Threading




Fig.1





Fig.2






Fig.3




The values for dimension WF below are only for reference.
The actual value is the value on F66.
minus the PDY profile distance.

### Holder

Dimensions (mm)

| Cat. No. | Stock | Diameter DCON | Height H | Overall Length LF | Head LH | Functional Width WF | Min. Bore Dia. DMIN*2 | Fig |
|---|---|---|---|---|---|---|---|---|
| SSTI R1812M16*3 | ● | 12 | 11,0 | 150 | 32,0 | 10,2 | 18 | 1 |
| SSTI R2016M16*3 | ● | 16 | 15,0 | 150 | 63,5 | 9,2 | 20 | 2 |
| SSTI R2420Q16 | ● | 20 | 18,0 | 180 | 19,0 | 13,5 | 24 | 3 |
| SSTI R3125S16 | ● | 25 | 23,0 | 250 | 14,3 | 16,5 | 31 | 3 |
| SSTI R3732S16 | ● | 32 | 30,0 | 250 | 14,3 | 20,0 | 37 | 3 |

### Parts


| Screw | N·m | Shim Screw | Flat Washer | Shim | Wrench |
|---|---|---|---|---|---|
| BFTX03085N | 2,0 | – | – | – | TRX10 |
| BFTX0312N | 2,0 | BX0304*1 | PW3 | YI3 | |

*1 Shim screw wrench is sold separately. *2 The minimum bore diameter is the diameter of the prepared hole. *3 Left-hand threads are not available.

## Shim and Selection Criteria

| Applications | Recommended Lead Angle ($T_1$) | External Turning Cat. No. | External Turning Stock | Internal Boring Cat. No. | Internal Boring Stock |
|---|---|---|---|---|---|
| Right-hand Thread | 4,5° | YE3-3P | ❍ | YI3-3P | ❍ |
| | 3,5° | YE3-2P | ❍ | YI3-2P | ❍ |
| | 2,5° | YE3-1P | ❍ | YI3-1P | ❍ |
| | 1,5° | YE3*4 | ❍ | YI3*4 | ❍ |
| | 0,5° | YE3-1N | ❍ | YI3-1N | ❍ |
| Left-hand Thread | -0,5° | YE3-2N | ❍ | YI3-2N | ❍ |
| | -1,5° | YE3-3N | ❍ | YI3-3N | ❍ |

*4 Standard shim supplied with holder.




## Holder Identification Code

**S S T E R 25 25 M 16**

| (1) Series |
|---|
| SST Type |

| (2) External/ Internal | |
|---|---|
| Symbol | Distinction |
| E | External |
| I | Internal |

| (3) Feed Direction | |
|---|---|
| Symbol | FeedDirection |
| R | FeedDirection |

| (4) Shank Height/ Work Diameter | | |
|---|---|---|
| | Symbol | (mm) |
| Ext. Turn. (Height) | 16 | 16 |
| | 20 | 20 |
| | 25 | 25 |
| Internal Boring (Min. bore dia.) | 18 | 18 |
| | 20 | 20 |
| | 24 | 24 |
| | 31 | 31 |
| | 37 | 37 |

| (5) Shank Width/ Diameter | | |
|---|---|---|
| | Symbol | (mm) |
| Ext. Turn. (Width) | 16 | 16 |
| | 20 | 20 |
| | 25 | 25 |
| Internal Boring (Diameter) | 12 | 12 |
| | 16 | 16 |
| | 20 | 20 |
| | 25 | 25 |
| | 32 | 32 |

| (6) Overall Length Symbol | |
|---|---|
| Symbol | (mm) |
| H | 100 |
| K | 125 |
| M | 150 |
| Q | 180 |
| S | 250 |

| (7) Insert Size | |
|---|---|
| Symbol | Inscribed Circle (mm) |
| 16 | 9,525 |

Details of Shim Selection →F67

New

## Threading Inserts for External Diameter Machining

External

Fig.1






Fig.2




### 60°/55° General-purpose Threads (Without Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch | | X Direction | Y Direction | Corner Radius | Pcs/ Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| | | | mm | Threads/ Inch | PDX | PDY | RE | | |
| 60° | 16ER A60-CB | ● | 0,5-1,5 | 16 - 48 | 0,8 | 0,6 | 0,09 | 5 | 1 |
| | 16ER AG60-CB | ● | 0,5-3,0 | 8 - 48 | 1,5 | 1,1 | 0,10 | | 1 |
| | 16ER G60-CB | ○ | 2,0-3,0 | 8 - 14 | 1,5 | 1,1 | 0,20 | | 1 |
| 55° | 16ER A55-CB | ● | — | 16 - 48 | 0,8 | 0,5 | 0,05 | 5 | 1 |
| | 16ER AG55-CB | ● | — | 8 - 48 | 1,5 | 1,1 | 0,08 | | 1 |
| | 16ER G55-CB | ○ | — | 8 - 14 | 1,5 | 1,1 | 0,22 | | 1 |

### 60° ISO Metric Thread (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch | | X Direction | Y Direction | Corner Radius | Pcs/ Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| | | | mm | Threads/ Inch | PDX | PDY | RE | | |
| 60° | 16ER 075 ISO-CB | ● | 0,75 | — | 0,5 | 1,0 | 0,09 | 5 | 2 |
| | 16ER 100 ISO-CB | ● | 1,00 | — | 0,8 | 0,6 | 0,14 | | 2 |
| | 16ER 125 ISO-CB | ● | 1,25 | — | 0,8 | 0,7 | 0,15 | | 2 |
| | 16ER 150 ISO-CB | ● | 1,50 | — | 0,8 | 0,7 | 0,20 | | 2 |
| | 16ER 175 ISO-CB | ● | 1,75 | — | 1,5 | 1,0 | 0,23 | | 2 |
| | 16ER 200 ISO-CB | ● | 2,00 | — | 1,5 | 1,1 | 0,26 | | 2 |
| | 16ER 250 ISO-CB | ● | 2,50 | — | 1,5 | 1,2 | 0,33 | | 2 |
| | 16ER 300 ISO-CB | ● | 3,00 | — | 1,5 | 1,1 | 0,41 | | 2 |

### 60° Unified Thread (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch | | X Direction | Y Direction | Corner Radius | Pcs/ Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| | | | mm | Threads/ Inch | PDX | PDY | RE | | |
| 60° | 16ER 32UN-CB | ○ | — | 32 | 0,5 | 1,0 | 0,10 | 5 | 2 |
| | 16ER 28UN-CB | ○ | — | 28 | 0,8 | 0,7 | 0,11 | | 2 |
| | 16ER 24UN-CB | ○ | — | 24 | 0,8 | 0,7 | 0,13 | | 2 |
| | 16ER 20UN-CB | ○ | — | 20 | 0,8 | 0,7 | 0,16 | | 2 |
| | 16ER 18UN-CB | ○ | — | 18 | 0,8 | 0,7 | 0,18 | | 2 |
| | 16ER 16UN-CB | ○ | — | 16 | 0,8 | 0,8 | 0,20 | | 2 |
| | 16ER 14UN-CB | ○ | — | 14 | 1,5 | 1,2 | 0,23 | | 2 |
| | 16ER 13UN-CB | ○ | — | 13 | 1,5 | 1,1 | 0,26 | | 2 |
| | 16ER 12UN-CB | ○ | — | 12 | 1,5 | 1,0 | 0,27 | | 2 |
| | 16ER 10UN-CB | ○ | — | 10 | 1,5 | 1,2 | 0,33 | | 2 |
| | 16ER 08UN-CB | ○ | — | 8 | 1,5 | 1,2 | 0,42 | | 2 |

### 55° Parallel Thread for Pipe/Whitworth (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch | | X Direction | Y Direction | Corner Radius | Pcs/ Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| | | | mm | Threads/ Inch | PDX | PDY | RE | | |
| 55° | 16ER 36W-CB | ○ | — | 36 | 0,5 | 1,0 | 0,10 | 5 | 2 |
| | 16ER 32W-CB | ○ | — | 32 | 0,5 | 1,0 | 0,11 | | 2 |
| | 16ER 28W-CB | ○ | — | 28 | 0,8 | 0,6 | 0,12 | | 2 |
| | 16ER 24W-CB | ○ | — | 24 | 0,8 | 0,6 | 0,15 | | 2 |
| | 16ER 20W-CB | ○ | — | 20 | 0,8 | 0,6 | 0,18 | | 2 |
| | 16ER 19W-CB | ○ | — | 19 | 0,8 | 0,6 | 0,18 | | 2 |
| | 16ER 18W-CB | ○ | — | 18 | 0,8 | 0,6 | 0,19 | | 2 |
| | 16ER 16W-CB | ○ | — | 16 | 0,8 | 0,6 | 0,22 | | 2 |
| | 16ER 14W-CB | ○ | — | 14 | 1,5 | 1,0 | 0,25 | | 2 |
| | 16ER 12W-CB | ○ | — | 12 | 1,5 | 1,1 | 0,29 | | 2 |
| | 16ER 11W-CB | ○ | — | 11 | 1,5 | 1,1 | 0,32 | | 2 |
| | 16ER 10W-CB | ○ | — | 10 | 1,5 | 1,1 | 0,35 | | 2 |
| | 16ER 08W-CB | ○ | — | 8 | 1,5 | 1,1 | 0,43 | | 2 |

For these inserts, only SSTE Type holders can be used.

### 60° American NPT (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch | | X Direction | Y Direction | Corner Radius | Pcs/ Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| | | | mm | Threads/ Inch | PDX | PDY | RE | | |
| 60° | 16ER 27NPT-CB | ○ | — | 27 | 0,8 | 0,6 | 0,06 | 5 | 2 |
| | 16ER 18NPT-CB | ○ | — | 18 | 0,8 | 0,6 | 0,06 | | 2 |
| | 16ER 14NPT-CB | ○ | — | 14 | 1,5 | 1,0 | 0,08 | | 2 |
| | 16ER 115NPT-CB | ○ | — | 11,5 | 1,5 | 1,0 | 0,08 | | 2 |
| | 16ER 08NPT-CB | ○ | — | 8 | 1,5 | 1,1 | 0,13 | | 2 |

### 55° Taper Thread for Pipe/BSPT (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch | | X Direction | Y Direction | Corner Radius | Pcs/ Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| | | | mm | Threads/ Inch | PDX | PDY | RE | | |
| 55° | 16ER 28BSPT-CB | ○ | — | 28 | 0,8 | 0,6 | 0,13 | 5 | 2 |
| | 16ER 19BSPT-CB | ○ | — | 19 | 0,8 | 0,6 | 0,18 | | 2 |
| | 16ER 14BSPT-CB | ○ | — | 14 | 1,5 | 1,3 | 0,25 | | 2 |
| | 16ER 11BSPT-CB | ○ | — | 11 | 1,5 | 1,0 | 0,31 | | 2 |

### 60° American NPTF (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch | | X Direction | Y Direction | Corner Radius | Pcs/ Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| | | | mm | Threads/ Inch | PDX | PDY | RE | | |
| 60° | 16ER 27NPTF-CB | ○ | — | 27 | 0,8 | 0,6 | 0,06 | 5 | 2 |
| | 16ER 18NPTF-CB | ○ | — | 18 | 0,8 | 0,6 | 0,06 | | 2 |
| | 16ER 14NPTF-CB | ○ | — | 14 | 1,5 | 1,0 | 0,13 | | 2 |
| | 16ER 115NPTF-CB | ○ | — | 11,5 | 1,5 | 1,0 | 0,12 | | 2 |

### 60° UNJ (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch | | X Direction | Y Direction | Corner Radius | Pcs/ Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| | | | mm | Threads/ Inch | PDX | PDY | RE | | |
| 60° | 16ER 32UNJ-CB | ○ | — | 32 | 0,5 | 1,0 | 0,13 | 5 | 2 |
| | 16ER 28UNJ-CB | ○ | — | 28 | 0,8 | 0,6 | 0,15 | | 2 |
| | 16ER 24UNJ-CB | ○ | — | 24 | 0,8 | 0,6 | 0,18 | | 2 |
| | 16ER 20UNJ-CB | ○ | — | 20 | 0,8 | 0,7 | 0,21 | | 2 |
| | 16ER 18UNJ-CB | ○ | — | 18 | 0,8 | 0,6 | 0,23 | | 2 |
| | 16ER 16UNJ-CB | ○ | — | 16 | 0,8 | 0,6 | 0,25 | | 2 |
| | 16ER 14UNJ-CB | ○ | — | 14 | 1,5 | 1,1 | 0,29 | | 2 |
| | 16ER 12UNJ-CB | ○ | — | 12 | 1,5 | 1,1 | 0,34 | | 2 |
| | 16ER 10UNJ-CB | ○ | — | 10 | 1,5 | 1,1 | 0,40 | | 2 |

## Insert Identification Table

**16 E R 150 ISO - CB**

| (1) Insert Size | |
|---|---|
| Symbol | Inscribed Circle (mm) |
| 16 | 9,525 |

| (2) External/Internal | |
|---|---|
| Symbol | Distinction |
| E | External |
| I | Internal |

| (3) Feed Direction | |
|---|---|
| Symbol | Feed Direction |
| R | Right Hand |

(4) Pitch or TPI

With Wiper Flat: Metric = Pitch x 100; Inch=TPI (115 only for 11.5)
(Example) 075: Pitch 0.75 mm; 150: Pitch 1.5 mm; 20: 20 TPI

Without Wiper Flat:

| Symbol | Pitch/TPI |
|---|---|
| A | Pitch : 0.5 to 1.5 mm; TPI : 16 to 48 |
| AG | Pitch : 0.5 to 3.0 mm; TPI : 8 to 48 |
| G | Pitch : 2.0 to 3.0 mm; TPI : 8 to 14 |

(5) Thread Type

| Wiper Flat | Symbol | Type |
|---|---|---|
| Yes | ISO | Metric Thread |
| | UN | Unified Thread |
| | W | Whitworth |
| | NPT | Americ. Taper Thread f. Pipe |
| | BSPT | Taper Thread for Pipe |
| | NPTF | Americ. Taper Thread f. Pipe |
| | UNJ | For Aerospace Equipment |
| No | 60 | 60° General-purpose Thread |
| | 55 | 55° General-purpose Thread |

| (6) Chipbreaker | |
|---|---|
| Symbol | Description |
| CB | With Chipbreaker |



● = Euro stock
○ = Japan stock

## Threading Inserts for Inner Diameter Machining

Fig.1






Fig.2




### 60°/55° General-purpose Threads (Without Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch mm | Pitch Threads/Inch | X Direction PDX | Y Direction PDY | Corner Radius RE | Pcs/Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 60° | 16IR A60-CB | ● | 0,5-1,5 | 16 - 48 | 0,8 | 0,5 | 0,09 | 5 | 1 |
| | 16IR AG60-CB | ● | 0,5-3,0 | 8 - 48 | 1,5 | 1,1 | 0,10 | | 1 |
| | 16IR G60-CB | ❍ | 2,0-3,0 | 8 - 14 | 1,5 | 1,1 | 0,18 | | 1 |
| 55° | 16IR A55-CB | ● | — | 16 - 48 | 0,8 | 0,5 | 0,05 | 5 | 1 |
| | 16IR AG55-CB | ● | — | 8 - 48 | 1,5 | 1,1 | 0,08 | | 1 |
| | 16IR G55-CB | ❍ | — | 8 - 14 | 1,5 | 1,1 | 0,20 | | 1 |

### 60° ISO Metric Thread (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch mm | Pitch Threads/Inch | X Direction PDX | Y Direction PDY | Corner Radius RE | Pcs/Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 60° | 16IR 075 ISO-CB | ● | 0,75 | — | 0,5 | 0,9 | 0,04 | 5 | 2 |
| | 16IR 100 ISO-CB | ● | 1,00 | — | 0,8 | 0,6 | 0,06 | | 2 |
| | 16IR 125 ISO-CB | ● | 1,25 | — | 0,8 | 0,6 | 0,07 | | 2 |
| | 16IR 150 ISO-CB | ● | 1,50 | — | 0,8 | 0,6 | 0,09 | | 2 |
| | 16IR 175 ISO-CB | ● | 1,75 | — | 1,5 | 1,0 | 0,10 | | 2 |
| | 16IR 200 ISO-CB | ● | 2,00 | — | 1,5 | 1,1 | 0,13 | | 2 |
| | 16IR 250 ISO-CB | ● | 2,50 | — | 1,5 | 1,1 | 0,15 | | 2 |
| | 16IR 300 ISO-CB | ● | 3,00 | — | 1,5 | 1,1 | 0,19 | | 2 |

### 60° Unified Thread (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch mm | Pitch Threads/Inch | X Direction PDX | Y Direction PDY | Corner Radius RE | Pcs/Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 60° | 16IR 32UN-CB | ❍ | — | 32 | 0,5 | 0,9 | 0,04 | 5 | 2 |
| | 16IR 28UN-CB | ❍ | — | 28 | 0,8 | 0,6 | 0,06 | | 2 |
| | 16IR 24UN-CB | ❍ | — | 24 | 0,8 | 0,7 | 0,06 | | 2 |
| | 16IR 20UN-CB | ❍ | — | 20 | 0,8 | 0,6 | 0,08 | | 2 |
| | 16IR 18UN-CB | ❍ | — | 18 | 0,8 | 0,6 | 0,08 | | 2 |
| | 16IR 16UN-CB | ❍ | — | 16 | 0,8 | 0,7 | 0,09 | | 2 |
| | 16IR 14UN-CB | ❍ | — | 14 | 1,5 | 1,1 | 0,13 | | 2 |
| | 16IR 13UN-CB | ❍ | — | 13 | 1,5 | 1,1 | 0,11 | | 2 |
| | 16IR 12UN-CB | ❍ | — | 12 | 1,5 | 1,1 | 0,13 | | 2 |
| | 16IR 10UN-CB | ❍ | — | 10 | 1,5 | 1,1 | 0,15 | | 2 |
| | 16IR 08UN-CB | ❍ | — | 8 | 1,5 | 1,1 | 0,20 | | 2 |

### 55° Parallel Thread for Pipe/Whitworth (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch mm | Pitch Threads/Inch | X Direction PDX | Y Direction PDY | Corner Radius RE | Pcs/Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 55° | 16IR 28W-CB | ❍ | — | 28 | 0,8 | 0,6 | 0,12 | 5 | 2 |
| | 16IR 24W-CB | ❍ | — | 24 | 0,8 | 0,6 | 0,14 | | 2 |
| | 16IR 20W-CB | ❍ | — | 20 | 0,8 | 0,6 | 0,18 | | 2 |
| | 16IR 19W-CB | ❍ | — | 19 | 0,8 | 0,6 | 0,18 | | 2 |

For these inserts, only SSTI Type holders can be used.

### 60° American NPT (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch mm | Pitch Threads/Inch | X Direction PDX | Y Direction PDY | Corner Radius RE | Pcs/Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 60° | 16IR 27NPT-CB | ❍ | — | 27 | 0,8 | 0,6 | 0,06 | 5 | 2 |
| | 16IR 18NPT-CB | ❍ | — | 18 | 0,8 | 0,6 | 0,06 | | 2 |
| | 16IR 14NPT-CB | ❍ | — | 14 | 1,5 | 1,1 | 0,08 | | 2 |
| | 16IR 115NPT-CB | ❍ | — | 11,5 | 1,5 | 1,0 | 0,08 | | 2 |
| | 16IR 08NPT-CB | ❍ | — | 8 | 1,5 | 1,0 | 0,13 | | 2 |

### 55° Taper Thread for Pipe/BSPT (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch mm | Pitch Threads/Inch | X Direction PDX | Y Direction PDY | Corner Radius RE | Pcs/Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 55° | 16IR 28BSPT-CB | ❍ | — | 28 | 0,8 | 0,6 | 0,13 | 5 | 2 |
| | 16IR 19BSPT-CB | ❍ | — | 19 | 0,8 | 0,6 | 0,18 | | 2 |

### 60° American NPTF (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch mm | Pitch Threads/Inch | X Direction PDX | Y Direction PDY | Corner Radius RE | Pcs/Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 60° | 16IR 27NPTF-CB | ❍ | — | 27 | 0,8 | 0,6 | 0,06 | 5 | 2 |
| | 16IR 18NPTF-CB | ❍ | — | 18 | 0,8 | 0,6 | 0,08 | | 2 |
| | 16IR 14NPTF-CB | ❍ | — | 14 | 1,5 | 1,0 | 0,13 | | 2 |
| | 16IR 115NPTF-CB | ❍ | — | 11,5 | 1,5 | 1,0 | 0,08 | | 2 |
| | 16IR 08NPTF-CB | ❍ | — | 8 | 1,5 | 1,1 | 0,13 | | 2 |

### 60° UNJ (With Wiper Flat)

Dimensions (mm)

| Included Angle | Cat. No. | AC530U | Pitch mm | Pitch Threads/Inch | X Direction PDX | Y Direction PDY | Corner Radius RE | Pcs/Pack | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 60° | 16IR 32UNJ-CB | ❍ | — | 32 | 0,5 | 0,9 | 0,04 | 5 | 2 |
| | 16IR 28UNJ-CB | ❍ | — | 28 | 0,8 | 0,6 | 0,05 | | 2 |
| | 16IR 24UNJ-CB | ❍ | — | 24 | 0,8 | 0,6 | 0,06 | | 2 |
| | 16IR 20UNJ-CB | ❍ | — | 20 | 0,8 | 0,6 | 0,06 | | 2 |
| | 16IR 18UNJ-CB | ❍ | — | 18 | 0,8 | 0,6 | 0,06 | | 2 |
| | 16IR 16UNJ-CB | ❍ | — | 16 | 0,8 | 0,6 | 0,09 | | 2 |
| | 16IR 14UNJ-CB | ❍ | — | 14 | 1,5 | 1,1 | 0,09 | | 2 |
| | 16IR 12UNJ-CB | ❍ | — | 12 | 1,5 | 1,1 | 0,11 | | 2 |
| | 16IR 10UNJ-CB | ❍ | — | 10 | 1,5 | 1,1 | 0,15 | | 2 |

### Insert Identification Table

**16 I R 150 ISO - CB**

| (1) Insert Size | |
|---|---|
| Symbol | Inscribed Circle (mm) |
| 16 | 9.525 |

| (2) External/Internal | |
|---|---|
| Symbol | Distinction |
| E | External |
| I | Internal |

| (3) Feed Direction | |
|---|---|
| Symbol | Feed Direction |
| R | Right Hand |

(4) Pitch or TPI

With Wiper Flat: Metric = Pitch x 100; Inch=TPI (115 only for 11.5)

(Example) 075: Pitch 0.75 mm; 150: Pitch 1.5 mm; 20: 20 TPI

| Without Wiper Flat | | |
|---|---|---|
| Symbol | Pitch/TPI | |
| A | Pitch : 0.5 to 1.5 mm; TPI : 16 to 48 | |
| AG | Pitch : 0.5 to 3.0 mm; TPI : 8 to 48 | |
| G | Pitch : 2.0 to 3.0 mm; TPI : 8 to 14 | |


| (5) Thread Type | | |
|---|---|---|
| Wiper Flat | Symbol | Type |
| Yes | ISO | Metric Thread |
| | UN | Unified Thread |
| | W | Whitworth |
| | NPT | Americ. Taper Thread f. Pipe |
| | BSPT | Taper Thread for Pipe |
| | NPTF | Americ. Taper Thread f. Pipe |
| | UNJ | For Aerospace Equipment |
| No | 60 | 60° General-purpose Thread |
| | 55 | 55° General-purpose Thread |

| (6) Chipbreaker | |
|---|---|
| Symbol | Description |
| CB | With Chipbreaker |

# SSTE / SSTI Type


## ■ Shim Selection

If the pitch is large or thread diameter is small, the lead angle of the thread becomes larger and the effective relief angle of the leading edge becomes smaller. It is ideal to set the threading insert so that both right and left relief angles are equal.
Therefore, it is necessary to select an appropriate shim based on the thread pitch and effective diameter using the table below.




## ■ Shim Selection Procedure

(1) Choose from [Right-Hand Thread / Left-Hand Thread] in the table.
(2) Locate the required threading „pitch“.
(3) Locate the cell with the required „Effective Diameter“ range.
(4) Confirm the part no. at the „Shim“ row above the corresponding „Effective Diameter“ cell located previously.
If the shim part no. is different from the one currently in use, change to the correct one.




Example: When machining an M16×2,0 external right-hand thread, the pitch diameter is 14.701 mm. In the table below, locate [2,0] mm under the "Pitch" column and then move along the row to the right to locate the required "Effective Diameter" range [11,4 - 17,4] mm. As such, the correct shim should be [YE3-1P], shown in the corresponding cell under the "Internal" row below.

## ● Pitch (mm)


| Right-hand/Left-hand Thread | | For Right-hand Thread | | | | | For Left-hand Thread | |
|---|---|---|---|---|---|---|---|---|
| Lead Angle | | 4,5° | 3,5° | 2,5° | 1,5° | 0,5° | -0,5° | -1,5° |
| Shim | External | YE3-3P | YE3-2P | YE3-1P | **YE3*** | YE3-1N | YE3-2N | YE3-3N |
| | Internal | YI3-3P | YI3-2P | YI3-1P | **YI3*** | YI3-1N | YI3-2N | YI3-3N |
| | Shim Angle (T1) | 3° | 2° | 1° | 0° | -1° | -2° | -3° |
| Pitch (mm) | | Effective Diameter (mm) | | | | | | |
| **0,5** | | 1,9 - 2,2 | 2,2 - 2,8 | 2,8 - 4,3 | 4,3 - 11,4 | > 11,4 | > 11,4 | 11,4 - 4,3 |
| **0,75** | | 2,8 - 3,3 | 3,3 - 4,3 | 4,3 - 6,5 | 6,5 - 17,1 | > 17,1 | > 17,1 | 17,1 - 6,5 |
| **1,0** | | 3,8 - 4,3 | 4,3 - 5,7 | 5,7 - 8,7 | 8,7 - 22,8 | > 22,8 | > 22,8 | 22,8 - 8,7 |
| **1,25** | | 4,7 - 5,4 | 5,4 - 7,1 | 7,1 - 10,9 | 10,9 - 28,5 | > 28,5 | > 28,5 | 28,5 - 10,9 |
| **1,5** | | 5,7 - 6,5 | 6,5 - 8,5 | 8,5 - 13,0 | 13,0 - 34,2 | > 34,2 | > 34,2 | 34,2 - 13,0 |
| **1,75** | | 6,6 - 7,6 | 7,6 - 10,0 | 10,0 - 15,2 | 15,2 - 39,9 | > 39,9 | > 39,9 | 39,9 - 15,2 |
| **2,0** | | 7,6 - 8,7 | 8,7 - 11,4 | 11,4 - 17,4 | 17,4 - 45,6 | > 45,6 | > 45,6 | 45,6 - 17,4 |
| **2,5** | | 9,5 - 10,8 | 10,8 - 14,2 | 14,2 - 21,7 | 21,7 - 57,0 | > 57,0 | > 57,0 | 57,0 - 21,7 |
| **3,0** | | 11,4 - 13,0 | 13,0 - 17,1 | 17,1 - 26,0 | 26,0 - 68,4 | > 68,4 | > 68,4 | 68,4 - 26,0 |

## ● TPI (Threads/Inch)

| Right-hand/Left-hand Thread | | For Right-hand Thread | | | | | For Left-hand Thread | |
|---|---|---|---|---|---|---|---|---|
| Lead Angle | | 4,5° | 3,5° | 2,5° | 1,5° | 0,5° | -0,5° | -1,5° |
| Shim | External | YE3-3P | YE3-2P | YE3-1P | **YE3*** | YE3-1N | YE3-2N | YE3-3N |
| | Internal | YI3-3P | YI3-2P | YI3-1P | **YI3*** | YI3-1N | YI3-2N | YI3-3N |
| | Shim Angle (T1) | 3° | 2° | 1° | 0° | -1° | -2° | -3° |
| TPI (Threads/Inch) | | Effective Diameter (mm) | | | | | | |
| **32** | | 3,0 - 3,3 | 3,3 - 4,6 | 4,6 - 6,9 | 6,9 - 18,0 | > 18,0 | > 18,0 | 18,0 - 6,9 |
| **28** | | 3,0 - 3,8 | 3,8 - 5,1 | 5,1 - 7,9 | 7,9 - 20,8 | > 20,8 | > 20,8 | 20,8 - 7,9 |
| **27** | | 3,6 - 4,1 | 4,1 - 5,3 | 5,3 - 8,1 | 8,1 - 21,3 | > 21,3 | > 21,3 | 21,3 - 8,1 |
| **24** | | 4,1 - 4,6 | 4,6 - 6,1 | 6,1 - 9,1 | 9,1 - 24,4 | > 24,4 | > 24,4 | 24,4 - 9,1 |
| **20** | | 4,8 - 5,6 | 5,6 - 7,1 | 7,1 - 10,9 | 10,9 - 29,0 | > 29,0 | > 29,0 | 29,0 - 10,9 |
| **18** | | 5,3 - 6,1 | 6,1 - 8,1 | 8,1 - 12,4 | 12,4 - 32,5 | > 32,5 | > 32,5 | 32,5 - 12,4 |
| **16** | | 5,8 - 6,9 | 6,9 - 8,9 | 8,9 - 13,7 | 13,7 - 35,8 | > 35,8 | > 35,8 | 35,8 - 13,7 |
| **14** | | 6,9 - 7,9 | 7,9 - 10,2 | 10,2 - 15,7 | 15,7 - 41,1 | > 41,1 | > 41,1 | 41,1 - 15,7 |
| **13** | | 7,4 - 8,4 | 8,4 - 11,2 | 11,2 - 17,0 | 17,0 - 44,7 | > 44,7 | > 44,7 | 44,7 - 17,0 |
| **12** | | 8,1 - 9,1 | 9,1 - 12,2 | 12,2 - 18,5 | 18,5 - 48,8 | > 48,8 | > 48,8 | 48,8 - 18,5 |
| **11,5** | | 8,4 - 9,7 | 9,7 - 12,4 | 12,4 - 19,3 | 19,3 - 50,3 | > 50,3 | > 50,3 | 50,3 - 19,3 |
| **11** | | 8,9 - 9,9 | 9,9 - 13,2 | 13,2 - 20,1 | 20,1 - 52,6 | > 52,6 | > 52,6 | 52,6 - 20,1 |
| **10** | | 9,7 - 10,9 | 10,9 - 14,5 | 14,5 - 22,1 | 22,1 - 57,9 | > 57,9 | > 57,9 | 57,9 - 22,1 |
| **9** | | 10,7 - 12,2 | 12,2 - 16,0 | 16,0 - 24,4 | 24,4 - 64,3 | > 64,3 | > 64,3 | 64,3 - 24,4 |
| **8** | | 11,9 - 13,7 | 13,7 - 18,0 | 18,0 - 27,7 | 27,7 - 72,4 | > 72,4 | > 72,4 | 72,4 - 27,7 |

* SSTE Type/SSTI Type holders are shipped with shims for a lead angle of Y1 = 1,5° (SSTE Type: **YE3**, SSTI Type: **YI3**).
Shims for lead angles of Y1 = -1,5°, -0,5°, 0,5°, 2,5°, 3,5°, and 4,5° are sold separately.
* Shims are not needed for SSTI R1812M16 and SSTI R2016M16. (The holders are already provided with the standard holder inclination of 1,5°.)

## Shim Replacement




Remove the insert to expose the shim.




Loosen the shim set screw by one to two turns.






Remove the shim and attach a different shim that matches the lead.




Tighten the shim set screw (recommended tightening torque 1,0 to 1,5 Nm).

## Wiper Flat

| Without Wiper Flat | With Wiper Flat |
|---|---|
|   |   |
| • Performs threading without machining thread ridges (the machined surface from the previous process is left unworked.)<br>• Enables machining of threads with different pitch widths with the same insert<br>• Finishing of the internal (or external) diameter is required before the threading process.<br>• Fine burrs are easily formed on edges of ridges. | • Enables machining of workpieces into shapes compliant with thread standards<br>• Only specific thread specifications and pitch can be machined<br>• In order to finish a thread with the wiper flat, a finishing allowance of 0,1 mm on each side is required.<br>• Edges of ridges can be rounded off. |


## Infeed Method

The modified flank infeed is recommended for the SSTE type/SSTI type.
This infeed method, which features reduced chip curl diameters and stable chip control, can also decrease chipping on trailing edges that often occurs in radial infeed machining. (1° is recommended for the modification angle.)

● Impact of the Infeed Method on Chip Shapes


Work Material: X5CrMo17-12-2, M30 x 1,5 Cutting Conditions: $v_c$ = 60 mm/min, wet, 8 Passes

Modified Flank Infeed




Reduced curl diameters ensure smooth, stable chip control (performance)

Radial Infeed Machining




Large curl diameters cause unstable chip control.

## SSTE Type Guidelines for Depth of Cut

External Metric Threads (Depth of cut per pass: mm)

| Pitch (mm) | 0,75 | 1,00 | 1,25 | 1,50 | 1,75 | 2,00 | 2,50 | 3,00 |
|---|---|---|---|---|---|---|---|---|
| Overall Depth of Cut (mm) | 0,48 | 0,64 | 0,80 | 0,92 | 1,10 | 1,26 | 1,57 | 1,87 |
| No. of Passes | 4 | 5 | 7 | 8 | 10 | 12 | 14 | 16 |
| **1** | 0,24 | 0,25 | 0,25 | 0,28 | 0,28 | 0,30 | 0,38 | 0,40 |
| **2** | 0,12 | 0,15 | 0,15 | 0,15 | 0,15 | 0,16 | 0,19 | 0,22 |
| **3** | 0,07 | 0,11 | 0,12 | 0,12 | 0,12 | 0,13 | 0,15 | 0,15 |
| **4** | 0,05 | 0,08 | 0,09 | 0,10 | 0,10 | 0,10 | 0,10 | 0,13 |
| **5** | | 0,05 | 0,08 | 0,09 | 0,10 | 0,09 | 0,10 | 0,12 |
| **6** | | | 0,06 | 0,07 | 0,09 | 0,09 | 0,09 | 0,10 |
| **7** | | | 0,05 | 0,06 | 0,08 | 0,08 | 0,09 | 0,10 |
| **8** | | | | 0,05 | 0,07 | 0,07 | 0,08 | 0,09 |
| **9** | | | | | 0,06 | 0,07 | 0,08 | 0,09 |
| **10** | | | | | 0,05 | 0,06 | 0,07 | 0,08 |
| **11** | | | | | | 0,06 | 0,07 | 0,08 |
| **12** | | | | | | 0,05 | 0,06 | 0,07 |
| **13** | | | | | | | 0,06 | 0,07 |
| **14** | | | | | | | 0,05 | 0,06 |
| **15** | | | | | | | | 0,06 |
| **16** | | | | | | | | 0,05 |

External Unified Threads (Depth of cut per pass: mm)

| Threads/Inch | 32 | 28 | 24 | 20 | 18 | 16 | 14 | 13 | 12 | 11 | 10 | 9 | 8 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Overall Depth of Cut (mm) | 0,50 | 0,57 | 0,67 | 0,80 | 0,89 | 1,00 | 1,15 | 1,23 | 1,34 | 1,46 | 1,60 | 1,78 | 2,00 |
| No. of Passes | 4 | 4 | 5 | 7 | 8 | 10 | 11 | 12 | 12 | 14 | 14 | 16 | 16 |
| **1** | 0,24 | 0,25 | 0,25 | 0,26 | 0,26 | 0,28 | 0,28 | 0,30 | 0,30 | 0,30 | 0,38 | 0,38 | 0,40 |
| **2** | 0,14 | 0,17 | 0,19 | 0,15 | 0,15 | 0,15 | 0,15 | 0,18 | 0,18 | 0,18 | 0,20 | 0,20 | 0,25 |
| **3** | 0,07 | 0,10 | 0,12 | 0,10 | 0,12 | 0,10 | 0,12 | 0,13 | 0,13 | 0,13 | 0,15 | 0,13 | 0,19 |
| **4** | 0,05 | 0,05 | 0,06 | 0,09 | 0,10 | 0,09 | 0,10 | 0,10 | 0,12 | 0,12 | 0,12 | 0,12 | 0,16 |
| **5** | | | 0,05 | 0,08 | 0,08 | 0,08 | 0,10 | 0,08 | 0,11 | 0,11 | 0,10 | 0,11 | 0,14 |
| **6** | | | | 0,07 | 0,07 | 0,07 | 0,09 | 0,08 | 0,10 | 0,10 | 0,09 | 0,10 | 0,12 |
| **7** | | | | 0,05 | 0,06 | 0,07 | 0,08 | 0,07 | 0,09 | 0,08 | 0,09 | 0,10 | 0,11 |
| **8** | | | | | 0,05 | 0,06 | 0,07 | 0,07 | 0,08 | 0,08 | 0,08 | 0,09 | 0,10 |
| **9** | | | | | | 0,05 | 0,06 | 0,06 | 0,07 | 0,07 | 0,08 | 0,09 | 0,09 |
| **10** | | | | | | 0,05 | 0,05 | 0,06 | 0,06 | 0,07 | 0,07 | 0,08 | 0,08 |
| **11** | | | | | | | 0,05 | 0,05 | 0,05 | 0,06 | 0,07 | 0,08 | 0,07 |
| **12** | | | | | | | | 0,05 | 0,05 | 0,06 | 0,06 | 0,07 | 0,07 |
| **13** | | | | | | | | | | 0,05 | 0,06 | 0,07 | 0,06 |
| **14** | | | | | | | | | | 0,05 | 0,05 | 0,06 | 0,06 |
| **15** | | | | | | | | | | | | 0,05 | 0,05 |
| **16** | | | | | | | | | | | | 0,05 | 0,05 |

No. of passes and depths of cut in the table above are general guidelines only. Increase or decrease depending on conditions. However, the maximum depth of cut should be kept to 0,5mm or less.
When using an insert with a wiper flat, add machining allowance to the total depth of cut.

## Recommended Cutting Conditions

| Work Material | P Carbon Steel | P Alloy Steel (up to 330HB) | M Stainless Steel | K Grey Cast Iron (up to 330HB) | K Ductile Cast Iron | S Titanium Alloy |
|---|---|---|---|---|---|---|
| Cutting Speed $v_c$ (m/min) | 75–150 | 75–135 | 60–120 | 90–180 | 75–135 | 24–90 |

## ■ SSTI Type Guidelines for Depth of Cut

### Internal Metric Threads (Depth of cut per pass: mm)

| Pitch (mm) | 0,75 | 1,00 | 1,25 | 1,50 | 1,75 | 2,00 | 2,50 | 3,00 |
|---|---|---|---|---|---|---|---|---|
| Overall Depth of Cut (mm) | 0,49 | 0,58 | 0,74 | 0,89 | 1,04 | 1,18 | 1,47 | 1,76 |
| No. of Passes | 4 | 5 | 8 | 10 | 11 | 12 | 14 | 16 |
| **1** | 0,20 | 0,22 | 0,22 | 0,25 | 0,25 | 0,25 | 0,30 | 0,30 |
| **2** | 0,12 | 0,14 | 0,14 | 0,12 | 0,17 | 0,18 | 0,19 | 0,20 |
| **3** | 0,12 | 0,10 | 0,09 | 0,08 | 0,10 | 0,12 | 0,15 | 0,17 |
| **4** | 0,05 | 0,07 | 0,07 | 0,08 | 0,08 | 0,10 | 0,12 | 0,14 |
| **5** | | 0,05 | 0,06 | 0,07 | 0,08 | 0,09 | 0,10 | 0,12 |
| **6** | | | 0,06 | 0,07 | 0,07 | 0,08 | 0,09 | 0,11 |
| **7** | | | 0,05 | 0,06 | 0,07 | 0,07 | 0,08 | 0,10 |
| **8** | | | 0,05 | 0,06 | 0,06 | 0,07 | 0,08 | 0,10 |
| **9** | | | | 0,05 | 0,06 | 0,06 | 0,07 | 0,08 |
| **10** | | | | 0,05 | 0,05 | 0,06 | 0,07 | 0,08 |
| **11** | | | | | 0,05 | 0,05 | 0,06 | 0,07 |
| **12** | | | | | | 0,05 | 0,06 | 0,07 |
| **13** | | | | | | | 0,05 | 0,06 |
| **14** | | | | | | | 0,05 | 0,06 |
| **15** | | | | | | | | 0,05 |
| **16** | | | | | | | | 0,05 |

### Internal Unified Threads (Depth of cut per pass: mm)

| Threads/Inch | 32 | 28 | 24 | 20 | 18 | 16 | 14 | 13 | 12 | 11 | 10 | 9 | 8 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Overall Depth of Cut (mm) | 0,43 | 0,49 | 0,57 | 0,69 | 0,76 | 0,86 | 0,98 | 1,06 | 1,15 | 1,25 | 1,37 | 1,53 | 1,72 |
| No. of Passes | 4 | 4 | 5 | 7 | 8 | 10 | 11 | 12 | 12 | 14 | 14 | 16 | 16 |
| **1** | 0,20 | 0,20 | 0,20 | 0,22 | 0,22 | 0,22 | 0,25 | 0,25 | 0,27 | 0,27 | 0,27 | 0,30 | 0,30 |
| **2** | 0,10 | 0,16 | 0,16 | 0,12 | 0,13 | 0,13 | 0,15 | 0,15 | 0,16 | 0,16 | 0,18 | 0,18 | 0,22 |
| **3** | 0,08 | 0,08 | 0,09 | 0,09 | 0,10 | 0,08 | 0,10 | 0,10 | 0,12 | 0,12 | 0,16 | 0,16 | 0,18 |
| **4** | 0,05 | 0,05 | 0,07 | 0,08 | 0,08 | 0,08 | 0,08 | 0,08 | 0,10 | 0,10 | 0,12 | 0,11 | 0,15 |
| **5** | | | 0,05 | 0,07 | 0,07 | 0,07 | 0,07 | 0,08 | 0,09 | 0,08 | 0,10 | 0,09 | 0,12 |
| **6** | | | | 0,06 | 0,06 | 0,07 | 0,07 | 0,07 | 0,08 | 0,08 | 0,09 | 0,09 | 0,11 |
| **7** | | | | 0,05 | 0,05 | 0,06 | 0,06 | 0,07 | 0,07 | 0,07 | 0,08 | 0,08 | 0,10 |
| **8** | | | | | 0,05 | 0,06 | 0,06 | 0,06 | 0,06 | 0,07 | 0,07 | 0,08 | 0,09 |
| **9** | | | | | | 0,05 | 0,05 | 0,06 | 0,06 | 0,06 | 0,06 | 0,07 | 0,08 |
| **10** | | | | | | 0,04 | 0,05 | 0,05 | 0,05 | 0,06 | 0,06 | 0,07 | 0,07 |
| **11** | | | | | | | 0,04 | 0,05 | 0,05 | 0,05 | 0,05 | 0,06 | 0,06 |
| **12** | | | | | | | | 0,04 | 0,04 | 0,05 | 0,05 | 0,06 | 0,06 |
| **13** | | | | | | | | | | 0,04 | 0,04 | 0,05 | 0,05 |
| **14** | | | | | | | | | | 0,04 | 0,04 | 0,05 | 0,05 |
| **15** | | | | | | | | | | | | 0,04 | 0,04 |
| **16** | | | | | | | | | | | | 0,04 | 0,04 |

No. of passes and depths of cut in the table above are general guidelines only. Increase or decrease depending on conditions. However, the maximum depth of cut should be kept to 0,5 mm or less.
When using an insert with a wiper flat, add machining allowance to the total depth of cut.

## ■ Recommended Cutting Conditions

| Work Material | P Carbon Steel | P Alloy Steel (up to 330HB) | M Stainless Steel | K Grey Cast Iron (up to 330HB) | K Ductile Cast Iron | S Titanium Alloy |
|---|---|---|---|---|---|---|
| Cutting Speed $v_c$ (m/min) | 75–150 | 75–135 | 60–120 | 90–180 | 75–135 | 24–90 |







# Milling Cutters

**G1–G86**




| | | | |
|---|---|---|---|
| | Selection Guide | **Milling Cutter Selection Guide** | G 2-3 |
| | ISO | **Milling Insert Identification Table** | G 4-5 |
| **Face Milling** | "Sumi Dual Mill", General Purpose Face Mills (Expansion) | DGC (M/F) 13000 | G 6-9 |
| | "Wave Mill", General Purpose Face Mills (Expansion) | WGX (M/F) 13000 | G10-11 |
| | | UFO (F) 4000/5000 | G12-13 |
| | | DNX (F) 12000 | G14-15 |
| **Multi Purpose Milling** | "Wave Radius Mill" with Polygon Inserts | WRCX (F) 12000/16000/20000 | G16-17 |
| | with Round Inserts | RSX | G18-19 |
| | | RSX (F) 10000/12000/16000/20000 | G20-21 |
| **Shoulder Milling** | "Sumi Dual Mill" (Expansion) | DFC 09000 | G22-25 |
| | "Wave Mill" for Shoulder Milling (Expansion) | WFX | G26-27 |
| | | WFX (M/F) 08000 | G28 |
| | | WFX (F) 12000 | G29 |
| | "Sumi Dual Mill", tangential (Expansion) | TSX | G30-31 |
| | | TSX (F) 08000 | G34 |
| | | TSX (M) 13000 | G35-36 |
| | | TSX (F) 13000 (New) | G37 |
| | Sumi Dual Mill" Repeater Mill | TSXR 08000/13000 | G38-39 |
| | Wave Mill" for Shoulder Milling (Expansion) | WEZ | G40-47 |
| | | WEZ 11000/17000 | G48-51 |
| | "Wave Mill" Repeater Mill | WEZR (New) | G52-53 |
| | | WEZR 11000/17000 | G54-57 |
| | "Wave Mill" for Shoulder Milling | WEX (F) 1000/2000/3000 | G58 |
| | Repeater Mill | WRX (F) | G59 |
| **Others** | Shoulder Milling Cutter for Titanium | MTIX (New) | G60-62 |
| | "Sumi Dual Mill", High Feed Milling | DMSW (New) | G63-65 |
| | | DMSW 80000 | G66 |
| | High Feed Milling | MSX 08000/12000/14000 | G67 |
| | High Feed Milling (Expansion) | WFXH | G68-69 |
| | | WFXH 08000/12000 | G70-71 |
| | "Wave Mill" Series for Aluminium | WAX 3000 | G72 |
| | | WAX 4000 | G73 |
| | High Speed Non-Ferrous Milling (Expansion) | ANX | G74-77 |
| | | ANXS/ANXA 16000 | G78-81 |
| | Aluminium Milling | SUMIDIA "RF" | G82 |
| | | SUMIDIA "SRF" | G83 |
| | Grey Cast Iron Milling | SUMIBORON "BN Finish Mill" FMU | G84-85 |

# Face Mill and Shoulder Mill
# Selection Guide

| Application | Cutter Type | Series | Insert Type | Approach Angle / Max. Depth of Cut (mm) | Cutter Diameter (mm) | Application: Face Milling – General Purpose | Face Milling – Finishing | Face Milling – High Feed | Shoulder Milling | Groove Milling | Ramping | Chamfering | Drilling | Profiling | Profile Finishing | Work Material: P – Carbon Steel / Alloy Steel | P – Tempered Steel / Die Steel | M – Stainless Steel | K – Cast Iron / Ductile Cast Iron | N – Non-Ferrous Metal | N – Aluminium Alloy | S – Ti Alloy / Heat Resistant Alloy | H – Hardened Steel HRC 45 ~ 55 | Ref. Page |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Face Milling | DGC  | DGC (-M/F) 13000RS | SNM/EU 13T6..  ONM/EU 05T6..  | SNMU 6 mm 45° ONMU 3 mm 45° | 40–250 | ◎ | | | | | | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | G8 |
| | WGX  | WGX (-M/F) 13000RS | SEE/MT 13T3..  | 6 mm 45° | 40–250 | ◎ | ◎ | | | | | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | G10 |
| | UFO  | UFO (-F) 4000 RS | SFK-N/R12T3.., SFK-N1504...  | 5 mm 45° | 50–315 | ○ | ○ | | | | | | | | | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | G12 |
| | | UFO 5000 RS | | 7 mm 45° | 80–315 | | | | | | | | | | | | | | | | | | | G13 |
| | DNX  | DNX (-F) 12000RS | SNMT 1205..  | 8 mm 65° | 80–160 | ○ | ○ | | | | | | | | | ○ | | | ◎ | | | | | G14 |
| Radius Milling | RSX  | RSX (-F) 10000RS | RDET10T3.. RDET1204..  | 5 mm | 40–52 | ◎ | | ○ | ◎ | ○ | ◎ | | | ◎ | | ◎ | ◎ | ◎ | ◎ | | | ◎ | | G20 |
| | | RSX (-F) 12000RS | | 6 mm | 40–100 | | | | | | | | | | | | | | | | | | | |
| | | RSX (-F) 16000RS | | 8 mm | 63–160 | | | | | | | | | | | | | | | | | | | |
| | | RSX (-F) 20000RS | RDET1606.. RDET2006.. | 10 mm | 80–160 | | | | | | | | | | | | | | | | | | | |
| Multi-Purpose | WRCX  | WRCX (-F/X) 12000RS 16000RS 20000RS | QPMT1204../1606../2006 QPET1204../1606..  | 6-10 mm | 40–160 | ◎ | | ○ | ◎ | ○ | ◎ | | | ◎ | | ◎ | ◎ | ◎ | ◎ | | ◎ | | | G17 |
| High Feed Milling | DMSW  | DMSW08000R(S) | WNMU0807..  | 3 mm 15° | 50–160 | | | ◎ | ○ | ○ | ○ | | | | | ◎ | ◎ | ○ | ◎ | | | | ○ | G66 |
| | MSX  | MSX 08000RS 12000RS 14000RS | WDMT0603../0804../1205.. 1406..  | 1,5-2,5mm 20° | 40–100 | | | ◎ | ○ | ○ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | | | | ○ | G67 |
| | WFXH  | WFXH 08000RS | SOMT0803.., SOMT1204..  | 1,5 mm 15° | 40–63 | | | ◎ | ○ | ○ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | | | ○ | ○ | G70 |
| | | WFXH 12000RS | | 2,5 mm 15° | 50–63 | | | | | | | | | | | | | | | | | | | G71 |
| Shoulder Milling | DFC  | DFC (-M/F) 09000RS | XNMU0606..  | 6 mm 90° | 50–200 | ◎ | ○ | | ◎ | ○ | | | | | | ◎ | ◎ | ○ | ◎ | | | ○ | | G24 |
| | WFX  | WFX (-F/-M) 08000RS | SOMT080.. SOMT1204..  | 6 mm 90° | 40–100 | ○ | ◎ | | ◎ | ○ | | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | G28 |
| | | WFX (-F) 12000 RS | | 10 mm 90° | 50–160 | | | | | | | | | | | | | | | | | | | G29 |

◎ : Best
○ : Suitable


| Application | Cutter Type | Series | Insert Type | Approach Angle / Max. Depth of Cut (mm) | Cutter Diameter (mm) | Application: Face Milling – General Purpose | Face Milling – Finishing | Face Milling – High Feed | Shoulder Milling | Groove Milling | Ramping | Chamfering | Drilling | Profiling | Profile Finishing | Work Material: P – Carbon Steel / Alloy Steel | P – Tempered Steel / Die Steel | M – Stainless Steel | K – Cast Iron / Ductile Cast Iron | N – Non-Ferrous Metal | N – Aluminium Alloy | S – Ti Alloy / Heat Resistant Alloy | H – Hardened Steel HRC 45 ~ 55 | Ref. Page |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Shoulder Milling | TSX | TSX (-F) 08000RS | LNEX0804..,LNEX1306.. | 8 mm 90° | 40–80 | ◎ | ◎ | | ◎ | ○ | | | | | | ◎ | ◎ | ◎ | ◎ | | | ◎ | | G34 G35 G36 G37 |
| | | TSXM13000RS TSX F13000RS | | 12 mm 90° | 40–315 40–160 | | | | | | | | | | | | | | | | | | | |
| | TSXR New | TSXR 08000RS | | 34-60 mm 90° | 32–63 | ○ | | | ◎ | | | | | | | ◎ | ◎ | ◎ | ◎ | | | ◎ | | G38 G39 |
| | | TSXR 13000RS | | 41-60 mm 90° | 40–125 | | | | | | | | | | | | | | | | | | | |
| | WEZ | WEZ 11000R(S) | AOMT11T3.., AOET11T3.. AOMT1705.., AOET1705.. | 10 mm 90° | 40–100 | ◎ | ◎ | | ◎ | ◎ | ◎ | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | G48 G50 |
| | | WEZ 17000R(S) | | 15 mm 90° | 40–160 | | | | | | | | | | | | | | | | | | | |
| | WEZR New | WEZR 11000R(S) | | 44-63 mm 90° | 40–50 | ◎ | ◎ | | ◎ | ◎ | ◎ | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | G54 G56 |
| | | WEZR 17000R(S) | | 29-57 mm 90° | 40–80 | | | | | | | | | | | | | | | | | | | |
| | WEX | WEX 1000F | AXMT0602.. AXMT1235..AXMT1705.. | 5 mm 90° | 32–63 | ○ | | | ◎ | ◎ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | G58 |
| | | WEX 2000F | | 10 mm 90° | 40–63 | | | | | | | | | | | | | | | | | | | |
| | | WEX 3000F | | 14 mm 90° | 40–125 | | | | | | | | | | | | | | | | | | | |
| | WRX | WRX 2000F | AXMT12350../1705.. | 18-36 mm 90° | 40–50 | ○ | | | ◎ | ◎ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | G59 |
| | | WRX 3000F | | 27-53 mm 90° | 50–100 | | | | | | | | | | | | | | | | | | | |
| | MTIX New | MTIX16000RS | XOMT1605.. | 13 mm 90° | 50–63 | ◎ | ◎ | | ◎ | ◎ | ◎ | | | | | | | ○ | | | | ◎ | | G61 |
| Aluminium Alloy and Non-Ferrous Metals | WAX | WAX 3000 RS | AECT1604 | 16-18 mm 90° | 50–125 | ○ | | | ◎ | ◎ | ◎ | | | ◎ | | | | | | ○ | ◎ | | | G72 G73 |
| | | WAX 4000 RS | | 22-24 mm 90° | | | | | | | | | | | | | | | | | | | | |
| | ANX | ANXS 16000R(S) | ANB 1600R-L | 3 mm 90° | 40–125 | ○ | ◎ | ◎ | ◎ | | | | | | | | | | | ◎ | ◎ | | | G80 G78 |
| | | ANXA 16000R(S) | | | 80–160 | | | | | | | | | | | | | | | | | | | |
| | RF | RF 4000 RS | SNEW1204.. SDET1204.. | 3 mm 90° | 80–125 | ◎ | ◎ | | | | | | | | | | | | | ○ | ◎ | | | G82 |
| | SRF | SRF 50/63 RS | SNEW09T3.. | 5 mm 90° | 30–63 | ◎ | ◎ | | ○ | | | | | | | | | | | ○ | ◎ | | | G83 |
| High Speed Finishing of Cast Iron | FMU | FMU 4000 RS | SNEW1203.. | 0,5 mm 90° | 80–100 | | ◎ | | | | | | | | | | | | ◎ | | | | | G85 |

# ISO Identification Table



| Insert shape | | | |
|---|---|---|---|
| C | 80° | A | 85° |
| D | 55° | B | 82° |
| E | 75° | K | 55° |
| F | 50° | H | 120° |
| V | 35° | O | 135° |
| R | - | P | 108° |
| S | 90° | L | 90° |
| T | 60° | M | 86° |
| W | 80° | | |

| Clearance angle | |
|---|---|
| A | 3° |
| B | 5° |
| C | 7° |
| D | 15° |
| E | 20° |
| F | 25° |
| G | 30° |
| N | 0° |
| P | 11° |






O Other clearance angle with specific description

| Insert type | | | |
|---|---|---|---|
| A | | W | |
| G | | T | |
| M | | | |
| N | | | |
| R | | X | Non standard |

**S E M T**

## Tolerances





IC: theoretical diameter of inscribed circle
m: nose height
s: thickness

| Class | Tolerances (mm) | | |
|---|---|---|---|
| | m | IC | s |
| A | ±0,005 | ±0,025 | ±0,025 |
| F | ±0,005 | ±0,013 | ±0,025 |
| C | ±0,013 | ±0,025 | ±0,025 |
| H | ±0,013 | ±0,013 | ±0,025 |
| E | ±0,025 | ±0,025 | ±0,025 |
| G | ±0,025 | ±0,025 | ±0,13 |


| Class | Tolerances (mm) | | |
|---|---|---|---|
| | m | IC | s |
| J | ±0,005 | ±0,05 – ±0,13* | ±0,025 |
| K | ±0,013 | ±0,05 – ±0,13* | ±0,025 |
| L | ±0,025 | ±0,05 – ±0,13* | ±0,025 |
| M | ±0,08~ ±0,18*) | ±0,05 – ±0,13* | ±0,13 |
| N | ±0,08~ ±0,18*) | ±0,05 – ±0,13* | ±0,025 |
| U | ±0,13~ ±0,38*) | ±0,08 – ±0,25* | ±0,13 |




*) The tolerance is dependent upon the insert size of IC. See tables below.

**Tolerance class for dimension m**

| m | S | T | C | W | V | D |
|---|---|---|---|---|---|---|
| 6,35 | ±0,08 | | | | - | ±0,11 |
| 9,525 | ±0,08 | | | | ±0,13 | ±0,11 |
| 12,7 | ±0,13 | | | | | ±0,15 |
| 15,875 | ±0,15 | | | | | ±0,18 |
| 19,05 | ±0,15 | | | | | ±0,18 |
| 25,4 | ±0,18 | | | | | |





**Tolerance class for dimension IC**

| IC | S | T | C | D | V | W | R |
|---|---|---|---|---|---|---|---|
| 6,35 | ±0,05 | | | | | | |
| 9,525 | ±0,05 | | | | | | ±0,05 |
| 12,7 | ±0,08 | | | | | | ±0,08 |
| 15,875 | ±0,10 | | | | | | ±0,10 |
| 19,05 | ±0,10 | | | | | | ±0,10 |
| 25,4 | ±0,13 | | | | | | ±0,10 |

# ISO Identification Table




## Thickness




| | |
|---|---|
| **02** | s = 2,38 mm |
| **03** | s = 3,18 |
| **T3** | **s = 3,97** |
| **04** | s = 4,76 |
| **05** | s = 5,56 |
| **06** | s = 6,35 |
| **07** | s = 7,94 |
| **09** | s = 9,52 |

## Corner geometry with wiper flat


### Entering angle




| | |
|---|---|
| **A** | **45°** |
| **D** | 60° |
| **E** | 75° |
| **F** | 85° |
| **P** | 90° |
| **Z** | - Others |


1. Major cutting edge
2. Chamfered corner
3. Wiper flat
4. Side cutting edge

### Clearance angle on wiper flat



| | |
|---|---|
| **A** | 3° |
| **B** | 5° |
| **C** | 7° |
| **D** | 15° |
| **E** | 20° |
| **F** | **25°** |
| **G** | 30° |
| **N** | 0° |
| **P** | 11° |
| **Z** | - **Others** |

## Radius




| | |
|---|---|
| **02** | r = 0,2 mm |
| **04** | r = 0,4 |
| **08** | r = 0,8 |
| **12** | r = 1,2 |
| **16** | r = 1,6 |
| **20** | r = 2,0 |
| **24** | r = 2,4 |

**M0** - Round insert (metric)
**00** - Round insert (inch)


**1 3 T 3 A G S R**

## Insert size


Symbol and cutting edge length (mm)

| Insert type / IC / d (mm) | C | D | R | S | T | V | W |
|---|---|---|---|---|---|---|---|
| 3,97 | | | | | **06** (6,9) | | |
| 4,76 | | | | | **08** (8,2) | | |
| 5,0 | | | **05** (5,0) | | | | |
| 5,56 | | | | | **09** (9,6) | **09** (9,7) | **03** (3,8) |
| 6,0 | | | **06** (6,0) | | | | |
| 6,35 | **06** (6,4) | **07** (7,7) | | **06** (6,35) | **11** (11,0) | **11** (11,1) | **04** (4,3) |
| 7,94 | **08** (8,0) | | | **07** (7,94) | | | **05** (5,4) |
| 8,0 | | | **08** (8,0) | | | | |
| 9,525 | **09** (9,7) | **11** (11,6) | **09** (9,525) | **09** (9,525) | **16** (16,5) | **16** (16,6) | **06** (6,5) |
| 10 | | | **10** (10,0) | | | | |
| 12 | | | **12** (12,0) | | | | |
| **12,7** | **12** (12,9) | **15** (15,5) | **12** (12,7) | **12** (12,7) | **22** (22,0) | | **08** (8,7) |
| 15,875 | **16** (16,1) | **19** (19,4) | **15** (15,875) | **15** (15,875) | **27** (27,5) | | **10** (10,9) |
| 16 | | | **16** (16,0) | | | | |
| 19,05 | **19** (19,3) | | **19** (19,05) | **19** (19,05) | **33** (33,0) | | |
| 20 | | | **20** (20,0) | | | | |
| 25 | | | **25** (25,0) | | | | |
| 25,4 | | | **25** (25,4) | **25** (25,4) | | | |
| 31,75 | | | **31** (31,75) | **31** (31,75) | | | |
| 32 | | | **32** (32,0) | | | | |

## Cutting edge condition




## Feed direction



Expansion



## General Features

Sumi Dual Mill DGC type utilizes double-sided inserts for excellent economy. This is a general-purpose cutter featuring high cutting edge strength for high efficiency milling and low-burr chipbreaker design that provides high qualitiy machined surface.


The DGC type insert lineup includes double-sided SNMU / SNEU and ONMU / ONEU types.
Up to 16 corners can be used for improved economy.





## Characteristics

- Same cutting performance as single-sided inserts plus superior economy.
- Achieves level of cutting edge sharpness and machined surface quality equivalent to single-sided cutter at a maximum cutting depth of $a_p \leq 3$ mm.

## Recommended Cutting Conditions for General Steel Milling




## Cutting Force Comparison




| | |
|---|---|
| Work Material: | 34CrMo4 |
| Tool: | Ø 100 |
| Cutting Data: | $v_c$=200m/min, $f_z$=0,3mm/t, $a_p$=3mm, $a_e$=85mm |

## Dual-Purpose Body

Two types of inserts can be used with a single body depending on milling application to help reduce costs. Stronger than single-sided cutters.




– first recommendation
– economical double-sided design offers 8 cutting edges with SN_U inserts
– maximum depth of cut: $a_p$ = 6 mm







– double-sided design with 16 corners for improved economy
– maximum depth of cut: $a_p$ = 3 mm



max. $a_p$ = 6 mm
8 corners use

Use two types of inserts for different applications.



max. $a_p$ = 3 mm
16 corners use

## Line-up


Choose a tool that fits your application from a comprehensive line-up

| Cat. No | DGC 13000 RS | DGCM 13000 RS | DGCF 13000 RS | DGC 13000 EW |
|---|---|---|---|---|
| Type | Standard pitch | Medium pitch | Fine pitch | Endmill type |
| Cutter Diameter | Ø 40 mm – Ø 250 mm | Ø 50 mm – Ø 250 mm | Ø 50 mm – Ø 250 mm | Ø 40 mm – Ø 63 mm |
| Cutting Edges | 3–10 | 4–14 | 5–18 | 3–4 |
| Shape |  |  |  |  → H6 |


## High Reliability

Employs New Super ZX Coating, a multi-layer PVD coating grade and CVD coating grade with enhanced coating strength provided by newly developed stress control technology.
Improved run-out precision reduces tool life deviation to achieve highly reliable tool life.

## Multi-layer PVD Coating




## Wear Resistance





## Cutter Diameter and Cutter Body Height

Insert: SN_U 13T6 ANER (square)




Insert: ON_U 05T6 ANER (octagonal)





| Example: DC = 100mm | Number of Cutting Edges | Tool Diameter (mm) | Cutter Height (mm) | Max. Depth of Cut (mm) |
|---|---|---|---|---|
| SNMU/SNEU  | 8 | 100,0 | 63,0 | 6,0 |
| ONMU/ONEU  | 16 | 102,9 | 61,4 | 3,0 |

Square inserts (SNMU/SNEU) and octagonal inserts (ONMU/ONEU) can be used interchangeably on the same body.
Using these inserts the cutter will have different cutter diameter and cutter body height.

General Milling of Steel and Cast Iron

| Rake Angle | | |
|---|---|---|
| | Radial | –10° |
| | Axial | –5° |



SNMU ONMU

## Body – Shell type



Fig. 1





Fig. 2





Fig. 3






Fig. 4




Cutter body Ø DC ≥ 160 mm: no inner coolant

## Body

### ● Type: DGC, Standard Pitch

| Cat. No. | Stock | Dimension (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | D1 | KWW | KDP | CBDP | | | |
| DGC 13040 RS | ❍ | 40 (42,90) | 54 | 36 | 40 (38,44) | 16 | 13,5 | 8,4 | 5,6 | 18 | 3 | 0,3 | 1 |
| 13050 RS | ● | 50 (52,90) | 64 | 40 | 40 (38,44) | 22 | 18,0 | 10,4 | 6,3 | 20 | 3 | 0,4 | 1 |
| 13063 RS | ● | 63 (65,90) | 77 | 50 | 40 (38,44) | 22 | 18,0 | 10,4 | 6,3 | 20 | 4 | 0,5 | 1 |
| 13080 RS | ● | 80 (82,90) | 94 | 60 | 50 (48,44) | 27 | 20,0 | 12,4 | 7,0 | 25 | 4 | 1,2 | 1 |
| DGC 13100 RS | ● | 100 (102,90) | 114 | 70 | 50 (48,44) | 32 | 46,0 | 14,4 | 8,5 | 32 | 5 | 1,6 | 2 |
| 13125 RS | ● | 125 (127,90) | 139 | 80 | 63 (61,44) | 40 | 52,0 | 16,4 | 9,5 | 29 | 6 | 2,8 | 1 |
| 13160 RS | ❍ | 160 (162,90) | 174 | 130 | 63 (61,44) | 40 | 88,0 | 16,4 | 9,5 | 29 | 7 | 4,5 | 3 |
| DGC 13200 RS | ❍ | 200 (202,90) | 214 | 150 | 63 (61,44) | 60 | 130,0 | 25,7 | 14,0 | 35 | 8 | 7,1 | 4 |
| 13250 RS | ❍ | 250 (252,90) | 264 | 190 | 63 (61,44) | 60 | 160,0 | 25,7 | 14,0 | 35 | 10 | 11,2 | 4 |

### ● Type: DGCM, Medium Pitch

| Cat. No. | Stock | Dimension (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | D1 | KWW | KDP | CBDP | | | |
| DGCM 13050 RS | ● | 50 (52,90) | 64 | 40 | 40 (38,44) | 22 | 18 | 10,4 | 6,3 | 20 | 4 | 0,3 | 1 |
| 13063 RS | ● | 63 (65,90) | 77 | 50 | 40 (38,44) | 22 | 18 | 10,4 | 6,3 | 20 | 5 | 0,5 | 1 |
| 13080 RS | ● | 80 (82,90) | 94 | 60 | 50 (48,44) | 27 | 20 | 12,4 | 7,0 | 25 | 6 | 1,1 | 1 |
| DGCM 13100 RS | ● | 100 (102,90) | 114 | 70 | 50 (48,44) | 32 | 46 | 14,4 | 8,5 | 32 | 7 | 1,5 | 2 |
| 13125 RS | ● | 125 (127,90) | 139 | 80 | 63 (61,44) | 40 | 52 | 16,4 | 9,5 | 29 | 8 | 2,8 | 1 |
| 13160 RS | ● | 160 (162,90) | 174 | 130 | 63 (61,44) | 40 | 88 | 16,4 | 9,5 | 29 | 10 | 4,6 | 3 |
| DGCM 13200 RS | ❍ | 200 (202,90) | 214 | 150 | 63 (61,44) | 60 | 130 | 25,7 | 14,0 | 35 | 12 | 7,0 | 4 |
| 13250 RS | ❍ | 250 (252,90) | 264 | 190 | 63 (61,44) | 60 | 160 | 25,7 | 14,0 | 35 | 14 | 11,1 | 4 |

### ● Type: DGCF, Fine Pitch

| Cat. No. | Stock | Dimension (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | D1 | KWW | KDP | CBDP | | | |
| DGCF 13050 RS | ● | 50 (52,90) | 64 | 40 | 40 (38,44) | 22 | 18 | 10,4 | 6,3 | 20 | 5 | 0,3 | 1 |
| 13063 RS | ● | 63 (65,90) | 77 | 50 | 40 (38,44) | 22 | 18 | 10,4 | 6,3 | 20 | 6 | 0,5 | 1 |
| 13080 RS | ● | 80 (82,90) | 94 | 60 | 50 (48,44) | 27 | 20 | 12,4 | 7,0 | 25 | 8 | 1,1 | 1 |
| DGCF 13100 RS | ● | 100 (102,90) | 114 | 70 | 50 (48,44) | 32 | 46 | 14,4 | 8,5 | 32 | 10 | 1,4 | 2 |
| 13125 RS | ● | 125 (127,90) | 139 | 80 | 63 (61,44) | 40 | 52 | 16,4 | 9,5 | 29 | 12 | 2,7 | 1 |
| 13160 RS | ● | 160 (162,90) | 174 | 130 | 63 (61,44) | 40 | 88 | 16,4 | 9,5 | 29 | 14 | 4,4 | 3 |
| DGCF 13200 RS | ❍ | 200 (202,90) | 214 | 150 | 63 (61,44) | 60 | 130 | 25,7 | 14,0 | 35 | 16 | 6,9 | 4 |
| 13250 RS | ❍ | 250 (252,90) | 264 | 190 | 63 (61,44) | 60 | 160 | 25,7 | 14,0 | 35 | 18 | 11,0 | 4 |

( ) Figures in brackets indicate values for ONMU inserts.
Inserts are not included.

## Identification Details

| DGC | M | 13 | 050 | R | S |
|---|---|---|---|---|---|
| Cutter Series | M: Medium F: Fine | Insert Size | Cutter Diameter | Direction | Metric |



● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

# "Sumi Dual Mill"
# DGC Type

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | Cermet | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed/Light cut | ● | ● | ● | | | ● | ● | | ● | | ● | |
| General Purpose | ● | ● | | ● | ● | ● | ● | | ● | | ● | |
| Roughing | ● | | | ● | ● | | | ● | | ● | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | T4500A | Fig. |
| SNMU 13T6ANER L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 1 |
| 13T6ANER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 1 |
| 13T6ANER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 1 |
| 13T6ANER FL | ● | | ● | ● | ● | | ● | ● | | | | 2 |
| 13T6ANER FG | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 2 |
| SNEU 13T6ANER L | | | | | | | | | ● | ● | | 1 |
| 13T6ANER G | | | | | | | | | ● | ● | | 1 |
| 13T6ANER FL | | | | | | | | | ❍ | ❍ | | 2 |
| 13T6ANER FG | | | | | | | | | ● | ● | | 2 |
| XNEU 13T6ANEN W | ● | ❍ | | ● | | ❍ | | ● | | | ● | 3 |
| ONMU 05T6ANER L | ● | | ● | ● | ● | | ● | ● | | | | 4 |
| 05T6ANER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 4 |
| ONEU 05T6ANER L | | | | | | | | | ● | ● | | 4 |
| 05T6ANER G | | | | | | | | | ● | ● | | 4 |

Fig. 1





Fig. 2





Fig. 3







Fig. 4






## Chipbreaker




## Improved Milling Quality


FG type chipbreakers feature chamfer to minimize burrs and provide excellent milling qualitiy.





FG type inserts with low-burr design enable high-qualitiy milling with few burrs and little edge chipping.

## Attaching Inserts





**Octagonal Inserts**

Firmly align insert with supporting face, press down in the direction of the arrow and tighten the screw to fix the insert.




## Spare Parts

| Shim | Shim Screw | L Seat Wrench | Insert Srew | Insert Wrench |
|---|---|---|---|---|
|  |  |  |   |  |
| DGCS13R | BW0609F | LH040 | BFTX0412IP | TRDR15IP |

### Optional

| Insert Srew (*) |
|---|
|  |
| BFTX0418IP |

*Corners can be changed simply by loosening the screw. (Only suitable for DGC/DGCM types with body size ≥ Ø 80 mm).

## Recommended Cutting Conditions (SN_U)

| ISO | Work Material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (min/t) | Depth of Cut (mm) | Grade |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,10–**0,25**–0,40 | <4 | ACU2500 ACP200 ACP300 XCU2500 |
| | Alloyed Steel | ≤180 | 180–**250**–350 | 0,10–**0,30**–0,45 | <4 | |
| | Die Steel | 200–220 | 100–**150**–200 | 0,15–**0,25**–0,35 | <4 | |
| M | Stainless Steel | – | 160–**200**–250 | 0,15–**0,23**–0,30 | <3 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**200**–250 | 0,10–**0,25**–0,40 | <5 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Steel | – | 30–**50**–80 | 0,10–**0,20**–0,30 | <3 | ACU2500 ACM200 ACM300 |


## Recommended Cutting Conditions (ON_U)

| ISO | Work Material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (min/t) | Depth of Cut (mm) | Grade |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,10–**0,30**–0,50 | <2 | ACU2500 ACP200 ACP300 XCU2500 |
| | Alloyed Steel | ≤180 | 180–**250**–350 | 0,10–**0,50**–0,50 | <2 | |
| | Die Steel | 200–220 | 100–**150**–200 | 0,15–**0,25**–0,30 | <2 | |
| M | Stainless Steel | – | 160–**200**–250 | 0,15–**0,23**–0,30 | <2 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**200**–250 | 0,10–**0,30**–0,50 | <2 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Steel | – | 30–**50**–80 | 0,10–**0,20**–0,30 | <2 | ACU2500 ACM200 ACM300 |

Min. – **Optimum** – Max.

## General Milling of Steel and Cast Iron

| Rake Angle | | |
|---|---|---|
| | Radial | 20°–24° |
| | Axial | 20°–22° |




### Body – Shell type

Fig. 1







Fig. 2





Fig. 3






Fig. 4




Cutter body DC ≥ 160 mm: no inner coolant

### Body

Inner coolant available for DC ≤ Ø 125mm

#### ● Type: WGX, Standard Pitch

| Cat. No. | | Stock | Dimension (mm) | | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | DC | DCX | DCSFMS | LF | DCB | D1 | D2 | KWW | KDP | CBDP | | | |
| WGX | 13040 RS | ● | 40 | 52 | 32 | 40 | 16 | 14,0 | 9,0 | 8,4 | 5,6 | 18 | 3 | 0,3 | 1 |
| | 13050 RS | ● | 50 | 62 | 40 | 40 | 22 | 18,0 | 11,0 | 10,4 | 6,3 | 20 | 3 | 0,4 | 1 |
| | 13063 RS | ● | 63 | 76 | 50 | 40 | 22 | 18,0 | 11,0 | 10,4 | 6,3 | 20 | 4 | 0,6 | 1 |
| | 13080 RS | ● | 80 | 93 | 55 | 50 | 27 | 20,0 | 13,5 | 12,4 | 7,0 | 25 | 4 | 1,2 | 1 |
| WGX | 13100 RS | ● | 100 | 113 | 70 | 50 | 32 | 46,0 | - | 14,4 | 8,5 | 32 | 5 | 1,6 | 2 |
| | 13125 RS | ● | 125 | 138 | 80 | 63 | 40 | 52,0 | 29,0 | 16,4 | 9,5 | 29 | 6 | 2,8 | 1 |
| | 13160 RS | ● | 160 | 173 | 130 | 63 | 40 | 88,0 | - | 16,4 | 9,5 | 29 | 7 | 4,5 | 3 |
| WGX | 13200 RS | ● | 200 | 213 | 150 | 63 | 60 | 130,0 | - | 25,7 | 14,0 | 35 | 8 | 7,1 | 4 |
| | 13250 RS | ❍ | 250 | 263 | 190 | 63 | 60 | 160,0 | - | 25,7 | 14,0 | 35 | 10 | 11,2 | 4 |

#### ● Type: WGXM, Medium Pitch

| Cat. No. | | Stock | Dimension (mm) | | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | DC | DCX | DCSFMS | LF | DCB | D1 | D2 | KWW | KDP | CBDP | | | |
| WGXM | 13050 RS | ● | 50 | 62 | 40 | 40 | 22 | 18,0 | 11,0 | 10,4 | 6,3 | 20 | 4 | 0,4 | 1 |
| | 13063 RS | ● | 63 | 77 | 50 | 40 | 22 | 18,0 | 11,0 | 10,4 | 6,3 | 20 | 5 | 0,6 | 1 |
| | 13080 RS | ● | 80 | 94 | 55 | 50 | 27 | 20,0 | 13,5 | 12,4 | 7,0 | 25 | 6 | 1,1 | 1 |
| WGXM | 13100 RS | ● | 100 | 114 | 70 | 50 | 32 | 46,0 | - | 14,4 | 8,5 | 32 | 7 | 1,6 | 2 |
| | 13125 RS | ● | 125 | 139 | 80 | 63 | 40 | 52,0 | 29,0 | 16,4 | 9,5 | 29 | 8 | 2,8 | 1 |
| | 13160 RS | ● | 160 | 174 | 130 | 63 | 40 | 88,0 | - | 16,4 | 9,5 | 29 | 10 | 4,5 | 3 |
| WGXM | 13200 RS | ● | 200 | 214 | 150 | 63 | 60 | 130,0 | - | 25,7 | 14,0 | 35 | 12 | 7,0 | 4 |
| | 13250 RS | ❍ | 250 | 264 | 190 | 63 | 60 | 160,0 | - | 25,7 | 14,0 | 35 | 14 | 11,1 | 4 |

#### ● Type: WGXF, Fine Pitch

| Cat. No. | | Stock | Dimension (mm) | | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | DC | DCX | DCSFMS | LF | DCB | D1 | D2 | KWW | KDP | CBDP | | | |
| WGXF | 13050 RS | ● | 50 | 62 | 40 | 40 | 22 | 18,0 | 11,0 | 10,4 | 6,3 | 20 | 5 | 0,4 | 1 |
| | 13063 RS | ● | 63 | 77 | 50 | 40 | 22 | 18,0 | 11,0 | 10,4 | 6,3 | 20 | 6 | 0,6 | 1 |
| | 13080 RS | ● | 80 | 94 | 55 | 50 | 27 | 20,0 | 13,5 | 12,4 | 7,0 | 25 | 8 | 1,1 | 1 |
| WGXF | 13100 RS | ● | 100 | 114 | 70 | 50 | 32 | 46,0 | - | 14,4 | 8,5 | 32 | 10 | 1,5 | 2 |
| | 13125 RS | ● | 125 | 139 | 80 | 63 | 40 | 52,0 | 29,0 | 16,4 | 9,5 | 29 | 12 | 2,7 | 1 |
| | 13160 RS | ● | 160 | 174 | 130 | 63 | 40 | 88,0 | - | 16,4 | 9,5 | 29 | 16 | 4,5 | 3 |
| WGXF | 13200 RS | ● | 200 | 214 | 150 | 63 | 60 | 130,0 | - | 25,7 | 14,0 | 35 | 20 | 6,9 | 4 |
| | 13250 RS | ❍ | 250 | 264 | 190 | 63 | 60 | 160,0 | - | 25,7 | 14,0 | 35 | 24 | 11,0 | 4 |

( ) Figures in brackets indicate values for ONMU inserts.
Inserts are not included.

### Identification Details

| WGX | M | 13 | 050 | R | S |
|---|---|---|---|---|---|
| Cutter Series | M: Medium<br>F: Fine | Insert Size | Cutter Diameter | Direction | Metric |



● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

# "Wave Face Mill"
# WGX (M/F) Type



## General Features

The Wavemill WGX Type employs unique chipbreaker design to provide lower cutting resistance and higher quality surface finishes than conventional tools.

## Series

| Type | Cat. No. | Cutter | No. of Teeth |
|---|---|---|---|
| Standard Pitch | WGX 13000RS | Ø 40 – Ø 250 | 3–10 |
| Medium Pitch | WGXM 13000RS | Ø 50 – Ø 250 | 4–14 |
| Fine Pitch | WGXF 13000RS | Ø 50 – Ø 250 | 5–24 |
| Endmill Type | WGX 13000EW | Ø 32 – Ø 63 | 3–5 |

Inner coolant available for DC ≤ Ø 125 mm


→ H7

## Characteristics

- **Stable Cutting**
  Special chipbreaker designed for WGX enables lower cutting forces.
- **High Quality**
  Improved run-out precision and unique wiper edge shape ensure excellent surface finish quality.
  Optimised chamfer edge reduces burr and edge chipping.
- **Long Tool Life**
  Features high precision technology that reduces insert run-out variation and a new coating to provide stable and long tool life.

## Insert Shape Characteristics

Unique wiper edge shape for improved surface roughness




## Inserts

| Application | Coated Carbide | | | | | | | | | | Carb. | DLC | Cermet | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed/Light Cut | | | P | | | K | K | | M S | | K N | N | | |
| General Purpose | | | | P M | M | K | K | | M S | M S | | N | P M | |
| Roughing | | | | P M | P M | | | K | | M S | | | P | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | T4500A | Fig. |
| SEET 13T3AGFR-L | | | | | | | | | | | ❍ | ❍ | | 1 |
| SEET 13T3AGSR-L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | ● | 1 |
| 13T3AGSR-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | ● | 1 |
| SEMT 13T3AGSR-L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | 1 |
| 13T3AGSR-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | 1 |
| 13T3AGSR-H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | 1 |
| SEMT 13T3AGSR-FG | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | 2 |
| XEEW 13T3AGER-WR | ● | ❍ | | ❍ | | ❍ | | ❍ | | | | | ❍ | 3 |

Dimensions (mm)

Fig. 1





Fig. 2







Fig. 3




## Spare Parts

| Applicable Cutters | Shim | Shim Screw | Insert Screw | Insert Wrench | Seat Wrench |
|---|---|---|---|---|---|
| |  |  |  3,0 N·m |  |  |
| WGX (-M/F) | WGCS 13 R | BW 0507 F | BFTX 03512 IP | TRDR 15 IP | LH 035 |

## Recommended Cutting Conditions


| ISO | Work Material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/tooth) | Grade |
|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,15–**0,20**–0,25 | ACU2500 ACP200 XCU2500 |
| P | Soft Steel | ≤180 | 180–**265**–350 | 0,10–**0,25**–0,40 | |
| P | Die Steel | 200–220 | 100–**150**–200 | 0,15–**0,20**–0,25 | |
| M | Stainless Steel | - | 160–**205**–250 | 0,15–**0,23**–0,30 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**175** –250 | 0,15–**0,23**–0,30 | ACU2500 ACK200 XCK2000 |
| N | Non Ferrous Alloy | - | 500–**750**–1000 | 0,15–**0,23**–0,30 | DL1000 |
| S | Exotic Alloy | - | 30 – **50**– 80 | 0,10–**0,20**–0,30 | ACU2500 ACM300 |

Minimum-**Optimum**-Maximum

## General Milling for Steel, Cast Iron & Exotic Material



## Specifications




Approach angle: 45°
Axial rake angle: + 27°
Radial rake angle: - 7°
(-10° for ø 50 and ø 63)
max depth of cut: 5,0 mm (UFO 4000 type)
7,0 mm (UFO 5000 type)

## Body

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | | No. of Teeth | Max. Depth of Cut | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | | | | |
| UFO 4050 R/L-S | ● | | 50 | 74 | 45 | 50 | 22 | 10,4 | 6,3 | 20 | 4 | | 1,3 | 1 |
| 4063 R/L-S | ● | | 63 | 86 | 50 | 50 | 22 | 10,4 | 6,3 | 20 | 5 | | 1,6 | 1 |
| 4080 R/L-S | ● | | 80 | 103 | 60 | 50 | 27 | 12,4 | 7,0 | 25 | 5 | | 2,1 | 1 |
| UFO 4100 R/L-S | ● | ● | 100 | 122 | 75 | 50 | 32 | 14,4 | 8,5 | 29 | 6 | | 2,9 | 2 |
| 4125 R/L-S | ● | | 125 | 146 | 75 | 63 | 40 | 16,4 | 9,5 | 29 | 7 | 5,0 | 4,2 | 2 |
| 4160 R/L-S | ● | | 160 | 180 | 100 | 63 | 40 | 16,4 | 9,5 | 29 | 9 | | 6,6 | 3 |
| UFO 4200 R/L-S | ● | | 200 | 220 | 130 | 63 | 60 | 25,7 | 14,0 | 32 | 11 | | 9,5 | 4 |
| 4250 R/L-S | ❑ | | 250 | 270 | 300 | 63 | 60 | 25,7 | 14,0 | 40 | 13 | | 14,8 | 4 |
| UFO 4315 R/L-S | ❑ | | 315 | 335 | 240 | 80 | 60 | 25,7 | 14,0 | 40 | 15 | | 26,6 | 5 |
| UFO 5080 R/L-S | ❑ | | 80 | 102 | 60 | 50 | 27 | 12,4 | 7,0 | 25 | 5 | | 2,1 | 1 |
| UFO 5100 R/L-S | ● | | 100 | 119 | 75 | 50 | 32 | 14,4 | 8,5 | 29 | 6 | | 2,9 | 2 |
| 5125 R/L-S | ● | | 125 | 143 | 75 | 63 | 40 | 16,4 | 9,5 | 29 | 7 | | 4,2 | 2 |
| 5160 R/L-S | ● | | 160 | 177 | 100 | 63 | 40 | 16,4 | 9,5 | 29 | 9 | 7,0 | 6,6 | 3 |
| UFO 5200 R/L-S | ● | | 200 | 217 | 130 | 63 | 60 | 25,7 | 14,0 | 32 | 11 | | 9,5 | 4 |
| 5250 R/L-S | ❑ | | 250 | 267 | 200 | 63 | 60 | 25,7 | 14,0 | 40 | 13 | | 14,8 | 4 |
| UFO 5315 R/L-S | ❑ | | 315 | 332 | 240 | 80 | 60 | 25,7 | 14,0 | 40 | 15 | | 26,6 | 5 |

Fig. 1





Fig. 2





Fig. 3





Fig. 4








Fig. 5





## Spare Parts

| Cutter | Locator | Insert block | Insert clamp |
|---|---|---|---|
| |  |  |  |
| 4050–4063 | UF 4 K R/L | S-UF 4 S R/L | UFTW R/L |
| 4080–4315 | UF 4 K R/L | UF 4 S R/L | |
| 5080–5315 | UF 5 K R/L | UF 5 S R/L | |

| Cutter | Locator clamp | Double screw | Wrench |
|---|---|---|---|
| |  |  |  |
| 4050–4063 | UFKW R/L | WB 7-15 T | TT 25 |
| 4080–4315 | | | |
| 5080–5315 | | | |

## Structure






● = Euro stock
○ = Japan stock
❑ = Delivery on request

## Features

- 45° approach face mills
- 27° super high rake multi purpose cutter for outstanding productivity milling steels, irons and alloys
- Substantially improves metal removal rates on low powered machines
- Differential pitched inserts guarantee smooth cutting action
- Rigid body incorporates carbide locators and HSS shims resulting in extremely low run out



## Body (Fine Pitch Type)

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | | No. of Teeth | Max. Depth of Cut | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | | | | |
| UFOF 4080 R/L-S | ● | | 80 | 103 | 60 | 50 | 27 | 12,4 | 7,0 | 25 | 6 | 5,0 | 2,1 | 1 |
| UFOF 4100 R/L-S | ● | | 100 | 122 | 75 | 50 | 32 | 14,4 | 8,5 | 29 | 8 | | 2,9 | 2 |
| 4160 R/L-S | ● | | 160 | 180 | 100 | 63 | 40 | 16,4 | 9,5 | 29 | 12 | | 6,6 | 3 |
| UFOF 4200 R/L-S | ❑ | | 200 | 220 | 130 | 63 | 60 | 25,7 | 14,0 | 32 | 16 | | 9,5 | 4 |
| 4250 R/L-S | ❑ | | 250 | 270 | 300 | 63 | 60 | 25,7 | 14,0 | 40 | 20 | | 14,8 | 4 |
| UFOF 4315 R/L-S | ❑ | | 315 | 335 | 240 | 80 | 60 | 25,7 | 14,0 | 40 | 24 | | 26,6 | 5 |

## Insert

Dimensions (mm)

| Grade | | Coated Carbide | | | | | Cermet | Uncoated Carbide | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed/Light Cut | | P | | | K | | | | | | | K N |
| General Purpose | | | P M | P M | K | | P | P | K | K | | |
| Roughing | | | P M | P M | | K | | | | | | |
| Cat. No. | | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | T250A | A30N | G10E | H1 | H10E | Fig. |
| UFO(F) 4000 | SFKN 12T3 AZFN | | | | ● | ● | | | ● | ● | | 1(2) |
| | 12T3 AZTN | ● | ● | ● | | | ❍ | ❍ | ● | | | 1(2) |
| | SFKR 12T3 AZTN | | ❑ | | | | | | | | | 3 |
| | UW 12500 R | | | | | | | | | | ❍ | 4 |
| UFO 5000 | SFKN 1504 AZFN | | | | | ❍ | | | | | | 5(6) |
| | 1504 AZTN | ● | ● | ● | | | | | | | | 5(6) |
| | | | | | | | | | | | | |
| | | | | | | | | | | | | |

Fig. 1 (Grades: ACP_, ACK_)





Fig. 2





Fig. 3





Fig. 4





Fig. 5 (Grades: ACP_, ACK_)






Fig. 6




## Recommended Cutting Conditions

($v_c$ =m/min, $f_z$ =mm/tooth) (min.– **optimum** – max.)

| Grade | | ACP100 | | | ACP200 | | | ACP300 | | ACK200 | | ACK300 | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Work Material / Insert Type | | Low carbon steel | Alloy steel | Die steel | Low carbon steel | Alloy steel | Die steel | Stainless steel austenitic | Stainless steel martensitic | Cast iron | Ductile cast iron | Cast iron | Ductile cast iron |
| UFO (-F) 4000 | $v_c$ | 100–**250**–400 | 80–**220**–280 | 80–**150**–250 | 80–**200**–370 | 70–**150**–250 | 60–**130**–220 | 120–**180**–240 | 100-**140**-200 | 220–**270**–450 | 150–**180**–250 | 180–**220**–270 | 130–**160**–220 |
| | $f_z$ | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 | 0,1–**0,2**–0,3 | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 | 0,1–**0,2**–0,3 | 0,1–**0,2**–0,3 | 0,1-**0,2**-0,3 | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 |
| | $a_p$ | 1,0–**3,0**–5,0 | | | 1,0–**3,0**–5,0 | | | 1,0–**2,0**–3,0 | | 1,0–**3,0**–5,0 | | 1,0–**3,0**–5,0 | |
| UFO (-F) 5000 | $v_c$ | 100–**250**–400 | 80–**220**–280 | 80–**150**–250 | 80–**200**–370 | 70–**150**–250 | 60–**130**–220 | 120–**180**–240 | 100–**140**–200 | 220-**270**-450 | 150–**180**–250 | 180–**220**–270 | 130–**160**–220 |
| | $f_z$ | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 | 0,1–**0,2**–0,3 | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 | 0,1–**0,2**–0,3 | 0,1–**0,2**–0,3 | 0,1–**0,2**–0,3 | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 | 0,1–**0,25**–0,4 |
| | $a_p$ | 1,0–**4,0**–7,0 | | | 1,0–**4,0**–7,0 | | | 1,0–**2,0**–5,0 | | 1,0–**4,0**–7,0 | | 1,0–**4,0**–7,0 | |

# Face Mill
# DNX / DNXF Type

## General Milling for Cast Iron and Steel

| | | |
|---|---|---|
| Approach angle | : | 65° |
| Axial rake angle | : | + 5° |
| Radial rake angle | : | - 6° |

8 mm / 65°



Fig. 1





Fig. 2





Fig. 3






Fig. 4




## ■ Body


### ● Standard DNX - Type

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No of Teeth | Max. Depth of Cut | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | D1 | KWW | KDP | CBDP | | | | |
| DNX 12080 RS | ● | 80 | 88 | 60 | 50 | 27 | - | 12,4 | 7,0 | 25 | 6 | 8,0 | 1,2 | 1 |
| DNX 12100 RS | ● | 100 | 108 | 80 | 50 | 32 | 46 | 14,4 | 8,5 | 29 | 7 | | 1,6 | 2 |
| 12125 RS | ● | 125 | 133 | 80 | 63 | 40 | 56 | 16,4 | 9,5 | 29 | 8 | | 2,8 | 2 |
| 12160 RS | ● | 160 | 168 | 100 | 63 | 40 | 88 | 16,4 | 9,5 | 29 | 10 | | 4,4 | 3 |
| DNX 12200 RS | ❑ | 200 | 210 | 150 | 63 | 60 | 130 | 25,7 | 14,0 | 35 | 16 | | 8,0 | 4 |
| 12250 RS | ❑ | 250 | 260 | 180 | 63 | 60 | 160 | 25,7 | 14,0 | 25 | 20 | | 12,2 | 4 |


### ● Fine Pitch DNXF - Type

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No of Teeth | Max. Depth of Cut | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | D1 | KWW | KDP | CBDP | | | | |
| DNXF 12080 RS | ● | 80 | 88 | 60 | 50 | 27 | - | 12,4 | 7,0 | 25 | 8 | 8,0 | 1,2 | 1 |
| DNXF 12100 RS | ● | 100 | 108 | 80 | 50 | 32 | 46 | 14,4 | 8,5 | 29 | 10 | | 1,6 | 2 |
| 12125 RS | ● | 125 | 133 | 80 | 63 | 40 | 56 | 16,4 | 9,5 | 29 | 11 | | 2,7 | 2 |
| 12160 RS | ● | 160 | 168 | 100 | 63 | 40 | 88 | 16,4 | 9,5 | 29 | 12 | | 4,4 | 3 |

## ■ First Recommendation: DNX




**DNX / DNXF**




Wiper width = 1,2 mm



| Max. depth of cut : 8 mm, Approach angle : 65° | | |
|---|---|---|
| Cutter Type | Diameter Range | Characteristics |
| DNX 12000 RS | Ø 80–Ø 250 mm | - General purpose<br>- Medium pitch type |
| DNXF 12000 RS | Ø 80–Ø 160 mm | - General purpose<br>- Fine pitch type |

## ■ Spare Parts

| Cutter | Insert Screw | Insert Wrench | Locator | Clamp Screw | Wrench |
|---|---|---|---|---|---|
| |  3,0 N·m |  |  |  |  |
| Ø 80 – Ø 160 | BFTX0412 IP | TRDR15 IP | – | – | – |
| Ø 200, Ø 250 | | | DNXK 12 R | BX 0515 | LH 040 |

## ■ Identification Details

**DNX F 12 080 R S**

| DNX | F | 12 | 080 | R | S |
|---|---|---|---|---|---|
| Cutter type | Fine pitch | Insert size | Diam. | Cutting direction | Shell type |



● = Euro stock
○ = Japan stock

❑ = Delivery on request

N·m Recommended Tightening Torque (N·m)



## Features

- Small inserts with 8 cutting edges
- Economic by double-side usage
- Excellent grade for cast iron machining
- Optimised geometry for best results in cast iron
- Special inserts for steel machining

## Insert

Dimensions (mm)

| Application | Coated Carbide | | | | | |
|---|---|---|---|---|---|---|
| High Speed/Light cut | | | K | K | | |
| General Purpose | P M | P M | K | K | | |
| Roughing | P M | P M | | | K | |
| Cat. No. | ACP200 | ACP300 | ACK100 | ACK200 | ACK300 | Fig. |
| SNMT 1205 ZNEN-L | ❍ | | | | | 1 |
| 1205 ZNEN-G | ● | | ● | ● | ● | 1 |
| 1205 ZNEN-H | ● | | ● | ● | ● | 2 |
| 1205 ZNEN-SH | ● | ❍ | ● | ● | ● | 3 |

Fig. 1 **L/G** Type





Fig. 2 **H** Type






Fig. 3 **SH** Type




**L** Type : For light machining
**G** Type : For general purpose
**H** Type : For heavy machining
**SH** Type : For steel machining

- Negative inserts
- Inserts with 8 cutting edges
- Applicable for steel machining



## Advantage of SH-Type when Steel machining

**G** Type



Chip packing causes higher cutting forces !

**SH** Type



Smooth chip evacuation reduces cutting forces !

## Recommended Cutting Conditions

($v_c$ = m/min, $f_z$ = mm/tooth) (min.– **optimum** – max.)

| ISO | Work Material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_t$ (mm/tooth) | Insert Grade |
|---|---|---|---|---|---|
| P | Carbon steel | 180–280 | 150–**175**–200 | 0,10–**0,15**–0,20 | ACP200 |
| | Alloy steel | 180–280 | 150–**175**–200 | 0,10–**0,15**–0,20 | ACP200 |
| K | Grey cast iron (GG) | 250 | 150–**225**–300 | 0,10–**0,20**–0,30 | ACK200/ACK300 |
| | Ductile cast iron (GGG) | 250 | 150–**225**–250 | 0,10–**0,18**–0,25 | ACK200/ACK300 |

# "Wave Radius Mill"
# WRCX Type



## Features

The "Wave Mill" WRCX type is a new multi purpose milling cutter for face milling, slotting, helical boring, plunging and profiling. Its unique design features 16 corner polygon inserts and a durable cutter body manufactured from high tensile alloyed steel protected by a hard surface treatment. Insert rigidity is maximised via close tolerance seat pockets and centre clamped using a torxscrew . Choose from a variety of insert grades such as our award winning Diamond like Carbon DL 1000 capable of high feed machining aluminium, our uncoated H1 grade suitable for non-ferrous metals or our new ACP/ACK grades for steels and irons.

## Advantages

- Durable cutter body – Special alloyed steel with hard surface.
- High feed cutting – Optimised pitch and high number of cutting edges
- Excellent chip removal – Wide pocket and integral coolant hole
- Maximum rigidity – Rigid clamping of inserts with TORXPLUS screw
- Wide application range – Carbon steels, alloy steels, stainless steels, high temperature alloys, diemould steels, aluminiums, non-ferrous metals etc

## Insert

| Application | Coated Carbide | | | | | Uncoated Carbide | Diamond Coated |
|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | K N | N |
| General Purpose | | P M | P M | K | | | N |
| Roughing | | P M | P M | | K | | |

| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | H1 | DL1000 | Dimensions (mm) IC | RE | S | Fig. | Applicable Endmill |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| QPMT 120440 PPEN | ● | ● | ● | ● | ● | | | 12 | 4,0 | 4,76 | 1 | WRCX/-F 12000 RS |
| 120440 PPEN-H | ● | ● | ● | ● | ● | | | | | | | |
| QPET 120460 PPFR-S | | | | | | ● | ● | | 6,0 | | 2 | WRCX/-F/-X 16000 RS |
| QPMT 160660 PPEN | ● | ● | ● | ● | ● | | | 16 | 6,0 | 6,5 | 1 | |
| 160660 PPEN-H | ● | ● | ● | ● | ● | | | | | | | |
| QPET 160680 PPFR-S | | | | | | ● | ● | | 8,0 | | 2 | WRCXF 20000 RS |
| QPMT 200670 PPEN | | ● | ● | ● | ● | | | 20 | 7,0 | 6,5 | 1 | |
| 200670 PPEN-H | | ● | ● | ● | ● | | | | | | | |

Fig. 1






Fig. 2




QPMT... : Standard 16 cornered polygon type
QPMT...-H: Stronger cutting edge type

QPET...-S: Polished round insert for non-ferrous material

## ● Anti-Vibration Type (Paired Sets for Vibration Free Machining)

| Application | Coated Carbide | | | | | Uncoated Carbide | Diamond Coated |
|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | K N | N |
| General Purpose | | P M | P M | K | | | N |
| Roughing | | P M | P M | | K | | |

| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | H1 | DL1000 | Dimensions (mm) IC | RE | S | Fig. | Applicable Endmill |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| QPMT 160608 PPEN | ● | ● | ● | ● | ● | | | 16 | 0,8 | 6,5 | 1 | WRCX/-F/-X 16000 RS |
| 160608 PPEN-CP | | ● | ● | ● | ● | | | | | | 3 | |
| QPMT 200608 PPEN | ● | ● | ● | | ● | | | 20 | 0,8 | 6,5 | 1 | WRCXF 20000 RS |
| 200608 PPEN-CP | | ● | ● | | ● | | | | | | 3 | |

Fig. 1
08







Fig.3
CP




The combination of different inserts in a staggered formation varies the cut depth and eliminates vibration when feed rate is

$f_z < 0,15$ (IC = 16 mm)
or
$f_z < 0,2$ (IC = 20 mm).




## ● Chip Formation

| Anti-vibration Type | Standard Type |
|---|---|
|  |  |

| | |
|---|---|
| Work Material: | 50C |
| Cutting Data: | $f_z$ = 0,1mm/tooth, $a_p$ = 7 mm |
| Insert Size: | IC = 20 mm |



● = Euro stock
○ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)



Fig. 1





Fig. 2






Fig. 3

Axial rake angle: - 3°
Radial rake angle: 0°




## ■ Body

* Note Fig.3 for DCX=160 : Coolant cap (CCAP-160) with 4 screws (BX0620) and wrench (TH050) is available seperately.

### ● Standard WRCX Type

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | | | No. of Teeth | Helical Boring øB Standard | Ramping αmax. | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX* | DC | BD | DCSFMS | LF* | KWW | KDP | DCB | D2 | D1 | CBDP | | | | | |
| WRCX 12040 RS | ● | 40 | 28 | 36 | 36 | 40 | 8,4 | 5,6 | 16 | 9 | 14 | 18 | 4 | 68 ± 11 | 10° | 0,2 | 1 |
| 12050 RS | ● | 50 | 38 | 46 | 40 | 40 | 10,4 | 6,3 | 22 | 11 | 18 | 20 | 4 | 88 ± 11 | 7° | 0,3 | 1 |
| 12052 RS | ● | 52 | 40 | 48 | 40 | 40 | 10,4 | 6,3 | 22 | 11 | 18 | 20 | 5 | 92 ± 11 | 6°30' | 0,3 | 1 |
| 12063 RS | ● | 63 | 51 | 59 | 40 | 40 | 10,4 | 6,3 | 22 | 11 | 18 | 20 | 5 | 114 ± 11 | 5° | 0,4 | 1 |
| 12080 RS | ● | 80 | 68 | 76 | 55 | 50 | 12,4 | 7,0 | 27 | 13,5 | 20 | 25 | 6 | 148 ± 11 | 3°30' | 0,9 | 1 |
| WRCX 16063 RS | ● | 63 | 47 | 50 | 50 | 40 | 10,4 | 6,3 | 22 | 11 | 18 | 20 | 3 | 110 ± 15 | 8° | 0,4 | 1 |
| 16080 RS | ● | 80 | 64 | 70 | 55 | 50 | 12,4 | 7,0 | 27 | 13,5 | 20 | 25 | 4 | 144 ± 15 | 5°30' | 0,8 | 1 |
| WRCX 16100 RS | ● | 100 | 84 | 90 | 70 | 50 | 14,4 | 8,5 | 32 | - | 46 | 32 | 5 | 184 ± 15 | 4° | 1,3 | 2 |
| 16125 RS | ❑ | 125 | 109 | 115 | 80 | 63 | 16,4 | 9,5 | 40 | - | 52 | 38 | 5 | 234 ± 15 | 3° | 2,4 | 2 |


### ● Fine Pitch WRCXF Type

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | | | No. of Teeth | Helical Boring øB Standard | Ramping αmax. | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX* | DC | BD | DCSFMS | LF* | KWW | KDP | DCB | D2 | D1 | CBDP | | | | | |
| WRCXF 12050 RS | ❍ | 50 | 38 | 46 | 40 | 40 | 10,4 | 6,3 | 22 | 11 | 18 | 20 | 5 | 88 ± 11 | 7° | 0,3 | 1 |
| 12063 RS | ❍ | 63 | 51 | 59 | 40 | 40 | 10,4 | 6,3 | 22 | 11 | 18 | 20 | 6 | 114 ± 11 | 5° | 0,4 | 1 |
| WRCXF 16052 RS | ● | 52 | 36 | 45 | 45 | 40 | 10,4 | 6,3 | 22 | 11 | 17,7 | 20 | 4 | 88 ± 15 | 10° | 0,3 | 1 |
| 16063 RS | ● | 63 | 47 | 50 | 50 | 40 | 10,4 | 6,3 | 22 | 11 | 18 | 20 | 4 | 110 ± 15 | 8° | 0,4 | 1 |
| 16080 RS | ● | 80 | 64 | 70 | 55 | 50 | 12,4 | 7,0 | 27 | 13,5 | 20 | 25 | 5 | 144 ± 15 | 5°30' | 0,8 | 1 |
| WRCXF 16100 RS | ● | 100 | 84 | 90 | 70 | 50 | 14,4 | 8,5 | 32 | - | 46 | 32 | 6 | 184 ± 15 | 4° | 1,3 | 2 |
| 16125 RS | ● | 125 | 109 | 115 | 80 | 63 | 16,4 | 9,5 | 40 | 29 | 52 | 29 | 6 | 234 ± 15 | 3° | 2,4 | 1 |
| 16160 RS | ● | 160 | 144 | 150 | 100 | 63 | 16,4 | 9,5 | 40 | - | 93 | 29 | 8 | 304 ± 15 | 2° | 4,0 | 3* |
| WRCXF 20080 RS | ● | 80 | 60 | 68 | 55 | 50 | 12,4 | 7,0 | 27 | 13,5 | 20 | 25 | 5 | 140 ± 18 | 7° | 0,7 | 1 |
| WRCXF 20100 RS | ● | 100 | 80 | 88 | 70 | 50 | 14,4 | 8,5 | 32 | - | 46 | 32 | 6 | 180 ± 18 | 5° | 1,1 | 2 |
| 20125 RS | ● | 125 | 105 | 113 | 80 | 63 | 16,4 | 9,5 | 40 | 29 | 52 | 29 | 6 | 230 ± 18 | 3°30' | 2,3 | 1 |
| 20160 RS | ● | 160 | 140 | 148 | 100 | 63 | 16,4 | 9,5 | 40 | - | 93 | 29 | 8 | 300 ± 18 | 2°30' | 3,9 | 3* |

### ● Extra Fine Pitch WRCXX Type

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | | | No. of Teeth | Helical Boring øB Standard | Ramping αmax. | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX* | DC | BD | DCSFMS | LF* | KWW | KDP | DCB | D2 | D1 | CBDP | | | | | |
| WRCXX 16080 RS | ● | 80 | 64 | 70 | 55 | 50 | 12,4 | 7,0 | 27 | 13,5 | 20 | 25 | 6 | 144 ± 15 | 5°30' | 0,8 | 1 |
| 16100 RS | ● | 100 | 84 | 90 | 70 | 50 | 14,4 | 8,5 | 32 | - | 46 | 32 | 7 | 184 ± 15 | 4° | 1,3 | 2 |


* Note : When using CP type anti-vibration inserts / IC = 16, please change above dimensions: DCX* +0,3 & LF* +0,15 mm
In case of anti-vibration inserts / IC = 20, please change above dimensions: DCX* +0,4 & LF* +0,2 mm




## ■ Maximum Rotation (min$^{-1}$) for Non-ferrous cutting when using QPET Insert

| Cutter DC (mm) | Insert Cat. No. | | |
|---|---|---|---|
| | QPET**10**...**S** | QPET**12**...**S** | QPET**16**...**S** |
| **25** | 28.000 | | |
| **32** | 25.000 | | |
| **40** | | 22.000 | 15.000 |
| **50** | | 20.000 | 14.000 |
| **63** | | 18.000 | 13.000 |
| **80** | | 16.000 | 12.000 |
| **100** | | | 10.000 |
| **125** | | | 9.000 |
| **160** | | | 8.000 |


**Ramping (Slant Milling)**




α max : (see tables)

**Helical Boring**

øB Standard : (see tables)




## ■ Spare Parts

| Cutter | | Screw | | Screw |
|---|---|---|---|---|
| | |  | N·m |  |
| WRCX | 12○○○ | BFTX 0409 IP | 3,0 | TRDR 15 IP |
| WRCX/-F/-X | 16052–16100 | BFTX 0511 IP | 5,0 | TRDR 20 IP |
| | 16125–16160 | BFTX 0513 IP | 5,0 | |
| WRCX/-F | 20○○○ | BFTX 0615 IP | 5,0 | TRDR 25 IP |

## ■ Recommended Cutting Conditions

| DCX (mm) \ Material / Grade | | Carbon steel (ex. C40 ~ C50) | Alloy steel (Below HRC40) | Stainless steel (ex. X10CrNiS18-9) | Cast iron (ex. GG20) | Non-ferrous material |
|---|---|---|---|---|---|---|
| | | ACP100, ACP200 | ACP100, ACP200 | ACP200, ACP300 | ACK200, ACK300 | DL1000, H1 |
| 40 ~ 80 | $v_c$ | 100–**160**–200 | 100–**140**–180 | 80–**120**–160 | 80–**120**–160 | 200–**500**–1000 |
| | $f_z$ | 0,2–**0,4**–0,6 | 0,2–**0,3**–0,4 | 0,1–**0,2**–0,3 | 0,1–**0,2**–0,4 | 0,1–**0,3**–0,4 |
| 100 ~ 160 | $v_c$ | 150–**200**–250 | 100–**160**–200 | 160–**180**–200 | 100–**150**–200 | 200–**500**–1000 |
| | $f_z$ | 0,3–**0,4**–0,6 | 0,1–**0,3**–0,5 | 0,15–**0,2**–0,3 | 0,1–**0,15**–0,2 | 0,2–**0,3**–0,6 |

[$v_c$ = m/min, $f_z$ = mm/tooth] [min.– optimum – max.]

→ H74-75



## Features

The Wave Radius Mill RSX Series enables stable machining even when using equipment with low clamp rigidity thanks to its body design achieving excellent cutting performance and rigidity.
In addition to the ACM Series for stainless steel and exotic alloys two grades have been added:
ACP200 grade for steel machining and
ACK300 grade for cast iron machining.
Handle an even wider range of milling needs with the RSX(F)08000 and RSX(F)20000 types.

## Characteristics


Smooth cutting action and low vibration machining provided based on the high rake angle design and high rigidity body.
High reliability achieved with ACM100/ACM200/ACM300 adopted for exotic alloy machining.
ACP200 for steel and ACK300 for cast iron enable stable machining in a wide range of applications.

## Series


| Image | Series | Insert Size | Cat. No. | External Diameter (mm) | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | Ø 20 | Ø 25 | Ø 32 | Ø 40 | Ø 50 | Ø 52 | Ø 63 | Ø 66 | Ø 80 | Ø 100 | Ø 125 | Ø 160 |
| Shank Type  → H76 | Standard | 08 | RSX 08000 ES | ● | ● | | | | | | | | | | |
| | | 10 | 10000 ES | | ● | ● | | | | | | | | | |
| | | 12 | 12000 ES | | | ● | | | | | | | | | |
| | Fine Pitch | 08 | RSXF 08000 ES | ● | ● | | | | | | | | | | |
| | | 10 | 10000 ES | | ● | ● | | | | | | | | | |
| | | 12 | 12000 ES | | | ● | | | | | | | | | |
| Shell Type  | Standard | 10 | RSX 10000 RS | | | | ● | ● | ● | | | | | | |
| | | 12 | 12000 RS | | | | ● | ● | ● | ● | ● | ● | ● | | |
| | | 16 | 16000 RS | | | | | | | ● | | ● | ● | ● | |
| | | 20 | 20000 RS | | | | | | | | | ● | ● | ● | ● |
| | Fine Pitch | 10 | RSXF 10000 RS | | | | ● | ● | ● | | | | | | |
| | | 12 | 12000 RS | | | | ● | ● | ● | ● | ● | ● | ● | | |
| | | 16 | 16000 RS | | | | | | | ● | | ● | ● | ● | ❑ |
| | | 20 | 20000 RS | | | | | | | | | ● | ● | ● | ● |
| Modular Type  → H77 | Standard | 08 | RSX 08000 M | ● | ● | ● | | | | | | | | | |
| | | 10 | 10000 M | | ● | ● | | | | | | | | | |
| | | 12 | 12000 M | | | ● | ● | | | | | | | | |
| | Fine Pitch | 08 | RSXF 08000 M | ● | ● | ● | | | | | | | | | |
| | | 10 | 10000 M | | ● | ● | | | | | | | | | |
| | | 12 | 12000 M | | | ● | ● | | | | | | | | |

## Cutting Performance

### Tool Life Comparison (Fracture Resistance)





### Cutting Resistance Comparison




Work Material: X5CrNiS1810
Tool: Ø 50
Cutting Data: $v_c$ = 200m/min, $f_z$ = 0,5mm/t, $a_p$ = 2,0mm, $a_e$= 10,0mm, Wet

### Cutting Vibration Comparison







● = Euro stock
❑ = Delivery on request


## Low Cutting Resistance, Less Vibration

Low cutting resistance and low vibration machining have been achieved with super high rake angle design + high rigidity body.





## High Operability

Ease of corner control has been achieved with the adoption of a unique positioning mechanism that is highly precise and highly operable.





Insert size of 12 and 16 mm uses a maximum of 8 corners and an insert size of 10 mm uses a maximum of 4 corners.

## Stable and Long Tool Life





A long life ensured with the adoption of the ACM series and significant improvements have been made in processing exotic alloy and stainless steel machining.

**ACM100/ACM300**




**ACM200**




### New Super ZX Coat


The product series with a coating film hardness approximately 40 % higher and an oxidation onset temperature 200 °C higher than conventional products.
Enables machining at least 1,5 times faster and more efficiently than conventional products.
A product life at least twice as long as that of conventional products achieved under the same machining conditions.

### Super FF Coat

Smooth coating surface provides excellent adhesion and chipping resistance.
Improved coating adhesion strength.
Harder than conventional coatings with hugh improvements in wear resistance.
High speed, high effiency machining of more than 1,5 times than of conventional grades possible.
Achieving more than double the tool life of conventional grades under the same cutting conditions.

Milling of steel, stainless steel, cast iron and exotic alloys

| Rake Angle | | |
|---|---|---|
| | Radial | –5° |
| | Axial | 10° |



(10000RS) (12000RS) (16000RS) (20000RS)

## ■ Body – Dimensions



Fig. 1





Fig. 2






Fig. 3




## ■ Body

### ● RSX...RS, Standard

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| RSX 10040 RS | ● | 40 | 34 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 4 | 0,2 | 1 |
| 10050 RS | ● | 50 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,3 | 1 |
| 10052 RS | ● | 52 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,4 | 1 |
| RSX 12040 RS | ● | 40 | 32 | 40 | 16 | 8,4 | 5,6 | 18 | 13,5 | 9 | 3 | 0,2 | 1 |
| 12050 RS | ● | 50 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,3 | 1 |
| 12052 RS | ❍ | 52 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,3 | 1 |
| 12063 RS | ● | 63 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,4 | 1 |
| 12066 RS | ● | 66 | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 6 | 0,7 | 1 |
| 12080 RS | ● | 80 | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 6 | 1,0 | 1 |
| RSX 12100 RS | ● | 100 | 70 | 50 | 32 | 14,4 | 8,5 | 32 | 46 | - | 6 | 1,4 | 2 |
| RSX 16063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,5 | 1 |
| 16080 RS | ● | 80 | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 5 | 0,9 | 1 |
| RSX 16100 RS | ● | 100 | 70 | 50 | 32 | 14,4 | 8,5 | 32 | 46 | - | 6 | 1,3 | 2 |
| 16125 RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9,5 | 29 | 52 | 29 | 6 | 2,6 | 1 |
| RSX 20080 RS | ❍ | 80 | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | 4 | 0,9 | 1 |
| RSX 20100 RS | ● | 100 | 70 | 63 | 32 | 14,4 | 8,0 | 32 | 46 | - | 5 | 1,8 | 2 |
| 20125 RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9,0 | 29 | 52 | 29 | 6 | 2,6 | 1 |
| 20160 RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9,0 | 29 | 90 | - | 7 | 4,7 | 3 |

### ● RSXF...RS, Fine Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| RSXF 10040 RS | ● | 40 | 34 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 5 | 0,2 | 1 |
| 10050 RS | ● | 50 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,3 | 1 |
| 10052 RS | ● | 52 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,3 | 1 |
| RSXF 12040 RS | ● | 40 | 32 | 40 | 16 | 8,4 | 5,6 | 18 | 13,5 | 9 | 4 | 0,2 | 1 |
| 12050 RS | ● | 50 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,3 | 1 |
| 12052 RS | ● | 52 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,3 | 1 |
| 12063 RS | ● | 63 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,4 | 1 |
| 12066 RS | ● | 66 | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 7 | 0,7 | 1 |
| 12080 RS | ● | 80 | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 7 | 0,9 | 1 |
| RSXF 12100 RS | ● | 100 | 70 | 50 | 32 | 14,4 | 8,5 | 32 | 46 | - | 10 | 1,3 | 2 |
| RSXF 16063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,4 | 1 |
| 16080 RS | ● | 80 | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 6 | 0,8 | 1 |
| RSXF 16100 RS | ● | 100 | 70 | 50 | 32 | 14,4 | 8,5 | 32 | 46 | - | 7 | 1,3 | 2 |
| 16125 RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9,5 | 29 | 52 | 29 | 8 | 2,5 | 1 |
| 16160 RS | ❑ | 160 | 130 | 63 | 40 | 16,4 | 9,5 | 29 | 88 | - | 10 | 4,8 | 3 |
| RSXF 20080 RS | ● | 80 | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | 5 | 0,9 | 1 |
| RSXF 20100 RS | ● | 100 | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | - | 6 | 1,8 | 2 |
| 20125 RS | ❍ | 125 | 80 | 63 | 40 | 16,4 | 9,0 | 29 | 52 | 29 | 7 | 2,6 | 1 |
| 20160 RS | ❍ | 160 | 130 | 63 | 40 | 16,4 | 9,0 | 29 | 90 | - | 9 | 4,6 | 3 |

## ■ Identification Details

| RSX | F | 12 | 040 | R | S |
|---|---|---|---|---|---|
| Cutter Series | Fine Pitch Type | Insert Size | Cutter Diameter | Cutting Direction | Metric |




● = Euro stock
○ = Japan stock
❑ = Delivery on request
Recommended Tightening Torque (N·m)

## Various Machining Use


Various types of processing, such as mould engraving, slant milling and helical processing.

### Helical Milling

Helical Milling





≤ Work Diameter




Center uncut portion cannot be removed by traverse cutting with the same cutter.


≥ Work Diameter




Center uncut portion can be removed by traverse cutting with the same cutter.

### Ramping

Use at α° or lower




### Recommended Values for Helical and Ramping


| Insert Cat. No. | Helical | | | | Taper |
|---|---|---|---|---|---|
| | Cutter ØDC | Work Diameter | | | Ramping Angle α°(max) |
| | | Min. | Optimal Ø | Max. | |
| RDET10... | 25 | 33,0 | 40 | 49 | 10°30' |
| | 32 | 46,0 | 54 | 63 | 6°45' |
| | 40 | 62,0 | 70 | 79 | 4°30' |
| | 50 | 82,0 | 90 | 99 | 3°15' |
| | 52 | 86,0 | 94 | 103 | 3°10' |
| RDET12... | 32 | 41,5 | 52 | 63 | 12°30' |
| | 40 | 57,5 | 68 | 79 | 8°00' |
| | 50 | 77,5 | 88 | 99 | 5°30' |
| | 52 | 81,5 | 92 | 103 | 5°15' |
| | 63 | 103,5 | 114 | 125 | 4°00' |
| | 66 | 109,5 | 120 | 131 | 3°45' |
| | 80 | 137,5 | 148 | 159 | 2°50' |
| | 100 | 177,5 | 188 | 199 | 2°10' |
| RDET16... | 63 | 96,0 | 110 | 125 | 6°00' |
| | 80 | 130,0 | 144 | 159 | 4°10' |
| | 100 | 170,0 | 184 | 199 | 3°00' |
| | 125 | 220,0 | 234 | 249 | 2°20' |
| RDET20... | 80 | 122,0 | 140 | 159 | 4°15' |
| | 100 | 162,0 | 180 | 199 | 3°00' |
| | 125 | 212,0 | 230 | 249 | 2°00' |
| | 160 | 282,0 | 300 | 319 | 1°15' |

## Inserts

Dimensions (mm)

| Application | Grade | | | | |
|---|---|---|---|---|---|
| High Speed/Light Cut | | | MS | MS | |
| General Purpose | PM | | MS | MS | MS |
| Roughing | PM | K | | | MS |

| Cat. No. | ACP200 | ACK300 | ACM100 | ACM200 | ACM300 | Dimens. ød (IC) | Dimens. S | Applicable Cutters |
|---|---|---|---|---|---|---|---|---|
| RDET 10T3M0EN G | ● | ● | ● | ● | ● | 10 | 3,97 | RSX(F) 10000RS |
| 10T3M0EN H | ● | ● | ● | ● | ● | 10 | 3,97 | |
| RDET 1204M0EN G | ● | ● | ● | ● | ● | 12 | 4,76 | RSX(F) 12000RS |
| 1204M0EN H | ● | ● | ● | ● | ● | 12 | 4,76 | |
| RDET 1606M0EN G | ● | ● | ● | ● | ● | 16 | 6,5 | RSX(F) 16000RS |
| 1606M0EN H | ● | ● | ❍ | ● | ● | 16 | 6,5 | |
| RDET 2006M0EN G | ● | ● | ❍ | ● | ● | 20 | 6,5 | RSX(F) 20000RS |
| 2006M0EN H | ❍ | ● | ❍ | ❍ | ● | 20 | 6,5 | |




Cutting Edge Cross Section



**G** - Type **H** - Type

M0: IC is metric

## Spare Parts

| Applicable Cutters | Wrench | Screw | |
|---|---|---|---|
| |  |  | N·m |
| RSX(F) 10000RS | TRDR15IP | BFTX03584IP | **3,0** |
| RSX(F) 12000RS | | BFTX0409IP | **3,0** |
| RSX(F) 16000RS | TRDR20IP | BFTX0511IP | **5,0** |
| RSX(F) 20000RS | TRDR25IP | BFTX0615IP | **5,0** |

## Recommended Cutting Conditions

Min.-**Optimum**-Max.

| ISO | Work Material | | | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|---|---|
| P | Carbon Steel | | | 180–280 | 100–**160**–200 | 0,20–**0,40**–0,60 | ACP200 |
| | Alloy Steel | | | 180–280 | 100–**140**–180 | 0,20–**0,30**–0,40 | ACP200 |
| M | Stain-less Steel | Cr Based | Ferritic | 200 | 150–**180**–200 | 0,15–**0,25**–0,35 | ACM300 |
| | | | Martensitic | 200–330 | 80–**120**–180 | 0,15–**0,25**–0,35 | ACM300 |
| | | Cr-Ni Based | Austenitic | 200 | 150–**180**–200 | 0,15–**0,25**–0,35 | ACM300 |
| | | | Austenitic, ferritic | 230–270 | 80–**120**–180 | 0,15–**0,25**–0,35 | ACM200 |
| | | | Precipitation hardening | 330 | 60–**100**–160 | 0,15–**0,25**–0,35 | ACM200 |
| K | Cast Iron | | | 250 | 80–**120**–160 | 0,10–**0,30**–0,40 | ACK300 |
| S | Heat resistant alloy | | Ni based material | 250–350 | 20–**30**–40 | 0,10–**0,20**–0,30 | ACM100 ACM200 |
| | Titanium | | Pure Titanium | (Rm 400) | 60–**80**–100 | 0,10–**0,20**–0,30 | |
| | | | α + β alloy system | (Rm 1050) | 40–**50**–60 | 0,10–**0,20**–0,30 | |

Expansion

## General Features

The Sumi Dual Mill DFC type employs cost effective double-sided inserts for high toughness and enhanced accuracy.
The double-side inserts are flexible and reduces costs.



## Large Line-up

- Diameter from Ø 25 mm to Ø 200 mm
- Available as standard, fine and extra-fine pitch
- Bore diameter: metric
- Insert geometry: L, G, GS, H


## Cutter Body

| Type | | Cat. No. | Diameter (mm) | No. of Teeth | Image |
|---|---|---|---|---|---|
| Shank → H17 | Standard Pitch | DFC 09000 E | Ø 25–Ø 80 | 2–5 |  |
| | Medium Pitch | DFCM 09000 E | Ø 32–Ø 80 | 3–7 | |
| Shell | Standard Pitch | DCF 09000 RS | Ø 50–Ø 200 | 4–10 |  |
| | Medium Pitch | DFCM 09000 RS | Ø 50–Ø 200 | 5–16 | |
| | Fine Pitch | DFCF 09000 RS | Ø 50–Ø 200 | 6–20 | |


## 90 Degree Accuracy

Work material: Carbon steel

Cutting conditions:
$v_c$ = 200 m/min, $f_z$ = 0,1 mm/t
$a_e$ = 5,0 mm, $a_p$ = 5,0 mm x 3 passes



Shell type: ø 63 mm



Number of passes (1 pass = 0.30 mm)

## Applications and Recommended Chipbreakers


| Face milling | Shoulder milling | Slot milling | Side face milling |
|---|---|---|---|
| **G** | **GS** | | **G, GS** |
|  |  |  |  |

● = Euro stock

## New Insert Design Provides Excellent Machining Accuracy

- The new insert design separates the location area and cutting edge producing an optimized solution.
- Machining accuracy is comparable to single sided inserts provided the DOC is less than 3 mm.
- The SEC-Sumi Dual Mill design, equips the user with a highly stable cutter for high feed machining applications.




### Chipbreaker Selection Map




### Inserts


| Cat. No. | RE0,4 | RE0,8 | RE1,2 | RE1,6 |
|---|---|---|---|---|
| XNMU0606__PNER-L | ● | ● | | |
| XNMU0606__PNER-G | ● | ● | ● | ● |
| XNMU0606__PNER-GS | ● | ● | ● | ● |
| XNMU0606__PNER-H | | ● | ● | ● |

Expansion

| Work Material | P M K S | | | |
|---|---|---|---|---|
| Chipbreaker | L type | G type | GS type | H type |
| |  |  |  |  |
| Applications | Light cutting | General purpose to interrupted milling | Shoulder milling | Heavy cutting |
| Cutting edge geometry |  30° | 0,1 mm  20° | 0,1 mm  20° | 0,15 mm  20° |
| Features | Low rigidity milling, reduction of burrs | Face milling | Shoulder milling | Roughing, heavy interrupted and hardness steel milling |

## Stable and High Cutting Performance Combined with High Toughness

- The excellent cutter performance offers efficient machining, enables high feed rate capability.
- The new insert construction provides extremely accurate edge to edge indexing whilst the location area offers high security and stability.



# DFC(M/F) 09000RS

## Body – Shell type

| Rake Angle | Radial | –9° |
|---|---|---|
| | Axial | –5° |

Max. $a_p$: 6 mm



Fig.1





Fig.2






Fig.3




## Body – Dimensions

### Sumi Dual Mill DFC type, Standard Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| DFC 09050RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,3 | 1 |
| 09063RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,5 | 1 |
| 09080RS | ● | 80 | 55 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | 5 | 1,0 | 1 |
| DFC 09100RS | ● | 100 | 70 | 50 | 32 | 14,4 | 8 | 26 | 46 | - | 6 | 1,4 | 2 |
| 09125RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9 | 29 | 52 | 29 | 7 | 2,8 | 1 |
| 09160RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9 | 29 | 90 | - | 8 | 4,6 | 3 |
| DFC 09200RS | ❑ | 200 | 150 | 63 | 60 | 25,7 | 14 | 35 | 135 | - | 10 | 5,7 | |

### Sumi Dual Mill DFC type, Medium Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| DFCM 09050RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,3 | 1 |
| 09063RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,5 | 1 |
| 09080RS | ● | 80 | 55 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | 7 | 0,9 | 1 |
| DFCM 09100RS | ● | 100 | 70 | 50 | 32 | 14,4 | 8 | 26 | 46 | - | 8 | 1,4 | 2 |
| 09125RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9 | 29 | 52 | 29 | 11 | 2,7 | 1 |
| 09160RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9 | 29 | 90 | - | 12 | 4,5 | 3 |
| DFCM 09200RS | ❑ | 200 | 150 | 63 | 60 | 25,7 | 14 | 35 | 135 | - | 16 | 5,6 | |

### Sumi Dual Mill DFC type, Fine Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| DFCF 09050RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,3 | 1 |
| 09063RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 7 | 0,5 | 1 |
| 09080RS | ● | 80 | 55 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | 9 | 0,9 | 1 |
| DFCF 09100RS | ● | 100 | 70 | 50 | 32 | 14,4 | 8 | 26 | 46 | - | 11 | 1,3 | 2 |
| 09125RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9 | 29 | 52 | 29 | 14 | 2,6 | 1 |
| 09160RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9 | 29 | 90 | - | 16 | 4,6 | 3 |
| DFCF 09200RS | ❑ | 200 | 150 | 63 | 60 | 25,7 | 14 | 35 | 135 | - | 20 | 5,5 | |

## Identification Details

| DFC | M | 09 | 050 | R | S |
|---|---|---|---|---|---|
| Cutter Series | M: Medium F: Fine | Insert Size | Cutter Diameter | Direction | Metric |

## Spare Parts

| Screw | | Wrench |
|---|---|---|
|  | N·m |  |
| BFTX03512IP | 5,0 | TRDR15IP |



● = Euro stock
❑ = Delivery on request


N·m Recommended Tightening Torque (N·m)

Expansion

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | | | | | | |
| General Purpose Cutting | | | | | | | | | | | |
| Rough Cutting | | | | | | | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| XNMU 060604 PNER-L | ● | ❍ | | ● | ● | ❍ | | ● | | ● | 0,4 |
| 060608 PNER-L | ● | ❍ | | ● | ● | ❍ | | ● | | ● | 0,8 |
| XNMU 060604 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,4 |
| 060608 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 060612 PNER-G | ● | | ● | ● | ● | | ● | ● | ● | ● | 1,2 |
| 060616 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ● | ● | 1,6 |
| XNMU 060604 PNER-GS | ❍ | | ● | ● | ● | | | | ● | ● | 0,4 |
| 060608 PNER-GS | ❍ | ❍ | ● | ● | ● | ❍ | | | ● | ● | 0,8 |
| 060612 PNER-GS | ❍ | | ❍ | ❍ | ❍ | | | | ❍ | ❍ | 1,2 |
| 060616 PNER-GS | ❍ | | ❍ | ❍ | ❍ | | | | ❍ | ❍ | 1,6 |
| XNMU 060608 PNER-H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 060612 PNER-H | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,2 |
| 060616 PNER-H | ● | | ❍ | ● | ❍ | | ❍ | ● | ❍ | ● | 1,6 |




## Recommemded Cutting Conditions

Min.–**Optimum**–Max.

| ISO | Work-material | Hardness (HB) | Cutting Speed (m/min) | Feed Rate | Depth of Cut (mm) | Grade |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,10–**0,20**–0,30 | < 6 | ACU2500 ACP200 ACP300 XCU2500 |
| | Soft Steel | ≤180 | 180–**250**–350 | 0,15–**0,25**–0,35 | < 6 | |
| | Die Steel | 200–220 | 100–**150**–200 | 0,10–**0,18**–0,25 | < 4 | |
| M | Stainless Steel | – | 160–**205**–250 | 0,12–**0,18**–0,25 | < 6 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**175**–250 | 0,10–**0,20**–0,30 | < 6 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Alloy | – | 30–**50**–80 | 0,10–**0,20**–0,30 | < 6 | ACU2500 ACM200 ACM300 |

## Application Examples

| Work piece | | Sumitomo | Comp. |
|---|---|---|---|
| Workpiece material: Steel (HRB 269-330) | Breaker | G | |
| | Grade | ACP200 | |
| | $v_c$ (m/min) | 226 | 200 |
| | $v_f$ (mm/min) | 1260 | |
| | $f_z$ (mm/t) | 0,28 | 0,2 |
| | $a_p$ (mm) | 2 | 2 |
| | $a_e$ (mm) | 5 | 5 |
| | Dry or Wet | Wet | Wet |
| | Tool diam. Ø | 80 | |
| | No. of Teeth | 5 | |
| | Result | Efficiency: 158 % achieved | |
| | Evaluation | Wear resistance, efficiency | |




| Work piece | | Sumitomo | Comp. |
|---|---|---|---|
| Workpiece material: S235 (Carbon steel) Face milling | Breaker | G | |
| | Grade | ACP200 | |
| | $v_c$ (m/min) | 180 | 180 |
| | $v_f$ (mm/min) | 1092 | 910 |
| | $f_z$ (mm/t) | 0,3 | 0,2 |
| | $a_p$ (mm) | 2 x 2 mm | 2 x 2 mm |
| | $a_e$ (mm) | 50 | 50 |
| | Dry or Wet | Dry | Dry |
| | Tool diam. Ø | 63 mm | 63 mm |
| | No. of Teeth | 4 | 5 |
| | Result | Efficiency: 120 % achieved | |
| | Evaluation | Wear resistance, efficiency | |



| Work piece | | Sumitomo | Comp. |
|---|---|---|---|
| Workpiece material: Cast Iron | Breaker | G | |
| | Grade | ACP200 | |
| | $v_c$ (m/min) | 156 | 156 |
| | $v_f$ (mm/min) | 536 | 404 |
| | $f_z$ (mm/t) | 0,17 | 0,09 |
| | $a_p$ (mm) | 2,2 | 2,2 |
| | $a_e$ (mm) | 63,5 | 63,5 |
| | Dry or Wet | Dry | Dry |
| | Tool diam. Ø | 80 mm | 80 mm |
| | No. of Teeth | 5 | 7 |
| | Result | Efficiency: 133 % achieved<br>Tool life: 138 % achieved | |
| | Evaluation | Efficiency, tool life | |



| Work piece | | Sumitomo | Comp. |
|---|---|---|---|
| Workpiece material: Cr-Mo alloy | Breaker | G | |
| | Grade | ACP200 | |
| | $v_c$ (m/min) | 200 | 200 |
| | $v_f$ (mm/min) | 838 | 838 |
| | $f_z$ (mm/t) | 0,2 | 0,13 |
| | $a_p$ (mm) | 6 | 6 |
| | $a_e$ (mm) | 43 | 43 |
| | Dry or Wet | Dry | Dry |
| | Tool diam. Ø | 80 mm | 80 mm |
| | No. of Teeth | 5 | 8 |
| | Result | Efficiency: 120 % achieved | |
| | Evaluation | Efficiency | |




# WFX Type

Expansion




## General Features

Wave Mill WFX type for shoulder milling is a screw-locking type cutter capable of using four corners.
Ideal cutting edge design delivers good squareness.
Series expansion with the high-feed **WFXH** type and the **WFXC** type for chamfering.
A comprehensive lineup that covers a wide variety of applications.




## Characteristics

The insert shape, optimized for shoulder milling and combined with a high-precision body, leaves a superior machined surface finish.





### ● Max. Depth of Cut





WFX08000 type　　WFX12000 type

### ● Optimized Edge Shape




① The convex shape ensures the cutting edge strength.

② The flat shape minimises differences in step levels.




③ The wiper edge function improves the surface roughness.

## Product Range

| Application | Type | Cat. No. | No. of Teeth | Cutter Diameter (mm) | Shape |
|---|---|---|---|---|---|
| Shoulder Milling | Shell Type | WFX 08000 RS | 3 - 8 | 40–100 | |
| | | WFXM 08000 RS | 4 - 10 | 40–100 | |
| | | WFXF 08000 RS | 6 - 12 | 40–100 | |
| | | WFX 08000 R | 6 - 8 | 80–100 | |
| | | WFXM 08000 R | 8 - 10 | 80–100 | |
| | | WFXF 08000 R | 10 - 12 | 80–100 | |
| | | WFX 12000 RS | 3 - 5 | 60–100 | |
| | | WFXF 12000 RS | 4 - 7 | 60–100 | |
| | | WFX 12000 R | 4 - 12 | 80–250 | |
| | | WFXF 12000 R | 6 - 18 | 80–250 | |
| | Endmill Type | WFX 08000 E | 2 - 5 | 20–63 | → H18/19 |
| | | WFXM 08000 E | 3 - 6 | 25–63 | |
| | | WFX 12000 E | 3 - 4 | 40–80 | |
| | | WFXF 12000 E | 4 - 6 | 60–80 | |
| | Modular Type | WFX 08000 M | 2 - 3 | 20–40 | |
| High Efficiency | Shell Type | WFXH 08000 RS | 4 - 6 | 40–63 | |
| | | WFXH 12000 RS | 4 - 5 | 60– 63 | |
| | Modular Type | WFXH 08000 M | 2 - 3 | 25–32 | |
| | | WFXH 12000 M | 3 | 40 | → H14/15 |
| Chamfering | Endmill Type | WFXC 08000 E | 1 - 2 | 8–16 | |
| | | WFXC 12000 E | 3 | 25–32 | |
| | Modular Type | WFXC 08000 M | 2 | 16 | |
| | | WFXC 12000 M | 3 | 25–32 | → H78-80 |

## Inserts

| Cat. No. | RE0,2 | RE0,4 | RE0,8 | RE1,2 | RE1,6 |
|---|---|---|---|---|---|
| SOMT 0803_ _PZER-L | | ● | ● | | |
| 0803_ _PZER-G | | ● | ● | ● | |
| 0803_ _PZER-H | | | ● | ● | |
| SOET 0803_ _PZER-G | | ● | ● | ● | |
| 0803_ _PZFR-S | ● | ● | ● | | |
| SOMT 1204_ _PDER-L | | | ● | | |
| 1204_ _PDER-G | | ● | ● | ● | ● |
| 1204_ _PDER-H | | | ● | | |
| SOET 1204_ _PDFR-S | | | ● | | |



WFX08000 type insert (General Purpose G type chipbreaker)





WFX12000 type insert (General Purpose G type chipbreaker)

● = Euro stock

## Cutting Performance


### Squareness of Machined Shoulder





Work Material: C50
Tool: WFX12100RS (Ø 100 mm x 5 teeth)
Cutting Conditions: $v_c$ = 200m/min, $a_p$ = 8,0 mm x 3 times
$f_z$ = 0,15mm/t, $a_e$ = 20 mm

### Comparison of Surface Roughness





Work Material: 42CrMo4
Tool: WFX12100RS (Ø 100 mm x 5 teeth)
Cutting Conditions: $v_c$ = 200 m/min, $a_p$ = 3,0 mm
$f_z$ = 0,10 mm/t, $a_e$ = 90 mm











### Comparison of Cutting Force




Work Material: C50
Tool: WFX12100R (Ø 100 mm x 5 teeth)
Cutting Conditions: $v_c$ = 200 m/min, $a_p$ = 10 mm,
$f_z$ = 0,15 mm/t, $a_e$ = 20 mm


## Chipbreaker Selection





| Work Material | P M K S | | | | N |
|---|---|---|---|---|---|
| Breaker | **L Type** | **G Type** | **H Type** | **Wiper Type** | **S Type** |
| |  |  |  |  |  |
| Characteristic | Low Cutting Force | General Purpose | Strong Edge | Wiper Edge | Sharp Edge |
| 08 Type Cross Section |   |   |   |   |   |
| 12 Type Cross Section |   |   |   |   |   |
| Work Material-Application | Light Cutting<br>Low rigidity Milling<br>Low-Burr Design | **Main Chipbreaker**<br>General to Interrupted Milling | Heavy Cut<br>Heavy Interrupted Machining<br>Tempered Steel | Precision Finishing | Non-Ferrous Metal |

## Wiper Insert

Optimised wiper edge shape provides superior surface roughness.




Wiper inserts are single-cornered.
Attach the wiper insert so that the chamfered corner is in location ① shown in the figure.
Be sure to use the corner with the ID mark (② in the figure).
(08 size inserts have no marks)

# WFX(M/F) 08000 RS

Expansion

## Body - Shell Type


| Rake Angle | | |
|---|---|---|
| Radial | –6° | 6 mm |
| Axial | 12° | 90° |



WFX08000RS



WFXM08000RS



WFXF08000RS

Fig. 1






Fig. 2




## Body - WFX, Standard Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| WFX 08040 RS | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 3 | 0,2 | 1 |
| 08050 RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,3 | 1 |
| 08063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,6 | 1 |
| 08080 RS | ● | 80* | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 6 | 1,0 | 1 |
| WFX 08100 RS | ● | 100* | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | - | 8 | 1,4 | 2 |

## Body - WFXM, Medium Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| WFXM 08040 RS | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 4 | 0,2 | 1 |
| 08050 RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,3 | 1 |
| 08063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,5 | 1 |
| 08080 RS | ● | 80* | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 8 | 1,0 | 1 |
| WFXM 08100 RS | ● | 100* | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | - | 10 | 1,4 | 2 |

## Body - WFXF, Fine Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| WFXF 08040 RS | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 6 | 0,2 | 1 |
| 08050 RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 7 | 0,3 | 1 |
| 08063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 8 | 0,5 | 1 |
| 08080 RS | ● | 80* | 55 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 14 | 10 | 0,9 | 1 |
| WFXF 08100 RS | ● | 100* | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | - | 12 | 1,4 | 2 |

Inserts are not included.

*Please use JIS B1176 hexagonal bolt (Ø80: M12x30~35mm, Ø100: M16x40~45mm) for securing Ø80 / Ø100 cutter on the arbor.

## Recommended Cutting Conditions


| ISO | Work Material | Hardness (HB) | Cutting Speed | Feed Rate | DOC | Grades |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,08–**0,12**–0,18 | <6 | ACU2500 ACP200 ACP300 XCU2500 |
| | Soft Steel | ≤180 | 180–**250**–350 | 0,10–**0,15**–0,20 | <6 | |
| | Die Steel | 200–220 | 100–**150**–200 | 0,08–**0,12**–0,18 | <4 | |
| M | Stainless Steel | - | 160–**200**–250 | 0,10–**0,15**–0,20 | <6 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**175**–250 | 0,10–**0,15**–0,20 | <6 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| N | Non Ferrous Metal | - | 300–**500**–1000 | 0,10–**0,15**–0,20 | <6 | H1 DL1000 |
| S | Exoric Alloy | - | 30–**50**–80 | 0,08–**0,13**–0,18 | <6 | ACU2500 ACM200 ACM300 |

Min. - **Optimum** - Max.

## Identification Details

| WFX | F | 08 | 040 | R | S |
|---|---|---|---|---|---|
| Cutter Series | M: Medium Pitch<br>F: Fine Pitch | Insert Size | Cutter Diameter | Direction | Metric Type |

## Spare Parts

| Screw | | Wrench |
|---|---|---|
|  | |  |
| BFTX0306IP | 2,0 | TRDR08IP |

## Inserts

Dimensions (mm)

Fig. 3






Fig. 4 Wiper Insert




| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | K M S | P K M | P | | | K | K | | M S | | K N | N | | |
| General Purpose | K M S | P K M | | P M | P M | K | K | | M S | M S | | N | | |
| Roughing | K M S | | | P M | P M | | | K | | M S | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | RE | Fig. |
| SOMT 080304 PZER L | ● | ❍ | ● | ● | ❍ | ❍ | ❍ | ● | ● | ● | – | – | 0,4 | 3 |
| 080308 PZER L | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| SOMT 080304 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,4 | 3 |
| 080308 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| 080312 PZER G | ● | | ● | ● | ● | | ❍ | ● | ● | ● | – | – | 1,2 | 3 |
| SOMT 080308 PZER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| 080312 PZER H | ● | | ● | ● | ● | | ❍ | ● | ❍ | ● | – | – | 1,2 | 3 |
| SOET 080304 PZER G | ● | | ❍ | ❍ | ❍ | | ❍ | ● | ● | ❍ | – | – | 0,4 | 3 |
| 080308 PZER G | ● | | ❍ | ❍ | ❍ | | ❍ | ● | ● | ❍ | – | – | 0,8 | 3 |
| 080312 PZER G | ● | | ❍ | ● | ❍ | | ❍ | ● | ❍ | ❍ | – | – | 1,2 | 3 |
| SOET 080302 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,2 | 3 |
| 080304 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,4 | 3 |
| 080308 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,8 | 3 |
| XOEW 080308 PZTR W | ● | – | – | – | – | – | | ● | | | – | – | 0,8 | 4 |



● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

## Body - Shell Type

| Rake Angle | | |
|---|---|---|
| | Radial | –8° |
| | Axial | 8° |

10 mm, 90°



WFX 12000RS



WFXF12000RS

Fig. 1





Fig. 2






Fig. 3




## Body - WFX, Standard Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| WFX 12050 RS | ● | 50 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 3 | 0,2 | 1 |
| 12063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,4 | 1 |
| 12080 RS | ● | 80* | 60 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 13,5 | 4 | 0,9 | 1 |
| WFX 12100 RS | ● | 100* | 70 | 50 | 32 | 14,4 | 8,5 | 32 | 46 | - | 5 | 1,3 | 2 |
| 12125 RS | ● | 125 | 90 | 63 | 40 | 16,4 | 9,5 | 29 | 52 | - | 6 | 2,7 | 2 |
| 12160 RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9,5 | 29 | 88 | - | 8 | 4,8 | 3 |

## Body - WFXF, Fine Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| WFXF 12050 RS | ● | 50 | 40 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,2 | 1 |
| 12063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,4 | 1 |
| 12080 RS | ● | 80* | 60 | 50 | 27 | 12,4 | 7,0 | 25 | 20 | 13,5 | 6 | 0,9 | 1 |
| WFXF 12100 RS | ● | 100* | 70 | 50 | 32 | 14,4 | 8,5 | 32 | 46 | - | 7 | 1,2 | 2 |
| 12125 RS | ● | 125 | 90 | 63 | 40 | 16,4 | 9,5 | 29 | 52 | - | 8 | 2,6 | 2 |
| 12160 RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9,5 | 29 | 88 | - | 12 | 4,7 | 3 |

Inserts are not included.
*Please use JIS B1176 hexagonal bolt (Ø80: M12x30~35mm, Ø100: M16x40~45mm) for securing Ø80 / Ø100 cutter on the arbor.
Cutters ≥ Ø160 do not have coolant holes.

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Cutting Speed | Feed Rate | DOC | Grades |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,10–**0,15**–0,20 | <10 | ACU2500 ACP200 ACP300 XCU2500 |
| P | Soft Steel | ≤180 | 180–**250**–350 | 0,10–**0,15**–0,20 | <10 | |
| P | Die Steel | 200–220 | 100–**150**–200 | 0,10–**0,15**–0,20 | <6 | |
| M | Stainless Steel | - | 160–**200**–250 | 0,10–**0,15**–0,20 | <10 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**175**–250 | 0,10–**0,15**–0,20 | <10 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| N | Non Ferrous Metal | - | 300–**500**–1000 | 0,10–**0,15**–0,20 | <10 | H1 DL1000 |
| S | Exotic Alloy | - | 30–**50**–80 | 0,10–**0,15**–0,20 | <10 | ACU2500 ACM200 ACM300 |

Min. - **Optimum** - Max.

## Inserts

Dimensions (mm)

Fig. 3






Fig. 4
Wiper Insert




| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | ● | ● | ● | | | ● | ● | | ● | | ● | ● | | |
| General Purpose | ● | ● | | ● | ● | ● | ● | | ● | ● | | ● | | |
| Roughing | ● | | | ● | ● | | | ● | | ● | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | RE | Fig. |
| SOMT 120408 PDER L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| SOMT 120404 PDER G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,4 | 3 |
| 120408 PDER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| 120412 PDER G | ● | | ❍ | ● | ❍ | | ● | ❍ | ❍ | ● | – | – | 1,2 | 3 |
| 120416 PDER G | ● | | ● | ● | ● | | ❍ | ❍ | ❍ | ❍ | – | – | 1,6 | 3 |
| SOMT 120408 PDER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| SOET 120408 PDFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,8 | 3 |
| XOEW 120408 PDTR W | ● | – | – | – | – | – | – | ❍ | – | – | – | – | – | 4 |

## Identification Details

| WFX | F | 12 | 050 | R | S |
|---|---|---|---|---|---|
| Cutter Series | F: Fine Pitch | Insert Size | Cutter Diameter | Direction | Metric Type |

## Spare Parts

| Shim | Shim Screw | Insert Screw | | Insert Wrench | Wrench (Shim) |
|---|---|---|---|---|---|
|  |  |  | N·m |  |  |
| WFXS4R | BW0507F | BFTX03512IP | **3,0** | TRDR15IP | LH035 |



# TSX Type

Expansion



## General Features

High-efficient and high precision tangential shoulder milling cutter with tangentially mounted carbide inserts.

## Characteristics

- **Tough & Sharp cutting edge**
  Tangentially mounted carbide insert design and optimized edge geometry realize extremely tough and sharp cutting action.

- **Very accurate and excellent surface finish**
  Thanks to newly developed fine carbide press / sintering technology and very accurate grinding technics, very periphery ground inserts generate very accurate and excellent surface finish.

- **Wide product range**
  2 different insert size series, 3 chip breaker range and various carbide grade combination offers wide range of machining application.

## Product Range

Shoulder Milling Cutter

| | Cat. No. | Series | Diameter Range / No of Teeth | | | | | | | | | | | | | | Shape |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | Ø16 | Ø20 | Ø25 | Ø32 | Ø40 | Ø50 | Ø63 | Ø80 | Ø100 | Ø125 | Ø160 | Ø200 | Ø250 | Ø315 | |
| Shell Type | TSX 08000RS | Standard Pitch | | | | | 4 | 5 | 6 | 7 | | | | | | |  |
| | TSXF 08000RS | Fine Pitch | | | | | 6 | 8 | 10 | 11 | | | | | | | |
| | TSX 13000RS | Standard Pitch | | | | | 3 | 4 | 5 | 5 | 6 | 7 | 8 | 12 | 14 | 16 | |
| | TSXM 13000RS | Medium Pitch | | | | | 4 | 5 | 6 | 7 | 8 | 10 | 12 | 16 | 20 | 24 | |
| | TSXF 13000RS | Fine Pitch | | | | | 5 | 6 | 7 | 8 | 10 | 14 | 16 | | | | |
| Shank Type | TSX 08000E | Standard Pitch | 2 | 2* | 3* | 3* | 4 | 5 | 6 | 7 | | | | | | |  |
| | TSXF 08000E | Fine Pitch | | 3 | 4 | 5 | 6 | 8 | 10 | 11 | | | | | | | |
| | TSX 13000E | Standard Pitch | | | 2 | 2 | 3 | 4 | 5 | 5 | | | | | | | |
| | TSXM 13000E | Medium Pitch | | | | 3 | 4 | 5 | 6 | 7 | | | | | | | |
| | TSXF 13000E | Fine Pitch | | | | | 5 | 6 | 7 | 8 | | | | | | | ⟶ H20-23 |

* Different shank diameters in stock

TSXR - Repeater

New






| Type | Cat. No. | Diameter Range / No of Teeth | | | | | | | | | | Shape |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | Ø16 | Ø20 | Ø25 | Ø32 | Ø40 | Ø50 | Ø63 | Ø80 | Ø100 | Ø125 | |
| Shell | TSXR 08000RS | | | | 2 | 3 | 3 | 4 | 5 | | |  |
| | TSXR 13000RS | | | | | 2 | 3 | | 3 | 4 | 4 | 5 | 5 | 6 | 7 | |
| Shank | TSXR 08000E | | 1 | 2 | 2 | 3 | | | | | | | | | |  |
| | TSXR 13000E | | | | | 2 | 3 | | | | | | | | | ⟶ H24-25 |






● = Euro stock

## Chipbreaker Lineup

| Work Material | P M K S | | |
|---|---|---|---|
| Chipbreaker | L type | G type | H type |
| |  |  |  |
| Feature | Low cutting force | General purpose | Strong edge |
| LNEX08<br>Cutting edge geometry |  |  | – |
| LNEX13<br>Cutting edge geometry |  |  |  |
| Application | Light cut, low rigidity milling and reduced burrs | Main breaker for general purpose applications | Roughing, heavy interrupted and hardness steel milling |

## Chipbreaker Selection





## Inserts


| Cat. No. | RE0,4 | RE0,8 | RE1,2 | RE1,6 | RE2,4 | RE3,2 |
|---|---|---|---|---|---|---|
| LNEX0804__PNER-L | ● | ● | | | | |
| LNEX0804__PNER-G | ● | ● | ● | ● | | |
| LNEX1306__PNER-L | ● | ● | | | | |
| LNEX1306__PNER-G | | ● | | ● | ● | ● |
| LNEX1306__PNER-H | ● | ● | | ● | ● | ● |

## Suitable Applications


Face milling



Shoulder milling




Side face milling




Slot milling

Recommended
≤ ø32 mm



Hole expansion milling




## Toughness

TSX type has extremely stable cutting edge.


| Cutting Length | 4 Passes | 8 Passes | 12 Passes |
|---|---|---|---|
| TSX | Available | | |
| Competitor A | Breakage | | |
| Competitor B | Breakage | | |

Machine: M/C BT-50, vertical Work Material: C50
Tool: TSX13100RS Insert: LNEX130608PNER-G (ACP200)
Cutting Conditions:
$v_c$ = 150 m/min, $f_z$ = 0,6 mm/t, $a_p$ = 3 mm, $a_e$ = 40 mm, dry



## Squareness of Machined Shoulder


TSX type shows excellent squareness due to ground insert and optimized design.




Machine: M/C BT-50, vertical Work Material: Carbon Steel
Tool: TSX13100RS Insert: LNEX130608PNER-G (ACP200)
Cutting Conditions:
$v_c$ = 200 m/min, $f_z$ = 0,2 mm/t, $a_p$ = 5 mm x 3 passes, $a_e$ = 5 mm, dry

## Surface Finish


TSX type shows excellent surface roughness.




Machine: M/C BT-50, vertical Work Material: C50
Tool: TSX13100RS Insert: LNEX130608PNER-G (ACP200)
Cutting Conditions:
$v_c$ = 200 m/min, $f_z$ = 0,2 mm/t, $a_p$ = 3 mm, $a_e$ = 60 mm, dry

## Tool Life

Longer tool life and stability due to superior wear resistance.





Machine: M/C BT-50, vertical Work Material: C50
Tool: TSX08025E Insert: LNEX080408PNER-G (ACP200)
Cutting Conditions:
$v_c$ = 200 m/min, $f_z$ = 0,10 mm/t, $a_p$ = 2 mm, $a_e$ = 5 mm

TSX-Series
(After 60 minutes)



Competitor A
(After 48 minutes)



Competitor B
(After 60 minutes)



## ■ Shoulder Milling Tool Selection Guide

**TSX Series – Accuracy**


Ground insert



**WEX Series – Sharpness**


High rake wave cutting edge






**DFC Series – Economical**

Six-cornered double side insert



**WFX Series – General Purpose**

Four-cornered single side insert



★★★ Top recommendation

| | Surface Finish | Shoulder Accuracy | Cutting Force | Chip Control | Number of Corners | Cutting edge Strength |
|---|---|---|---|---|---|---|
| **TSX** Series | ★★★ | ★★★ | ★★ | ★☆ | ★★ | ★★★ |
| **DFC** Series | ★★ | ★ | ★ | ★☆ | ★★★ | ★★★ |
| **WEX** Series | ★ | ★★ | ★★★ | ★★★ | ★ | ★★ |
| **WFX** Series | ★★ | ★★ | ★★ | ★★★ | ★★ | ★ |

# TSX(F) 08000 RS


Expansion

## Body - Shell Type

| Rake Angle | | |
|---|---|---|
| | Radial | –20° |
| | Axial | –6° |

8 mm, 90°






## Body - TSX, Standard Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | |
| TSX 08040 RS | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 4 | 0,21 |
| 08050 RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,30 |
| 08063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,53 |
| 08080 RS | ● | 80* | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | 7 | 0,99 |

Check the arbor attachement size (DCB) when selecting the cutter. Inserts are not included.
* Please use JIS B1176 hexagonal bolt (M12x30 to 35 mm) for securing a Ø 80 mm cutter to the arbor.

## Body - TSXF, Fine Pitch


| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | |
| TSXF 08040 RS | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 6 | 0,21 |
| 08050 RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 8 | 0,31 |
| 08063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 10 | 0,54 |
| 08080 RS | ● | 80* | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | 11 | 0,97 |

Check the arbor attachement size (DCB) when selecting the cutter. Inserts are not included.
* Please use JIS B1176 hexagonal bolt (M12x30 to 35 mm) for securing a Ø 80 mm cutter to the arbor.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | K | K | | M | | |
| General Purpose Cutting | | | | | | K | K | | M | | |
| Rough Cutting | | | | | | | | K | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 080404 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 080408 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 080412 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,2 |
| 080416 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| LNEX 080404 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 080408 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 080412 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,2 |
| 080416 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |




## Recommended Cutting Conditions


Min. - **Optimum** - Max.

| ISO | Work-material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | TSX 08000 Feed Rate $f_t$ (mm/T) | TSX 13000 Feed Rate $f_t$ (mm/T) | Grade |
|---|---|---|---|---|---|---|
| P | Carbon Steel | 180–280 | 150–**225**–300 | 0,08–**0,20**–0,30 | 0,10–**0,30**–0,40 | ACU2500 ACP100 ACP200 ACP300 XCU2500 |
| | | > 280 | 75–**150**–230 | 0,08–**0,20**–0,30 | 0,10–**0,30**–0,40 | |
| | Alloy Steel | 180–280 | 100–**175**–250 | 0,08–**0,15**–0,25 | 0,10–**0,25**–0,35 | |
| M | Stainless Steel | 220–280 | 90–**135**–180 | 0,08–**0,15**–0,25 | 0,10–**0,20**–0,30 | ACU2500 ACM200 ACM300 |
| | | >280 | 75–**125**–170 | 0,08–**0,15**–0,25 | 0,10–**0,20**–0,30 | |
| K | Cast Iron Ductile Cast Iron | 250 | 100–**175**–250 | 0,08–**0,20**–0,30 | 0,10–**0,30**–0,40 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Material | – | 30–**60**–90 | 0,05–**0,10**–0,15 | 0,05–**0,15**–0,20 | ACU2500 ACM200 ACM300 |

## Identification Details

| TSX | F | 08 | 050 | R | S |
|---|---|---|---|---|---|
| Cutter Series | F: Fine Pitch | Insert Size | Cutter Diameter | Direction | Metric Type |

## Spare Parts

| Screw | | Wrench |
|---|---|---|
|  | |  |
| BFTX0308IP | 2,0 | TRDR08IP |

● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

Expansion

## Shell Type

| Rake Angle | | |
|---|---|---|
| | Radial | -23°– -15° |
| | Axial | -6° |

12 mm 90°




Fig. 1






Fig. 2



Fig. 3



In case of TSX 13160RS
*1: Ø 66,7 / *2: 4–Ø 14

Fig. 4



## Body - TSX, Standard Pitch


| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| TSX 13040 RS | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 3 | 0,20 | 1 |
| 13050 RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,30 | 1 |
| 13063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,50 | 1 |
| 13080 RS | ● | 80* | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | 5 | 0,92 | 1 |
| 13100 RS | ● | 100* | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | – | 6 | 1,35 | 2 |
| 13125 RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9,0 | 29 | 52 | 29 | 7 | 2,55 | 1 |
| 13160 RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9,0 | 29 | 90 | – | 8 | 4,97 | 3* |
| 13200 RS | ● | 200 | 160 | 63 | 60 | 25,7 | 14,0 | 35 | 135 | – | 12 | 6,20 | 3 |
| 13250 RS | ● | 250 | 180 | 63 | 60 | 25,7 | 14,0 | 35 | 160 | – | 14 | 9,35 | 3 |
| 13315 RS | ❍ | 315 | 240 | 63 | 60 | 25,7 | 14,0 | 35 | 230 | – | 16 | 16,42 | 4 |

Check the arbor attachement size (DCB) when selecting the cutter. Inserts are not included.
*Please use JIS B1176 hexagonal bolt (Ø 80: M12x30 to 35 mm, Ø 100: M16 x 40 to 45 mm) for securing Ø 80 / Ø 100 cutter on the arbor.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | K | K | | M S | |
| General Purpose Cutting | | | | P M | | K | K | | M S | M S |
| Rough Cutting | | | | P M | P M | | | K | | M S |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 130604 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 130608 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 130612 PNER-L | ❍ | | | ● | | | | ● | ● | ● | 1,2 |
| 130616 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| 130620 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,4 |
| 130632 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 3,2 |
| LNEX 130604 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 130608 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 130612 PNER-G | ❍ | | ● | ● | ● | | ● | ● | ● | ● | 1,2 |
| 130616 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |
| 130620 PNER-G | ❍ | | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 2,4 |
| 130632 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 3,2 |
| LNEX 130604 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 0,4 |
| 130608 PNER-H | ● | ❍ | | ● | ● | ❍ | ● | ● | | | 0,8 |
| 130612 PNER-H | ❍ | | | ● | ● | | ● | ● | | | 1,2 |
| 130616 PNER-H | ● | | | ● | ● | | ● | ● | | | 1,6 |
| 130620 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 2,0 |
| 130624 PNER-H | ● | | | ● | ● | | ● | ● | | | 2,4 |
| 130632 PNER-H | ● | | | ● | ● | | ● | ● | | | 3,2 |





## Recommended Cutting Conditions

→ G34

## Identification Details

| TSX | 13 | 100 | R | S |
|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Direction | Metric Type |

## Spare Parts

| Screw | | Wrench |
|---|---|---|
|  | |  |
| BFTX03510IP | 3,0 | TRDR15IP |

# TSXM 13000 RS

Expansion

## Shell Type

| Rake Angle | | |
|---|---|---|
| Radial | -23°– -15° | 12 mm / 90° |
| Axial | -6° | |



Fig. 1





Fig. 2







Fig. 3




In case of TSX 13160RS
*1: Ø66,7 / *2: 4-Ø14

Fig. 4




## Body - TSXM, Medium Pitch


| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| TSXM 13040 RS | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 4 | 0,19 | 1 |
| 13050 RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,28 | 1 |
| 13063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,50 | 1 |
| 13080 RS | ● | 80* | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | 7 | 0,92 | 1 |
| 13100 RS | ● | 100* | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | – | 8 | 1,36 | 2 |
| 13125 RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9,0 | 29 | 52 | 29 | 10 | 2,57 | 1 |
| 13160 RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9,0 | 29 | 90 | – | 12 | 5,02 | 3* |
| 13200 RS | ● | 200 | 160 | 63 | 60 | 25,7 | 14,0 | 35 | 135 | – | 16 | 6,32 | 3 |
| 13250 RS | ● | 250 | 180 | 63 | 60 | 25,7 | 14,0 | 35 | 160 | – | 20 | 9,42 | 3 |
| 13315 RS | ❍ | 315 | 240 | 63 | 60 | 25,7 | 14,0 | 35 | 230 | – | 24 | 16,37 | 4 |

Check the arbor attachement size (DCB) when selecting the cutter. Inserts are not included.
*Please use JIS B1176 hexagonal bolt (Ø 80: M12x30 to 35 mm, Ø 100: M16 x 40 to 45 mm) for securing Ø 80 / Ø 100 cutter on the arbor.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | K | K | | M S | |
| General Purpose Cutting | | | | P M | | K | K | | M S | M S |
| Rough Cutting | M K | | | P M | P M | | | K | | M S |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 130604 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 130608 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 130612 PNER-L | ❍ | | | ● | | | | ● | ● | ● | 1,2 |
| 130616 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| 130620 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,4 |
| 130632 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 3,2 |
| LNEX 130604 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 130608 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 130612 PNER-G | ❍ | | ● | ● | ● | | ● | ● | ● | ● | 1,2 |
| 130616 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |
| 130620 PNER-G | ❍ | | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 2,4 |
| 130632 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 3,2 |
| LNEX 130604 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 0,4 |
| 130608 PNER-H | ● | ❍ | | ● | ● | ❍ | ● | ● | | | 0,8 |
| 130612 PNER-H | ❍ | | | ● | ● | | ● | ● | | | 1,2 |
| 130616 PNER-H | ● | | | ● | ● | | ● | ● | | | 1,6 |
| 130620 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 2,0 |
| 130624 PNER-H | ● | | | ● | ● | | ● | ● | | | 2,4 |
| 130632 PNER-H | ● | | | ● | ● | | ● | ● | | | 3,2 |




## Recommended Cutting Conditions

→ G34

## Identification Details

| TSX | M | 13 | 100 | R | S |
|---|---|---|---|---|---|
| Cutter Series | M: Medium Pitch | Insert Size | Cutter Diameter | Direction | Metric Type |

## Spare Parts

| Screw | | Wrench |
|---|---|---|
|  |  |  |
| BFTX03510IP | 3,0 | TRDR15IP |



● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

Expansion

## Shell Type

| Rake Angle | | |
|---|---|---|
| | Radial | -23°– -15° |
| | Axial | -6° |

12 mm

90°



Fig. 1





Fig. 2






Fig. 3




## Body - TSXF, Fine Pitch


| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| TSXF 13040 RS | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 5 | 0,18 | 1 |
| 13050 RS | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,29 | 1 |
| 13063 RS | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 7 | 0,50 | 1 |
| 13080 RS | ● | 80* | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | 8 | 0,92 | 1 |
| 13100 RS | ● | 100* | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | – | 10 | 1,34 | 2 |
| 13125 RS | ● | 125 | 80 | 63 | 40 | 16,4 | 9,0 | 29 | 52 | 29 | 14 | 2,58 | 1 |
| 13160 RS | ● | 160 | 130 | 63 | 40 | 16,4 | 9,0 | 29 | 90 | – | 16 | 5,08 | 3 |

Check the arbor attachement size (DCB) when selecting the cutter. Inserts are not included.
*Please use JIS B1176 hexagonal bolt (Ø 80: M12x30 to 35 mm, Ø 100: M16 x 40 to 45 mm) for securing Ø 80 / Ø 100 cutter on the arbor.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | K | K | | M S | |
| General Purpose Cutting | | | | P M | | K | K | | M S | M S |
| Rough Cutting | | | | P M | P M | | | K | | M S |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 130604 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 130608 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 130612 PNER-L | ❍ | | | ● | | | | ● | ● | ● | 1,2 |
| 130616 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| 130620 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,4 |
| 130632 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 3,2 |
| LNEX 130604 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 130608 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 130612 PNER-G | ❍ | | ● | ● | ● | | ● | ● | ● | ● | 1,2 |
| 130616 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |
| 130620 PNER-G | ❍ | | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 2,4 |
| 130632 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 3,2 |
| LNEX 130604 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 0,4 |
| 130608 PNER-H | ● | ❍ | | ● | ● | ❍ | ● | ● | | | 0,8 |
| 130612 PNER-H | ❍ | | | ● | ● | | ● | ● | | | 1,2 |
| 130616 PNER-H | ● | | | ● | ● | | ● | ● | | | 1,6 |
| 130620 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 2,0 |
| 130624 PNER-H | ● | | | ● | ● | | ● | ● | | | 2,4 |
| 130632 PNER-H | ● | | | ● | ● | | ● | ● | | | 3,2 |





## Recommended Cutting Conditions

→ G34

## Identification Details


| TSX | F | 13 | 100 | R | S |
|---|---|---|---|---|---|
| Cutter Series | F: Fine Pitch | Insert Size | Cutter Diameter | Direction | Metric Type |

## Spare Parts

| Screw | | Wrench |
|---|---|---|
|  | |  |
| BFTX03510IP | 3,0 | TRDR15IP |

## Shell Type






| Rake Angle | | |
|---|---|---|
| | Radial | -20°– -15° |
| | Axial | -6° – -3° |

34-60 mm 90°

## Body - TSXR


| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | | No. of Teeth | Steps | Effective Teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | APMX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| TSXR 08032RS3416Z02 | ❍ | 32 | 34 | 33 | 55 | 16,0 | 8,4 | 5,6 | 18,0 | 14 | 9 | 10 | 5 | 2 |
| 08040RS4016Z03 | ❍ | 40 | 40 | 37 | 60 | 16,0 | 8,4 | 5,6 | 18,0 | 14 | 9 | 18 | 6 | 3 |
| 08050RS5422Z03 | ❍ | 50 | 54 | 47 | 75 | 22,0 | 10,4 | 6,3 | 20,0 | 18 | 11 | 24 | 8 | 3 |
| 08050RS5422Z04 | ❍ | 50 | 54 | 47 | 75 | 22,0 | 10,4 | 6,3 | 20,0 | 18 | 11 | 32 | 8 | 4 |
| 08063RS6027Z05 | ❍ | 63 | 60 | 60 | 80 | 27,0 | 12,4 | 7,0 | 22,0 | 20 | 14 | 45 | 9 | 5 |

Inserts are not included.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | ● | ● | ● | | | ● | ● | | ● | |
| General Purpose Cutting | ● | ● | ● | ● | | ● | ● | | ● | ● |
| Rough Cutting | ● | | | ● | ● | | | ● | | ● |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 080404 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 080408 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 080412 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,2 |
| 080416 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| LNEX 080404 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 080408 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 080412 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,2 |
| 080416 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |




## Recommended Cutting Conditions

Min. - **Optimum** - Max.

| ISO | Work-material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | TSX 08000 Feed Rate $f_t$ (mm/T) | TSX 13000 Feed Rate $f_t$ (mm/T) | Grade |
|---|---|---|---|---|---|---|
| P | Carbon Steel | 180–280 | 150–**225**–300 | 0,08–**0,20**–0,30 | 0,10–**0,30**–0,40 | ACU2500 ACP100 ACP200 ACP300 XCU2500 |
| | | > 280 | 75–**150**–230 | 0,08–**0,20**–0,30 | 0,10–**0,30**–0,40 | |
| | Alloy Steel | 180–280 | 100–**175**–250 | 0,08–**0,15**–0,25 | 0,10–**0,25**–0,35 | |
| M | Stainless Steel | 220–280 | 90–**135**–180 | 0,08–**0,15**–0,25 | 0,10–**0,20**–0,30 | ACU2500 ACM200 ACM300 |
| | | >280 | 75–**125**–170 | 0,08–**0,15**–0,25 | 0,10–**0,20**–0,30 | |
| K | Cast Iron Ductile Cast Iron | 250 | 100–**175**–250 | 0,08–**0,20**–0,30 | 0,10–**0,30**–0,40 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Material | – | 30–**60**–90 | 0,05–**0,10**–0,15 | 0,05–**0,15**–0,20 | ACU2500 ACM200 ACM300 |

## Identification Details

| TSXR | 08 | 050 | R | S | 54 | 22 | Z03 |
|---|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Direction | Metric Type | Max. Depth of Cut | Bore Diameter | Effective Teeth |

## Spare Parts

| Applicable Cutters | | | | Bolt |
|---|---|---|---|---|
| TSXR 08032RS3416Z02 | TRDR08IP | BFTX0308IP | 2,0 | BX0845 |
| TSXR 08040RS4016Z03 | | | | BX0850 |
| TSXR 08050RS5422Z03 | | | | BX1060 |
| TSXR 08050RS5422Z04 | | | | |
| TSXR 08063RS6027Z05 | | | | BX1265 |



● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)


# "Sumi Dual Mill" Series
# TSXR 13000 RS

| Rake Angle | | |
|---|---|---|
| | Radial | -23°– -15° |
| | Axial | -6° – -3° |

41-60 mm
90°

## Shell Type






## Body - TSXR


| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | | No. of Teeth | Steps | Effective Teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | APMX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | |
| TSXR 13040RS4116Z02 | ❍ | 40 | 41 | 37 | 60 | 16,0 | 8,4 | 5,6 | 18,0 | 14 | 9 | 8 | 4 | 2 |
| 13050RS6022Z03 | ❍ | 50 | 60 | 47 | 80 | 22,0 | 10,4 | 6,3 | 20,0 | 18 | 11 | 18 | 6 | 3 |
| 13063RS5027Z03 | ❍ | 63 | 50 | 60 | 75 | 27,0 | 12,4 | 7,0 | 22,0 | 20 | 14 | 15 | 5 | 3 |
| 13063RS6027Z04 | ❍ | 63 | 60 | 60 | 80 | 27,0 | 12,4 | 7,0 | 22,0 | 20 | 14 | 24 | 6 | 4 |
| 13080RS6032Z04 | ❍ | 80 | 60 | 77 | 80 | 32,0 | 14,4 | 8,0 | 32,0 | 25 | 18 | 24 | 6 | 4 |
| 13080RS6032Z05 | ❍ | 80 | 60 | 77 | 80 | 32,0 | 14,4 | 8,0 | 32,0 | 25 | 18 | 30 | 6 | 5 |
| 13100RS6040Z05 | ❍ | 100 | 60 | 88 | 85 | 40,0 | 16,4 | 9,0 | 29,0 | 32 | 21 | 30 | 6 | 5 |
| 13100RS6040Z06 | ❍ | 100 | 60 | 88 | 85 | 40,0 | 16,4 | 9,0 | 29,0 | 32 | 21 | 36 | 6 | 6 |
| 13125RS6040Z07 | ❍ | 125 | 60 | 100 | 85 | 40,0 | 16,4 | 9,0 | 29,0 | 32 | 21 | 42 | 6 | 7 |

Inserts are not included.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | K | K | | MS | |
| General Purpose Cutting | | | | | | K | K | | MS | MS |
| Rough Cutting | | | | | | | | K | | MS |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 130604 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 130608 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 130612 PNER-L | ❍ | | | ● | | | | ● | ● | ● | 1,2 |
| 130616 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| 130620 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,4 |
| 130632 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 3,2 |
| LNEX 130604 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 130608 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 130612 PNER-G | ❍ | | ● | ● | ● | | ● | ● | ● | ● | 1,2 |
| 130616 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |
| 130620 PNER-G | ❍ | | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 2,4 |
| 130632 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 3,2 |
| LNEX 130604 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 0,4 |
| 130608 PNER-H | ● | ❍ | | ● | ● | ❍ | ● | ● | | | 0,8 |
| 130612 PNER-H | ❍ | | | ● | ● | | ● | ● | | | 1,2 |
| 130616 PNER-H | ● | | | ● | ● | | ● | ● | | | 1,6 |
| 130620 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 2,0 |
| 130624 PNER-H | ● | | | ● | ● | | ● | ● | | | 2,4 |
| 130632 PNER-H | ● | | | ● | ● | | ● | ● | | | 3,2 |




## Recommended Cutting Conditions

→ G38

## Spare Parts

| Applicable Cutters | Insert Wrench | Insert Screw | | Bolt |
|---|---|---|---|---|
| TSXR 13040RS4116Z02 | TRDR15IP | BFTX03510IP | 3,0 | BX0850 |
| TSXR 13050RS6022Z03 | | | | BX1060 |
| TSXR 13063RS5027Z03 | | | | BX1260 |
| TSXR 13063RS6027Z04 | | | | BX1265 |
| TSXR 13080RS6032Z04 | | | | BX1660 |
| TSXR 13080RS6032Z05 | | | | |
| TSXR 13100RS6040Z05 | | | | BX2065 |
| TSXR 13100RS6040Z06 | | | | |
| TSXR 13125RS6040Z07 | | | | |

## Identification Details

| TSXR | 13 | 050 | R | S | 60 | 22 | Z03 |
|---|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Direction | Metric Type | Max. Depth of Cut | Bore Diameter | Effective Teeth |

Expansion



## General Features

- **Supports Various Machining Operations**

  A lineup of cutter sizes from Ø 14 to Ø 160 mm, which enable large ramping angles, 28 repeater type items are now available in addition to the modular type and short shank type.

- **Excellent Machining Quality**

  With a combination of optimised cutting edge shape and high-precision molding technology, superb wall surface accuracy and surface finish qualitiy are achieved.

- **Excellent Sharpness with Low Resistance**

  Reducing machining noise and suppressing burrs, the lineup includes ground type inserts with a focus on sharpness.

- **Applicable to Various Work Materials**

  In addition to the general-purpose grade ACU2500, the new generatioin coated carbide grades XCU2500/XCK2000 are available. Applicable to various work materials such as steel, stainless steel, cast iron, exotic alloys and more.

## Product Range WEZ (Standard)

| Type | Cat. No. | Diameter Range (mm) / No of Teeth | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | Ø14 | Ø16 | Ø18 | Ø20 | Ø22 | Ø25 | Ø26 | Ø28 | Ø30 | Ø32 | Ø35 | Ø40 | Ø50 | Ø63 | Ø80 | Ø100 | Ø125 | Ø160 |
| Shell | WEZ 11000RS | | | | | | | | | | | | 4, 6 | 5,7 | 6, 8 | 7, 10 | 9, 12 | | |
| | WEZ 11000R (Inch) | | | | | | | | | | | | | | | 7, 10 | 9, 12 | | |
| | WEZ 17000RS | | | | | | | | | | | | 3, 4 | 3, 5 | 4, 6 | 4, 7 | 5, 8 | 6, 9, 11 | 8, 10 12 |
| | WEZ 17000R (Inch) | | | | | | | | | | | | | | | 4, 7 | 5, 8 | 6, 9, 11 | 8, 10 12 |
| Shank | WEZ 11000E | 1 | 2* | 2 | 2*, 3* | 3 | 2, 3*, 4* | | 4 | 4 | 2, 3, 4, 5* | 5 | 2, 4, 6 | 5, 7 | 8 | 10 | | | |
| | WEZ 11000ES | 1 | 2* | | 3* | | 4* | | | | | | | | | | | | |
| | WEZ 11000EL | 1 | 2* | 2 | 2* | 2 | 2*, 3 | | 2 | 2 | 2*, 3 | 2, 3 | 2 | 3 | | | | | |
| | WEZ 17000E | → H30-41 | | | | | 2* | | 2 | 3 | 2, 3* | 3 | 3, 4 | 3*, 5* | 4*, 6* | 7 | | | |
| | WEZ 17000ES | | | | | | 2 | | | | 3 | | | | | | | | |
| | WEZ 17000EL | | | | | | 2 | | 2 | 2 | 2*, 3 | 2 | 2, 3, 4 | 3*, 5* | 4*, 6* | | | | |
| Modu-lar | WEZ 11000M | | 2 | 2 | 2, 3 | 3 | 2, 3, 4 | 4, 5 | 4, 5 | 2, 4, 5 | 2, 3, 4, 5 | 2, 5 | 2, 4, 5, 6 | | | | | | |
| | WEZ 17000M | → H46-49 | | | | | 2, 3 | | 2 | 2, 3 | 2, 3, 4 | 2, 3 | 2, 3, 4 | | | | | | |

* Different shank diameters in stock


## Product Range WEZR (Repeater)

| Type | Cat. No. | Diameter Range (mm) / No of Teeth | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| | | Ø20 | Ø25 | Ø30 | Ø32 | Ø35 | Ø40 | Ø50 | Ø63 | Ø80 |
| Shell | WEZR 11000RS | | | | | | 4 | 4 | | |
| | WEZR 17000RS | | | | | | | 2, 3, 4 | 3, 4, 5 | 5 |
| Shank | WEZR 11000E | 1,2 | 2 | 2 | 2, 3 | 3 | 3, 4 | | | |
| | WEZR 17000E | → H42-45 | | | | | 2,3 | 2,3 | | |
| Modu-lar | WEZR 11000M | | | | 3 | | | | | |
| | WEZR 17000M | → H50-53 | | | | | 3 | | | |


## Suitable Applications

- **Supports Ramping, Helical Milling, Plunge Cutting**

Face milling



Shoulder milling




Side face milling



Groove milling



Hole expansion milling



Ramping



Helical milling



Plunge cutting



## Optimised Body Design

Wide guide face for stable insert clamping.




WEZ11 type

● = Euro stock

## Chipbreaker Lineup

| Work Material | P | M | K | S | H | N |
|---|---|---|---|---|---|---|
| Chipbreaker | L Type | G Type | H Type | F Type | P Type | S Type |
| **AO_T11** Cutting edge geometry | | 28° | 20° | 28° | 28° | 28° |
| **AO_T17** Cutting edge geometry | 28° | 20° | 10° | 28° | 28° | 28° |
| Applications | Light cut, low rigidity machining | Main breaker for general purpose to interrupted machining | Heavy cut, heavy interrup-ted machining, hardened steel | Light cut, finishing, low-burr design | Light cut, high-precision machining, high surface wall quality | For non-ferrous metals |





## Product Range Inserts

Main Grade: ACU2500; S-Type: H20, DL2000

| Cat. No. | Nose Radius (mm) | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R0,2 | R0,4 | R0,5 | R0,8 | R1,0 | R1,2 | R1,6 | R2,0 | R2,4 | R3,0 | R3,2 | R4,0 | R5,0 | R6,4 |
| AOMT 11T3__PEER-G | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | |
| AOMT 11T3__PEER-H | | ● | | ● | | ● | ● | | | | | | | |
| AOET 11T3__PEER-F | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | |
| AOET 11T3__PEER-P16 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 11T3__PEER-P20 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 11T3__PEER-P25 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 11T3__PEFR-S | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | |
| AOMT 1705__PEER-L | ● | ● | | ● | | ● | ● | | | | | | | |
| AOMT 1705__PEER-G | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| AOMT 1705__PEER-H | | ● | | ● | | ● | ● | | | | | | | |
| AOET 1705__PEER-F | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| AOET 1705__PEER-P25 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 1705__PEER-P32 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 1705__PEFR-S | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |


## Improved Milling Quality

### ● Excellent Squareness





| | |
|---|---|
| Machine: | Vertical Machining Centre BT40, |
| Work Material: | C50 |
| Tool: | WEZ 11020 E03 (Ø 20, 3 teeth) |
| Insert: | AOMT11T308PEER-G (ACU2500) |
| Cutting Conditions: | $v_c$ = 150 m/min, $f_z$ = 0,15 mm/t, $a_p$ = 6 mm x 4 passes, $a_e$ = 5 mm, dry |

### ● Excellent Surface Quality




### ● Lower cutting force helps reduce machining noise




| | |
|---|---|
| Machine: | Vertical Machining Centre BT40, |
| Work Material: | C50 |
| Tool: | WEZ 11020 E03 (Ø 20, 3 teeth) |
| Insert: | AOMT11T308PEER-G (ACU2500) |
| Cutting Conditions: | $v_c$ = 150 m/min, $f_z$ = 0,15 mm/t, $a_p$ = 8 mm, $a_e$ = 5 mm, dry |



## Features

### Developed for Multi-tasking Machines

Short shank type ideal for low-rigidity multi-tasking machines

### Superb Machining Quality


Shank design ideal for ER collets with face contact design that increases rigidity, realizing excellent shoulder accuracy and finished surface quality.


### A Wide Selection of Inserts


Supports various machining applications with a wide selection of chipbreakers, with sharp cutting edges, different nose radi and dedicated grades for specific work materials.

## Cutting Performance

### Excellent Squareness








| | |
|---|---|
| Machine: | Composite NC lathe |
| Work Matarial: | X5CrNiS1810, Ø 16 round bar |
| Tool: | WEZ11020ES03-10 (Ø 20, 3 flutes) |
| Insert: | AOET11T308PEER-F (ACU2500) |
| Cutting Data: | $v_c$ = 100 m/min, $f_z$ = 0,08 mm/t<br>$a_p$ = 6 mm x 2 passes, $a_e$ = 2 mm, wet |

### Excellent Machined Surface Quality






| | |
|---|---|
| Machine: | Composite NC lathe |
| Work Matarial: | X5CrNiS1810, Ø 16 round bar |
| Tool: | WEZ11020ES03-10 (Ø 20, 3 flutes) |
| Insert: | AOET11T308PEER-F (ACU2500) |
| Cutting Data: | **WEZ** type: $v_c$ = 100 m/min, $f_z$ = 0,05 mm/t, $a_p$ = 2 mm, $a_e$ = 12 mm, wet<br>Competitor: $v_c$ = 100 m/min, $f_z$ = 0,05 mm/t, $a_p$ = 2 mm, $a_e$ = 6 mm x 2 passes, wet (solid carbide endmill) |

Larger tool diameter than carbide solid endmills enables reduced number of passes for high-efficiency machining.

Good shoulder accuracy and machined surface quality, eliminating the finishing process.

## ■ Shoulder Milling Tool Selection Guide

**TSX Series – Accuracy**


Ground insert



**WEZ Series – Sharpness**


High rake wave cutting edge






**DFC Series – Economical**

Six-cornered double side insert



**WFX Series – General Purpose**

Four-cornered single side insert




★★★ Top recommendation

| | Surface Finish | Shoulder Accuracy | Cutting Force | Chip Control | Number of Corners | Cutting edge Strength |
|---|---|---|---|---|---|---|
| **WEZ** Series | ★★★ | ★★★ | ★★★ | ★★★ | ★ | ★☆ |
| **TSX** Series | ★★★ | ★★★ | ★★ | ★☆ | ★★ | ★★★ |
| **DFC** Series | ★☆ | ★ | ★ | ★☆ | ★★★ | ★★★ |
| **WFX** Series | ★☆ | ★★ | ★★ | ★★★ | ★★ | ★★ |

## High-precision Ground Class Insert with Excellent Sharpness

### Ground Finish on Cutting Edge and Guide Face

The guide face has a ground finish as well as the cutting edge, minimizing corner difference when mounting on the body.
Stable runout precision and machining qualitiy.




## Lineup of Chipbreakers for Ground Inserts


### F Type

Cutting edge specialized for sharpness and machining accuracy




Sharpness from ground finish enables burr control.

Excellent squareness with all diameters.










| | |
|---|---|
| Machine: | Vertical Machining Centre BT50, |
| Work Material | X5CrNiS18 9 |
| Tool: | WEZ 11050 RS07 (Ø 50, 7 teeth) |
| Insert: | AOET11T308PEER-F (ACU2500) |
| Cutting Conditions: | $v_c$ = 120 m/min, $f_z$ = 0,12 mm/t, $a_p$ = 1 mm, $a_e$ = 30 mm, dry |


### P Type


Chipbreaker for wall surface squareness equivalent to solid endmills



Premium item with cutting edge shape optimised for each cutter diameter while maintaining the F type chipbreaker's sharpness.

Enables wall surface squareness equal to solid endmills through a blade shape optimised for each tool diameter.




P Type Chipbreaker Selection

| Cat. No. | Cutter Diameter (mm) | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | Ø14 | Ø16 | Ø18 | Ø20 | Ø22 | Ø25 | Ø28 | Ø30 | Ø32 | Ø35 | => Ø40 |
| AOET11T3_ _PEER-P_ _ | -P16 | | -P20 | | – | -P25 | | – | | | |
| AOET1705_ _PEER-P_ _ | – | | | | | -P25 | | -P32 | | | – |

| | |
|---|---|
| Machine: | Vertical Machining Centre BT50, |
| Work Material: | C50 |
| Tool: | WEZ 11020 E03 (Ø 20, 3 teeth) |
| Insert: | AOET11T308PEER-P20 (ACU2500) |
| Cutting Conditions: | $v_c$ = 150 m/min, $f_z$ = 0,1 mm/t, $a_p$ = 8 mm x 3 passes, $a_e$ = 1 mm, dry |

### S Type

Sharp edge chipbreaker for non-ferrous metals, with excellent adhesion resistance



Suppresses adhesion with rake face lapping.

DLC coat inserts available for further improved adhesion resistance.











| | |
|---|---|
| Machine: | Vertical Machining Centre BT50, |
| Work Material: | AlSi12Cu |
| Tool: | WEZ 11020 E03 (Ø 20, 3 teeth) |
| Insert: | AOET11T308PEER-S (H20) |
| Cutting Conditions: | $v_c$ = 350 m/min, $f_z$ = 0,1 mm/t, $a_p$ = 3 mm, $a_e$ = 10 mm, dry |

## Insert Grades Selection Guide


New generation coated carbide grades **XCU2500/ XCK2000** now available. Enhanced lineup of coatings in addition to cemented carbide and cermet for milling steel, stainless steel, cast iron and aluminum alloy.




## Coating Features

New Absotech ™ (absolute technology) coating technology that realises absolute stability.

### ABSOTECH CVD





**Special Surface Treatment**
Suppresses thermal cracking by introducing high compressive stress, resulting in chipping resistance more than twice as good as conventional types

**Crystal Orientation Control $Al_2O_3$**
By controlling the growth direction, $Al_2O_3$ is reinforced for crater wear resistance more than twice as good as conventional types

**High Hardness TiCN**
Increased TiCN hardness by using a C-rich composition for flank wear resistance more than twice as good as conventional types.

Grades: ACP2000, ACK2000

### ABSOTECH PVD





**New Super Multi-Layered Composition**
Higher hardness and twice the conventional wear resistance due to a fine crystal structure
AlTiCrBN-based nano-layered coating.

**High Adhesion Strength**
Significantly improved coating adhesion. Chipping resistance more than twice as good as conventional types.

Grades: ACU2500, ACP3000, ACK3000

### ABSOTECH X CVD




**Pure cubic crystal AlTiN with high Al content**
With proprietary structural control technology, differently composed layers of AlTiN are stacked at the nanometre level.
With a high Al-compositioin containing over 80% Al on average, it also maintains a cubic crystalline structure to achieve excellent thermal resitance and high hardness.
Vastly improved wear resistance.

**Special Surface Treatment**
Proprietary surface treatment introduces high compressioin stress to the coating, suppressing the development of cracks.
Greatly improved fracture and thermal crack resistance.

Grades: XCU2500, XCK2000

## Grade Characteristic Values

### CVD

| ISO | Grade | Hardness (HRA) | TRS (GPa) | Coating Type | Coating Thickness (μm) | Features | Old Grade |
|---|---|---|---|---|---|---|---|
| P | ACP2000 | 89,5 | 3.2 | ABSOTECH | 10 | · For high-speed machining of steel<br>· Stable long tool life in high-speed machining is realised by adopting a tough carbide substrate and a new coating with excellent thermal crack resistance | ACP100 |
| P | New XCU2500 | 89,5 | 3,2 | ABSOTECH X | 6 | · General-purpose grade for a wide variety of materials such as steel, cast iron and stainless steel<br>· New coating combining wear and fracture resistance realises long tool life in medium-speed to high-speed machining | — |
| M | ACM200 | 89,8 | 3,4 | Super FF Coat | 6 | · For machining high-hardness stainless steel<br>· Adopts newly developed high-strength cemented carbide substrate with excellent wear resistance and thermal resistance, realizing outstanding stability when machining hardened stainless steel | AC230 |
| K | ACK2000 | 91,7 | 3,1 | ABSOTECH | 10 | · For high-speed cast iron milling<br>· Stable long tool life in high-speed machining is realised by adopting a tough carbide substrate and a new coating with excellent thermal resistance | ACK100<br>ACK200 |
| K | New XCK2000 | 91,7 | 2,5 | ABSOTECH X | 6 | · For high-speed cast iron milling<br>· Along with a high-hardness carbide substrate, the new coating combining wear and fracture resistance realises superb long tool life in medium-speed to high-speed machining | — |

### PVD

| ISO | Grade | Hardness (HRA) | TRS (GPa) | Coating Type | Coating Thickness (μm) | Features | Old Grade |
|---|---|---|---|---|---|---|---|
| P | ACU2500 | 91,6 | 3,8 | ABSOTECH | 3 | · General-purpose grade supporting steel, stainless steel, and cast iron machining<br>· Adopts a carbide substrate with excellent fracture resistance and wear resistance, plus a new coating with excellent wear resistance and chipping resistance, realising stable long tool life with various work material grades | — |
| P | ACP3000 | 89,5 | 3,2 | ABSOTECH | 3 | · Our 1st recommended grade for milling steel<br>· Carbide substrate with excellent thermal crack resistance, plus a new coating with excellent wear resistance and chipping resistance, realises stable long tool life over a wide range of cutting conditions | ACP200<br>ACP300 |
| M | ACM300 | 89,8 | 3,4 | (New) Super ZX Coat | 3 | · Our 1st recommended grade for milling stainless steel<br>· Adopts high-strength cemented carbide substrate and super multi-layered coating for next-level wear resistance and fracture resistance | — |
| K | ACK3000 | 91,7 | 3,1 | ABSOTECH | 3 | · Our 1st recommended grade for milling cast iron<br>· Adopts a high thermal conductivity carbide substrate and a new coating with excellent wear resistance and chipping resistance, realizing stable long tool life over a wide range of cast iron machining operations | ACK300 |
| N | DL2000 | 91,6 | 3,8 | AURORA Coat (DLC) | 0,5 | · Grade for milling non-ferrous metal, utilising DLC coat with a low coefficient of friction and excellent adhesion resistance | — |

### Cermet


| ISO | Grade | Hardness (HRA) | TRS (GPa) | Coating Type | Coating Thickness (μm) | Features | Old Grade |
|---|---|---|---|---|---|---|---|
| P M | T2500A | 91,8 | 2,4 | — | — | · For finishing of steel and stainless steel<br>· Fine, uniform grain structure greatly improves toughness, realising long tool life and excellent surface finishes | T250A |

Expansion

## Recommended Cutting Conditions

### WEZ11 Type

Cutter: WEZ 11020 E03
Insert: AO_T11T3 type
Cutting Data: $a_p$ = 3 mm, $a_e$ = 10 mm, dry





Min. - **Optimum** - Max.

| ISO | Material | HB | Chipbreaker | Grade | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | ACU2500 | XCU2500 | ACP2000 | ACP3000 | T2500A | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | DL2000 |
| | | | | Feed Rate (mm/tooth) | | | | | | | | | | |
| | | | | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,18 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,05–0,10–0,15 |
| | | | | Cutting Speed $v_c$ (m/min) | | | | | | | | | | |
| P | Unalloyed steel, <0, 15%C, annealed | 125 | G | 270–320–370 | 300–350–400 | 300–350–400 | 250–300–350 | 230–280–330 | | | | | | |
| P | · , <0, 45%C, annealed | 190 | G | 170–220–270 | 200–250–300 | 200–250–300 | 150–200–250 | 130–180–230 | | | | | | |
| P | · , <0, 45%C, tempered | 250 | G | 140–180–220 | 160–200–245 | 160–200–245 | 120–160–200 | 105–145–185 | | | | | | |
| P | · , <0, 75%C, annealed | 270 | G | 110–145–175 | 130–165–195 | 130–165–195 | 100–130–165 | 85–115–150 | | | | | | |
| P | · , <0, 75%C, tempered | 300 | G | 70–90–110 | 80–100–120 | 80–100–120 | 60–80–100 | 50–70–90 | | | | | | |
| P | Low alloyed steel, annealed | 180 | G | 160–205–255 | 190–235–280 | 190–235–280 | 140–190–235 | 120–170–215 | | | | | | |
| P | · , tempered | 275 | G | 90–120–150 | 110–135–165 | 110–135–165 | 80–110–140 | 70–100–125 | | | | | | |
| P | · , tempered | 300 | G | 85–110–130 | 100–125–150 | 100–125–150 | 75–100–125 | 65–90–115 | | | | | | |
| P | · , tempered | 350 | G | 60–80–100 | 70–90–110 | 70–90–110 | 50–70–90 | 45–65–85 | | | | | | |
| P | High alloyed and tool steel, annealed | 200 | G | 140–180–220 | 160–200–245 | 160–200–245 | 120–160–205 | | | | | | | |
| P | · , tempered | 325 | G | 55–70–85 | 60–80–100 | 60–80–100 | 50–65–80 | | | | | | | |
| M | Stainless steel, ferritic/martensitic, annealed | 200 | G | 110–140–170 | 160–190–210 | | | | | | | 140–170–190 | 90–110–140 | |
| M | · , martensitic, tempered | 240 | G | 100–125–150 | 145–170–190 | | | | | | | 125–150–170 | 80–100–125 | |
| M | · , austenitic, plunged | 180 | G | 120–150–180 | 170–200–220 | | | | | | | 150–180–200 | 100–120–150 | |
| K | Grey cast iron | | G | 150–200–250 | 250–300–350 | | | | 250–300–350 | 250–300–350 | 170–220–270 | | | |
| K | Nodular cast iron | | G | 90–120–150 | 150–180–210 | | | | 150–180–210 | 150–180–210 | 100–130–160 | | | |
| S | High tempered resist. alloys, Fe based, annealed | | G | 30–40–55 | | | | | | | | 35–45–60 | 25–35–50 | |
| S | · , hardened | | G | 60–80–100 | | | | | | | | 70–90–110 | 50–70–90 | |
| N | Aluminium alloy, Si < 12,6% | | S | | | | | | | | | | | 500–750–100 |
| N | · , Si > 12,6% | | S | | | | | | | | | | | 170–200–250 |
| N | Copper alloy | | S | | | | | | | | | | | 300–330–350 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.
For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

### WEZ17 Type

Cutter: WEZ 17032 E03
Insert: AO_T1705 type
Cutting Data: $a_p$ = 5 mm, $a_e$ = 16 mm, dry





Min. - **Optimum** - Max.

| ISO | Material | HB | Chipbreaker | Grade | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | ACU2500 | XCU2500 | ACP2000 | ACP3000 | T2500A | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | DL2000 |
| | | | | Feed Rate (mm/tooth) | | | | | | | | | | |
| | | | | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,15–0,22 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,05–0,10–0,15 |
| | | | | Cutting Speed $v_c$ (m/min) | | | | | | | | | | |
| P | Unalloyed steel, <0, 15%C, annealed | 125 | G | 285–335–390 | 315–360–420 | 315–360–420 | 265–315–370 | 240–295–345 | | | | | | |
| P | · , <0, 45%C, annealed | 190 | G | 180–230–285 | 210–265–315 | 210–265–315 | 160–210–265 | 135–190–240 | | | | | | |
| P | · , <0, 45%C, tempered | 250 | G | 145–190–230 | 170–210–255 | 170–210–255 | 130–170–215 | 110–155–195 | | | | | | |
| P | · , <0, 75%C, annealed | 270 | G | 115–150–185 | 135–170–205 | 135–170–205 | 100–135–170 | 90–125–155 | | | | | | |
| P | · , <0, 75%C, tempered | 300 | G | 70–90–115 | 85–105–125 | 85–105–125 | 65–85–105 | 55–75–95 | | | | | | |
| P | Low alloyed steel, annealed | 180 | G | 170–220–265 | 200–245–295 | 200–245–295 | 150–200–250 | 130–180–225 | | | | | | |
| P | · , tempered | 275 | G | 100–130–155 | 115–145–175 | 115–145–175 | 85–115–145 | 75–105–135 | | | | | | |
| P | · , tempered | 300 | G | 90–115–140 | 105–130–155 | 105–130–155 | 75–105–130 | 65–90–120 | | | | | | |
| P | · , tempered | 350 | G | 65–85–100 | 75–95–115 | 75–95–115 | 55–75–95 | 50–70–85 | | | | | | |
| P | High alloyed and tool steel, annealed | 200 | G | 145–185–230 | 170–215–255 | 170–215–255 | 130–170–215 | | | | | | | |
| P | · , tempered | 325 | G | 55–75–90 | 65–85–100 | 65–85–100 | 50–65–85 | | | | | | | |
| M | Stainless steel, ferritic/martensitic, annealed | 200 | G | 115–145–175 | 165–195–215 | | | | | | | 145–175–195 | 100–115–145 | |
| M | · , martensitic, tempered | 240 | G | 105–130–155 | 150–175–195 | | | | | | | 130–155–175 | 85–105–130 | |
| M | · , austenitic, plunged | 180 | G | 125–155–190 | 180–210–230 | | | | | | | 160–190–210 | 105–125–160 | |
| K | Grey cast iron | | G | 160–210–265 | 265–315–370 | | | | 265–315–370 | 265–315–370 | 180–230–285 | | | |
| K | Nodular cast iron | | G | 95–125–160 | 160–190–220 | | | | 160–190–220 | 160–190–220 | 105–140–170 | | | |
| S | High tempered resist. alloys, Fe based, annealed | | G | 30–40–60 | | | | | | | | 35–45–60 | 25–35–50 | |
| S | · , hardened | | G | 60–85–105 | | | | | | | | 75–95–115 | 50–75–95 | |
| N | Aluminium alloy, Si < 12,6% | | S | | | | | | | | | | | 500–750–100 |
| N | · , Si > 12,6% | | S | | | | | | | | | | | 170–200–250 |
| N | Copper alloy | | S | | | | | | | | | | | 300–330–350 |


The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.
For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

## Ramping / Helical Milling Upper Limits


Ramping




Flat Bottom Machining




Machining with Prepared Hole




### WEZ11 Type


| DC Ø (mm) | Max.Ramping Angle | Flat Bottom Machining | | | | Machining with Prepared Hole | |
|---|---|---|---|---|---|---|---|
| | RPMX (°) | Max. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) |
| 14 | 13,2 | 25,3 | 8,4 | 23,1 | 5,9 | 19,0 | 1,9 |
| 16 | 10,5 | 29,3 | 7,6 | 27,0 | 5,6 | 21,7 | 1,5 |
| 18 | 8,1 | 33,3 | 6,7 | 30,9 | 5,0 | 25,2 | 1,4 |
| 20 | 6,5 | 37,3 | 6,0 | 34,9 | 4,6 | 29,1 | 1,3 |
| 22 | 5,3 | 41,3 | 5,4 | 38,8 | 4,3 | 32,9 | 1,3 |
| 25 | 4,1 | 47,3 | 4,8 | 44,8 | 3,9 | 38,9 | 1,3 |
| 28 | 3,4 | 53,3 | 4,4 | 50,7 | 3,6 | 44,9 | 1,3 |
| 30 | 3,0 | 57,3 | 4,2 | 54,7 | 3,5 | 48,8 | 1,3 |
| 32 | 2,7 | 61,3 | 4,0 | 58,7 | 3,3 | 52,8 | 1,2 |
| 35 | 2,3 | 67,3 | 3,8 | 64,6 | 3,1 | 58,8 | 1,2 |
| 40 | 1,8 | 77,3 | 3,4 | 74,6 | 2,9 | 68,8 | 1,2 |
| 50 | 1,2 | 97,3 | 3,0 | 94,6 | 2,6 | 88,8 | 1,1 |
| 63 | 0,8 | 123,3 | 2,8 | 120,5 | 2,5 | 114,7 | 1,1 |

### WEZ17 Type

| DC Ø (mm) | Max.Ramping Angle | Flat Bottom Machining | | | | Machining with Prepared Hole | |
|---|---|---|---|---|---|---|---|
| | RPMX (°) | Max. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) |
| 25 | 10,8 | 47,3 | 13,0 | 41,0 | 8,3 | 33,1 | 1,8 |
| 28 | 8,1 | 53,3 | 11,1 | 46,9 | 7,5 | 39,0 | 1,8 |
| 30 | 7,0 | 57,3 | 10,2 | 50,9 | 7,0 | 43,0 | 1,8 |
| 32 | 6,1 | 61,3 | 9,5 | 54,9 | 6,7 | 47,0 | 1,7 |
| 35 | 5,1 | 67,3 | 8,7 | 60,8 | 6,2 | 53,0 | 1,7 |
| 40 | 4,0 | 77,3 | 7,7 | 70,8 | 5,7 | 63,0 | 1,7 |
| 50 | 2,5 | 97,3 | 6,5 | 90,7 | 5,0 | 83,0 | 1,6 |
| 63 | 1,8 | 123,3 | 5,6 | 116,7 | 4,5 | 109,0 | 1,6 |

* The table above shows values with nose radius 0,8 mm

## Plunge Cutting - Upper Limit for Radial Width $a_e$




| Type | Max. $a_e$ (mm) |
|---|---|
| WEZ11 | 3 |
| WEZ17 | 5 |


## Precautions for Mounting

(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.






# WEZ 11000 R(S)

| Rake Angle | | |
|---|---|---|
| | Radial | -7° – -11° |
| | Axial | 14° – 15° |

10 mm 90°



Fig. 1





Fig. 2






Fig. 3




## Body - WEZ (Shell Type)

Dimensions (mm)

| | Cat. No. | Stock | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | D3 | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | WEZ 11040RS04 | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | – | 4 | 0,21 | 1 |
| | 11040RS06 | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | – | 6 | 0,20 | 1 |
| | 11050RS05 | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 5 | 0,32 | 1 |
| | 11050RS07 | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 7 | 0,31 | 1 |
| | 11063RS06 | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 6 | 0,58 | 1 |
| | 11063RS08 | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 8 | 0,57 | 1 |
| | 11080RS07 | ● | *80 | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | – | 7 | 1,08 | 1 |
| | 11080RS10 | ● | *80 | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | – | 10 | 1,07 | 1 |
| | 11100RS09 | ● | 100 | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | – | – | 9 | 1,57 | 3 |
| | 11100RS12 | ● | 100 | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | – | – | 12 | 1,56 | 3 |
| Inch | WEZ 11080R07 | ❍ | *80 | 55 | 50 | 25,4 | 9,5 | 6,0 | 25 | 20 | 14 | – | 7 | 1,09 | 1 |
| | 11080R10 | ❍ | *80 | 55 | 50 | 25,4 | 9,5 | 6,0 | 25 | 20 | 14 | – | 10 | 1,08 | 1 |
| | 11100R09 | ❍ | *100 | 70 | 63 | 31,75 | 12,7 | 8,0 | 32 | 46 | 27 | 18 | 9 | 2,12 | 2 |
| | 11100R12 | ❍ | *100 | 70 | 63 | 31,75 | 12,7 | 8,0 | 32 | 46 | 27 | 18 | 12 | 2,10 | 2 |

Inserts are sold separately. Check the arbor mounting size (DCB) when selecting the cutter.



* For securing the Ø 80 mm and Ø 100 mm cutter to the arbors, use JIS B1176 hexagonal bolt. (Ø 80 mm: M12x30 to 35 mm, Ø 100 mm: M16x40x45 mm)

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| WEZ 11040RS04 | BFTX0306IP | 1,5 | TRDR08IP |
| 11040RS06 | | | |
| 11050RS05 | | | |
| 11050RS07 | | | |
| 11063RS06 | | | |
| 11063RS08 | | | |
| 11080R(S)07 | | | |
| 11080R(S)10 | | | |
| 11100R(S)09 | | | |
| 11100R(S)12 | | | |

## Recommended Cutting Conditions

→ G46

## Identification Details

| WEZ | 11 | 050 | R | S | 07 |
|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Feed Direction | Metric | Number of Teeth |

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT11T324PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
❍ = Japan stock
❑ = On request
– = Not available
N·m Recommended Tightening Torque (N·m)

Expansion

## ■ Inserts

Precautions for Mounting → G47

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | K P M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | K P M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 11T302PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ● | 0,2 | 1 |
| 11T304PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 11T305PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 11T308PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 11T310PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 11T312PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 11T316PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 11T320PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 11T324PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 11T330PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 2 |
| 11T332PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 3,2 | 2 |
| AOMT 11T304PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 11T308PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 11T312PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 11T316PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 11T302PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T316PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 11T320PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 11T324PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 11T330PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 2 |
| 11T332PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 2 |
| AOET 11T302PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 11T304PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 11T305PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 11T308PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 11T310PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 11T312PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 11T316PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 11T320PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 11T324PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 11T330PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 2 |
| 11T332PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

# WEZ 17000 R(S)

| Rake Angle | Radial | -4° – -9° |
|---|---|---|
| | Axial | 10° – 15° |

15 mm 90°




Fig. 1




Fig. 2




Fig. 3





Fig. 4



Fig. 5



## Body - WEZ (Shell Type)

Dimensions (mm)

| | Cat. No. | Stock | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | D3 | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | WEZ 17040RS03 | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | – | 3 | 0,19 | 1 |
| | 17040RS04 | ● | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | – | 4 | 0,16 | 1 |
| | 17050RS03 | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 3 | 0,30 | 1 |
| | 17050RS05 | ● | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 5 | 0,26 | 1 |
| | 17063RS04 | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 4 | 0,54 | 1 |
| | 17063RS06 | ● | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 6 | 0,51 | 1 |
| | 17080RS04 | ● | *80 | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | – | 4 | 1,10 | 1 |
| | 17080RS07 | ● | *80 | 55 | 50 | 27 | 12,4 | 7,0 | 22 | 20 | 14 | – | 7 | 1,05 | 1 |
| | 17100RS05 | ● | 100 | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | – | – | 5 | 1,58 | 3 |
| | 17100RS08 | ● | 100 | 70 | 50 | 32 | 14,4 | 8,0 | 32 | 46 | – | – | 8 | 1,57 | 3 |
| | 17125RS06 | ● | 125 | 80 | 63 | 40 | 16,4 | 9,0 | 29 | 52 | 29 | – | 6 | 3,04 | 1 |
| | 17125RS09 | ● | 125 | 80 | 63 | 40 | 16,4 | 9,0 | 29 | 52 | 29 | – | 9 | 3,07 | 1 |
| | 17125RS11 | ● | 125 | 80 | 63 | 40 | 16,4 | 9,0 | 29 | 52 | 29 | – | 11 | 3,02 | 1 |
| | 17160RS08 | ● | 160 | 130 | 63 | 40 | 16,4 | 9,0 | 29 | 90 | – | – | 8 | 5,24 | 5 |
| | 17160RS10 | ● | 160 | 130 | 63 | 40 | 16,4 | 9,0 | 29 | 90 | – | – | 10 | 5,31 | 5 |
| | 17160RS12 | ● | 160 | 130 | 63 | 40 | 16,4 | 9,0 | 29 | 90 | – | – | 12 | 5,26 | 5 |
| Inch | WEZ 17080R04 | ❍ | *80 | 55 | 50 | 25,4 | 9,5 | 6,0 | 25 | 20 | 14 | – | 4 | 1,10 | 1 |
| | 17080R07 | ❍ | *80 | 55 | 50 | 25,4 | 9,5 | 6,0 | 25 | 20 | 14 | – | 7 | 1,06 | 1 |
| | 17100R05 | ❍ | *100 | 70 | 63 | 31,75 | 12,7 | 8,0 | 32 | 46 | 27 | 18 | 5 | 2,08 | 2 |
| | 17100R08 | ❍ | *100 | 70 | 63 | 31,75 | 12,7 | 8,0 | 32 | 46 | 27 | 18 | 8 | 2,07 | 2 |
| | 17125R06 | ❍ | 125 | 80 | 63 | 38,1 | 15,9 | 10,0 | 35,5 | 55 | 30 | – | 6 | 3,09 | 1 |
| | 17125R09 | ❍ | 125 | 80 | 63 | 38,1 | 15,9 | 10,0 | 35,5 | 55 | 30 | – | 9 | 3,11 | 1 |
| | 17125R11 | ❍ | 125 | 80 | 63 | 38,1 | 15,9 | 10,0 | 35,5 | 55 | 30 | – | 11 | 3,06 | 1 |
| | 17160R08 | ❍ | 160 | 100 | 63 | 50,8 | 19,1 | 11,0 | 38 | 72 | – | – | 8 | 5,04 | 4 |
| | 17160R10 | ❍ | 160 | 100 | 63 | 50,8 | 19,1 | 11,0 | 38 | 72 | – | – | 10 | 5,09 | 4 |
| | 17160R12 | ❍ | 160 | 100 | 63 | 50,8 | 19,1 | 11,0 | 38 | 72 | – | – | 12 | 5,04 | 4 |

Inserts are sold separately. Check the arbor mounting size (DCB) when selecting the cutter.

* For securing the Ø 80 mm and Ø 100 mm cutter to the arbors, use JIS B1176 hexagonal bolt. (Ø 80 mm: M12x30 to 35 mm, Ø 100 mm: M16x40x45 mm)

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench | Handle Grip | Wrench Bit |
|---|---|---|---|---|---|
| | | N·m | | | |
| WEZ 17040RS03<br>17040RS04<br>17050RS03<br>17050RS05<br>17063RS04<br>17063RS06<br>17080R(S)04<br>17080R(S)07<br>17100R(S)05<br>17100R(S)08<br>17125R(S)06<br>17125R(S)09<br>17125R(S)11 | BFTX0409IP | 3,0 | – | HPS1015 | TRB15IP |
| 17160R(S)08<br>17160R(S)10<br>17160R(S)12 | | | TRDR15IP | – | – |

## Identification Details

| WEZ | 17 | 100 | R | S | 05 |
|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Feed Direction | Metric | Number of Teeth |

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT170524PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Corner radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Corner radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Corner radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

## Recommended Cutting Conditions

→ G46



● = Euro stock
❍ = Japan stock
❑ = On request
– = Not available
N·m Recommended Tightening Torque (N·m)

## Inserts

Precautions for Mounting → G47

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 170502PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170508PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170512PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,2 | 1 |
| 170516PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,6 | 1 |
| AOMT 170502PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170505PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 170508PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170510PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 170512PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 170516PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 170520PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 170524PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 170530PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 1 |
| 170532PEER-G | ● | | ❑ | ❑ | | ❑ | ● | ● | ● | – | – | | 3,2 | 1 |
| 170540PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 4,0 | 1 |
| 170550PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 5,0 | 2 |
| 170564PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 6,4 | 2 |
| AOMT 170504PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 170508PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 170512PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 170516PEER-H | ● | | ❑ | ● | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 170502PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170516PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 170520PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 170524PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 170530PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 1 |
| 170532PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 1 |
| 170540PEER-F | ● | | – | | | – | | – | | – | – | – | 4,0 | 1 |
| 170550PEER-F | ● | | – | | | – | | – | | – | – | – | 5,0 | 2 |
| 170564PEER-F | ● | | – | | | – | | – | | – | – | – | 6,4 | 2 |
| AOET 170502PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 170504PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 170505PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 170508PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 170510PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 170512PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 170516PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 170520PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 170524PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 170530PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 1 |
| 170532PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 1 |
| 170540PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 4,0 | 1 |
| 170550PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 5,0 | 2 |
| 170564PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 6,4 | 2 |

Fig. 1







Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals



## Features

- **High-efficiency Shoulder Milling**

  Inserts for "WaveMill" WEZ type are arranged in multiple stages forming a long cutting edge, to enable high-efficiency shoulder milling of deep steps.

- **Very Low Vibration Tendency**

  Sharp milling inserts and irregular pitched body help to reduce chatter marks caused by vibration.


- **Support for all Types of Work Materials**

  A lineup of grades specific to each work materials, as well as the general-purpose ACU2500 grade, which is applicable to steel, stainless steel and cast iron.


## Body Features

- **Improved Flute Shape**

Optimised, upward tapering chip pocket geometry for improved chip removal and increased rigidity of the cutter body.



- **Irregular Pitched Body**





Irregular pitched body reduces vibration tendency


## Cutting Performance

- **Significantly less vibrations are a result of the combination of sharp inserts and irregular tooth pitch.**

Capable of stable machining even with BT40 spindle machines

Vertical Machining Centre BT40








| | |
|---|---|
| Machine: | Vertical Machining Centre BT40, |
| Work Material: | C55, overhang amount 60 mm |
| Tool: | WEZR 11032E3632Z03 (Ø 32, 3 teeth, 4-stage) |
| Insert: | AOET11T308PEER-G (ACU2500) |
| Cutting Conditions: | $v_c$ = 150 m/min, $f_z$ = 0,1 mm/t, $a_p$ = 30 mm, dry |

Capable of stable machining even with a long overhang

Vertical Machining Centre BT50





| | |
|---|---|
| Machine: | Vertical Machining Centre BT50, |
| Work Material: | 42CrMo4 |
| Tool: | WEZR 17063RS5727Z04 (Ø 63, 4 teeth, 4-stage) |
| Insert: | AOET170508PEER-G (ACU2500) |
| Cutting Conditions: | $v_c$ = 150 m/min, $f_z$ = 0,15 mm/t, $a_p$ = 50 mm, dry |


## Cutting Performance

- Optimised cutting edge shape and high-precision molding technology result in excellent shoulder accuracy.












| | |
|---|---|
| Machine: | Vertical Machining Centre BT50, |
| Work Material: | C55, overhang amount 60 mm |
| Tool: | WEZR 11032E3632Z02 (Ø 32, 2 teeth, 4-stage) |
| Insert: | AOET11T308PEER-G (ACU2500) |
| Cutting Conditions: | $v_c$ = 160 m/min, $f_z$ = 0,15 mm/t, $a_p$ = 30 mm, $a_p$ = 30 mm, dry |

## Application Range

- Steel, stainless steel, cast iron
- Aluminum alloys, titanium alloys




**Note:**
The depth of cut figures above are guidelines for use with BT50 machine tools. Use a depth of cut of approximately 50% if using BT40.
For a tool overhang of L/D = 3 or L/D = 4, use a depth of cut of approximately 50% or 25%, respectively.
There may be cases where machining cannot be performed at the depth of cut figures above, depending on the machine rigidity and work rigidity.
Cutting speed and feed rate data you will find on the next pages,

# WEZR 11000 RS

New


Repeater

| Rake Angle | Radial | -11° – -9° |
|---|---|---|
| | Axial | 14° – 15° |

44–53 mm 90°



Fig. 1




## Body (Shell Type)

Dimensions (mm)

| | Cat. No. | Stock | DC | APMX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | Total No. of Teeth | Steps | Effective No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | WEZR 11040RS4416Z04 | ❍ | 40 | 44 | 37 | 60 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 20 | 5 | 4 | 0,27 | 1 |
| | 11050RS5322Z04 | ❍ | 50 | 53 | 47 | 70 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 24 | 6 | 4 | 0,57 | 1 |

Take note of the cutter mounting size (DCB) when selecting a cutter. Inserts are sold seperately.

## Spare Parts

| Applicable Cutters | Insert Screw | N·m | Wrench | Bolt |
|---|---|---|---|---|
| WEZR 11040RS4416Z04 | BFTX0306IP | 1,5 | TRDR08IP | BX0850 |
| 11050RS5322Z04 | | | | BX1060 |

## Identification Details

| WEZR | 11 | 040 | R | S | 44 | 16 | Z04 |
|---|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Feed Direction | Metric | Max. Depth of Cut | Mounting Hole Diameter | Number of Teeth |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Chipbreaker | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grades |
|---|---|---|---|---|---|---|
| P | Carbon Steel | ≤ 280HB | G | 100–**150**–200 | 0,08–**0,12**–0,20 | ACU2500 XCU2500 ACP2000 ACP3000 |
| | | > 280HB | G | 80–**100**–120 | 0,08–**0,12**–0,20 | |
| | Alloy Steel | ≤ 280HB | G | 100–**150**–80 | 0,08–**0,12**–0,20 | |
| M | Stainless Steel | ≤ 280HB | G | 80–**120**–160 | 0,08–**0,12**–0,20 | ACU2500 ACM200 ACM300 |
| K | Cast Iron Ductile Cast Iron | – | G | 100–**150**–200 | 0,08–**0,12**–0,20 | ACU2500 XCK2000 ACK2000 ACK3000 |
| S | Exotic Alloy | – | G | 40–**50**–60 | 0,08–**0,12**–0,20 | ACU2500 ACM200 ACM300 |
| N | Aluminum Alloy | Si ≤ 12,6% | S | 300–**500**–800 | 0,05–**0,10**–0,15 | DL2000 H20 |
| | | Si >12,6% | S | 100–**200**–250 | 0,05–**0,10**–0,15 | |

Min. - **Optimum** - Max.

Note:
The cutting conditions above are a guide. Actual conditions will need to be adjusted according to machine rigidity, work clamp rigidity, depth of cut and other factors.
There may be cases where machining cannot be performed under recommended cutting conditions, depending on the machine rigidity and work rigidity.

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT11T324PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
❍ = Japan stock
❑ = On request
– = Not available
N·m Recommended Tightening Torque (N·m)

## Inserts

Precautions for Mounting → G47

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 11T302PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ● | 0,2 | 1 |
| 11T304PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 11T305PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 11T308PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 11T310PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 11T312PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 11T316PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 11T320PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 11T324PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 11T330PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 2 |
| 11T332PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 3,2 | 2 |
| AOMT 11T304PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 11T308PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 11T312PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 11T316PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 11T302PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T316PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 11T320PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 11T324PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 11T330PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 2 |
| 11T332PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 2 |
| AOET 11T302PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 11T304PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 11T305PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 11T308PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 11T310PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 11T312PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 11T316PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 11T320PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 11T324PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 11T330PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 2 |
| 11T332PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

# WEZR 17000 RS

New


Repeater

| Rake Angle | Radial | -8° – -6 |
|---|---|---|
| | Axial | 7° – 15° |

29–57 mm 90°



Fig. 1




## Body (Shell Type)

Dimensions (mm)

| | Cat. No. | Stock | DC | APMX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | Total No. of Teeth | Steps | Effective No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | WEZR 17050RS2922Z04 | ❍ | 40 | 29 | 47 | 50 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 8 | 2 | 4 | 0,35 | 1 |
| | 17050RS5722Z02 | ❍ | 50 | 57 | 47 | 80 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 8 | 4 | 2 | 0,70 | 1 |
| | 17050RS5722Z03 | ❍ | 50 | 57 | 47 | 80 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 12 | 4 | 3 | 0,59 | 1 |
| | 17063RS2927Z05 | ❍ | 63 | 29 | 60 | 55 | 27 | 12,4 | 7 | 22 | 20 | 14 | 10 | 2 | 5 | 0,74 | 1 |
| | 17063RS5727Z03 | ❍ | 63 | 57 | 60 | 80 | 27 | 12,4 | 7 | 22 | 20 | 14 | 12 | 4 | 3 | 1,11 | 1 |
| | 17063RS5727Z04 | ❍ | 63 | 57 | 60 | 80 | 27 | 12,4 | 7 | 22 | 20 | 14 | 16 | 4 | 4 | 1,05 | 1 |
| | 17080RS5627Z05 | ❍ | 80 | 56 | 70 | 80 | 27 | 12,4 | 7 | 22 | 20 | 14 | 20 | 4 | 5 | 1,85 | 1 |
| | 17080RS5632Z05 | ❍ | 80 | 56 | 70 | 80 | 32 | 14,4 | 8 | 26 | 25 | 18 | 20 | 4 | 5 | 1,76 | 1 |

Take note of the cutter mounting size (DCB) when selecting a cutter. Inserts are sold seperately.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench | Handle Grip | Wrench Bit | Bolt |
|---|---|---|---|---|---|---|
| WEZR 17050RS2922Z04 | BFTX0409IP | 3,0 | – | HPS1015 | TRB15IP | BX1045 |
| 17050RS5722Z02 | | | | | | BX1070 |
| 17050RS5722Z03 | | | | | | |
| 17063RS2927Z05 | | | | | | BX1240 |
| 17063RS5727Z03 | | | | | | BX1265 |
| 17063RS5727Z04 | | | | | | |
| 17080RS5627Z05 | | | TRDR15IP | – | – | BX1265 |
| 17080RS5632Z05 | | | | | | BX1660 |

## Identification Details

**WEZR 17 050 R S 29 22 Z04**

| Cutter Series | Insert Size | Cutter Diameter | Feed Direction | Metric | Max. Depth of Cut | Mounting Hole Diameter | Number of Teeth |
|---|---|---|---|---|---|---|---|

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Chipbreaker | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grades |
|---|---|---|---|---|---|---|
| P | Carbon Steel | ≤ 280HB | G | 100–**150**–200 | 0,10–**0,20**–0,30 | ACU2500 XCU2500 ACP2000 ACP3000 |
| | | > 280HB | G | 80–**100**–120 | 0,10–**0,20**–0,30 | |
| | Alloy Steel | ≤ 280HB | G | 100–**150**–80 | 0,10–**0,20**–0,30 | |
| M | Stainless Steel | ≤ 280HB | G | 80–**120**–160 | 0,10–**0,20**–0,30 | ACU2500 ACM200 ACM300 |
| K | Cast Iron Ductile Cast Iron | – | G | 100–**150**–200 | 0,10–**0,20**–0,30 | ACU2500 XCK2000 ACK2000 ACK3000 |
| S | Exotic Alloy | – | G | 40–**50**–60 | 0,10–**0,20**–0,30 | ACU2500 ACM200 ACM300 |
| N | Aluminum Alloy | Si ≤ 12,6% | S | 300–**500**–800 | 0,05–**0,10**–0,15 | DL2000 H20 |
| | | Si >12,6% | S | 100–**200**–250 | 0,05–**0,10**–0,15 | |

Min. - **Optimum** - Max.

Note:
The cutting conditions above are a guide. Actual conditions will need to be adjusted according to machine rigidity, work clamp rigidity, depth of cut and other factors.
There may be cases where machining cannot be performed under recommended cutting conditions, depending on the machine rigidity and work rigidity.

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT170524PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Corner radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Corner radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Corner radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm
C: Chamfer
R: Radius





● = Euro stock
❍ = Japan stock
❑ = On request
– = Not available
(N·m) Recommended Tightening Torque (N·m)

## Inserts

Precautions for Mounting → G47

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 170502PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170508PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170512PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,2 | 1 |
| 170516PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,6 | 1 |
| AOMT 170502PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170505PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 170508PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170510PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 170512PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 170516PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 170520PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 170524PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 170530PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 1 |
| 170532PEER-G | ● | | ❑ | ❑ | | ❑ | ● | ● | ● | – | – | | 3,2 | 1 |
| 170540PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 4,0 | 1 |
| 170550PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 5,0 | 2 |
| 170564PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 6,4 | 2 |
| AOMT 170504PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 170508PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 170512PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 170516PEER-H | ● | | ❑ | ● | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 170502PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170516PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 170520PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 170524PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 170530PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 1 |
| 170532PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 1 |
| 170540PEER-F | ● | | – | | | – | | – | | – | – | – | 4,0 | 1 |
| 170550PEER-F | ● | | – | | | – | | – | | – | – | – | 5,0 | 2 |
| 170564PEER-F | ● | | – | | | – | | – | | – | – | – | 6,4 | 2 |
| AOET 170502PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 170504PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 170505PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 170508PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 170510PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 170512PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 170516PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 170520PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 170524PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 170530PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 1 |
| 170532PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 1 |
| 170540PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 4,0 | 1 |
| 170550PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 5,0 | 2 |
| 170564PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 6,4 | 2 |

Fig. 1








Fig. 2





L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

# "Wave Mill" Series
# WEX (-F) Type








## Body (Shell Type "F")


| Cat. No. | Dimensions (mm) | | | | | | | | No.of Teeth | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|
| | Stock | DC | DCB | D2 | KWW | KDP | LF | CBDP | | |
| WEX 1032 F | ▲ | 32 | 16 | 9 | 8,4 | 5,6 | 40 | 18 | 8 | 1 |
| 1040 F | ▲ | 40 | 16 | 11 | 8,4 | 5,6 | 40 | 18 | 10 | 1 |
| 1050 F | ▲ | 50 | 22 | 11 | 10,4 | 6,3 | 40 | 20 | 12 | 1 |
| 1063 F | ▲ | 63 | 22 | 11 | 10,4 | 6,3 | 40 | 20 | 14 | 1 |
| WEX 2040 F | ▲ | 40 | 16 | 9 | 8,4 | 5,6 | 40 | 18 | 6 | 2 |
| 2050 F | ▲ | 50 | 22 | 11 | 10,4 | 6,3 | 40 | 20 | 7 | 2 |
| 2063 F | ▲ | 63 | 22 | 11 | 10,4 | 6,3 | 40 | 20 | 8 | 2 |
| 2080 F | ▲ | 80 | 27 | 13,5 | 12,4 | 7,0 | 50 | 25 | 10 | 2 |
| WEX 2100 F | ❑ | 100 | 32 | 32 | 14,4 | 8,5 | 50 | 26 | 12 | 2 |
| WEX 3040 F | ▲ | 40 | 16 | 9 | 8,4 | 5,6 | 40 | 18 | 4 | 3 |
| 3050 F | ▲ | 50 | 22 | 11 | 10,4 | 6,3 | 40 | 20 | 5 | 3 |
| 3063 F | ▲ | 63 | 22 | 11 | 10,4 | 6,3 | 40 | 20 | 6 | 3 |
| 3080 F | ▲ | 80 | 27 | 13,5 | 12,4 | 7,0 | 50 | 25 | 7 | 3 |
| WEX 3100 F | ▲ | 100 | 32 | 32 | 14,4 | 8,5 | 50 | 26 | 8 | 3 |

## Inserts for WEX1000 / 2000 Type




| Application | Coated Carbide | | | | | | | Carbide | DLC | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M S | | K N | N | |
| General Purpose | | P M | P M | K | | M S | M S | | N | |
| Roughing | | P M | P M | | K | | M S | | | |
| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
| AXMT 060204 PDER-L | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | | | 0,4 |
| 060208 PDER-L | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | | | 0,8 |
| 060212 PDER-L | | ▲ | | | ❍ | ▲ | ▲ | | | 1,2 |
| AXMT 060204 PDER-G | ▲ | ▲ | ▲ | ❍ | ▲ | ▲ | ▲ | | | 0,4 |
| 060208 PDER-G | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | | | 0,8 |
| 060212 PDER-G | ❍ | ▲ | ▲ | | ▲ | ▲ | ▲ | | | 1,2 |
| AXMT 060204 PDER-H | ❍ | ▲ | ▲ | | ▲ | ▲ | ▲ | | | 0,4 |
| 060208 PDER-H | | ▲ | ▲ | | ▲ | ▲ | ▲ | | | 0,8 |
| 060212 PDER-H | ❍ | ▲ | ▲ | | ▲ | ▲ | ▲ | | | 1,2 |
| AXMT 123504 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 123508 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 123512 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 123504 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 123508 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 123512 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 123504 PEER-E | | | | | | ▲ | ▲ | – | – | 0,4 |
| 123508 PEER-E | | | | | | ▲ | ▲ | – | – | 0,8 |
| 123512 PEER-E | | | | | | ▲ | ▲ | – | – | 1,2 |
| AXMT 123508 PEER-EH | | | | | | ▲ | ▲ | – | – | 0,8 |
| AXMT 060202 PDFR-S | – | – | – | – | – | – | – | ❍ | ❍ | 0,2 |
| AXET 123502 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,2 |
| 123504 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,4 |
| 123508 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,8 |

## Inserts for WEX3000 Type





| Application | Coated Carbide | | | | | | | Carbide | DLC | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M S | | K N | N | |
| General Purpose | | P M | P M | K | | M S | M S | | N | |
| Roughing | | P M | P M | | K | | M S | | | |
| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
| AXMT 170508 PEER-L | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| AXMT 170504 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 170508 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 170512 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| 170516 PEER-G | ❍ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,6 |
| 170520 PEER-G* | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 2,0 |
| 170530 PEER-G* | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 3,0 |
| AXMT 170508 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 170512 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 170504 PEER-E | | | | | | ▲ | ▲ | – | – | 0,4 |
| 170508 PEER-E | | | | | | ▲ | ▲ | – | – | 0,8 |
| 170512 PEER-E | | | | | | ▲ | ▲ | – | – | 1,2 |
| 170516 PEER-E | | | | | | ▲ | ▲ | – | – | 1,6 |
| 170520 PEER-E* | | | | | | ▲ | ▲ | – | – | 2,0 |
| 170530 PEER-E* | | | | | | ▲ | ▲ | – | – | 3,0 |
| AXMT 170508 PEER-EH | | | ▲ | | | ▲ | ▲ | – | – | 0,8 |
| AXET 170502 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,2 |
| 170504 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,4 |
| 170508 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,8 |

∗ Cutter body modification is required.

– Unable to produce

L – Low cutting force
G – General type
H – Strong cutting edge
E – For stainless steel
EH– Strong edge for stainless steel
S – For aluminium

## Spare Parts

| Screw | Wrench | | Applicable Endmill |
|---|---|---|---|
|  |  | N·m | |
| BFTX 01804 IP | TRX 06 IP | 0,5 | WEX 1000 F |
| BFTX 0306 IP | TRDR 08 IP | 2,0 | WEX 2000 F |
| BFTX 0409 IP | TRDR 15 IP | 3,0 | WEX 3000 F |

## Identification Details

| WEX | 2 | 016 | F |
|---|---|---|---|
| Cutter Series | 2000 Series | Cutter Diameter | Shell Type |




● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item


→ H56-60

N·m Recommended Tightening Torque (N·m)

18–36 mm 90°




27–53 mm 90°





## Body (Shell Type "F")

| Cat. No. | Stock | Depth of cut ($a_p$) | Dimensions (mm) øD | ød1 | ød2 | a | b | l1 | l | l | No. of teeth | No. of rows | Effective teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| WRX2040RH18F16 | ❑ | 18 | 40 | 16 | 9 | 8,4 | 5,6 | 50 | 39 | 18 | 10 | 2 | 5 |
| WRX2040RH36F16 | ● | 36 | 40 | 16 | 9 | 8,4 | 5,6 | 55 | 44 | 18 | 16 | 4 | 4 |
| WRX2050RH18F22 | ❑ | 18 | 50 | 22 | 11 | 10,4 | 6,3 | 50 | 36 | 20 | 10 | 2 | 5 |
| WRX2050RH36F22 | ● | 36 | 50 | 22 | 11 | 10,4 | 6,3 | 55 | 41,5 | 20 | 16 | 4 | 4 |

## Body (Shell Type "F")

| Cat. No. | Stock | Depth of Cut ($a_p$) | Dimensions (mm) øD | ød1 | ød2 | a | b | l1 | l | l | No. of teeth | No. of rows | Effective teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| WRX3050RH27F22 | ❑ | 27 | 50 | 22 | 11 | 10 | 6,3 | 50 | 36 | 20 | 8 | 2 | 4 |
| WRX3050RH53F22 | ● | 53 | 50 | 22 | 11 | 10 | 6,3 | 70 | 56 | 20 | 12 | 4 | 3 |
| WRX3063RH27F27 | ❑ | 27 | 63 | 27 | 13,5 | 12 | 7 | 70 | 34 | 2 | 10 | 2 | 5 |
| WRX3063RH53F27 | ● | 53 | 63 | 27 | 13,5 | 12 | 7 | 70 | 54 | 2 | 16 | 4 | 4 |
| WRX3080RH27F32 | ❑ | 27 | 80 | 32 | 17 | 14 | 8 | 50 | 30 | 2 | 12 | 2 | 6 |
| WRX3080RH53F32 | ● | 53 | 80 | 32 | 17 | 14 | 8 | 85 | 63 | 2 | 20 | 4 | 5 |
| WRX3100RH27F40 | ❑ | 27 | 100 | 40 | 21 | 16 | 9,5 | 85 | 40 | 30 | 14 | 2 | 7 |
| WRX3100RH53F40 | ● | 53 | 100 | 40 | 21 | 16 | 9,5 | 85 | 59 | 30 | 24 | 4 | 6 |

## Inserts (Same as for Wavemill WEX 2000 Type)





| Application | Coated Carbide | | | | | | | Carbide | DLC |
|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M S | | K N | N |
| General Purpose | | P | | K | | M S | M S | | N |
| Roughing | | P | P | | K | | M S | | |

| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
|---|---|---|---|---|---|---|---|---|---|---|
| AXMT 123504 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 123508 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 123512 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 123504 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 123508 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 123512 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 123504 PEER-E | | | | | | ▲ | ▲ | – | – | 0,4 |
| 123508 PEER-E | | | | | | ▲ | ▲ | – | – | 0,8 |
| 123512 PEER-E | | | | | | ▲ | ▲ | – | – | 1,2 |
| AXMT 123508 PEER-EH | | | | | | ▲ | ▲ | – | – | 0,8 |
| AXET 123502 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,2 |
| 123504 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,4 |
| 123508 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,8 |

– Unable to produce
L – Low cutting force
G – General type
H – Strong cutting edge
E – For stainless steel
EH– Strong edge for stainless steel
S – For aluminium

## Inserts (Same as for Wavemill WEX 3000 Type)




| Application | Coated Carbide | | | | | | | Carbide | DLC |
|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M S | | K N | N |
| General Purpose | | P M | P M | K | | M S | M S | | N |
| Roughing | | P M | P M | | K | | M S | | |

| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
|---|---|---|---|---|---|---|---|---|---|---|
| AXMT 170508 PEER-L | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| AXMT 170504 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 170508 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 170512 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| 170516 PEER-G | ❍ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,6 |
| 170520 PEER-G* | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 2,0 |
| 170530 PEER-G* | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 3,0 |
| AXMT 170508 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 170512 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 170504 PEER-E | | | | | | ▲ | ▲ | – | – | 0,4 |
| 170508 PEER-E | | | | | | ▲ | ▲ | – | – | 0,8 |
| 170512 PEER-E | | | | | | ▲ | ▲ | – | – | 1,2 |
| 170516 PEER-E | | | | | | ▲ | ▲ | – | – | 1,6 |
| 170520 PEER-E* | | | | | | ▲ | ▲ | – | – | 2,0 |
| 170530 PEER-E* | | | | | | ▲ | ▲ | – | – | 3,0 |
| AXMT 170508 PEER-EH | | | ▲ | | | ▲ | ▲ | – | – | 0,8 |
| AXET 170502 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,2 |
| 170504 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,4 |
| 170508 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,8 |

* Cutter body modification is required.

## Spare Parts

| Screw | Wrench | N·m | Applicable Endmill |
|---|---|---|---|
|  |  | | |
| BFTX 0306 IP | TRDR 08 IP | 2,0 | WRX 2_ _ _ _ RH_ _F_ _ |
| BFTX 0409 IP | TRDR 15 IP | 3,0 | WRX 3_ _ _ _ RH_ _F_ _ |

## Identification Details

WRX 20 (Insert Size) 40 (Tool øD) R (Cutting Direction) H (Inner coolant) 18 (Cutting Edge Length) F (Arbor Type) 16 (Arbor Diameter)

**E** - Straight Shank
**W** - Weldon Shank
**F** - Shell Type

→ H64-67

# MTIX 16000 Type

New



## General Features


### Stable and Reliabel Tool Life in Titanium Roughing

With combination of high toughness grade ACM300 and optimized cutting edge shape, stable and reliable tool life are achieved in roughing application of Titanium.

### Suitable for Titanium Structure Parts for Aircraft

MTIX cutter with wide range of insert nose-radius and large ramping angle availiability is suitable for variable application of titanium structure parts for aircraft.

### Large Application Range



| ISO | Grade | Coating Thickness (µm) | Features |
|---|---|---|---|
| S | ACM300 | 3 | Realises superb stability in machining of Titanium, due to a high-strength carbide substrate and highly chipping-resistance coating. |


## Recommended Cutting Conditions

Min. - **Optimum** - Max.


| ISO | Material | Cutting Speed (m/min) | Feed Rate (mm/t) | $a_p$ (mm) | Grade |
|---|---|---|---|---|---|
| S | Titanium | 30–**60**–90 | 0,05–**0,10**–0,15 | <13 | ACM300 |

## Ramping / Helical Milling Upper Limits


Ramping




Flat Bottom Machining




Machining with Prepared Hole




| Tools | | Ramping |
|---|---|---|
| DC Ø (mm) | Nose Radius | Max. RMPX (°) |
| Ø 32 | RE ≥ 5,0 | 8,4 |
| | RE ≤ 4,0 | 12,2 |
| Ø 50 | RE ≥ 5,0 | 3,6 |
| | RE ≤ 4,0 | 5,6 |
| Ø 63 | RE ≥ 5,0 | 2,5 |
| | RE ≤ 4,0 | 3,9 |

| Tools | | Flat Bottom Machining | | | | Machining with Prepared Hole | |
|---|---|---|---|---|---|---|---|
| DC Ø (mm) | Nose Radius | Max. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) |
| Ø 32 | 4,0 | 55,3 | 13,0 | 55,2 | 13,0 | 45,9 | 3,0 |
| | 0,8 | 61,3 | 13,0 | 56,3 | 13,0 | 45,9 | 2,9 |
| Ø 50 | 4,0 | 91,6 | 11,2 | 91,6 | 11,2 | 81,9 | 2,8 |
| | 0,8 | 97,3 | 13,0 | 92,2 | 11,0 | 81,9 | 2,7 |
| Ø 63 | 4,0 | 117,6 | 10,1 | 117,6 | 10,1 | 107,9 | 2,7 |
| | 0,8 | 123,3 | 11,7 | 118,2 | 9,9 | 107,9 | 2,6 |






● = Euro stock

Recommended Tightening Torque (N·m)

| Rake Angle | | |
|---|---|---|
| | Radial | -9° – -6° |
| | Axial | 8° – 14° |

13 mm 90°






## Body - MTIX (Shell Type)

Dimensions (mm)

| Insert Radius RE | Cat. No. | Stock | DC | DCB | LF | D2 | KWW | KDP | CBDP | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|
| ≤ 4,0 | MTIX 16050RS05 | ● | 50 | 22 | 50 | 11 | 10,4 | 6,3 | 20 | 5 | 0,33 |
| | 16063RS06 | ● | 63 | 22 | 50 | 11 | 10,4 | 6,3 | 20 | 6 | 0,34 |
| ≥ 5,0 | MTIX16050RS05-5,0 | ● | 50 | 22 | 50 | 11 | 10,4 | 6,3 | 20 | 5 | 0,62 |
| | 16063RS06-5,0 | ● | 63 | 22 | 50 | 11 | 10,4 | 6,3 | 20 | 6 | 0,63 |

→ H69

Inserts are sold separately.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench | Handle Grip | Wrench Bit |
|---|---|---|---|---|---|
| |  |  |  |  |  |
| MTIX 16050RS05(-5,0) | BFTX0409IP | 3,0 | – | HPS1015 | TPB15IP |
| 16063RS06(-5,0) | | | | | |

## Identification Details

| MTIX | 16 | 050 | R | S | 05 |
|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Feed Direction | Metric | Number of Teeth |

## Inserts

| Application | Coated Carbide |
|---|---|
| High Speed / Light Cut | |
| General Purpose | S |
| Roughing | S |

Dimensions (mm)

| Cat. No. | ACM300 | RE (mm) | Fig. |
|---|---|---|---|
| XOMT 160508PEER-E | ● | 0,8 | 1 |
| 160512PEER-E | ● | 1,2 | 1 |
| 160516PEER-E | ● | 1,6 | 1 |
| 160520PEER-E | ● | 2,0 | 1 |
| 160530PEER-E | ● | 3,0 | 1 |
| 160540PEER-E | ● | 4,0 | 1 |
| 160550PEER-E | ● | 5,0 | 2 |
| 160560PEER-E | ● | 6,0 | 2 |
| 160564PEER-E | ● | 6,35 | 2 |

Fig. 1







Fig. 2




Inserts with nose radius of RE ≥ 5,0 are for use with bodies that have a "-5,0" part number suffix

New

## Precautions for Mounting








(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.

| Cutter Body | MTIX16 ____ | MTIX16 ____-5,0 |
|---|---|---|
| Insert Radius<br>RE ≤ 4,0 mm | **OK**  |  Not recommended. The insert has no support from the cutter body. |
| Insert Radius<br>RE ≥ 4,0 mm | OK with modification  1,5 mm less height | **OK**  |
| Modification method<br>① Grind 1,5 mm from top<br>② Add chamfer 4,5 mm |  | |

## Cutting Performance

Ti 6Al4V, Machine: DMU80P (HSK100)

Cutter: Dia. 50 mm, 5 teeth, Insert: 16-18 size, R 4,0

$v_c$ = 60 m/min
$f_z$ = 0,12 mm/teeth
$a_p$ = 10 mm
$a_e$ = 21 mm
HP coolant
70 bar





**MTIX** Competitor

$v_c$ = 50 m/min
$f_z$ = 0,12 mm/teeth
$a_p$ = 4 mm
$a_e$ = 50 mm
HP coolant
70 bar

3°





**MTIX** Competitor

$v_c$ = 50 m/min
$f_z$ = 0,12 mm/teeth
$a_p$ = 4 mm
$a_e$ = 50 mm
HP coolant
70 bar

5,5°





**MTIX**

Impossible


Competitor

## Application Example

Structural Parts, Ti 6Al4V, Countering / Ramping

ACM300 achieved twice longer tool life against competitor's grade.






Cutter: MTIX 16050RS05 (Ø 50, No. of teeth:5)
Insert: XOMT 160540 PEER-E (ACM300)

Cutting Data: $v_c$ = 50 M/min, $a_p$ = 4 mm, $f_z$ = 0,12mm/t, $a_e$ = 10 mm, wet


New



## General Features

- High productivity thanks to an ultra-high metal removal rate as well as high economic efficiency, due to the stable six-edged insert.
- The arc-shaped cutting edge reduces the cutting force to a minimum. High-efficiency machining at maximum feed rate per tooth of 3,5 mm/t is possible.

## Application Range






- Cutting depths up to 3 mm can be achieved. Feed rate per tooth up to 3,5 mm/t.
- Increases productivity.

## Product Range


| Type | Cat. No. | Diameter range (mm) / No of teeth | | | | | | | | | | | | Shape |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | Ø35 | Ø40 | Ø42 | Ø50 | Ø52 | Ø63 | Ø66 | Ø80 | Ø85 | Ø100 | Ø125 | Ø160 | |
| Shell | DMSW 08000RS | | | | 4<br>5 | 4<br>5 | 4<br>5*<br>6* | 5<br>6 | 6<br>8 | 6<br>8 | 6 | 8 | 10 |  |
| | DMSW 08000R (Inch) | | | | 4<br>5 | | 4<br>5<br>6 | | 6<br>8 | | 6 | 8 | 10 | |
| Shank | DMSW 08000E | 2 | 3 | | 3 | | 4 | | | | | → H8 | |  |
| | DMSW 08000EL | 2 | 3 | | 3 | | 4 | | | | | | | |
| Modular | DMSW 08000M | 2 | 3 | 3 | | | | | | | | → H9 | |  |

* Different shank diameters in stock

## Chipbreaker

| Work Material | P Steel M Stainless steel K Cast iron | P Steel M Stainless steel K Cast iron |
|---|---|---|
| Applications | Main chipbreaker general-purpose to interrupted milling | Roughing, heavy interrupted cutting and hardened steel milling |
| | General purpose | High strength |
| Chip breaker | **G** type | **H** type |
| |  |  |
| Cutting edge cross section | 0,12 mm<br> | 0,22 mm<br> |


## Chipbreaker Selection Guide




New

## Features

- A small chip cross-section due to a small cutting angle enables high feed rates per tooth.








- Economical double-sided insert with 6-corner specification. Reassuring thick at 7 mm.

**WNMU** type





Conventional tool




- Even at high feedrates of 2,0 mm/t or more, a reasonable surface finish can be attained.




**DMSW** type




**Ra = 3,3 µm, Rz = 14,1 µm**

Competitor's product A (high-feed tool)






Ra = 11,2 µm, Rz = 51,0 µm

| | | | |
|---|---|---|---|
| Machine: | Vertical machining centre BT50, Work material: C50 | Insert: | WNMU 0807ZNER-G (ACU2500) |
| Tool: | DMSW 08063RS04 | Cutting data: | $v_c$ = 150 m/min, $f_z$ = 2,5 mm/t, $a_p$ = 0,5 mm, $a_e$ = 40 mm, dry |


- Small cutting angle (15°) controls cutting force toward the back force direction.
  Suppresses chatter in long tool overhang machining, increasing efficiency.

**DMSW** type






(Reference) Shoulder milling tool




**DMSW** type




Competitor's product B (high-feed tool)




| | | | |
|---|---|---|---|
| Machine: | Vertical machining centre BT50, Work material: C50 | | |
| Tool: | DMSW 08050RS04 | | |
| Insert: | WNMU 0807ZNER-G (ACU2500) | | |
| Cutting data: | $v_c$ = 160 m/min, $f_z$ = 0,65 mm/t, $a_p$ = 0,80 mm, $a_e$ = 45 mm, dry | | |

## Precautions for Corner Finishing

Actual machined corners will have uncut and overcut portions due to the shape of the inserts.

Fig. 1






Fig. 2





| Programmed corner radius | Uncut portion | Overcut portion | Fig. |
|---|---|---|---|
| 2,0 | 1,22 | 0 | 1 |
| 2,5 | 1,08 | 0 | 1 |
| 3,0 | 0,95 | 0 | 1 |
| 3,5 | 0,83 | 0,04 | 2 |

(mm)


## Ramping/Helical Milling Upper Limit

### Ramping





### Helical Milling

≤ Min. diameter




Below the min. machining diameter: Centre uncut portion cannot be removed by traverse cutting with the same cutter.


≥ Max. diameter




Above the max. machining diameter: Centre uncut portion can be removed by traverse cutting with the same cutter.

| Max. dia. DCX (mm) | Ramping | Helical milling | | | | | |
|---|---|---|---|---|---|---|---|
| | Max. ramping angle RPMX (°) | Max. machining dia. (mm) | Max. pitch (mm/rev) | Standard diameter (mm) | Max. pitch (mm/rev) | Min. machining dia. (mm) | Max. pitch (mm/rev) |
| 35 | 0,5 | 069,3 | 1,3 | 53,5 | 0,5 | 052,0 | 0,5 |
| 40 | 0,8 | 079,3 | 2,0 | 63,4 | 1,0 | 060,2 | 0,5 |
| 42 | 0,8 | 083,3 | 2,0 | 67,4 | 1,0 | 063,9 | 0,5 |
| 50 | 1,4 | 099,3 | 2,0 | 83,3 | 2,0 | 079,1 | 1,0 |
| 52 | 1,4 | 103,3 | 2,0 | 87,3 | 2,0 | 082,8 | 1,0 |
| 63 | 1,2 | 125,3 | 2,0 | 109,3 | 2,0 | 103,6 | 1,0 |
| 66 | 1,2 | 131,3 | 2,0 | 115,3 | 2,0 | 109,4 | 1,0 |
| 80 | 1,2 | 159,3 | 2,0 | 143,2 | 2,0 | 134,0 | 1,0 |
| 85 | 1,2 | 169,3 | 2,0 | 153,2 | 2,0 | 144,0 | 1,0 |
| 100 | 0,8 | 199,3 | 2,0 | 183,2 | 2,0 | 174,0 | 1,0 |
| 125 | Not recommended | | | | | | |
| 160 | Not recommended | | | | | | |

## Plunge Cutting Upper Limit




| Max. $a_e$ (mm) | Max. $f_z$ (mm/t) |
|---|---|
| 10 | 0,2 |

## Recommended Cutting Conditions

min.–optimum–max.

| ISO | Work material | Hardness | Cutting speed $v_c$ (m/min) | Feed rate $f_z$ (mm/t) |
|---|---|---|---|---|
| P | General steel | < 280 HB | 100–160–250 | 1,0–1,5–2,0 |
| P | Alloy steel | < 280 HB | 100–160–200 | 1,0–1,5–1,8 |
| P | Alloy steel | < 42 HRC | 100–150–180 | 0,8–1,0–1,2 |
| M | Stainless steel | – | 80–120–150 | 0,8–1,0–1,2 |
| K | Cast iron | – | 100–160–250 | 1,0–1,5–1,8 |
| H | Hardened steel | < 52 HRC | 80–100–120 | 0,3–0,5–0,7 |

The above figures are guidelines for use with BT50 machine tools at depth of cut ($a_p$) of 1,5 mm.
The above recommended cutting conditions may require adjustment depending on machine rigidity and workpiece rigidity.

# "Sumi Dual Mill"
# DMSW 08000 R(S)

New

| Rake angle | Radial | -7° to -10° |
|---|---|---|
| | Axial | -6° |

3 mm
15°




Fig 1




Fig 2




Fig 3





Fig 4



Fig 5



## Body (Shell Type)

Dimensions (mm)

| | Cat. No. | Stock | DCX | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | D3 | Number of teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | DMSW 08050RS04 | ● | 50 | 33,4 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 16,7 | 11 | – | 4 | 0,25 | 1 |
| | 08050RS05 | ● | 50 | 33,4 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 16,7 | 11 | – | 5 | 0,24 | 1 |
| | 08052RS04 | | 52 | 35,4 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 17 | 11 | – | 4 | 0,27 | 1 |
| | 08052RS05 | | 52 | 35,4 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 17 | 11 | – | 5 | 0,25 | 1 |
| | 08063RS04 | ● | 63 | 46,4 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 4 | 0,46 | 1 |
| | 08063RS05 | ● | 63 | 46,4 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 5 | 0,46 | 1 |
| | 08063RS06 | ● | 63 | 46,4 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | – | 6 | 0,44 | 1 |
| | 08063RS05-27 | ● | 63 | 46,4 | 50 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | – | 5 | 0,55 | 1 |
| | 08063RS06-27 | ● | 63 | 46,4 | 50 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | – | 6 | 0,53 | 1 |
| | 08066RS05-27 | | 66 | 49,4 | 50 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | – | 5 | 0,60 | 1 |
| | 08066RS06-27 | | 66 | 49,4 | 50 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | – | 6 | 0,58 | 1 |
| | 08080RS06 | ● | *80 | 63,3 | 55 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | – | 6 | 0,88 | 1 |
| | 08080RS08 | ● | *80 | 63,3 | 55 | 50 | 27 | 12,4 | 7 | 22 | 20 | 14 | – | 8 | 0,84 | 1 |
| | 08100RS06 | ● | 100 | 83,3 | 70 | 50 | 32 | 14,4 | 8 | 32 | 46 | – | – | 6 | 1,29 | 3 |
| | 08125RS08 | ● | 125 | 108,3 | 80 | 63 | 40 | 16,4 | 9 | 29 | 52 | 29 | – | 8 | 2,41 | 1 |
| | 08160RS10 | ● | 160 | 143,3 | 130 | 63 | 40 | 16,4 | 9 | 29 | 90 | – | – | 10 | 4,73 | 5 |
| Inch | DMSW 08050R04 | ❍ | 50 | 33,4 | 41 | 40 | 22,225 | 8,4 | 5 | 20 | 16,7 | 11 | – | 4 | 0,25 | 1 |
| | 08050R05 | ❍ | 50 | 33,4 | 41 | 40 | 22,225 | 8,4 | 5 | 20 | 16,7 | 11 | – | 5 | 0,24 | 1 |
| | 08063R04 | ❍ | 63 | 46,4 | 50 | 40 | 22,225 | 8,4 | 5 | 20 | 18 | 11 | – | 4 | 0,46 | 1 |
| | 08063R05 | ❍ | 63 | 46,4 | 50 | 40 | 22,225 | 8,4 | 5 | 20 | 18 | 11 | – | 5 | 0,46 | 1 |
| | 08063R06 | ❍ | 63 | 46,4 | 50 | 40 | 22,225 | 8,4 | 5 | 20 | 18 | 11 | – | 6 | 0,44 | 1 |
| | 08080R06 | ❍ | *80 | 63,3 | 70 | 63 | 31,75 | 12,7 | 8 | 32 | 27 | 18 | – | 6 | 1,32 | 1 |
| | 08080R08 | ❍ | *80 | 63,3 | 70 | 63 | 31,75 | 12,7 | 8 | 32 | 27 | 18 | – | 8 | 1,28 | 1 |
| | 08100R06 | ❍ | *100 | 83,3 | 70 | 63 | 31,75 | 12,7 | 8 | 32 | 46 | 27 | 18 | 6 | 1,75 | 2 |
| | 08125R08 | ❍ | 125 | 108,3 | 80 | 63 | 38,1 | 15,9 | 10 | 35,5 | 55 | 30 | – | 8 | 2,55 | 1 |
| | 08160R10 | ❍ | 160 | 143,3 | 100 | 63 | 50,8 | 19,1 | 11 | 38 | 72 | – | – | 10 | 4,18 | 4 |

Take note of the cutter mounting size (DCB) when selecting a cutter. Inserts are sold seperately.

For mounting the Ø 80 mm, Ø 85 mm and Ø 100 mm sized cutters marked with * to an arbor, use a JIS B1176 hexagonal socket bolt (metric specification : M12x30 to 35 mm, inch specification: M16x40 to 45 mm).

## Parts

| Applicable cutters | Insert screw | | Wrench | Handle grip | Wrench bit |
|---|---|---|---|---|---|
| |  | N·m |  |  |  |
| DMSW 08160R(S)10 | BFTX0513IP | 5,0 | TRDR20IP | – | – |
| Other than above | | | – | HPL2025 | TRB20IP |

## Identification Details

**DMSW 08 063 R S 05 - 27**

| Cutter series | Insert size | Cutter diameter | Feed direction | Metric | Number of teeth | Mounting size |
|---|---|---|---|---|---|---|

## Recommended Cutting Conditions

→ G.65


## Inserts

Dimension (mm)

| Application | Coated carbide | | | | |
|---|---|---|---|---|---|
| High speed / Light cut | | P | | K | |
| General purpose | P K M S | P | P | K | K |
| Roughing | P K M S | | P | | K |

| Cat. No. | ACU2500 | ACP2000 | ACP3000 | ACK2000 | ACK3000 | IC | S | RE | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| WNMU 0807ZNER-G | ● | ● | ● | ● | ● | 13 | 7 | 1,6 | 1 |
| WNMU 0807ZNER-H | ● | ● | ● | | | 13 | 7 | 1,6 | 1 |

Fig 1






● = Euro stock ❍ = Japan stock

## High Feed Milling of Steel, Stainless Steel, Die Steel and Cast Iron



1,5 mm 20° (MSX 08000□□)　2,0 mm 20° (MSX 12000□□)　2,5 mm 20° (MSX 14000□□)

→ H10-13

Fig. 1







Fig. 2





## Body

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of teeth | Helical Boring øB (max-min) | Ramping αmax. | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | | | | |
| MSX 08040 RS | ● | 40 | 37 | 45 | 16 | 8,4 | 5,6 | 18 | 13,5 | 9 | 4 | 65–78 | 1°30' | 0,2 | 1 |
| MSX 12050 RS | ● | 50 | 47 | 50 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 78–99 | 2°30' | 0,3 | 1 |
| 12052 RS | ● | 52 | 47 | 50 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 82–103 | 2°00' | 0,3 | 1 |
| 12063 RS | ● | 63 | 60 | 50 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 104–125 | 1°30' | 0,4 | 1 |
| 12066 RS | ● | 66 | 60 | 63 | 27 | 12,4 | 7,0 | 25 | 20 | 13,5 | 5 | 110–131 | 1°00' | 0,4 | 1 |
| MSX 14050 RS | ● | 50 | 47 | 50 | 22 | 10,4 | 6,3 | 20 | 17 | 11 | 3 | 73–98 | 3°30' | 0,3 | 1 |
| 14063 RS | ● | 63 | 60 | 50 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 99–124 | 2°00' | 0,6 | 1 |
| 14066 RS | ● | 66 | 60 | 63 | 27 | 12,4 | 7,0 | 25 | 13,5 | 20 | 4 | 107–132 | 2°00' | 0,7 | 1 |
| 14080 RS | ● | 80 | 76 | 63 | 27 | 12,4 | 7,0 | 25 | 13,5 | 20 | 5 | 133–158 | 1°30' | 1,2 | 1 |
| MSX 14100 RS | ● | 100 | 96 | 63 | 32 | 14,4 | 8,5 | 32 | - | 44 | 6 | 173–198 | 1°00' | 1,8 | 2 |


**Ramping (Slant Milling)**




**Helical Boring**




## Inserts




| Application | Coated Carbide | | | |
|---|---|---|---|---|
| High Speed / Light cut | | | KH | |
| General Purpose | PM | PM | KH | |
| Roughing | PM | PM | | KH |

| Cat. No. | ACP200 | ACP300 | ACK200 | ACK300 | Dimensions (mm) IC | S | RE |
|---|---|---|---|---|---|---|---|
| WDMT 0804 ZDTR | ● | ● | | ● | 8,5 | 4,0 | 2,0 |
| 0804 ZDTR-H | ● | ● | ❍ | ● | | | |
| WDMT 1205 ZDTR | ● | ● | | ● | 12 | 5,0 | 2,0 |
| 1205 ZDTR-H | ● | ● | ❍ | ● | | | |
| WDMT 1406 ZDTR | ● | ● | ❍ | ● | 14 | 6,0 | 2,0 |
| 1406 ZDTR-H | ● | ● | | ● | | | |

ZDTR-H : Stronger cutting edge

## Recommended Cutting Conditions

Depth of cut : $a_p$ (mm)
Feed rate : $f_z$ (mm/tooth)

| Work Material | Insert Type | Cutting Speed $v_c$ (m/min) | Insert Cat. No. | ø 40 | | ø 50–66 | | ø 80–100 | |
|---|---|---|---|---|---|---|---|---|---|
| | | | | $a_p$ | $f_z$ | $a_p$ | $f_z$ | $a_p$ | $f_z$ |
| General Steel (Below HB200) | ACP200 | 100-**150**-200 | WDMT 0804 | 1,0 | 1,2 | – | – | – | – |
| | | | WDMT 1205 | – | – | 1,2 | 1,4 | – | – |
| | | | WDMT 1406 | – | – | 1,5 | 1,5 | 1,5 | 1,5 |
| Alloy Steel (Below HRC45) | ACP200 | 80-**130**-180 | WDMT 0804 | 0,8 | 1,2 | – | – | – | – |
| | | | WDMT 1205 | – | – | 1,0 | 1,4 | – | – |
| | | | WDMT 1406 | – | – | 1,3 | 1,5 | 1,3 | 1,5 |
| Stainless Steel (X5CRNI1810) | ACP300 | 80-**120**-150 | WDMT 0804 | 1,0 | 0,8 | – | – | – | – |
| | | | WDMT 1205 | – | – | 1,2 | 1,2 | – | – |
| | | | WDMT 1406 | – | – | 1,5 | 1,3 | 1,5 | 1,3 |
| Cast Iron GG, GGG | ACK300 | 100-**150**-200 | WDMT 0804 | 1,0 | 1,4 | – | – | – | – |
| | | | WDMT 1205 | – | – | 1,2 | 1,5 | – | – |
| | | | WDMT 1406 | – | – | 1,5 | 1,8 | 1,5 | 1,8 |
| Hardened Steel (Below HRC50) | ACK300 | 40-**80**-100 | WDMT 0804 | 0,5 | 0,8 | – | – | – | – |
| | | | WDMT 1205 | – | – | 0,6 | 1,0 | – | – |
| | | | WDMT 1406 | – | – | 1,0 | 1,2 | 1,0 | 1,2 |

- The above recommended cutting conditions may require adjustment according to machine rigidity and work rigidity.
- The above figures are guidelines for use with the BT50 machine tool.

## Spare Parts

| Screw | | Wrench | Clamp | C Ring | Cramp screw | Applicable endmill |
|---|---|---|---|---|---|---|
| BFTX 0306 IP | **2,0** | TRDR 08 IP | CCH 3,5 | CR 03 | BFTX 03510 IP 08 | MSX 08000RS |
| BFTX 0409 IP | **3,0** | TRDR 15 IP | CCH 3,5 | CR 03 | BFTX 03510 IP 15 | MSX 12000RS |
| BFTX 0511 IP | **5,0** | TRDR 20 IP | CCH 4,5 | CR 03 | BFTX 04513 IP 20 | MSX 14000RS |



Remark: If depth-of-cut exceeds 5 mm, reduce recommended feedrates by 50 %.
The conditions above are meant as a guide, please adjust the cutting conditions according to actual work material and machine ridgidity.

Expansion




## General Features


WaveMill WFXH type is a high efficiency, multi-purpose cutter, that uses the WFX series inserts for high-feed roughing and a variety of processes.

## Characteristics

Stable, high-efficiency milling with superior cutting edge sharpness.
Supports various types of processes (ramping and helical milling).
Able to use the selection of inserts from the WFX series.

## Chipbreaker Selection




| Work Material | P M K Steel, Stainless Steel, Cast Iron | | | N Aluminium Alloy |
|---|---|---|---|---|
| Breaker | **L Type** | **G Type** | **H Type** | **S Type** |
| |  |  |  |  |
| Characteristic | Low Cutting Force | General Purpose | Strong Edge | Sharp Edge |
| Cutting Edge Figure |  20° |  15° |  10° |  25° |
| Work Material Application | Light Cutting<br>Low rigidity Milling<br>Low-Burr Design | **Main Chipbreaker**<br>General to<br>Interrupted Milling | Heavy Cut<br>Heavy Interrupted<br>Machining<br>Tempered Steel | Non-Ferrous Metal |

## Notes on Corner Finishing - Remaining Material

Actual machined corners will have uncut and overcut portions due to the shape of the inserts.

Fig. 1






Fig. 2




### WFXH 08000 RS Type


| Programmed Corner R | SOMT 08○○04-□ | | | SOMT 08○○08-□ | | | SOMT 08○○12-□ | | |
|---|---|---|---|---|---|---|---|---|---|
| | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape |
| 2,0 | 1,41 | 0 | Fig. 1 | 1,30 | 0 | Fig. 1 | 1,21 | 0 | Fig. 1 |
| 2,5 | 1,30 | 0,02 | Fig. 2 | 1,19 | 0,01 | Fig. 2 | 1,09 | 0 | Fig. 2 |
| 3,0 | - | - | - | - | - | - | 0,98 | 0,05 | Fig. 2 |


### WFXH 12000 RS Type

| Programmed Corner R | SOMT 12○○04-□ | | | SOMT 12○○08-□ | | | SOMT 12○○12-□ | | | SOMT 12○○16-□ | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape |
| 2,0 | 2,58 | 0 | Fig. 1 | 2,48 | 0 | Fig. 1 | 2,37 | 0 | Fig. 1 | 2,25 | 0 | Fig. 1 |
| 2,5 | 2,47 | 0 | Fig. 1 | 2,37 | 0 | Fig. 1 | 2,25 | 0 | Fig. 1 | 2,14 | 0 | Fig. 1 |
| 3,0 | 2,36 | 0 | Fig. 1 | 2,26 | 0 | Fig. 1 | 2,14 | 0 | Fig. 1 | 2,11 | 0 | Fig. 1 |
| 3,5 | 2,24 | 0,01 | Fig. 2 | 2,14 | 0 | Fig. 1 | 2,03 | 0 | Fig. 1 | 1,91 | 0 | Fig. 1 |
| 4,0 | - | - | - | 2,03 | 0,04 | Fig. 2 | 1,91 | 0,03 | Fig. 2 | 1,8 | 0,01 | Fig. 2 |

## Minimum Cutting Diameter


Minimum cutting diameter (DCN) will depend on the insert that is used. Using an insert with a large nose radius is recommended for the WFXH type.




| Body Cat. No. | DC | DCN based on insert nose | | | |
|---|---|---|---|---|---|
| | | RE0,4 | RE0,8 | RE1,2 | RE1,6 |
| WFXH 08025 M12Z2 | 25 | 10,4 | 10,9 | 11,5 | - |
| 08032 M12Z3 | 32 | 17,4 | 17,9 | 18,5 | - |
| WFXH 08040 RS | 40 | 25,4 | 25,9 | 26,5 | - |
| 08050 RS | 50 | 35,4 | 35,9 | 36,5 | - |
| 08050 RSZ6 | 50 | 35,4 | 35,9 | 36,5 | - |
| 08063 RS | 63 | 48,4 | 48,9 | 49,5 | - |
| WFXH 12040 M12Z3 | 40 | 16,6 | 17,1 | 17,5 | 18,1 |
| WFXH 12050 RS | 50 | 26,6 | 27,2 | 27,7 | 28,2 |
| 12063 RS | 63 | 39,5 | 40,0 | 40,4 | 41,1 |

## Taper Cutting and Helical Milling




Minimum and Maximum Diameters





Ramping Angle

| Insert Cat. No. | DC | Helical Millilng | | Taper Cutting |
|---|---|---|---|---|
| | | Min. | Max. | Max. Ramping Angle |
| SOMT 08○○04-□ | 25 | 35 | 49 | 1°30‘ |
| | 32 | 49 | 63 | 0°30‘ |
| | 40 | 65 | 79 | 0°30‘ |
| | 50 | Impossible | Impossible | 0°30‘ |
| | 63 | Impossible | Impossible | Impossible |
| SOMT 08○○08-□ | 25 | 35 | 48 | 3° |
| | 32 | 49 | 62 | 1°30‘ |
| | 40 | 65 | 78 | 1° |
| | 50 | 85 | 98 | 0°30‘ |
| | 63 | 111 | 124 | 0°30‘ |
| SOMT 08○○12-□ | 25 | 34 | 47 | 4°30‘ |
| | 32 | 48 | 61 | 2°30‘ |
| | 40 | 64 | 77 | 1°30‘ |
| | 50 | 84 | 97 | 1° |
| | 63 | 110 | 123 | 0°30‘ |

| Insert Cat. No. | DC | Helical Millilng | | Taper Cutting |
|---|---|---|---|---|
| | | Min. | Max. | Max. Ramping Angle |
| SOMT 12○○04-□ | 40 | 56 | 79 | 1° |
| | 50 | 76 | 99 | 0°30‘ |
| | 63 | Impossible | Impossible | Impossible |
| SOMT 12○○08-□ | 40 | 56 | 78 | 1°30‘ |
| | 50 | 76 | 98 | 1° |
| | 63 | 102 | 124 | 0°30‘ |
| SOMT 12○○12-□ | 40 | 55 | 77 | 2°30‘ |
| | 50 | 75 | 97 | 1°30‘ |
| | 63 | 101 | 123 | 1° |
| SOMT 12○○16-□ | 40 | 55 | 76 | 3°30‘ |
| | 50 | 75 | 96 | 2° |
| | 63 | 101 | 122 | 1°30‘ |

## Maximum Width of Cut when Plunge Milling




| Insert Cat. No. | Max. Width of Cut ae (max) |
|---|---|
| SOMT08 | 6 mm |
| SOMT12 | 10 mm |

Lower the feed rate when plunge milling.

## Recommended Cutting Conditions

| ISO | Work Material | Grade | Cutting Speed (vc (m/min) | Insert Cat. No. | ø 25 | | ø 32 | | ø 40 | | ø 50 | | ø 63 | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | ap (mm) | fz (mm/t) | ap (mm) | fz (mm/t) | ap (mm) | fz (mm/t) | ap (mm) | fz (mm/t) | ap (mm) | fz (mm/t) |
| P | General Steel <200HB | ACP200 | 100 - **150** - 200 | SOMT08 | 0,8 | 0,8 | 0,8 | 0,8 | - | - | 0,8 | 0,8 | 0,8 | 0,8 |
| | | | | SOMT12 | - | - | - | - | 1,0 | 1,0 | 1,0 | 1,0 | 1,0 | 1,0 |
| | Alloy Steel <HRC45 | ACP200 | 80 - **130** - 180 | SOMT08 | 0,7 | 0,8 | 0,7 | 0,8 | - | - | 0,7 | 0,8 | 0,7 | 0,8 |
| | | | | SOMT12 | - | - | - | - | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 |
| K | Stainless Steel (X5CrNiS18 10, other) | ACM300 | 80 - **120** - 150 | SOMT08 | 0,8 | 0,7 | 0,8 | 0,7 | - | - | 0,8 | 0,7 | 0,8 | 0,7 |
| | | | | SOMT12 | - | - | - | - | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 |
| M | Cast Iron FC, FCD | ACK300 | 100 - **150** - 200 | SOMT08 | 0,8 | 1,0 | 0,8 | 1,0 | - | - | 0,8 | 1,0 | 0,8 | 1,0 |
| | | | | SOMT12 | - | - | - | - | 1,0 | 1,2 | 1,0 | 1,2 | 1,0 | 1,2 |
| H | Hardened Steel <HRC50 | ACK300 | 40 - **80** - 100 | SOMT08 | 0,5 | 0,5 | 0,5 | 0,5 | - | - | 0,5 | 0,5 | 0,5 | 0,5 |
| | | | | SOMT12 | - | - | - | - | 0,6 | 0,8 | 0,6 | 0,8 | 0,6 | 0,8 |

The above recommended cutting conditions may require adjustment according to machine rigidity and work rigidity. The above figures are guidelines for use with the BT50 machine tool.
The above conditions assume a tool overhang length of L/D = 3 (i.e. overhang length is 3 times tool diameter) or less.
When tool overhang is more than L/D = 3 and less or equal L/D = 5, settings should be adjusted to approximately 70 % to 80 % of those indicated in the above cutting conditions (i.e. ap and fz).
When tool overhang is more than L/D = 5 and less or equal L/D = 8, settings should be adjusted to approximately 50 % to 60 % of those indicated in the above cutting conditions (i.e. ap and fz).

# WFXH 08000 RS


Expansion

## High Efficiency Machining for Steel, Stainless Steel, Die Steel and Non-Ferrous Metal

| Rake Angle | | |
|---|---|---|
| | Radial | –6° |
| | Axial | 6° |

1,5 mm, 15°






## Body - WFXH08000RS

| Cat. No. | | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | |
| WFXH | 08040 RS | ❍ | 40 | 33 | 40 | 16 | 8,4 | 5,6 | 18 | 14 | 9 | 4 | 0,2 |
| | 08050 RS | ❍ | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,3 |
| | 08050 RSZ6 | ❍ | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,3 |
| | 08063 RS | ❍ | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 6 | 0,5 |

⟶ H15

Inserts are not included.

## Identification Details


| WFX | H | 08 | 040 | R | S | - Z6 |
|---|---|---|---|---|---|---|
| Cutter Series | High Efficiency Milling | Insert Size | Cutter Diameter | Direction | Metric Type | Fine Pitch Type (Value is number of teeth) |

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | Cermet |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | | | P | | | K | K | | | | | | |
| General Purpose | | | | | | K | K | | | | | N | |
| Roughing | | | | | | | | K | | | | N | P |

| Cat. No. | | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCU2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | T4500A | RE |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| SOMT | 080304 PZER L | ● | ❍ | ● | ● | ❍ | ❍ | ❍ | ● | ● | ● | – | – | | 0,4 |
| | 080308 PZER L | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 |
| SOMT | 080304 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,4 |
| | 080308 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 |
| | 080312 PZER G | ● | | ● | ● | ● | | | ● | ● | ● | – | – | | 1,2 |
| SOMT | 080308 PZER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 |
| | 080312 PZER H | ● | | ● | ● | ● | | ❍ | ● | | ● | – | – | | 1,2 |
| SOET | 080304 PZER G | ● | | | | ❍ | | | ● | ● | | – | – | ❍ | 0,4 |
| | 080308 PZER G | ● | | | ❍ | | | ● | | | ● | – | – | ❍ | 0,8 |
| | 080312 PZER G | ● | | | ● | ❍ | | | ● | ❍ | ❍ | – | – | ❍ | 1,2 |
| SOET | 080302 PZFR S* | – | – | – | – | – | – | – | – | – | – | ● | ● | | 0,2 |
| | 080304 PZFR S* | – | – | – | – | – | – | – | – | – | – | ● | ● | | 0,4 |
| | 080308 PZFR S* | – | – | – | – | – | – | – | – | – | – | ● | ● | | 0,8 |




* If the cutting edge lacks strength when performing high efficiency milling of non-ferrous metals, try G type chipbreakers (ACK300).

## Spare Parts

| Screw | | Wrench |
|---|---|---|
| BFTX0306IP | 2,0 | TRDR08IP |

## Recommended Cutting Conditions

⟶ G69

## Programming and Dimension Information

⟶ G68



● = Euro stock
❍ = Japan stock
– = Not available
Recommended Tightening Torque (N·m)


# "Wave Mill" Series
# WFXH 12000 RS

## High Efficiency Machining for Steel, Stainless Steel, Die Steel and Non-Ferrous Metal

| Rake Angle | | |
|---|---|---|
| | Radial | –6° |
| | Axial | 6° |

2,5 mm, 15°






## Body - WFXH12000RS

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | | |
| WFXH 12050 RS | ❍ | 50 | 41 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 4 | 0,3 |
| 12063 RS | ❍ | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 20 | 18 | 11 | 5 | 0,4 |

Inserts are not included.

⟶ H15


## Identification Details

| WFX | H | 12 | 050 | R | S |
|---|---|---|---|---|---|
| Cutter Series | High Efficiency Milling | Insert Size | Cutter Diameter | Direction | Metric Type |

## Inserts


Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | Cermet | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | | | | | | | | | | | | | | |
| General Purpose | | | | | | | | | | | | | | |
| Roughing | | | | | | | | | | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCU2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | T4500A | RE |
| SOMT 120408 PDER L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 |
| SOMT 120404 PDER G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,4 |
| 120408 PDER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | ❍ | 0,8 |
| 120412 PDER G | ● | | ❍ | ● | ❍ | | ● | ❍ | ❍ | ● | – | – | | 1,2 |
| 120416 PDER G | ● | | ● | ● | ● | | ❍ | ❍ | ❍ | | – | – | | 1,6 |
| SOMT 120408 PDER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 |
| SOET 120408 PDFR S* | – | – | – | – | – | – | – | – | – | – | ● | ● | | 0,8 |




* If the cutting edge lacks strength when performing high efficiency milling of non-ferrous metals, try G type chipbreakers (ACK300).

## Spare Parts

| Screw | | Wrench |
|---|---|---|
|  | |  |
| BFTX03512IP | 3,0 | TRDR15IP |

## Recommended Cutting Conditions

⟶ G69

## Programming and Dimension Information

⟶ G68


# WAX 3000 RS

16–18mm 90°

P M K S N

(Shellmill)






## Body

(For inserts with nose radius ≤ 3,2 mm)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | No.of teeth | Weight (Kg) |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCB | LF | D2 | KWW | KDP | CBDP | | |
| WAX 3050 RS-3.2 | ● | 50 | 22 | 50 | 11 | 10,4 | 6.3 | 21 | 4 | 0,34 |
| 3063 RS-3.2 | ● | 63 | 22 | 50 | 11 | 10,4 | 6.3 | 21 | 5 | 0,6 |
| 3080 RS-3.2 | ● | 80 | 27 | 50 | 13,5 | 12,4 | 7 | 23 | 5 | 1,0 |
| WAX 3100 RS-3.2 | ● | 100 | 32 | 63 | 18 | 14,4 | 8 | 26 | 6 | 2,2 |
| 3125 RS-3.2 | ● | 125 | 40 | 63 | 22 | 16,4 | 9 | 29 | 7 | 3,5 |

## Body


(For inserts with nose radius ≥ 4,0mm)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | No.of teeth | Weight (Kg) |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCB | LF | D2 | KWW | KDP | CBDP | | |
| WAX 3050 RS-4.0 | ● | 50 | 22 | 50 | 11 | 10,4 | 6.3 | 21 | 4 | 0,34 |
| 3063 RS-4.0 | ● | 63 | 22 | 50 | 11 | 10,4 | 6.3 | 21 | 4 | 0,6 |
| 3080 RS-4.0 | ● | 80 | 27 | 50 | 13,5 | 12,4 | 7 | 23 | 5 | 1,0 |
| WAX 3100 RS-4.0 | ❍ | 100 | 32 | 63 | 18 | 14,4 | 8 | 26 | 6 | 2,2 |
| 3125 RS-4.0 | ● | 125 | 40 | 63 | 22 | 16,4 | 9 | 29 | 7 | 3,5 |


## Inserts for WAX 3000 Type

| Application | DLC Coated | Carbide |
|---|---|---|
| High Speed / Light cut | K N | N |
| General Purpose | | N |
| Roughing | | |

| Cat. No. | DL1000 | H1 | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | | APMX | INSL | BS | RE | S | D1 |
| AECT 160404 PEFRA | ● | ● | 18 | 16,4 | 1,4 | 0,4 | 5 | 4,4 |
| 160408 PEFRA | ● | ● | 18 | 16,4 | 1,0 | 0,8 | 5 | 4,4 |
| 160412 PEFRA | ● | ● | 18 | 16,4 | 0,6 | 1,2 | 5 | 4,4 |
| 160416 PEFRA | ● | ● | 17,5 | 16,4 | 0,5 | 1,6 | 5 | 4,4 |
| 160420 PEFRA | ● | ● | 17,5 | 16,4 | 0,5 | 2,0 | 5 | 4,4 |
| 160430 PEFRA | ● | ● | 17 | 16,4 | 0,7 | 3,0 | 5 | 4,4 |
| 160432 PEFRA | ● | ● | 17 | 16,4 | 0,5 | 3,2 | 5 | 4,4 |
| AECT 160440 PRFRA | ● | ● | 16,5 | 16,4 | 0,5 | 4,0 | 5 | 4,4 |
| 160450 PEFRA | ● | ● | 16 | 16,4 | 0,4 | 5,0 | 5 | 4,4 |




## Spare Parts

| Screw | Insert Wrench | Applicable Endmill |
|---|---|---|
|  3,0 N·m |  | |
| BFTX 0408 | TRD 15 | Ø 50 – Ø 125 |





● = Euro stock
❍ = Japan stock

❑ = Delivery on request


→ H61-63

N·m Recommended Tightening Torque (N·m)

22-24mm 90°

**(Shellmill**






## Body

(For inserts with nose radius ≤ 3,2 mm)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | No.of teeth | Weight (Kg) |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCB | LF | D2 | KWW | KDP | CBDP | | |
| WAX 4050RS-3.2 | ❑ | 50 | 16 | 50 | 9 | 8,4 | 5,6 | 18 | 2 | 0,37 |
| 4063RS-3.2 | ❑ | 63 | 22 | 50 | 11 | 10,4 | 6,3 | 21 | 3 | 0,54 |
| 4080RS-3.2 | ❑ | 80 | 27 | 50 | 13,5 | 12,4 | 7 | 23 | 4 | 0,81 |
| WAX 4100RS-3.2 | ❑ | 100 | 32 | 63 | 18 | 14,4 | 8 | 26 | 5 | 1,7 |
| 4125RS-3.2 | ❑ | 125 | 40 | 63 | 22 | 16,4 | 9 | 29 | 6 | 2,6 |

## Body


(For inserts with nose radius ≥ 4,0 mm)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | No.of teeth | Weight (Kg) |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCB | LF | D2 | KWW | KDP | CBDP | | |
| WAX 4050RS-4.0 | ❑ | 50 | 16 | 50 | 9 | 8,4 | 5,6 | 18 | 2 | 0,37 |
| 4063RS-4.0 | ❑ | 63 | 22 | 50 | 11 | 10,4 | 6,3 | 21 | 3 | 0,54 |
| 4080RS-4.0 | ❑ | 80 | 27 | 50 | 13,5 | 12,4 | 7 | 23 | 4 | 0,81 |
| WAX 4100RS-4.0 | ❑ | 100 | 32 | 63 | 18 | 14,4 | 8 | 26 | 5 | 1,7 |
| 4125RS-4.0 | ❑ | 125 | 40 | 63 | 22 | 16,4 | 9 | 29 | 6 | 2,6 |



## Inserts for WAX 4000 Type

| Application | DLC Coated | Carbide |
|---|---|---|
| High Speed / Light cut | K N | N |
| General Purpose | | N |
| Roughing | | |

| Cat. No. | DL1000 | H1 | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | | APMX | INSL | BS | RE | S | D1 |
| AECT 220604 PEFRA | ❑ | ❑ | 24 | 21,8 | 1,5 | 0,4 | 6,35 | 6 |
| 220608 PEFRA | ❑ | ❑ | 24 | 21,8 | 1,2 | 0,8 | 6,35 | 6 |
| 220612 PEFRA | ❑ | ❑ | 24 | 21,8 | 0,8 | 1,2 | 6,35 | 6 |
| 220616 PEFRA | ❑ | ❑ | 24 | 21,8 | 0,4 | 1,6 | 6,35 | 6 |
| 220620 PEFRA | ❑ | ❑ | 24 | 21,8 | 0,5 | 2,0 | 6,35 | 6 |
| 220630 PEFRA | ❑ | ❑ | 23 | 21,8 | 0,6 | 3,0 | 6,35 | 6 |
| 220632 PEFRA | ❑ | ❑ | 23 | 21,8 | 0,4 | 3,2 | 6,35 | 6 |
| AECT 220640 PRFRA | ❑ | ❑ | 22 | 21,8 | 1,2 | 4,0 | 6,35 | 6 |
| 220650 PEFRA | ❑ | ❑ | 22 | 21,8 | 0,4 | 5,0 | 6,35 | 6 |




## Spare Parts

| Screw | Insert Wrench | Applicable Endmill |
|---|---|---|
|  5,0 N·m |  | |
| BFTX0511N | TRD20 | Ø 50 – Ø 125 |

→ H61-63

Expansion



## Features

- **Drastically Reduced Runout Adjustment Time**
  Simple screw-fastening structure enables fine adjustments to be made easily.

- **Blade Through Coolant**
  Secures a supply of coolant to the cutting edge and breaks chips thoroughly.

- **Lightweight Aluminum Alloy Body**
  Utilizing aluminum alloy to achieve a total weight of less than 1,3 kg for a Ø 125 mm cutter with 22 teeth.










## Product Range

| Type | Cat. No. | Body Material | Diameter Range (mm) / No of Teeth | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | Ø 25 | Ø 30 | Ø 32 | Ø 40 | Ø 50 | Ø 63 | Ø 80 | Ø 100 | Ø 125 | Ø 160 |
| Shell | ANXA 16000RS | Aluminum Alloy | | | | | | | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | 12, 20, 28 |
| | ANXA 16000R (Inch) | Aluminum Alloy | | | | | | | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | 12, 20, 28 |
| | ANXS 16000RS | Steel | | | | 4, 6 | 4, 6, 9 | 6, 8, 12 | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | |
| | ANXS 16000R (Inch) | Steel | | | | | | 6, 8, 12 | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | |
| Shank | ANXS 16000E | Steel | 2 | 3, 4 | 3, 4 | 4, 6 | 4, 6, 9 | → H84 | | | | |
| Modular | ANXS 16000M | Steel | 2 | 3, 4 | 3, 4 | 4, 6 | | → H86 | | | | |

→ M58-M69


Inch Inch Bore


## Blade Selection Guide

| Work Material | N | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| Applications | Finishing / Light Cutting | General Purpose | Roughing | | Combined Milling *1 | Corner Radius Milling | Corner Radius Milling | Finishing | Burr-free / Mirror Finishing |
| Features | Low Cutting Force | Standard | Long Edge | High Strength | High Strength | Corner Radius 0,4 | Corner Radius 0,8 | Wiper | Wiper |
| Type | L | G | GX | H | GB | - | - | W | WS |
| Cutting Edge Shape |  |  |  |  |  |  |  |  |  |
| Edge Length(*2) | 6,0 mm | 6,0 mm | 9,0 mm | 6,0 mm | 6,0 mm | 6,0 mm | 6,0 mm | 2,0 mm | — |

*1 Machining of components combining aluminum alloy and cast iron

## Edge Selection Guide








*2 Edge length
GX type = 9,0 mm

- **Reduces Running Costs by Drastically Increasing Blade, Insert Regrinding Allowance (to 1,0 mm)**

Assuming 0,2 mm of regrinding each time, an edge can be used up to 6 times.
(Peripheral edge cannot be reground.)




If you wish to use reground blades you shall use sets of blades with matching size of the same level in order to keep the balance.

## Performances


### High-Speed / High-Efficiency Cutting

Realizes ultra-high efficiency machining with $v_f$ = 30.000 mm/min




Comparison: Cutter Diameter Ø 100 mm


| | Spindle Speed $min^{-1}$ | Number of Teeth | Feed Rate $v_f$ (mm/min) |
|---|---|---|---|
| ANX Series | 18.000 | 18 | 32.400 |
| Competitor | 9.500 | 12 | 11.400 |




### Drastically Reduces Runout Adjustment Time

– Simple screw-fastening structure
– Enables fine adjustments to be made easily
– High-rigidity body




### Chip Control




Blade-Through Coolant Chip Breaking




ALNEX ANX Series




Competitor

Work Material: G-AlSi12Cu
Cutting Conditions: $v_c$ = 2500 m/min, $f_z$ = 0,05 mm/t, $a_p$ = 0,5 mm, wet

## Adjustment of the Blades, Runout Alignment

① 

Insert the blade into its seat.

② 

While holding the blade against the seat, install the clamping bolt using the provided wrench, pre-tightening the bolt. (recommended pre-torque is 1 N·m)

③ 

Using the provided wrench for the height adjustment screw, set the height to your predetermined value.

④ 

Fully tighten the clamp bolt. (recommended torque is 2 N·m)

Expansion




## CVD Single Crystal Diamond SCV10 Wiper Blade

Wiper blade adopts high-strength single-crystal diamond using Sumitomo Electric Hardmetal's vapour phase synthesis technology.
Sharp cutting edge realises burr-free, mirror finish surface quality in aluminum alloy machining.
Superior wear resistance maintains cutting edge sharpness for a long time, reducing total tool costs.


## Burr-free

Sharp cutting edge and excellent wear resistance suppress burrs over the long term.




## Mirror Finishing

Sharp cutting edge achieves mirror finish with cutting alone.




Workpiece surface after machining

## Polycrystalline Diamond SUMIDIA DA1000 / DA90

Through the ideal combination of diamond particle size and binder, SUMIDIA DA1000/DA90 possess various features and is suitable for all kinds of applications such as machining of aluminum alloy and cemented carbide.

## Grades, Features and Applications

| Grade | Features | Applications | Diamond share (%) | Average grain size of diamond particles (μm) | Hardness HK (GPa) | TRS (GPa) |
|---|---|---|---|---|---|---|
| DA1000 | High-density sintered grade made of ultra-fine grain diamond that exhibits excellent wear and fracture resistance as well as edge sharpness. | Machining of High-Silicon Aluminum Alloy, Rough, Interrupt and Finish Machining of Aluminum Alloy, Woodcraft or Wooden Board Cutting/Facing, General Finishing of Non-Ferrous Metals | 90–95 | ≤ 0,5 | 50–60 | ≈ 2,60 |
| DA90 | Contains coarser diamond particles than other grades, giving it good wear resistance suitable for the machining of carbides and high-silicon aluminum. Shows the highest diamond content for excellent wear resistance. | Machining of High-Silicon Aluminum Alloy, Machining of Aluminum Composite (MMC), Green or Semi-Sintered Cemented Carbide & Ceramic Roughing, Machining of Sintered Ceramic/Stone/Rock | 90–95 | ≤ 50 | 50–65 | ≈ 1,10 |

## Grade Applications

| | Work Material | Applicable Grade | Example Parts |
|---|---|---|---|
| Aluminum | Sintered Aluminum, Wrought Aluminum Alloy | DA1000 | Piston Liners, Machine Parts, etc. |
| | Alloys for Die Casting | | Transmission Case, Oil Pan, Cylinder Block |
| | Alloys for Casting Low Si (≤ 12%) | | Cylinder Head |
| | Alloys for Casting High Si (> 12%) | | Cylinder Block |
| Non-ferrous metal | Non-Ferrous Sintered Alloy | DA1000 | Bush |
| | Gunmetal, Carbon | | Connecting Rod |
| | Fe Combined | DA90 | Cylinder Block, Bearing Cap |


# ANXA 16000 R(S)

Expansion

| Rake Angle | Radial | +5° |
|---|---|---|
| | Axial | +5° |

3 mm 90°






## Body - ANXA (Aluminum Alloy)

Dimensions (mm)

| | Cat. No. | Stock | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | ANXA 16080RS06 | ❍ | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 6 | 0,5 |
| | 16080RS10 | ● | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 10 | 0,5 |
| | 16080RS14 | ● | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 14 | 0,5 |
| | 16100RS08 | ❍ | 98 | 100 | 50 | 59 | 27 | 12,4 | 7 | 34 | 35 | 14 | 8 | 0,8 |
| | 16100RS12 | ● | 98 | 100 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 12 | 0,8 |
| | 16100RS18 | ● | 98 | 100 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 18 | 0,9 |
| | 16125RS10 | ❍ | 123 | 125 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 10 | 1,2 |
| | 16125RS14 | ● | 123 | 125 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 14 | 1,2 |
| | 16125RS22 | ● | 123 | 125 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 22 | 1,3 |
| | 16160RS12 | ❍ | 158 | 160 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | 29 | 12 | 2,6 |
| | 16160RS20 | ❍ | 158 | 160 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | 29 | 20 | 2,6 |
| | 16160RS28 | ❍ | 158 | 160 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | 29 | 28 | 2,6 |
| Inch | ANXA 16080R06 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 6 | 0,5 |
| | 16080R10 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 10 | 0,5 |
| | 16080R14 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 14 | 0,5 |
| | 16100R08 | ❍ | 98 | 100 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 8 | 0,8 |
| | 16100R12 | ❍ | 98 | 100 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 12 | 0,9 |
| | 16100R18 | ❍ | 98 | 100 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 18 | 0,9 |
| | 16125R10 | ❍ | 123 | 125 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 10 | 1,2 |
| | 16125R14 | ❍ | 123 | 125 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 14 | 1,2 |
| | 16125R22 | ❍ | 123 | 125 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 22 | 1,3 |
| | 16160R12 | ❍ | 158 | 160 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 55 | 30 | 12 | 2,3 |
| | 16160R20 | ❍ | 158 | 160 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 55 | 30 | 20 | 2,4 |
| | 16160R28 | ❍ | 158 | 160 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 55 | 30 | 28 | 2,6 |

Blades are sold separately. If using a blade for corner radius machining (ANB1604R/ANB1608R), DC = DCX.
The weight includes the weight of the blade and parts (excluding the centre bolt).
All aluminium alloy bodies with a maximum blade diameter (DCX) of Ø 80 to Ø 125 have the same diameter (DCB) of the retainer hole (metric Ø 27/in Ø 25,4).

## Identification Details

| ANX | A | 16 | 100 | R | S | 18 |
|---|---|---|---|---|---|---|
| Cutter Series | Aluminum Alloy Body | Blade Size | Cutter Diameter | Feed Direction | Metric | Number of Teeth |





● = Euro stock
❍ = Japan stock
❑ = Delivery on request
Recommended Tightening Torque (N·m)

Expansion

## Blades

Dimensions (mm)

| Application | SUMIDIA | | CVD |
|---|---|---|---|
| High Speed / Light Cut | N | KN | N |
| General Purpose | N | KN | |
| Roughing | N | KN | |

| Cat. No. | DA1000 | DA90 | SCV10 | Cutting Edge Length | RE | Wiper Edge Shape | Applications | Fig. |
|---|---|---|---|---|---|---|---|---|
| ANB 1600R-L | ● | | – | 6,0 | – | Linear | Low Cutting Force | 1 |
| 1600R-G | ● | | – | 6,0 | – | Arc-Shaped | General Purpose | 1 |
| 1600R-GB | | ● | – | 6,0 | – | Arc-Shaped | Combined Milling* | 1 |
| 1600R-H | ● | – | – | 6,0 | – | Arc-Shaped | Strong Edge | 1 |
| 1600R-GX | ❍ | | – | 9,0 | – | Arc-Shaped | Long Edge | 2 |
| 1604R | ❍ | | – | 6,0 | 0,4 | Linear | Corner Radius | 3 |
| 1608R | ❍ | | – | 6,0 | 0,8 | Linear | Corner Radius | 3 |
| 1600R-W | ❍ | | – | 2,0 | – | Arc-Shaped | Wiper | 4 |
| 1600R-WS | – | – | ❒ | – | – | Arc-Shaped | Wiper | 5 |


Fig. 1 



Fig. 2 



Fig. 3 




Fig. 4 


Fig. 5 


Wiper Blade

Wiper Blade

* Cast Iron/Aluminum Alloy

## Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 2.000–**2.500**–3.000 | 0,05–**0,13**–0,20 | DA1000 |

Si content > 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 400–**600**–800 | 0,05–**0,13**–0,20 | DA1000 DA90 |

Combined Milling of Cast Iron/Aluminum Alloy

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| K N | Cast Iron/ Aluminum Alloy | – | 300–**400**–500 | 0,05–**0,13**–0,20 | DA90 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

## Max. Allowable Spindle Speed

| Cat. No. | n max (min$^{-1}$) |
|---|---|
| ANXA 16080RS06 | 20.000 |
| 16080RS10 | 20.000 |
| 16080RS14 | 20.000 |
| 16100RS08 | 18.000 |
| 16100RS12 | 18.000 |
| 16100RS18 | 18.000 |
| 16125RS10 | 16.000 |
| 16125RS14 | 16.000 |
| 16125RS22 | 16.000 |
| 16160RS12 | 14.000 |
| 16160RS20 | 14.000 |
| 16160RS28 | 14.000 |
| ANXA 16080R06 | 20.000 |
| 16080R10 | 20.000 |
| 16080R14 | 20.000 |
| 16100R08 | 18.000 |
| 16100R12 | 18.000 |
| 16100R18 | 18.000 |
| 16125R10 | 16.000 |
| 16125R14 | 16.000 |
| 16125R22 | 16.000 |
| 16160R12 | 14.000 |
| 16160R20 | 14.000 |
| 16160R28 | 14.000 |

## Spare Parts


Sold separately.

| Applicable Cutters | Clamp Screw | | Adjustment Screw | Wrench | Adjustment Wrench | Centre Bolt | | Assembly Wrench |
|---|---|---|---|---|---|---|---|---|
| |  |  |  |  |  |  |  |  |
| ANXA 16080R(S)_ _<br>16100R(S)_ _<br>16125R(S)_ _<br>16160R(S)_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | BXH1235-D33 | 50 | HFVT |
| | | | | | | BXH2036-D50 | 200 | |

The adjustment spanner (ANT) can also be used for height adjustment of the RF type cutters for high speed machining and the HF type cutters for high efficiency machining.

### Wiper Blade Step Amount

When using the wiper blade, in order to maintain balance, be sure to use a cutter with an even number of cutting edges and place the wiper blades at opposite positions.



# ANXS 16000 R(S)

Expansion

| Rake Angle | Radial | +5° |
|---|---|---|
| | Axial | +5° |

3 mm 90°



Fig. 1






Fig. 2




## Body - ANXS (Steel)

Dimensions (mm)

| | Cat. No. | Stock | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | ANXS 16040RS04 | ❍ | 38 | 40 | 38,5 | 40 | 16 | 8,4 | 5,6 | 26 | 14 | 9 | 4 | 0,3 | 1 |
| | 16040RS06 | ● | 38 | 40 | 38,5 | 40 | 16 | 8,4 | 5,6 | 26 | 14 | 9 | 6 | 0,3 | 1 |
| | 16050RS04 | ❍ | 48 | 50 | 48,5 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 4 | 0,4 | 1 |
| | 16050RS06 | ● | 48 | 50 | 48,5 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 6 | 0,4 | 1 |
| | 16050RS09 | ❍ | 48 | 50 | 48,5 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 9 | 0,5 | 1 |
| | 16063RS06 | ❍ | 61 | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 6 | 0,7 | 1 |
| | 16063RS08 | ● | 61 | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 8 | 0,7 | 1 |
| | 16063RS12 | ● | 61 | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 12 | 0,7 | 1 |
| | 16080RS06 | ❍ | 78 | 80 | 50 | 40 | 27 | 12,4 | 7 | 34 | 35 | 14 | 6 | 1,2 | 1 |
| | 16080RS10 | ❍ | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 10 | 1,2 | 1 |
| | 16080RS14 | ❍ | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 14 | 1,2 | 1 |
| | 16100RS08 | ❍ | 98 | 100 | 80 | 50 | 32 | 14,4 | 8 | 32 | 46 | – | 8 | 1,9 | 2 |
| | 16100RS12 | ❍ | 98 | 100 | 80 | 50 | 32 | 14,4 | 8 | 32 | 46 | – | 12 | 2,0 | 2 |
| | 16100RS18 | ❍ | 98 | 100 | 80 | 50 | 32 | 14,4 | 8 | 32 | 46 | – | 18 | 2,0 | 2 |
| | 16125RS10 | ❍ | 123 | 125 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | – | 10 | 3,8 | 2 |
| | 16125RS14 | ❍ | 123 | 125 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | – | 14 | 3,9 | 2 |
| | 16125RS22 | ❍ | 123 | 125 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | – | 22 | 3,9 | 2 |
| Inch | ANXS 16063R06 | ❍ | 61 | 63 | 50 | 50 | 25,4 | 9,5 | 6 | 31 | 20 | 14 | 6 | 0,9 | 1 |
| | 16063R08 | ❍ | 61 | 63 | 50 | 50 | 25,4 | 9,5 | 6 | 31 | 20 | 14 | 8 | 0,9 | 1 |
| | 16063R12 | ❍ | 61 | 63 | 50 | 50 | 25,4 | 9,5 | 6 | 31 | 20 | 14 | 12 | 0,9 | 1 |
| | 16080R06 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 6 | 1,2 | 1 |
| | 16080R10 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 10 | 1,2 | 1 |
| | 16080R14 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 14 | 1,2 | 1 |
| | 16100R08 | ❍ | 98 | 100 | 80 | 50 | 31,75 | 12,7 | 8 | 36 | 42 | – | 8 | 1,9 | 2 |
| | 16100R12 | ❍ | 98 | 100 | 80 | 50 | 31,75 | 12,7 | 8 | 36 | 42 | – | 12 | 2,0 | 2 |
| | 16100R18 | ❍ | 98 | 100 | 80 | 50 | 31,75 | 12,7 | 8 | 36 | 42 | – | 18 | 2,0 | 2 |
| | 16125R10 | ❍ | 123 | 125 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 52 | – | 10 | 3,9 | 2 |
| | 16125R14 | ❍ | 123 | 125 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 52 | – | 14 | 3,9 | 2 |
| | 16125R22 | ❍ | 123 | 125 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 52 | – | 22 | 3,9 | 2 |

Blades are sold separately. If using a blade for corner radius machining (ANB1604R/ANB1608R), DC = DCX.
The weight includes the weight of the blade and parts (excluding the centre bolt).

## Identification Details

| ANX | S | 16 | 100 | R | S | 18 |
|---|---|---|---|---|---|---|
| Cutter Series | Steel Body | Blade Size | Cutter Diameter | Feed Direction | Metric | Number of Teeth |





● = Euro stock
❍ = Japan stock
❑ = Delivery on request
Recommended Tightening Torque (N·m)

Expansion

## Blades

Dimensions (mm)

| Application | SUMIDIA | | CVD |
|---|---|---|---|
| High Speed / Light Cut | N | KN | N |
| General Purpose | N | KN | |
| Roughing | N | KN | |

| Cat. No. | DA1000 | DA90 | SCV10 | Cutting Edge Length | RE | Wiper Edge Shape | Applications | Fig. |
|---|---|---|---|---|---|---|---|---|
| ANB 1600R-L | ● | | – | 6,0 | – | Linear | Low Cutting Force | 1 |
| 1600R-G | ● | | – | 6,0 | – | Arc-Shaped | General Purpose | 1 |
| 1600R-GB | | ● | – | 6,0 | – | Arc-Shaped | Combined Milling* | 1 |
| 1600R-H | ● | – | – | 6,0 | – | Arc-Shaped | Strong Edge | 1 |
| 1600R-GX | ❍ | | – | 9,0 | – | Arc-Shaped | Long Edge | 2 |
| 1604R | ❍ | | – | 6,0 | 0,4 | Linear | Corner Radius | 3 |
| 1608R | ❍ | | – | 6,0 | 0,8 | Linear | Corner Radius | 3 |
| 1600R-W | ❍ | | – | 2,0 | – | Arc-Shaped | Wiper | 4 |
| 1600R-WS | – | – | ❒ | – | – | Arc-Shaped | Wiper | 5 |


Fig. 1




Fig. 2






Fig. 3



Fig. 4



Wiper Blade

Fig. 5



Wiper Blade

* Cast Iron/Aluminum Alloy

## Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 2.000–**2.500**–3.000 | 0,05–**0,13**–0,20 | DA1000 |

Si content > 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 400–**600**–800 | 0,05–**0,13**–0,20 | DA1000 DA90 |

Combined Milling of Cast Iron/Aluminum Alloy

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| K N | Cast Iron/ Aluminum Alloy | – | 300–**400**–500 | 0,05–**0,13**–0,20 | DA90 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

## Spare Parts

Sold separately.

| Applicable Cutters | Clamp Screw | | Adjustment Screw | Wrench | Adjustment Wrench | Centre Bolt | | Assembly Wrench |
|---|---|---|---|---|---|---|---|---|
| ANX 16040RS_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | BXH0825-D13 | 15 | HFVT |
| 16050RS_ _ | | | | | | BXH1030-D16 | 25 | |
| 16063RS_ _ | | | | | | | | |
| 16080RS_ _ | | | | | | BXH1235-D33 | 50 | |
| 16100RS_ _ | | | | | | BXH1635-D40 | 100 | |
| 16125RS_ _ | | | | | | BXH2036-D50 | 200 | |
| 16063R_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | BXH1235-D18 | 40 | |
| 16080R_ _ | | | | | | BXH1235-D33 | 50 | |
| 16100R_ _ | | | | | | BXH1635-D40 | 100 | |
| 16125R_ _ | | | | | | BXH2036-D50 | 200 | |


The adjustment spanner (ANT) can also be used for height adjustment of the RF type cutters for high speed machining and the HF type cutters for high efficiency machining.

## Max. Allowable Spindle Speed

| Cat. No. | n max (min$^{-1}$) |
|---|---|
| ANXS 16040RS04 | 25.000 |
| 16040RS06 | 25.000 |
| 16050RS04 | 25.000 |
| 16050RS06 | 25.000 |
| 16050RS09 | 25.000 |
| 16063RS06 | 22.000 |
| 16063RS08 | 22.000 |
| 16063RS12 | 22.000 |
| 16080RS06 | 20.000 |
| 16080RS10 | 20.000 |
| 16080RS14 | 20.000 |
| 16100RS08 | 18.000 |
| 16100RS12 | 18.000 |
| 16100RS18 | 18.000 |
| 16125RS10 | 16.000 |
| 16125RS14 | 16.000 |
| 16125RS22 | 16.000 |
| ANXS 16063R06 | 22.000 |
| 16063R08 | 22.000 |
| 16063R12 | 22.000 |
| 16080R06 | 20.000 |
| 16080R10 | 20.000 |
| 16080R14 | 20.000 |
| 16100R08 | 18.000 |
| 16100R12 | 18.000 |
| 16100R18 | 18.000 |
| 16125R10 | 16.000 |
| 16125R14 | 16.000 |
| 16125R22 | 16.000 |

### Wiper Blade Step Amount

When using the wiper blade, in order to maintain balance, be sure to use a cutter with an even number of cutting edges and place the wiper blades at opposite positions.



## High Speed Finishing of Aluminium Alloy



Fig. 1






Fig. 2




## Body

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | No. of Teeth | Max. Depth of Cut | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | | | | |
| RF 4080 RS | ● | 80 | 82 | 60 | 50 | 27 | 12,4 | 7,0 | 29 | 6 | 3,0 | 0,7 | 1 |
| RF 4100 RS | ❑ | 100 | 102 | 75 | 50 | 32 | 14,4 | 8,5 | 29 | 6 | | 1,0 | 1 |
| 4125 RS | ● | 125 | 127 | 75 | 63 | 40 | 16,4 | 9,5 | 29 | 8 | | 1,6 | 1 |
| 4160 RS | ❑ | 160 | 162 | 100 | 63 | 40 | 16,4 | 9,5 | 29 | 10 | | 2,6 | 2 |

Remark: PCD blades and inserts are not included.

## Insert for Roughing and Finishing





Fig. 1





Fig. 2






Fig. 3

| Application | Carbide | SUMIDIA | | |
|---|---|---|---|---|
| High Speed / Light cut | N | N | N | |
| General Purpose | N | N | N | |
| Roughing | N | N | N | |
| **Cat. No.** | **H1** | **DA1000** | **DA2200** | **Fig.** |
| SDET 1204 ZDFR | ● | | | 1 |
| SNEW 1204 ADFR-NF | | ● | ▲ | 2 |
| SNEW 1204 ADFR-W-NF | | ❍ | ▲ | 3 |

## Structure





## "Sumidia" Blade

| PCD grade DA2200 | Cat. No. | Stock |
|---|---|---|
| Standard type  | **RFB** | ❑ |
| Wiper type  | **RFBW** | ❑ |

## Dummy Blade

| | | |
|---|---|---|
|  | **RFD** | ❍ |

## Cartridge

| Shape | Cat. No. | Stock |
|---|---|---|
| For carbide insert  | **RFR** | ● |
| For Sumidia insert  | **RFF** | ● |

## Cutting Insert Selection

**For easy assembling**:
PCD blade **RFB**
PCD blade **RFB** (wiper type)

**For finishing**:
Cartridge **RFF**
PCD insert SNEW 1204 ADFR-NF (standard type)
SNEW 1204 ADFR-W-NF (wiper type)
PCD grade: DA1000

**For roughing:**
Cartridge **RFR**
Uncoated carbide insert
SDET 1204 ZDFR, grade: H1

## Spare Parts

|  |  |  10,0 N·m |  3,0 N·m |  |  |  6,0 N·m |  TH050 TH015,TH025 |  |
|---|---|---|---|---|---|---|---|---|
| Cover | Position setting stoper | Main clamp screw | Sub clamp screw | Cover clamp screw | Adjustment screw | Insert clamp screw | Insert wrench | Cartridge wrench |
| RFC | RFS | BX0620 | BTD0510 | FBUP2-A0-8 | RFJ | BFTX0509N | TH015, TH025 TH050 | TTX20 |

## Setting Gauge



RF-SET

Dial-gauge is not included.



● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item

## High Speed Finishing of Aluminium Alloy



Fig. 1






Fig. 2




## Body

| Cat. No. | Stock | Dimensions (mm) | | No. of teeth | Fig. | Weight (Kg) |
|---|---|---|---|---|---|---|
| | | DC | DCSFMS | | | |
| SRF 30 R-ST | ❍ | 30 | - | 3 | 1 | 0,34 |
| SRF 40 R-ST | ❍ | 40 | - | 4 | 1 | 0,50 |
| SRF 50 RS | ❑ | 50 | 46,5 | 5 | 2 | 0,59 |
| SRF 63 RS | ❑ | 63 | 45,0 | 6 | 2 | 0,67 |

Inserts are sold seperately.

## Inserts

Dimensions (mm)






Fig. 1 Fig. 2 Fig. 3

| Application | SUMIDIA |
|---|---|
| High Speed / Light cut | N |
| General Purpose | N |
| Roughing | N |

| Cat. No. | DA1000 | Cutting Edge | Fig. |
|---|---|---|---|
| SNEW 09T3 ADTR-NF | ❑ | Standard | 1 |
| 09T3 ADTR-U-NF | ❑ | Wiper | 2 |
| 09T3 ADTR-R-NF | ❍ | Nose Radius | 3 |

- Standard inserts and Wiper inserts can be used on the same cutter body.
- Standard inserts with nose radius should be used where vibration is present. As such, Wiper-inserts will not be applicable.
- Inserts can be regrind 3 times (up to minimum IC diameter 9,225 mm).
- When using reground inserts, it is advisable to reconfirm insert height and cutting diameter with a tool pre-setter.
- Do not mix new and reground inserts, or even inserts with different regrind amount on the same cutter.

## Spare Parts




## Maximum D.O.C. Guide (SRF50RS, 5 teeth)

The contains guidelines on the maximum D.O.C., determined from internal tests. "O" mark indicates the possible application range. Actual cutting conditions should be set, based on actual machine and work characteristics.

| D.O.C. (mm) \ Feed | Feed Speed, $v_f$ (mm/min) | | |
|---|---|---|---|
| | 2.500 | 4.000 | 5.000 |
| | Feed Rate, $f_z$ (mm/tooth) | | |
| | 0,05 | 0,08 | 0,10 |
| 0,5 | ○ | ○ | ○ |
| 1,0 | ○ | ○ | ○ |
| 1,5 | ○ | ○ | ○ |
| 2,0 | ○ | ○ | ○ |
| 2,5 | ○ | ○ | ○ |
| 3,0 | ○ | ○ | ○ |
| 3,5 | ○ | ○ | – |
| 4,0 | ○ | – | – |
| 4,5 | ○ | – | – |
| 5,0 | ○ | – | – |

● Cutting Conditions

Cutter: SRF 50 RS
Insert: SNEW 09T3 ADFR-NF (DA1000)
n : 10.000 rpm
Width: 35mm at D.O.C. indicated above



## Recommended Cutting Conditions for RF and SRF Type Cutters

| Work Material | | Process | Grade | Cutting Speed (m/min) | | Feed Rate (mm/tooth) | Depth of Cut (mm) | |
|---|---|---|---|---|---|---|---|---|
| | | | | RF Type | SRF Type | | RF Type | SRF Type |
| Aluminium Alloy | Si < 13 % | Finishing | **DA1000** (PCD) | 2.000–5.000 | –4.000 | 0,05–0,2 | –3,0 | –5,0 |
| | | Roughing | H1 (Carbide) | 1.000–2.500 | – | | | |
| | Si ≥ 13 % | Finishing | **DA1000** (PCD) | 400–800 | –800 | | | |
| | | Roughing | H1 (Carbide) | 200–400 | – | | | |

## High Speed Finishing of Grey Cast Iron



### Features

- High speed machining $v_c$=1.500m/min
- Excellent surface roughness Rz = 3,2 (Ra = 1,0)
- Safety structure for the centrifugal force under high speed cutting conditions
- Run-out is less than 10 µm
- Easy assembling method using the setting gauge
- Running cost is reduced because of economical insert

## SUMIBORON ”BN Finish Mill”

### Application

GG25–GG30 (HB200–250) grey cast iron with pearlite matrix, and ferrite matrix (HB130–160)
Application examples: engine block, cylinder block, etc



### Specifications


FMU Type: ø80–ø315 mm
Insert: SNEW1203ADTR/L
Low cutting force type: SNEW1203ADTR/L-S

### Recommended Cutting Conditions

Speed: $v_c$ = 800–2000 m/min
Feed: $f_z$ = 0,1–0,3 mm/tooth
Depth: $a_p$ = 0,5 mm or less
Dry cutting


### Performance

● Tool Life Diagram




Work Material : GG25 $H_B$ 240 (Pearlite)
Cutting Speed : $v_c$ = 600–4000 m/min
Feed Rate : $f_z$ = 0,15 mm/tooth
Depth of Cut : $a_p$ = 0,5 mm, Dry

● Estimated Tool Life




Work Material : GG25 $H_B$ 240 (Pearlite)
Cutting Speed : $v_c$ = 400–4000 m/min
Feed Rate : $f_z$ = 0,15 mm/tooth
Depth of Cut : $a_p$ = 0,5 mm, Dry

- Milling of ductile cast iron and alloy steel casting do not produce the best results.
- Dry cutting is recommended. Wet cutting will result in chipping of cutting edges in the early stages due to thermal cracking.







● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
Recommended Tightening Torque (N·m)

## Specifications

Approach angle: 90°
Axial rake angle: + 8°
Radial rake angle: + 2°




## Structure




## Body

Fig. 1





Fig. 2





Fig. 3





Fig. 4






Fig. 5




| Cat. No. | Stock | Dimensions (mm) | | | | | | | | No. of Teeth | Max. Depth of Cut | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | | | | |
| FMU 4080 RS | ❑ | 80 | 82,8 | 60 | 63 | 27 | 12,4 | 7,0 | 25 | 6 | 0,5 | 1,6 | 1 |
| FMU 4100 RS | ● | 100 | 102,8 | 76 | 63 | 32 | 14,4 | 8,5 | 29 | 8 | | 2,4 | 2 |
| 4125 RS | ❑ | 125 | 127,8 | 75 | 63 | 40 | 16,4 | 9,5 | 29 | 10 | | 3,4 | 2 |
| 4160 RS | ❑ | 160 | 162,8 | 100 | 63 | 40 | 16,4 | 9,5 | 29 | 12 | | 5,6 | 3 |
| FMU 4200 RS | ❑ | 200 | 202,8 | 130 | 63 | 60 | 25,7 | 14,0 | 38 | 16 | | 9,2 | 4 |
| 4250 RS | ❑ | 250 | 252,8 | 130 | 63 | 60 | 25,7 | 14,0 | 38 | 20 | | 14,3 | 4 |
| FMU 4315 RS | | 315 | 317,8 | 240 | 80 | 60 | 25,7 | 14,0 | 40 | 24 | | 27,8 | 5 |

## Inserts

Fig. 1







Fig. 2




| Application | CBN | |
|---|---|---|
| High Speed / Light cut | K | K |
| General Purpose | K | K |
| Roughing | | |


| Cat. No. | BN700 | BN7000 | Figure |
|---|---|---|---|
| SNEW 1203 ADT R | ▲ | ❍ | 1 |
| 1203 ADT R-S | ▲ | ❍ | 2 |

## Cartridge




| Cartridge | Insert Screw | Adjustment Screw | O-ring | Insert Wrench | Pin |
|---|---|---|---|---|---|
| FMUU | BFTX0509N | FMUJ | P3 | TRX20 | 1,8 x 45 |

## Spare Parts



| Cartridge Screw | Screw | Setting clamp | Double screw | Wrench | Wrench | Wrench |
|---|---|---|---|---|---|---|
| BH0620 | BTD0609 | FMUE | WB5-10 | TH040 | LH030 | LH025 |

## Gauge



RF-SET

Dial-gauge is not included.

# Indexable Endmills

**H1–H88**














| | | | |
|---|---|---|---|
| | Selection Guide | Milling Cutter Selection Guide | H2–3 |
| | Exchangeable Head Endmills | According to Work Materials / Applications | |
| | | Modular Tools | H4–5 |
| **Face Milling** | "Sumi Dual", General Purpose Face Mills Expansion | DGC 13000 EW | H6 |
| | "Wave Mill", General Purpose Face Mills Expansion | WGX 13000 EW | H7 |
| | "Sumi Dual", High Feed Milling | DMSW 08000 E(L) | H8 |
| | | DMSW 08000 M | H9 |
| | High Feed Milling | MSX 06000/08000/12000/14000 ES/EM/EW | H10–11 |
| | | MSX 06000/08000/12000/12000 M | H12–13 |
| | High Feed Milling Expansion | WFXH 08000/12000 M | H14–15 |
| **Shoulder Milling** | "Sumi Dual Mill" Expansion | DFC(M) 09000 E | H16–17 |
| | "Wave Mill" for Shoulder Milling Expansion | WFX(F/M) 08000/12000 E | H18–19 |
| | | WFX 08000 M | H18 |
| | "Sumi Dual Mill", tangential Expansion | TSX(F/M) 08000/13000 E | H20–23 |
| | "Sumi Dual Mill", Repeater Mill | TSXR 08000/13000 E New | H24–25 |
| | "Sumi Wave" for Shoulder Milling Expansion | WEZ | H26–29 |
| | | WEZ 11000 E/ES/EL | H30–35 |
| | | WEZ 17000 E/ES/EL | H36–41 |
| | "Wave Mill", Repeater Mill | WEZR 11000/17000 E New | H42–45 |
| | | WEZ 11000/17000 M | H46–49 |
| | | WEZR 11000/17000 M New | H50–53 |
| | "Wave Mill" for Shoulder Milling | WEX 1000/2000/3000 E/EL/EW/M | H54–60 |
| | "Wave Mill" Series for Aluminium | WAX 3000 E/EL | H61–62 |
| | | WAX 4000 E/EL | H63 |
| | Repeater Mill | WRX 2000 / 3000 | H64–67 |
| | Shoulder Milling Cutter for Titanium | MTIX 16000 New | H68–69 |
| **Others** | "Wave Ball-Mill" for Roughing | WBMR 2000/2000L | H70–71 |
| | "Wave Ball-Mill" for Finishing | WBMF 1000 | H72–73 |
| | "Wave Radius Mill" with Polygon Inserts | WRCX 08000/10000 E | H74 |
| | | 08000/10000/12000 M | H75 |
| | "Wave Radius Mill" with Round Inserts | RSX(F) 08000/10000/12000 ES | H76 |
| | | 08000/10000/12000 M | H77 |
| | "Wave Mill" for Chamfering Expansion | WFXC 08000/12000 E | H78–79 |
| | | WFXC 08000/12000 M | H80 |
| | High Speed Non-Ferrous Mill Expansion | ANX | H82–83 |
| | | ANXS 16000 E | H84–85 |
| | | ANXS 16000 M New | H86–87 |

# Selection Guide

| Application | Cutter Type | Series | Insert Type | Approach Angle / Max. Depth of Cut (mm) | Cutter Diameter (mm) | Application: Face Milling – General Purpose | Face Milling – Finishing | Face Milling – High Feed | Shoulder Milling | Groove Milling | Ramping | Chamfering | Drilling | Profiling | Profile Finishing | Work Material: P – Carbon Steel / Alloy Steel | P – Tempered Steel / Die Steel | M – Stainless Steel | K – Cast Iron / Ductile Cast Iron | N – Non-Ferrous Metal | N – Aluminium Alloy | S – Ti Alloy / Heat Resistant Alloy | H – Hardened Steel HRC 45–55 | Ref. Page |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Face Milling | DGC | DGC 13000-EW | SNMU13T6..ONMU05T6.. | 3–6 mm 45° | 40–63 | ◎ | | | | | | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | H6 |
| | WGX | WGX 13000-EW | SEE/MT 13T3.. | 6 mm 45° | 32–63 | ◎ | ◎ | | | | | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | H7 |
| High Feed Milling | DMSW (New) | DMSW 08000-E(L) | WNMU0807... | 3 mm 15° | 35–63 | | | ◎ | ○ | ○ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | | | | ○ | H8 |
| | DMSW-M (New) | DMSW 08000-M | | 3 mm 15° | 35–42 | | | ◎ | ○ | ○ | ○ | | | | | ◎ | ◎ | ○ | ◎ | | | | ○ | H9 |
| | MSX | MSX(ES/EM/EW) 06000, 0800, 12000, 14000 | WDMT0603.., WDMT0804.. WDMT1205.., WDMT1406.. | 1,0–2,5 mm 20° | 16–63 | | | ◎ | ○ | ○ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | | | | ○ | H11 |
| | MSX-M | MSX 06000-M 08000-M 12000-M | | 1,0–2,0 mm 20° | 16–40 | | | ◎ | ○ | ○ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | | | | ○ | H12 |
| | WFXH-M | WFXH 08000-M | SOMT 1204.. | 1,5 mm 15° | 25–32 | | | ◎ | ○ | ○ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | | | ○ | ○ | H15 |
| | | WFXH 12000-M | | 2,5 mm 15° | 40 | | | | | | | | | | | | | | | | | | | |
| Shoulder Milling | DFC | DFC (M) 09000-E | XNMU 0606.. | 6 mm 90° | 25–80 | ◎ | ○ | | ◎ | ○ | | | | | | ◎ | ◎ | ○ | ◎ | | | ○ | | H17 |
| | WFX | WFX(M/F) 08000-E 12000-E | SOMT 0803.. | 6 mm 90° | 20–63 | ○ | ◎ | | ◎ | ○ | | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | H18 |
| | | | | 10 mm 90° | 40–80 | | | | | | | | | | | | | | | | | | | H19 |
| | WFX-M | WFX 08000-M | SOMT 1204.. | 6 mm 90° | 20–40 | | | | | | | | | | | | | | | | | | | H18 |
| | TSX | TSX (-F) 08000-E TSX (-M) 13000-E | LNEX 0804.. | 8 mm 90° | 16–80 | ◎ | ◎ | | ◎ | ○ | | | | | | ◎ | ◎ | ◎ | ◎ | | | ◎ | | H22 |
| | | | | 12 mm 90° | 25–80 | | | | | | | | | | | | | | | | | | | H23 |
| | TSXR (New) | TSXR 08000-E 13000-E | LNEX1306.. | 21–40mm 90° | 20–40 | ○ | | | ◎ | | | | | | | ◎ | ◎ | ◎ | ◎ | | | ◎ | | H24 |
| | | | | 41–60mm 90° | 40–50 | | | | | | | | | | | | | | | | | | | H25 |
| | WEZ | WEZ 11000 -E/ES/EL | AOMT 11T3..., AOET11T3..., AOMT 1705..., AOET1705... | 10 mm 90° | 14–80 | ◎ | ◎ | | ◎ | ◎ | ◎ | | | ○ | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | H30 H32 H34 |
| | | WEZ 17000 -E/ES/EL | | 15 mm 90° | 25–80 | | | | | | | | | | | | | | | | | | | H36 H38 H40 |
| | WEZR -E -M (New) | WEZR 11000-E, 17000-E | | 19–84mm 90° | 20–40, 40–50 | ◎ | ◎ | | ◎ | ◎ | ◎ | | | ○ | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | H42 H44 |
| | | WEZR 11000-M, 17000-M | | 27–29mm 90° | 32, 40 | | | | | | | | | | | | | | | | | | | H50 H52 |
| | WEX | WEX 1000-E/EL | AXMT0602.., AXMT1235.., AXMT1705.. | 5 mm 90° | 10–25 | ○ | | | ◎ | ◎ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | H56 |
| | | WEX 2000-E/EL | | 10 mm 90° | 14–63 | | | | | | | | | | | | | | | | | | | H57 |
| | | WEX 3000-E/EL | | 14 mm 90° | 25–63 | | | | | | | | | | | | | | | | | | | H58 |
| | WEX-M | WEX 2000-M | | 10 mm 90° | 16–40 | ○ | | | ◎ | ◎ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | H57 |
| | | WEX 3000-M | | 14 mm 90° | 25–40 | | | | | | | | | | | | | | | | | | | H58 |
| | WRX | WRX 2000-E/W | AXMT1235.. , AXMT1705.. | 19–36mm 90° | 20–40 | ○ | | | ◎ | ◎ | ○ | | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | H65 |
| | | WRX 3000-E/W | | 27–53mm 90° | 32–50 | | | | | | | | | | | | | | | | | | | H66 |

◎ : Preferred choice
○ : Suitable

| Application | Cutter Type | Series | Insert Type | Approach Angle / Max. Depth of Cut (mm) | Cutter Diameter (mm) | Application: Face Milling – General Purpose | Face Milling – Finishing | Face Milling – High Feed | Shoulder Milling | Groove Milling | Ramping | Chamfering | Drilling | Profiling | Profile Finishing | Work Material: P – Carbon Steel / Alloy Steel | P – Tempered Steel / Die Steel | M – Stainless Steel | K – Cast Iron / Ductile Cast Iron | N – Non-Ferrous Metal | N – Aluminium Alloy | S – Ti Alloy / Heat Resistant Alloy | H – Hardened Steel HRC 45–55 | Ref. Page |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Shoulder M. | MTIX (New)  | MTIX 16000 | XOMT1605..  | 13 mm 90° | 32 | ◎ | ◎ | | ◎ | ◎ | ◎ | | | | | | | ○ | | | | ◎ | | H69 |
| Multi-Purpose | WRCX  | WRCX 08000-E 10000-E | QPMT 0803../10T3../1204.. QPET 10T35../1204..  | 4–5 mm | 12–32 | ○ | | ○ | ○ | ○ | ◎ | | | ◎ | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | | H74 |
| | WRCX-M  | WRCX 08000-M 12000-M | | 4–6 mm | 20–40 | ○ | | ○ | ○ | ○ | ◎ | | | ◎ | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | | | H75 |
| | RSX  | RSX(F) 08000-ES 10000-ES 12000-ES | RDET0803..RDET10T3.. RDET1204..  | 4 mm / 5 mm / 6 mm | 20–32(ES) 40(M) | ○ | | ○ | ○ | ○ | ◎ | | | ◎ | | ◎ | ◎ | ◎ | ◎ | | | ◎ | | H76 H77 |
| | RSX-M  | RSX(F) 08000-M 10000-M 12000-M | | | | | | | | | | | | | | | | | | | | | | |
| Alumimium | WAX  | WAX 3000-E/EL | AECT1604.., AECT2206..  | 16–18 mm 90° | 20–40 | ○ | | | ◎ | ◎ | ◎ | | | ◎ | | | | | | ○ | ◎ | | | H62 H63 |
| | | WAX 4000-E/EL | | 22–24 mm 90° | 25–40 | | | | | | | | | | | | | | | | | | | |
| 3D Profiling | WBMR  | WBMR 2000 | ZNMT 1804100-C 2004100-S  | 20–47 mm | R10 (20)–R25 (50) | | | | | ◎ | | | | ◎ | | ◎ | ◎ | ◎ | ◎ | | | | | H71 |
| |  | WBMR 2000-L | | 30–69 mm | | | | | | | | | | | | | | | | | | | | |
| | WBMF  | WBMF 1000 | ZPGU 1551050  | 0,1–0,4 mm | R5 (10)–R15 (30) | | | | | ◎ | | | | ◎ | ◎ | ◎ | ◎ | ◎ | | | | | | H73 |
| Chamfering | WFXC-E  | WFXC 08000-E | SOMT0803../1204.. SOET0803../1204..  | 45° | 08–16 | | | | | | | ◎ | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | H79 |
| | | WFXC 12000-E | | | 25–32 | | | | | | | | | | | | | | | | | | | |
| | WFXC-M  | WFXC 08000-M | | 45° | 16 | | | | | | | ◎ | | | | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | H80 |
| | | WFXC 12000-M | | | 25–32 | | | | | | | | | | | | | | | | | | | |
| High Speed Non-Ferrous Milling | ANX  | ANXS 16000-E | ANB 1600R-L  | 3 mm 90° | 32–40 | ○ | ◎ | ◎ | ◎ | ○ | | | | | | | | | | ◎ | ◎ | | | H84 |
| | ANXS-M (New)  | ANXS 16000-E | ANB 1600...  | 3 mm 90° | 23–38 | ○ | ◎ | ◎ | ◎ | ○ | | | | | | | | | | ◎ | ◎ | | | H86 |

# Modular Tools



## General Features


Indexable head endmills are available in 10 types:

| | |
|---|---|
| **WEZ** | **MSX** |
| **WEX** | **RSX** |
| **WFX** | **WRXC** |
| **DMSW** | **WFXC** |
| **WFXH** | **ANXS** |

In addition to carbide arbors and steel arbors, the lineup of integrated BBT types enables a variety of combinations.

General-purpose grade applicable to any work material. Introducing the new grade ACU2500, which is applicable to a wide variety of processes and work materials such as steel, stainless steel and cast iron.

Suitable for milling with **long overhangs** when combined with carbide or steel arbors!




Easy to change screw-on endmill type WEX and carbide arbor

When combined with BBT integrated arbors, **high load milling** is supported.




RSX type + BBT30 integrated arbor

**Modular Head + Carbide Arbor**




Standard Shank Type Endmill





Note: Cutting conditions can vary according to cutter reach, rigidity of machine tool / workpiece etc.

## Screw Size and Mounting Cutter Size


| Screw CRKS | Applicable Cutter Size (DC) |
|---|---|
| M8 | Ø 16, Ø 18 |
| M10 | Ø 20, Ø 22 |
| M12 | Ø 24, Ø 28 |
| M16 | Ø 30, Ø 32, Ø 35, Ø 40 |

## Performance


● A Carbide Arbor improves feed rates, surface finish, sizing, and tool life.




● **Shoulder Milling Squareness**




Carbide Arbor Comparison ...




| | | |
|---|---|---|
| Work Material | : | C50 |
| Tool | : | WEX2025M12Z4 (ø D = 25, 4 teeth) |
| Cutting Conditions: | | $v_c$ = 100 m/min, $f_z$ = 0,1 mm/tooth |
| | | $a_p$ = 8 mm x 3 passes, $a_e$ = 2,0 mm, Equipment: M/C BT50 |




● = Euro stock
○ = Japan stock

Recommended Tightening Torque (N·m)

## BBT Integrated Type - Modular Tools Special Arbors







## BBT Integrated Arbor


Dimensions (mm)

| Cat. No. | Stock | CRKS | DCB | BD | L6 | LBX | L7 | LF* | Coolant Hole |
|---|---|---|---|---|---|---|---|---|---|
| BBT30- M8-50 | ❍ | M8 | 8,5 | 15,9 | 73 | 50 | 18 | 98 | Yes |
| M10-45 | ❍ | M10 | 10,5 | 19,9 | 68 | 45 | 20 | 98 | Yes |
| M12-40 | ❍ | M12 | 12,5 | 24,9 | 63 | 40 | 22 | 98 | Yes |
| M16-35 | ❍ | M16 | 17 | 31,9 | 58 | 35 | 24 | 98 | Yes |

* Overhang length for LF is with head mounted. Can also be used with BT30 special machines.

## Carbide and Steel Arbor




## Carbide Arbor

| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | CRKS | DCB | DMM | LF2 | L4 | L5 | LF* |
| MA 15 M08 L120C | ● | M8 | 8,5 | 15 | 120 | 10 | 18 | 145 |
| 15 M08 L160C | ● | M8 | 8,5 | 15 | 160 | 10 | 18 | 185 |
| MA 16 M08 L120C | ● | M8 | 8,5 | 16 | 120 | 10 | 18 | 145 |
| 16 M08 L160C | ● | M8 | 8,5 | 16 | 160 | 10 | 18 | 185 |
| MA 18 M10 L150C | ● | M10 | 10,5 | 18 | 150 | 10 | 20 | 180 |
| 18 M10 L200C | ● | M10 | 10,5 | 18 | 200 | 10 | 20 | 230 |
| MA 20 M10 L150C | ● | M10 | 10,5 | 20 | 150 | 10 | 20 | 180 |
| 20 M10 L200C | ❍ | M10 | 10,5 | 20 | 200 | 10 | 20 | 230 |
| MA 23 M12 L200C | ● | M12 | 12,5 | 23 | 200 | 10 | 22 | 235 |
| 23 M12 L250C | ● | M12 | 12,5 | 23 | 250 | 10 | 22 | 285 |
| MA 25 M12 L200C | ● | M12 | 12,5 | 25 | 200 | 10 | 22 | 235 |
| 25 M12 L250C | ● | M12 | 12,5 | 25 | 250 | 10 | 22 | 285 |
| MA 28 M16 L200C | ● | M16 | 17,0 | 28 | 200 | 10 | 24 | 240 |
| 28 M16 L300C | ● | M16 | 17,0 | 28 | 300 | 10 | 24 | 340 |
| MA 32 M16 L200C | ● | M16 | 17,0 | 32 | 200 | 10 | 24 | 240 |
| 32 M16 L300C | ● | M16 | 17,0 | 32 | 300 | 10 | 24 | 340 |

●*Modular Tool System




## Steel Arbor

| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | CRKS | DCB | DMM | LF2 | L4 | L5 | LF* |
| MA 16 M08 L120S | ● | M8 | 8,5 | 16 | 120 | 10 | 18 | 145 |
| MA 20 M10 L150S | ● | M10 | 10,5 | 20 | 150 | 10 | 20 | 180 |
| MA 25 M12 L200S | ● | M12 | 12,5 | 25 | 200 | 10 | 22 | 235 |
| MA 32 M16 L200S | ● | M16 | 17,0 | 32 | 200 | 10 | 24 | 240 |

## Identification of Catalogue No.

**MA 15 M08 L120 C**

- MA: Modular Arbor
- 15: Shank Diameter
- M08: Mounting Screw
- L120: Arbor Length
- C: Material (C: Carbide, S: Steel)

## Recommended Tightening Torque

| Screw | Wrench | | (N·m) |
|---|---|---|---|
| | W | S | |
| M 8 | 8 | 13 | 23 |
| M10 | 8 | 15 | 46 |
| M12 | 10 | 19 | 60 |
| M16 | 10 | 24 | 80 |



Notes about tightening the head:

- Refer to the Head Cat. No. chart on pages H18, H19, H35 and H37 to select the arbor size in the table above.
- Check the mounting screw size of the head and arbor beforehand.
- When attaching head to an arbor, follow the standard tighting torque in the table above.

# "Sumi Dual Mill" Face Mill
# DGC(EW) Type

Expansion

## General Milling for Steel and Cast Iron


| Rake Angle | | |
|---|---|---|
| | Radial | -10° |
| | Axial | -5° |

SNMU / SNEU: 6 mm, 45°

ONMU / ONEU: 3 mm, 45°

## ■ Body – Shank Type






## ■ Body

| Cat. No. | Stock | Dimensions (mm) DC | DCX | DMM | LH | LS | LF | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|
| DGC 13040 EW | ● | 40 (42,90) | 54 | 32 | 40 (38,44) | 85 | 125 | 3 | 0,7 |
| 13050 EW | ❍ | 50 (52,90) | 65 | 32 | 40 (38,44) | 85 | 125 | 3 | 0,9 |
| 13063 EW | ❍ | 63 (65,90) | 77 | 32 | 40 (38,44) | 85 | 125 | 4 | 1,1 |

( ) Figures in brackets indicate values for inserts of type ONMU

## ■ Identification Details

| DGC | 13 | 040 | EW |
|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Endmill Type Weldon |

## ■ Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | Cermet | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed/Light cut | KM MS | PM KM | P | | | K | K | | MS | | PM | |
| General Purpose | KM MS | PM KM | | PM | M | K | K | | MS | | P | |
| Roughing | KM MS | | | PM | PM | | | K | | MS | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | T4500A | Fig. |
| SNMU 13T6ANER L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 1 |
| 13T6ANER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 1 |
| 13T6ANER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 1 |
| 13T6ANER FL | ● | | ● | ● | ● | | ● | ● | | | | 2 |
| 13T6ANER FG | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 2 |
| SNEU 13T6ANER L | | | | | | | | | ● | ● | | 1 |
| 13T6ANER G | | | | | | | | | ● | ● | | 1 |
| 13T6ANER FL | | | | | | | | | ❍ | ❍ | | 2 |
| 13T6ANER FG | | | | | | | | | ● | ● | | 2 |
| XNEU 13T6ANEN W | ● | ❍ | | ● | | ❍ | | ● | | | ● | 3 |
| ONMU 05T6ANER L | ● | | ● | ● | ● | | ● | ● | | | | 4 |
| 05T6ANER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | | | | 4 |
| ONEU 05T6ANER L | | | | | | | | | ● | ● | | 4 |
| 05T6ANER G | | | | | | | | | ● | ● | | 4 |

Fig. 1





Fig. 2





Fig. 3








Fig. 4




**Attaching Octagonal Inserts**

Firmly align insert with supporting face, press down in the direction of the arrow and tighten the screw to fix the insert.




## ■ Spare Parts

| Shim | Shim Screw | L Seat Wrench | Insert Srew | Insert Wrench |
|---|---|---|---|---|
|  |  |  |  3,0 |  |
| DGCS 13 R | BW 0609 F | LH 040 | BFTX 0412 IP | TRDR 15 IP |

### Optional

| Insert Srew (*) |
|---|
|  |
| BFTX 0418 IP |

*Corners can be changed simply by loosening the screw. (Only suitable for DGC / DGCM types with body size ≥ Ø 80).

## ■ SNMU – Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (min/t) | Depth of Cut (mm) | Grade |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,10–**0,25**–0,40 | <4 | ACU2500 ACP200 ACP300 XCU2500 |
| | Alloyed Steel | ≤180 | 180–**250**–350 | 0,10–**0,30**–0,45 | <4 | |
| | Die Steel | 200–220 | 100–**150**–200 | 0,15–**0,25**–0,35 | <4 | |
| M | Stainless Steel | – | 160–**200**–250 | 0,15–**0,23**–0,30 | <3 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**200**–250 | 0,10–**0,25**–0,40 | <5 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Steel | – | 30–**50**–80 | 0,10–**0,20**–0,30 | <3 | ACU2500 ACM200 ACM300 |

## ■ ONMU – Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (min/t) | Depth of Cut (mm) | Grade |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,10–**0,30**–0,50 | <2 | ACU2500 ACP200 ACP300 XCU2500 |
| | Alloyed Steel | ≤180 | 180–**250**–350 | 0,10–**0,50**–0,50 | <2 | |
| | Die Steel | 200–220 | 100–**150**–200 | 0,15–**0,25**–0,30 | <2 | |
| M | Stainless Steel | – | 160–**200**–250 | 0,15–**0,23**–0,30 | <2 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**200**–250 | 0,10–**0,30**–0,50 | <2 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Steel | – | 30–**50**–80 | 0,10–**0,20**–0,30 | <2 | ACU2500 ACM200 ACM300 |

Min. – **Optimum** – Max.

● = Euro stock
○ = Japan stock

→ G6-G9

Recommended Tightening Torque (N·m)

# "Sumi Wave" Face Mill
# WGX (EW) Type


## General Milling for Steel and Cast Iron

| Rake Angle | | |
|---|---|---|
| | Radial | -20°–24° |
| | Axial | 20°–22° |

6 mm 45°

## Body – Shank Type






## Body – Dimensions

| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DMM | LH | LS | LF | |
| WGX 13032 EW | ❍ | 32 | 44 | 32 | 40 | 85 | 125 | 3 |
| 13040 EW | ❍ | 40 | 52 | 32 | 40 | 85 | 125 | 3 |
| 13050 EW | ❍ | 50 | 62 | 32 | 40 | 85 | 125 | 4 |
| 13063 EW | ❍ | 63 | 76 | 32 | 40 | 85 | 125 | 5 |

Inserts are not included.
ø32 mm cutters do not have a seat.

## Identification Details


| WGX | 13 | 032 | EW |
|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Endmill Type Weldon |

## Insert Shape Characteristics

Unique wiper edge shape for improved surface roughness

General-purpose
G type chipbreaker

Low-burr design
FG type chipbreaker




## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | Carb. | DLC | Cermet | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed/Light Cut | | | P | | | K | K | | M S | | K N | N | | |
| General Purpose | | | | P M | M | K | K | | M S | M S | | N | P M | |
| Roughing | | | | P M | P M | | | K | | M S | | | P | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | T4500A | |
| SEET 13T3AGFR-L | | | | | | | | | | | ❍ | ❍ | | 1 |
| SEET 13T3AGSR-L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | ● | 1 |
| 13T3AGSR-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | ● | 1 |
| SEMT 13T3AGSR-L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | 1 |
| 13T3AGSR-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | 1 |
| 13T3AGSR-H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | 1 |
| SEMT 13T3AGSR-FG | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | | | | 2 |
| XEEW 13T3AGER-WR | ● | ❍ | | ❍ | | ❍ | | ❍ | | | | | ❍ | 3 |

Fig. 1





Fig. 2







Fig. 3




## Spare Parts

| Applicable Cutters | Seat | Seat Screw | Insert Screw | Insesrt Wrench | N·m | Spanner (for Seat) |
|---|---|---|---|---|---|---|
| WGX 130__EW |  |  |  |  | |  |
| øD = 32 | – | – | BFTX 03512 IP | TRDR 15 IP | 3,0 | – |
| øD = 40–63 | WGCS 13 R | BW 0507 F | BFTX 03512 IP | TRDR 15 IP | 3,0 | LH 035 |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/tooth) | Grade |
|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,15–**0,20**–0,25 | ACU2500 ACP200 XCU2500 |
| | Soft Steel | ≤180 | 180–**265**–350 | 0,10–**0,25**–0,40 | |
| | Die Steel | 200–220 | 100–**150**–200 | 0,15–**0,20**–0,25 | |
| M | Stainless Steel | - | 160–**205**–250 | 0,15–**0,23**–0,30 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**175** –250 | 0,15–**0,23**–0,30 | ACU2500 ACK200 XCK2000 |
| N | Non Ferrous Alloy | - | 500–**750**–1000 | 0,15–**0,23**–0,30 | DL1000 |
| S | Exotic Alloy | - | 30 – **50**– 80 | 0,10–**0,20**–0,30 | ACU2500 ACM300 |

Minimum-**Optimum**-Maximum

→ G10/G11

# "Sumi Dual Mill"
# DMSW 08000 E(L)


New

| Rake angle | Radial | -7° to -10° |
|---|---|---|
| | Axial | -6° |

3 mm 15°



Fig 1




## Body (Shank Type)

Dimensions (mm)

| Cat. No. | Stock | DCX | DC | DMM | LH | LF | Number of teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| DMSW 08035E02 | ● | 35 | 18,6 | 32 | 50 | 150 | 2 | 0,85 | 1 |
| 08040E03 | ● | 40 | 23,5 | 32 | 50 | 150 | 3 | 0,86 | 1 |
| 08050E03-42 | ● | 50 | 33,4 | 42 | 50 | 150 | 3 | 1,51 | 1 |

Inserts are sold seperately.

## Body (Long Shank Type)

Dimensions (mm)

| Cat. No. | Stock | DCX | DC | DMM | LH | LF | Number of teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| DMSW 08035EL02 | ● | 35 | 18,6 | 32 | 60 | 210 | 2 | 1,21 | 1 |
| 08040EL03 | ● | 40 | 23,5 | 32 | 60 | 210 | 3 | 1,22 | 1 |
| 08050EL03-42 | ● | 50 | 33,4 | 42 | 50 | 250 | 3 | 2,54 | 1 |

Inserts are sold seperately.

## Parts

| Insert screw | | Wrench |
|---|---|---|
|  |  |  |
| BFTX0513IP | 5,0 | TRDR20IP |

## Identification Details

| DMSW | 08 | 050 | E | L | 03 | - | 42 |
|---|---|---|---|---|---|---|---|
| Cutter series | Insert size | Cutter diameter | Shank | Long shank type | Number of teeth | | Shank diameter |


## Inserts

Dimensions (mm)

| Application | Coated carbide | | | | |
|---|---|---|---|---|---|
| High speed / light cut | | P | | K | |
| General purpose | P K M S | P | P | K | K |
| Roughing | P K M S | | P | | K |

| Cat. No. | ACU2500 | ACP2000 | ACP3000 | ACK2000 | ACK3000 | IC | S | RE | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| WNMU 0807ZNER-G | ● | ● | ● | ● | ● | 13 | 7 | 1,6 | 1 |
| WNMU 0807ZNER-H | ● | ● | ● | | | 13 | 7 | 1,6 | 1 |

Fig 1




## Recommended Cutting Conditions

min.–optimum–max.

| ISO | Work material | Hardness | Cutting speed $v_c$ (m/min) | Feed rate $f_z$ (mm/t) |
|---|---|---|---|---|
| P | General steel | < 280 HB | 100–160–250 | 1,0–1,5–2,0 |
| P | Alloy steel | < 280 HB | 100–160–200 | 1,0–1,5–1,8 |
| P | Alloy steel | < 42 HRC | 100–150–180 | 0,8–1,0–1,2 |
| M | Stainless steel | – | 80–120–150 | 0,8–1,0–1,2 |
| K | Cast iron | – | 100–160–250 | 1,0–1,5–1,8 |
| H | Hardened steel | < 52 HRC | 80–100–120 | 0,3–0,5–0,7 |

The above figures are guidelines for use with BT50 machine tools at depth of cut ($a_p$) of 1,5 mm.
The above recommended cutting conditions may require adjustment depending on machine rigidity and workpiece rigidity.





● = Euro stock
❍ = Japan stock

→G63-G66

# DMSW 08000 M


## Modular Type

| Rake angle | | |
|---|---|---|
| | Radial | -11° to -13° |
| | Axial | -6° |

3 mm
15°



Fig 1




## Head

Dimensions (mm)

| Cat. No. | Stock | DCX | DC | DCSFMS | DCON | CRKS | OAL | LF | LS2 | L11 | H | Number of teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DMSW 08035M16Z2 | ● | 35 | 18,6 | 28,5 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,19 | 1 |
| 08040M16Z3 | ● | 40 | 23,5 | 28,5 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 3 | 0,21 | 1 |

Inserts are sold seperately.

## Parts

| Insert screw | | Wrench |
|---|---|---|
|  |  |  |
| BFTX0513IP | 5,0 | TRDR20IP |

## Identification Details

| DMSW | 08 | 040 | M16 | Z3 |
|---|---|---|---|---|
| Cutter series | Insert size | Cutter diameter | Mounting screw size | Number of teeth |


## Inserts

Dimensions (mm)

| Application | Coated carbide | | | | |
|---|---|---|---|---|---|
| High speed / light cut | | P | | K | |
| General purpose | P K M S | P | P | K | K |
| Roughing | P K M S | | P | | K |

| Cat. No. | ACU2500 | ACP2000 | ACP3000 | ACK2000 | ACK3000 | IC | S | RE | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| WNMU 0807ZNER-G | ● | ● | ● | ● | ● | 13 | 7 | 1,6 | 1 |
| WNMU 0807ZNER-H | ● | ● | ● | | | 13 | 7 | 1,6 | 1 |

Fig 1




## Recommended Cutting Conditions

min.–optimum–max.

| ISO | Work material | Hardness | Cutting speed $v_c$ (m/min) | Feed rate $f_z$ (mm/t) |
|---|---|---|---|---|
| P | General steel | < 280 HB | 100–160–250 | 1,0–1,5–2,0 |
| P | Alloy steel | < 280 HB | 100–160–200 | 1,0–1,5–1,8 |
| P | Alloy steel | < 42 HRC | 100–150–180 | 0,8–1,0–1,2 |
| M | Stainless steel | – | 80–120–150 | 0,8–1,0–1,2 |
| K | Cast iron | – | 100–160–250 | 1,0–1,5–1,8 |
| H | Hardened steel | < 52 HRC | 80–100–120 | 0,3–0,5–0,7 |

The above figures are guidelines for use with BT50 machine tools at depth of cut ($a_p$) of 1,5 mm.
The above recommended cutting conditions may require adjustment depending on machine rigidity and workpiece rigidity.


→ H5

→ G63-G66

# MSX Type

Ultra High Feed

Boosts Productivity – Cuts Costs



## Features

The Metal Slash Mill type MSX is a new multi function high shear milling cutter with ultra high feed capability suitable for face milling, slotting, plunging and helical boring. At 50GPa the ultra hard Super ZX coated inserts feature a sharp cutting edge which demonstrates extreme resistance to wear and heat massively boosting productivity and tool life.

The vibration free cutting action ensures accurate sizing, improved surface finish, and protection of the machine tool/workpiece from damage. Inserts are double clamped in wide chip gullets to maximise rigidity and chip evacuation with temperature at the cutting edge being easily controlled via an optional air blast through integral coolant holes.The MSX cutter is readily applied to general purpose machining across the P (steel) M (stainless) and K (cast iron) range of workpiece materials with impressive results.

## Advantages

**Integral Coolant Hole**


Otimised chip removal – massive chip avacuation pockets

**Wide Application Range**

Face milling, slotting, helical boring and plunging

**Low Cutting Force**

Unique insert shape reduces cutting force



Durable Cutter Body


Special alloyed steel with hard surface

**Double Clamp**

Secure insert clamping for stable cutting

## Application Range

**Roughing operation** (Carbon steel, $a_e$ = 30 %)




| | Face Milling | | Slotting | Helical Boring | Profiling |
|---|---|---|---|---|---|
| | General Condition | High Feed Condition | | | |
| **MSX** | ☺ | ☺☺☺ | ☺ | ☺☺☺ | – |
| **WRCX** | ☺☺☺ | ☺ | ☺ | ☺☺ | ☺☺ |

☺☺☺ excellent
☺☺ very good
☺ good

● = Euro stock
❍ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

# "METAL SLASH MILL"
# MSX 06000/08000 ES/EM/EW

1,0 mm 20° 1,5 mm 20°

Fig. 1






Fig. 2




## Body

For insert type : WDMT 0603 □□□□

| Cat. No. | Stock | Dimensions (mm) DCX | DMM | LH | LS | LF | No.of teeth | Fig. |
|---|---|---|---|---|---|---|---|---|
| MSX 06016 ES | ❑ | 16 | 16 | 30 | 80 | 110 | 2 | 1 |
| 06016 EM | ● | 16 | 16 | 70 | 80 | 150 | 2 | 1 |
| 06016 EM15 | ❑ | 16 | 15 | 30 | 120 | 150 | 2 | 1 |
| MSX 06017 EM | ❍ | 17 | 16 | 20 | 130 | 150 | 2 | 1 |
| MSX 06018 EM | ❍ | 18 | 16 | 20 | 130 | 150 | 2 | 1 |
| MSX 06020 ES | ● | 20 | 20 | 50 | 80 | 130 | 3 | 1 |
| 06020 EM | ● | 20 | 20 | 100 | 80 | 180 | 3 | 1 |
| 06020 EM19 | ❑ | 20 | 19 | 50 | 130 | 180 | 3 | 1 |
| MSX 06022 EM | ❍ | 22 | 20 | 30 | 150 | 180 | 3 | 1 |
| MSX 06025 ES | ● | 25 | 25 | 60 | 80 | 140 | 3 | 1 |
| 06025 ES24 | ❑ | 25 | 24 | 60 | 80 | 140 | 3 | 1 |
| 06025 EM | ● | 25 | 25 | 120 | 130 | 250 | 3 | 1 |
| 06025 EM24 | ❑ | 25 | 24 | 60 | 190 | 250 | 3 | 1 |
| MSX 06020 EW | ● | 20 | 20 | 50 | 80 | 130 | 3 | 1 |
| MSX 06025 EW | ● | 25 | 25 | 60 | 80 | 140 | 3 | 1 |

## Body

For insert type : WDMT 0804 □□□□

| Cat. No. | Stock | Dimensions (mm) DCX | DMM | LH | LS | LF | No.of teeth | Fig. |
|---|---|---|---|---|---|---|---|---|
| MSX 08020 ES | ● | 20 | 20 | 50 | 80 | 130 | 2 | 1 |
| 08020 EM | ● | 20 | 20 | 100 | 80 | 180 | 2 | 1 |
| 08020 EM19 | ❑ | 20 | 19 | 50 | 130 | 180 | 2 | 1 |
| MSX 08022 EM | ❍ | 22 | 20 | 30 | 150 | 180 | 2 | 1 |
| MSX 08025 ES | ● | 25 | 25 | 60 | 80 | 140 | 2 | 2 |
| 08025 EM | ● | 25 | 25 | 120 | 130 | 250 | 2 | 2 |
| 08025 EM24 | ❑ | 25 | 24 | 60 | 190 | 250 | 2 | 2 |
| MSX 08028 EM | ❑ | 28 | 25 | 40 | 210 | 250 | 2 | 2 |
| MSX 08032 ES | ❍ | 32 | 32 | 70 | 80 | 150 | 3 | 2 |
| 08032 EM | ❑ | 32 | 32 | 120 | 130 | 250 | 3 | 2 |
| MSX 08035 EM | ❍ | 35 | 32 | 50 | 200 | 250 | 3 | 2 |
| MSX 08020 EW | ● | 20 | 20 | 50 | 80 | 130 | 2 | 1 |
| MSX 08025 EW | ● | 25 | 25 | 60 | 80 | 140 | 2 | 2 |
| MSX 08032 EW | ● | 32 | 32 | 70 | 80 | 150 | 3 | 2 |

## Identification Details

| MSX | 06 | 016 | E | S |
|---|---|---|---|---|
| Cutter type | Insert size | Cutter Diameter | Shank Type | S: Short type with cylindrical shank<br>M: Long type with cylindrical shank<br>W: Short type with Weldon shank |

# "METAL SLASH MILL"
# MSX 12000/14000 ES/EM/EW

2,0 mm 20° 2,5 mm 20°



## Body

For insert type : WDMT 1205 □□□□

| Cat. No. | Stock | Dimensions (mm) DCX | DMM | LH | LS | LF | No.of teeth | Fig. |
|---|---|---|---|---|---|---|---|---|
| MSX 12032 ES | ● | 32 | 32 | 70 | 80 | 150 | 2 | 2 |
| 12032 EM | ● | 32 | 32 | 120 | 130 | 250 | 2 | 2 |
| MSX 12035 EM | ❍ | 35 | 32 | 50 | 200 | 250 | 2 | 2 |
| MSX 12040 ES | ❍ | 40 | 32 | 50 | 100 | 150 | 3 | 2 |
| 12040 EM | ❍ | 40 | 32 | 50 | 200 | 250 | 3 | 2 |
| MSX 12050 EM | ❑ | 50 | 42 | 50 | 200 | 250 | 4 | 2 |
| MSX 12032 EW | ● | 32 | 32 | 70 | 80 | 150 | 2 | 2 |


## Body

For insert type : WDMT 1406 □□□□

| Cat. No. | Stock | Dimensions (mm) DCX | DMM | LH | LS | LF | No.of teeth | Fig. |
|---|---|---|---|---|---|---|---|---|
| MSX 14040 ES | ❑ | 40 | 32 | 50 | 100 | 150 | 2 | 2 |
| 14040 EM | ❑ | 40 | 32 | 50 | 200 | 250 | 2 | 2 |
| MSX 14050 ES | ❑ | 50 | 42 | 50 | 100 | 150 | 3 | 2 |
| MSX 14050 EM | ❑ | 50 | 42 | 50 | 200 | 250 | 3 | 2 |
| 14063 ES | ❑ | 63 | 42 | 50 | 100 | 150 | 4 | 2 |
| MSX 14063 EM | ❑ | 63 | 42 | 50 | 200 | 250 | 4 | 2 |

## Inserts

| Application | Coated Carbide | | | |
|---|---|---|---|---|
| High Speed / Light cut | | | KH | |
| General Purpose | PM | PM | KH | |
| Roughing | PM | PM | | KH |




| Cat. No. | ACP200 | ACP300 | ACK200 | ACK300 | Dimensions (mm) IC | S | RE | Applicable Endmill |
|---|---|---|---|---|---|---|---|---|
| WDMT0603 ZDTR | ● | ● | ❍ | ● | 6,35 | 3,0 | 1,5 | MSX06000E□ |
| 0603 ZDTR-H | ● | ● | ❍ | ● | | | | |
| WDMT0804 ZDTR | ● | ● | | ● | 8,5 | 4,0 | 2,0 | MSX08000E□ |
| 0804 ZDTR-H | ● | ● | ❍ | ● | | | | |
| WDMT1205 ZDTR | ● | ● | | ● | 12 | 5,0 | 2,0 | MSX12000E□ |
| 1205 ZDTR-H | ● | ● | ❍ | ● | | | | |
| WDMT1406 ZDTR | ● | ● | ❍ | ● | 14 | 6,0 | 2,0 | MSX14000E□ |
| 1406 ZDTR-H | ● | ● | | ● | | | | |

ZDTR-H : Stronger cutting edge

## Spare Parts

| Insert Screw | N·m | Insert Wrench | Clamp | C Ring | Clamp Screw | Applicable Endmill MSX - E□ |
|---|---|---|---|---|---|---|
| BFTX 02505 IP | 1,5 | TRDR 08 IP | – | – | – | MSX 06000E□ |
| BFTX 0306 IP | 2,0 | TRDR 08 IP | – | – | – | MSX 08020E□, MSX 08022E□ |
| BFTX 0306 IP | 2,0 | TRDR 08 IP | CCH 3,5 | CR 03 | BFTX 03510 IP 08 | MSX 08025E□, MSX 08028E□, MSX 08032E□, MSX 08035E□ |
| BFTX 0409 IP | 3,0 | TRDR 15 IP | CCH 3,5 | CR 03 | BFTX 03510 IP 15 | MSX 12000E□ |
| BFTX 0511 IP | 5,0 | TRDR 20 IP | CCH 4,5 | CR 03 | BFTX 04513 IP 20 | MSX 14000E□ |

→ G67

1,0 mm 20°

High feed and high efficiency machining endmills




## Modular Type

1,5 mm 20° (MSX 08000M)


2,0 mm 20° (MSX 12000M)

High feed and high efficiency machining endmills






Axial rake angle: 8°
Radial rake angle: -3°– -8°




Axial rake angle: 8°
Radial rake angle: -3°– -8°

## Heads

For insert type : WDMT 0603

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| MSX 06016M08Z2 | ● | 16 | 8,5 | M8 | 42 | 25 | 5 | 17 | 8 | 13 | 2 |
| 06018M08Z2 | ❍ | 18 | 8,5 | M8 | 42 | 25 | 5 | 17 | 8 | 13 | 2 |
| MSX 06020M10Z3 | ● | 20 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 3 |
| 06022M10Z3 | ❑ | 22 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 3 |
| MSX 06025M12Z3 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 3 |

Inserts are not included.

## Heads

For insert type : WDMT 0804

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| MSX 08025M12Z2 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 |
| 08028M12Z2 | ❑ | 28 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 |
| MSX 08030M16Z3 | ❑ | 30 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |
| 08032M16Z3 | ● | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |
| MSX 08035M16Z3 | ❍ | 35 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |

Inserts are not included.

## Heads

For insert type : WDMT 1205


| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| MSX 12032M16Z2 | ● | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 2 |
| 12035M16Z2 | ❍ | 35 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 2 |
| MSX 12040M16Z3 | ● | 40 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |

Inserts are not included.

## Inserts

| Application | Coated Carbide | | | |
|---|---|---|---|---|
| General Purpose | PM | PM | KH | |
| Roughing | PM | PM | | KH |


| Cat. No. | ACP200 | ACP300 | ACK200 | ACK300 | Dimensions (mm) IC | S | RE | Applicable Endmill |
|---|---|---|---|---|---|---|---|---|
| WDMT 0603 ZDTR | ● | ● | ❍ | ● | 6,35 | 3,0 | 1,5 | MSX06000M□ |
| 0603 ZDTR-H | ● | ● | ❍ | ● | | | | |
| WDMT 0804 ZDTR | ● | ● | | ● | 8,5 | 4,0 | 2,0 | MSX08000M□ |
| 0804 ZDTR-H | ● | ● | ❍ | ● | | | | |
| WDMT 1205 ZDTR | ● | ● | | ● | 12 | 5,0 | 2,0 | MSX12000M□ |
| 1205 ZDTR-H | ● | ● | ❍ | ● | | | | |




H – Strong Cutting Edge

## Identification Details

| MSX | 06 | 016 | M08 | Z2 |
|---|---|---|---|---|
| Cutter type | Insert size | Diameter | Mounting screw | No. of teeth |




## Spare Parts

| Clamp Screw | | Insert Wrench | Clamp | C Ring | Insert Screw | Applicable Endmill |
|---|---|---|---|---|---|---|
| | N·m | | | | | |
| BFTX 02505 IP | 1,5 | TRDR 08 IP | – | – | – | MSX 06016M – MSX 06025M |
| BFTX 0306 IP | 2,0 | TRDR 08 IP | CCH 3,5 | CR 03 | BFTX 03510 IP 08 | MSX 08025M – MSX 08035M |
| BFTX 0409 IP | 3,0 | TRDR 15 IP | CCH 3,5 | CR 03 | BFTX 03510 IP 15 | MSX 12032M – MSX 12040M |





● = Euro stock
❍ = Japan stock

❑ = Delivery on request

N·m Recommended Tightening Torque (N·m)

## Recommended Cutting Conditions

| Work Material | | Coated Carbide Grade | Cutting Speed $v_c$ (m/min) | Insert Cat. No. | Endmill Type (Ø DC) 16 $a_p$ (mm) | 16 Feed rate (mm/tooth) | 20 $a_p$ (mm) | 20 Feed rate (mm/tooth) | 25 $a_p$ (mm) | 25 Feed rate (mm/tooth) | 32 $a_p$ (mm) | 32 Feed rate (mm/tooth) | 40 $a_p$ (mm) | 40 Feed rate (mm/tooth) | Shell Type (Ø DC) 50–66 $a_p$ (mm) | 50–66 Feed rate (mm/tooth) | 80–100 $a_p$ (mm) | 80–100 Feed rate (mm/tooth) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| P | General Steel (Below HB200) | ACP200 | 100–**150**–200 | WDMT 0603 | 0,8 | 0,8 | 0,8 | 0,8 | 0,8 | 0,8 | – | – | – | – | – | – | – | – |
| | | | | WDMT 0804 | – | – | 1,0 | 1,0 | 1,0 | 1,2 | 1,0 | 1,2 | – | – | – | – | – | – |
| | | | | WDMT 1205 | – | – | – | – | – | – | 1,2 | 1,4 | 1,2 | 1,4 | 1,2 | 1,4 | – | – |
| | | | | WDMT 1406 | – | – | – | – | – | – | – | – | 1,5 | 1,5 | 1,5 | 1,5 | 1,5 | 1,5 |
| P | Alloy Steel (Below HRC45) | ACP200 | 80–**130**–180 | WDMT 0603 | 0,7 | 0,8 | 0,7 | 0,8 | 0,7 | 0,8 | – | – | – | – | – | – | – | – |
| | | | | WDMT 0804 | – | – | 0,8 | 1,0 | 0,8 | 1,2 | 0,8 | 1,2 | – | – | – | – | – | – |
| | | | | WDMT 1205 | – | – | – | – | – | – | 1,0 | 1,4 | 1,0 | 1,4 | 1,0 | 1,4 | – | – |
| | | | | WDMT 1406 | – | – | – | – | – | – | – | – | 1,3 | 1,5 | 1,3 | 1,5 | 1,3 | 1,5 |
| M | Stainless Steel X5CRNI1810, Others | ACP300 | 80–**120**–150 | WDMT 0603 | 0,8 | 0,7 | 0,8 | 0,7 | 0,8 | 0,7 | – | – | – | – | – | – | – | – |
| | | | | WDMT 0804 | – | – | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 | – | – | – | – | – | – |
| | | | | WDMT 1205 | – | – | – | – | – | – | 1,2 | 1,2 | 1,2 | 1,2 | 1,2 | 1,2 | – | – |
| | | | | WDMT 1406 | – | – | – | – | – | – | – | – | 1,5 | 1,3 | 1,5 | 1,3 | 1,5 | 1,3 |
| K | Cast Iron GG, GGG | ACK300 | 100–**150**–200 | WDMT 0603 | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 | – | – | – | – | – | – | – | – |
| | | | | WDMT 0804 | – | – | 1,0 | 1,2 | 1,0 | 1,4 | 1,0 | 1,4 | – | – | – | – | – | – |
| | | | | WDMT 1205 | – | – | – | – | – | – | 1,2 | 1,5 | 1,2 | 1,5 | 1,2 | 1,5 | – | – |
| | | | | WDMT 1406 | – | – | – | – | – | – | – | – | 1,5 | 1,8 | 1,5 | 1,8 | 1,5 | 1,8 |
| H | Hardened Steel (Below HRC50) | ACK300 | 40–**80**–100 | WDMT 0603 | 0,5 | 0,5 | 0,5 | 0,5 | 0,5 | 0,5 | – | – | – | – | – | – | – | – |
| | | | | WDMT 0804 | – | – | 0,5 | 0,6 | 0,5 | 0,8 | 0,5 | 0,8 | – | – | – | – | – | – |
| | | | | WDMT 1205 | – | – | – | – | – | – | 0,6 | 1,0 | 0,6 | 1,0 | 0,6 | 1,0 | – | – |
| | | | | WDMT 1406 | – | – | – | – | – | – | – | – | 1,0 | 1,2 | 1,0 | 1,2 | 1,0 | 1,2 |

| Insert Cat. No. | Max $a_p$ | RE |
|---|---|---|
| WDMT 0603.... | 1,0 | 1,5 |
| WDMT 0804.... | 1,5 | 2,0 |
| WDMT 1205.... | 2,0 | 2,0 |
| WDMT 1406.... | 2,5 | 2,0 |

- The above recommended cutting conditions may require adjustment according to machine rigidity and work rigidity.
  The above figures are guidelines for use with the BT50 machine tool.
- The above cutting conditions assume a tool overhang length of L/D = 3 (i.e. overhang length is 3 times tool diameter) or less.
  When tool overhang is **more than L/D = 3 and less than or equal L/D = 5**, settings should be adjusted to approximately **70 to 80 %** of those indicated in the above cutting conditions (i.e. $a_p$ and Feed Rate).
  When tool overhang is **more than L/D = 5 and less than or equal L/D = 8**, settings should be adjusted to approximately **50 to 60 %** of those indicated in the above cutting conditions (i.e. $a_p$ and Feed Rate).


## Information for Programming

For machine programming, please use the theoretical corner radius (R) shown in the list.
Maximum depth (d) between theoretical radius and actual profile will be left on the finished surface, as shown below.




| Body | Insert | Theoretical Radius (R) | Remaining Depth (d) |
|---|---|---|---|
| MSX **06**000 | WDMT **06**03.... | 2,0 | 0,403 |
| MSX **08**000 | WDMT **08**04.... | 2,5 | 0,593 |
| MSX **12**000 | WDMT **12**05.... | 3,0 | 1,030 |
| MSX **14**000 | WDMT **14**06.... | 3,5 | 1,219 |

## Plunging and Helical Boring




| Cutter Ø | WDMT0603ZDTR $a_p$: max 1,0 Ramping α max. | Helical boring min. øB | Helical boring max. øB | WDMT0804ZDTR $a_p$: max 1,5 Ramping α max. | Helical boring min. øB | Helical boring max. øB | WDMT1205ZDTR $a_p$: max 2,0 Ramping α max. | Helical boring min. øB | Helical boring max. øB | WDMT1406ZDTR $a_p$: max 2,5 Ramping α max. | Helical boring min. øB | Helical boring max. øB |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| **16** | **6°00'** | **21** | **31** | | | | | | | | | |
| 17 | 5°00' | 23 | 33 | | | | | | | | | |
| 18 | 4°30' | 25 | 35 | | | | | | | | | |
| **20** | **3°30'** | **29** | **39** | **7°30'** | **25** | **38** | | | | | | |
| 22 | 3°00' | 33 | 43 | 5°30' | 29 | 42 | | | | | | |
| **25** | **2°00'** | **39** | **48** | **4°00'** | **35** | **48** | | | | | | |
| 28 | | | | 3°00' | 41 | 54 | | | | | | |
| **32** | | | | **2°30'** | **49** | **62** | **6°30'** | **42** | **63** | | | |
| 35 | | | | 2°00' | 55 | 68 | 5°00' | 48 | 69 | | | |
| **40** | | | | **1°30'** | **65** | **78** | **4°00'** | **58** | **79** | **6°00'** | **53** | **78** |
| **50** | | | | | | | **2°30'** | **78** | **99** | **3°30'** | **73** | **98** |
| **63** | | | | | | | **2°00'** | **103** | **124** | **2°00'** | **99** | **124** |
| 66 | | | | | | | 1°30' | 109 | 130 | 1°45' | 105 | 130 |
| **80** | | | | | | | | | | **1°30'** | **133** | **158** |
| **100** | | | | | | | | | | **1°00'** | **173** | **198** |

# WFXH Type

Expansion



## General Features

WaveMill WFXH type is a high efficiency, multi-purpose cutter, that uses the WFX series inserts for high-feed roughing and a variety of processes.

## Characteristics

Stable, high-efficiency milling with superior cutting edge sharpness.
Supports various types of processes (ramping and helical milling).
Able to use the selection of inserts from the WFX series.

## Notes on Corner Finishing - Remaining Material

Actual machined corners will have uncut and overcut portions due to the shape of the inserts.

Fig. 1






Fig. 2




### WFXH 08000 Type


| Programmed Corner R | SOMT 08○○04-□ | | | SOMT 08○○08-□ | | | SOMT 08○○12-□ | | |
|---|---|---|---|---|---|---|---|---|---|
| | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape |
| 2,0 | 1,41 | 0 | Fig. 1 | 1,30 | 0 | Fig. 1 | 1,21 | 0 | Fig. 1 |
| 2,5 | 1,30 | 0,02 | Fig. 2 | 1,19 | 0,01 | Fig. 2 | 1,09 | 0 | Fig. 2 |
| 3,0 | - | - | - | - | - | - | 0,98 | 0,05 | Fig. 2 |


### WFXH 12000 Type

| Programmed Corner R | SOMT 12○○04-□ | | | SOMT 12○○08-□ | | | SOMT 12○○12-□ | | | SOMT 12○○16-□ | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape | Uncut Portion | Overcut Portion | Shape |
| 2,0 | 2,58 | 0 | Fig. 1 | 2,48 | 0 | Fig. 1 | 2,37 | 0 | Fig. 1 | 2,25 | 0 | Fig. 1 |
| 2,5 | 2,47 | 0 | Fig. 1 | 2,37 | 0 | Fig. 1 | 2,25 | 0 | Fig. 1 | 2,14 | 0 | Fig. 1 |
| 3,0 | 2,36 | 0 | Fig. 1 | 2,26 | 0 | Fig. 1 | 2,14 | 0 | Fig. 1 | 2,11 | 0 | Fig. 1 |
| 3,5 | 2,24 | 0,01 | Fig. 2 | 2,14 | 0 | Fig. 1 | 2,03 | 0 | Fig. 1 | 1,91 | 0 | Fig. 1 |
| 4,0 | - | - | - | 2,03 | 0,04 | Fig. 2 | 1,91 | 0,03 | Fig. 2 | 1,8 | 0,01 | Fig. 2 |

## Minimum Cutting Diameter


Minimum cutting diameter (DCN) will depend on the insert that is used. Using an insert with a large nose radius is recommended for the WFXH type.








| Body Cat. No. | DC | DCN based on insert nose | | | |
|---|---|---|---|---|---|
| | | R0,4 | R0,8 | R1,2 | R1,6 |
| WFXH 08025 M | 25 | 9,69 | 9,48 | 9,27 | - |
| 08032 M | 32 | 16,6 | 16,4 | 16,2 | - |
| WFXH 12040 M | 40 | 15,8 | 15,5 | 15,3 | 15,1 |

## Taper Cutting and Helical Milling




Minimum and Maximum Diameters




Ramping Angle

| Insert Cat. No. | DC | Helical Millilng | | Taper Cutting |
|---|---|---|---|---|
| | | Min. | Max. | Max. Ramping Angle |
| SOMT 08○○04-□ | 25 | 35 | 49 | 1°30‘ |
| | 32 | 49 | 63 | 0°30‘ |
| SOMT 08○○08-□ | 25 | 35 | 48 | 3° |
| | 32 | 49 | 62 | 1°30‘ |
| SOMT 08○○12-□ | 25 | 34 | 47 | 4°30‘ |
| | 32 | 48 | 61 | 2°30‘ |
| SOMT 12○○04-□ | 40 | 56 | 79 | 1° |
| SOMT 12○○08-□ | 40 | 56 | 78 | 1°30‘ |
| SOMT 12○○12-□ | 40 | 55 | 77 | 2°30‘ |
| SOMT 12○○16-□ | 40 | 55 | 76 | 3°30‘ |





● = Euro stock
❍ = Japan stock

→ G68-G71


Recommended Tightening Torque (N·m)

Expansion


## Modular Type




| Rake Angle | | |
|---|---|---|
| | Radial | -6° |
| | Axial | 6° |



(08000M Type)



(12000M Type)




## Head

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | | |
| WFXH08025M12Z2 | ❍ | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 | 0,1 |
| 08032M12Z3 | ❍ | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 | 0,2 |

Inserts are not included.

## Identification Details

| WFX | 08 | 020 | M10 | Z2 |
|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Screw Size | No. of Teeth |

## Head

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | | |
| WFXH12040M12Z3 | ❍ | 40 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 | 0,2 |

Inserts are not included.




## Inserts

| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | | | P | | | K | K | | | | | | | | |
| General Purpose | | | | P | P | K | K | | | | | N | P | | |
| Roughing | | | | P | P | | | K | | | | N | P | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCU2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | T4500Z | RE | Fig. |
| SOMT 080304 PZER L | ● | ❍ | ● | ● | ❍ | ❍ | ❍ | ● | ● | ● | – | – | | 0,4 | 1 |
| 080308 PZER L | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 | 1 |
| SOMT 080304 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,4 | 1 |
| 080308 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 | 1 |
| 080312 PZER G | ● | | ● | ● | ● | | | ● | ● | ● | – | – | | 1,2 | 1 |
| SOMT 080308 PZER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 | 1 |
| 080312 PZER H | ● | | ● | ● | ● | | ❍ | ● | | ● | – | – | | 1,2 | 1 |
| SOET 080304 PZER G | ● | | | | ❍ | | | ● | ● | | – | – | ❍ | 0,4 | 1 |
| 080308 PZER G | ● | | | ❍ | | | ● | | | ● | – | – | ❍ | 0,8 | 1 |
| 080312 PZER G | ● | | | ● | ❍ | | | ● | ❍ | ❍ | – | – | ❍ | 1,2 | 1 |
| SOET 080302 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | | 0,2 | 1 |
| 080304 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | | 0,4 | 1 |
| 080308 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | | 0,8 | 1 |
| SOMT 120408 PDER L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 | 2 |
| SOMT 120404 PDER G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,4 | 2 |
| 120408 PDER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | ❍ | 0,8 | 2 |
| 120412 PDER G | ● | | ❍ | ● | ❍ | | ● | ❍ | ❍ | ● | – | – | | 1,2 | 2 |
| 120416 PDER G | ● | | ● | ● | ● | | ❍ | ❍ | ❍ | | – | – | | 1,6 | 2 |
| SOMT 120408 PDER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | | 0,8 | 2 |
| SOET 120408 PDFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | | 0,8 | 2 |

Fig. 1






Fig. 2




## Spare Parts

| Applicable Cutter | Screw | | Insert Wrench |
|---|---|---|---|
| | | N·m | |
| WFXH08000M | BFTX0306IP | 2,0 | TRDR08IP |
| WFXH12000M | BFTX03512IP | 3,0 | TRDR15IP |

## Recommended Cutting Conditions

| ISO | Work Material | Grade | Cutting Speed ($v_c$ (m/min)) | Insert Cat. No. | Ø 25 | | Ø 32 | | Ø 40 | | Ø 50 | | Ø 63 | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | $a_p$ (mm) | $f_z$ (mm/t) | $a_p$ (mm) | $f_z$ (mm/t) | $a_p$ (mm) | $f_z$ (mm/t) | $a_p$ (mm) | $f_z$ (mm/t) | $a_p$ (mm) | $f_z$ (mm/t) |
| P | General Steel <200HB | ACP200 | 100–**150**–200 | SOMT08 | 0,8 | 0,8 | 0,8 | 0,8 | 0,8 | 0,8 | 0,8 | 0,8 | 0,8 | 0,8 |
| | | | | SOMT12 | - | - | - | - | 1,0 | 1,0 | | | | |
| | Alloy Steel <HRC45 | ACP200 | 80–**130**–180 | SOMT08 | 0,7 | 0,8 | 0,7 | 0,8 | 0,7 | 0,8 | 0,7 | 0,8 | 0,7 | 0,8 |
| | | | | SOMT12 | - | - | - | - | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 |
| M | Stainless Steel (X5CrNiS18 10, other) | ACM300 | 80–**120**–150 | SOMT08 | 0,8 | 0,7 | 0,8 | 0,7 | 0,8 | 0,7 | 0,8 | 0,7 | 0,8 | 0,7 |
| | | | | SOMT12 | - | - | - | - | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 |
| K | Cast Iron FC, FCD | ACK300 | 100–**150**–200 | SOMT08 | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 | 0,8 | 1,0 |
| | | | | SOMT12 | - | - | - | - | 1,0 | 1,2 | 1,0 | 1,2 | 1,0 | 1,2 |
| H | Hardened Steel <HRC50 | ACK300 | 40–**80**–100 | SOMT08 | 0,5 | 0,5 | 0,5 | 0,5 | 0,5 | 0,5 | 0,5 | 0,5 | 0,5 | 0,5 |
| | | | | SOMT12 | - | - | - | - | 0,6 | 0,8 | 0,6 | 0,8 | 0,6 | 0,8 |

The above recommended cutting conditions may require adjustment according to machine rigidity and work rigidity. The above figures are guidelines for use with the BT50 machine tool.
The above conditions assume a tool overhang length of L/D = 3 (i.e. overhang length is 3 times tool diameter) or less.
When tool overhang is more than L/D = 3 and less or equal L/D = 5, settings should be adjusted to approximately 70 % to 80 % of those indicated in the above cutting conditions (i.e. ap and ft).
When tool overhang is more than L/D = 5 and less or equal L/D = 8, settings should be adjusted to approximately 50 % to 60 % of those indicated in the above cutting conditions (i.e. ap and ft).

Expansion

## General Features

The Sumi Dual Mill DFC type employs cost effective double-sided inserts for high toughness and enhanced accuracy.
The double-side inserts are flexible and reduces costs.



## Large Line-up

- Diameter from Ø 25 mm to Ø 200 mm
- Available as standard, fine and extra-fine pitch
- Bore diameter: metric
- Insert geometry: L, G, GS, H

## Cutter Body


| Type | | Cat. No. | Diameter (mm) | No. of Teeth | Image |
|---|---|---|---|---|---|
| Shank | Standard Pitch | DFC 09000 E | Ø 25 – Ø 80 | 2–5 |  |
| | Fine Pitch | DFCM 09000 E | Ø 32 – Ø 80 | 3–7 | |
| Shell | Standard Pitch | DFC 09000 RS | Ø 50 – Ø 200 | 4–10 |  |
| | Fine Pitch | DFCM 09000 RS | Ø 50 – Ø 200 | 5–16 | |
| →G22-G25 | Extra-Fine Pitch | DFCF 09000 RS | Ø 50 – Ø 200 | 6–20 | |





## New Insert Design Provides Excellent Machining Accuracy

### Inserts


| Cat. No. | RE0,4 | RE0,8 | RE1,2 | RE1,6 |
|---|---|---|---|---|
| XNMU0606__PNER-L | ● | ● | | |
| XNMU0606__PNER-G | ● | ● | ● | ● |
| Expansion XNMU0606__PNER-GS | ● | ● | ● | ● |
| XNMU0606__PNER-H | | ● | ● | ● |

### Chipbreaker Selection Map




| Work Material | P M K S | | | |
|---|---|---|---|---|
| Chipbreaker | L type | G type | GS type | H type |
| |  |  |  |  |
| Applications | Light cutting | General purpose to interrupted milling | Shoulder milling | Heavy cutting |
| Cutting edge geometry |  30° | 0,1 mm  20° | 0,1 mm  20° | 0,15 mm  20° |
| Features | Low rigidity milling, reduction of burrs | Face milling | Shoulder milling | Roughing, heavy interrupted and hardness steel milling |

## Stable and High Cutting Performance Combined with High Toughness






● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)


Expansion

## Body – Shank Type

| Rake Angle | Radial | -9° |
|---|---|---|
| | Axial | -5° |

Max. $a_p$: 6 mm






## Body – Dimensions

### DFC type, Standard Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | |
| DFC 09025E | ● | 25 | 25 | 40 | 80 | 120 | 2 |
| DFC 09032E | ● | 32 | 32 | 50 | 80 | 130 | 2 |
| 09040E | ● | 40 | 32 | 50 | 80 | 130 | 3 |
| 09050E | ● | 50 | 32 | 50 | 80 | 130 | 3 |
| DFC 09050E-42 | | 50 | 42 | 50 | 100 | 150 | 3 |
| DFC 09063E | ● | 63 | 32 | 50 | 80 | 130 | 4 |
| DFC 09063E-42 | | 63 | 42 | 50 | 100 | 150 | 4 |
| DFC 09080E | ● | 80 | 32 | 50 | 80 | 130 | 5 |
| DFC 09080E-42 | | 80 | 42 | 50 | 100 | 150 | 5 |

### DFCM type, Medium Pitch


| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | |
| DFCM 09032E | ● | 32 | 32 | 50 | 80 | 130 | 3 |
| 09040E | ● | 40 | 32 | 50 | 80 | 130 | 4 |
| 09050E | ● | 50 | 32 | 50 | 80 | 130 | 5 |
| DFCM 09050E-42 | | 50 | 42 | 50 | 100 | 150 | 5 |
| DFCM 09063E | ● | 63 | 32 | 50 | 80 | 130 | 6 |
| DFCM 09063E-42 | | 63 | 42 | 50 | 100 | 150 | 6 |
| DFCM 09080E | ● | 80 | 32 | 50 | 80 | 130 | 7 |
| DFCM 09080E-42 | | 80 | 42 | 50 | 100 | 150 | 7 |

## Identification Details

| DFC | M | 09 | 050 | E |
|---|---|---|---|---|
| Cutter Series | M: Medium | Insert Size | Cutter Diameter | Shank Type |

## Inserts

| Application | Coated Carbide | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | P M S | P M | P M | | | K | K | | M S | | |
| General Purpose Cutting | P M S | P M | P M | P M | | K | K | | M S | M S | |
| Rough Cutting | P M S | | | P M | P M | | | K | | M S | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| XNMU 060604 PNER-L | ● | ❍ | | ● | ● | ❍ | | ● | | ● | 0,4 |
| 060608 PNER-L | ● | ❍ | | ● | ● | ❍ | | ● | | ● | 0,8 |
| XNMU 060604 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,4 |
| 060608 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 060612 PNER-G | ● | | ● | ● | ● | | ● | ● | ● | ● | 1,2 |
| 060616 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ● | ● | 1,6 |
| XNMU 060604 PNER-GS | ❍ | | ● | ● | ● | | | | ● | ● | 0,4 |
| 060608 PNER-GS | ❍ | ❍ | ● | ● | ● | ❍ | | | ● | ● | 0,8 |
| 060612 PNER-GS | ❍ | | ❍ | ❍ | ❍ | | | | ❍ | ❍ | 1,2 |
| 060616 PNER-GS | ❍ | | ❍ | ❍ | ❍ | | | | ❍ | ❍ | 1,6 |
| XNMU 060608 PNER-H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 060612 PNER-H | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,2 |
| 060616 PNER-H | ● | | ❍ | ● | ❍ | | ❍ | ● | ❍ | ● | 1,6 |




## Spare Parts

| Screw | Wrench |
|---|---|
| BFTX03512IP | TRDR15IP 5,0 N·m |

## Recommemded Cutting Conditions

Min.–**Optimum**–Max.

| ISO | Work-material | Hardness (HB) | Cutting Speed (m/min) | Feed Rate | Depth of Cut (mm) | Grade |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,10–**0,20**–0,30 | < 6 | ACU2500 ACP200 ACP300 XCU2500 |
| | Soft Steel | ≤180 | 180–**250**–350 | 0,15–**0,25**–0,35 | < 6 | |
| | Die Steel | 200–220 | 100–**150**–200 | 0,10–**0,18**–0,25 | < 4 | |
| M | Stainless Steel | – | 160–**205**–250 | 0,12–**0,18**–0,25 | < 6 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**175**–250 | 0,10–**0,20**–0,30 | < 6 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Alloy | – | 30–**50**–80 | 0,10–**0,20**–0,30 | < 6 | ACU2500 ACM200 ACM300 |

## Applications and Recommended Chipbreakers

Face milling **G**



Shoulder milling **GS**



Shot milling



Side face milling **G, GS**



# "Sumi Wave" Shoulder Mill
# WFX (M) 08000 E


Expansion

# "Sumi Wave" Shoulder Mill
# WFX 08000 M

## Body - Shank Type



WFX08000E




## Modular Type


| Rake Angle | | |
|---|---|---|
| | Radial | -6° |
| | Axial | 12° |

6 mm

90°



WFX08000M




## Body - WFX_E, Standard Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | |
| WFX 08020 E-16 | ● | 20 | 16 | 30 | 80 | 110 | 2 |
| WFX 08020 E | ● | 20 | 20 | 30 | 80 | 110 | 2 |
| 08022 E | ● | 22 | 20 | 30 | 90 | 120 | 2 |
| WFX 08025 E-20 | ● | 25 | 20 | 30 | 90 | 120 | 2 |
| WFX 08025 E | ● | 25 | 25 | 30 | 90 | 120 | 2 |
| 08028 E | ● | 28 | 25 | 30 | 90 | 120 | 2 |
| 08030 E | ● | 30 | 25 | 30 | 90 | 120 | 3 |
| WFX 08032 E | ● | 32 | 32 | 30 | 90 | 120 | 3 |
| 08033 E | ● | 33 | 32 | 30 | 90 | 120 | 3 |
| 08040 E | ● | 40 | 32 | 30 | 90 | 120 | 3 |
| 08050 E | ● | 50 | 32 | 30 | 90 | 120 | 4 |
| 08063 E | ● | 63 | 32 | 30 | 90 | 120 | 5 |

Inserts are not included.

## Body - WFXM_E, Medium Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | |
| WFXM 08025 E | ● | 25 | 25 | 30 | 90 | 120 | 3 |
| WFXM 08032 E | ● | 32 | 32 | 30 | 90 | 120 | 4 |
| 08040 E | ● | 40 | 32 | 30 | 90 | 120 | 4 |
| 08050 E | ● | 50 | 32 | 30 | 90 | 120 | 5 |
| 08063 E | ● | 63 | 32 | 30 | 90 | 120 | 6 |

Inserts are not included.

## Identification Details

| WFX | M | 08 | 025 | E |
|---|---|---|---|---|
| Cutter Series | M: Medium | Insert Size | Cutter Diameter | Endmill Type |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Cutting Speed | Feed Rate | DOC | Grades |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,08–**0,12**–0,18 | <6 | ACU2500 ACP200 ACP300 XCU2500 |
| P | Soft Steel | ≤180 | 180–**250**–350 | 0,10–**0,15**–0,20 | <6 | |
| P | Die Steel | 200–220 | 100–**150**–200 | 0,08–**0,12**–0,18 | <4 | |
| M | Stainless Steel | - | 160–**200**–250 | 0,10–**0,15**–0,20 | <6 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**175**–250 | 0,10–**0,15**–0,20 | <6 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| N | Non Ferrous Metal | - | 300–**500**–1000 | 0,10–**0,15**–0,20 | <6 | H1 DL1000 |
| S | Exoric Alloy | - | 30–**50**–80 | 0,08–**0,13**–0,18 | <6 | ACU2500 ACM200 ACM300 |


Min. - **Optimum** - Max.

## Head

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| WFX 08020 M10Z2 | ● | 20 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 2 |
| 08022 M10Z2 | ● | 22 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 2 |
| WFX 08025 M12Z2 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 |
| 08028 M10Z2 | ● | 28 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 |
| WFX 08030 M16Z3 | ● | 30 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |
| 08032 M16Z3 | ● | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |
| 08040 M16Z3 | ● | 40 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |

## Identification Details

| WFX | 08 | 020 | M10 | Z2 |
|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Screw Size | No. of Teeth |




## Inserts

Dimensions (mm)

Fig. 3






Fig. 4
Wiper Insert




| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | KPMS | KPM | P | | | K | K | | MS | | KN | N | | |
| General Purpose | KPMS | KPM | | PM | PM | K | K | | MS | MS | | N | | |
| Roughing | KPMS | | | PM | PM | | | K | | MS | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | RE | Fig. |
| SOMT 080304 PZER L | ● | ❍ | ● | ● | ❍ | ❍ | ❍ | ● | ● | ● | – | – | 0,4 | 3 |
| 080308 PZER L | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| SOMT 080304 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,4 | 3 |
| 080308 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| 080312 PZER G | ● | | ● | ● | ● | | ❍ | ● | ● | ● | – | – | 1,2 | 3 |
| SOMT 080308 PZER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| 080312 PZER H | ● | | ● | ● | ● | | ❍ | ● | ❍ | ● | – | – | 1,2 | 3 |
| SOET 080304 PZER G | ● | | ❍ | ❍ | ❍ | | ❍ | ● | ● | ❍ | – | – | 0,4 | 3 |
| 080308 PZER G | ● | | ❍ | ❍ | ❍ | | ❍ | ● | ● | ❍ | – | – | 0,8 | 3 |
| 080312 PZER G | ● | | ❍ | ● | ❍ | | ❍ | ● | ❍ | ❍ | – | – | 1,2 | 3 |
| SOET 080302 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,2 | 3 |
| 080304 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,4 | 3 |
| 080308 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,8 | 3 |
| XOEW 080308 PZTR W | ● | – | – | – | – | – | | ● | | | – | – | 0,8 | 4 |

## Spare Parts

| Screw | | Wrench |
|---|---|---|
|  |  |  |
| BFTX0306IP | 2,0 | TRDR08IP |

# "Sumi Wave" Shoulder Mill
# WFX (F) 12000 E


## Body - Shank Type

| Rake Angle | | |
|---|---|---|
| | Radial | -8° |
| | Axial | 8° |

10mm, 90°



WFX12000E




## Body - WFX_E, Standard Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | |
| WFX 12040 E | ● | 40 | 32 | 30 | 90 | 120 | 3 |
| 12050 E | ● | 50 | 32 | 30 | 90 | 120 | 3 |
| 12063 E | ● | 63 | 32 | 30 | 90 | 120 | 4 |
| 12080 E | ● | 80 | 32 | 30 | 90 | 120 | 4 |

Inserts are not included.

## Body - WFXF_E, Fine Pitch

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | |
| WFXF 12050 E | ● | 50 | 32 | 30 | 90 | 120 | 4 |
| 12063 E | ● | 63 | 32 | 30 | 90 | 120 | 5 |
| 12080 E | ● | 80 | 32 | 30 | 90 | 120 | 6 |

Inserts are not included.

## Identification Details

| WFX | F | 12 | 050 | E |
|---|---|---|---|---|
| Cutter Series | F: Fine | Insert Size | Cutter Diameter | Endmill Type |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Cutting Speed | Feed Rate | DOC | Grades |
|---|---|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,10–**0,15**–0,20 | <10 | ACU2500 |
| | Soft Steel | ≤180 | 180–**250**–350 | 0,10–**0,15**–0,20 | <10 | ACP200 ACP300 |
| | Die Steel | 200–220 | 100–**150**–200 | 0,10–**0,15**–0,20 | <6 | XCU2500 |
| M | Stainless Steel | - | 160–**200**–250 | 0,10–**0,15**–0,20 | <10 | ACU2500 ACM300 |
| K | Cast Iron | 250 | 100–**175**–250 | 0,10–**0,15**–0,20 | <10 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| N | Non Ferrous Metal | - | 300–**500**–1000 | 0,10–**0,15**–0,20 | <10 | H1 DL1000 |
| S | Exoric Alloy | - | 30–**50**–80 | 0,10–**0,15**–0,20 | <10 | ACU2500 ACM200 ACM300 |

Min. - **Optimum** - Max.

## Inserts

Dimensions (mm)

Fig. 3







Fig. 4
Wiper Insert




| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | PS | PM | P | | | K | K | | MS | | KN | N | | |
| General Purpose | PS | PM | | PM | PM | K | K | | MS | MS | | N | | |
| Roughing | PS | | | PM | PM | | | K | | MS | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | RE | Fig. |
| SOMT 120408 PDER L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| SOMT 120404 PDER G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,4 | 3 |
| 120408 PDER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| 120412 PDER G | ● | | ❍ | ● | ❍ | | ● | ❍ | ❍ | ● | – | – | 1,2 | 3 |
| 120416 PDER G | ● | | ● | ● | ● | | ❍ | ❍ | ❍ | ❍ | – | – | 1,6 | 3 |
| SOMT 120408 PDER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 3 |
| SOET 120408 PDFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,8 | 3 |
| XOEW 120408 PDTR W | ❍ | – | – | – | – | – | – | ❍ | – | – | – | – | – | 4 |

## Spare Parts

| Shim | Shim Screw | Insert Screw | | Insert Wrench | Seat Wrench |
|---|---|---|---|---|---|
|  |  |  | |  |  |
| WFXS4R | BW0507F | BFTX03512IP | **3,0** | TRDR15IP | LH035 |



# "Sumi Dual Mill" Series
# TSX Type

Expansion



## General Features

High-efficient and high precision tangential shoulder milling cutter with tangentially mounted carbide inserts.

## Characteristics

- Tough & Sharp cutting edge
- Very accurate and excellent surface finish
- Wide product range

## Product Range

### TSX Shoulder Milling Cutter

| | Cat. No. | Series | Diameter Range / No of Teeth | | | | | | | | | | | | | | Shape |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | Ø16 | Ø20 | Ø25 | Ø32 | Ø40 | Ø50 | Ø63 | Ø80 | Ø100 | Ø125 | Ø160 | Ø200 | Ø250 | Ø315 | |
| Shell Type | TSX 08000RS | Standard Pitch | | | | | 4 | 5 | 6 | 7 | | | | | | |  → G30-G37 |
| | TSXF 08000RS | Fine Pitch | | | | | 6 | 8 | 10 | 11 | | | | | | | |
| | TSX 13000RS | Standard Pitch | | | | | 3 | 4 | 5 | 5 | 6 | 7 | 8 | 12 | 14 | 16 | |
| | TSXM 13000RS | Medium Pitch | | | | | 4 | 5 | 6 | 7 | 8 | 10 | 12 | 16 | 20 | 24 | |
| | TSXF 13000RS | Fine Pitch | | | | | 5 | 6 | 7 | 8 | 10 | 14 | 16 | | | | |
| Shank Type | TSX 08000E | Standard Pitch | 2 | 2* | 3* | 3* | 4 | 5 | 6 | 7 | | | | | | |  |
| | TSXF 08000E | Fine Pitch | | 3 | 4 | 5 | 6 | 8 | 10 | 11 | | | | | | | |
| | TSX 13000E | Standard Pitch | | | 2 | 2 | 3 | 4 | 5 | 5 | | | | | | | |
| | TSXM 13000E | Medium Pitch | | | | 3 | 4 | 5 | 6 | 7 | | | | | | | |
| | TSXF 13000E | Fine Pitch | | | | | 5 | 6 | 7 | 8 | | | | | | | |

* Different shank diameters in stock

### TSXR Repeater

| Type | Cat. No. | Diameter Range / No of Teeth | | | | | | | | | | | | | Shape |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | Ø16 | Ø20 | Ø25 | Ø32 | Ø40 | Ø50 | | Ø63 | | Ø80 | | Ø100 | | Ø125 | |
| Shell | TSXR 08000RS | | | | 2 | 3 | 3 | 4 | 5 | | | | | | | → G38-G39  |
| | TSXR 13000RS | | | | | 2 | 3 | | 3 | 4 | 4 | 5 | 5 | 6 | 7 | |
| Shank | TSXR 08000E | | 1 | 2 | 2 | 3 | | | | | | | | | |  |
| | TSXR 13000E | | | | | 2 | 3 | | | | | | | | | |

## Recommended Cutting Conditions

Min. - **Optimum** - Max.






| ISO | Work-material | Hardness (HB) | Cutting Speed $v_c$ (m/min) | TSX _ _ _ E Feed Rate $f_t$ (mm/T) | Grade |
|---|---|---|---|---|---|
| P | Carbon Steel | 180–280 | 150–**225**–300 | 0,08–**0,20**–0,30 | ACU2500 ACP100 ACP200 ACP300 XCU2500 |
| | | > 280 | 75–**150**–230 | 0,08–**0,20**–0,30 | |
| | Alloy Steel | 180–280 | 100–**175**–250 | 0,08–**0,15**–0,25 | |
| M | Stainless Steel | 220–280 | 90–**135**–180 | 0,08–**0,15**–0,25 | ACU2500 ACM200 ACM300 |
| | | >280 | 75–**125**–170 | 0,08–**0,15**–0,25 | |
| K | Cast Iron Ductile Cast Iron | 250 | 100–**175**–250 | 0,08–**0,20**–0,30 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Material | – | 30–**60**–90 | 0,05–**0,10**–0,15 | ACU2500 ACM200 ACM300 |






● = Euro stock

## Chipbreaker Lineup

| Work Material | P M K S | | |
|---|---|---|---|
| Chipbreaker | L type | G type | H type |
| |  |  |  |
| Feature | Low cutting force | General purpose | Strong edge |
| LNEX08<br>Cutting edge geometry |  |  | – |
| LNEX13<br>Cutting edge geometry |  |  |  |
| Application | Light cut, low rigidity milling and reduced burrs | Main breaker for general purpose applications | Roughing, heavy interrupted and hardness steel milling |

## Chipbreaker Selection





## Inserts


| Cat. No. | RE0,4 | RE0,8 | RE1,2 | RE1,6 | RE2,4 | RE3,2 |
|---|---|---|---|---|---|---|
| LNEX0804__PNER-L | ● | ● | | | | |
| LNEX0804__PNER-G | ● | ● | ● | ● | | |
| LNEX1306__PNER-L | ● | ● | | | | |
| LNEX1306__PNER-G | | ● | | ● | ● | ● |
| LNEX1306__PNER-H | ● | ● | | ● | ● | ● |

## Suitable Applications


Face milling



Shoulder milling




Side face milling




Slot milling

Recommended
≤ ø32 mm



Hole expansion milling



# TSX(F) 08000 E

Expansion

## Shank Type

| Rake Angle | | |
|---|---|---|
| Radial | -36°– -20° | 8 mm / 90° |
| Axial | -6° | |



Fig. 1






Fig. 2




## Body - TSX, Standard Pitch

| Cat. No. | | Stock | Dimensions (mm) DC | DMM | LH | LS | LF | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|
| TSX | 08016 E | ● | 16 | 16 | 25 | 75 | 100 | 2 | 0,13 | 1 |
| | 08020 E | ● | 20 | 20 | 30 | 80 | 110 | 2 | 0,22 | 1 |
| | 08020 E-16 | ❍ | 20 | 16 | 30 | 80 | 110 | 2 | 0,15 | 2 |
| | 08025 E | ● | 25 | 25 | 30 | 90 | 120 | 3 | 0,40 | 1 |
| | 08025 E-20 | ❍ | 25 | 20 | 30 | 90 | 120 | 3 | 0,26 | 2 |
| | 08032 E | ● | 32 | 32 | 30 | 90 | 120 | 3 | 0,67 | 1 |
| | 08032 E-25 | ❍ | 32 | 25 | 30 | 90 | 120 | 3 | 0,43 | 2 |
| | 08040 E | ● | 40 | 32 | 30 | 90 | 120 | 4 | 0,72 | 2 |
| | 08050 E | ❍ | 50 | 32 | 30 | 90 | 120 | 5 | 0,85 | 2 |
| | 08063 E | ❍ | 63 | 32 | 35 | 90 | 125 | 6 | 1,09 | 2 |
| | 08080 E | ❍ | 80 | 32 | 35 | 90 | 125 | 7 | 1,44 | 2 |

Inserts are not included.

## Body - TSXF, Fine Pitch


| Cat. No. | | Stock | Dimensions (mm) DC | DMM | LH | LS | LF | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|
| TSXF | 08020 E | ● | 20 | 20 | 30 | 80 | 110 | 3 | 0,22 | 1 |
| | 08025 E | ● | 25 | 25 | 30 | 90 | 120 | 4 | 0,40 | 1 |
| | 08032 E | ● | 32 | 32 | 30 | 90 | 120 | 5 | 0,67 | 1 |
| | 08040 E | ● | 40 | 32 | 30 | 90 | 120 | 6 | 0,73 | 2 |
| | 08050 E | ❍ | 50 | 32 | 30 | 90 | 120 | 8 | 0,85 | 2 |
| | 08063 E | ❍ | 63 | 32 | 35 | 90 | 125 | 10 | 1,10 | 2 |
| | 08080 E | ❍ | 80 | 32 | 35 | 90 | 125 | 11 | 1,42 | 2 |

Inserts are not included.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | K | K | | MS | | |
| General Purpose Cutting | | | | | | K | K | | MS | | MS |
| Rough Cutting | | | | | | | | K | | | MS |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 080404 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 080408 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 080412 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,2 |
| 080416 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| LNEX 080404 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 080408 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 080412 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,2 |
| 080416 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |




## Recommended Cutting Conditions

→ H20

## Identification Details

| TSX | F/M | 08 | 032 | E |
|---|---|---|---|---|
| Cutter Series | F: Fine Pitch<br>M: Medium Pitch | Insert Size | Cutter Diameter | Endmill Type |

## Spare Parts

| Insert Screw | | Insert Wrench | Applicable Cutters |
|---|---|---|---|
| BFTX0306IP | 2,0 | TRDR08IP | TSX08016E, TSX08020E, TSXF08020E |
| BFTX0308IP | | | TSX08025E–80E, TSXF08025E–80E |





● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

Expansion

| Rake Angle | | |
|---|---|---|
| | Radial | -31°– -15° |
| | Axial | -6° |

12 mm

90°

## Shank Type



Fig. 1






Fig. 2




## Body - TSX, Standard Pitch

| Cat. No. | | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | DC | DMM | LH | LS | LF | | | |
| TSX | 13025 E | ● | 25 | 25 | 35 | 85 | 120 | 2 | 0,38 | 1 |
| | 13032 E | ● | 32 | 32 | 35 | 85 | 120 | 2 | 0,66 | 1 |
| | 13040 E | ● | 40 | 32 | 30 | 90 | 120 | 3 | 0,71 | 2 |
| | 13050 E | ● | 50 | 32 | 30 | 90 | 120 | 4 | 0,81 | 2 |
| | 13063 E | ❍ | 63 | 32 | 35 | 90 | 125 | 5 | 1,08 | 2 |
| | 13080 E | ❍ | 80 | 32 | 35 | 90 | 125 | 5 | 1,40 | 2 |

Inserts are not included.

## Body - TSXM, Medium Pitch

| Cat. No. | | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | DC | DMM | LH | LS | LF | | | |
| TSXM | 13032 E | ● | 32 | 32 | 35 | 85 | 120 | 3 | 0,35 | 1 |
| | 13040 E | ● | 40 | 32 | 30 | 90 | 120 | 4 | 0,71 | 2 |
| | 13050 E | ● | 50 | 32 | 30 | 90 | 120 | 5 | 0,80 | 2 |
| | 13063 E | ❍ | 63 | 32 | 35 | 90 | 125 | 6 | 1,07 | 2 |
| | 13080 E | ❍ | 80 | 32 | 35 | 90 | 125 | 7 | 1,41 | 2 |

Inserts are not included.

## Body - TSXF, Fine Pitch


| Cat. No. | | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) | Figure |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | DC | DMM | LH | LS | LF | | | |
| TSXF | 13040 E | ● | 40 | 32 | 30 | 90 | 120 | 5 | 0,70 | 2 |
| | 13050 E | ● | 50 | 32 | 30 | 90 | 120 | 6 | 0,80 | 2 |
| | 13063 E | ❍ | 63 | 32 | 30 | 90 | 125 | 7 | 1,07 | 2 |
| | 13080 E | ❍ | 80 | 32 | 35 | 90 | 125 | 8 | 1,42 | 2 |

Inserts are not included.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | K | K | | M S | |
| General Purpose Cutting | | | | P M | | K | K | | M S | M S |
| Rough Cutting | | | | P M | P M | | | K | | M S |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 130604 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 130608 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 130612 PNER-L | ❍ | | | ● | | | | ● | ● | ● | 1,2 |
| 130616 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| 130620 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,4 |
| 130632 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 3,2 |
| LNEX 130604 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 130608 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 130612 PNER-G | ❍ | | ● | ● | ● | | ● | ● | ● | ● | 1,2 |
| 130616 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |
| 130620 PNER-G | ❍ | | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 2,4 |
| 130632 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 3,2 |
| LNEX 130604 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 0,4 |
| 130608 PNER-H | ● | ❍ | | ● | ● | ❍ | ● | ● | | | 0,8 |
| 130612 PNER-H | ❍ | | | ● | ● | | ● | ● | | | 1,2 |
| 130616 PNER-H | ● | | | ● | ● | | ● | ● | | | 1,6 |
| 130620 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 2,0 |
| 130624 PNER-H | ● | | | ● | ● | | ● | ● | | | 2,4 |
| 130632 PNER-H | ● | | | ● | ● | | ● | ● | | | 3,2 |




## Recommended Cutting Conditions

→ H20

## Identification Details

→ H22

## Spare Parts

| Insert Screw | | Insert Wrench |
|---|---|---|
|  | |  |
| BFTX03510IP | 3,0 | TRDR15IP |

# TSXR 08000 E


Expansion

## Shank Type

| Rake Angle | | |
|---|---|---|
| | Radial | -33°– -18° |
| | Axial | -6° – -3° |

21-40 mm | 90°






## Body - TSXR


| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of Teeth | Steps | Effective Teeth |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | APMX | DMM | LH | LS | LF | | | |
| TSXR 08020E2120Z01 | ❍ | 20 | 21 | 20 | 30 | 80 | 110 | 3 | 3 | 1 |
| 08025E2725Z02 | ❍ | 25 | 27 | 25 | 35 | 90 | 125 | 8 | 4 | 2 |
| 08032E3432Z02 | ❍ | 32 | 34 | 32 | 50 | 90 | 140 | 10 | 5 | 2 |
| 08040E4032Z03 | ❍ | 40 | 40 | 32 | 60 | 90 | 150 | 18 | 6 | 3 |

Inserts are not included.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | ● | ● | | | | |
| General Purpose Cutting | | | | | | ● | ● | | | | |
| Rough Cutting | | | | | | | | ● | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 080404 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 080408 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 080412 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,2 |
| 080416 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| LNEX 080404 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 080408 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 080412 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,2 |
| 080416 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |




## Recommended Cutting Conditions

Min. - **Optimum** - Max.

| ISO | Work-material | Hardness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_t$ (mm/T) | Grade |
|---|---|---|---|---|---|
| P | Carbon Steel | 180–280HB | 110–**200**–280 | 0,10–**0,20**–0,30 | ACU2500 ACP100 ACP200 ACP300 XCU2500 |
| | | > 280HB | 70–**135**–200 | 0,10–**0,20**–0,30 | |
| | Alloy Steel | 180–280HB | 90–**155**–220 | 0,10–**0,15**–0,25 | |
| M | Stainless Steel | 220–280HB | 90–**135**–180 | 0,10–**0,15**–0,25 | ACU2500 ACM200 ACM300 |
| | | >280HB | 70–**115**–160 | 0,10–**0,15**–0,25 | |
| K | Cast Iron Ductile Cast Iron | 250HB | 125–**175**–225 | 0,10–**0,20**–0,30 | ACU2500 ACK200 ACK300 XCU2500 XCK2000 |
| S | Exotic Material | – | 30–**60**–90 | 0,05–**0,10**–0,15 | ACU2500 ACM200 ACM300 |

## Identification Details

| TSXR | 08 | 025 | E | 27 | 25 | Z02 |
|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Shank Type | Max. Depth of Cut | Shank Diameter | Effective Teeth |

## Spare Parts

| Insert Wrench | Insert Screw | |
|---|---|---|
|  |  | |
| TRDR08IP | BFTX0308IP | 2,0 |



● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)


Expansion

| Rake Angle | | |
|---|---|---|
| | Radial | -23°– -18° |
| | Axial | -6° – -3° |

41-60 mm | 90°

## Shank Type






## Body - TSXR


| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of Teeth | Steps | Effective Teeth |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | APMX | DMM | LH | LS | LF | | | |
| TSXR 13040E4132Z02 | ❍ | 40 | 41 | 32 | 60 | 90 | 150 | 8 | 4 | 2 |
| 13050E6042Z03 | ❍ | 50 | 60 | 42 | 80 | 90 | 170 | 18 | 6 | 3 |

Inserts are not included.

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cutting | | | | | | | | | | |
| General Purpose Cutting | | | | | | | | | | |
| Rough Cutting | | | | | | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | RE |
| LNEX 130604 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,4 |
| 130608 PNER-L | ● | | | ● | ❍ | | ❍ | ● | ❍ | ● | 0,8 |
| 130612 PNER-L | ❍ | | | ● | | | | ● | ● | ● | 1,2 |
| 130616 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 1,6 |
| 130620 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 2,4 |
| 130632 PNER-L | ❍ | | | ❍ | | | | ❍ | ❍ | ❍ | 3,2 |
| LNEX 130604 PNER-G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ❍ | ● | 0,4 |
| 130608 PNER-G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | 0,8 |
| 130612 PNER-G | ❍ | | ● | ● | ● | | ● | ● | ● | ● | 1,2 |
| 130616 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 1,6 |
| 130620 PNER-G | ❍ | | ❍ | ❍ | ❍ | | ❍ | ❍ | ❍ | ❍ | 2,0 |
| 130624 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 2,4 |
| 130632 PNER-G | ● | | ❍ | ● | ● | | ● | ● | ❍ | ● | 3,2 |
| LNEX 130604 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 0,4 |
| 130608 PNER-H | ● | ❍ | | ● | ● | ❍ | ● | ● | | | 0,8 |
| 130612 PNER-H | ❍ | | | ● | ● | | ● | ● | | | 1,2 |
| 130616 PNER-H | ● | | | ● | ● | | ● | ● | | | 1,6 |
| 130620 PNER-H | ❍ | | | ❍ | ❍ | | ❍ | ❍ | | | 2,0 |
| 130624 PNER-H | ● | | | ● | ● | | ● | ● | | | 2,4 |
| 130632 PNER-H | ● | | | ● | ● | | ● | ● | | | 3,2 |




## Recommended Cutting Conditions

→ H24

## Identification Details

| TSXR | 13 | 050 | E | 60 | 42 | Z03 |
|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Shank Type | Max. Depth of Cut | Shank Diameter | Effective Teeth |

## Spare Parts

| Insert Wrench | Insert Screw | |
|---|---|---|
|  |  | N·m |
| TRDR15IP | BFTX03510IP | 3,0 |

Expansion



## General Features

- Supports various machining operations
- Excellent machining quality
- Excellent sharpness with low resistance
- General-purpose grade applicable to any work material

## Product Range


| Type | Cat. No. | Diameter Range (mm) / No of Teeth | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | Ø14 | Ø16 | Ø18 | Ø20 | Ø22 | Ø25 | Ø26 | Ø28 | Ø30 | Ø32 | Ø35 | Ø40 | Ø50 | Ø63 | Ø80 | Ø100 | Ø125 | Ø160 |
| Shell | WEZ 11000RS → G48 | | | | | | | | | | | | 4, 6 | 5,7 | 6, 8 | 7, 10 | 9, 12 | | |
| | WEZ 11000R (Inch) | | | | | | | | | | | | | | | 7, 10 | 9, 12 | | |
| | WEZ 17000RS → G50 | | | | | | | | | | | | 3, 4 | 3, 5 | 4, 6 | 4, 7 | 5, 8 | 6, 9, 11 | 8, 10 12 |
| | WEZ 17000R (Inch) | | | | | | | | | | | | | | | 4, 7 | 5, 8 | 6, 9, 11 | 8, 10 12 |
| Shank | WEZ 11000E | 1 | 2* | 2 | 2*, 3* | 3 | 2, 3*, 4* | | 4 | 4 | 2, 3, 4, 5* | 5 | 2, 4, 6 | 5, 7 | 8 | 10 | | | |
| | WEZ 11000ES | 1 | 2* | | 3* | | 4* | | | | | | | | | | | | |
| | WEZ 11000EL | 1 | 2* | 2 | 2* | 2 | 2*, 3 | | 2 | 2 | 2*, 3 | 2, 3 | 2 | 3 | | | | | |
| | WEZ 17000E | | | | | | 2* | | 2 | 3 | 2, 3* | 3 | 3, 4 | 3*, 5* | 4*, 6* | 7 | | | |
| | WEZ 17000ES | | | | | | 2 | | | | 3 | | | | | | | | |
| | WEZ 17000EL | | | | | | 2 | | 2 | 2 | 2*, 3 | 2 | 2, 3, 4 | 3*, 5* | 4*, 6* | | | | |
| Modular | WEZ 11000M | | 2 | 2 | 2, 3 | 3 | 2, 3, 4 | 4, 5 | 4, 5 | 2, 4, 5 | 2, 3, 4, 5 | 2, 5 | 2, 4, 5, 6 | | | | | | |
| | WEZ 17000M | | | | | | 2, 3 | | 2 | 2, 3 | 2, 3, 4 | 2, 3 | 2, 3, 4 | | | | | | |

* Different shank diameters in stock


## Suitable Applications

- Supports Ramping, Helical Milling, Plunge Cutting


Face milling



Shoulder milling




Side face milling



Groove milling




Hole expansion milling




Ramping



Helical milling



Plunge cutting



## Optimised Body Design


Wide guide face for stable insert clamping.



WEZ11 type

## Chipbreaker Lineup

| Work Material | P M K S H | N |
|---|---|---|
| Chipbreaker | L Type / G Type / H Type / F Type / P Type | S Type |
| **AO_T11** Cutting edge geometry | 28° / 20° / 28° / 28° | 28° |
| **AO_T17** Cutting edge geometry | 28° / 20° / 10° / 28° / 28° | 28° |
| Applications | Light cut, low rigidity machining / Main breaker for general purpose to interrupted machining / Heavy cut, heavy interrup-ted machining, hardened steel / Light cut, finishing, low-burr design / Light cut, high-precision machining, high surface wall quality | For non-ferrous metals |








● = Euro stock

## Product Range Inserts

Main Grade: ACU2500; S-Type: H20, DL2000

| Cat. No. | Nose Radius (mm) | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R0,2 | R0,4 | R0,5 | R0,8 | R1,0 | R1,2 | R1,6 | R2,0 | R2,4 | R3,0 | R3,2 | R4,0 | R5,0 | R6,4 |
| AOMT 11T3_ _ PEER-G | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | |
| AOMT 11T3_ _ PEER-H | | ● | | ● | | ● | ● | | | | | | | |
| AOET 11T3_ _ PEER-F | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | |
| AOET 11T3_ _ PEER-P16 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 11T3_ _ PEER-P20 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 11T3_ _ PEER-P25 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 11T3_ _ PEFR-S | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | |
| AOMT 1705_ _ PEER-L | ● | ● | | ● | | ● | ● | | | | | | | |
| AOMT 1705_ _ PEER-G | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| AOMT 1705_ _ PEER-H | | ● | | ● | | ● | ● | | | | | | | |
| AOET 1705_ _ PEER-F | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| AOET 1705_ _ PEER-P25 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 1705_ _ PEER-P32 | ● | ● | ● | ● | ● | ● | | | | | | | | |
| AOET 1705_ _ PEFR-S | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |

## Lineup of Chipbreakers for Ground Inserts


### F Type

Cutting edge specialized for sharpness and machining accuracy




Sharpness from ground finish enables burr control.

Excellent squareness with all diameters.










| | |
|---|---|
| Machine: | Vertical Machining Centre BT50, |
| Work Material | X5CrNiS18 9 |
| Tool: | WEZ 11050 RS07 (Ø 50, 7 teeth) |
| Insert: | AOET11T308PEER-F (ACU2500) |
| Cutting Conditions: | $v_c$ = 120 m/min, $f_z$ = 0,12 mm/t, $a_p$ = 1 mm, $a_e$ = 30 mm, dry |


### P Type


Chipbreaker for wall surface squareness equivalent to solid endmills



Premium item with cutting edge shape optimised for each cutter diameter while maintaining the F type chipbreaker's sharpness.

Enables wall surface squareness equal to solid endmills through a blade shape optimised for each tool diameter.




P Type Chipbreaker Selection

| Cat. No. | Cutter Diameter (mm) | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | Ø14 | Ø16 | Ø18 | Ø20 | Ø22 | Ø25 | Ø28 | Ø30 | Ø32 | Ø35 | => Ø40 |
| AOET11T3_ _PEER-P_ _ | -P16 | | -P20 | | – | -P25 | | – | | | |
| AOET1705_ _PEER-P_ _ | – | | | | | -P25 | | -P32 | | | – |

| | |
|---|---|
| Machine: | Vertical Machining Centre BT50, |
| Work Material: | C50 |
| Tool: | WEZ 11020 E03 (Ø 20, 3 teeth) |
| Insert: | AOET11T308PEER-P20 (ACU2500) |
| Cutting Conditions: | $v_c$ = 150 m/min, $f_z$ = 0,1 mm/t, $a_p$ = 8 mm x 3 passes, $a_e$ = 1 mm, dry |

### S Type

Sharp edge chipbreaker for non-ferrous metals, with excellent adhesion resistance



Suppresses adhesion with rake face lapping.

DLC coat inserts available for further improved adhesion resistance.




No Adhesion




Adhesion




Adhesion


| | |
|---|---|
| Machine: | Vertical Machining Centre BT50, |
| Work Material: | AlSi12Cu |
| Tool: | WEZ 11020 E03 (Ø 20, 3 teeth) |
| Insert: | AOET11T308PEER-S (H20) |
| Cutting Conditions: | $v_c$ = 350 m/min, $f_z$ = 0,1 mm/t, $a_p$ = 3 mm, $a_e$ = 10 mm, dry |

Expansion

## Recommended Cutting Conditions

### WEZ11 Type

Cutter: WEZ 11020 E03
Insert: AO_T11T3 type
Cutting Data: $a_p$ = 3 mm, $a_e$ = 10 mm, dry





Min. - **Optimum** - Max.

| ISO | Material | HB | Chipbreaker | Grade | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | ACU2500 | XCU2500 | ACP2000 | ACP3000 | T2500A | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | DL2000 |
| | | | | Feed Rate (mm/tooth) | | | | | | | | | | |
| | | | | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,18 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,08–0,15–0,20 | 0,05–0,10–0,15 |
| | | | | Cutting Speed $v_c$ (m/min) | | | | | | | | | | |
| P | Unalloyed steel, <0, 15%C, annealed | 125 | G | 270–320–370 | 300–350–400 | 300–350–400 | 250–300–350 | 230–280–330 | | | | | | |
| | · , <0, 45%C, annealed | 190 | G | 170–220–270 | 200–250–300 | 200–250–300 | 150–200–250 | 130–180–230 | | | | | | |
| | · , <0, 45%C, tempered | 250 | G | 140–180–220 | 160–200–245 | 160–200–245 | 120–160–200 | 105–145–185 | | | | | | |
| | · , <0, 75%C, annealed | 270 | G | 110–145–175 | 130–165–195 | 130–165–195 | 100–130–165 | 85–115–150 | | | | | | |
| | · , <0, 75%C, tempered | 300 | G | 70–90–110 | 80–100–120 | 80–100–120 | 60–80–100 | 50–70–90 | | | | | | |
| | Low alloyed steel, annealed | 180 | G | 160–205–255 | 190–235–280 | 190–235–280 | 140–190–235 | 120–170–215 | | | | | | |
| | · , tempered | 275 | G | 90–120–150 | 110–135–165 | 110–135–165 | 80–110–140 | 70–100–125 | | | | | | |
| | · , tempered | 300 | G | 85–110–130 | 100–125–150 | 100–125–150 | 75–100–125 | 65–90–115 | | | | | | |
| | · , tempered | 350 | G | 60–80–100 | 70–90–110 | 70–90–110 | 50–70–90 | 45–65–85 | | | | | | |
| | High alloyed and tool steel, annealed | 200 | G | 140–180–220 | 160–200–245 | 160–200–245 | 120–160–205 | | | | | | | |
| | · , tempered | 325 | G | 55–70–85 | 60–80–100 | 60–80–100 | 50–65–80 | | | | | | | |
| M | Stainless steel, ferritic/martensitic, annealed | 200 | G | 110–140–170 | 160–190–210 | | | | | | | 140–170–190 | 90–110–140 | |
| | · , martensitic, tempered | 240 | G | 100–125–150 | 145–170–190 | | | | | | | 125–150–170 | 80–100–125 | |
| | · , austenitic, plunged | 180 | G | 120–150–180 | 170–200–220 | | | | | | | 150–180–200 | 100–120–150 | |
| K | Grey cast iron | | G | 150–200–250 | 250–300–350 | | | | 250–300–350 | 250–300–350 | 170–220–270 | | | |
| | Nodular cast iron | | G | 90–120–150 | 150–180–210 | | | | 150–180–210 | 150–180–210 | 100–130–160 | | | |
| S | High tempered resist. alloys, Fe based, annealed | | G | 30–40–55 | | | | | | | | 35–45–60 | 25–35–50 | |
| | · , hardened | | G | 60–80–100 | | | | | | | | 70–90–110 | 50–70–90 | |
| N | Aluminium alloy, Si < 12,6% | | S | | | | | | | | | | | 500–750–100 |
| | · , Si > 12,6% | | S | | | | | | | | | | | 170–200–250 |
| | Copper alloy | | S | | | | | | | | | | | 300–330–350 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.
For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

### WEZ17 Type

Cutter: WEZ 17032 E03
Insert: AO_T1705 type
Cutting Data: $a_p$ = 5 mm, $a_e$ = 16 mm, dry





Min. - **Optimum** - Max.

| ISO | Material | HB | Chipbreaker | Grade | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | ACU2500 | XCU2500 | ACP2000 | ACP3000 | T2500A | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | DL2000 |
| | | | | Feed Rate (mm/tooth) | | | | | | | | | | |
| | | | | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,15–0,22 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,10–0,20–0,28 | 0,05–0,10–0,15 |
| | | | | Cutting Speed $v_c$ (m/min) | | | | | | | | | | |
| P | Unalloyed steel, <0, 15%C, annealed | 125 | G | 285–335–390 | 315–360–420 | 315–360–420 | 265–315–370 | 240–295–345 | | | | | | |
| | · , <0, 45%C, annealed | 190 | G | 180–230–285 | 210–265–315 | 210–265–315 | 160–210–265 | 135–190–240 | | | | | | |
| | · , <0, 45%C, tempered | 250 | G | 145–190–230 | 170–210–255 | 170–210–255 | 130–170–215 | 110–155–195 | | | | | | |
| | · , <0, 75%C, annealed | 270 | G | 115–150–185 | 135–170–205 | 135–170–205 | 100–135–170 | 90–125–155 | | | | | | |
| | · , <0, 75%C, tempered | 300 | G | 70–90–115 | 85–105–125 | 85–105–125 | 65–85–105 | 55–75–95 | | | | | | |
| | Low alloyed steel, annealed | 180 | G | 170–220–265 | 200–245–295 | 200–245–295 | 150–200–250 | 130–180–225 | | | | | | |
| | · , tempered | 275 | G | 100–130–155 | 115–145–175 | 115–145–175 | 85–115–145 | 75–105–135 | | | | | | |
| | · , tempered | 300 | G | 90–115–140 | 105–130–155 | 105–130–155 | 75–105–130 | 65–90–120 | | | | | | |
| | · , tempered | 350 | G | 65–85–100 | 75–95–115 | 75–95–115 | 55–75–95 | 50–70–85 | | | | | | |
| | High alloyed and tool steel, annealed | 200 | G | 145–185–230 | 170–215–255 | 170–215–255 | 130–170–215 | | | | | | | |
| | · , tempered | 325 | G | 55–75–90 | 65–85–100 | 65–85–100 | 50–65–85 | | | | | | | |
| M | Stainless steel, ferritic/martensitic, annealed | 200 | G | 115–145–175 | 165–195–215 | | | | | | | 145–175–195 | 100–115–145 | |
| | · , martensitic, tempered | 240 | G | 105–130–155 | 150–175–195 | | | | | | | 130–155–175 | 85–105–130 | |
| | · , austenitic, plunged | 180 | G | 125–155–190 | 180–210–230 | | | | | | | 160–190–210 | 105–125–160 | |
| K | Grey cast iron | | G | 160–210–265 | 265–315–370 | | | | 265–315–370 | 265–315–370 | 180–230–285 | | | |
| | Nodular cast iron | | G | 95–125–160 | 160–190–220 | | | | 160–190–220 | 160–190–220 | 105–140–170 | | | |
| S | High tempered resist. alloys, Fe based, annealed | | G | 30–40–60 | | | | | | | | 35–45–60 | 25–35–50 | |
| | · , hardened | | G | 60–85–105 | | | | | | | | 75–95–115 | 50–75–95 | |
| N | Aluminium alloy, Si < 12,6% | | S | | | | | | | | | | | 500–750–100 |
| | · , Si > 12,6% | | S | | | | | | | | | | | 170–200–250 |
| | Copper alloy | | S | | | | | | | | | | | 300–330–350 |


The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.
For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

## Ramping / Helical Milling Upper Limits


Ramping




Flat Bottom Machining




Machining with Prepared Hole




### WEZ11 Type


| DC Ø (mm) | Max.Ramping Angle | Flat Bottom Machining | | | | Machining with Prepared Hole | |
|---|---|---|---|---|---|---|---|
| | RPMX (°) | Max. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) |
| 14 | 13,2 | 25,3 | 8,4 | 23,1 | 5,9 | 19,0 | 1,9 |
| 16 | 10,5 | 29,3 | 7,6 | 27,0 | 5,6 | 21,7 | 1,5 |
| 18 | 8,1 | 33,3 | 6,7 | 30,9 | 5,0 | 25,2 | 1,4 |
| 20 | 6,5 | 37,3 | 6,0 | 34,9 | 4,6 | 29,1 | 1,3 |
| 22 | 5,3 | 41,3 | 5,4 | 38,8 | 4,3 | 32,9 | 1,3 |
| 25 | 4,1 | 47,3 | 4,8 | 44,8 | 3,9 | 38,9 | 1,3 |
| 28 | 3,4 | 53,3 | 4,4 | 50,7 | 3,6 | 44,9 | 1,3 |
| 30 | 3,0 | 57,3 | 4,2 | 54,7 | 3,5 | 48,8 | 1,3 |
| 32 | 2,7 | 61,3 | 4,0 | 58,7 | 3,3 | 52,8 | 1,2 |
| 35 | 2,3 | 67,3 | 3,8 | 64,6 | 3,1 | 58,8 | 1,2 |
| 40 | 1,8 | 77,3 | 3,4 | 74,6 | 2,9 | 68,8 | 1,2 |
| 50 | 1,2 | 97,3 | 3,0 | 94,6 | 2,6 | 88,8 | 1,1 |
| 63 | 0,8 | 123,3 | 2,8 | 120,5 | 2,5 | 114,7 | 1,1 |

### WEZ17 Type

| DC Ø (mm) | Max.Ramping Angle | Flat Bottom Machining | | | | Machining with Prepared Hole | |
|---|---|---|---|---|---|---|---|
| | RPMX (°) | Max. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) |
| 25 | 10,8 | 47,3 | 13,0 | 41,0 | 8,3 | 33,1 | 1,8 |
| 28 | 8,1 | 53,3 | 11,1 | 46,9 | 7,5 | 39,0 | 1,8 |
| 30 | 7,0 | 57,3 | 10,2 | 50,9 | 7,0 | 43,0 | 1,8 |
| 32 | 6,1 | 61,3 | 9,5 | 54,9 | 6,7 | 47,0 | 1,7 |
| 35 | 5,1 | 67,3 | 8,7 | 60,8 | 6,2 | 53,0 | 1,7 |
| 40 | 4,0 | 77,3 | 7,7 | 70,8 | 5,7 | 63,0 | 1,7 |
| 50 | 2,5 | 97,3 | 6,5 | 90,7 | 5,0 | 83,0 | 1,6 |
| 63 | 1,8 | 123,3 | 5,6 | 116,7 | 4,5 | 109,0 | 1,6 |

* The table above shows values with nose radius 0,8 mm

## Plunge Cutting - Upper Limit for Radial Width $a_e$




| Type | Max. $a_e$ (mm) |
|---|---|
| WEZ11 | 3 |
| WEZ17 | 5 |


## Precautions for Mounting

(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.






# WEZ 11000 E

| Rake Angle | | |
|---|---|---|
| | Radial | -7° – -18° |
| | Axial | 6° – 15° |

10 mm 90°




Fig. 1






Fig. 2




## Body - WEZ (Shank Type)

Dimensions (mm)

| Cat. No. | Stock | DC | DMM | LH | LS | LF | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| WEZ 11014E01 | ● | 14 | 16 | 25 | 55 | 80 | 1 | 0,10 | 1 |
| 11016E02 | ● | 16 | 16 | 25 | 75 | 100 | 2 | 0,13 | 1 |
| 11016E02-12 | ● | 16 | 12 | 25 | 75 | 100 | 2 | 0,07 | 2 |
| 11018E02 | ● | 18 | 16 | 25 | 75 | 100 | 2 | 0,13 | 2 |
| 11020E02 | ● | 20 | 20 | 30 | 80 | 110 | 2 | 0,23 | 1 |
| 11020E02-16 | ● | 20 | 16 | 30 | 80 | 110 | 2 | 0,15 | 2 |
| 11020E03 | ● | 20 | 20 | 30 | 80 | 110 | 3 | 0,22 | 1 |
| 11020E03-16 | ● | 20 | 16 | 30 | 80 | 110 | 3 | 0,14 | 2 |
| 11022E03 | ● | 22 | 20 | 30 | 80 | 110 | 3 | 0,23 | 1 |
| 11025E02 | ● | 25 | 25 | 35 | 85 | 120 | 2 | 0,40 | 1 |
| 11025E03 | ● | 25 | 25 | 35 | 85 | 120 | 3 | 0,40 | 1 |
| 11025E03-20 | ● | 25 | 20 | 35 | 85 | 120 | 3 | 0,26 | 2 |
| 11025E04 | ● | 25 | 25 | 35 | 85 | 120 | 4 | 0,39 | 2 |
| 11025E04-20 | ● | 25 | 20 | 35 | 85 | 120 | 4 | 0,26 | 2 |
| 11028E04 | ● | 28 | 25 | 35 | 85 | 120 | 4 | 0,41 | 1 |
| 11030E04 | ● | 30 | 25 | 40 | 90 | 130 | 4 | 0,46 | 1 |
| 11032E02 | ● | 32 | 32 | 40 | 90 | 130 | 2 | 0,74 | 1 |
| 11032E03 | ● | 32 | 32 | 40 | 90 | 130 | 3 | 0,73 | 1 |
| 11032E04 | ● | 32 | 32 | 40 | 90 | 130 | 4 | 0,73 | 2 |
| 11032E05 | ● | 32 | 32 | 40 | 90 | 130 | 5 | 0,72 | 2 |
| 11032E05-25 | ● | 32 | 25 | 40 | 90 | 130 | 5 | 0,46 | 2 |
| 11035E05 | ● | 35 | 32 | 40 | 90 | 130 | 5 | 0,75 | 2 |
| 11040E02 | ● | 40 | 32 | 30 | 120 | 150 | 2 | 0,96 | 2 |
| 11040E04 | ● | 40 | 32 | 30 | 120 | 150 | 4 | 0,94 | 2 |
| 11040E06 | ● | 40 | 32 | 30 | 120 | 150 | 6 | 0,93 | 2 |
| 11050E05 | ● | 50 | 32 | 30 | 120 | 150 | 5 | 1,04 | 2 |
| 11050E07 | ● | 50 | 32 | 30 | 120 | 150 | 7 | 1,04 | 2 |
| 11063E08 | ● | 63 | 32 | 30 | 120 | 150 | 8 | 1,24 | 2 |
| 11080E10 | ● | 80 | 32 | 30 | 120 | 150 | 10 | 1,52 | 2 |

Inserts are sold separately.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| | | N·m | |
| WEZ 11014E01 | BFTX0305IP | 2,0 | TRDR08IP |
| 11016E02(-12) | | | |
| 11018E02 | | | |
| 11020E02(-16) | BFTX0306IP | 1,5 | |
| 11020E03(-16) | | | |
| 11022E03 | | | |
| 11025E02 | | | |
| 11025E03(-20) | | | |
| 11025E04(-20) | | | |
| 11028E04 | | | |
| 11030E04 | | | |
| 11032E02 | | | |
| 11032E03 | | | |
| 11032E04 | | | |
| 11032E05(-25) | | | |
| 11035E05 | | | |
| 11040E02 | | | |
| 11040E04 | | | |
| 11040E06 | | | |
| 11050E05 | | | |
| 11050E07 | | | |
| 11063E08 | | | |
| 11080E10 | | | |

## Identification Details

| WEZ | 11 | 025 | E | 02 | - | 22 |
|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Round Shank | Number of Teeth | | Shank Diameter |

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT11T324PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

Expansion

## Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 11T302PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ● | 0,2 | 1 |
| 11T304PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 11T305PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 11T308PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 11T310PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 11T312PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 11T316PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 11T320PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 11T324PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 11T330PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 2 |
| 11T332PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 3,2 | 2 |
| AOMT 11T304PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 11T308PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 11T312PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 11T316PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 11T302PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T316PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 11T320PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 11T324PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 11T330PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 2 |
| 11T332PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 2 |
| AOET 11T302PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P16 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P16 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 11T302PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 11T304PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 11T305PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 11T308PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 11T310PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 11T312PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 11T316PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 11T320PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 11T324PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 11T330PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 2 |
| 11T332PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P16 is applicable to cutter diameters Ø 14 mm and Ø 16 mm.
*P20 is applicable to cutter diameters Ø 18 mm, Ø 20 mm.
*P25 is applicable to cutter diameters Ø 25 mm, Ø 28 mm.

## Recommended Cutting Conditions

→ H28

| Rake Angle | | |
|---|---|---|
| | Radial | -14° – -18° |
| | Axial | 6° – 10° |

10 mm 90°



Fig. 1






Fig. 2




## Body - WEZ (Short Shank Type)

Dimensions (mm)

| Cat. No. | Stock | DC | DCSFMS | DMM | LH | LU | LS | LF | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WEZ 11014ES01-12 | ❍ | 14 | 18 | 12 | 30 | 27 | 35 | 65 | 1 | 0,05 | 1 |
| 11016ES02-10 | ❍ | 16 | 18 | 10 | 25 | 22 | 30 | 55 | 2 | 0,04 | 1 |
| 11016ES02-12 | ❍ | 16 | 18 | 12 | 30 | 27 | 35 | 65 | 2 | 0,05 | 1 |
| 11020ES03-10 | ❍ | 20 | 18 | 10 | 25 | – | 30 | 55 | 3 | 0,04 | 2 |
| 11020ES03-12 | ❍ | 20 | 18 | 12 | 30 | – | 35 | 65 | 3 | 0,06 | 2 |
| 11020ES03-16 | ❍ | 20 | 23 | 16 | 30 | 27 | 40 | 70 | 3 | 0,10 | 1 |
| 11025ES04-12 | ❍ | 25 | 23 | 12 | 30 | – | 35 | 65 | 4 | 0,09 | 2 |
| 11025ES04-16 | ❍ | 25 | 23 | 16 | 30 | – | 40 | 70 | 4 | 0,12 | 2 |

Inserts are sold separately.

## Spare Parts

| Applicable Cutters | Insert Screw | Wrench (N·m) | Wrench |
|---|---|---|---|
| WEZ 11014ES01-12 | BFTX0305IP | 1,5 | TRDR08IP |
| 11016ES02-10 | | | |
| 11016ES02-12 | | | |
| 11020ES03-10 | BFTX0306IP | | |
| 11020ES03-12 | | | |
| 11020ES03-16 | | | |
| 11025ES04-12 | | | |
| 11025ES04-16 | | | |

## Identification Details

| WEZ | 11 | 020 | E | S | 03 | - | 12 |
|---|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Round Shank | Short Shank | Number of Teeth | | Shank Diameter |

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.


Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT11T324PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm


C: Chamfer
R: Radius

## Recommended Cutting Conditions

→ H28

Tool: WEZ11016ES02-10
Insert: AOET11T3_ _ PEER-F




For cutting conditions by work material, see page H28.
When using G type chipbreakers, set the efficiency to 80%.
The recommended cutting conditions may not be practical depending on the operating conditions (e. g. machine, work material shape, clamping system).





● = Euro stock
○ = Japan stock
❍ = On request
– =Not available
(N·m) Recommended Tightening Torque (N·m)

Expansion

## Inserts

**Precautions for Mounting** → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 11T302PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ● | 0,2 | 1 |
| 11T304PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 11T305PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 11T308PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 11T310PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 11T312PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 11T316PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 11T320PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 11T324PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 11T330PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 2 |
| 11T332PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 3,2 | 2 |
| AOMT 11T304PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 11T308PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 11T312PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 11T316PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 11T302PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T316PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 11T320PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 11T324PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 11T330PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 2 |
| 11T332PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 2 |
| AOET 11T302PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P16 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P16 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 11T302PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 11T304PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 11T305PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 11T308PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 11T310PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 11T312PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 11T316PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 11T320PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 11T324PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 11T330PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 2 |
| 11T332PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P16 is applicable to cutter diameters Ø 14 mm and Ø 16 mm.
*P20 is applicable to cutter diameters Ø 18 mm, Ø 20 mm.
*P25 is applicable to cutter diameters Ø 25 mm, Ø 28 mm.

# WEZ 11000 EL

| Rake Angle | | |
|---|---|---|
| | Radial | -7° – -18° |
| | Axial | 6° – 15° |

10 mm 90°




Fig. 1






Fig. 2




## Body - WEZ (Long Type)

Dimensions (mm)

| Cat. No. | Stock | DC | DMM | LH | LS | LF | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| WEZ 11014EL01 | ● | 14 | 16 | 25 | 95 | 120 | 1 | 0,16 | 1 |
| 11016EL02 | ● | 16 | 16 | 25 | 120 | 145 | 2 | 0,19 | 1 |
| 11016EL02-14 | ● | 16 | 14 | 25 | 120 | 145 | 2 | 0,15 | 2 |
| 11018EL02 | ● | 18 | 16 | 25 | 120 | 145 | 2 | 0,20 | 2 |
| 11020EL02 | ● | 20 | 20 | 40 | 110 | 150 | 2 | 0,31 | 1 |
| 11020EL02-18 | ● | 20 | 18 | 25 | 125 | 150 | 2 | 0,26 | 2 |
| 11022EL02 | ● | 22 | 20 | 30 | 120 | 150 | 2 | 0,32 | 2 |
| 11025EL02 | ● | 25 | 25 | 50 | 120 | 170 | 2 | 0,57 | 1 |
| 11025EL02-22 | ● | 25 | 22 | 30 | 140 | 170 | 2 | 0,46 | 2 |
| 11025EL03 | ● | 25 | 25 | 50 | 120 | 170 | 3 | 0,57 | 1 |
| 11028EL02 | ● | 28 | 25 | 30 | 140 | 170 | 2 | 0,60 | 2 |
| 11030EL02 | ● | 30 | 25 | 30 | 140 | 170 | 2 | 0,62 | 2 |
| 11032EL02 | ● | 32 | 32 | 60 | 110 | 170 | 2 | 0,97 | 1 |
| 11032EL02-30 | ● | 32 | 30 | 30 | 140 | 170 | 2 | 0,88 | 2 |
| 11032EL03 | ● | 32 | 32 | 60 | 110 | 170 | 3 | 0,96 | 1 |
| 11035EL02 | ● | 35 | 32 | 30 | 140 | 170 | 2 | 1,02 | 2 |
| 11035EL03 | ● | 35 | 32 | 30 | 140 | 170 | 3 | 1,00 | 2 |
| 11040EL02 | ● | 40 | 32 | 30 | 140 | 170 | 2 | 1,08 | 2 |
| 11050EL03 | ● | 50 | 32 | 30 | 140 | 170 | 3 | 1,19 | 2 |

Inserts are sold separately.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| | | N·m | |
| WEZ 11014EL01 | BFTX0305IP | 2,0 | TRDR08IP |
| 11016EL02(-14) | | 1,5 | |
| 11018EL02 | | | |
| 11020EL02(-18) | BFTX0306IP | | |
| 11022EL02 | | | |
| 11025EL02(-22) | | | |
| 11025EL03 | | | |
| 11028EL02 | | | |
| 11030EL02 | | | |
| 11032EL02(-30) | | | |
| 11032EL03 | | | |
| 11035EL02 | | | |
| 11035EL03 | | | |
| 11040EL02 | | | |
| 11050EL03 | | | |

## Identification Details

| WEZ | 11 | 025 | E | L | 02 | - | 22 |
|---|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Round Shank | Long Type | Number of Teeth | | Shank Diameter |

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT11T324PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

## Recommended Cutting Conditions

→ H28





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

Expansion

## Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 11T302PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ● | 0,2 | 1 |
| 11T304PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 11T305PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 11T308PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 11T310PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 11T312PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 11T316PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 11T320PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 11T324PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 11T330PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 2 |
| 11T332PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 3,2 | 2 |
| AOMT 11T304PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 11T308PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 11T312PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 11T316PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 11T302PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T316PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 11T320PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 11T324PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 11T330PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 2 |
| 11T332PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 2 |
| AOET 11T302PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P16 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P16 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 11T302PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 11T304PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 11T305PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 11T308PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 11T310PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 11T312PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 11T316PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 11T320PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 11T324PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 11T330PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 2 |
| 11T332PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P16 is applicable to cutter diameters Ø 14 mm and Ø 16 mm.
*P20 is applicable to cutter diameters Ø 18 mm, Ø 20 mm.
*P25 is applicable to cutter diameters Ø 25 mm, Ø 28 mm.

# WEZ 17000 E

| Rake Angle | | |
|---|---|---|
| | Radial | -6° – -12° |
| | Axial | 6° – 15° |

15 mm 90°



Fig. 1






Fig. 2




## Body - WEZ (Shank Type)

Dimensions (mm)

| Cat. No. | Stock | DC | DMM | LH | LS | LF | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| WEZ 17025E02 | ● | 25 | 25 | 35 | 85 | 120 | 2 | 0,38 | 1 |
| 17025E02-20 | ● | 25 | 20 | 35 | 85 | 120 | 2 | 0,25 | 2 |
| 17028E02 | ● | 28 | 25 | 35 | 85 | 120 | 2 | 0,40 | 2 |
| 17030E03 | ● | 30 | 25 | 40 | 90 | 130 | 3 | 0,43 | 2 |
| 17032E02 | ● | 32 | 32 | 40 | 90 | 130 | 2 | 0,71 | 1 |
| 17032E03 | ● | 32 | 32 | 40 | 90 | 130 | 3 | 0,69 | 1 |
| 17032E03-25 | ● | 32 | 25 | 40 | 90 | 130 | 3 | 0,44 | 2 |
| 17035E03 | ● | 35 | 32 | 40 | 90 | 130 | 3 | 0,72 | 2 |
| 17040E03 | ● | 40 | 32 | 30 | 105 | 135 | 3 | 0,81 | 2 |
| 17040E04 | ● | 40 | 32 | 30 | 105 | 135 | 4 | 0,79 | 2 |
| 17050E03 | ● | 50 | 32 | 30 | 105 | 135 | 3 | 0,93 | 2 |
| 17050E03-42 | ● | 50 | 42 | 30 | 105 | 135 | 3 | 1,41 | 2 |
| 17050E05 | ● | 50 | 32 | 30 | 105 | 135 | 5 | 0,89 | 2 |
| 17050E05-42 | ● | 50 | 42 | 30 | 105 | 135 | 5 | 1,37 | 2 |
| 17063E04 | ● | 63 | 32 | 30 | 105 | 135 | 4 | 1,10 | 2 |
| 17063E04-42 | ● | 63 | 42 | 30 | 105 | 135 | 4 | 1,58 | 2 |
| 17063E06 | ● | 63 | 32 | 30 | 105 | 135 | 6 | 1,08 | 2 |
| 17063E06-42 | ● | 63 | 42 | 30 | 105 | 135 | 6 | 1,56 | 2 |
| 17080E07 | ● | 80 | 32 | 30 | 105 | 135 | 7 | 1,39 | 2 |

Inserts are sold separately.

## Spare Parts

| Applicable Cutters | Insert Screw | (N·m) | Wrench |
|---|---|---|---|
| WEZ 17025E02(-20) | BFTX0407IP | 3,0 | TRDR15IP |
| 17028E02 | | | |
| 17030E03 | | | |
| 17032E02 | BFTX0409IP | | |
| 17032E03(-25) | | | |
| 17035E03 | | | |
| 17040E03 | | | |
| 17040E04 | | | |
| 17050E03(-42) | | | |
| 17050E05(-42) | | | |
| 17063E04(-42) | | | |
| 17063E06(-42) | | | |
| 17080E07 | | | |

## Identification Details

| WEZ | 17 | 032 | E | 02 | - | 30 |
|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Round Shank | Number of Teeth | | Shank Diameter |

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT170524PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Corner radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Corner radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Corner radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

## Recommended Cutting Conditions

→ H28





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
(N·m) Recommended Tightening Torque (N·m)

Expansion

## Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 170502PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170508PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170512PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,2 | 1 |
| 170516PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,6 | 1 |
| AOMT 170502PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170505PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 170508PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170510PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 170512PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 170516PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 170520PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 170524PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 170530PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 1 |
| 170532PEER-G | ● | | ❑ | ❑ | | ❑ | ● | ● | ● | – | – | | 3,2 | 1 |
| 170540PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 4,0 | 1 |
| 170550PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 5,0 | 2 |
| 170564PEER-G | ❑ | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 6,4 | 2 |
| AOMT 170504PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 170508PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 170512PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 170516PEER-H | ● | | ❑ | ● | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 170502PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170516PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 170520PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 170524PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 170530PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 1 |
| 170532PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 1 |
| 170540PEER-F | ● | | – | | | – | | – | | – | – | – | 4,0 | 1 |
| 170550PEER-F | ● | | – | | | – | | – | | – | – | – | 5,0 | 2 |
| 170564PEER-F | ● | | – | | | – | | – | | – | – | – | 6,4 | 2 |
| AOET 170502PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170502PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-P32 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-P32 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 170502PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 170504PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 170505PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 170508PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 170510PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 170512PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 170516PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 170520PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 170524PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 170530PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 1 |
| 170532PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 1 |
| 170540PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 4,0 | 1 |
| 170550PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 5,0 | 2 |
| 170564PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 6,4 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P25 is applicable to cutter diameters Ø 25 mm and Ø 28 mm.
*P32 is applicable to cutter diameters Ø 30 mm, Ø 32 mm and Ø 35 mm.

# WEZ 17000 ES


## Series for Multi-Tasking Machines

| Rake Angle | | |
|---|---|---|
| Radial | -10° – -12° | |
| Axial | 6° – 8° | |

15 mm 90°



Fig. 1




## Body - WEZ (Short Shank Type)

Dimensions (mm)

| Cat. No. | Stock | DC | DCSFMS | DMM | LH | LS | LF | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|
| WEZ 17025ES02-16 | ❍ | 25 | 23 | 16 | 30 | 40 | 70 | 2 | 0,11 | 1 |
| 17032ES03-16 | ❍ | 32 | 27 | 16 | 30 | 40 | 70 | 3 | 0,14 | 1 |

Inserts are sold separately.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| |  |  |  |
| WEZ 17025ES02-16 | BFTX0407IP | 3,0 | TRDR15IP |
| 17032ES03-16 | BFTX0409IP | | |

## Identification Details

| WEZ | 17 | 025 | E | S | 02 | - | 16 |
|---|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Round Shank | Short Shank | Number of Teeth | | Shank Diameter |

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.


Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT170524PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Corner radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Corner radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Corner radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm


C: Chamfer
R: Radius

## Recommended Cutting Conditions

→ H28

Tool: WEZ17025ES02-16
Insert: AOET1705_ _ PEER-F




For cutting conditions by work material, see page 8.
When using G type chipbreakers, set the efficiency to 80%.
The recommended cutting conditions may not be practical depending on the operating conditions (e. g. machine, work material shape, clamping system).



● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
(N·m) Recommended Tightening Torque (N·m)

Expansion

## Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 170502PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170508PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170512PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,2 | 1 |
| 170516PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,6 | 1 |
| AOMT 170502PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170505PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 170508PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170510PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 170512PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 170516PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 170520PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 170524PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 170530PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 1 |
| 170532PEER-G | ● | | ❑ | ❑ | | ❑ | ● | ● | ● | – | – | | 3,2 | 1 |
| 170540PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 4,0 | 1 |
| 170550PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 5,0 | 2 |
| 170564PEER-G | ❑ | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 6,4 | 2 |
| AOMT 170504PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 170508PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 170512PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 170516PEER-H | ● | | ❑ | ● | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 170502PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170516PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 170520PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 170524PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 170530PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 1 |
| 170532PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 1 |
| 170540PEER-F | ● | | – | | | – | | – | | – | – | – | 4,0 | 1 |
| 170550PEER-F | ● | | – | | | – | | – | | – | – | – | 5,0 | 2 |
| 170564PEER-F | ● | | – | | | – | | – | | – | – | – | 6,4 | 2 |
| AOET 170502PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170502PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-P32 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-P32 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 170502PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 170504PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 170505PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 170508PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 170510PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 170512PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 170516PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 170520PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 170524PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 170530PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 1 |
| 170532PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 1 |
| 170540PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 4,0 | 1 |
| 170550PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 5,0 | 2 |
| 170564PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 6,4 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P25 is applicable to cutter diameters Ø 25 mm and Ø 28 mm.
*P32 is applicable to cutter diameters Ø 30 mm, Ø 32 mm and Ø 35 mm.

# WEZ 17000 EL

| Rake Angle | | |
|---|---|---|
| | Radial | -6° – -12° |
| | Axial | 6° – 15° |

15 mm 90°



Fig. 1






Fig. 2




## Body - WEZ (Long Type)

Dimensions (mm)

| Cat. No. | Stock | DC | DMM | LH | LS | LF | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|
| WEZ 17025EL02 | ● | 25 | 25 | 50 | 120 | 170 | 2 | 0,55 | 1 |
| 17028EL02 | ● | 28 | 25 | 50 | 120 | 170 | 2 | 0,57 | 2 |
| 17030EL02 | ● | 30 | 25 | 50 | 120 | 170 | 2 | 0,59 | 2 |
| 17032EL02 | ● | 32 | 32 | 60 | 110 | 170 | 2 | 0,94 | 1 |
| 17032EL02-30 | ● | 32 | 30 | 50 | 120 | 170 | 2 | 0,85 | 2 |
| 17032EL03 | ● | 32 | 32 | 60 | 110 | 170 | 3 | 0,92 | 1 |
| 17035EL02 | ● | 35 | 32 | 50 | 120 | 170 | 2 | 0,98 | 2 |
| 17040EL02 | ● | 40 | 32 | 50 | 120 | 170 | 2 | 1,09 | 2 |
| 17040EL03 | ● | 40 | 32 | 50 | 120 | 170 | 3 | 1,08 | 2 |
| 17040EL04 | ● | 40 | 32 | 50 | 120 | 170 | 4 | 1,05 | 2 |
| 17050EL03 | ● | 50 | 32 | 50 | 120 | 170 | 3 | 1,29 | 2 |
| 17050EL03-42 | ● | 50 | 42 | 50 | 120 | 170 | 3 | 1,83 | 2 |
| 17050EL05 | ● | 50 | 32 | 50 | 120 | 170 | 5 | 1,25 | 2 |
| 17050EL05-42 | ● | 50 | 42 | 50 | 120 | 170 | 5 | 1,79 | 2 |
| 17063EL04 | ● | 63 | 32 | 50 | 120 | 170 | 4 | 1,61 | 2 |
| 17063EL04-42 | ● | 63 | 42 | 50 | 120 | 170 | 4 | 2,16 | 2 |
| 17063EL06 | ● | 63 | 32 | 50 | 120 | 170 | 6 | 1,58 | 2 |
| 17063EL06-42 | ● | 63 | 42 | 50 | 120 | 170 | 6 | 2,13 | 2 |

Inserts are sold separately.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| | | N·m | |
| WEZ 17025EL02 | BFTX0407IP | 3,0 | TRDR15IP |
| 17028EL02 | | | |
| 17030EL02 | | | |
| 17032EL02(-30) | BFTX0409IP | | |
| 17032EL03 | | | |
| 17035EL02 | | | |
| 17040EL02 | | | |
| 17040EL03 | | | |
| 17040EL04 | | | |
| 17050EL03(-42) | | | |
| 17050EL05(-42) | | | |
| 17063EL04(-42) | | | |
| 17063EL06(-42) | | | |

## Identification Details

| WEZ | 17 | 032 | E | L | 02 | - | 30 |
|---|---|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Round Shank | Long Type | Number of Teeth | | Shank Diameter |

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT170524PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Corner radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Corner radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Corner radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

## Recommended Cutting Conditions

→ H28





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

Expansion

## Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 170502PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170508PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170512PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,2 | 1 |
| 170516PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,6 | 1 |
| AOMT 170502PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170505PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 170508PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170510PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 170512PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 170516PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 170520PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 170524PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 170530PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 1 |
| 170532PEER-G | ● | | ❑ | ❑ | | ❑ | ● | ● | ● | – | – | | 3,2 | 1 |
| 170540PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 4,0 | 1 |
| 170550PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 5,0 | 2 |
| 170564PEER-G | ❑ | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 6,4 | 2 |
| AOMT 170504PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 170508PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 170512PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 170516PEER-H | ● | | ❑ | ● | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 170502PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170516PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 170520PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 170524PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 170530PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 1 |
| 170532PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 1 |
| 170540PEER-F | ● | | – | | | – | | – | | – | – | – | 4,0 | 1 |
| 170550PEER-F | ● | | – | | | – | | – | | – | – | – | 5,0 | 2 |
| 170564PEER-F | ● | | – | | | – | | – | | – | – | – | 6,4 | 2 |
| AOET 170502PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170502PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-P32 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-P32 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 170502PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 170504PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 170505PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 170508PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 170510PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 170512PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 170516PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 170520PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 170524PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 170530PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 1 |
| 170532PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 1 |
| 170540PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 4,0 | 1 |
| 170550PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 5,0 | 2 |
| 170564PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 6,4 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P25 is applicable to cutter diameters Ø 25 mm and Ø 28 mm.
*P32 is applicable to cutter diameters Ø 30 mm, Ø 32 mm and Ø 35 mm.

# WEZR 11000 E

New

Repeater Type

| Rake Angle | Radial | -15° – -11° |
|---|---|---|
| | Axial | 8° – 14° |

19–61 mm 90°




Fig. 1






Fig. 2




## Body (Shank Type)

Dimensions (mm)

| Cat. No. | Stock | DC | APMX | DMM | LH | LF | Total No. of Teeth | Steps | Effective No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WEZR 11020E1920Z02 | ❍ | 20 | 19 | 20 | 30 | 110 | 4 | 2 | 2 | 0,22 | 1 |
| 11020E3620Z01 | ❍ | 20 | 36 | 20 | 45 | 125 | 4 | 4 | 1 | 0,24 | 1 |
| 11025E2725Z02 | ❍ | 25 | 27 | 25 | 40 | 130 | 6 | 3 | 2 | 0,41 | 1 |
| 11025E3625Z02 | ❍ | 25 | 36 | 25 | 50 | 140 | 8 | 4 | 2 | 0,42 | 1 |
| 11030E5325Z02 | ❍ | 30 | 53 | 25 | 65 | 155 | 12 | 6 | 2 | 0,52 | 2 |
| 11032E3632Z02 | ❍ | 32 | 36 | 32 | 50 | 140 | 8 | 4 | 2 | 0,74 | 1 |
| 11032E3632Z03 | ❍ | 32 | 36 | 32 | 50 | 140 | 12 | 4 | 3 | 0,71 | 1 |
| 11032E5332Z02 | ❍ | 32 | 53 | 32 | 70 | 160 | 12 | 6 | 2 | 0,90 | 1 |
| 11035E5332Z03 | ❍ | 35 | 53 | 32 | 65 | 155 | 18 | 6 | 3 | 0,88 | 2 |
| 11040E4432Z03 | ❍ | 40 | 44 | 32 | 60 | 150 | 15 | 5 | 3 | 0,87 | 2 |
| 11040E4432Z04 | ❍ | 40 | 44 | 32 | 60 | 150 | 20 | 5 | 4 | 0,85 | 2 |
| 11040E6132Z03 | ❍ | 40 | 61 | 32 | 75 | 165 | 21 | 7 | 3 | 0,95 | 2 |

Inserts are sold seperately.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| |  | N·m |  |
| WEZR 11_ _ _ | BFTX0306IP | 1,5 | TRDR08IP |

## Identification Details

**WEZR 11 032 E 36 32 Z02**

| Cutter Series | Insert Size | Cutter Diameter | Shank Type | Max. Depth of Cut | Shank Dia-meter | Effective Number of Teeth |
|---|---|---|---|---|---|---|

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Chipbreaker | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grades |
|---|---|---|---|---|---|---|
| P | Carbon Steel | ≤ 280HB | G | 100–**150**–200 | 0,08–**0,12**–0,20 | ACU2500 XCU2500 ACP2000 ACP3000 |
| | | > 280HB | G | 80–**100**–120 | 0,08–**0,12**–0,20 | |
| | Alloy Steel | ≤ 280HB | G | 100–**150**–80 | 0,08–**0,12**–0,20 | |
| M | Stainless Steel | ≤ 280HB | G | 80–**120**–160 | 0,08–**0,12**–0,20 | ACU2500 ACM200 ACM300 |
| K | Cast Iron Ductile Cast Iron | – | G | 100–**150**–200 | 0,08–**0,12**–0,20 | ACU2500 XCK2000 ACK2000 ACK3000 |
| S | Exotic Alloy | – | G | 40–**50**–60 | 0,08–**0,12**–0,20 | ACU2500 ACM200 ACM300 |
| N | Aluminum Alloy | Si ≤ 12,6% | S | 300–**500**–800 | 0,05–**0,10**–0,15 | DL2000 H20 |
| | | Si >12,6% | S | 100–**200**–250 | 0,05–**0,10**–0,15 | |

Min. - **Optimum** - Max.

Note:
The cutting conditions above are a guide. Actual conditions will need to be adjusted according to machine rigidity, work clamp rigidity, depth of cut and other factors.
There may be cases where machining cannot be performed under recommended cutting conditions, depending on the machine rigidity and work rigidity.

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT11T324PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

## Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P M K | P | | K | K | | M S | | | N | P | | |
| General Purpose | M S K | P M K | | P | K | | K | M S | M S | N | N | | | |
| Roughing | M S K | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 11T302PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ● | 0,2 | 1 |
| 11T304PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 11T305PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 11T308PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 11T310PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 11T312PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 11T316PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 11T320PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 11T324PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 11T330PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 2 |
| 11T332PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 3,2 | 2 |
| AOMT 11T304PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 11T308PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 11T312PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 11T316PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 11T302PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T316PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 11T320PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 11T324PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 11T330PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 2 |
| 11T332PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 2 |
| AOET 11T302PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 11T302PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 11T304PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 11T305PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 11T308PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 11T310PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 11T312PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 11T316PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 11T320PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 11T324PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 11T330PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 2 |
| 11T332PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P20 is applicable to cutter diameters Ø 18 mm, Ø 20 mm.
*P25 is applicable to cutter diameters Ø 25 mm, Ø 28 mm.

Use peripheral inserts with RE ≤ 0,8 mm from the second step and above.

# WEZR 17000 E

New

Repeater Type

| Rake Angle | Radial | -9° – -8° |
|---|---|---|
| | Axial | 10° – 12° |

29–84 mm 90°





Fig. 1




## Body (Shank Type)

Dimensions (mm)

| Cat. No. | Stock | DC | APMX | DMM | LH | LF | Total No. of Teeth | Steps | Effective No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WEZR 17040E2932Z03 | ❍ | 40 | 29 | 32 | 45 | 110 | 6 | 3 | 2 | 0,75 | 1 |
| 17040E4332Z02 | ❍ | 40 | 43 | 32 | 60 | 125 | 6 | 2 | 3 | 0,86 | 1 |
| 17050E5742Z03 | ❍ | 50 | 57 | 42 | 75 | 130 | 12 | 3 | 4 | 1,58 | 1 |
| 17050E8442Z02 | ❍ | 50 | 84 | 42 | 105 | 140 | 12 | 2 | 6 | 1,04 | 1 |

Inserts are sold seperately.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| |  | N·m |  |
| WEZR 17_ _ _ | BFTX0409IP | 3,0 | TRDR15IP |

## Identification Details

**WEZR 17 040 E 29 32 Z03**

| Cutter Series | Insert Size | Cutter Diameter | Shank Type | Max. Depth of Cut | Shank Diameter | Effective Number of Teeth |
|---|---|---|---|---|---|---|

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Chipbreaker | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grades |
|---|---|---|---|---|---|---|
| P | Carbon Steel | ≤ 280HB | G | 100–**150**–200 | 0,10–**0,20**–0,30 | ACU2500 XCU2500 ACP2000 ACP3000 |
| | | > 280HB | G | 80–**100**–120 | 0,10–**0,20**–0,30 | |
| | Alloy Steel | ≤ 280HB | G | 100–**150**–80 | 0,10–**0,20**–0,30 | |
| M | Stainless Steel | ≤ 280HB | G | 80–**120**–160 | 0,10–**0,20**–0,30 | ACU2500 ACM200 ACM300 |
| K | Cast Iron Ductile Cast Iron | – | G | 100–**150**–200 | 0,10–**0,20**–0,30 | ACU2500 XCK2000 ACK2000 ACK3000 |
| S | Exotic Alloy | – | G | 40–**50**–60 | 0,10–**0,20**–0,30 | ACU2500 ACM200 ACM300 |
| N | Aluminum Alloy | Si ≤ 12,6% | S | 300–**500**–800 | 0,05–**0,10**–0,15 | DL2000 H20 |
| | | Si >12,6% | S | 100–**200**–250 | 0,05–**0,10**–0,15 | |

Min. - **Optimum** - Max.

Note:
The cutting conditions above are a guide. Actual conditions will need to be adjusted according to machine rigidity, work clamp rigidity, depth of cut and other factors.
There may be cases where machining cannot be performed under recommended cutting conditions, depending on the machine rigidity and work rigidity.

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT170524PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Corner radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Corner radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Corner radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

## Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 170502PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170508PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170512PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,2 | 1 |
| 170516PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,6 | 1 |
| AOMT 170502PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170505PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 170508PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170510PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 170512PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 170516PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 170520PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 170524PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 170530PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 1 |
| 170532PEER-G | ● | | ❑ | ❑ | | ❑ | ● | ● | ● | – | – | | 3,2 | 1 |
| 170540PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 4,0 | 1 |
| 170550PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 5,0 | 2 |
| 170564PEER-G | ❑ | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 6,4 | 2 |
| AOMT 170504PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 170508PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 170512PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 170516PEER-H | ● | | ❑ | ● | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 170502PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170516PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 170520PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 170524PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 170530PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 1 |
| 170532PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 1 |
| 170540PEER-F | ● | | – | | | – | | – | | – | – | – | 4,0 | 1 |
| 170550PEER-F | ● | | – | | | – | | – | | – | – | – | 5,0 | 2 |
| 170564PEER-F | ● | | – | | | – | | – | | – | – | – | 6,4 | 2 |
| AOET 170502PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 170504PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 170505PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 170508PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 170510PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 170512PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 170516PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 170520PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 170524PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 170530PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 1 |
| 170532PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 1 |
| 170540PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 4,0 | 1 |
| 170550PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 5,0 | 2 |
| 170564PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 6,4 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

Use peripheral inserts with RE ≤ 0,8 mm from the second step and above.

# WEZ 11000 M


## Modular Type

| Rake Angle | Radial | -7° – -18° |
|---|---|---|
| | Axial | 6° – 15° |

10 mm 90°



Fig. 1




## Head

Dimensions (mm)

| Cat. No. | Stock | DC | DCON | CRKS | OAL | LF | LS2 | L11 | H | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| WEZ 11016M08Z2 | ● | 16 | 8,5 | M8 | 42 | 25 | 5 | 8 | 13 | 2 | 0,03 | 1 |
| 11018M08Z2 | ● | 18 | 8,5 | M8 | 42 | 25 | 5 | 8 | 13 | 2 | 0,03 | 1 |
| 11020M10Z2 | ● | 20 | 10,5 | M10 | 49 | 30 | 5 | 8 | 15 | 2 | 0,06 | 1 |
| 11020M10Z3 | ● | 20 | 10,5 | M10 | 49 | 30 | 5 | 8 | 15 | 3 | 0,05 | 1 |
| 11022M10Z3 | ● | 22 | 10,5 | M10 | 49 | 30 | 5 | 8 | 15 | 3 | 0,06 | 1 |
| 11025M12Z2 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 2 | 0,11 | 1 |
| 11025M12Z3 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 3 | 0,10 | 1 |
| 11025M12Z4 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 4 | 0,10 | 1 |
| 11026M12Z4 | ● | 26 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 4 | 0,10 | 1 |
| 11026M12Z5 | ● | 26 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 5 | 0,09 | 1 |
| 11028M12Z4 | ● | 28 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 4 | 0,11 | 1 |
| 11028M12Z5 | ● | 28 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 5 | 0,10 | 1 |
| 11030M16Z2 | ● | 30 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,20 | 1 |
| 11030M16Z4 | ● | 30 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 4 | 0,19 | 1 |
| 11030M16Z5 | ● | 30 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 5 | 0,17 | 1 |
| 11032M16Z2 | ● | 32 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,22 | 1 |
| 11032M16Z3 | ● | 32 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 3 | 0,20 | 1 |
| 11032M16Z4 | ● | 32 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 4 | 0,20 | 1 |
| 11032M16Z5 | ● | 32 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 5 | 0,19 | 1 |
| 11035M16Z2 | ● | 35 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,24 | 1 |
| 11035M16Z5 | ● | 35 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 5 | 0,22 | 1 |
| 11040M16Z2 | ● | 40 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,28 | 1 |
| 11040M16Z4 | ● | 40 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 4 | 0,26 | 1 |
| 11040M16Z5 | ● | 40 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 5 | 0,26 | 1 |
| 11040M16Z6 | ● | 40 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 6 | 0,25 | 1 |

Inserts are sold separately. Arbor → H5.

## Spare Parts

| Applicable Cutters | Insert Screw | N·m | Wrench |
|---|---|---|---|
| WEZ 11016M08Z2 | BFTX0305IP | 1,5 | TRDR08IP |
| 11018M08Z2 | | | |
| 11020M10Z2–11040M16Z2 | BFTX0306IP | | |

## Identification Details

| WEZ | 11 | 016 | M 08 | Z2 |
|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Mounting Screw Size | Number of Teeth |

## Recommended Cutting Conditions

→ H. 28

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT11T324PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

Expansion

## ■ Inserts

Precautions for Mounting → H. 29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 11T302PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ● | 0,2 | 1 |
| 11T304PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 11T305PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 11T308PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 11T310PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 11T312PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 11T316PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 11T320PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 11T324PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 11T330PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 2 |
| 11T332PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 3,2 | 2 |
| AOMT 11T304PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 11T308PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 11T312PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 11T316PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 11T302PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T316PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 11T320PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 11T324PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 11T330PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 2 |
| 11T332PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 2 |
| AOET 11T302PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P16 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P16 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P16 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P20 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P20 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T302PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 11T302PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 11T304PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 11T305PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 11T308PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 11T310PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 11T312PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 11T316PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 11T320PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 11T324PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 11T330PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 2 |
| 11T332PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals


*P16 is applicable to cutter diameters Ø 14 mm and Ø 16 mm.
*P20 is applicable to cutter diameters Ø 18 mm, Ø 20 mm.
*P25 is applicable to cutter diameters Ø 25 mm, Ø 28 mm.

| Rake Angle | | |
|---|---|---|
| | Radial | -6° – -12° |
| | Axial | 6° – 15° |

15 mm 90°



Fig. 1




## Head

Dimensions (mm)

| Cat. No. | Stock | DC | DCON | CRKS | OAL | LF | LS2 | L11 | H | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| WEZ 17025M012Z2 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 2 | 0,08 | 1 |
| 17025M012Z3 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 3 | 0,07 | 1 |
| 17028M012Z2 | ● | 28 | 12,5 | M12 | 56 | 35 | 5 | 10 | 19 | 2 | 0,10 | 1 |
| 17030M016Z2 | ● | 30 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,17 | 1 |
| 17030M016Z3 | ● | 30 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 3 | 0,15 | 1 |
| 17032M016Z2 | ● | 32 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,19 | 1 |
| 17032M016Z3 | ● | 32 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 3 | 0,16 | 1 |
| 17032M016Z4 | ● | 32 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 4 | 0,14 | 1 |
| 17035M016Z2 | ● | 35 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,21 | 1 |
| 17035M016Z3 | ● | 35 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 3 | 0,19 | 1 |
| 17040M016Z2 | ● | 40 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 2 | 0,15 | 1 |
| 17040M016Z3 | ● | 40 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 3 | 0,23 | 1 |
| 17040M016Z4 | ● | 40 | 17 | M16 | 63 | 40 | 5 | 10 | 24 | 4 | 0,21 | 1 |

Inserts are sold separately. Arbor → H5.

## Spare Parts

| Applicable Cutters | Insert Screw | N·m | Wrench |
|---|---|---|---|
| WEZ 17025M12Z2–17030M16Z3 | BFTX0407IP | 3,0 | TRDR15IP |
| 17032M16Z2–17040M16Z4 | BFTX0409IP | | |

## Identification Details

| WEZ | 17 | 025 | M 12 | Z2 |
|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Mounting Screw Size | Number of Teeth |

## Recommended Cutting Conditions

→ H. 28

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT170524PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Corner radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Corner radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Corner radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

Expansion

## Inserts

Precautions for Mounting ⟶ H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 170502PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170508PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170512PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,2 | 1 |
| 170516PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,6 | 1 |
| AOMT 170502PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170505PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 170508PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170510PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 170512PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 170516PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 170520PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 170524PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 170530PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 1 |
| 170532PEER-G | ● | | ❑ | ❑ | | ❑ | ● | ● | ● | – | – | | 3,2 | 1 |
| 170540PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 4,0 | 1 |
| 170550PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 5,0 | 2 |
| 170564PEER-G | ❑ | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 6,4 | 2 |
| AOMT 170504PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 170508PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 170512PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 170516PEER-H | ● | | ❑ | ● | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 170502PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170516PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 170520PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 170524PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 170530PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 1 |
| 170532PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 1 |
| 170540PEER-F | ● | | – | | | – | | – | | – | – | – | 4,0 | 1 |
| 170550PEER-F | ● | | – | | | – | | – | | – | – | – | 5,0 | 2 |
| 170564PEER-F | ● | | – | | | – | | – | | – | – | – | 6,4 | 2 |
| AOET 170502PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-P25 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-P25 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170502PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-P32 | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-P32 | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-P32 | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| AOET 170502PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 170504PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 170505PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 170508PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 170510PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 170512PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 170516PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 170520PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 170524PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 170530PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 1 |
| 170532PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 1 |
| 170540PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 4,0 | 1 |
| 170550PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 5,0 | 2 |
| 170564PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 6,4 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P25 is applicable to cutter diameters Ø 25 mm and Ø 28 mm.
*P32 is applicable to cutter diameters Ø 30 mm, Ø 32 mm and Ø 35 mm.

# "Wave Mill" Series
# WEZR 11000 M

New


## Repeater, Modular Type

| Rake Angle | Radial | -12° |
|---|---|---|
| | Axial | 11° |

27 mm 90°



Fig. 1




## Head

Dimensions (mm)

| Cat. No. | Stock | DC | APMX | DCSFMS | DCON | CRKS | OAL | LF | LS2 | L11 | H | Total No. of Teeth | Steps | Effective No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| WEZR 11032M1627Z3 | ❍ | 32 | 27 | 28,5 | 17 | M16 | 73 | 50 | 5 | 12 | 24 | 9 | 3 | 3 | 0,21 | 1 |

Inserts are sold separately. Arbor → H5.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| | | N·m | |
| WEZR 11_ _ _ | BFTX0306IP | 1,5 | TRDR08IP |

## Identification Details

| WEZR | 11 | 032 | M16 | 27 | Z3 |
|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Mounting Screw Size | Max. Depth of Cut | Effective Number of Teeth |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Chipbreaker | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grades |
|---|---|---|---|---|---|---|
| P | Carbon Steel | ≤ 280HB | G | 100–**150**–200 | 0,08–**0,12**–0,20 | ACU2500 XCU2500 ACP2000 ACP3000 |
| | | > 280HB | G | 80–**100**–120 | 0,08–**0,12**–0,20 | |
| | Alloy Steel | ≤ 280HB | G | 100–**150**–80 | 0,08–**0,12**–0,20 | |
| M | Stainless Steel | ≤ 280HB | G | 80–**120**–160 | 0,08–**0,12**–0,20 | ACU2500 ACM200 ACM300 |
| K | Cast Iron Ductile Cast Iron | – | G | 100–**150**–200 | 0,08–**0,12**–0,20 | ACU2500 XCK2000 ACK2000 ACK3000 |
| S | Exotic Alloy | – | G | 40–**50**–60 | 0,08–**0,12**–0,20 | ACU2500 ACM200 ACM300 |
| N | Aluminum Alloy | Si ≤ 12,6% | S | 300–**500**–800 | 0,05–**0,10**–0,15 | DL2000 H20 |
| | | Si >12,6% | S | 100–**200**–250 | 0,05–**0,10**–0,15 | |

Min. - **Optimum** - Max.

Note:
The cutting conditions above are a guide. Actual conditions will need to be adjusted according to machine rigidity, work clamp rigidity, depth of cut and other factors.
There may be cases where machining cannot be performed under recommended cutting conditions, depending on the machine rigidity and work rigidity.

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT11T324PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

## ■ Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 11T302PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ● | 0,2 | 1 |
| 11T304PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 11T305PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 11T308PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 11T310PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 11T312PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 11T316PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 11T320PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 11T324PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 11T330PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 2 |
| 11T332PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 3,2 | 2 |
| AOMT 11T304PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 11T308PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 11T312PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 11T316PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 11T302PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 11T304PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 11T305PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 11T308PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 11T310PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 11T312PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 11T316PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 11T320PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 11T324PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 11T330PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 2 |
| 11T332PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 2 |
| AOET 11T302PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 11T304PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 11T305PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 11T308PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 11T310PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 11T312PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 11T316PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 11T320PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 11T324PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 11T330PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 2 |
| 11T332PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 2 |

Fig. 1






Fig. 2




L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

Use peripheral inserts with RE ≤ 0,8 mm from the second step and above.

# "Wave Mill" Series
# WEZR 17000 M

New


## Repeater, Modular Type

| Rake Angle | | |
|---|---|---|
| | Radial | -9° |
| | Axial | 10° |

29 mm 90°



Fig. 1




## Head

Dimensions (mm)

| Cat. No. | Stock | DC | APMX | DCSFMS | DCON | CRKS | OAL | LF | LS2 | L11 | H | Total No. of Teeth | Steps | Effective No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| WEZR 17040M1629Z3 | ❍ | 40 | 29 | 28,5 | 17 | M16 | 80 | 57 | 5 | 12 | 24 | 6 | 2 | 3 | 0,29 | 1 |

Inserts are sold separately. Arbor → H5.

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench |
|---|---|---|---|
| | | N·m | |
| WEZR 17_ _ _ | BFTX0409IP | 1,5 | TRDR15IP |

## Identification Details

| WEZR | 17 | 040 | M16 | 29 | Z3 |
|---|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Mounting Screw Size | Max. Depth of Cut | Effective Number of Teeth |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Chipbreaker | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grades |
|---|---|---|---|---|---|---|
| P | Carbon Steel | ≤ 280HB | G | 100–**150**–200 | 0,10–**0,20**–0,30 | ACU2500 XCU2500 ACP2000 ACP3000 |
| | | > 280HB | G | 80–**100**–120 | 0,10–**0,20**–0,30 | |
| | Alloy Steel | ≤ 280HB | G | 100–**150**–80 | 0,10–**0,20**–0,30 | |
| M | Stainless Steel | ≤ 280HB | G | 80–**120**–160 | 0,10–**0,20**–0,30 | ACU2500 ACM200 ACM300 |
| K | Cast Iron Ductile Cast Iron | – | G | 100–**150**–200 | 0,10–**0,20**–0,30 | ACU2500 XCK2000 ACK2000 ACK3000 |
| S | Exotic Alloy | – | G | 40–**50**–60 | 0,10–**0,20**–0,30 | ACU2500 ACM200 ACM300 |
| N | Aluminum Alloy | Si ≤ 12,6% | S | 300–**500**–800 | 0,05–**0,10**–0,15 | DL2000 H20 |
| | | Si >12,6% | S | 100–**200**–250 | 0,05–**0,10**–0,15 | |

Min. - **Optimum** - Max.

Note:
The cutting conditions above are a guide. Actual conditions will need to be adjusted according to machine rigidity, work clamp rigidity, depth of cut and other factors.
There may be cases where machining cannot be performed under recommended cutting conditions, depending on the machine rigidity and work rigidity.

*When mounting inserts with nose radius of ≥ 2,4 mm, modification of the body is required.



Modify this edge.

Reworking guidelines
Corner radius = 2,4 mm: C = 1 mm (AOMT170524PEER)
Corner radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Corner radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Corner radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Corner radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Corner radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius





● = Euro stock
○ = Japan stock
❑ = On request
– =Not available
N·m Recommended Tightening Torque (N·m)

## Inserts

Precautions for Mounting → H29

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | Carbide | DLC | Cermet | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light Cut | | P K M | P | | K | K | | M S | | | N | P | | |
| General Purpose | P K M S | P K M | | P | K | | K | M S | M S | N | N | | | |
| Roughing | P K M S | | | P | | | K | | M S | | | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP2000 | ACP3000 | XCK2000 | ACK2000 | ACK3000 | ACM200 | ACM300 | H20 | DL2000 | T2500A | RE | Fig. |
| AOMT 170502PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170508PEER-L | ● | ❍ | – | ● | ❍ | – | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170512PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,2 | 1 |
| 170516PEER-L | ● | | – | ❑ | | – | ❑ | ● | ● | – | – | | 1,6 | 1 |
| AOMT 170502PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 0,2 | 1 |
| 170504PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,4 | 1 |
| 170505PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 0,5 | 1 |
| 170508PEER-G | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | ● | 0,8 | 1 |
| 170510PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | ❑ | 1,0 | 1 |
| 170512PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | ❑ | 1,2 | 1 |
| 170516PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 1,6 | 1 |
| 170520PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 2,0 | 1 |
| 170524PEER-G | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 2,4 | 1 |
| 170530PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 3,0 | 1 |
| 170532PEER-G | ● | | ❑ | ❑ | | ❑ | ● | ● | ● | – | – | | 3,2 | 1 |
| 170540PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 4,0 | 1 |
| 170550PEER-G | ● | | ❑ | ● | | ❑ | ● | ● | ● | – | – | | 5,0 | 2 |
| 170564PEER-G | ❑ | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | | 6,4 | 2 |
| AOMT 170504PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,4 | 1 |
| 170508PEER-H | ● | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | – | 0,8 | 1 |
| 170512PEER-H | ● | | ❑ | ❑ | | ❑ | ❑ | ● | ● | – | – | – | 1,2 | 1 |
| 170516PEER-H | ● | | ❑ | ● | | ❑ | ❑ | ● | ● | – | – | – | 1,6 | 1 |
| AOET 170502PEER-F | ● | | – | | | – | | – | | – | – | – | 0,2 | 1 |
| 170504PEER-F | ● | | – | | | – | | – | | – | – | – | 0,4 | 1 |
| 170505PEER-F | ● | | – | | | – | | – | | – | – | – | 0,5 | 1 |
| 170508PEER-F | ● | | – | | | – | | – | | – | – | – | 0,8 | 1 |
| 170510PEER-F | ● | | – | | | – | | – | | – | – | – | 1,0 | 1 |
| 170512PEER-F | ● | | – | | | – | | – | | – | – | – | 1,2 | 1 |
| 170516PEER-F | ● | | – | | | – | | – | | – | – | – | 1,6 | 1 |
| 170520PEER-F | ● | | – | | | – | | – | | – | – | – | 2,0 | 1 |
| 170524PEER-F | ● | | – | | | – | | – | | – | – | – | 2,4 | 1 |
| 170530PEER-F | ● | | – | | | – | | – | | – | – | – | 3,0 | 1 |
| 170532PEER-F | ● | | – | | | – | | – | | – | – | – | 3,2 | 1 |
| 170540PEER-F | ● | | – | | | – | | – | | – | – | – | 4,0 | 1 |
| 170550PEER-F | ● | | – | | | – | | – | | – | – | – | 5,0 | 2 |
| 170564PEER-F | ● | | – | | | – | | – | | – | – | – | 6,4 | 2 |
| AOET 170502PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,2 | 1 |
| 170504PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,4 | 1 |
| 170505PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,5 | 1 |
| 170508PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 0,8 | 1 |
| 170510PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,0 | 1 |
| 170512PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,2 | 1 |
| 170516PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 1,6 | 1 |
| 170520PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,0 | 1 |
| 170524PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 2,4 | 1 |
| 170530PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,0 | 1 |
| 170532PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 3,2 | 1 |
| 170540PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 4,0 | 1 |
| 170550PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 5,0 | 2 |
| 170564PEFR-S | – | – | – | – | – | – | – | – | – | ● | ● | – | 6,4 | 2 |

Fig. 1






Fig. 2





L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

Use peripheral inserts with RE ≤ 0,8 mm from the second step and above.



## General Features

Wide Application Range



## Ramping (Slant Milling)


| Tool Diam. Ø D | Max. Ramping Angle | | |
|---|---|---|---|
| | Type 1000 | Type 2000 | Type 3000 |
| 10 | 2°30' | | |
| 12 | 1°45' | | |
| 14 | 1°25' | 1°40' | |
| 16 | 1°00 | 1°20' | |
| 18 | 0°45' | 1°10' | |
| 20 | 0°30' | 1°00' | |
| 25 | 0°30' | 0°45' | 1°30' |
| 32 | 0°25' | 0°35' | 1°00' |
| 40 | 0°20' | 0°25' | 0°45' |
| 50 | 0°15' | 0°20' | 0°30' |
| 63 | 0°10' | 0°15' | 0°20' |
| 80 | | | 0°15' |
| 100 | | | – |

Maximum ramping angle ($\alpha$ max. max.) depends on cutter diameter.


### ● Precision insert with strong cutting edge and low cutting force

Wave shaped cutting edge design lowers cutting resistance yet improves cutting edge strength.
Achieving high quality finish with high precision cutting edge.
Smooth cutting even for deep grooves and low rigidity machines.

High precision curved cutting edge




High rake wave cutting edge






### ● Internal Coolant Holes

Improved chip evacuation with air or coolant supply.

### ● Wide Variety of Inserts

6 types of chipbreaker design
(L, G, H, E, EH and S)
9 milling grades for a wide range of work materials and applications.
- ACP100, ACP200, ACP300
  (steel milling grades)
- ACK200, ACK300
  (cast iron milling grades)
- ACM200, ACM300
  (stainless steel, exotic alloy milling grades)
- DL1000, H1
  (aluminium milling grades)

### ● High Durable Body

Special surface treatment improves corrosion resistance as well as scratch resistance.
Increased screw size improves clamping force and durability.

## Product Range

| Type | Cat. No. | Series | Diameter Range (mm) | Image |
|---|---|---|---|---|
| Shank | WEX 1000E | Short Type | 10 – 25 |  |
| | WEX 1000EL | Long Type | 10 – 20 | |
| | WEX 2000E | Short Type | 14 – 63 | |
| | WEX 2000EL | Long Type | 14 – 40 | |
| | WEX 2000EW | Weldon Shank Short Type | 16 – 20 | |
| | WEX 3000E | Short Type | 25 – 63 | |
| | WEX 3000EL | Long Type | 25 – 40 | |
| | WEX 3000EW | Weldon Shank Short Type | 25 – 32 | |
| Shell | WEX 1000F | Shell Type | 32 – 63 |   → G58 |
| | WEX 2000F | Shell Type | 40 – 63 | |
| | WEX 3000F | Shell Type | 40 – 63 | |
| Modular | WEX 2000M | ModularType | 16 – 40 |  |
| | WEX 3000M | Modular Type | 25 – 40 | |

WEX3000 WEX2000 WEX1000

## WEX1000 Type Expansion


- Efficient machining via high number of inserts
- Precise insert change tolerance provides high surface roughness qualitiy
- High shoulder accuracy due to optimized cutting edge
- Stable cutting conditions when utilising low rigidity machines
- Economic advantages using small AXMT06 inserts




WEX3000 WEX2000 WEX1000

## Application Range






Shoulder Milling





## Chipbreaker Selection





## Characteristics

| Work Material | Steel, Cast Iron | | | Stainless Steel, Exotic Alloy | | Aluminium |
|---|---|---|---|---|---|---|
| Chipbreaker | L | G | H | E | EH | S |
| |  |  |  |  |  |  |
| Features | Low Cutting Force | General Purpose | Strong Edged | General Purpose | Strong Edged | High Rake |
| Chipbreaker Profile for 1000 Series Insert |  25° |  25° |  15° | | | |
| Chipbreaker Profile for 2000 Series Insert | |  28° |  20° |  17° |  17° |  27° |
| Chipbreaker Profile for 3000 Series Insert |  25° |  20° |  5° |  14° |  8° |  30° |
| Application | Light cut, low rigidity milling and reduced burrs | **Main chipbreaker** general purpose to interrupted milling | Roughing, heavy interrupted and hardened steel milling | Light cutting to general purpose | Heavy interrupted machining | Aluminium, non-ferrous metal |

## Grade Selection




# WEX 1000 E/L

## WEX 1000 E/EL

### Shank Type

| Rake Angle | | |
|---|---|---|
| | Radial | 8°–15° |
| | Axial | 16°–24° |

5 mm 90°




### Body (Short Type „E“)


| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 1010 E | ▲ | 10 | 10 | 17 | 33 | 50 | 2 | 0,03 |
| 1012 E | ▲ | 12 | 12 | 20 | 60 | 80 | 3 | 0,06 |
| 1014 E | ▲ | 14 | 16 | 22 | 59 | 80 | 3 | 0,10 |
| 1016 E | ▲ | 16 | 16 | 20 | 72 | 90 | 4 | 0,12 |
| 1018 E | ▲ | 18 | 20 | 20 | 80 | 100 | 4 | 0,21 |
| WEX 1020 E | ▲ | 20 | 20 | 22 | 78 | 100 | 5 | 0,22 |
| 1025 E | ▲ | 25 | 20 | 25 | 90 | 115 | 7 | 0,27 |

### Body (Long Type „EL“)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 1010 EL | ▲ | 10 | 8 | 17 | 83 | 100 | 2 | 0,03 |
| 1012 EL | ▲ | 12 | 10 | 20 | 100 | 120 | 2 | 0,06 |
| 1014 EL | ▲ | 14 | 12 | 20 | 125 | 145 | 3 | 0,11 |
| 1016 EL | ▲ | 16 | 14 | 20 | 140 | 160 | 3 | 0,17 |
| 1016 EL15 | ▲ | 16 | 15 | 20 | 140 | 160 | 3 | 0,19 |
| 1018 EL | ▲ | 18 | 16 | 20 | 160 | 180 | 3 | 0,25 |
| WEX 1020 EL | ▲ | 20 | 18 | 25 | 175 | 200 | 4 | 0,36 |
| 1020 EL19 | ▲ | 20 | 19 | 25 | 175 | 200 | 4 | 0,38 |

Inserts are not included.

### Inserts for WEX1000 Type




| Application | Coated Carbide | | | | | | | Carbide | DLC | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M S | | K N | N | |
| General Purpose | | P M | P M | K | | M S | M S | | N | |
| Roughing | | P M | P M | | K | | M S | | | |
| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
| AXMT 060204 PDER-L | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | – | – | 0,4 |
| 060208 PDER-L | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | – | – | 0,8 |
| 060212 PDER-L | | ▲ | | | ❍ | ▲ | ▲ | – | – | 1,2 |
| AXMT 060204 PDER-G | ▲ | ▲ | ▲ | ❍ | ▲ | ▲ | ▲ | – | – | 0,4 |
| 060208 PDER-G | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | ▲ | – | – | 0,8 |
| 060212 PDER-G | ❍ | ▲ | ▲ | | ▲ | ▲ | ▲ | – | – | 1,2 |
| AXMT 060204 PDER-H | ❍ | ▲ | ▲ | | ▲ | ▲ | ▲ | – | – | 0,4 |
| 060208 PDER-H | | ▲ | ▲ | | ▲ | ▲ | ▲ | – | – | 0,8 |
| 060212 PDER-H | ❍ | ▲ | ▲ | | ▲ | ▲ | ▲ | – | – | 1,2 |
| AXMT 060202 PDFR-S | – | – | – | – | – | – | – | ❍ | ❍ | 0,2 |

L - Low cutting force
G - General type
H - Strong cutting edge
S - For aluminium alloy

### Identification Details

| WEX | 1 | 016 | EL | 15 |
|---|---|---|---|---|
| Cutter Series | 1000 Series | Cutter Diameter | Shank Type | Shank Diameter |

### Spare Parts

| Screw | Wrench | Applicable Endmill |
|---|---|---|
| 0,5 N·m | | |
| BFTX 01804 IP | TRX 06 IP | WEX 1000 |






❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
N·m Recommended Tightening Torque (N·m)

## WEX 2000 E/EL

### Shank Type

| Rake Angle | | |
|---|---|---|
| | Radial | 8°–15° |
| | Axial | 16°–24° |

10 mm 90°




#### Body (Short Type „E“)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 2014 E | ▲ | 14 | 16 | 25 | 55 | 80 | 1 | 0,10 |
| 2016 E | ▲ | 16 | 16 | 25 | 75 | 100 | 2 | 0,13 |
| 2018 E | ▲ | 18 | 16 | 25 | 75 | 100 | 2 | 0,14 |
| WEX 2020 E | ▲ | 20 | 20 | 30 | 80 | 110 | 3 | 0,22 |
| 2022 E | ▲ | 22 | 20 | 30 | 80 | 110 | 3 | 0,23 |
| WEX 2025 E | ▲ | 25 | 25 | 35 | 85 | 120 | 4 | 0,38 |
| 2028 E | ❍ | 28 | 25 | 35 | 85 | 120 | 4 | 0,39 |
| 2030 E | ▲ | 30 | 25 | 35 | 85 | 120 | 4 | 0,40 |
| WEX 2032 E | ▲ | 32 | 32 | 40 | 90 | 130 | 5 | 0,70 |
| 2040 E | ❍ | 40 | 32 | 30 | 120 | 150 | 6 | 0,91 |
| WEX 2050 E | ❍ | 50 | 32 | 30 | 120 | 150 | 7 | 1,02 |
| 2063 E | ❍ | 63 | 32 | 30 | 120 | 150 | 8 | 1,22 |

#### Body (Long Type „EL“)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 2014 EL | ▲ | 14 | 16 | 25 | 95 | 120 | 1 | 0,14 |
| 2016 EL | ▲ | 16 | 16 | 25 | 120 | 145 | 2 | 0,19 |
| 2018 EL | ❍ | 18 | 16 | 25 | 120 | 145 | 2 | 0,19 |
| WEX 2020 EL | ▲ | 20 | 20 | 40 | 110 | 150 | 2 | 0,32 |
| 2022 EL | ❍ | 22 | 20 | 30 | 120 | 150 | 2 | 0,33 |
| WEX 2025 EL | ▲ | 25 | 25 | 50 | 120 | 170 | 2 | 0,55 |
| 2028 EL | ❍ | 28 | 25 | 30 | 140 | 170 | 2 | 0,59 |
| 2030 EL | ❍ | 30 | 25 | 30 | 140 | 170 | 2 | 0,60 |
| WEX 2032 EL | ❍ | 32 | 32 | 60 | 120 | 180 | 2 | 0,99 |
| 2040 EL | ❍ | 40 | 32 | 30 | 150 | 180 | 2 | 1,12 |

#### Body (Long Type „E“ + Small Shank)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 2016 EL15 | ▲ | 16 | 15 | 25 | 120 | 145 | 2 | 0,17 |
| 2020 EL19 | ▲ | 20 | 19 | 40 | 110 | 150 | 2 | 0,30 |
| 2025 EL24 | ▲ | 25 | 24 | 50 | 120 | 170 | 2 | 0,53 |
| 2025 EL24Z3 | ▲ | 25 | 24 | 50 | 120 | 170 | 3 | 0,50 |
| 2032 EL30Z4 | ▲ | 32 | 30 | 60 | 120 | 180 | 2 | 0,95 |

#### Body (Weldon Shank Short Type „EW“)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 2016 EW | ▲ | 16 | 16 | 25 | 75 | 100 | 2 | 0,12 |
| 2020 EW | ▲ | 20 | 20 | 30 | 80 | 110 | 3 | 0,21 |

Inserts are not included.

### Identification Details

| WEX | 2 | 016 | EL | 15 |
|---|---|---|---|---|
| Cutter Series | 2000 Series | Cutter Diameter | Shank Type | Shank Diameter |

### Spare Parts

| Screw | Wrench | Applicable Endmill |
|---|---|---|
| 2,0 N·m | | |
| BFTX 0305 IP | TRDR 08 IP | WEX 2014 – WEX 2018 |
| BFTX 0306 IP | | WEX 2020 – WEX 2063 |




## WEX 2000 M

### Modular Type

| Rake Angle | | |
|---|---|---|
| | Radial | 10°–18° |
| | Axial | 14°–25° |

10mm 90°





#### Head

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| WEX 2016M08Z2 | ▲ | 16 | 8,5 | M8 | 42 | 25 | 5 | 17 | 8 | 13 | 2 |
| 2018M08Z2 | ❍ | 18 | 8,5 | M8 | 42 | 25 | 5 | 17 | 8 | 13 | 2 |
| WEX 2020M10Z3 | ▲ | 20 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 3 |
| 2022M10Z3 | ❍ | 22 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 3 |
| WEX 2025M12Z4 | ▲ | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 4 |
| 2028M12Z4 | ❍ | 28 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 4 |
| WEX 2030M16Z4 | ❍ | 30 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 4 |
| 2032M16Z5 | ▲ | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 5 |
| 2040M16Z6 | ❍ | 40 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 6 |

Inserts are not included.

### Inserts for WEX2000 Type




| Application | Coated Carbide | | | | | | | Carbide | DLC | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M/S | | K/N | N | |
| General Purpose | | P/M | P/M | K | | M/S | M/S | | N | |
| Roughing | | P/M | P/M | | K | | M/S | | | |
| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
| AXMT 123504 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 123508 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 123512 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 123504 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 123508 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 123512 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 123504 PEER-E | | | | | | ▲ | ▲ | – | – | 0,4 |
| 123508 PEER-E | | | | | | ▲ | ▲ | – | – | 0,8 |
| 123512 PEER-E | | | | | | ▲ | ▲ | – | – | 1,2 |
| AXMT 123508 PEER-EH | | | | | | ▲ | ▲ | – | – | 0,8 |
| AXET 123502 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,2 |
| 123504 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,4 |
| 123508 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,8 |

G - General type
H - Strong cutting edge
E - For stainless steel / exotic alloy
EH - Strong edge for stainless steel / exotic alloy
S - For aluminium alloy

– Unable to produce

### Identification Details

| WEX | 2 | 016 | M08 | Z2 |
|---|---|---|---|---|
| Cutter Series | 2000 Series | Cutter Diameter | Mounting Screw Size | No. of Teeth |




### Spare Parts


| Screw | Wrench | N·m | Applicable Endmill |
|---|---|---|---|
| BFTX 0305 IP | TRDR 08 IP | 2,0 | WEX 2016M, WEX 2018M |
| BFTX 0306 IP | | 2,0 | WEX 2020M – WEX 2040M |
| BFTX 0407 IP | TRDR 15 IP | 3,0 | WEX 3025M – WEX 3030M |
| BFTX 0409 IP | | 3,0 | WEX 3032M – WEX 3040M |

## WEX 3000 E/EL

### Shank Type

Rake Angle: Radial 8°–15°, Axial 16°–24°

14 mm, 90°




▲

### Body (Short Type „E“)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 3025 E | ▲ | 25 | 25 | 35 | 85 | 120 | 2 | 0,37 |
| 3028 E | ❍ | 28 | 25 | 35 | 85 | 120 | 2 | 0,39 |
| 3030 E | ❍ | 30 | 25 | 40 | 90 | 130 | 3 | 0,42 |
| WEX 3032 E | ▲ | 32 | 32 | 40 | 90 | 130 | 3 | 0,67 |
| 3035 E | ▲ | 35 | 32 | 40 | 90 | 130 | 3 | 0,69 |
| 3040 E | ▲ | 40 | 32 | 50 | 120 | 170 | 4 | 1,01 |
| 3050 E | ❍ | 50 | 32 | 50 | 120 | 170 | 5 | 1,23 |
| 3063 E | ❍ | 63 | 32 | 50 | 120 | 170 | 6 | 1,58 |

### Body (Short Type „E“ + Small Shank)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 3025 E20 | ❍ | 25 | 20 | 35 | 85 | 120 | 2 | 0,25 |
| 3032 E25 | ❍ | 32 | 25 | 40 | 90 | 130 | 3 | 0,43 |

### Body (Long Type „EL“)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 3025 EL | ▲ | 25 | 25 | 50 | 120 | 170 | 2 | 0,54 |
| 3028 EL | ❍ | 28 | 25 | 50 | 120 | 170 | 2 | 0,56 |
| 3030 EL | ❍ | 30 | 25 | 60 | 120 | 180 | 2 | 0,60 |
| WEX 3032 EL | ▲ | 32 | 32 | 60 | 120 | 180 | 2 | 0,95 |
| 3035 EL | ▲ | 35 | 32 | 60 | 120 | 180 | 2 | 0,98 |
| 3040 EL | ▲ | 40 | 32 | 80 | 140 | 220 | 2 | 1,38 |

### Body (Weldon Shank Short Type „EW“)

| Cat. No. | Stock | Dimensions (mm) | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LH | LS | LF | | |
| WEX 3025 EW | ▲ | 25 | 25 | 35 | 85 | 120 | 2 | 0,36 |
| 3032 EW | ▲ | 32 | 32 | 40 | 90 | 130 | 3 | 0,65 |

Inserts are not included.

∗ **ATTENTION**: If nose radius of inserts is 2,0 mm or more please modify cutter body as indicated.



Standard Chamfer is 0,5 mm by 45 degrees

Increase Chamfer to 1 mm x 45 degrees
when using 2,0 mm radius inserts
AXMT 170520PEER

Increase chamfer to 1,5 mm x 45 degrees
when using 3,0 mm radius inserts
AXMT 170530 PEER

### Spare Parts


| Screw | Wrench | Applicable Endmill |
|---|---|---|
| 3,0 (N·m) | | |
| BFTX 0407 IP<br>BFTX 0409 IP | TRDR 15 IP | WEX 3025 – WEX 3030<br>WEX 3032 – WEX 3063 |

## WEX 3000 M

### Modular Type

Rake Angle: Radial 8°–15°, Axial 16°–24°

14 mm, 90°





### Head

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| WEX 3025M12Z2 | ▲ | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 |
| 3028M12Z2 | ❍ | 28 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 |
| WEX 3030M16Z3 | ❍ | 30 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |
| 3032M16Z3 | ▲ | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |
| 3035M16Z3 | ❍ | 35 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |
| 3040M16Z4 | ❍ | 40 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 4 |

Inserts are not included.

### Inserts for WEX3000 Type





| Application | Coated Carbide | | | | | | | Carbide | DLC | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M S | | K N | N | |
| General Purpose | | P M | P M | K | | M S | M S | | N | |
| Roughing | | P M | P M | | K | | M S | | | |
| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
| AXMT 170508 PEER-L | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| AXMT 170504 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 170508 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 170512 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| 170516 PEER-G | ❍ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,6 |
| 170520 PEER-G* | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 2,0 |
| 170530 PEER-G* | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 3,0 |
| AXMT 170508 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 170512 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 170504 PEER-E | | | | | | ▲ | ▲ | – | – | 0,4 |
| 170508 PEER-E | | | | | | ▲ | ▲ | – | – | 0,8 |
| 170512 PEER-E | | | | | | ▲ | ▲ | – | – | 1,2 |
| 170516 PEER-E | | | | | | ▲ | ▲ | – | – | 1,6 |
| 170520 PEER-E* | | | | | | ▲ | ▲ | – | – | 2,0 |
| 170530 PEER-E* | | | | | | ▲ | ▲ | – | – | 3,0 |
| AXMT 170508 PEER-EH | | | ▲ | | | ▲ | ▲ | – | – | 0,8 |
| AXET 170502 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,2 |
| 170504 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,4 |
| 170508 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,8 |

L - Low cutting force
G - General type
H - Strong cutting edge
E - For stainless steel / exotic alloy
EH - Strong edge for stainless steel / exotic alloy
S - For aluminium alloy

– Unable to produce
∗ Cutter body modification is required

### Identification Details

| WEX | 3 | 025 | M12 | Z2 |
|---|---|---|---|---|
| Cutter Series | 3000 Series | Cutter Diameter | Mounting Screw Size | No. of Teeth |









❍ = Japan stock

❑ = Delivery on request
▲ = To be replaced by new item

(N·m) Recommended Tightening Torque (N·m)

## Recommended Cutting Conditions




### WEX1000 Series

Cutter: WEX1012E Insert: AXMT060208PDER - ☐

Cutting Data: $a_p$ = 4 mm, $a_e$ = 1 mm, dry

| ISO | Material | HB | Chipbreaker | Coated Carbide | | | | | | | | | | | | | | | | | | | | | „Diamond like Carbon" Coated Carbide | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | ACP100 | | | ACP200 | | | ACP300 | | | ACK200 | | | ACK300 | | | ACM200 | | | ACM300 | | | DL1000 | | |
| | | | | Feed Rate (mm/tooth) | | | | | | | | | | | | | | | | | | | | | | | |
| | | | | 0,08 | 0,12 | 0,16 | 0,08 | 0,12 | 0,16 | 0,08 | 0,12 | 0,16 | 0,10 | 0,15 | 0,20 | 0,10 | 0,15 | 0,20 | 0,08 | 0,10 | 0,12 | 0,08 | 0,10 | 0,12 | | | |
| | | | | Cutting Speed $v_c$ (m/min) | | | | | | | | | | | | | | | | | | | | | | | |
| P | Unalloyed steel, <0, 15%C, annealed | 125 | G | 280 | 240 | 220 | 240 | 220 | 200 | 220 | 200 | 180 | | | | | | | | | | | | | | | |
| | " , <0, 45%C, annealed | 190 | G | 200 | 180 | 160 | 180 | 160 | 140 | 180 | 160 | 140 | | | | | | | | | | | | | | | |
| | " , <0, 45%C, tempered | 250 | G | 180 | 120 | 140 | 160 | 140 | 120 | 150 | 130 | 110 | | | | | | | | | | | | | | | |
| | " , <0, 75%C, annealed | 270 | G | 160 | 140 | 120 | 150 | 130 | 110 | 130 | 110 | 110 | | | | | | | | | | | | | | | |
| | " , <0, 75%C, tempered | 300 | G | 100 | 80 | 70 | 90 | 70 | 60 | 70 | 60 | 50 | | | | | | | | | | | | | | | |
| | Low alloyed steel, annealed | 180 | G | 200 | 180 | 160 | 180 | 160 | 150 | 160 | 150 | 130 | | | | | | | | | | | | | | | |
| | " , tempered | 275 | G | 130 | 110 | 90 | 120 | 100 | 90 | 100 | 90 | 80 | | | | | | | | | | | | | | | |
| | " , tempered | 300 | G | 120 | 100 | 80 | 100 | 90 | 80 | 90 | 80 | 60 | | | | | | | | | | | | | | | |
| | " , tempered | 350 | G | 90 | 80 | 60 | 80 | 70 | 60 | 70 | 60 | 40 | | | | | | | | | | | | | | | |
| | High alloyed and tool steel, annealed | 200 | G | 180 | 170 | 160 | 170 | 160 | 130 | 150 | 140 | 120 | | | | | | | | | | | | | | | |
| | " , tempered | 325 | G | 100 | 80 | 60 | 80 | 60 | 50 | 60 | 50 | 30 | | | | | | | | | | | | | | | |
| M | Stainless steel, ferritic/martensitic, annealed | 200 | E | | | | | | | | | | | | | | | | 175 | 150 | 120 | 140 | 130 | 110 | | | |
| | Martensitic, tempered | 240 | E | | | | | | | | | | | | | | | | 140 | 120 | 100 | 120 | 100 | 90 | | | |
| | Austenitic, plunged | 180 | E | | | | | | | | | | | | | | | | 180 | 160 | 140 | 160 | 140 | 130 | | | |
| K | Grey cast iron | | G | | | | | | | | | | 240 | 220 | 200 | 220 | 200 | 180 | | | | | | | | | |
| | Nodular cast iron | | G | | | | | | | | | | 160 | 140 | 120 | 140 | 120 | 100 | | | | | | | | | |
| S | High tempered resist. alloys, Fe based, annealed | | E | | | | | | | | | | | | | | | | 50 | 35 | | 45 | 25 | | | | |
| N | Aluminium alloy, Si < 13% | | | | | | | | | | | | | | | | | | | | | | | | 800 | 600 | 400 |
| | Aluminium alloy, Si > 13% | | | | | | | | | | | | | | | | | | | | | | | | 240 | 200 | 160 |
| | Copper alloy | | | | | | | | | | | | | | | | | | | | | | | | 330 | 300 | 270 |


The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.

For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

### WEX2000 Series

Cutter: WEX2025E Insert: AXMT123508PEER - ☐

Cutting Data: $a_p$ = 3 mm, $a_e$ = 12,5 mm, dry





| ISO | Material | HB | Chipbreaker | Coated Carbide | | | | | | | | | | | | | | | | | | | | | „Diamond like Carbon" Coated Carbide | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | ACP100 | | | ACP200 | | | ACP300 | | | ACK200 | | | ACK300 | | | ACM200 | | | ACM300 | | | DL1000 | | |
| | | | | Feed Rate (mm/tooth) | | | | | | | | | | | | | | | | | | | | | | | |
| | | | | 0,08 | 0,15 | 0,20 | 0,08 | 0,15 | 0,20 | 0,08 | 0,15 | 0,20 | 0,08 | 0,15 | 0,20 | 0,08 | 0,15 | 0,20 | 0,08 | 0,15 | 0,20 | 0,08 | 0,15 | 0,20 | 0,05 | 0,15 | 0,22 |
| | | | | Cutting Speed $v_c$ (m/min) | | | | | | | | | | | | | | | | | | | | | | | |
| P | Unalloyed steel, <0, 15%C, annealed | 125 | G | 380 | 350 | 330 | 350 | 330 | 315 | 330 | 315 | 295 | | | | | | | | | | | | | | | |
| | " , <0, 45%C, annealed | 190 | G | 285 | 255 | 235 | 255 | 235 | 220 | 235 | 220 | 220 | | | | | | | | | | | | | | | |
| | " , <0, 45%C, tempered | 250 | G | 235 | 210 | 190 | 210 | 190 | 170 | 190 | 170 | 150 | | | | | | | | | | | | | | | |
| | " , <0, 75%C, annealed | 270 | G | 190 | 162 | 143 | 171 | 152 | 133 | 152 | 133 | 115 | | | | | | | | | | | | | | | |
| | " , <0, 75%C, tempered | 300 | G | 145 | 115 | 95 | 115 | 95 | 75 | 95 | 75 | 55 | | | | | | | | | | | | | | | |
| | Low alloyed steel, annealed | 180 | G | 265 | 235 | 220 | 235 | 220 | 200 | 220 | 200 | 180 | | | | | | | | | | | | | | | |
| | " , tempered | 275 | G | 170 | 145 | 125 | 150 | 130 | 115 | 130 | 115 | 95 | | | | | | | | | | | | | | | |
| | " , tempered | 300 | G | 150 | 125 | 105 | 135 | 115 | 95 | 115 | 95 | 75 | | | | | | | | | | | | | | | |
| | " , tempered | 350 | G | 125 | 95 | 75 | 105 | 85 | 65 | 85 | 65 | 45 | | | | | | | | | | | | | | | |
| | High alloyed and tool steel, annealed | 200 | G | 235 | 210 | 190 | 210 | 190 | 170 | 190 | 170 | 150 | | | | | | | | | | | | | | | |
| | " , tempered | 325 | G | 125 | 95 | 75 | 95 | 75 | 55 | 75 | 55 | 35 | | | | | | | | | | | | | | | |
| M | Stainless steel, ferritic/martensitic, annealed | 200 | E | | | | | | | | | | | | | | | | 175 | 155 | 125 | 155 | 140 | 110 | | | |
| | Martensitic, tempered | 240 | EH | | | | | | | | | | | | | | | | 160 | 140 | 110 | 145 | 125 | 100 | | | |
| | Austenitic, plunged | 180 | E | | | | | | | | | | | | | | | | 190 | 170 | 140 | 170 | 150 | 125 | | | |
| K | Grey cast iron | | G | | | | | | | | | | 285 | 255 | 235 | 255 | 235 | 220 | | | | | | | | | |
| | Nodular cast iron | | G | | | | | | | | | | 190 | 160 | 140 | 160 | 140 | 125 | | | | | | | | | |
| S | High tempered resist. alloys, Fe based, annealed | 300 | E | | | | | | | | | | | | | | | | 50 | 40 | | 45 | 35 | | | | |
| | " , hardened | 330 | E | | | | | | | | | | | | | | | | 35 | 25 | | 30 | 20 | | | | |
| N | Aluminium alloy, Si < 13% | | S | | | | | | | | | | | | | | | | | | | | | | 1000 | 750 | 500 |
| | Aluminium alloy, Si > 13% | | S | | | | | | | | | | | | | | | | | | | | | | 250 | 200 | 170 |
| | Copper alloy | | S | | | | | | | | | | | | | | | | | | | | | | 350 | 330 | 300 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.

For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

## ■ Recommended Cutting Conditions

### ● WEX3000 Series




Cutter: WEX30325E Insert: AXMT170508PEER - □

Cutting Data: $a_p$ = 5 mm, $a_e$ = 16 mm, dry

| ISO | Material | HB | Chipbreaker | Coated Carbide | | | | | | | | | | | | | | | | | | | | | „Diamond like Carbon" Coated Carbide | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | ACP100 | | | ACP200 | | | ACP300 | | | ACK200 | | | ACK300 | | | ACM200 | | | ACM300 | | | DL1000 | | |
| | | | | Feed Rate (mm/tooth) | | | | | | | | | | | | | | | | | | | | | | | |
| | | | | 0,12 | 0,25 | 0,35 | 0,12 | 0,25 | 0,35 | 0,12 | 0,25 | 0,35 | 0,12 | 0,25 | 0,35 | 0,12 | 0,25 | 0,35 | 0,12 | 0,25 | 0,35 | 0,12 | 0,25 | 0,35 | 0,05 | 0,15 | 0,25 |
| | | | | Cutting Speed $v_c$ (m/min) | | | | | | | | | | | | | | | | | | | | | | | |
| P | Unalloyed steel, <0, 15%C, annealed | 125 | G | 400 | 370 | 350 | 370 | 350 | 330 | 350 | 330 | 310 | | | | | | | | | | | | | | | |
| | " , <0, 45%C, annealed | 190 | G | 300 | 270 | 250 | 270 | 250 | 230 | 250 | 230 | 210 | | | | | | | | | | | | | | | |
| | " , <0, 45%C, tempered | 250 | G | 250 | 220 | 200 | 220 | 200 | 180 | 200 | 180 | 160 | | | | | | | | | | | | | | | |
| | " , <0, 75%C, annealed | 270 | G | 200 | 170 | 150 | 180 | 160 | 140 | 160 | 140 | 120 | | | | | | | | | | | | | | | |
| | " , <0, 75%C, tempered | 300 | G | 150 | 120 | 100 | 120 | 100 | 80 | 100 | 80 | 60 | | | | | | | | | | | | | | | |
| | Low alloyed steel, annealed | 180 | G | 280 | 250 | 230 | 250 | 230 | 210 | 230 | 210 | 190 | | | | | | | | | | | | | | | |
| | " , tempered | 275 | G | 180 | 150 | 130 | 160 | 140 | 120 | 140 | 120 | 100 | | | | | | | | | | | | | | | |
| | " , tempered | 300 | G | 160 | 130 | 110 | 140 | 120 | 100 | 120 | 100 | 80 | | | | | | | | | | | | | | | |
| | " , tempered | 350 | G | 130 | 100 | 80 | 110 | 90 | 70 | 90 | 70 | 50 | | | | | | | | | | | | | | | |
| | High alloyed and tool steel, annealed | 200 | G | 250 | 220 | 200 | 220 | 200 | 180 | 200 | 180 | 160 | | | | | | | | | | | | | | | |
| | " , tempered | 325 | G | 130 | 100 | 80 | 100 | 80 | 60 | 80 | 60 | 40 | | | | | | | | | | | | | | | |
| M | Stainless steel, ferritic/martensitic, annealed | 200 | E | | | | | | | | | | | | | | | | 185 | 165 | 135 | 165 | 150 | 120 | | | |
| | Martensitic, tempered | 240 | EH | | | | | | | | | | | | | | | | 170 | 150 | 120 | 150 | 135 | 110 | | | |
| | Austenitic, plunged | 180 | E | | | | | | | | | | | | | | | | 200 | 180 | 150 | 180 | 160 | 135 | | | |
| K | Grey cast iron | | G | | | | | | | | | | 300 | 270 | 250 | 270 | 250 | 230 | | | | | | | | | |
| | Nodular cast iron | | G | | | | | | | | | | 200 | 170 | 150 | 170 | 150 | 130 | | | | | | | | | |
| S | High tempered resist. alloys, Fe based, annealed | 300 | E | | | | | | | | | | | | | | | | 50 | 30 | | 45 | 25 | | | | |
| | " , hardened | 330 | E | | | | | | | | | | | | | | | | 50 | 30 | | 45 | 25 | | | | |
| N | Aluminium alloy, Si < 13% | | S | | | | | | | | | | | | | | | | | | | | | | 1000 | 750 | 500 |
| | Aluminium alloy, Si > 13% | | S | | | | | | | | | | | | | | | | | | | | | | 250 | 200 | 170 |
| | Copper alloy | | S | | | | | | | | | | | | | | | | | | | | | | 350 | 330 | 300 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.


For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.



## ■ Recommended Values for Helical Milling and Ramping


### ● Helical Boring

≤ Min. Diameter




Center uncut portion cannot be removed by traverse cutting with the same cutter.


≥ Max. Diameter




Center uncut portion can be removed by traverse cutting with the same cutter.

### ● Plunging

Use at ≤ RMPX




### ● Recommended Values for Helical and Plunging

| Cutter External Diameter DC | WEX1000 (AXMT06...) | | | WEX2000 (AX□T12...) | | | WEX3000 (AX□T17...) | | |
|---|---|---|---|---|---|---|---|---|---|
| | Helical | | Plunging | Helical | | Plunging | Helical | | Plunging |
| | Work Diameter | | Max. Ramping Angle | Work Diameter | | Max. Ramping Angle | Work Diameter | | Max. Ramping Angle |
| | Min. | Max. | | Min. | Max. | | Min. | Max. | |
| 10 | 16,0 | 18,0 | 2°30' | | | | | | |
| 12 | 20,0 | 22,0 | 1°45' | | | | | | |
| 14 | 24,0 | 26,0 | 1°25' | 25,0 | 27,0 | 1°40' | | | |
| 16 | 28,0 | 30,0 | 1°00' | 29,0 | 31,0 | 1°20' | | | |
| 18 | 32,0 | 34,0 | 0°45' | 33,0 | 35,0 | 1°10' | | | |
| 20 | 36,0 | 38,0 | 0°30' | 37,0 | 39,0 | 1°00' | | | |
| 22 | | | | 41,0 | 43,0 | 0°50' | | | |
| 25 | 46,0 | 48,0 | 0°30' | 47,0 | 49,0 | 0°45' | 44,5 | 48,0 | 1°30' |
| 28 | | | | 53,0 | 55,0 | 0°45' | 50,5 | 54,0 | 1°10' |
| 30 | | | | 57,0 | 59,0 | 0°40' | 54,5 | 58,0 | 1°10' |
| 32 | 60,0 | 62,0 | 0°25' | 61,0 | 63,0 | 0°35' | 58,5 | 62,0 | 1°00' |
| 35 | | | | | | | 64,5 | 68,0 | 0°50' |
| 40 | 76,0 | 78,0 | 0°20' | 77,0 | 79,0 | 0°25' | 74,5 | 78,0 | 0°45' |
| 50 | 96,0 | 98,0 | 0°15' | 97,0 | 99,0 | 0°20' | 94,5 | 98,0 | 0°30' |
| 63 | 122,0 | 124,0 | 0°10' | 123,0 | 125,0 | 0°15' | 120,5 | 124,0 | 0°20' |
| 80 | | | | | | | 154,5 | 158,0 | 0°15' |
| 100 | | | | | | | | | |
| 125 | | | | | | | | | |

The above recommended values are for a nose radius of 0,8 mm.

# "Wave Mill" Series
# WAX Type




## Overview

Based on our proven Wavemill design this new range of WAX cutters is capable of rough and finishing Aluminium Alloys and other Non Ferrous Metals. It is ideal for high productivity Aluminium machining to exacting tolerances in the Aircraft, Electronics, and Automotive industries. The award winning Auroracoat DLC (diamond like carbon) inserts resist chip adhesion and substantially increase both tool life and productivity when dry machining Aluminium helping customers boost compliance with ISO14001 accreditation standards


## Advantages

- High Productivity
- Dry machining capability with MQL system
- DLC (diamond like carbon) inserts
- True 90 degree shoulder milling
- Chip adhesion resistance
- Wide range of nose radius



## Ramping (Slant Milling)

Maximum ramping angle ($\alpha$ max. max.) depends on cutter diameter.
Minimum milling length (L min) is the ramping distance required to reach the maximum cutting depth ($a_p$ max) at the maximum ramping angle of that cutter.
Minimum milling length (L) for any depth can be calculated by the equation below:






### WAX3000 E/EL Type

(mm)


| Cutter Diameter DC | Ramping Angle RMPX max. | Depth- of Cut $a_p$ max. | Milling Distance L min |
|---|---|---|---|
| 20 | 8° | 10 | 72 |
| 25 | 17° | 10 | 33 |
| 32 | 12° | 10 | 47 |
| 40 | 9° | 10 | 64 |

### WAX3000 RS Type

(mm)

| Cutter Diameter DC | Ramping Angle RMPX max. | Depth- of Cut $a_p$ max. | Milling Distance L min |
|---|---|---|---|
| 50 | 7° | 10 | 82 |
| 60 | 5° | 10 | 115 |
| 80 | 3° | 10 | 191 |
| 100 | 3° | 10 | 191 |
| 125 | 2° | 10 | 287 |

## Helical Milling






### Helical Milling Diameter

(mm)

| Cutter Diameter DC | Milling Diameter øD | |
|---|---|---|
| | Min. | Max. |
| 20 | 22 | 33 |
| 25 | 29 | 43 |
| 32 | 43 | 57 |
| 40 | 59 | 73 |
| 50 | 79 | 93 |
| 63 | 105 | 119 |
| 80 | 139 | 153 |
| 100 | 179 | 193 |
| 125 | 229 | 243 |

## Maximum Allowable Spindle Speed

| Cutter Diameter DC | Spindle Revolution n (min$^{-1}$) | Cutting Speed $v_c$ (m/min) |
|---|---|---|
| 20 | 14.000 | 880 |
| 25 | 29.000 | 2.200 |
| 32 | 25.000 | 2.500 |
| 40 | 23.000 | 2.900 |
| 50 | 20.000 | 3.100 |
| 63 | 18.000 | 3.500 |
| 80 | 16.000 | 4.000 |
| 100 | 14.000 | 4.400 |
| 125 | 13.000 | 5.100 |

## Recommended Cutting Conditions

| Work Material | Aluminum Alloy |
|---|---|
| Cutting Speed | 600–1.200 m/min |
| Feed Rate | 0,05–0,25 mm/tooth |

# WAX 3000 E/EL


16–18mm 90°

| | |
|---|---|
| Axial rake angle | 6° |
| Radial rake angle | 19–25° |



**(Endmill)**

Short Type "E"
Long Type "EL"




## Body

(For inserts with nose radius ≤ 3,2 mm)

| Cat. No. | Stock | Dimensions (mm) | | | | | No.of teeth | Weight (Kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LF | LH | LS | | |
| WAX 3020 E -3.2 | ● | 20 | 20 | 130 | 60 | 70 | 1 | 0,25 |
| WAX 3025 E -3.2 | ● | 25 | 25 | 140 | 60 | 80 | 2 | 0,42 |
| 3025 EL-3.2 | ● | 25 | 25 | 200 | 60 | 140 | 2 | 0,63 |
| WAX 3032 E -3.2 | ● | 32 | 32 | 150 | 70 | 80 | 2 | 0,75 |
| 3032 EL-3.2 | ● | 32 | 32 | 220 | 70 | 150 | 2 | 1,2 |
| WAX 3040 E -3.2 | ● | 40 | 32 | 160 | 70 | 90 | 3 | 1,0 |
| 3040 EL-3.2 | ● | 40 | 32 | 220 | 70 | 150 | 3 | 1,4 |


## Body

(For inserts with nose radius ≥ 4,0 mm)

| Cat. No. | Stock | Dimensions (mm) | | | | | No.of teeth | Weight (Kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LF | LH | LS | | |
| WAX 3020 E -4.0 | | 20 | 20 | 130 | 60 | 70 | 1 | 0,25 |
| WAX 3025 E -4.0 | ● | 25 | 25 | 140 | 60 | 80 | 2 | 0,42 |
| 3025 EL-4.0 | ● | 25 | 25 | 200 | 60 | 140 | 2 | 0,63 |
| WAX 3032 E -4.0 | ● | 32 | 32 | 150 | 70 | 80 | 2 | 0,75 |
| 3032 EL-4.0 | | 32 | 32 | 220 | 70 | 150 | 2 | 1,2 |
| WAX 3040 E -4.0 | ❍ | 40 | 32 | 160 | 70 | 90 | 3 | 1,0 |
| 3040 EL-4.0 | ● | 40 | 32 | 220 | 70 | 150 | 3 | 1,4 |



## Inserts for WAX 3000 Type




| Application | DLC Coated | Carbide |
|---|---|---|
| High Speed / Light cut | K N | N |
| General Purpose | | N |
| Roughing | | |

| Cat. No. | DL1000 | H1 | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | | APMX | INSL | BS | RE | S | D1 |
| AECT 160404 PEFRA | ● | ● | 18 | 16,4 | 1,4 | 0,4 | 5 | 4,4 |
| 160408 PEFRA | ● | ● | 18 | 16,4 | 1,0 | 0,8 | 5 | 4,4 |
| 160412 PEFRA | ● | ● | 18 | 16,4 | 0,6 | 1,2 | 5 | 4,4 |
| 160416 PEFRA | ● | ● | 17,5 | 16,4 | 0,5 | 1,6 | 5 | 4,4 |
| 160420 PEFRA | ● | ● | 17,5 | 16,4 | 0,5 | 2,0 | 5 | 4,4 |
| 160430 PEFRA | ● | ● | 17 | 16,4 | 0,7 | 3,0 | 5 | 4,4 |
| 160432 PEFRA | ● | ● | 17 | 16,4 | 0,5 | 3,2 | 5 | 4,4 |
| AECT 160440 PEFRA | ● | ● | 16,5 | 16,4 | 0,5 | 4,0 | 5 | 4,4 |
| 160450 PEFRA | ● | ● | 16 | 16,4 | 0,4 | 5,0 | 5 | 4,4 |

## Spare Parts

| Insert Screw | | Insert Wrench | Applicable Endmill |
|---|---|---|---|
|  | N·m |  | |
| BFTX 0408 | 3,0 | TRD 15 | WAX 3000 E/EL |



● = Euro stock
❍ = Japan stock
❑ = Delivery on request


→ G72-G73

N·m Recommended Tightening Torque (N·m)

# WAX 4000 E/EL


22–24mm 90°

| | |
|---|---|
| Axial rake angle | 6° |
| Radial rake angle | 19–25° |



**(Endmill)**

Short Type "E"
Long Type "EL"




## Body

(For inserts with nose radius ≤ 3,2 mm)


| Cat. No. | Stock | Dimensions (mm) | | | | | No.of teeth | Weight (Kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LF | LH | LS | | |
| WAX 4025E -3.2 | ❑ | 25 | 25 | 140 | 60 | 80 | 1 | 0,41 |
| 4025EL-3.2 | ❑ | 25 | 25 | 200 | 60 | 140 | 1 | 0,63 |
| WAX 4032E -3.2 | ❑ | 32 | 32 | 150 | 70 | 80 | 1 | 0,72 |
| 4032EL-3.2 | ❑ | 32 | 32 | 220 | 70 | 150 | 1 | 1,2 |
| WAX 4040E -3.2 | ❑ | 40 | 32 | 160 | 70 | 90 | 2 | 0,88 |
| 4040EL-3.2 | ❑ | 40 | 32 | 220 | 70 | 150 | 2 | 1,2 |

## Body

(For inserts with nose radius ≥ 4,0 mm)

| Cat. No. | Stock | Dimensions (mm) | | | | | No.of teeth | Weight (Kg) |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | LF | LH | LS | | |
| WAX 4025E -4.0 | ❑ | 25 | 25 | 140 | 60 | 80 | 1 | 0,41 |
| 4025EL-4.0 | ❑ | 25 | 25 | 200 | 60 | 140 | 1 | 0,63 |
| WAX 4032E -4.0 | ❑ | 32 | 32 | 150 | 70 | 80 | 1 | 0,72 |
| 4032EL-4.0 | ❑ | 32 | 32 | 220 | 70 | 150 | 1 | 1,2 |
| WAX 4040E -4.0 | ❑ | 40 | 32 | 160 | 70 | 90 | 2 | 0,88 |
| 4040EL-4.0 | ❑ | 40 | 32 | 220 | 70 | 150 | 2 | 1,2 |

## Inserts for WAX 4000 Type




| Application | DLC Coated | Carbide |
|---|---|---|
| High Speed / Light cut | K N | N |
| General Purpose | | N |
| Roughing | | |

| Cat. No. | DL1000 | H1 | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | | APMX | INSL | BS | RE | S | D1 |
| AECT 220604 PEFRA | ❑ | ❑ | 24 | 21,8 | 1,5 | 0,4 | 6,35 | 6,0 |
| 220608 PEFRA | ❑ | ❑ | 24 | 21,8 | 1,2 | 0,8 | 6,35 | 6,0 |
| 220612 PEFRA | ❑ | ❑ | 24 | 21,8 | 0,8 | 1,2 | 6,35 | 6,0 |
| 220616 PEFRA | ❑ | ❑ | 24 | 21,8 | 0,4 | 1,6 | 6,35 | 6,0 |
| 220620 PEFRA | ❑ | ❑ | 24 | 21,8 | 0,5 | 2,0 | 6,35 | 6,0 |
| 220630 PEFRA | ❑ | ❑ | 23 | 21,8 | 0,6 | 3,0 | 6,35 | 6,0 |
| 220632 PEFRA | ❑ | ❑ | 23 | 21,8 | 0,4 | 3,2 | 6,35 | 6,0 |
| AECT 220640 PEFRA | ❑ | ❑ | 22 | 21,8 | 1,2 | 4,0 | 6,35 | 6,0 |
| 220650 PEFRA | ❑ | ❑ | 22 | 21,8 | 0,4 | 5,0 | 6,35 | 6,0 |

## Spare Parts

| Insert Screw | | Insert Wrench | Applicable Endmill |
|---|---|---|---|
|  | N·m |  | |
| BFTX 0509 N | 5,0 | TRD 20 | Ø 25 – Ø 32 |
| BFTX 0511 N | | TRD 20 | Ø 40 – Ø 125 |



→ G72-G73



## General Features

The WRX Wave repeater end mill system features AXMT style inserts vertically mounted and positioned to provide a long continuous cutting edge suitable for deep shoulder milling. Designed to run at elevated feed rates the soft cutting action reduces cutting resistance, vibration and noise to substantially improve tool life and surface finish.


Available with our new generation Super FF and Super ZX coated inserts for unbeatable performance.

## Product Range


- WRX 2000 series with 12 mm inserts
- WRX 3000 series with 17 mm inserts
- Cutter Diameters - 20 mm ($a_p$ = 18 mm) to 100 mm ($a_p$ = 53 mm)
- Special Order Options – WRX Cutter with integrated arbor
  Shell type with detachable head
- Wide ISO Application Range – P/M/K/N classification

## Advantages


- Optimised insert positions reduce cutting resistance and vibration
- Integral coolant improves chip flow
- Primary chip slot for smooth and fast chip evacuation
- Optimised insert pocket maximises rigidity
- Bottom edge support improves tool life and cutting performance




## Cutting Resistance Comparison




## Vibration Comparison




| | |
|---|---|
| Work Material: | C50 |
| Tool: | WRX2025RH27E25 |
| Cutting Conditions: | $v_c$ = 100 m/min, $f_z$ = 0,15 mm/tooth |
| | $a_p$ = 25 mm, $a_e$ = 10 mm, dry |


| | |
|---|---|
| Work Material: | C50 |
| Tool: | WRX3080RH53F32 |
| Cutting Conditions: | $v_c$ = 150 m/min, $f_z$ = 0,15 mm/tooth |
| | $a_p$ = 25 mm, $a_e$ = 10 mm, dry |






● = Euro stock
❑ = Delivery on request
▲ = To be replaced by new item
Recommended Tightening Torque (N·m)

# WRX 2000 Series with AXMT 12 mm inserts







## Body (Cylindrical Shank Type)

| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of teeth | No. of rows | Effective teeth |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | APMX | DMM | LF | LH | LS | | | |
| WRX2020RH18E20 | ● | 20 | 18 | 20 | 120 | 40 | 80 | 4 | 2 | 2 |
| WRX2020RH36E20 | ❑ | 20 | 36 | 20 | 130 | 45 | 85 | 4 | 4 | 1 |
| WRX2025RH18E25 | ● | 25 | 18 | 25 | 130 | 45 | 85 | 6 | 2 | 3 |
| WRX2025RH27E25 | ● | 25 | 27 | 25 | 130 | 45 | 85 | 6 | 3 | 2 |
| WRX2032RH18E32 | ❑ | 32 | 18 | 32 | 140 | 50 | 90 | 8 | 2 | 4 |
| WRX2032RH27E32 | ● | 32 | 27 | 32 | 130 | 45 | 85 | 9 | 3 | 3 |
| WRX2040RH18E40 | ❑ | 40 | 18 | 40 | 160 | 40 | 120 | 10 | 2 | 5 |
| WRX2040RH36E40 | ❑ | 40 | 36 | 40 | 130 | 45 | 85 | 16 | 4 | 4 |

## Body (Weldon Shank Type)

| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of teeth | No. of rows | Effective teeth |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | APMX | DMM | LF | LH | LS | | | |
| WRX2020RH18W20 | ● | 20 | 18 | 20 | 120 | 40 | 80 | 4 | 2 | 2 |
| WRX2020RH36W20 | ❑ | 20 | 36 | 20 | 130 | 45 | 85 | 4 | 4 | 1 |
| WRX2025RH18W25 | ● | 25 | 18 | 25 | 130 | 45 | 85 | 6 | 2 | 3 |
| WRX2025RH27W25 | ● | 25 | 27 | 25 | 130 | 45 | 85 | 6 | 3 | 2 |
| WRX2032RH18W32 | ❑ | 32 | 18 | 32 | 140 | 50 | 90 | 8 | 2 | 4 |
| WRX2032RH27W32 | ● | 32 | 27 | 32 | 130 | 45 | 85 | 9 | 3 | 3 |
| WRX2040RH18W40 | ❑ | 40 | 18 | 40 | 160 | 40 | 120 | 10 | 2 | 5 |
| WRX2040RH36W40 | ❑ | 40 | 36 | 40 | 130 | 45 | 85 | 16 | 4 | 4 |

## Inserts (Same as for Wavemill WEX 2000 Type)




| Application | Coated Carbide | | | | | | | Carbide | DLC | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M S | | K N | N | |
| General Purpose | | P M | P M | K | | M S | M S | | N | |
| Roughing | | P M | P M | | K | | M S | | | |
| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
| AXMT 123504 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 123508 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 123512 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 123504 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 123508 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 123512 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 123504 PEER-E | | | | | | ▲ | ▲ | – | – | 0,4 |
| 123508 PEER-E | | | | | | ▲ | ▲ | – | – | 0,8 |
| 123512 PEER-E | | | | | | ▲ | ▲ | – | – | 1,2 |
| AXMT 123508 PEER-EH | | | | | | ▲ | ▲ | – | – | 0,8 |
| AXET 123502 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,2 |
| 123504 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,4 |
| 123508 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,8 |

– Unable to produce

G - General type
H - Strong cutting edge
E - For stainless steel / exotic alloy
EH - Strong edge for stainless steel / exotic alloy
S - For aluminium alloy

## Spare Parts (WRX 2000)

| Screw | Wrench |
|---|---|
|  |  |
| BFTX 0306 IP | TRDR 08 IP |

## Identification Details

**WRX 20 25 R H 27 W 25**

- 20 — Insert Size
- 25 — Tool øD
- R — Cutting Direction
- H — Inner coolant
- 27 — Cutting Edge Lengh
- W — Arbor Type
  - **E** - Straight Shank
  - **W** - Weldon Shank
  - **F** - Shell Type
- 25 — Arbor Diameter

## Application Examples

### Example





| Work Material | Construction Machine Parts (USt.42-2) | | |
|---|---|---|---|
| Tool | Body | Sumitomo | Competitor |
| | | WRX2000 Weldon shank | Ø 38,1 |
| | Insert | AXMT | 18 mm |
| | Insert grade | ACP200 | PVD Type |
| | Tool dia. (mm) | 38,1 | 38,1 |
| | Total teeth | 24 | 16 |
| | Effective teeth | 4 | 4 |
| Cutting Data | Cutting speed (m/min) | 180 | 137 |
| | Feed (mm/t) | 0,09 | 0,1 |
| | Axial depth of cut (mm) | 38,1 | 38,1 |
| | Radial width of cut (mm) | 3,2 | 3,2 |
| | Coolant | Wet | Wet |
| Result | Tool life / Cutting edge | 60 | 40 |
| Benefits | 1,5 times longer tool life<br>30 % increased productivity | | |



→ G59

# WRX 3000 Series with AXMT 17 mm inserts



## Body (Cylindrical Shank Type)

| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of teeth | No. of rows | Effective teeth |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | APMX | DMM | LF | LH | LS | | | |
| WRX3032RH40E32 | ● | 32 | 40 | 32 | 150 | 65 | 85 | 6 | 3 | 2 |
| WRX3040RH27E40 | ❑ | 40 | 27 | 40 | 180 | 60 | 120 | 6 | 2 | 3 |
| WRX3040RH40E40 | ● | 40 | 40 | 40 | 150 | 65 | 85 | 9 | 3 | 3 |
| WRX3050RH27E40 | ❑ | 50 | 27 | 40 | 180 | 60 | 120 | 8 | 2 | 4 |
| WRX3050RH53E40 | ● | 50 | 53 | 40 | 165 | 75 | 90 | 12 | 4 | 3 |


## Body (Weldon Shank Type)

| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of teeth | No. of rows | Effective teeth |
|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | APMX | DMM | LF | LH | LS | | | |
| WRX3040RH27W40 | ❑ | 40 | 27 | 40 | 180 | 60 | 120 | 6 | 2 | 3 |
| WRX3040RH40W40 | ● | 40 | 40 | 40 | 150 | 65 | 85 | 9 | 3 | 3 |
| WRX3050RH27W40 | ❑ | 50 | 27 | 40 | 180 | 60 | 120 | 8 | 2 | 4 |
| WRX3050RH53W40 | ● | 50 | 53 | 40 | 165 | 75 | 90 | 12 | 4 | 3 |

## Spare Parts (WRX 3000)

| Screw | Wrench |
|---|---|
|  3,0 (N·m) |  |
| BFTX 0409 IP | TRDR 15 IP |

## Inserts (Same as for Wavemill WEX 3000 Type)




| Application | Coated Carbide | | | | | | | Carbide | DLC | |
|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | M S | | K N | N | |
| General Purpose | | P | | K | | M S | M S | | N | |
| Roughing | | P | P | | K | | M S | | | |
| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | Radius RE |
| AXMT 170508 PEER-L | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| AXMT 170504 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,4 |
| 170508 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 170512 PEER-G | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| 170516 PEER-G | ❍ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,6 |
| 170520 PEER-G* | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 2,0 |
| 170530 PEER-G* | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 3,0 |
| AXMT 170508 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 0,8 |
| 170512 PEER-H | ▲ | ▲ | ▲ | ▲ | ▲ | | | – | – | 1,2 |
| AXMT 170504 PEER-E | | | | | | ▲ | ▲ | – | – | 0,4 |
| 170508 PEER-E | | | | | | ▲ | ▲ | – | – | 0,8 |
| 170512 PEER-E | | | | | | ▲ | ▲ | – | – | 1,2 |
| 170516 PEER-E | | | | | | ▲ | ▲ | – | – | 1,6 |
| 170520 PEER-E* | | | | | | ▲ | ▲ | – | – | 2,0 |
| 170530 PEER-E* | | | | | | ▲ | ▲ | – | – | 3,0 |
| AXMT 170508 PEER-EH | | | ▲ | | | ▲ | ▲ | – | – | 0,8 |
| AXET 170502 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,2 |
| 170504 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,4 |
| 170508 PEFR-S | – | – | – | – | – | – | – | ▲ | ▲ | 0,8 |

– Unable to produce

L – Low cutting force
G – General type
H – Strong cutting edge
E – For stainless steel
EH– Strong edge for stainless steel
S – For aluminium
* Cutter body modification is required.

## Application Examples

### Example 1



| Work Material | Automotive Component / Cast Iron | | |
|---|---|---|---|
| Tool | Body | Sumitomo | Competitor |
| | | WRX3000 Type Integrated Arbor | Ø 50 |
| | Insert | AXMT | 18 mm |
| | Insert grade | ACK300 | PVD Type |
| | Tool dia. (mm) | 50 | 50 |
| | Total teeth | 15 | 12 |
| | Effective teeth | 3 | 3 |
| Cutting Data | Cutting speed (m/min) | 78 | 78 |
| | Feed (mm/t) | 0,13 | 0,13 |
| | Axial depth of cut (mm) | 45 | 45 |
| | Radial width of cut (mm) | 5 | 5 |
| | Coolant | Dry | Dry |
| Result | Tool life / Cutting edge | 500 min | 300 min |
| Benefits | 1,7 times longer tool life | | |

### Example 2



| Work Material | Machine Parts / Stainless Steel | | |
|---|---|---|---|
| Tool | Body | Sumitomo | Competitor |
| | | WRX3040RH40E40 | Ø 40 |
| | Insert | AXMT | 18 mm |
| | Insert grade | ACP300 | PVD Type |
| | Tool dia. (mm) | 40 | 40 |
| | Total teeth | 9 | 6 |
| | Effective teeth | 3 | 2 |
| Cutting Data | Cutting speed (m/min) | 125 | 125 |
| | Feed (mm/t) | 0,2 | 0,2 |
| | Axial depth of cut (mm) | 40 | 40 |
| | Radial width of cut (mm) | 5 | 5 |
| | Coolant | Wet | Wet |
| Result | Tool life / Cutting edge | 20 | 5 ~ 10 |
| Benefits | Stable machining, double tool life with no breakage | | |




→ G59





● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
(N·m) Recommended Tightening Torque (N·m)

## Chipbreaker Selection

| Work Material | Steel, Cast Iron | | | Stainless Steel | | Aluminium |
|---|---|---|---|---|---|---|
| Chipbreaker Type | L | G | H | E | EH | S |
| |  |  |  |  |  |  |
| Feature | Low cutting force | General purpose | Strong cutting edge | E type for smooth cutting | Strong cutting edge | Sharp cutting edge |
| 2000 Type Figure | — |  28° |  20° |  17° |  17° |  27° |
| 3000 Type Figure |  25° |  20° |  5° |  14° |  8° |  30° |
| Application | Light cut, low rigidity milling and less burrs | General to Interrupted milling | Roughing, heavy interrupted and hardened steel milling | Light cutting to general purpose | Heavy interrupted machining | Aluminium alloy and non-ferrous metal |

## Ramping (Slant Milling)

| Tool Diameter | Max. Ramping Angle | |
|---|---|---|
| | WRX 2000 Typ | WRX 3000 Typ |
| 20 | 4° | |
| 25 | 2° | |
| 32 | 1°30' | |
| 40 | 1° | 2° |
| 50 | 0°30' | 1° |
| 63 | | 0°30' |
| 80 | | 0°30' |
| 100 | | Not possible |



## Recommended Cutting Conditions

Tool: WRX 3050 RH53 F22, DC = 50 mm, $a_p$ = 50 mm

| ISO | Work Material | Property, Condition | Hardness (HB) | Grades (optimum grade in bold letters) | | | Chip Breaker | Recommended cutting speed and feed / tooth according to width of cut ( $a_e$ /DC ) - must be adjusted to actual machine and workpiece conditions. | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | | | | 10% | | 25% | | >50% | |
| | | | | | | | | $v_c$ | $f_z$ | $v_c$ | $f_z$ | $v_c$ | $f_z$ |
| | | | | | | | | min. **Optimum** max. | min. **Optimum** max. | min. **Optimum** max. | min. **Optimum** max. | min. **Optimum** max. | min. **Optimum** max. |
| P | Steel, carbon steel | < 0,15% C, annealed | 125 | ACP 100 | **ACP 200** | ACP 300 | L - **G** | 170 – **215** – 240 | 0,21 – **0,28** – 0,35 | 160 – **195** – 220 | 0,16 – **0,21** – 0,26 | 130 – **160** – 180 | 0,08 – **0,10** – 0,13 |
| | | < 0,45% C, annealed | 190 | ACP 100 | **ACP 200** | ACP 300 | L - **G** | 160 – **195** – 220 | 0,21 – **0,28** – 0,35 | 140 – **175** – 190 | 0,16 – **0,21** – 0,26 | 110 – **140** – 160 | 0,08 – **0,10** – 0,13 |
| | | < 0,45% C, tempered | 250 | ACP 100 | **ACP 200** | ACP 300 | L - **G** - H | 140 – **180** – 200 | 0,19 – **0,26** – 0,32 | 130 – **165** – 180 | 0,14 – **0,19** – 0,24 | 100 – **130** – 140 | 0,08 – **0,10** – 0,13 |
| | | < 0,75% C, annealed | 270 | ACP 100 | **ACP 200** | ACP 300 | L - **G** - H | 140 – **170** – 190 | 0,19 – **0,26** – 0,32 | 120 – **155** – 170 | 0,14 – **0,19** – 0,24 | 100 – **130** – 140 | 0,07 – **0,10** – 0,12 |
| | | < 0,75% C, tempered | 300 | ACP 100 | **ACP 200** | ACP 300 | L - **G** - H | 130 – **165** – 180 | 0,19 – **0,26** – 0,32 | 120 – **150** – 170 | 0,14 – **0,19** – 0,24 | 100 – **120** – 130 | 0,07 – **0,10** – 0,12 |
| | Low alloyed steel | annealed | 180 | ACP 100 | **ACP 200** | ACP 300 | **G** - H | 130 – **165** – 180 | 0,18 – **0,24** – 0,30 | 120 – **150** – 170 | 0,13 – **0,18** – 0,22 | 100 – **120** – 130 | 0,07 – **0,09** – 0,11 |
| | | tempered | 275 | ACP 100 | **ACP 200** | ACP 300 | **G** - H | 130 – **160** – 180 | 0,17 – **0,23** – 0,28 | 120 – **145** – 160 | 0,12 – **0,16** – 0,20 | 100 – **120** – 130 | 0,07 – **0,09** – 0,11 |
| | | tempered | 300 | ACP 100 | **ACP 200** | ACP 300 | **G** - H | 110 – **140** – 160 | 0,16 – **0,22** – 0,27 | 100 – **130** – 140 | 0,11 – **0,15** – 0,19 | 90 – **110** – 120 | 0,07 – **0,09** – 0,11 |
| | | tempered | 350 | ACP 100 | **ACP 200** | ACP 300 | **G** - H | 100 – **130** – 140 | 0,16 – **0,21** – 0,26 | 100 – **120** – 130 | 0,11 – **0,15** – 0,19 | 80 – **100** – 110 | 0,06 – **0,08** – 0,10 |
| | High alloyed and tool steel | annealed | 200 | **ACP 100** | ACP 200 | | G - **H** | 70 – **85** – 90 | 0,15 – **0,21** – 0,26 | 60 – **80** – 90 | 0,11 – **0,14** – 0,18 | 60 – **70** – 80 | 0,06 – **0,08** – 0,10 |
| | | tempered | 325 | **ACP 100** | ACP 200 | | G - **H** | 30 – **35** – 40 | 0,14 – **0,19** – 0,24 | 30 – **35** – 40 | 0,10 – **0,14** – 0,17 | 20 – **30** – 30 | 0,06 – **0,08** – 0,10 |
| M | Stainless steel, ferritic/martensitic | annealed | 200 | | ACP 200 | **ACP 300** | L - **G** - H | 120 – **150** – 170 | 0,15 – **0,20** – 0,25 | 110 – **135** – 150 | 0,11 – **0,14** – 0,18 | 90 – **110** – 120 | 0,07 – **0,09** – 0,11 |
| | Stainless, martensitic | tempered | 240 | | ACP 200 | **ACP 300** | L - **G** - H | 100 – **125** – 140 | 0,16 – **0,22** – 0,27 | 90 – **115** – 130 | 0,12 – **0,16** – 0,20 | 80 – **100** – 110 | 0,07 – **0,10** – 0,12 |
| | Stainless, austenitic | plunged | 180 | | ACM 200 | **ACM 300** | L - **G** | 80 – **95** – 110 | 0,15 – **0,20** – 0,25 | 70 – **85** – 90 | 0,11 – **0,14** – 0,18 | 60 – **70** – 80 | 0,06 – **0,08** – 0,10 |
| K | Gray cast iron | GG | 180 | **ACK 200** | ACK 300 | | **G** - H | 190 – **240** – 270 | 0,19 – **0,26** – 0,32 | 180 – **220** – 240 | 0,14 – **0,19** – 0,24 | 140 – **170** – 190 | 0,09 – **0,12** – 0,15 |
| | Nodular cast iron | GGG | 250 | **ACK 200** | ACK 300 | | **G** - H | 140 – **170** – 190 | 0,16 – **0,21** – 0,26 | 120 – **155** – 170 | 0,12 – **0,16** – 0,20 | 100 – **130** – 140 | 0,07 – **0,10** – 0,12 |
| S | Exotic alloys (Resistant alloys, Ti + Ni alloys) | Fe based, annelaed | 200 | ACK 200 | **ACK 300** | | L - **G** | 40 – **45** – 50 | 0,12 – **0,16** – 0,21 | 30 – **40** – 45 | 0,08 – **0,11** – 0,14 | 30 – **35** – 40 | 0,07 – **0,09** – 0,11 |
| | | hardened | 280 | ACK 200 | **ACK 300** | | L - **G** | 15 – **20** – 25 | 0,10 – **0,14** – 0,17 | 10 – **15** – 20 | 0,07 – **0,10** – 0,12 | 10 – **15** – 20 | 0,05 – **0,07** – 0,09 |
| N | Aluminum alloy | Si < 13% | | | **DL 1000** | H1 | **S** | 510 – **635** – 710 | 0,23 – **0,31** – 0,38 | 460 – **580** – 640 | 0,17 – **0,22** – 0,28 | 390 – **485** – 540 | 0,08 – **0,12** – 0,14 |
| | | Si ≥ 13% | | | **DL 1000** | H1 | **S** | 150 – **190** – 210 | 0,19 – **0,25** – 0,32 | 140 – **175** – 190 | 0,14 – **0,18** – 0,23 | 130 – **165** – 180 | 0,08 – **0,10** – 0,13 |
| | Copper alloy | | | | **DL 1000** | H1 | **S** | 320 – **405** – 450 | 0,15 – **0,21** – 0,26 | 300 – **370** – 410 | 0,13 – **0,16** – 0,22 | 240 – **300** – 330 | 0,07 – **0,10** – 0,12 |

- Dry machining is recommended (air cooling) - if lubricant is used, we recommend CVD coated grades (ACP100 / ACK200) or tough PVD grades (ACP300 / ACK300).
- Insert geometry: L type for low cutting forces, thinly coated components. G type for general application, H type offers high cutting edge stability for rough and heavy cutting conditions.

# MTIX 16000 Type

New



## General Features


### Stable and Reliabel Tool Life in Titanium Roughing

With combination of high toughness grade ACM300 and optimized cutting edge shape, stable and reliable tool life are achieved in roughing application of Titanium.

### Suitable for Titanium Structure Parts for Aircraft

MTIX cutter with wide range of insert nose-radius and large ramping angle availiability is suitable for variable application of titanium structure parts for aircraft.

### Large Application Range



| ISO | Grade | Coating Thickness (µm) | Features |
|---|---|---|---|
| S | ACM300 | 3 | Realises superb stability in machining of Titanium, due to a high-strength carbide substrate and highly chipping-resistance coating. |


## Recommended Cutting Conditions

Min. - **Optimum** - Max.


| ISO | Material | Cutting Speed (m/min) | Feed Rate (mm/t) | $a_p$ (mm) | Grade |
|---|---|---|---|---|---|
| S | Titanium | 30–**60**–90 | 0,05–**0,10**–0,15 | <13 | ACM300 |

## Ramping / Helical Milling Upper Limits


Ramping




Flat Bottom Machining




Machining with Prepared Hole




| Tools | | Ramping |
|---|---|---|
| DC Ø (mm) | Nose Radius | Max. RMPX (°) |
| Ø 32 | RE ≥ 5,0 | 8,4 |
| | RE ≤ 4,0 | 12,2 |
| Ø 50 | RE ≥ 5,0 | 3,6 |
| | RE ≤ 4,0 | 5,6 |
| Ø 63 | RE ≥ 5,0 | 2,5 |
| | RE ≤ 4,0 | 3,9 |

| Tools | | Flat Bottom Machining | | | | Machining with Prepared Hole | |
|---|---|---|---|---|---|---|---|
| DC Ø (mm) | Nose Radius | Max. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) | Min. Machining Diam. (mm) | Max. Pitch (mm/rev) |
| Ø 32 | 4,0 | 55,3 | 13,0 | 55,2 | 13,0 | 45,9 | 3,0 |
| | 0,8 | 61,3 | 13,0 | 56,3 | 13,0 | 45,9 | 2,9 |
| Ø 50 | 4,0 | 91,6 | 11,2 | 91,6 | 11,2 | 81,9 | 2,8 |
| | 0,8 | 97,3 | 13,0 | 92,2 | 11,0 | 81,9 | 2,7 |
| Ø 63 | 4,0 | 117,6 | 10,1 | 117,6 | 10,1 | 107,9 | 2,7 |
| | 0,8 | 123,3 | 11,7 | 118,2 | 9,9 | 107,9 | 2,6 |






● = Euro stock


Recommended Tightening Torque (N·m)

| Rake Angle | | |
|---|---|---|
| | Radial | -9° – -6° |
| | Axial | 8° – 14° |

13 mm 90°








## Body - MTIX (Shankl Type)

Dimensions (mm)

| Insert Radius RE | Cat. No. | Stock | DC | DMM | LF | LH | LS | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|
| ≤ 4,0 | MTIX 16032E03 | ● | 32 | 32 | 180 | 70 | 110 | 3 | 0,96 |
| ≥ 5,0 | MTIX 16032E03-5,0 | ● | 32 | 32 | 180 | 70 | 110 | 3 | 0,96 |

Inserts are sold separately.

→ G61

## Spare Parts

| Applicable Cutters | Insert Screw | | Wrench | Handle Grip | Wrench Bit |
|---|---|---|---|---|---|
| |  |  |  |  |  |
| MTIX 16032E03(-5,0) | BFTX0409IP | 3,0 | TRDR15IP | – | – |

## Identification Details

| MTIX | 16 | 032 | E | 05 |
|---|---|---|---|---|
| Cutter Series | Insert Size | Cutter Diameter | Round Shank | Number of Teeth |

## Inserts

| Application | Coated Carbide |
|---|---|
| High Speed / Light Cut | |
| General Purpose | S |
| Roughing | S |

Dimensions (mm)

| Cat. No. | ACM300 | RE | Fig. |
|---|---|---|---|
| XOMT 160508PEER-E | ● | 0,8 | 1 |
| 160512PEER-E | ● | 1,2 | 1 |
| 160516PEER-E | ● | 1,6 | 1 |
| 160520PEER-E | ● | 2,0 | 1 |
| 160530PEER-E | ● | 3,0 | 1 |
| 160540PEER-E | ● | 4,0 | 1 |
| 160550PEER-E | ● | 5,0 | 2 |
| 160560PEER-E | ● | 6,0 | 2 |
| 160564PEER-E | ● | 6,35 | 2 |

Fig. 1






Fig. 2




Inserts with nose radius of RE ≥ 5,0 are for use with bodies that have a "-5,0" part number suffix

## Precautions for Mounting


(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.








| Cutter Body | MTIX16 ____ | MTIX16 ____-5,0 |
|---|---|---|
| Insert Radius RE ≤ 4,0 mm |  OK |  Not recommended. The insert has no support from the cutter body. |
| Insert Radius RE ≥ 4,0 mm | OK with modification  1,5 mm less height | OK  |

Modification method

① Grind 1,5 mm from top

② Add chamfer 4,5 mm



# "Wave Ball Mill" for Roughing
# WBMR Type



## Features


Particularly suitable for die mold machining the WBMR replaceable insert ball nose endmill efficiently roughs complex profiles.

Its high feed rate capability is a direct result of a sharp cutting edge which is maintained during the cutting cycle by the special cemented carbide substrate working in parallel with the ultra hard ZX coating.



## Advantages

- Wave shaped cutting edge
- Economical M class insert
- Precise clamping
- High feed rate capability




**Chipbreaker**
(Nick type)
for r = 25
radial insert

ZNMT 4310250-N


## Performance

● Cutting Resistance





Cutting Conditions (Shoulder milling, downcut)
$v_c$ = 200 m/min, $f_z$ = 0.15 mm/tooth
Axial $a_p$: 5 mm, Radial $a_e$: 5 mm
Work Material : C50

● Anti-Rotational Mechanism




Circumferential movement of the insert caused by cutting forces is controlled by guide faces A, B & C, so as to allow stable cutting.

● Insert Life





Cutting Conditions (Shoulder milling, downcut)
$v_c$ = 100 m/min, $f_z$ = 0.15 mm/tooth
Axial $a_p$: 5mm, Radial $a_e$: 5 mm
Work Material : X 40 CrMoV 5-1(HRC45)

## Application Example

● Cold Molding Die

Work Material :
X 155 CrVMo 12 1




<Results>
Flank wear after continuous cutting for seven hours was less than other manufacturer's product.
Stable cutting was observed.

WBMR 2200S (ø 20 mm)
Insert Grade : ACZ350

Cutting Conditions :
n = 2200 rpm, $v_f$ = 500 mm/min
Depth of Cut : 0,3–2 mm
Non-water soluble cutting oil

● Injection Molded Part

(Cr-Mo steel + Stellite-overlay)




<Results>
Wave ball (ø30mm) could cut without chattering while other manufacturer's products could not cut at all due to chattering.

WBMR 2300M (ø 30 mm)
Insert Grade : ACZ350

Cutting Conditions :
n = 500 rpm, $v_f$ = 35 mm/min
Depth of Cut : 5 mm
Dry cut

## Recommended Cutting Conditions (2 teeth)


| Condition | Material | Carbon steel (Below HRC25) | Alloy steel (Below HRC45) | Stainless, Die steel etc. | Cast iron |
|---|---|---|---|---|---|
| (A) | $v_c$ | 200-**250**-300 | 100-**150**-200 | 50-**80**-100 | 100-**120**-150 |
| | $f_z$ | 0,1-**0,2**-0,3 | 0,1-**0,2**-0,3 | 0,1-**0,15**-0,2 | 0,2-**0,3**-0,4 |




[$v_c$ =m/min, $f_z$ =mm/tooth] [min.– optimum – max.]

## Recommended Cutting Conditions (4 teeth)

| Condition | Material | Carbon steel (Below HRC25) | Alloy steel (Below HRC45) | Stainless, Die steel etc. | Cast iron |
|---|---|---|---|---|---|
| (A) | $v_c$ | 200-**250**-300 | 100-**150**-200 | 50-**80**-100 | 100-**120**-150 |
| | $f_z$ | 0,1-**0,2**-0,3 | 0,1-**0,2**-0,3 | 0,1-**0,15**-0,2 | 0,2-**0,3**-0,4 |
| (B) | $v_c$ | 160-**200**-240 | 80-**120**-160 | 40-**60**-80 | 80-**100**-120 |
| | $f_z$ | 0,1-**0,2**-0,3 | 0,1-**0,2**-0,3 | 0,1-**0,15**-0,2 | 0,2-**0,3**-0,4 |




[$v_c$ =m/min, $f_z$ =mm/tooth] [min.– optimum – max.]





● = Euro stock
○ = Japan stock


Recommended Tightening Torque (N·m)

# "Wave Ball Mill" for Roughing
# WBMR 2000

| Rake Angle | | |
|---|---|---|
| | Radial | – |
| | Axial | -10° |

20–47mm






## Body (Short and middle length type, 2 teeth)

| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | APMX | LH | LS | LU | LF |
| WBMR 2200 S | ● | 20 | 25 | 20 | 60 | 80 | 40 | 140 |
| 2200 M | ● | 20 | 25 | 20 | 60 | 140 | 40 | 200 |
| 2200 MW | ● | 20 | 25 | 20 | 60 | 140 | 40 | 200 |
| WBMR 2250 S | ● | 25 | 32 | 23 | 70 | 80 | 50 | 150 |
| 2250 M | ● | 25 | 32 | 23 | 73 | 147 | 50 | 220 |
| 2250 MW | ● | 25 | 32 | 23 | 73 | 147 | 50 | 220 |
| WBMR 2320 S | ● | 32 | 32 | 31 | 80 | 80 | 60 | 160 |
| 2320 M | ● | 32 | 32 | 31 | 85 | 155 | 60 | 240 |
| 2320 MW | ● | 32 | 32 | 31 | 85 | 155 | 60 | 240 |
| WBMR 2400 S | ❍ | 40 | 42 | 35 | 100 | 100 | - | 200 |
| 2400 M | ❍ | 40 | 42 | 35 | 180 | 100 | - | 280 |
| WBMR 2500 S | ❍ | 50 | 42 | 47 | 100 | 100 | - | 200 |
| 2500 M | ❍ | 50 | 42 | 47 | 180 | 100 | - | 280 |


S: **S**hort type with cylindrical shank
M: **M**iddle length type with cylindrical shank
MW: **M**iddle length type with Weldon shank

# "Wave Ball Mill" for Roughing
# WBMR 2000 L

| Rake Angle | | |
|---|---|---|
| | Radial | – |
| | Axial | -10° |

30–69mm






## Body (Extra long type, 4 teeth)

| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | DC | DMM | APMX | LH | LS | LU | LF |
| WBMR 2200 LL | ● | 20 | 25 | 30 | 80 | 170 | 40 | 250 |
| 2200 LLW | ● | 20 | 25 | 30 | 80 | 170 | 40 | 250 |
| WBMR 2250 LL | ❍ | 25 | 32 | 38 | 100 | 200 | 50 | 300 |
| 2250 LLW | ● | 25 | 32 | 38 | 100 | 200 | 50 | 300 |
| WBMR 2320 LL | ● | 32 | 32 | 44 | 120 | 230 | 60 | 350 |
| 2320 LLW | ● | 32 | 32 | 44 | 120 | 230 | 60 | 350 |
| WBMR 2400 LL | ❍ | 40 | 42 | 50 | 250 | 100 | - | 350 |
| 2400 LLW | | 40 | 42 | 50 | 250 | 100 | - | 350 |
| WBMR 2500 LL | ❍ | 50 | 42 | 69 | 250 | 100 | - | 350 |
| 2500 LLW | | 50 | 42 | 69 | 250 | 100 | - | 350 |

LL: Extra long type with cylindrical shank
LLW: Extra long type with Weldon shank

## Inserts

| Application | Coated Carbide | | |
|---|---|---|---|
| High Speed / Light cut | | | |
| General Purpose | PM | PM | |
| Roughing | PM | PM | K |

| Cat. No. | ACP200 | ACP300 | ACK300 | Dimensions (mm) L | W1 | S | RE | Fig. | No. of teeth | Applicable Endmill |
|---|---|---|---|---|---|---|---|---|---|---|
| ZNMT 1804100-C | ● | ● | ● | 18,00 | 9,76 | 4,76 | 10,0 | 1 | 1 | WBMR 2200 |
| 2004100-S | ● | ● | ● | 20,00 | 7,50 | 4,37 | 10,0 | 2 | 1 | |
| SPMT 070308 | ❍ | ❍ | | 7,94 | - | 3,18 | - | 3 | 2 | |
| ZNMT 2205125-C | ● | ● | ● | 22,50 | 12,20 | 5,70 | 12,5 | 1 | 1 | WBMR 2250 |
| 2305125-S | ● | ● | ● | 23,00 | 9,38 | 5,56 | 12,5 | 2 | 1 | |
| SPMT 09T308 | ● | ● | ● | 9,53 | - | 3,97 | - | 3 | 2 | |
| ZNMT 2907160-C | ● | ● | ● | 29,00 | 15,62 | 7,15 | 16,0 | 1 | 1 | WBMR 2320 |
| 3006160-S | ● | ● | ● | 30,00 | 12,00 | 6,70 | 16,0 | 2 | 1 | |
| SPMT 09T308 | ● | ● | ● | 9,53 | - | 3,97 | - | 3 | 2 | |
| ZNMT 3608200 | ❍ | ❍ | ❍ | 36,00 | 19,50 | 6,70 | 20,0 | 4 | 2 | WBMR 2400 |
| SPMT 09T308 | ● | ● | ● | 9,53 | - | 3,97 | - | 3 | 2 | |
| ZNMT 4310250 | ❍ | | ❍ | 43,00 | 25,70 | 10,15 | 25 | 4 | 2 | WBMR 2500 |
| 4310250-N | ❍ | | ❍ | 43,00 | 25,70 | 10,15 | 25 | 5 | 2 | |
| SPMT 120408 | ❍ | ❍ | ❍ | 12,7 | - | 4,76 | - | 3 | 2 | |


Fig. 1




Fig. 2



Fig. 3






Fig. 4



Fig. 5



## Spare Parts

| Screw | | Wrench | Wrench | Applicable Endmill |
|---|---|---|---|---|
| | N·m | | | |
| BFTX 0307N | 2,0 | TRX10 | – | WBMR 2200, WBMR 2200 LL |
| BFTX 0409N | 3,4 | – | TRD15 | WBMR 2250, WBMR 2250LL |
| BFTX 0511N | 5,0 | – | TRD20 | WBMR 2320, WBMR 2320LL |
| BFTX 0407N | 3,0 | – | TRD15 | WBMR 2320LL |
| BFTX0619N | 7,5 | – | TRD25 | WBMR 2400, WBMR 2500, WBMR 2400LL, WBMR 2500LL |
| BFTX 0409N | 3,4 | – | TRD15 | WBMR 2500LL |

# "Wave Ball Mill" for Finishing
# WBMF Type



## Features


The outstanding results obtained from this finishing cutter are due to the combination of its large sigmoid blade and precise clamping system making it extremely rigid !

The WBMF achieves an excellent machined finish greatly reducing hand finishing and polishing operations.

## Advantages

- Unique rigid clamping system
- Large sigmoid blade
- Smooth cutting action
- High quality machined surface
- Ultra hard ZX coated cutting edge







## Application Example

● Bumper Moulding Die

Work Material :
C55




<Results>
Surface roughness after continuous cutting for twelve hours was better than other manufacturer's product.
Less width of flank wear was observed.

| | |
|---|---|
| WBMF1200M (ø20mm)<br>Insert : ZPGU2471100<br>Grade : ACZ120 | Cutting Conditions<br>$v_c$ = 88 m/min<br>$v_f$ = 700 mm/min ( $f_z$ = 0,25 mm/tooth)<br>Width of Cut : 0,5 mm<br>Depth of Cut : 0,5 mm<br>Dry |

● Bumper Moulding Die

Work Material :
C50



<Results>
Smooth cutting and good surface finish after continuous cutting for eight hours

| | |
|---|---|
| WBMF1200M (ø20mm)<br>Insert : ZPGU2471100<br>Grade : ACZ120 | Cutting Conditions<br>$v_c$ = 190 m/min<br>$v_f$ = 1200 mm/min ( $f_z$ = 0,21 mm/tooth)<br>Width of Cut : 0,2 mm<br>Depth of Cut : 0,2 mm<br>Dry |






● = Euro stock
○ = Japan stock

Recommended Tightening Torque (N·m)

# WBMF 1000

| Rake Angle | | |
|---|---|---|
| | Radial | – |
| | Axial | 0° |










## Body

| Cat. No. | | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| | | | DC | DMM | APMX | LH | LS | LU | LF |
| WBMF | 1100 S | ❍ | 10 | 16 | 9 | 30 | 70 | 17 | 100 |
| | 1100 M | ● | 10 | 16 | 9 | 35 | 95 | 17 | 130 |
| | 1100 L | ❍ | 10 | 16 | 9 | 50 | 130 | 17 | 180 |
| WBMF | 1120 S | ❍ | 12 | 16 | 10,5 | 40 | 70 | 19,5 | 110 |
| | 1120 M | ● | 12 | 16 | 10,5 | 40 | 110 | 19,5 | 150 |
| | 1120 MM12N | | 12 | 12 | 10,5 | 40 | 110 | 19,5 | 150 |
| | 1120 L | ❍ | 12 | 16 | 10,5 | 60 | 140 | 19,5 | 200 |
| WBMF | 1160 S | ❍ | 16 | 20 | 12 | 50 | 80 | 25,5 | 130 |
| | 1160 M | ● | 16 | 20 | 12 | 50 | 130 | 25,5 | 180 |
| | 1160 MM12N | | 16 | 16 | 12 | 50 | 130 | 25,5 | 180 |
| | 1160 L | ❍ | 16 | 20 | 12 | 70 | 150 | 25,5 | 220 |
| WBMF | 1200 S | ❍ | 20 | 25 | 15 | 60 | 80 | 32 | 140 |
| | 1200 M | ● | 20 | 25 | 15 | 60 | 140 | 32 | 200 |
| | 1200 MM20N | | 20 | 20 | 15 | 60 | 140 | 32 | 200 |
| | 1200 L | ❍ | 20 | 25 | 15 | 80 | 170 | 32 | 250 |
| WBMF | 1250 S | ❍ | 25 | 32 | 18,5 | 70 | 80 | 36 | 150 |
| | 1250 M | ● | 25 | 32 | 18,5 | 73 | 147 | 36 | 220 |
| | 1250 L | ❍ | 25 | 32 | 18,5 | 100 | 200 | 36 | 300 |
| WBMF | 1300 S | | 30 | 32 | 22,5 | 80 | 80 | 43 | 160 |
| | 1300 M | ● | 30 | 32 | 22,5 | 85 | 155 | 43 | 240 |
| | 1300 L | | 30 | 32 | 22,5 | 120 | 230 | 43 | 350 |

S : **S**hort type
M : **M**iddle length type
L : **L**ong type

## Inserts

| Application | Coated |
|---|---|
| High Speed / Light cut | P |
| General Purpose | |
| Roughing | |




| Cat. No. | ACZ120 | Dimensions (mm) | | | | | Applicable Endmill |
|---|---|---|---|---|---|---|---|
| | | DC | L | APMX | S | RE | |
| ZPGU 1551050 | ● | 10 | 15,6 | 9 | 5,1 | 5,0 | WBMF1100 |
| ZPGU 1856060 | ● | 12 | 18 | 10,5 | 5,6 | 6,0 | WBMF1120 |
| ZPGU 2061080 | ● | 16 | 20,5 | 12 | 6,1 | 8,0 | WBMF1160 |
| ZPGU 2471100 | ● | 20 | 24,5 | 15 | 7,1 | 10,0 | WBMF1200 |
| ZPGU 2876125 | ● | 25 | 28,5 | 18,5 | 7,6 | 12,5 | WBMF1250 |
| ZPGU 3486150 | ● | 30 | 34,4 | 22,5 | 8,6 | 15,0 | WBMF1300 |

## Spare Parts

| Screw | | Wrench | Applicable Endmill |
|---|---|---|---|
| | N·m | | |
| BFTG0408F | 3,4 | TRD15 | WBMF1100 |
| BFTG0409F | 3,4 | TRD15 | WBMF1120 |
| BFTG0513F | 5,0 | TRD20 | WBMF1160 |
| BFTG0617F | 7,5 | TRD25 | WBMF1200 |
| BFTG0621F | 7,5 | TRD25 | WBMF1250 |
| BFTG0825F | 7,5 | TRD25 | WBMF1300 |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Insert Grade |
|---|---|---|---|---|---|
| P | Carbon Steel | 180–280 HB | 200–**250**–300 | 0,10–**0,20**–0,30 | ACZ210 |
| | Alloy Steel | 180–280 HB | 100–**150**–200 | 0,10–**0,20**–0,30 | ACZ210 |

Min.–**Optimum**–Max.

# "Wave Radius Mill"
# WRCX 08000/10000 E


## Shank Type with Small Diameter Inserts

4,0 mm (WRCX 08000) 5,0 mm (WRCX 10000)



E_ : Cylindrical straight shank type

ES : **S**hort type with straight shank
EM : **M**iddle length type with straight shank
EL : **L**ong type with straight shank




Axial rake angle: – 3°
Radial rake angle: 0 – 35°

## Body

## Spare Parts

| Cat. No. | Stock | Dimensions (mm) DCX | DMM | DN | APMX | LF | LH | LS | No. of teeth | Axial Rake | Radial Rake | Helical Boring øB Standard | Plunging α max. | Spare Parts | N·m | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| WRCX 08012 ES | ● | 12 | 12 | 9,4 | 4 | 110 | 40 | 70 | 1 | -3° | -35° | - | 0°30' | BFTX 02505 IP | 1,5 | TRDR 08 IP |
| 08012 EM | | 12 | 12 | 9,4 | 4 | 150 | 70 | 80 | 1 | | | | | | | |
| WRCX 08016 ES | ● | 16 | 16 | 14 | 4 | 120 | 50 | 70 | 1 | -3° | -10° | $24^{+7}_{-4}$ | 5°30' | | | |
| 08016 EM | ● | 16 | 16 | 14 | 4 | 150 | 70 | 80 | 1 | | | | | | | |
| WRCX 08020 ES | ● | 20 | 20 | 18 | 4 | 130 | 50 | 80 | 2 | -3° | -3° | $32^{\pm7}$ | 13° | BFTX 02506 IP | 1,5 | TRDR 08 IP |
| 08020 EM | ● | 20 | 20 | 18 | 4 | 180 | 100 | 80 | 2 | | | | | | | |
| 08020 EL | ● | 20 | 20 | 18 | 4 | 250 | 130 | 120 | 2 | | | | | | | |
| WRCX 08025 ES | ● | 25 | 25 | 21 | 4 | 130 | 50 | 80 | 3 | -3° | 0° | $42^{\pm7}$ | 8°20' | | | |
| 08025 EM | ● | 25 | 25 | 21 | 4 | 180 | 100 | 80 | 3 | | | | | | | |
| 08025 EL | ● | 25 | 25 | 21 | 4 | 250 | 130 | 120 | 3 | | | | | | | |
| WRCX 10025 ES | ● | 25 | 25 | 21 | 5 | 130 | 50 | 80 | 2 | -3° | 0° | $40^{\pm8}$ | 13°10' | BFTX 03584 IP | 3,0 | TRDR 15 IP |
| 10025 EM | ● | 25 | 25 | 21 | 5 | 180 | 100 | 80 | 2 | | | | | | | |
| 10025 EL | ● | 25 | 25 | 21 | 5 | 250 | 130 | 120 | 2 | | | | | | | |
| WRCX 10032 ES | ● | 32 | 32 | 28 | 5 | 130 | 50 | 80 | 3 | -3° | 0° | $54^{\pm8}$ | 8° | | | |
| 10032 EM | ● | 32 | 32 | 28 | 5 | 200 | 120 | 80 | 3 | | | | | | | |
| 10032 EL | ● | 32 | 32 | 28 | 5 | 300 | 180 | 120 | 3 | | | | | | | |

## Inserts

| Application | Coated Carbide | | | | | Uncoated Carbide | Diamond Coated |
|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | K N | N |
| General Purpose | | P M | P M | K | | | N |
| Roughing | | P M | P M | | K | | |

| Cat. No. | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | H1 | DL1000 | Dimensions (mm) IC | RE | S | Fig. | Applicable Endmill |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| QPMT 080330 PPEN | | ● | ● | ● | ● | | | 8 | 3,0 | 3,18 | 1 | WRCX 08000 E |
| 080330 PPEN-H | ● | ● | ● | ● | ● | | | 8 | 3,0 | 3,18 | 1 | |
| QPMT 10T335 PPEN | | ● | ● | ● | ● | | | 10 | 3,5 | 3,97 | 1 | WRCX 10000 E |
| 10T335 PPEN-H | ● | ● | ● | ● | ● | | | 10 | 3,5 | 3,97 | 1 | |
| QPET 10T350 PPFR-S | | | | | | ● | ● | 10 | 5,0 | 3,97 | 2 | |

Fig. 1






Fig. 2




QPMT... : Standard 16 cornered polygon type
QPMT...-H: Stronger cutting edge type

QPET...-S: Polished round insert for non-ferrous material

## Recommended Cutting Conditions

| ISO | Work Material | Hardness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Insert Grade |
|---|---|---|---|---|---|
| P | Carbon Steel | 180–280 HB | 80–**120**–160 | 0,10–**0,30**–0,40 | ACP200 |
| P | Alloy Steel | 180–280 HB | 60–**100**–140 | 0,10–**0,20**–0,30 | ACP200 |
| M | Stainless Steel | – | 60–**100**–120 | 0,10–**0,15**–0,20 | ACP300 |
| K | Cast Iron | 250 HB | 60– **80**–120 | 0,10–**0,20**–0,30 | ACK200 |
| N | Non-ferrous Alloys | – | 200–**500**–1.000 | 0,10–**0,20**–0,30 | DL1000 |

Min.–**Optimum**–Max.





● = Euro stock

→ G17

Recommended Tightening Torque (N·m)

# WRCX 0800/10000/12000 M

## Modular Type


| Rake Angle | | |
|---|---|---|
| | Radial | -3°– 0° |
| | Axial | -3° |

4,0 mm (WRCX 08000M) | 5,0 mm (WRCX 10000M) | 6,0 mm (WRCX 12000M)


(WRCX 08000M)


(WRCX 10000M)


(WRCX 12000M)




### Heads — For insert type : QPMT 0803

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| WRCX 08020M10Z2 | ● | 20 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 2 |
| WRCX 08025M12Z3 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 3 |

Inserts are not included.

### Heads — For insert type : QPOT 10T3

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| WRCX 10025M12Z2 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 |
| 10028M12Z3 | | 28 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 |
| WRCX 10030M16Z3 | | 30 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |
| 10032M16Z3 | ● | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 |

Inserts are not included.

### Identification Details

| WRCX | 08 | 020 | M10 | Z2 |
|---|---|---|---|---|
| Cutter Type | Insert Size | Diameter | Mounting Screw | No. of Teeth |

### Heads — For insert type : QPOT 1204

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of teeth |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | |
| WRCX 12040M16Z4 | ❍ | 40 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 4 |

Inserts are not included.




### Inserts

| Application | Coated Carbide | | | | | Uncoated carbide | Diamond Coated |
|---|---|---|---|---|---|---|---|
| High Speed / Light cut | P | | | K | | K N | N |
| General Purpose | | P M | P M | K | | | N |
| Roughing | | P M | P M | | K | | |

QPMT... : 16 corner insert for general purpose application
QPMT...-H: 16 corner insert with strong cutting edge
QPET...-S: Round insert with sharp cutting edge for aluminium

| Cat. No. | | ACP100 | ACP200 | ACP300 | ACK200 | ACK300 | H1 | DL1000 | Dimensions (mm) IC | RE | S | Fig. | Applicable Endmill |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| QPMT | 080330 PPEN | | ● | ● | ● | ● | | | 8 | 3,0 | 3,18 | 1 | WRCX 08000 M |
| | 080330 PPEN-H | ● | ● | ● | ● | ● | | | 8 | 3,0 | 3,18 | 1 | |
| QPMT | 10T335 PPEN | | ● | ● | ● | ● | | | 10 | 3,5 | 3,97 | 1 | WRCX 10000 M |
| | 10T335 PPEN-H | ● | ● | ● | ● | ● | | | 10 | 3,5 | 3,97 | 1 | |
| QPET | 10T350 PPFR-S | | | | | | ● | ● | 10 | 5,0 | 3,97 | 2 | |
| QPMT | 120440 PPEN | ● | ● | ● | ● | ● | | | 12 | 4,0 | 4,76 | 1 | WRCX 12000 M |
| | 120440 PPEN-H | ● | ● | ● | ● | ● | | | 12 | 4,0 | 4,76 | 1 | |
| QPET | 120460 PPFR-S | | | | | | ● | ● | 12 | 6,0 | 4,76 | 2 | |

Fig. 1






Fig. 2




### Spare Parts

| Screw | | Wrench | Applicable Endmill |
|---|---|---|---|
| | N·m | | |
| BFTX 02506 IP | 1,5 | TRDR 08 IP | WRCX 08020M – WRCX 08025M |

### Spare Parts

| Screw | | Wrench | Applicable Endmill |
|---|---|---|---|
| | N·m | | |
| BFTX 03584 IP | 3,0 | TRDR 15 IP | WRCX 10025M – WRCX 10032M |
| BFTX 0409 IP | 3,0 | TRDR 15 IP | WRCX 12040M |

### Recommended Cutting Conditions

Diameter Ø20 – Ø32 mm

| ISO | Work Material | Hardness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Insert Grade |
|---|---|---|---|---|---|
| P | Carbon Steel | 180–280 HB | 80–**120**–160 | 0,10–**0,30**–0,40 | ACP200 |
| P | Alloy Steel | 180–280 HB | 60–**100**–140 | 0,10–**0,20**–0,30 | ACP200 |
| M | Stainless Steel | – | 60–**100**–120 | 0,10–**0,15**–0,20 | ACP300 |
| K | Cast Iron | 250 HB | 60– **80**–120 | 0,10–**0,20**–0,30 | ACK200 |
| N | Non-ferrous Alloys | – | 200–**500**–1.000 | 0,10–**0,20**–0,30 | DL1000 |

Min.–**Optimum**–Max.

Diameter Ø40 mm

| ISO | Work Material | Hardness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Insert Grade |
|---|---|---|---|---|---|
| P | Carbon Steel | 180–280 HB | 100–**160**–200 | 0,20–**0,40**–0,60 | ACP200 |
| P | Alloy Steel | 180–280 HB | 100–**140**–180 | 0,20–**0,30**–0,40 | ACP200 |
| M | Stainless Steel | – | 80–**120**–160 | 0,10–**0,20**–0,30 | ACP300 |
| K | Cast Iron | 250 HB | 80–120–160 | 0,10–**0,20**–0,40 | ACK200 |
| N | Non-ferrous Alloys | – | 200–**500**–1.000 | 0,10–**0,30**–0,40 | DL1000 |


Min.–**Optimum**–Max.

# "Wave Radius Mill"
# RSX(F)08000/10000/12000ES


Milling of steel, stainless steel, cast iron and exotic alloys

## Shank Type


| Rake Angle | | |
|---|---|---|
| | Radial | -5°– -8° |
| | Axial | 10° |



(08000ES)




(10000ES)



(12000ES)








## Body (RSX...ES, Standard)


| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DMM | DN | LH | LS | LF | | |
| RSX 08020 ES | ● | 20 | 20 | 16,9 | 30 | 70 | 100 | 2 | 0,3 |
| 08025 ES | ● | 25 | 25 | 21,9 | 40 | 80 | 120 | 3 | 0,4 |
| RSX 10025 ES | ● | 25 | 25 | 20,3 | 50 | 80 | 130 | 2 | 0,4 |
| 10032 ES | ● | 32 | 32 | 27,1 | 50 | 80 | 130 | 3 | 0,7 |
| RSX 12032 ES | ● | 32 | 32 | 25,6 | 50 | 80 | 130 | 2 | 0,7 |

## Body (RSXF...ES, Fine Pitch)

| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DMM | DN | LH | LS | LF | | |
| RSXF08020 ES | ● | 20 | 20 | 16,9 | 30 | 70 | 100 | 3 | 0,3 |
| 08025 ES | ● | 25 | 25 | 21,9 | 40 | 80 | 120 | 4 | 0,4 |
| RSXF10025 ES | ● | 25 | 25 | 20,3 | 50 | 80 | 130 | 3 | 0,4 |
| 10032 ES | ● | 32 | 32 | 27,1 | 50 | 80 | 130 | 4 | 0,7 |
| RSXF12032 ES | ● | 32 | 32 | 25,6 | 50 | 80 | 130 | 3 | 0,7 |

## Inserts

| Application | Grade | | | | | | | |
|---|---|---|---|---|---|---|---|---|
| High Speed/Light Cut | | | MS | MS | | | | |
| General Purpose | PM | | MS | MS | MS | | | |
| Roughing | PM | K | | | MS | | | |
| Cat. No. | ACP200 | ACK300 | ACM100 | ACM200 | ACM300 | Dimens. IC | Dimens. S | Applicable Cutters |
| RDET 0803M0EN G | ● | ● | ● | ● | ● | 8 | 3,18 | RSX(F) 08000ES |
| 0803M0EN H | ❍ | ● | ● | ● | ● | 8 | 3,18 | |
| RDET 10T3M0EN G | ● | ● | ● | ● | ● | 10 | 3,97 | RSX(F) 10000ES |
| 10T3M0EN H | ● | ● | ● | ● | ● | 10 | 3,97 | |
| RDET 1204M0EN G | ● | ● | ● | ● | ● | 12 | 4,76 | RSX(F) 12000ES |
| 1204M0EN H | ● | ● | ● | ● | ● | 12 | 4,76 | |




Cutting Edge Cross Section



**G** - Type **H** - Type

M0: IC is metric

## Spare Parts

| Applicable Cutters | Wrench | Screw | N·m |
|---|---|---|---|
| RSX(F) 08000ES | TRDR08IP | BFTX02506IP | **1,5** |
| RSX(F) 10000ES | TRDR15IP | BFTX03584IP | **3,0** |
| RSX(F) 12000ES | | BFTX0409IP | **3,0** |

## Identification Details

| RSX | F | 10 | 025 | ES |
|---|---|---|---|---|
| Cutter Series | Fine Pitch Type | Insert Size | Cutter Diameter | Endmill Type |

## Recommended Cutting Conditions

Min.-**Optimum**-Max.

| ISO | Work Material | | | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_t$ (mm/t) | Grade |
|---|---|---|---|---|---|---|---|
| P | Carbon Steel | | | 180–280 | 100–**160**–200 | 0,20–**0,40**–0,60 | ACP200 |
| | Alloy Steel | | | 180–280 | 100–**140**–180 | 0,20–**0,30**–0,40 | ACP200 |
| M | Stain-less Steel | Cr Based | Ferritic | 200 | 150–**180**–200 | 0,15–**0,25**–0,35 | ACM300 |
| | | | Martensitic | 200–330 | 80–**120**–180 | 0,15–**0,25**–0,35 | ACM300 |
| | | Cr-Ni Based | Austenitic | 200 | 150–**180**–200 | 0,15–**0,25**–0,35 | ACM300 |
| | | | Austenitic, ferritic | 230–270 | 80–**120**–180 | 0,15–**0,25**–0,35 | ACM200 |
| | | | Precipitation hardening | 330 | 60–**100**–160 | 0,15–**0,25**–0,35 | ACM200 |
| K | Cast Iron | | | 250 | 80–**120**–160 | 0,10–**0,30**–0,40 | ACK300 |
| S | Heat resistant alloy | | Ni based material | 250–350 | 20–**30**– 40 | 0,10–**0,20**–0,30 | ACM100 ACM200 |
| | Titanium | | Pure Titanium | (Rm400) | 60–**80**–100 | 0,10–**0,20**–0,30 | |
| | | | $\alpha + \beta$ alloy system | (Rm1050) | 40–**50**–60 | 0,10–**0,20**–0,30 | |





● = Euro stock
❍ = Japan stock


→ G20/G21


N·m Recommended Tightening Torque (N·m)

## Modular Type

| Rake Angle | | |
|---|---|---|
| | Radial | -5°– -8° |
| | Axial | 10° |

4,0 mm (08000ES) 5,0 mm (10000ES) 6,0 mm (12000ES)




### Body (RSX...M, Standard)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | | |
| RSX 08020M10Z2 | ● | 20 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 2 | 0,1 |
| 08025M12Z3 | ❍ | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 3 | 0,1 |
| 08032M16Z4 | ❍ | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 4 | 0,2 |
| RSX 10025M12Z2 | ❍ | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 2 | 0,1 |
| 10032M16Z3 | ● | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 | 0,2 |
| RSX 12032M16Z2 | ❍ | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 2 | 0,2 |
| 12040M16Z3 | ● | 40 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 | 0,3 |


### Body (RSXF...M, Fine Pitch)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | | |
| RSXF 08020M10Z3 | ❍ | 20 | 10,5 | M10 | 49 | 30 | 5 | 19 | 8 | 15 | 3 | 0,1 |
| 08025M12Z4 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 4 | 0,1 |
| 08032M16Z5 | ● | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 5 | 0,2 |
| RSXF 10025M12Z3 | ● | 25 | 12,5 | M12 | 56 | 35 | 5 | 21 | 10 | 19 | 3 | 0,1 |
| 10032M16Z4 | ● | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 4 | 0,2 |
| RSXF 12032M16Z3 | ● | 32 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 | 0,2 |
| 12040M16Z4 | ● | 40 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 4 | 0,3 |

### Inserts

| Application | Grade | | | | |
|---|---|---|---|---|---|
| | ACP200 | ACK300 | ACM100 | ACM200 | ACM300 |
| High Speed/Light Cut | | | MS | MS | |
| General Purpose | PM | | MS | MS | MS |
| Roughing | PM | K | | | MS |

| Cat. No. | ACP200 | ACK300 | ACM100 | ACM200 | ACM300 | Dimens. IC | Dimens. S | Applicable Cutters |
|---|---|---|---|---|---|---|---|---|
| RDET 0803M0EN G | ● | ● | ● | ● | ● | 8 | 3,18 | RSX(F) 08000ES |
| 0803M0EN H | ❍ | ● | ● | ● | ● | 8 | 3,18 | |
| RDET 10T3M0EN G | ● | ● | ● | ● | ● | 10 | 3,97 | RSX(F) 10000ES |
| 10T3M0EN H | ● | ● | ● | ● | ● | 10 | 3,97 | |
| RDET 1204M0EN G | ● | ● | ● | ● | ● | 12 | 4,76 | RSX(F) 12000ES |
| 1204M0EN H | ● | ● | ● | ● | ● | 12 | 4,76 | |




Cutting Edge Cross Section

**G** - Type **H** - Type

M0: IC is metric

### Spare Parts

| Applicable Cutters | Wrench | Screw | N·m |
|---|---|---|---|
| RSX(F) 08000M | TRDR08IP | BFTX02506IP | **1,5** |
| RSX(F) 10000M | TRDR15IP | BFTX03584IP | **3,0** |
| RSX(F) 12000M | | BFTX0409IP | **3,0** |

### Identification Details

| RSX | F | 10 | 025 | M12 | Z3 |
|---|---|---|---|---|---|
| Cutter Series | Fine Pitch Type | Insert Size | Cutter Diameter | Mounting Screw Size | No. of Teeth |

### Recommended Cutting Conditions

Min.-**Optimum**-Max.

| ISO | Work Material | | | Hardness (HB) | Cutting Speed $v_c$ (m/min) | Feed Rate $f_t$ (mm/t) | Grade |
|---|---|---|---|---|---|---|---|
| P | Carbon Steel | | | 180–280 | 100–**160**–200 | 0,20–**0,40**–0,60 | ACP200 |
| | Alloy Steel | | | 180–280 | 100–**140**–180 | 0,20–**0,30**–0,40 | ACP200 |
| M | Stain-less Steel | Cr Based | Ferritic | 200 | 150–**180**–200 | 0,15–**0,25**–0,35 | ACM300 |
| | | | Martensitic | 200–330 | 80–**120**–180 | 0,15–**0,25**–0,35 | ACM300 |
| | | Cr-Ni Based | Austenitic | 200 | 150–**180**–200 | 0,15–**0,25**–0,35 | ACM300 |
| | | | Austenitic, ferritic | 230–270 | 80–**120**–180 | 0,15–**0,25**–0,35 | ACM200 |
| | | | Precipitation hardening | 330 | 60–**100**–160 | 0,15–**0,25**–0,35 | ACM200 |
| K | Cast Iron | | | 250 | 80–**120**–160 | 0,10–**0,30**–0,40 | ACK300 |
| S | Heat resistant alloy | | Ni based material | 250–350 | 20–**30**–40 | 0,10–**0,20**–0,30 | ACM100 ACM200 |
| | Titanium | | Pure Titanium | (Rm 400) | 60–**80**–100 | 0,10–**0,20**–0,30 | |
| | | | $\alpha + \beta$ alloy system | (Rm 1050) | 40–**50**–60 | 0,10–**0,20**–0,30 | |

# WFXC Type

Expansion



## General Features


The WaveMill WFXC type is a chamfering tool that uses inserts for the WFX series. This allows the WFXC type to support many types of work materials using a variety of grades.

## Application Notes

Since chamfering uses the straight cutting edge portion of the insert, the range that can be chamfered will change depending on the corner radius (RE) of the insert that is attached to the body.
Work diameter: Use in a range grater or equal to DC1 and less than or equal to DC2.
Depth: The workpiece can be chamfered from „a“, which is the distance from the tip of the tool to the straight cutting edge at the depth indicated by „b“.

| Body | Insert | | Min. Work Diameter | Max. Work Diameter | Min. Depth | Max. Depth | Max. Diameter |
|---|---|---|---|---|---|---|---|
| | Cat. No. | RE | DC1 | DC2 | a | b | DCX |
| WFXC 08008E | SOMT 080304 | 0,4 | 7,5 | 15,8 | 0,1 | 4,1 | 17,8 |
| | SOMT 080308 | 0,8 | 8,0 | 15,8 | 0,2 | 3,9 | 17,5 |
| | SOMT 080312 | 1,2 | 8,5 | 15,8 | 0,4 | 3,6 | 17,2 |
| WFXC 08016E | SOMT 080304 | 0,4 | 15,5 | 23,8 | 0,1 | 4,1 | 25,8 |
| | SOMT 080308 | 0,8 | 16,0 | 23,8 | 0,2 | 3,9 | 25,5 |
| | SOMT 080312 | 1,2 | 16,5 | 23,8 | 0,3 | 3,6 | 25,2 |
| WFXC 12025E | SOMT 120404 | 0,4 | 24,6 | 38,3 | 0,1 | 6,8 | 41,3 |
| | SOMT 120408 | 0,8 | 25,0 | 38,3 | 0,2 | 6,6 | 41,0 |
| | SOMT 120412 | 1,2 | 25,6 | 38,3 | 0,4 | 6,3 | 40,7 |
| | SOMT 120416 | 1,6 | 26,1 | 38,3 | 0,5 | 6,1 | 40,4 |
| WFXC 12032E | SOMT 120404 | 0,4 | 31,6 | 45,3 | 0,1 | 6,8 | 48,3 |
| | SOMT 120408 | 0,8 | 32,0 | 45,3 | 0,2 | 6,6 | 48,0 |
| | SOMT 120412 | 1,2 | 32,6 | 45,3 | 0,4 | 6,3 | 47,7 |
| | SOMT 120416 | 1,6 | 33,1 | 45,3 | 0,5 | 6,1 | 47,4 |

Dimensions (mm)




→ G26/G27





● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)


# WFXC 08000/12000 E

Expansion



| Rake Angle | Radial | 0° |
|---|---|---|
| | Axial | 0° |

45°




## Body WFXC 08000E (Standard Type)

| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|
| | | DC1 | DCX | LF | LH | LS | DMM | | |
| WFXC 08008E | ❍ | 8 | 17,5 | 120 | 30 | 90 | 10 | 1 | 0,1 |
| 08016E | ❍ | 16 | 25,5 | 120 | 30 | 90 | 16 | 2 | 0,2 |

## Body WFXC 12000E (Standard Type)

| Cat. No. | Stock | Dimensions (mm) | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|
| | | DC1 | DCX | LF | LH | LS | DMM | | |
| WFXC 12025E | ❍ | 25 | 41,0 | 150 | 40 | 110 | 25 | 3 | 0,6 |
| 12032E | ❍ | 32 | 48,0 | 150 | 40 | 110 | 32 | 3 | 1,0 |

## Identification Details

| WFX | C | 08 | 016 | E |
|---|---|---|---|---|
| Cutter Series | Chamfering | Insert Size | Cutter Diameter | Endmill Type |

## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | | | P | | | K | K | | | | | | | | |
| General Purpose | | | | | | K | K | | | | | N | | | |
| Roughing | | | | | | | | K | | | | N | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | RE | Fig. | Applicable Cutters |
| SOMT 080304 PZER L | ● | ❍ | ● | ● | ❍ | ❍ | ❍ | ● | ● | ● | – | – | 0,4 | 1 | WFXC08000E |
| 080308 PZER L | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 1 | |
| SOMT 080304 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,4 | 1 | |
| 080308 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 1 | |
| 080312 PZER G | ● | | ● | ● | ● | | ❍ | ● | ● | ● | – | – | 1,2 | 1 | |
| SOMT 080308 PZER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 1 | |
| 080312 PZER H | ● | | ● | ● | ● | | ❍ | ● | ❍ | ● | – | – | 1,2 | 1 | |
| SOET 080304 PZER G | ● | | ❍ | ❍ | ❍ | | ❍ | ● | ● | ❍ | – | – | 0,4 | 1 | |
| 080308 PZER G | ● | | ❍ | ❍ | ❍ | | ❍ | ● | ● | ❍ | – | – | 0,8 | 1 | |
| 080312 PZER G | ● | | ❍ | ● | ❍ | | ❍ | ● | ❍ | ❍ | – | – | 1,2 | 1 | |
| SOET 080302 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,2 | 1 | |
| 080304 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,4 | 1 | |
| 080308 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,8 | 1 | |
| SOMT 120408 PDER L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 2 | WFXC12000E |
| SOMT 120404 PDER G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,4 | 2 | |
| 120408 PDER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 2 | |
| 120412 PDER G | ● | | ❍ | ● | ❍ | | ● | ❍ | ❍ | ● | – | – | 1,2 | 2 | |
| 120416 PDER G | ● | | ● | ● | ● | | ❍ | ❍ | ❍ | ❍ | – | – | 1,6 | 2 | |
| SOMT 120408 PDER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 2 | |
| SOET 120408 PDFR S | | | – | – | – | | – | – | – | – | ● | ● | 0,8 | 2 | |

Fig. 1






Fig. 2




## Spare Parts

| Applicable Cutter | Screw | | Wrench |
|---|---|---|---|
| | | (N·m) | |
| WFXC08000E | BFTX0306IP | 2,0 | TRDR08IP |
| WFXC12000E | BFTX03512IP | 3,0 | TRDR15IP |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Cutting Speed | Feed Rate |
|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,05–**0,10**–0,15 |
| | Soft Steel | ≤180 | 180–**265**–350 | 0,10–**0,15**–0,20 |
| | Die Steel | 200–220 | 100–**150**–200 | 0,05–**0,10**–0,15 |
| M | Stainless Steel | - | 150–**200**–250 | 0,05–**0,10**–0,15 |
| K | Cast Iron | 250 | 100–**175**–250 | 0,05–**0,10**–0,15 |

Min. - **Optimum** - Max.

# WFXC 08000/12000 M


Expansion

## Modular Type

| Rake Angle | | |
|---|---|---|
| | Radial | 0° |
| | Axial | 0° |

45°






## Head (WFXC 08000M)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC1 | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | | |
| WFXC 08016M08Z2 | ❍ | 16 | 25,5 | 8,5 | M8 | 42 | 25 | 5 | 17 | 8 | 13 | 2 | 0,1 |

## Identification Details

| WFX | C | 08 | 016 | M08 | Z2 |
|---|---|---|---|---|---|
| Cutter Series | Chamfe-ring | Insert Size | Cutter Diameter | Screw Size | No. of Teeth |

## Head (WFXC 12000M)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | | | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC1 | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | | |
| WFXC 12025M12Z3 | ❍ | 25 | 41,0 | 12,5 | M12 | 56 | 32 | 5 | 21 | 10 | 19 | 3 | 0,1 |
| 12032M16Z3 | ❍ | 32 | 48,0 | 17,0 | M16 | 63 | 40 | 5 | 23 | 10 | 24 | 3 | 0,2 |




## Inserts

Dimensions (mm)

| Application | Coated Carbide | | | | | | | | | | Carbide | DLC | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| High Speed / Light cut | | | P | | | K | K | | M S | | K N | | | | |
| General Purpose | | P K M | | P M | P M | K | K | | M S | M S | | N | | | |
| Roughing | | P K M | | P M | P M | | | K | | M S | | N | | | |
| Cat. No. | ACU2500 | XCU2500 | ACP100 | ACP200 | ACP300 | XCK2000 | ACK200 | ACK300 | ACM200 | ACM300 | H1 | DL1000 | RE | Fig. | Applicable Cutters |
| SOMT 080304 PZER L | ● | ❍ | ● | ● | ❍ | ❍ | ❍ | ● | ● | ● | – | – | 0,4 | 1 | WFXC08000E |
| 080308 PZER L | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 1 | |
| SOMT 080304 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,4 | 1 | |
| 080308 PZER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 1 | |
| 080312 PZER G | ● | | ● | ● | ● | | ❍ | ● | ● | ● | – | – | 1,2 | 1 | |
| SOMT 080308 PZER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 1 | |
| 080312 PZER H | ● | | ● | ● | ● | | ❍ | ● | ❍ | ● | – | – | 1,2 | 1 | |
| SOET 080304 PZER G | ● | | ❍ | ❍ | ❍ | | ❍ | ● | ● | ❍ | – | – | 0,4 | 1 | |
| 080308 PZER G | ● | | ❍ | ❍ | ❍ | | ❍ | ● | ● | ❍ | – | – | 0,8 | 1 | |
| 080312 PZER G | ● | | ❍ | ● | ❍ | | ❍ | ● | ❍ | ❍ | – | – | 1,2 | 1 | |
| SOET 080302 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,2 | 1 | |
| 080304 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,4 | 1 | |
| 080308 PZFR S | – | – | – | – | – | – | – | – | – | – | ● | ● | 0,8 | 1 | |
| SOMT 120408 PDER L | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 2 | WFXC12000E |
| SOMT 120404 PDER G | ● | ❍ | ❍ | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,4 | 2 | |
| 120408 PDER G | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 2 | |
| 120412 PDER G | ● | | ❍ | ● | ❍ | | ● | ❍ | ❍ | ● | – | – | 1,2 | 2 | |
| 120416 PDER G | ● | | ● | ● | ● | | ❍ | ❍ | ❍ | ❍ | – | – | 1,6 | 2 | |
| SOMT 120408 PDER H | ● | ❍ | ● | ● | ● | ❍ | ● | ● | ● | ● | – | – | 0,8 | 2 | |
| SOET 120408 PDFR S | | | – | – | – | | – | – | – | – | ● | ● | 0,8 | 2 | |

Fig. 1






Fig. 2




## Spare Parts

| Applicable Cutter | Screw | | Wrench |
|---|---|---|---|
| | | N·m | |
| WFXC08000M | BFTX0306IP | 2,0 | TRDR08IP |
| WFXC12000M | BFTX03512IP | 3,0 | TRDR15IP |

## Recommended Cutting Conditions

| ISO | Work Material | Hardness (HB) | Cutting Speed | Feed Rate |
|---|---|---|---|---|
| P | General Steel | 180–280 | 150–**200**–250 | 0,05–**0,10**–0,15 |
| P | Soft Steel | ≤180 | 180–**265**–350 | 0,10–**0,15**–0,20 |
| P | Die Steel | 200–220 | 100–**150**–200 | 0,05–**0,10**–0,15 |
| M | Stainless Steel | - | 150–**200**–250 | 0,05–**0,10**–0,15 |
| K | Cast Iron | 250HB | 100–**175**–250 | 0,05–**0,10**–0,15 |

Min. - **Optimum** - Max.



● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

Expansion



## Features

- **Drastically Reduced Runout Adjustment Time**
  Simple screw-fastening structure enables fine adjustments to be made easily.
- **Blade Through Coolant**
  Secures a supply of coolant to the cutting edge and breaks chips thoroughly.
- **Lightweight Aluminum Alloy Body**
  Utilizing aluminum alloy to achieve a total weight of less than 1,3 kg for a Ø 125 mm cutter with 22 teeth.









## Product Range

| Type | Cat. No. | Body Material | Diameter Range (mm) / No of Teeth | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | Ø 25 | Ø 30 | Ø 32 | Ø 40 | Ø 50 | Ø 63 | Ø 80 | Ø 100 | Ø 125 | Ø 160 |
| Shell | ANXA 16000RS | Aluminum Alloy | → G78 | | | | | | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | 12, 20, 28 |
| | ANXA 16000R (Inch) | Aluminum Alloy | | | | | | | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | 12, 20, 28 |
| | ANXS 16000RS | Steel | → G80 | | | 4, 6 | 4, 6, 9 | 6, 8, 12 | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | |
| | ANXS 16000R (Inch) | Steel | | | | | | 6, 8, 12 | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | |
| Shank | ANXS 16000E | Steel | 2 | 3, 4 | 3, 4 | 4, 6 | 4, 6, 9 | | | | | |
| Modular | ANXS 16000M | Steel | 2 | 3, 4 | 3, 4 | 4, 6 | | | | | | |

→ M58-M69


Inch Inch Bore


## Blade Selection Guide

| Work Material | N | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| Applications | Finishing / Light Cutting | General Purpose | Roughing | | Combined Milling *1 | Corner Radius Milling | Corner Radius Milling | Finishing | Burr-free / Mirror Finishing |
| Features | Low Cutting Force | Standard | Long Edge | High Strength | High Strength | Corner Radius 0,4 | Corner Radius 0,8 | Wiper | Wiper |
| Type | L | G | GX | H | GB | - | - | W | WS |
| Cutting Edge Shape |  |  |  |  |  |  |  |  |  |
| Edge Length(*2) | 6,0 mm | 6,0 mm | 9,0 mm | 6,0 mm | 6,0 mm | 6,0 mm | 6,0 mm | 2,0 mm | — |

*1 Machining of components combining aluminum alloy and cast iron

## Edge Selection Guide








*2 Edge length
GX type = 9,0 mm

- **Reduces Running Costs by Drastically Increasing Blade, Insert Regrinding Allowance (to 1,0 mm)**

Assuming 0,2 mm of regrinding each time, an edge can be used up to 6 times.
(Peripheral edge cannot be reground.)




If you wish to use reground blades you shall use sets of blades with matching size of the same level in order to keep the balance.

## Performances


### High-Speed / High-Efficiency Cutting

Realizes ultra-high efficiency machining with $v_f$ = 30.000 mm/min




Comparison: Cutter Diameter Ø 100 mm


| | Spindle Speed $min^{-1}$ | Number of Teeth | Feed Rate $v_f$ (mm/min) |
|---|---|---|---|
| ANX Series | 18.000 | 18 | 32.400 |
| Competitor | 9.500 | 12 | 11.400 |




### Drastically Reduces Runout Adjustment Time

– Simple screw-fastening structure
– Enables fine adjustments to be made easily
– High-rigidity body




### Chip Control




Blade-Through Coolant Chip Breaking




ALNEX ANX Series




Competitor

Work Material: G-AlSi12Cu
Cutting Conditions: $v_c$ = 2500 m/min, $f_z$ = 0,05 mm/t, $a_p$ = 0,5 mm, wet

## Adjustment of the Blades, Runout Alignment

① 



Insert the blade into its seat.

② 

While holding the blade against the seat, install the clamping bolt using the provided wrench, pre-tightening the bolt. (recommended pre-torque is 1 N·m)

③ 

Using the provided wrench for the height adjustment screw, set the height to your predetermined value.

④ 


Fully tighten the clamp bolt. (recommended torque is 2 N·m)


# ANXS 16000 E

Expansion

| Rake Angle | Radial | -2 – 0° |
|---|---|---|
| | Axial | +5° |

3 mm 90°






## Body - ANXS (Steel)

Dimensions (mm)

| Cat. No. | Stock | DC | DCX | DMM | LH | LS | LF | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|
| ANXS 16025E02 | ● | 23 | 25 | 20 | 35 | 60 | 95 | 2 | 0,2 |
| 16030E03 | ● | 28 | 30 | 20 | 35 | 60 | 95 | 3 | 0,3 |
| 16030E04 | ● | 28 | 30 | 20 | 35 | 60 | 95 | 4 | 0,3 |
| 16032E03 | ● | 30 | 32 | 20 | 35 | 60 | 95 | 3 | 0,3 |
| 16032E04 | ● | 30 | 32 | 20 | 35 | 60 | 95 | 4 | 0,3 |
| 16040E04 | ● | 38 | 40 | 20 | 40 | 60 | 100 | 4 | 0,4 |
| 16040E06 | ● | 38 | 40 | 20 | 40 | 60 | 100 | 6 | 0,5 |
| 16050E04 | ❍ | 48 | 50 | 32 | 40 | 80 | 120 | 4 | 1,0 |
| 16050E06 | ● | 48 | 50 | 32 | 40 | 80 | 120 | 6 | 1,0 |
| 16050E09 | ● | 48 | 50 | 32 | 40 | 80 | 120 | 9 | 1,0 |

Blades are sold separately. If using a blade for corner radius machining (ANB1604R/ANB1608R), DC = DCX.
The weight includes the weight of the blade and parts.

## Identification Details

| ANX | S | 16 | 032 | E | 04 |
|---|---|---|---|---|---|
| Cutter Series | Steel Body | Blade Size | Cutter Diameter | Round Shank | Number of Teeth |





● = Euro stock
❍ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

Expansion

## Blades

Dimensions (mm)

| Application | SUMIDIA | CVD |
|---|---|---|
| High Speed / Light Cut | N / K N | N |
| General Purpose | N / K N | |
| Roughing | N / K N | |

→ M60-M61

| Cat. No. | DA1000 | DA90 | SCV10 | Cutting Edge Length | RE | Wiper Edge Shape | Applications | Fig. |
|---|---|---|---|---|---|---|---|---|
| ANB 1600R-L | ● | | – | 6,0 | – | Linear | Low Cutting Force | 1 |
| 1600R-G | ● | | – | 6,0 | – | Arc-Shaped | General Purpose | 1 |
| 1600R-GB | | ● | – | 6,0 | – | Arc-Shaped | Combined Milling* | 1 |
| 1600R-H | ● | – | – | 6,0 | – | Arc-Shaped | Strong Edge | 1 |
| 1600R-GX | ❍ | | – | 9,0 | – | Arc-Shaped | Long Edge | 2 |
| 1604R | ❍ | | – | 6,0 | 0,4 | Linear | Corner Radius | 3 |
| 1608R | ❍ | | – | 6,0 | 0,8 | Linear | Corner Radius | 3 |
| 1600R-W | ❍ | | – | 2,0 | – | Arc-Shaped | Wiper | 4 |
| 1600R-WS | – | – | ❑ | – | – | Arc-Shaped | Wiper | 5 |

Fig. 1 16 6,0
Fig. 2 16 9,0
Fig. 3 16 6,0 RE
Fig. 4 16 2,0 Wiper Blade
Fig. 5 16 Wiper Blade

* Cast Iron/Aluminum Alloy

## Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 2.000–**2.500**–3.000 | 0,05–**0,13**–0,20 | DA1000 |

Si content > 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 400–**600**–800 | 0,05–**0,13**–0,20 | DA1000 DA90 |

Combined Milling of Cast Iron/Aluminum Alloy

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| K N | Cast Iron/ Aluminum Alloy | – | 300–**400**–500 | 0,05–**0,13**–0,20 | DA90 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

## Max. Allowable Spindle Speed

| Cat. No. | n max ($min^{-1}$) |
|---|---|
| ANXS 16025E02 | 10.000 |
| 16030E03 | 10.000 |
| 16030E04 | 10.000 |
| 16032E03 | 10.000 |
| 16032E04 | 10.000 |
| 16040E04 | 10.000 |
| 16040E06 | 10.000 |
| 16050E04 | 10.000 |
| 16050E06 | 10.000 |
| 16050E09 | 10.000 |

## Spare Parts


Sold separately.

| Applicable Cutters | Clamp Screw | | Adjustment Screw | Wrench | Adjustment Wrench | Assembly Wrench |
|---|---|---|---|---|---|---|
| ANXS 160_ _E_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | HFVT |

The adjustment spanner (ANT) can also be used for height adjustment of the RF type cutters for high speed machining and the HF type cutters for high efficiency machining.

### Wiper Blade Step Amount

When using the wiper blade, in order to maintain balance, be sure to use a cutter with an even number of cutting edges and place the wiper blades at opposite positions.



# ANXS 16000 M


New


Modular Type


| Rake Angle | Radial | -2 – 0° |
|---|---|---|
| | Axial | +5° |

3 mm 90°








## Body - ANXS (Steel)

Dimensions (mm)

| Cat. No. | Stock | DC | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ANXS 16025M12Z02 | ❍ | 23 | 25 | 12,5 | **M12** | 61 | 40 | 5 | 21 | 10 | 19 | 2 | 0,1 |
| 16030M16Z03 | ❍ | 28 | 30 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 3 | 0,2 |
| 16030M16Z04 | ❍ | 28 | 30 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 4 | 0,2 |
| 16032M16Z03 | ❍ | 30 | 32 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 3 | 0,3 |
| 16032M16Z04 | ❍ | 30 | 32 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 4 | 0,3 |
| 16040M16Z04 | ❍ | 38 | 40 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 4 | 0,4 |
| 16040M16Z06 | ❍ | 38 | 40 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 6 | 0,4 |

Blades are sold separately. If using a blade for corner radius machining (ANB1604R/ANB1608R), DC = DCX.
The weight includes the weight of the blade and parts.

## Identification Details

| ANX | S | 16 | 032 | M16 | Z03 |
|---|---|---|---|---|---|
| Cutter Series | Steel Body | Blade Size | Cutter Diameter | Screw size | Number of Blades |





● = Euro stock
❍ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

## Blades

Dimensions (mm)

| Application | SUMIDIA | CVD |
|---|---|---|
| High Speed / Light Cut | N / K N | N |
| General Purpose | N / K N | |
| Roughing | N / K N | |

→ M60-M61

| Cat. No. | DA1000 | DA90 | SCV10 | Cutting Edge Length | RE | Wiper Edge Shape | Applications | Fig. |
|---|---|---|---|---|---|---|---|---|
| ANB 1600R-L | ● | | – | 6,0 | – | Linear | Low Cutting Force | 1 |
| 1600R-G | ● | | – | 6,0 | – | Arc-Shaped | General Purpose | 1 |
| 1600R-GB | | ● | – | 6,0 | – | Arc-Shaped | Combined Milling* | 1 |
| 1600R-H | ● | – | – | 6,0 | – | Arc-Shaped | Strong Edge | 1 |
| 1600R-GX | ❍ | | – | 9,0 | – | Arc-Shaped | Long Edge | 2 |
| 1604R | ❍ | | – | 6,0 | 0,4 | Linear | Corner Radius | 3 |
| 1608R | ❍ | | – | 6,0 | 0,8 | Linear | Corner Radius | 3 |
| 1600R-W | ❍ | | – | 2,0 | – | Arc-Shaped | Wiper | 4 |
| 1600R-WS | – | – | ❑ | – | – | Arc-Shaped | Wiper | 5 |


Fig. 1 



Fig. 2 



Fig. 3 




Fig. 4 


Fig. 5 


Wiper Blade

Wiper Blade

* Cast Iron/Aluminum Alloy

## Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 2.000–**2.500**–3.000 | 0,05–**0,13**–0,20 | DA1000 |

Si content > 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 400–**600**–800 | 0,05–**0,13**–0,20 | DA1000 DA90 |

Combined Milling of Cast Iron/Aluminum Alloy

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| K N | Cast Iron/ Aluminum Alloy | – | 300–**400**–500 | 0,05–**0,13**–0,20 | DA90 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

## Max. Allowable Spindle Speed

| Cat. No. | n max ($min^{-1}$) |
|---|---|
| ANXS 16025M12Z02 | 10.000 |
| 16030M16Z03 | 10.000 |
| 16030M16Z04 | 10.000 |
| 16032M16Z03 | 10.000 |
| 16032M16Z04 | 10.000 |
| 16040M16Z04 | 10.000 |
| 16040M16Z06 | 10.000 |

## Spare Parts


Sold separately.

| Applicable Cutters | Clamp Screw | | Adjustment Screw | Wrench | Adjustment Wrench | Assembly Wrench |
|---|---|---|---|---|---|---|
| |  |  |  |  |  |  |
| ANXS160_ _M_Z_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | HFVT |

The adjustment spanner (ANT) can also be used for height adjustment of the RF type cutters for high speed machining and the HF type cutters for high efficiency machining.

### Wiper Blade Step Amount

When using the wiper blade, in order to maintain balance, be sure to use a cutter with an even number of cutting edges and place the wiper blades at opposite positions.



# J

# Coated & Solid Endmills

**J1–J44**






**Coated Endmills**

Selection Guide — According to Work Materials ..... J 2–3
GSX MILL Series — New **GSX** Global Standard Endmills ..... J 4–6

GSX MILL Series — **GSX** 20000 ..... J 7–11
**GSX** 30000 ..... J12–13
Slotted Type — **GSXSLT** 30000 ..... J14
**GSX** 40000 ..... J15–19
Anti-Vibration Type — **GSXVL** 40000 ..... J20–21
For High-Performance Milling — **EPMS** 4000/5000/6000 New ..... J22–23
SSEH MILL Series for Exotic Alloys — **SSEHVL** 4000W-R / **SSEH** 4000W-R ..... J24-26

GS MILL Series, Roughing Type — **GSRE** 4000SF ..... J27
Hard Type — **GSH** 4000/6000/8000SF ..... J28
AURORA COAT MILL Series — **ASM** 2000/4000DL / DL-R ..... J29–30
SSUP MILL Series — **SSUP** 4000ZX/ZX-R ..... J32–33

Hard Type — **LHHM** 4000/6000/8000ZX ..... J31
**EHHM** 4000/6000/8000ZX ..... J31

GSX Mills Ball Type — **GSXB** 20000 ..... J34
AURORA COAT Ball Type — **SNB** 2000DL ..... J35

**Uncoated Endmills**

For Aluminium Cutting — **ASM** 2000 ..... J36
SSEH MILL Series for Exotic Alloys — **SSEHVL** 4000-R / **SSEH** 4000-R ..... J37
Standard Type — **SSM** 2000/4000 ..... J38–39

SUMIBORON "Helical Master" for Hardened Steel — **BNES** 1000 ..... J40
SUMIBORON "Mould Finish Master" for Hardened Steel — **BNBP** 2R…4/6 ..... J41
SUMIDIA "Mould Finish Master" Binderless — **NPDRS / NPDB(S)** ..... J42–43

## ● According to Work Materials


### Square Type

Legend: Grade | Edge Type | Usage

#### General Steel (Common Use)

Coated | Sharp | General

Global Endmills
Standard
**GSX Type**
ø 1–25 mm
•2 Flutes
•3 Flutes
•4 Flutes



Anti-Vibration
Radius Corner
Endmills
**GSXVL Type**
ø 2–25 mm
•4 Flutes


➪ J7–19 ➪ J20–21

#### General Steel (Special Use)

Plunge Cut
Multi-Purpose

Coated | Sharp | General

GSX MILL
**GSXSLT Type**
ø 1–16 mm
•3 Flutes



➪ J14

High Efficiency

Coated | Strong | High Efficiency

UPMILL
**SSUP-ZX Type**
ø 2–20 mm
•4 Flutes



➪ J32–33

High Efficiency

Coated | Strong | High Efficiency

ROUGHING ENDMILL
**GSRE-SFType**
ø 6–20 mm
•4 Flutes



➪ J27

#### Hardened Steel

High performance Type

Coated | Strong | High Efficiency

GS-MILL-HARD
**GSH-SF Type**
ø 1–20 mm
•4 Flutes
•6 Flutes
•8 Flutes



➪ J28

High Rigidity Type

Coated | Strong | High Efficiency

HARD ENDMILL
**LHHM...ZX**
**EHHM...ZX**
ø 3–32 mm
•4 Flutes
•6 Flutes
•8 Flutes



➪ J31

SumiBoron Endmill

CBN

"Helical Master"
**BNES Type**
ø 6–16 mm
•1 Flute




➪ J40, M74

#### Exotic Metals

For Heat Resistant Steel

Coated | Sharp | High Efficiency

Radius Endmills
Anti-Vibration
**EPMS Type** New
ø10–26 mm
•6 Flutes




➪ J22-23

#### Non-ferrous Metal

SumiDia Endmill

PCD

SUMIDIA brazed
**DFE Type**
ø 4–13 mm
•1 Flute
•2 Flutes
•4 Flutes



➪ Stock in Japan

DLC-Coated Endmill

Coated | Sharp | General

AURORA COATED
**ASM-DL Type**
ø 2–16 mm
•2 Flutes
•4 Flutes




➪ J29–30

For Heat Resistant Steel

Coated | Sharp | General

Radius Endmills
Standard
**SSEH Type**
ø 4,5–25 mm
•4 Flutes

Anti-Vibration
Radius Endmills
**SSEHVL Type**
ø 4,5–25 mm
•4 Flutes



➪ J24, J26, J37 ➪ J24–25, J37

## ● According to Work Materials

### Ballnose Type

#### General Steel (Common Use)

Coated | General

GSX MILL BALL
**GSXB Type**
R 0,2–12,5 mm
•2 Flutes




➪ J34

#### General Steel (Short Series)

Coated | Short | General

NEOBALL SHORT FLUTE
**S-SNB-ZX Type**
R 1,5–15 mm
•2 Flutes



➪ Stock in Japan

Coated | Short | General

ZX-COATED SHORT FLUTE
**S-SSB-ZX Type**
R 1,5–4 mm
•2 Flutes



➪ Stock in Japan

#### Hardened Steel

High Rigidity Type

Coated | Strong | High Efficiency

HARDBALL
**SHB-ZX Type**
R 0,5–10 mm
•2 Flutes




➪ Stock in Japan

Hardened Steel

CBN | MOULD FINISH MASTER | PCD


SUMIBORON brazed
**BNBP Type**
R 0,2–1,0 mm
•2 Flutes



➪ J41, M75

SUMIDIA binderless
**NPDRS Type**
R 0,2–2,0 mm
•1 Flute
Radius Endmill

**NPDB(S) Type**
R 0,1–1,0 mm
•1 Flute
Ballnose Endmill



NPDRS NPDB(S)


➪ J42–43, M76–76

#### Non-ferrous Metal

DLC-Coated Endmill

Coated | General

AURORA COATED
**SNB-DL Type**
R 1–8 mm
•2 Flutes



➪ J35


# GSX MILL Series




## Characteristics and Applications

- Wide variation of three flute types and four flute lengths enable use in a wide variety of applications.
- Fine carbide substrate provides high transverse rupture strength and excellent thermal shock resistance improving reliability in wet cutting applications.
- GSX Coating provides improved reliability and longer tool life.
- Large rake angle and unique flute design improve sharpness and chip evacuation.
- Cutting teeth with gash land improves corner flute strength.
- Sharper edge S type and fracture resistant C type added to the 2D size series.


### ● Wear Resistance




### ● Thermal Resistance




### ● Improved Chip Evacuation





Large rake angle combined with our unique flute design improves sharpness and chip evacuation.


## 2 cutting edge designs expand machining applications

Sharper edge S type and fracture resistant C type added to the 2D size series.


**S Type** Sharp Corner: Sharper Edge Design



**C Type** Gash Land: Fracture Resistant Design



Note: In gash land drilling, some material remains as shown on the right. If you need sharp corners, use the S Type.




Ex.: Corner on a ø 10 mm hole

## Application Range

| P | | | | | H | | | M | S | | K | N | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| General Structure Rolled Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45 ~ 55 HRC | Hardened Steel 55 ~ 60 HRC | Hardened Steel 60 ~ 65 HRC | Stainless Steel | Ti Alloy | Heat Resistant Alloy | Cast Iron | Al Alloy | Cu Alloy | Graphite |
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ *1 | | | ◎ | ○ | ○ | ○ | | | |

◎ : Best
○ : Good

Blank : Not recommended
*1: GSXSLT30000C is recommended for 50 HRC or less

## Recommended Milling Examples

| Application | Surface Milling | | Grooving | | Groove Finishing | |
|---|---|---|---|---|---|---|
| Form |  | |  | |  | |
| | Rough | Finishing | Rough | Finishing | Rough | Finishing |
| **S Type** | | ◎ | | ○ | | ◎ |
| **C Type** | ◎ | ○ | ◎ | ◎ | ◎ | ○ |

S Type is best for removing inside corners.

*2: Use with small depth of cut.

# GSX MILL Series





Large rake angle and unique flute design improve sharpness and excellent chip evacuation.


## Product Range

| Application | No. of Teeth | Flute Length | | | | |
|---|---|---|---|---|---|---|
| | | 1,5 D | 2 D | | 3 D | 4 D |
| | | C Type | S Type | C Type | C Type | C Type |
| General Purpose | 2 Flutes | GSX20000C-1.5D ⇨ J 7 | GSX20000S-2D ⇨ J 8 | GSX20000C-2D ⇨ J 9 | GSX20000C-3D ⇨ J 10 | GSX20000C-4D ⇨ J 11 |
| | 3 Flutes | GSX30000C-1.5D ⇨ J 12 | | GSX30000C-2D ⇨ J 13 | | |
| | 4 Flutes | GSX40000C-1.5D ⇨ J 15 | GSX40000S-2D ⇨ J 16 | GSX40000C-2D ⇨ J 17 | GSX40000C-3D ⇨ J 18 | GSX40000C-4D ⇨ J 19 |
| Compound Endmilling | 3 Flutes | GSXSLT30000C-1.5D ⇨ J 14 | | | | |

## Multi-Purpose "GSX-SLT" Slot Type

- Optimized flute design of slotted 3 flute (1.5D) short type reduces cutting resistance.

① Allows drilling and slot milling and other continuous (compound) applications.
② Perfect for use with thin sheets and small machining centres







## Application Examples

### ● Carbon Steel Grooving with GSX20000C

**GSX** 20000**C** | Competitor





Gash land for stronger cutting edge.

| | |
|---|---|
| Tool dimension | ø 6 (2 Flutes) |
| Work material | C50 |
| Cutting speed | $v_c$ = 87 m/min |
| | n = 4615 rpm |
| Feed rate | $f_z$ = 0,06 mm/teeth |
| | $v_f$ = 553 mm/min |
| Depth of cut | $a_p$ = 3 mm |
| Wide of cut | $a_e$ = 6 mm |
| Cooland | Dry |
| Vertical machining centre (BT50) | |

### ● Cast Iron Grooving with GSX20000C

**GSX** 20000**C** | Competitor




GSX coating for improved wear resistance.

| | |
|---|---|
| Tool dimension | ø 10 (2 Flutes) |
| Work material | GGG60 |
| Cutting speed | $v_c$ = 66 m/min |
| | n = 2100 rpm |
| Feed rate | $f_z$ = 0,072 mm/teeth |
| | $v_f$ = 302 mm/min |
| Depth of cut | $a_p$ = 5 mm, 5 passes |
| Wide of cut | $a_e$ = 10 mm |
| Cooland | Dry |
| Vertical machining centre (BT40) | |

### ● Stainless Steel Machining with GSX20000C

**GSX** 20000**C** | Competitor





Improved reliability even under wet machining.

| | |
|---|---|
| Tool dimension | ø 10 (2 Flutes) |
| Work material | X5 CrNi 1812 |
| Cutting speed | $v_c$ = 50 m/min |
| | n = 1591 rpm |
| Feed rate | $f_z$ = 0,04 mm/teeth |
| | $v_f$ = 27 mm/min |
| Depth of cut | $a_p$ = 10 mm |
| Wide of cut | $a_e$ = 0,5 mm |
| Cooland | Wet |
| Vertical machining centre (BT50) | |

### ● Surface Milling C50 with GSX20000S

**GSX** 20000**S** | Competitor




S type delivers optimum cutting performance.

| | |
|---|---|
| Tool dimension | ø 6 (2 Flutes) |
| Work material | C50 |
| Cutting speed | $v_c$ = 87 m/min |
| | n = 4615 rpm |
| Feed rate | $f_z$ = 0,06 mm/teeth |
| | $v_f$ = 553 mm/min |
| Depth of cut | $a_p$ = 10 mm |
| Wide of cut | $a_e$ = 0,3 mm |
| Cooland | Dry |
| Vertical machining centre (BT50) | |

# GSX MILL Series



☞ J 20, J 21

## GSX MILL Anti-vibration Type (Square/Radius)

### ■ Characteristics and Applications

- Optimized irregular pitch and lead affords:
  - Drastically improved chattering and fracture resistance !
  - Less cutting force  Allows high-speed, high-feed cutting.
- Rounded lands greatly improve machined surface quality (from ø 4 and up).
- New fine-grained carbide substrate and special coating for better rigidity and thermal and wear resistance.

### ■ Product Range


GSX MILL Anti-vibration Square Type

| Series | No. of Teeth | Serie | DC (mm) |
|---|---|---|---|
| **GSXVL4000-2.5D** | 4 Flutes |  ⇨ J 20 | ø 2 – ø 20 |


GSX MILL Anti-vibration Corner Radius Type

| Series | No. of Teeth | Serie | DC (mm) |
|---|---|---|---|
| **GSXVL4000-R-2.5D** | 4 Flutes |  ⇨ J 21 | ø 3 – ø 20 |

### ■ Cutting Range




### ■ Cutting Resistance




### ■ Application Range

● Surface Finish Quality

GSX Anti-vibration | Competitor's Anti-vibration | Conventional Design



No Chattering Clean Surface | Minute Chattering Poor Surface | Heavy Chattering Poor Surface

| | | | |
|---|---|---|---|
| Work material: | C50 | Cutting Conditions: | n = 4.800 rpm<br>$v_f$ = 800 mm/min |
| Grooving: | | Depth of cut | $a_p$ = 10 mm |
| Tool dimension: | ø 10 | Equipment: | BT50 |



+ J 34

## GSX MILL Ball

### ■ Characteristics and Applications


- New coating combined with a fine-grained carbide substrate affords better thermal and wear resistance.
- Large helix angle on cutting edge reduces cutting resistance.
- Unique pocket design and expanded pocket area promotes better chip evacuation.

⊠ Expands the range of machineable material from soft to hardened steels, and offers reliability and longer tool life.

### ■ Product Range


| Series | No. of Teeth | Serie | DC (mm) |
|---|---|---|---|
| **GSX-B 20000** | 2 Flutes |  ⇨ J 36 | R=ø0,2 – ø15 (DC=0,2 – 30) |

### ■ Application Range





### ■ Application Examples

● Flank Wear





**GSX Ball (Cutting Length 140 m)**



Able to continue



Conventional Tool (Cutting Length 80 m)



Unable to continue



| | |
|---|---|
| Work Material : | X40CrVMo5-1 (50HRC) |
| Tool Dimensions : | R3 (2 Flutes) |
| Cutting Conditions : | $v_c$= 179 m/min (n = 9.500 rpm) |
| | $v_f$= 2.250 mm/min ($f_z$ = 0,12 mm/t) |

$a_p$ = 0,2 ~ 1,0 mm,  $a_e$ = 0,3 mm,  wet
Equipment Vertical Machining Centre  BT40

Chipping in centre
Heavy wear on flank face






● = Euro stock
❍ = Japan stock

# GSX MILL Endmills
# GSX 20000C-1.5D Type

Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 20100C-1.5D | ● | 1,0 | 1,5 | 2,5 | 40 | 4 |
| GSX 20150C-1.5D | ❍ | 1,5 | 2,3 | 3,3 | 40 | 4 |
| GSX 20200C-1.5D | ● | 2,0 | 3,0 | 4,0 | 40 | 4 |
| GSX 20250C-1.5D | ● | 2,5 | 3,8 | 4,8 | 40 | 4 |
| GSX 20300C-1.5D | ● | 3,0 | 4,5 | 6,0 | 45 | 6 |
| GSX 20350C-1.5D | ● | 3,5 | 5,3 | 6,8 | 45 | 6 |
| GSX 20400C-1.5D | ● | 4,0 | 6,0 | 7,5 | 45 | 6 |
| GSX 20450C-1.5D | ● | 4,5 | 6,8 | 8,3 | 50 | 6 |
| GSX 20500C-1.5D | ● | 5,0 | 7,5 | 9,5 | 50 | 6 |
| GSX 20550C-1.5D | | 5,5 | 8,3 | 10,3 | 50 | 6 |
| GSX 20600C-1.5D | ● | 6,0 | 9,0 | – | 50 | 6 |
| GSX 20700C-1.5D | | 7,0 | 11,0 | 13,0 | 60 | 8 |
| GSX 20800C-1.5D | ● | 8,0 | 12,0 | – | 60 | 8 |
| GSX 20900C-1.5D | ● | 9,0 | 14,0 | 16,0 | 70 | 10 |
| GSX 21000C-1.5D | ● | 10,0 | 15,0 | – | 70 | 10 |
| GSX 21200C-1.5D | ● | 12,0 | 18,0 | – | 75 | 12 |
| GSX 21400C-1.5D | | 14,0 | 21,0 | 24,5 | 90 | 16 |
| GSX 21500C-1.5D | | 15,0 | 23,0 | 26,5 | 90 | 16 |
| GSX 21600C-1.5D | | 16,0 | 24,0 | – | 90 | 16 |
| GSX 22000C-1.5D | | 20,0 | 30,0 | – | 100 | 20 |

## Endmill Identification (GSX MILL Series)


**GSX 2 0100 C - 1.5D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|

S: Sharp Edge
C: Gash Land Drilling

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### Shoulder Milling

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 19.600 | 250 | 19.600 | 250 | 19.600 | 250 | 18.300 | 180 | 12.700 | 100 | 9.000 | 60 | 11.000 | 70 | 9.000 | 50 |
| 2,0 | 11.200 | 340 | 11.200 | 340 | 11.200 | 340 | 10.500 | 240 | 7.300 | 130 | 5.300 | 80 | 6.400 | 90 | 5.300 | 70 |
| 4,0 | 6.400 | 460 | 6.400 | 460 | 6.400 | 460 | 6.000 | 320 | 4.200 | 180 | 3.000 | 110 | 3.600 | 120 | 3.000 | 90 |
| 6,0 | 4.600 | 560 | 4.600 | 560 | 4.600 | 560 | 4.300 | 400 | 3.000 | 210 | 2.200 | 130 | 2.700 | 140 | 2.200 | 100 |
| 8,0 | 3.400 | 560 | 3.400 | 560 | 3.400 | 560 | 3.200 | 400 | 2.200 | 210 | 1.600 | 130 | 2.000 | 140 | 1.600 | 100 |
| 10,0 | 2.800 | 560 | 2.800 | 560 | 2.800 | 560 | 2.600 | 400 | 1.800 | 210 | 1.300 | 130 | 1.600 | 140 | 1.300 | 100 |
| 12,0 | 2.300 | 560 | 2.300 | 560 | 2.300 | 560 | 2.200 | 400 | 1.500 | 210 | 1.100 | 130 | 1.300 | 140 | 1.100 | 100 |
| 16,0 | 1.700 | 450 | 1.700 | 450 | 1.700 | 450 | 1.600 | 320 | 1.100 | 180 | 800 | 100 | 1.000 | 110 | 800 | 85 |
| 20,0 | 1.350 | 380 | 1.350 | 380 | 1.350 | 380 | 1.300 | 280 | 900 | 160 | 650 | 90 | 800 | 100 | 650 | 75 |
| Shoulder cutting ap | 1,5 DC | | | | | | | | | | 1,0 DC | | | | | |
| Shoulder cutting ae | 0,05 DC | | | | | | | | | | 0,02 DC | | | | | |

### Grooving


| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 19.600 | 200 | 19.600 | 250 | 19.600 | 250 | 18.300 | 180 | 12.700 | 100 | 9.000 | 60 | 11.000 | 50 | 4.500 | 20 |
| 2,0 | 11.200 | 270 | 11.200 | 340 | 11.200 | 340 | 10.500 | 240 | 7.300 | 130 | 5.300 | 80 | 6.400 | 65 | 2.650 | 25 |
| 4,0 | 6.400 | 370 | 6.400 | 460 | 6.400 | 460 | 6.000 | 320 | 4.200 | 180 | 3.000 | 110 | 3.600 | 80 | 1.500 | 35 |
| 6,0 | 4.600 | 450 | 4.600 | 560 | 4.600 | 560 | 4.300 | 400 | 3.000 | 210 | 2.200 | 130 | 2.700 | 100 | 1.100 | 40 |
| 8,0 | 3.400 | 450 | 3.400 | 560 | 3.400 | 560 | 3.200 | 400 | 2.200 | 210 | 1.600 | 130 | 2.000 | 100 | 800 | 40 |
| 10,0 | 2.800 | 450 | 2.800 | 560 | 2.800 | 560 | 2.600 | 400 | 1.800 | 210 | 1.300 | 130 | 1.600 | 100 | 650 | 40 |
| 12,0 | 2.300 | 450 | 2.300 | 560 | 2.300 | 560 | 2.200 | 400 | 1.500 | 210 | 1.100 | 130 | 1.300 | 100 | 500 | 40 |
| 16,0 | 1.700 | 360 | 1.700 | 450 | 1.700 | 450 | 1.600 | 320 | 1.100 | 180 | 800 | 100 | 1.000 | 80 | 400 | 35 |
| 20,0 | 1.350 | 300 | 1.350 | 380 | 1.350 | 380 | 1.300 | 280 | 900 | 160 | 650 | 90 | 800 | 70 | 320 | 30 |
| Grooving ap | 0,2 DC | | 0,5 DC | | | | | | 0,2 DC | | 0,05 DC | | 0,2 DC | | | |

# GSX 20000S-2D Type



Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 20030S-2D | ❍ | 0,3 | 0,6 | 1,0 | 40 | 4 |
| GSX 20040S-2D | ❍ | 0,4 | 0,8 | 1,2 | 40 | 4 |
| GSX 20050S-2D | ❍ | 0,5 | 1,3 | 1,7 | 40 | 4 |
| GSX 20080S-2D | ❍ | 0,8 | 1,6 | 2,1 | 40 | 4 |
| GSX 20100S-2D | ● | 1,0 | 2,5 | 3,5 | 40 | 4 |
| GSX 20150S-2D | ● | 1,5 | 3,8 | 4,8 | 40 | 4 |
| GSX 20200S-2D | ● | 2,0 | 5,0 | 6,0 | 40 | 4 |
| GSX 20250S-2D | ● | 2,5 | 6,3 | 7,3 | 40 | 4 |
| GSX 20300S-2D | ● | 3,0 | 7,5 | 9,0 | 45 | 6 |
| GSX 20350S-2D | ● | 3,5 | 8,8 | 10,3 | 45 | 6 |
| GSX 20400S-2D | ● | 4,0 | 11,0 | 14,0 | 45 | 6 |
| GSX 20450S-2D | ● | 4,5 | 11,3 | 12,8 | 50 | 6 |
| GSX 20500S-2D | ● | 5,0 | 13,0 | 19,6 | 50 | 6 |
| GSX 20550S-2D | | 5,5 | 13,0 | 19,6 | 50 | 6 |
| GSX 20600S-2D | ● | 6,0 | 13,0 | – | 50 | 6 |
| GSX 20700S-2D | ● | 7,0 | 16,0 | 21,1 | 60 | 8 |
| GSX 20800S-2D | ● | 8,0 | 19,0 | – | 60 | 8 |
| GSX 20900S-2D | ● | 9,0 | 19,0 | 24,1 | 70 | 10 |
| GSX 21000S-2D | ● | 10,0 | 22,0 | – | 70 | 10 |
| GSX 21200S-2D | ● | 12,0 | 26,0 | – | 75 | 12 |
| GSX 21600S-2D | ❍ | 16,0 | 32,0 | – | 90 | 16 |
| GSX 22000S-2D | ❍ | 20,0 | 40,0 | – | 100 | 20 |

## Endmill Identification (GSX MILL Series)


**GSX 2 0050 S - 2D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|

S: Sharp Edge
C: Gash Land Drilling

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
5. This series is not recommended for grooving.
6. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 16.600 | 180 | 16.600 | 180 | 16.600 | 180 | 15.500 | 130 | 10.500 | 70 | 7.500 | 45 | 9.400 | 50 | 7.500 | 35 |
| 2,0 | 9.500 | 250 | 9.500 | 250 | 9.500 | 250 | 9.000 | 200 | 6.200 | 100 | 4.500 | 60 | 5.400 | 70 | 4.500 | 50 |
| 4,0 | 5.400 | 330 | 5.400 | 330 | 5.400 | 330 | 5.000 | 250 | 3.400 | 120 | 2.500 | 75 | 3.000 | 90 | 2.500 | 65 |
| 6,0 | 4.000 | 400 | 4.000 | 400 | 4.000 | 400 | 3.700 | 300 | 2.550 | 150 | 1.900 | 100 | 2.300 | 110 | 1.900 | 80 |
| 8,0 | 3.000 | 400 | 3.000 | 400 | 3.000 | 400 | 2.800 | 300 | 1.900 | 150 | 1.400 | 100 | 1.700 | 110 | 1.400 | 80 |
| 10,0 | 2.400 | 400 | 2.400 | 400 | 2.400 | 400 | 2.200 | 300 | 1.500 | 150 | 1.100 | 100 | 1.300 | 110 | 1.100 | 80 |
| 12,0 | 2.000 | 400 | 2.000 | 400 | 2.000 | 400 | 1.850 | 300 | 1.300 | 150 | 950 | 100 | 1.100 | 110 | 950 | 80 |
| 16,0 | 1.500 | 330 | 1.500 | 330 | 1.500 | 330 | 1.400 | 250 | 950 | 120 | 700 | 75 | 850 | 85 | 700 | 60 |
| 20,0 | 1.200 | 280 | 1.200 | 280 | 1.200 | 280 | 1.100 | 220 | 750 | 110 | 550 | 65 | 650 | 75 | 550 | 55 |
| Shoulder cutting ap | 1,5 DC | | | | | | | | | | 1,0 DC | | | | | |
| Shoulder cutting ae | 0,05 DC | | | | | | | | | | 0,02 DC | | | | | |

### ● Groove Finishing

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 16.600 | 180 | 16.600 | 180 | 16.600 | 180 | 15.500 | 130 | 10.500 | 70 | 7.500 | 45 | 9.400 | 50 | 7.500 | 35 |
| 2,0 | 9.500 | 250 | 9.500 | 250 | 9.500 | 250 | 9.000 | 200 | 6.200 | 100 | 4.500 | 60 | 5.400 | 70 | 4.500 | 50 |
| 4,0 | 5.400 | 330 | 5.400 | 330 | 5.400 | 330 | 5.000 | 250 | 3.400 | 120 | 2.500 | 75 | 3.000 | 90 | 2.500 | 65 |
| 6,0 | 4.000 | 400 | 4.000 | 400 | 4.000 | 400 | 3.700 | 300 | 2.550 | 150 | 1.900 | 100 | 2.300 | 110 | 1.900 | 80 |
| 8,0 | 3.000 | 400 | 3.000 | 400 | 3.000 | 400 | 2.800 | 300 | 1.900 | 150 | 1.400 | 100 | 1.700 | 110 | 1.400 | 80 |
| 10,0 | 2.400 | 400 | 2.400 | 400 | 2.400 | 400 | 2.200 | 300 | 1.500 | 150 | 1.100 | 100 | 1.300 | 110 | 1.100 | 80 |
| 12,0 | 2.000 | 400 | 2.000 | 400 | 2.000 | 400 | 1.850 | 300 | 1.300 | 150 | 950 | 100 | 1.100 | 110 | 950 | 80 |
| 16,0 | 1.500 | 330 | 1.500 | 330 | 1.500 | 330 | 1.400 | 250 | 950 | 120 | 700 | 75 | 850 | 85 | 700 | 60 |
| 20,0 | 1.200 | 280 | 1.200 | 280 | 1.200 | 280 | 1.100 | 220 | 750 | 110 | 550 | 65 | 650 | 75 | 550 | 55 |
| Groove finishing ap | 1,5 DC | | | | | | | | | | | | | | | |
| Groove finishing ae | –0,02 DC | | | | | | | | | | | | | | | |






● = Euro stock
❍ = Japan stock

# GSX MILL Endmills
# GSX 20000C-2D Type

Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 20050C-2D | ❍ | 0,5 | 1,0 | 1,4 | 40 | 4 |
| GSX 20100C-2D | ● | 1,0 | 2,0 | 3,0 | 40 | 4 |
| GSX 20150C-2D | ❍ | 1,5 | 3,0 | 4,0 | 40 | 4 |
| GSX 20200C-2D | ● | 2,0 | 4,0 | 5,0 | 40 | 4 |
| GSX 20250C-2D | ● | 2,5 | 5,0 | 6,0 | 40 | 4 |
| GSX 20300C-2D | ● | 3,0 | 6,0 | 7,5 | 45 | 6 |
| GSX 20350C-2D | | 3,5 | 7,0 | 8,5 | 45 | 6 |
| GSX 20400C-2D | ● | 4,0 | 8,0 | 9,5 | 45 | 6 |
| GSX 20450C-2D | ● | 4,5 | 9,0 | 10,5 | 50 | 6 |
| GSX 20500C-2D | ● | 5,0 | 10,0 | 12,0 | 50 | 6 |
| GSX 20550C-2D | | 5,5 | 11,0 | 13,0 | 50 | 6 |
| GSX 20600C-2D | ● | 6,0 | 12,0 | — | 50 | 6 |
| GSX 20700C-2D | ● | 7,0 | 14,0 | 16,0 | 60 | 8 |
| GSX 20800C-2D | ● | 8,0 | 16,0 | — | 60 | 8 |
| GSX 20900C-2D | ❍ | 9,0 | 18,0 | 20,0 | 70 | 10 |
| GSX 21000C-2D | ● | 10,0 | 20,0 | — | 70 | 10 |
| GSX 21200C-2D | ● | 12,0 | 24,0 | — | 75 | 12 |
| GSX 21400C-2D | | 14,0 | 28,0 | 31,5 | 90 | 16 |
| GSX 21500C-2D | | 15,0 | 30,0 | 33,5 | 90 | 16 |
| GSX 21600C-2D | ● | 16,0 | 32,0 | — | 90 | 16 |
| GSX 22000C-2D | ● | 20,0 | 40,0 | — | 100 | 20 |

## Endmill Identification (GSX MILL Series)


**GSX 2 0050 C - 2D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|

S: Sharp Edge
C: Gash Land Drilling

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
5. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### ● Shoulder Milling

| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 19.600 | 250 | 19.600 | 250 | 19.600 | 250 | 18.300 | 180 | 12.700 | 100 | 9.000 | 60 | 11.000 | 70 | 9.000 | 50 |
| 2,0 | | 11.200 | 340 | 11.200 | 340 | 11.200 | 340 | 10.500 | 240 | 7.300 | 130 | 5.300 | 80 | 6.400 | 90 | 5.300 | 70 |
| 4,0 | | 6.400 | 460 | 6.400 | 460 | 6.400 | 460 | 6.000 | 320 | 4.200 | 180 | 3.000 | 110 | 3.600 | 120 | 3.000 | 90 |
| 6,0 | | 4.600 | 560 | 4.600 | 560 | 4.600 | 560 | 4.300 | 400 | 3.000 | 210 | 2.200 | 130 | 2.700 | 140 | 2.200 | 100 |
| 8,0 | | 3.400 | 560 | 3.400 | 560 | 3.400 | 560 | 3.200 | 400 | 2.200 | 210 | 1.600 | 130 | 2.000 | 140 | 1.600 | 100 |
| 10,0 | | 2.800 | 560 | 2.800 | 560 | 2.800 | 560 | 2.600 | 400 | 1.800 | 210 | 1.300 | 130 | 1.600 | 140 | 1.300 | 100 |
| 12,0 | | 2.300 | 560 | 2.300 | 560 | 2.300 | 560 | 2.200 | 400 | 1.500 | 210 | 1.100 | 130 | 1.300 | 140 | 1.100 | 100 |
| 16,0 | | 1.700 | 450 | 1.700 | 450 | 1.700 | 450 | 1.600 | 320 | 1.100 | 180 | 800 | 100 | 1.000 | 110 | 800 | 85 |
| 20,0 | | 1.350 | 380 | 1.350 | 380 | 1.350 | 380 | 1.300 | 280 | 900 | 160 | 650 | 90 | 800 | 100 | 650 | 75 |
| Shoulder cutting | $a_p$ | 1,5 DC | | | | | | | | | | 1,0 DC | | | | | |
| | $a_e$ | 0,05 DC | | | | | | | | | | 0,02 DC | | | | | |

### ● Grooving


| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 19.600 | 200 | 19.600 | 250 | 19.600 | 250 | 18.300 | 180 | 12.700 | 100 | 9.000 | 60 | 11.000 | 50 | 4.500 | 20 |
| 2,0 | | 11.200 | 270 | 11.200 | 340 | 11.200 | 340 | 10.500 | 240 | 7.300 | 130 | 5.300 | 80 | 6.400 | 65 | 2.650 | 25 |
| 4,0 | | 6.400 | 370 | 6.400 | 460 | 6.400 | 460 | 6.000 | 320 | 4.200 | 180 | 3.000 | 110 | 3.600 | 80 | 1.500 | 35 |
| 6,0 | | 4.600 | 450 | 4.600 | 560 | 4.600 | 560 | 4.300 | 400 | 3.000 | 210 | 2.200 | 130 | 2.700 | 100 | 1.100 | 40 |
| 8,0 | | 3.400 | 450 | 3.400 | 560 | 3.400 | 560 | 3.200 | 400 | 2.200 | 210 | 1.600 | 130 | 2.000 | 100 | 800 | 40 |
| 10,0 | | 2.800 | 450 | 2.800 | 560 | 2.800 | 560 | 2.600 | 400 | 1.800 | 210 | 1.300 | 130 | 1.600 | 100 | 650 | 40 |
| 12,0 | | 2.300 | 450 | 2.300 | 560 | 2.300 | 560 | 2.200 | 400 | 1.500 | 210 | 1.100 | 130 | 1.300 | 100 | 500 | 40 |
| 16,0 | | 1.700 | 360 | 1.700 | 450 | 1.700 | 450 | 1.600 | 320 | 1.100 | 180 | 800 | 100 | 1.000 | 80 | 400 | 35 |
| 20,0 | | 1.350 | 300 | 1.350 | 380 | 1.350 | 380 | 1.300 | 280 | 900 | 160 | 650 | 90 | 800 | 70 | 320 | 30 |
| Grooving | $a_p$ | 0,2 DC | | 0,5 DC | | | | | | 0,2 DC | | 0,05 DC | | 0,2 DC | | | |

# GSX 20000C-3D Type



Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## ■ Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 20100C-3D | ● | 1,0 | 3,0 | 4,0 | 40 | 4 |
| GSX 20150C-3D | ● | 1,5 | 4,5 | 5,5 | 40 | 4 |
| GSX 20200C-3D | ● | 2,0 | 6,0 | 7,0 | 40 | 4 |
| GSX 20250C-3D | ● | 2,5 | 7,5 | 8,5 | 40 | 4 |
| GSX 20300C-3D | ● | 3,0 | 9,0 | 10,5 | 50 | 6 |
| GSX 20400C-3D | ● | 4,0 | 12,0 | 13,5 | 50 | 6 |
| GSX 20500C-3D | ● | 5,0 | 15,0 | 17,0 | 50 | 6 |
| GSX 20600C-3D | ● | 6,0 | 18,0 | — | 50 | 6 |
| GSX 20800C-3D | ● | 8,0 | 24,0 | — | 70 | 8 |
| GSX 21000C-3D | ● | 10,0 | 30,0 | — | 90 | 10 |
| GSX 21200C-3D | ● | 12,0 | 36,0 | — | 90 | 12 |
| GSX 21600C-3D | ● | 16,0 | 48,0 | — | 110 | 16 |
| GSX 22000C-3D | ❍ | 20,0 | 60,0 | — | 120 | 20 |

## ■ Endmill Identification (GSX MILL Series)


**GSX 2 0100 C - 3D**

| GSX | 2 | 0100 | C | - | 3D |
|---|---|---|---|---|---|
| Series Code | No. of Teeth | Diameter | Cutting Edge | | Cutting Edge Length |

S: Sharp Edge
C: Gash Land Drilling

## ■ Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. In rare cases, chattering may occur in early milling stages, dissipating after 2m of cutting.
5. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
6. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 16.600 | 190 | 16.600 | 190 | 16.600 | 190 | 15.500 | 140 | 10.500 | 70 | 7.500 | 45 | 9.400 | 50 | 7.500 | 35 |
| 2,0 | 9.500 | 250 | 9.500 | 250 | 9.500 | 250 | 9.000 | 200 | 6.200 | 120 | 4.500 | 60 | 5.200 | 70 | 4.500 | 50 |
| 4,0 | 5.200 | 330 | 5.200 | 330 | 5.200 | 330 | 4.800 | 200 | 3.400 | 150 | 2.250 | 75 | 2.600 | 90 | 2.250 | 65 |
| 6,0 | 3.500 | 360 | 3.500 | 360 | 3.500 | 360 | 3.200 | 250 | 2.550 | 170 | 1.500 | 90 | 1.700 | 100 | 1.500 | 80 |
| 8,0 | 2.600 | 320 | 2.600 | 320 | 2.600 | 320 | 2.400 | 240 | 1.900 | 170 | 1.100 | 90 | 1.300 | 105 | 1.100 | 80 |
| 10,0 | 2.100 | 300 | 2.100 | 300 | 2.100 | 300 | 1.900 | 230 | 1.500 | 170 | 900 | 90 | 1.000 | 100 | 900 | 80 |
| 12,0 | 1.750 | 280 | 1.750 | 280 | 1.750 | 280 | 1.600 | 230 | 1.250 | 170 | 750 | 90 | 850 | 100 | 750 | 80 |
| 16,0 | 1.300 | 240 | 1.300 | 240 | 1.300 | 240 | 1.200 | 200 | 950 | 150 | 550 | 75 | 650 | 85 | 550 | 65 |
| 20,0 | 1.050 | 220 | 1.050 | 220 | 1.050 | 220 | 950 | 180 | 750 | 140 | 450 | 70 | 500 | 75 | 450 | 60 |
| Shoulder cutting ap | 2,5 DC | | | | | | | | 2,0 DC | | | | | | | |
| Shoulder cutting ae | < ø3: 0,05 DC , ≤ ø3: 0,1 DC | | | | | | | | 0,02 DC | | | | | | | |

### ● Grooving

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 16.600 | 70 | 16.600 | 80 | 16.600 | 80 | 15.500 | 50 | 10.500 | 50 | 7.500 | 35 | 9.400 | 30 | 3.750 | 10 |
| 2,0 | 9.500 | 80 | 9.500 | 100 | 9.500 | 100 | 9.000 | 90 | 6.200 | 60 | 4.500 | 45 | 5.200 | 40 | 2.250 | 15 |
| 4,0 | 5.200 | 120 | 5.200 | 150 | 5.200 | 150 | 4.800 | 120 | 3.400 | 80 | 2.200 | 50 | 2.600 | 50 | 1.250 | 20 |
| 6,0 | 3.500 | 140 | 3.500 | 170 | 3.500 | 170 | 3.200 | 130 | 2.550 | 100 | 1.500 | 50 | 1.700 | 60 | 950 | 25 |
| 8,0 | 2.600 | 140 | 2.600 | 160 | 2.600 | 160 | 2.400 | 130 | 1.900 | 100 | 1.100 | 50 | 1.300 | 60 | 700 | 25 |
| 10,0 | 2.100 | 130 | 2.100 | 150 | 2.100 | 150 | 1.900 | 120 | 1.500 | 90 | 900 | 50 | 1.000 | 60 | 550 | 25 |
| 12,0 | 1.750 | 130 | 1.750 | 150 | 1.750 | 150 | 1.600 | 120 | 1.250 | 90 | 750 | 50 | 850 | 60 | 450 | 25 |
| 16,0 | 1.300 | 110 | 1.300 | 130 | 1.300 | 130 | 1.200 | 110 | 950 | 80 | 550 | 45 | 650 | 50 | 350 | 20 |
| 20,0 | 1.050 | 100 | 1.050 | 120 | 1.050 | 120 | 950 | 100 | 750 | 70 | 450 | 40 | 500 | 40 | 280 | 15 |
| Grooving ap | 0,1 DC | | 0,2 DC | | | | | | | | 0,05 DC | | 0,1 *D* | | | |
| Grooving ae | | | | | | | | | | | | | | | | |






● = Euro stock
❍ = Japan stock

# GSX MILL Endmills
# GSX 20000C-4D Type

Coated Carbide Grades — GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 20100C-4D | ● | 1,0 | 4,0 | 5,0 | 40 | 4 |
| GSX 20150C-4D | ● | 1,5 | 6,0 | 7,0 | 40 | 4 |
| GSX 20200C-4D | ● | 2,0 | 8,0 | 9,0 | 40 | 4 |
| GSX 20250C-4D | ● | 2,5 | 10,0 | 11,0 | 50 | 4 |
| GSX 20300C-4D | ● | 3,0 | 12,0 | 13,5 | 50 | 6 |
| GSX 20400C-4D | ● | 4,0 | 16,0 | 17,5 | 50 | 6 |
| GSX 20500C-4D | ● | 5,0 | 20,0 | 22,0 | 60 | 6 |
| GSX 20600C-4D | ● | 6,0 | 24,0 | – | 60 | 6 |
| GSX 20800C-4D | ● | 8,0 | 32,0 | – | 80 | 8 |
| GSX 21000C-4D | ● | 10,0 | 40,0 | – | 90 | 10 |
| GSX 21200C-4D | ❍ | 12,0 | 48,0 | – | 100 | 12 |
| GSX 21600C-4D | ❍ | 16,0 | 64,0 | – | 120 | 16 |
| GSX 22000C-4D | ❍ | 20,0 | 80,0 | – | 140 | 20 |


## Endmill Identification (GSX MILL Series)

**GSX 2 0100 C - 4D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|
| | | | S: Sharp Edge<br>C: Gash Land Drilling | |

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. In rear cases, chattering may occur in early milling stages, dissipating after 2 m of cutting.
5. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
6. This series is not recommended for grooving.
7. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### Shoulder Milling

| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 9.000 | 130 | 9.000 | 130 | 9.000 | 130 | 7.000 | 95 | 6.500 | 50 | 4.500 | 30 | 5.400 | 40 | 4.500 | 25 |
| 2,0 | | 4.500 | 180 | 4.500 | 180 | 4.500 | 180 | 3.500 | 120 | 3.200 | 70 | 2.300 | 40 | 2.700 | 50 | 2.300 | 35 |
| 4,0 | | 2.250 | 240 | 2.250 | 240 | 2.250 | 240 | 1.750 | 160 | 1.600 | 95 | 1.200 | 60 | 1.350 | 65 | 1.200 | 40 |
| 6,0 | | 1.500 | 300 | 1.500 | 300 | 1.500 | 300 | 1.150 | 170 | 1.050 | 110 | 800 | 70 | 900 | 70 | 800 | 50 |
| 8,0 | | 1.100 | 260 | 1.100 | 260 | 1.100 | 260 | 850 | 170 | 800 | 110 | 600 | 70 | 660 | 70 | 600 | 50 |
| 10,0 | | 900 | 250 | 900 | 250 | 900 | 250 | 700 | 160 | 650 | 110 | 460 | 70 | 540 | 70 | 460 | 50 |
| 12,0 | | 750 | 240 | 750 | 240 | 750 | 240 | 580 | 160 | 520 | 110 | 400 | 70 | 450 | 70 | 400 | 50 |
| 16,0 | | 550 | 200 | 550 | 200 | 550 | 200 | 440 | 140 | 400 | 95 | 300 | 55 | 330 | 60 | 300 | 45 |
| 20,0 | | 450 | 180 | 450 | 180 | 450 | 180 | 350 | 120 | 320 | 85 | 240 | 45 | 270 | 50 | 240 | 40 |
| Shoulder cutting | $a_p$ | 3,5 DC | | | | | | | | | | 3,0 DC | | | | | |
| | $a_e$ | 0,08 DC | | | | | | 0,04 DC | | | | | | | | | |


# GSX 30000C-1.5D Type



Coated Carbide — Grades

GSX — Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 30100C-1.5D | ● | 1,0 | 1,5 | 2,5 | 40 | 4 |
| GSX 30150C-1.5D | ● | 1,5 | 2,3 | 3,3 | 40 | 4 |
| GSX 30200C-1.5D | ● | 2,0 | 3,0 | 4,0 | 40 | 4 |
| GSX 30250C-1.5D | ● | 2,5 | 3,8 | 4,8 | 40 | 4 |
| GSX 30300C-1.5D | ● | 3,0 | 4,5 | 6,0 | 45 | 6 |
| GSX 30400C-1.5D | ● | 4,0 | 6,0 | 7,5 | 45 | 6 |
| GSX 30500C-1.5D | ● | 5,0 | 7,5 | 9,5 | 50 | 6 |
| GSX 30600C-1.5D | ● | 6,0 | 9,0 | – | 50 | 6 |
| GSX 30700C-1.5D | ● | 7,0 | 11,0 | 13,0 | 60 | 8 |
| GSX 30800C-1.5D | ● | 8,0 | 12,0 | – | 60 | 8 |
| GSX 30900C-1.5D | ❍ | 9,0 | 14,0 | 16,0 | 70 | 10 |
| GSX 31000C-1.5D | ● | 10,0 | 15,0 | – | 70 | 10 |
| GSX 31200C-1.5D | ● | 12,0 | 18,0 | – | 75 | 12 |
| GSX 31600C-1.5D | | 16,0 | 24,0 | – | 90 | 16 |
| GSX 32000C-1.5D | | 20,0 | 30,0 | – | 100 | 20 |

## Endmill Identification (GSX MILL Series)


**GSX** **3** **0100** **C** **-** **1.5D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|

S: Sharp Edge
C: Gash Land Drilling

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 19.600 | 300 | 19.600 | 300 | 19.600 | 300 | 18.300 | 210 | 12.700 | 130 | 9.000 | 80 | 11.000 | 90 | 9.000 | 65 |
| 2,0 | 11.200 | 410 | 11.200 | 410 | 11.200 | 410 | 10.500 | 280 | 7.300 | 170 | 5.300 | 100 | 6.400 | 120 | 5.300 | 90 |
| 4,0 | 6.400 | 550 | 6.400 | 550 | 6.400 | 550 | 6.000 | 370 | 4.200 | 230 | 3.000 | 140 | 3.600 | 150 | 3.000 | 120 |
| 6,0 | 4.600 | 670 | 4.600 | 670 | 4.600 | 670 | 4.300 | 460 | 3.000 | 270 | 2.200 | 170 | 2.700 | 180 | 2.200 | 130 |
| 8,0 | 3.400 | 670 | 3.400 | 670 | 3.400 | 670 | 3.200 | 460 | 2.200 | 270 | 1.600 | 170 | 2.000 | 180 | 1.600 | 130 |
| 10,0 | 2.800 | 670 | 2.800 | 670 | 2.800 | 670 | 2.600 | 460 | 1.800 | 270 | 1.300 | 170 | 1.600 | 180 | 1.300 | 130 |
| 12,0 | 2.300 | 670 | 2.300 | 670 | 2.300 | 670 | 2.200 | 460 | 1.500 | 270 | 1.100 | 170 | 1.300 | 180 | 1.100 | 130 |
| 16,0 | 1.700 | 550 | 1.700 | 550 | 1.700 | 550 | 1.600 | 370 | 1.100 | 230 | 800 | 140 | 1.000 | 150 | 800 | 100 |
| 20,0 | 1.350 | 490 | 1.350 | 490 | 1.350 | 490 | 1.300 | 330 | 900 | 210 | 650 | 120 | 800 | 130 | 650 | 90 |
| Shoulder cutting ap | 1,5 DC | | | | | | | | 1,0 DC | | | | | | | |
| Shoulder cutting ae | 0,05 DC | | | | | | | | 0,02 DC | | | | | | | |

### ● Grooving

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 19.600 | 240 | 19.600 | 300 | 19.600 | 300 | 18.300 | 210 | 12.700 | 130 | 9.000 | 80 | 11.000 | 65 | 4.500 | 25 |
| 2,0 | 11.200 | 320 | 11.200 | 410 | 11.200 | 410 | 10.500 | 280 | 7.300 | 170 | 5.300 | 100 | 6.400 | 85 | 2.650 | 35 |
| 4,0 | 6.400 | 450 | 6.400 | 550 | 6.400 | 550 | 6.000 | 370 | 4.200 | 230 | 3.000 | 140 | 3.600 | 100 | 1.500 | 50 |
| 6,0 | 4.600 | 540 | 4.600 | 670 | 4.600 | 670 | 4.300 | 460 | 3.000 | 270 | 2.200 | 170 | 2.650 | 130 | 1.150 | 55 |
| 8,0 | 3.400 | 540 | 3.400 | 670 | 3.400 | 670 | 3.200 | 460 | 2.200 | 270 | 1.600 | 170 | 2.000 | 130 | 800 | 55 |
| 10,0 | 2.800 | 540 | 2.800 | 670 | 2.800 | 670 | 2.600 | 460 | 1.800 | 270 | 1.300 | 170 | 1.600 | 130 | 650 | 55 |
| 12,0 | 2.300 | 540 | 2.300 | 670 | 2.300 | 670 | 2.200 | 460 | 1.500 | 270 | 1.100 | 170 | 1.300 | 130 | 500 | 55 |
| 16,0 | 1.700 | 440 | 1.700 | 550 | 1.700 | 550 | 1.600 | 370 | 1.100 | 230 | 800 | 140 | 1.000 | 110 | 400 | 45 |
| 20,0 | 1.350 | 390 | 1.350 | 490 | 1.350 | 490 | 1.300 | 330 | 900 | 210 | 650 | 120 | 800 | 90 | 320 | 40 |
| Grooving ap | 0,2 DC | | 0,5 DC | | | | | | | | 0,05 DC | | 0,2 DC | | | |
| Grooving ae | | | | | | | | | | | | | | | | |






● = Euro stock
❍ = Japan stock

# GSX MILL Endmills
# GSX 30000C-2D Type

Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 30100C-2D | ❍ | 1,0 | 2,5 | 3,5 | 40 | 4 |
| GSX 30150C-2D | ● | 1,5 | 3,8 | 4,8 | 40 | 4 |
| GSX 30200C-2D | ● | 2,0 | 5,0 | 6,0 | 40 | 4 |
| GSX 30250C-2D | ● | 2,5 | 6,3 | 7,3 | 40 | 4 |
| GSX 30300C-2D | ● | 3,0 | 7,5 | 9,0 | 45 | 6 |
| GSX 30400C-2D | ● | 4,0 | 11,0 | 12,5 | 45 | 6 |
| GSX 30500C-2D | ● | 5,0 | 13,0 | 15,0 | 50 | 6 |
| GSX 30600C-2D | ● | 6,0 | 13,0 | – | 50 | 6 |
| GSX 30700C-2D | ● | 7,0 | 16,0 | 18,0 | 60 | 8 |
| GSX 30800C-2D | ● | 8,0 | 19,0 | – | 60 | 8 |
| GSX 30900C-2D | ● | 9,0 | 19,0 | 21,0 | 70 | 10 |
| GSX 31000C-2D | ● | 10,0 | 22,0 | – | 70 | 10 |
| GSX 31200C-2D | ● | 12,0 | 26,0 | – | 75 | 12 |
| GSX 31600C-2D | | 16,0 | 32,0 | – | 90 | 16 |
| GSX 32000C-2D | | 20,0 | 40,0 | – | 100 | 20 |


## Endmill Identification (GSX MILL Series)

**GSX 3 0100 C - 2D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|
| | | | S: Sharp Edge<br>C: Gash Land Drilling | |

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### Shoulder Milling

| Work Material / Cond. | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 19.600 | 300 | 19.600 | 300 | 19.600 | 300 | 18.300 | 210 | 12.700 | 130 | 9.000 | 80 | 11.000 | 90 | 9.000 | 65 |
| 2,0 | 11.200 | 410 | 11.200 | 410 | 11.200 | 410 | 10.500 | 280 | 7.300 | 170 | 5.300 | 100 | 6.400 | 120 | 5.300 | 90 |
| 4,0 | 6.400 | 550 | 6.400 | 550 | 6.400 | 550 | 6.000 | 370 | 4.200 | 230 | 3.000 | 140 | 3.600 | 150 | 3.000 | 120 |
| 6,0 | 4.600 | 670 | 4.600 | 670 | 4.600 | 670 | 4.300 | 460 | 3.000 | 270 | 2.200 | 170 | 2.700 | 180 | 2.200 | 130 |
| 8,0 | 3.400 | 670 | 3.400 | 670 | 3.400 | 670 | 3.200 | 460 | 2.200 | 270 | 1.600 | 170 | 2.000 | 180 | 1.600 | 130 |
| 10,0 | 2.800 | 670 | 2.800 | 670 | 2.800 | 670 | 2.600 | 460 | 1.800 | 270 | 1.300 | 170 | 1.600 | 180 | 1.300 | 130 |
| 12,0 | 2.300 | 670 | 2.300 | 670 | 2.300 | 670 | 2.200 | 460 | 1.500 | 270 | 1.100 | 170 | 1.300 | 180 | 1.100 | 130 |
| 16,0 | 1.700 | 550 | 1.700 | 550 | 1.700 | 550 | 1.600 | 370 | 1.100 | 230 | 800 | 140 | 1.000 | 150 | 800 | 100 |
| 20,0 | 1.350 | 490 | 1.350 | 490 | 1.350 | 490 | 1.300 | 330 | 900 | 210 | 650 | 120 | 800 | 130 | 650 | 90 |
| Shoulder cutting $a_p$ | 1,5 DC | | | | | | | | | | 1,0 DC | | | | | |
| Shoulder cutting $a_e$ | 0,05 DC | | | | | | | | | | 0,02 DC | | | | | |

### Grooving

| Work Material / Cond. | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 19.600 | 240 | 19.600 | 300 | 19.600 | 300 | 18.300 | 210 | 12.700 | 130 | 9.000 | 80 | 11.000 | 65 | 4.500 | 25 |
| 2,0 | 11.200 | 320 | 11.200 | 410 | 11.200 | 410 | 10.500 | 280 | 7.300 | 170 | 5.300 | 100 | 6.400 | 85 | 2.650 | 35 |
| 4,0 | 6.400 | 450 | 6.400 | 550 | 6.400 | 550 | 6.000 | 370 | 4.200 | 230 | 3.000 | 140 | 3.600 | 100 | 1.500 | 50 |
| 6,0 | 4.600 | 540 | 4.600 | 670 | 4.600 | 670 | 4.300 | 460 | 3.000 | 270 | 2.200 | 170 | 2.650 | 130 | 1.150 | 55 |
| 8,0 | 3.400 | 540 | 3.400 | 670 | 3.400 | 670 | 3.200 | 460 | 2.200 | 270 | 1.600 | 170 | 2.000 | 130 | 800 | 55 |
| 10,0 | 2.800 | 540 | 2.800 | 670 | 2.800 | 670 | 2.600 | 460 | 1.800 | 270 | 1.300 | 170 | 1.600 | 130 | 650 | 55 |
| 12,0 | 2.300 | 540 | 2.300 | 670 | 2.300 | 670 | 2.200 | 460 | 1.500 | 270 | 1.100 | 170 | 1.300 | 130 | 500 | 55 |
| 16,0 | 1.700 | 440 | 1.700 | 550 | 1.700 | 550 | 1.600 | 370 | 1.100 | 230 | 800 | 140 | 1.000 | 110 | 400 | 45 |
| 20,0 | 1.350 | 390 | 1.350 | 490 | 1.350 | 490 | 1.300 | 330 | 900 | 210 | 650 | 120 | 800 | 90 | 320 | 40 |
| Grooving $a_p$ | 0,2 DC | | 0,5 DC | | | | | | 0,2 DC | | 0,05 DC | | 0,2 DC | | | |


# GSXSLT 30000C-1.5D Type



Coated Carbide — Grades

GSX — Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20


## ■ Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSXSLT 30100C-1.5D | ● | 1,0 | 1,5 | 2,5 | 40 | 4 |
| GSXSLT 30150C-1.5D | ● | 1,5 | 2,3 | 3,3 | 40 | 4 |
| GSXSLT 30200C-1.5D | | 2,0 | 3,0 | 4,0 | 40 | 4 |
| GSXSLT 30250C-1.5D | ❍ | 2,5 | 3,8 | 4,8 | 40 | 4 |
| GSXSLT 30300C-1.5D | ● | 3,0 | 4,5 | 6,0 | 45 | 6 |
| GSXSLT 30400C-1.5D | ● | 4,0 | 6,0 | 7,5 | 45 | 6 |
| GSXSLT 30500C-1.5D | ● | 5,0 | 7,5 | 9,5 | 50 | 6 |
| GSXSLT 30600C-1.5D | ● | 6,0 | 9,0 | – | 50 | 6 |
| GSXSLT 30700C-1.5D | ● | 7,0 | 11,0 | 13,0 | 60 | 8 |
| GSXSLT 30800C-1.5D | ● | 8,0 | 12,0 | – | 60 | 8 |
| GSXSLT 30900C-1.5D | ● | 9,0 | 14,0 | 16,0 | 70 | 10 |
| GSXSLT 31000C-1.5D | ● | 10,0 | 15,0 | – | 70 | 10 |
| GSXSLT 31200C-1.5D | ● | 12,0 | 18,0 | – | 75 | 12 |
| GSXSLT 31600C-1.5D | | 16,0 | 24,0 | – | 90 | 16 |

## ■ Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. Use step machining of 0.1Dc when drilling stainless steel, heat resistant alloy, and titanium alloy.
5. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### ● Shoulder Milling

| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 19.600 | 300 | 19.600 | 300 | 19.600 | 300 | 18.300 | 210 | 12.700 | 130 | 9.000 | 80 | 11.000 | 90 | 9.000 | 65 |
| 2,0 | | 11.200 | 410 | 11.200 | 410 | 11.200 | 410 | 10.500 | 280 | 7.300 | 170 | 5.300 | 100 | 6.400 | 120 | 5.300 | 90 |
| 4,0 | | 6.400 | 550 | 6.400 | 550 | 6.400 | 550 | 6.000 | 370 | 4.200 | 230 | 3.000 | 140 | 3.600 | 150 | 3.000 | 120 |
| 6,0 | | 4.600 | 670 | 4.600 | 670 | 4.600 | 670 | 4.300 | 460 | 3.000 | 270 | 2.200 | 170 | 2.700 | 180 | 2.200 | 130 |
| 8,0 | | 3.400 | 670 | 3.400 | 670 | 3.400 | 670 | 3.200 | 460 | 2.200 | 270 | 1.600 | 170 | 2.000 | 180 | 1.600 | 130 |
| 10,0 | | 2.800 | 670 | 2.800 | 670 | 2.800 | 670 | 2.600 | 460 | 1.800 | 270 | 1.300 | 170 | 1.600 | 180 | 1.300 | 130 |
| 12,0 | | 2.300 | 670 | 2.300 | 670 | 2.300 | 670 | 2.200 | 460 | 1.500 | 270 | 1.100 | 170 | 1.300 | 180 | 1.100 | 130 |
| 16,0 | | 1.700 | 550 | 1.700 | 550 | 1.700 | 550 | 1.600 | 370 | 1.100 | 230 | 800 | 140 | 1.000 | 150 | 800 | 100 |
| Shoulder cutting | $a_p$ | 1.5 DC | | | | | | | | | | 1.0 DC | | | | | |
| | $a_e$ | 0.05 DC | | | | | | | | | | 0.02 DC | | | | | |

### ● Grooving

| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 19.600 | 240 | 19.600 | 300 | 19.600 | 300 | 18.300 | 210 | 12.700 | 130 | 9.000 | 80 | 11.000 | 65 | 4.500 | 25 |
| 2,0 | | 11.200 | 320 | 11.200 | 410 | 11.200 | 410 | 10.500 | 280 | 7.300 | 170 | 5.300 | 100 | 6.400 | 85 | 2.650 | 35 |
| 4,0 | | 6.400 | 450 | 6.400 | 550 | 6.400 | 550 | 6.000 | 370 | 4.200 | 230 | 3.000 | 140 | 3.600 | 100 | 1.500 | 50 |
| 6,0 | | 4.600 | 540 | 4.600 | 670 | 4.600 | 670 | 4.300 | 460 | 3.000 | 270 | 2.200 | 170 | 2.650 | 130 | 1.150 | 55 |
| 8,0 | | 3.400 | 540 | 3.400 | 670 | 3.400 | 670 | 3.200 | 460 | 2.200 | 270 | 1.600 | 170 | 2.000 | 130 | 800 | 55 |
| 10,0 | | 2.800 | 540 | 2.800 | 670 | 2.800 | 670 | 2.600 | 460 | 1.800 | 270 | 1.300 | 170 | 1.600 | 130 | 650 | 55 |
| 12,0 | | 2.300 | 540 | 2.300 | 670 | 2.300 | 670 | 2.200 | 460 | 1.500 | 270 | 1.100 | 170 | 1.300 | 130 | 500 | 55 |
| 16,0 | | 1.700 | 440 | 1.700 | 550 | 1.700 | 550 | 1.600 | 370 | 1.100 | 230 | 800 | 140 | 1.000 | 110 | 400 | 45 |
| Grooving | $a_p$ | 0,2 DC | | 0,5 DC | | | | | | 0,2 DC | | 0,05 DC | | 0,2 DC | | | |

### ● Drilling

| Work Material / Cond. | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 19.600 | 70 | 19.600 | 90 | 19.600 | 90 | 18.300 | 60 | 12.700 | 40 | 9.000 | 25 | 11.000 | 20 | 4.500 | 10 |
| 2,0 | 11.200 | 90 | 11.200 | 120 | 11.200 | 120 | 10.500 | 80 | 7.300 | 50 | 5.300 | 30 | 6.400 | 25 | 2.650 | 15 |
| 4,0 | 6.400 | 130 | 6.400 | 160 | 6.400 | 160 | 6.000 | 110 | 4.200 | 70 | 3.000 | 40 | 3.600 | 30 | 1.500 | 20 |
| 6,0 | 4.600 | 160 | 4.600 | 200 | 4.600 | 200 | 4.300 | 130 | 3.000 | 80 | 2.200 | 50 | 2.650 | 40 | 1.150 | 20 |
| 8,0 | 3.400 | 160 | 3.400 | 200 | 3.400 | 200 | 3.200 | 130 | 2.200 | 80 | 1.600 | 50 | 2.000 | 40 | 800 | 20 |
| 10,0 | 2.800 | 160 | 2.800 | 200 | 2.800 | 200 | 2.600 | 130 | 1.800 | 80 | 1.300 | 50 | 1.600 | 40 | 650 | 20 |
| 12,0 | 2.300 | 160 | 2.300 | 200 | 2.300 | 200 | 2.200 | 130 | 1.500 | 80 | 1.100 | 50 | 1.300 | 40 | 500 | 20 |
| 16,0 | 1.700 | 130 | 1.700 | 160 | 1.700 | 160 | 1.600 | 110 | 1.100 | 70 | 800 | 40 | 1.000 | 35 | 400 | 15 |






● = Euro stock
❍ = Japan stock

# GSX MILL Endmills
# GSX 40000C-1.5D Type

Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20


## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 40100C-1.5D | ● | 1,0 | 1,5 | 2,5 | 40 | 4 |
| GSX 40150C-1.5D | ● | 1,5 | 2,3 | 3,3 | 40 | 4 |
| GSX 40200C-1.5D | ● | 2,0 | 3,0 | 4,0 | 40 | 4 |
| GSX 40250C-1.5D | ● | 2,5 | 3,8 | 4,8 | 40 | 4 |
| GSX 40300C-1.5D | ● | 3,0 | 4,5 | 6,0 | 45 | 6 |
| GSX 40350C-1.5D | ● | 3,5 | 5,3 | 6,8 | 45 | 6 |
| GSX 40400C-1.5D | ● | 4,0 | 6,0 | 7,5 | 45 | 6 |
| GSX 40450C-1.5D | ● | 4,5 | 6,8 | 8,3 | 50 | 6 |
| GSX 40500C-1.5D | ● | 5,0 | 7,5 | 9,5 | 50 | 6 |
| GSX 40550C-1.5D | ❍ | 5,5 | 8,3 | 10,3 | 50 | 6 |
| GSX 40600C-1.5D | ● | 6,0 | 9,0 | – | 50 | 6 |
| GSX 40700C-1.5D | ● | 7,0 | 11,0 | 13,0 | 60 | 8 |
| GSX 40800C-1.5D | ● | 8,0 | 12,0 | – | 60 | 8 |
| GSX 40900C-1.5D | ● | 9,0 | 14,0 | 16,0 | 70 | 10 |
| GSX 41000C-1.5D | ● | 10,0 | 15,0 | – | 70 | 10 |
| GSX 41200C-1.5D | ● | 12,0 | 18,0 | – | 75 | 12 |
| GSX 41400C-1.5D | ❍ | 14,0 | 21,0 | 24,5 | 90 | 16 |
| GSX 41500C-1.5D | ❍ | 15,0 | 23,0 | 26,5 | 90 | 16 |
| GSX 41600C-1.5D | ❍ | 16,0 | 24,0 | – | 90 | 16 |
| GSX 42000C-1.5D | ❍ | 20,0 | 30,0 | – | 100 | 20 |

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




## Shoulder Milling

| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 24.000 | 470 | 24.000 | 470 | 24.000 | 470 | 21.000 | 290 | 14.500 | 180 | 10.500 | 120 | 12.600 | 120 | 10.500 | 85 |
| 2,0 | | 12.800 | 570 | 12.800 | 570 | 12.800 | 570 | 12.000 | 380 | 8.300 | 230 | 6.000 | 150 | 7.200 | 160 | 6.000 | 110 |
| 4,0 | | 6.800 | 730 | 6.800 | 730 | 6.800 | 730 | 6.400 | 490 | 4.400 | 300 | 3.200 | 200 | 3.800 | 210 | 3.200 | 130 |
| 6,0 | | 4.600 | 780 | 4.600 | 780 | 4.600 | 780 | 4.300 | 520 | 3.000 | 320 | 2.200 | 210 | 2.650 | 220 | 2.200 | 150 |
| 8,0 | | 3.400 | 780 | 3.400 | 780 | 3.400 | 780 | 3.200 | 520 | 2.200 | 320 | 1.600 | 210 | 2.000 | 220 | 1.600 | 150 |
| 10,0 | | 2.800 | 780 | 2.800 | 780 | 2.800 | 780 | 2.600 | 520 | 1.800 | 320 | 1.300 | 210 | 1.500 | 220 | 1.300 | 150 |
| 12,0 | | 2.300 | 780 | 2.300 | 780 | 2.300 | 780 | 2.200 | 520 | 1.500 | 320 | 1.100 | 210 | 1.300 | 220 | 1.100 | 150 |
| 16,0 | | 1.700 | 650 | 1.700 | 650 | 1.700 | 650 | 1.600 | 420 | 1.100 | 280 | 800 | 170 | 1.000 | 180 | 800 | 120 |
| 20,0 | | 1.350 | 600 | 1.350 | 600 | 1.350 | 600 | 1.300 | 380 | 900 | 260 | 650 | 150 | 800 | 160 | 650 | 100 |
| Shoulder cutting | $a_p$ | 1,5 DC | | | | | | | | | | 1,0 DC | | | | | |
| | $a_e$ | 0,05 DC | | | | | | | | | | 0,02 DC | | | | | |

## Shoulder Milling (High Speed Machining Centre)

| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 60.000 | 1.200 | 60.000 | 1.200 | 60.000 | 1.200 | 60.000 | 850 | 60.000 | 720 | 48.000 | 500 | 32.000 | 300 | – | – |
| 2,0 | | 47.800 | 2.200 | 47.800 | 2.200 | 47.800 | 2.200 | 47.800 | 1.600 | 39.800 | 1.200 | 31.800 | 900 | 15.900 | 400 | – | – |
| 4,0 | | 23.900 | 2.600 | 23.900 | 2.600 | 23.900 | 2.600 | 23.900 | 1.900 | 19.900 | 1.400 | 15.900 | 1.100 | 8.000 | 490 | – | – |
| 6,0 | | 16.000 | 2.700 | 16.000 | 2.700 | 16.000 | 2.700 | 16.000 | 2.000 | 13.300 | 1.500 | 10.600 | 1.200 | 5.300 | 520 | – | – |
| 8,0 | | 12.000 | 2.700 | 12.000 | 2.700 | 12.000 | 2.700 | 12.000 | 2.000 | 10.000 | 1.500 | 8.000 | 1.200 | 4.000 | 520 | – | – |
| 10,0 | | 9.600 | 2.700 | 9.600 | 2.700 | 9.600 | 2.700 | 9.600 | 2.000 | 8.000 | 1.500 | 6.400 | 1.200 | 3.200 | 520 | – | – |
| 12,0 | | 8.000 | 2.700 | 8.000 | 2.700 | 8.000 | 2.700 | 8.000 | 2.000 | 6.700 | 1.500 | 5.300 | 1.200 | 2.700 | 520 | – | – |
| 16,0 | | 6.000 | 2.200 | 6.000 | 2.200 | 6.000 | 2.200 | 6.000 | 1.600 | 5.000 | 1.200 | 4.000 | 900 | 2.000 | 450 | – | – |
| 20,0 | | 4.800 | 2.000 | 4.800 | 2.000 | 4.800 | 2.000 | 4.800 | 1.400 | 4.000 | 1.100 | 3.200 | 750 | 1.600 | 380 | – | – |
| Shoulder cutting | $a_p$ | 1,5 DC | | | | | | | | | | 1,0 DC | | | | | |
| | $a_e$ | 0,05 DC | | | | | | | | | | 0,02 DC | | | | | |

## Grooving


| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 24.000 | 380 | 24.000 | 470 | 24.000 | 470 | 21.000 | 290 | 14.500 | 180 | 10.500 | 120 | 12.600 | 85 | 5.200 | 30 |
| 2,0 | | 12.800 | 460 | 12.800 | 570 | 12.800 | 570 | 12.000 | 380 | 8.300 | 230 | 6.000 | 150 | 7.200 | 110 | 3.000 | 40 |
| 4,0 | | 6.800 | 580 | 6.800 | 730 | 6.800 | 730 | 5.400 | 490 | 4.400 | 300 | 3.200 | 200 | 3.800 | 130 | 1.600 | 55 |
| 6,0 | | 4.600 | 620 | 4.600 | 780 | 4.600 | 780 | 4.300 | 520 | 3.000 | 320 | 2.200 | 210 | 2.650 | 160 | 1.100 | 65 |
| 8,0 | | 3.400 | 620 | 3.400 | 780 | 3.400 | 780 | 3.200 | 520 | 2.200 | 320 | 1.600 | 210 | 2.000 | 160 | 800 | 65 |
| 10,0 | | 2.800 | 620 | 2.800 | 780 | 2.800 | 780 | 2.600 | 520 | 1.800 | 320 | 1.300 | 210 | 1.600 | 160 | 650 | 65 |
| 12,0 | | 2.300 | 620 | 2.300 | 780 | 2.300 | 780 | 2.200 | 520 | 1.500 | 320 | 1.100 | 210 | 1.300 | 160 | 550 | 65 |
| 16,0 | | 1.700 | 520 | 1.700 | 560 | 1.700 | 560 | 1.600 | 420 | 1.100 | 280 | 800 | 170 | 1.000 | 130 | 400 | 55 |
| 20,0 | | 1.350 | 480 | 1.350 | 600 | 1.350 | 600 | 1.300 | 380 | 900 | 260 | 650 | 150 | 800 | 110 | 320 | 50 |
| Grooving | $a_p$ | 0,2 DC | | 0,5 DC | | | | | | 0,2 DC | | 0,05 DC | | 0,2 DC | | | |

# GSX 40000S-2D Type



Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 40100S-2D | ● | 1,0 | 2,5 | 3,5 | 40 | 4 |
| GSX 40150S-2D | ❍ | 1,5 | 3,8 | 4,8 | 40 | 4 |
| GSX 40200S-2D | ● | 2,0 | 5,0 | 6,0 | 40 | 4 |
| GSX 40250S-2D | ● | 2,5 | 6,3 | 7,3 | 40 | 4 |
| GSX 40300S-2D | ● | 3,0 | 7,5 | 9,0 | 45 | 6 |
| GSX 40350S-2D | ● | 3,5 | 8,8 | 10,0 | 45 | 6 |
| GSX 40400S-2D | ● | 4,0 | 11,0 | 14,0 | 45 | 6 |
| GSX 40450S-2D | ❍ | 4,5 | 11,3 | 12,8 | 50 | 6 |
| GSX 40500S-2D | ● | 5,0 | 13,0 | 19,6 | 50 | 6 |
| GSX 40550S-2D | ❍ | 5,5 | 13,0 | 19,6 | 50 | 6 |
| GSX 40600S-2D | ● | 6,0 | 13,0 | – | 50 | 6 |
| GSX 40700S-2D | ● | 7,0 | 16,0 | 21,1 | 60 | 8 |
| GSX 40800S-2D | ● | 8,0 | 19,0 | – | 60 | 8 |
| GSX 40900S-2D | ❍ | 9,0 | 19,0 | 24,1 | 70 | 10 |
| GSX 41000S-2D | ● | 10,0 | 22,0 | – | 70 | 10 |
| GSX 41200S-2D | ● | 12,0 | 26,0 | – | 75 | 12 |
| GSX 41600S-2D | ● | 16,0 | 32,0 | – | 90 | 16 |
| GSX 42000S-2D | ● | 20,0 | 40,0 | – | 100 | 20 |

## Endmill Identification (GSX MILL Series)


**GSX 4 1000 S - 2D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|

S: Sharp Edge
C: Gash Land Drilling

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
5. This series is not recommended for grooving.
6. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 22.000 | 360 | 22.000 | 360 | 22.000 | 360 | 19.000 | 220 | 13.000 | 140 | 9.500 | 90 | 11.300 | 90 | 9.500 | 65 |
| 2,0 | 11.500 | 440 | 11.500 | 440 | 11.500 | 440 | 11.000 | 290 | 7.500 | 180 | 5.400 | 110 | 6.500 | 120 | 5.400 | 85 |
| 4,0 | 6.000 | 560 | 6.000 | 560 | 6.000 | 560 | 5.800 | 370 | 4.000 | 230 | 2.900 | 150 | 3.400 | 160 | 2.900 | 100 |
| 6,0 | 4.200 | 600 | 4.200 | 600 | 4.200 | 600 | 4.000 | 400 | 2.700 | 240 | 2.000 | 160 | 2.400 | 170 | 2.000 | 120 |
| 8,0 | 3.000 | 600 | 3.000 | 600 | 3.000 | 600 | 2.800 | 400 | 2.000 | 240 | 1.450 | 160 | 1.800 | 170 | 1.450 | 120 |
| 10,0 | 2.500 | 600 | 2.500 | 600 | 2.500 | 600 | 2.350 | 400 | 1.600 | 240 | 1.200 | 160 | 1.450 | 170 | 1.200 | 120 |
| 12,0 | 2.100 | 600 | 2.100 | 600 | 2.100 | 600 | 2.000 | 400 | 1.350 | 240 | 1.000 | 160 | 1.200 | 170 | 1.000 | 120 |
| 16,0 | 1.500 | 500 | 1.500 | 500 | 1.500 | 500 | 1.450 | 320 | 1.000 | 210 | 750 | 130 | 900 | 140 | 750 | 90 |
| 20,0 | 1.200 | 460 | 1.200 | 460 | 1.200 | 460 | 1.150 | 290 | 800 | 200 | 600 | 110 | 700 | 120 | 600 | 75 |
| Shoulder cutting ap | 2,0 DC | | | | | | | | | | | | | | | |
| Shoulder cutting ae | 0,03 DC | | | | | | | | | | 0,01 DC | | | | | |

### ● Groove Finishing

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 22.000 | 360 | 22.000 | 360 | 22.000 | 360 | 19.000 | 220 | 13.000 | 140 | 9.500 | 90 | 11.300 | 90 | 9.500 | 65 |
| 2,0 | 11.500 | 440 | 11.500 | 440 | 11.500 | 440 | 11.000 | 290 | 7.500 | 180 | 5.400 | 110 | 6.500 | 120 | 5.400 | 85 |
| 4,0 | 6.000 | 560 | 6.000 | 560 | 6.000 | 560 | 5.800 | 370 | 4.000 | 230 | 2.900 | 150 | 3.400 | 160 | 2.900 | 100 |
| 6,0 | 4.200 | 600 | 4.200 | 600 | 4.200 | 600 | 4.000 | 400 | 2.700 | 240 | 2.000 | 160 | 2.400 | 170 | 2.000 | 120 |
| 8,0 | 3.000 | 600 | 3.000 | 600 | 3.000 | 600 | 2.800 | 400 | 2.000 | 240 | 1.450 | 160 | 1.800 | 170 | 1.450 | 120 |
| 10,0 | 2.500 | 600 | 2.500 | 600 | 2.500 | 600 | 2.350 | 400 | 1.600 | 240 | 1.200 | 160 | 1.450 | 170 | 1.200 | 120 |
| 12,0 | 2.100 | 600 | 2.100 | 600 | 2.100 | 600 | 2.000 | 400 | 1.350 | 240 | 1.000 | 160 | 1.200 | 170 | 1.000 | 120 |
| 16,0 | 1.500 | 500 | 1.500 | 500 | 1.500 | 500 | 1.450 | 320 | 1.000 | 210 | 750 | 130 | 900 | 140 | 750 | 90 |
| 20,0 | 1.200 | 460 | 1.200 | 460 | 1.200 | 460 | 1.150 | 290 | 800 | 200 | 600 | 110 | 700 | 120 | 600 | 75 |
| Groove finishing ap | 1,5 DC | | | | | | | | | | | | | | | |
| Groove finishing ae | –0,02 DC | | | | | | | | | | | | | | | |






● = Euro stock
❍ = Japan stock

# GSX MILL Endmills
# GSX 40000C-2D Type

Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20


## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 40100C-2D | ● | 1,0 | 2,0 | 3,0 | 40 | 4 |
| GSX 40150C-2D | ● | 1,5 | 3,0 | 4,0 | 40 | 4 |
| GSX 40200C-2D | ● | 2,0 | 4,0 | 5,0 | 40 | 4 |
| GSX 40250C-2D | ● | 2,5 | 5,0 | 6,0 | 40 | 4 |
| GSX 40300C-2D | ● | 3,0 | 6,0 | 7,5 | 45 | 6 |
| GSX 40350C-2D | ❍ | 3,5 | 7,0 | 8,5 | 45 | 6 |
| GSX 40400C-2D | ● | 4,0 | 8,0 | 9,5 | 45 | 6 |
| GSX 40450C-2D | ● | 4,5 | 9,0 | 10,5 | 50 | 6 |
| GSX 40500C-2D | ● | 5,0 | 10,0 | 12,0 | 50 | 6 |
| GSX 40550C-2D | ● | 5,5 | 11,0 | 13,0 | 50 | 6 |
| GSX 40600C-2D | ● | 6,0 | 12,0 | – | 50 | 6 |
| GSX 40700C-2D | ● | 7,0 | 14,0 | 16,0 | 60 | 8 |
| GSX 40800C-2D | ● | 8,0 | 16,0 | – | 60 | 8 |
| GSX 40900C-2D | ● | 9,0 | 18,0 | 20,0 | 70 | 10 |
| GSX 41000C-2D | ● | 10,0 | 20,0 | – | 70 | 10 |
| GSX 41200C-2D | ● | 12,0 | 24,0 | – | 75 | 12 |
| GSX 41400C-2D | ❍ | 14,0 | 28,0 | 31,5 | 90 | 16 |
| GSX 41500C-2D | | 15,0 | 30,0 | 33,5 | 90 | 16 |
| GSX 41600C-2D | ● | 16,0 | 32,0 | – | 90 | 16 |
| GSX 42000C-2D | ● | 20,0 | 40,0 | – | 100 | 20 |

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
5. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




## ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 24.000 | 470 | 24.000 | 470 | 24.000 | 470 | 21.000 | 290 | 14.500 | 180 | 10.500 | 120 | 12.600 | 120 | 10.500 | 85 |
| 2,0 | 12.800 | 570 | 12.800 | 570 | 12.800 | 570 | 12.000 | 380 | 8.300 | 230 | 6.000 | 150 | 7.200 | 160 | 6.000 | 110 |
| 4,0 | 6.800 | 730 | 6.800 | 730 | 6.800 | 730 | 6.400 | 490 | 4.400 | 300 | 3.200 | 200 | 3.800 | 210 | 3.200 | 130 |
| 6,0 | 4.600 | 780 | 4.600 | 780 | 4.600 | 780 | 4.300 | 520 | 3.000 | 320 | 2.200 | 210 | 2.650 | 220 | 2.200 | 150 |
| 8,0 | 3.400 | 780 | 3.400 | 780 | 3.400 | 780 | 3.200 | 520 | 2.200 | 320 | 1.600 | 210 | 2.000 | 220 | 1.600 | 150 |
| 10,0 | 2.800 | 780 | 2.800 | 780 | 2.800 | 780 | 2.600 | 520 | 1.800 | 320 | 1.300 | 210 | 1.500 | 220 | 1.300 | 150 |
| 12,0 | 2.300 | 780 | 2.300 | 780 | 2.300 | 780 | 2.200 | 520 | 1.500 | 320 | 1.100 | 210 | 1.300 | 220 | 1.100 | 150 |
| 16,0 | 1.700 | 650 | 1.700 | 650 | 1.700 | 650 | 1.600 | 420 | 1.100 | 280 | 800 | 170 | 1.000 | 180 | 800 | 120 |
| 20,0 | 1.350 | 600 | 1.350 | 600 | 1.350 | 600 | 1.300 | 380 | 900 | 260 | 650 | 150 | 800 | 160 | 650 | 100 |
| Shoulder cutting ap | 1,5 DC | | | | | | | | | | 1,0 DC | | | | | |
| Shoulder cutting ae | 0,05 DC | | | | | | | | | | 0,02 DC | | | | | |

## ● Shoulder Milling (High Speed Machining Centre)

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 60.000 | 1.200 | 60.000 | 1.200 | 60.000 | 1.200 | 60.000 | 850 | 60.000 | 720 | 48.000 | 500 | 32.000 | 300 | – | – |
| 2,0 | 47.800 | 2.200 | 47.800 | 2.200 | 47.800 | 2.200 | 47.800 | 1.600 | 39.800 | 1.200 | 31.800 | 900 | 15.900 | 400 | – | – |
| 4,0 | 23.900 | 2.600 | 23.900 | 2.600 | 23.900 | 2.600 | 23.900 | 1.900 | 19.900 | 1.400 | 15.900 | 1.100 | 8.000 | 490 | – | – |
| 6,0 | 16.000 | 2.700 | 16.000 | 2.700 | 16.000 | 2.700 | 16.000 | 2.000 | 13.300 | 1.500 | 10.600 | 1.200 | 5.300 | 520 | – | – |
| 8,0 | 12.000 | 2.700 | 12.000 | 2.700 | 12.000 | 2.700 | 12.000 | 2.000 | 10.000 | 1.500 | 8.000 | 1.200 | 4.000 | 520 | – | – |
| 10,0 | 9.600 | 2.700 | 9.600 | 2.700 | 9.600 | 2.700 | 9.600 | 2.000 | 8.000 | 1.500 | 6.400 | 1.200 | 3.200 | 520 | – | – |
| 12,0 | 8.000 | 2.700 | 8.000 | 2.700 | 8.000 | 2.700 | 8.000 | 2.000 | 6.700 | 1.500 | 5.300 | 1.200 | 2.700 | 520 | – | – |
| 16,0 | 6.000 | 2.200 | 6.000 | 2.200 | 6.000 | 2.200 | 6.000 | 1.600 | 5.000 | 1.200 | 4.000 | 900 | 2.000 | 450 | – | – |
| 20,0 | 4.800 | 2.000 | 4.800 | 2.000 | 4.800 | 2.000 | 4.800 | 1.400 | 4.000 | 1.100 | 3.200 | 750 | 1.600 | 380 | – | – |
| Shoulder cutting ap | 1,5 DC | | | | | | | | | | 1,0 DC | | | | | |
| Shoulder cutting ae | 0,05 DC | | | | | | | | | | 0,02 DC | | | | | |

## ● Grooving

| Work Material / Cond. / DC (mm) | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | 24.000 | 380 | 24.000 | 470 | 24.000 | 470 | 21.000 | 290 | 14.500 | 180 | 10.500 | 120 | 12.600 | 85 | 5.200 | 30 |
| 2,0 | 12.800 | 460 | 12.800 | 570 | 12.800 | 570 | 12.000 | 380 | 8.300 | 230 | 6.000 | 150 | 7.200 | 110 | 3.000 | 40 |
| 4,0 | 6.800 | 580 | 6.800 | 730 | 6.800 | 730 | 5.400 | 490 | 4.400 | 300 | 3.200 | 200 | 3.800 | 130 | 1.600 | 55 |
| 6,0 | 4.600 | 620 | 4.600 | 780 | 4.600 | 780 | 4.300 | 520 | 3.000 | 320 | 2.200 | 210 | 2.650 | 160 | 1.100 | 65 |
| 8,0 | 3.400 | 620 | 3.400 | 780 | 3.400 | 780 | 3.200 | 520 | 2.200 | 320 | 1.600 | 210 | 2.000 | 160 | 800 | 65 |
| 10,0 | 2.800 | 620 | 2.800 | 780 | 2.800 | 780 | 2.600 | 520 | 1.800 | 320 | 1.300 | 210 | 1.600 | 160 | 650 | 65 |
| 12,0 | 2.300 | 620 | 2.300 | 780 | 2.300 | 780 | 2.200 | 520 | 1.500 | 320 | 1.100 | 210 | 1.300 | 160 | 550 | 65 |
| 16,0 | 1.700 | 520 | 1.700 | 560 | 1.700 | 560 | 1.600 | 420 | 1.100 | 280 | 800 | 170 | 1.000 | 130 | 400 | 55 |
| 20,0 | 1.350 | 480 | 1.350 | 600 | 1.350 | 600 | 1.300 | 380 | 900 | 260 | 650 | 150 | 800 | 110 | 320 | 50 |
| Grooving ap | 0,2 DC | | 0,5 DC | | | | | | 0,2 DC | | 0,05 DC | | 0,2 DC | | | |


# GSX 40000C-3D Type



Coated Carbide — Grades

GSX — Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 40100C-3D | ❍ | 1,0 | 3,0 | 4,0 | 40 | 4 |
| GSX 40150C-3D | ● | 1,5 | 4,5 | 5,5 | 40 | 4 |
| GSX 40200C-3D | ● | 2,0 | 6,0 | 7,0 | 40 | 4 |
| GSX 40250C-3D | ❍ | 2,5 | 7,5 | 8,5 | 40 | 4 |
| GSX 40300C-3D | ● | 3,0 | 9,0 | 10,5 | 50 | 6 |
| GSX 40400C-3D | ● | 4,0 | 12,0 | 13,5 | 50 | 6 |
| GSX 40500C-3D | ● | 5,0 | 15,0 | 17,0 | 50 | 6 |
| GSX 40600C-3D | ● | 6,0 | 18,0 | – | 50 | 6 |
| GSX 40800C-3D | ● | 8,0 | 24,0 | – | 70 | 8 |
| GSX 41000C-3D | ● | 10,0 | 30,0 | – | 90 | 10 |
| GSX 41200C-3D | ● | 12,0 | 36,0 | – | 90 | 12 |
| GSX 41600C-3D | ● | 16,0 | 48,0 | – | 110 | 16 |
| GSX 42000C-3D | ❍ | 20,0 | 60,0 | – | 120 | 20 |

## Endmill Identification (GSX MILL Series)


**GSX** **4** **0100** **C** - **2D / 3D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|

S: Sharp Edge
C: Gash Land Drilling

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. In rear cases, chattering may occur in early milling stages, dissipating after 2 m of cutting.
5. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
6. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




### ● Shoulder Milling

| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 21.000 | 360 | 21.000 | 360 | 21.000 | 360 | 19.000 | 220 | 13.000 | 140 | 9.000 | 90 | 10.500 | 90 | 9.000 | 65 |
| 2,0 | | 10.500 | 360 | 10.500 | 360 | 10.500 | 360 | 9.600 | 290 | 7.500 | 180 | 4.500 | 110 | 5.200 | 120 | 4.500 | 85 |
| 4,0 | | 5.200 | 500 | 5.200 | 500 | 5.200 | 500 | 4.800 | 370 | 4.000 | 280 | 2.250 | 150 | 2.600 | 160 | 2.250 | 100 |
| 6,0 | | 3.500 | 560 | 3.500 | 560 | 3.500 | 560 | 3.200 | 400 | 2.700 | 300 | 1.500 | 160 | 1.700 | 170 | 1.500 | 120 |
| 8,0 | | 2.600 | 520 | 2.600 | 520 | 2.600 | 520 | 2.400 | 400 | 2.000 | 300 | 1.100 | 160 | 1.300 | 170 | 1.100 | 120 |
| 10,0 | | 2.100 | 500 | 2.100 | 500 | 2.100 | 500 | 1.900 | 400 | 1.600 | 300 | 900 | 160 | 1.000 | 160 | 900 | 120 |
| 12,0 | | 1.750 | 500 | 1.750 | 500 | 1.750 | 500 | 1.600 | 400 | 1.350 | 300 | 750 | 150 | 850 | 160 | 750 | 120 |
| 16,0 | | 1.300 | 420 | 1.300 | 420 | 1.300 | 420 | 1.200 | 330 | 1.000 | 260 | 550 | 120 | 650 | 140 | 550 | 100 |
| 20,0 | | 1.050 | 380 | 1.050 | 380 | 1.050 | 380 | 950 | 290 | 800 | 230 | 450 | 110 | 500 | 120 | 450 | 90 |
| Shoulder cutting | $a_p$ | 2,5 DC | | | | | | | | | | 2,0 DC | | | | | |
| | $a_e$ | < ø3: 0,05 DC , ≤ ø3< ø8: 0,1 DC , ≤ ø8: 0,15 DC | | | | | | | | 0,02 DC | | | | | | | |

### ● Grooving

| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 16.600 | 140 | 16.600 | 140 | 16.600 | 140 | 15.500 | 100 | 10.500 | 100 | 7.500 | 70 | 9.400 | 60 | 3.750 | 20 |
| 2,0 | | 9.500 | 160 | 9.500 | 160 | 9.500 | 160 | 9.000 | 180 | 6.200 | 120 | 4.500 | 90 | 5.200 | 80 | 2.250 | 30 |
| 4,0 | | 5.200 | 160 | 5.200 | 180 | 5.200 | 180 | 4.800 | 160 | 3.400 | 110 | 2.200 | 65 | 2.600 | 70 | 1.250 | 25 |
| 6,0 | | 3.500 | 160 | 3.500 | 200 | 3.500 | 200 | 3.200 | 160 | 2.550 | 120 | 1.500 | 65 | 1.700 | 70 | 950 | 25 |
| 8,0 | | 2.600 | 160 | 2.600 | 200 | 2.600 | 200 | 2.400 | 160 | 1.900 | 120 | 1.100 | 65 | 1.300 | 70 | 700 | 25 |
| 10,0 | | 2.100 | 160 | 2.100 | 200 | 2.100 | 200 | 1.900 | 160 | 1.500 | 120 | 900 | 65 | 1.000 | 70 | 550 | 25 |
| 12,0 | | 1.750 | 160 | 1.750 | 200 | 1.750 | 200 | 1.600 | 160 | 1.250 | 120 | 750 | 65 | 850 | 70 | 450 | 25 |
| 16,0 | | 1.300 | 160 | 1.300 | 200 | 1.300 | 200 | 1.200 | 160 | 950 | 120 | 550 | 65 | 650 | 70 | 350 | 25 |
| 20,0 | | 1.050 | 160 | 1.050 | 200 | 1.050 | 200 | 950 | 160 | 750 | 120 | 450 | 65 | 500 | 70 | 280 | 25 |
| Grooving | $a_p$ | 0,1 DC | | 0,2 DC | | | | | | | | 0,05 DC | | 0,1 DC | | | |






● = Euro stock
❍ = Japan stock

# GSX MILL Endmills
# GSX 40000C-4D Type

Coated Carbide Grades | GSX Coating

| Structural Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




| DC | Tolerance |
|---|---|
| D ≤ 3,0 | 0 – 0,015 |
| 3,0 < D ≤ 12 | 0 – 0,020 |
| 12,0 < D | 0 – 0,030 |

Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSX 40100C-4D | ● | 1,0 | 4,0 | 5,0 | 40 | 4 |
| GSX 40150C-4D | ● | 1,5 | 6,0 | 7,0 | 40 | 4 |
| GSX 40200C-4D | ● | 2,0 | 8,0 | 9,0 | 40 | 4 |
| GSX 40250C-4D | ● | 2,5 | 10,0 | 11,0 | 50 | 4 |
| GSX 40300C-4D | ● | 3,0 | 12,0 | 13,5 | 50 | 6 |
| GSX 40400C-4D | ● | 4,0 | 16,0 | 17,5 | 50 | 6 |
| GSX 40500C-4D | ● | 5,0 | 20,0 | 22,0 | 60 | 6 |
| GSX 40600C-4D | ● | 6,0 | 24,0 | – | 60 | 6 |
| GSX 40800C-4D | ● | 8,0 | 32,0 | – | 80 | 8 |
| GSX 41000C-4D | ● | 10,0 | 40,0 | – | 90 | 10 |
| GSX 41200C-4D | ● | 12,0 | 48,0 | – | 100 | 12 |
| GSX 41600C-4D | ● | 16,0 | 64,0 | – | 120 | 16 |
| GSX 42000C-4D | ❍ | 20,0 | 80,0 | – | 140 | 20 |


## Endmill Identification (GSX MILL Series)

**GSX 4 0100 C - 4D**

| Series Code | No. of Teeth | Diameter | Cutting Edge | Cutting Edge Length |
|---|---|---|---|---|
| | | | S: Sharp Edge<br>C: Gash Land Drilling | |

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. In rear cases, chattering may occur in early milling stages, dissipating after 2m of cutting.
5. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
6. This series is not recommended for grooving.
7. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




## Shoulder Milling


| Work Material / Cond. | | Structural Steel | | Carbon Steel (150 to 250HB) | | Cast Iron | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (35 to 45HRC) | | Hardened Steel (45 to 55HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 1,0 | | 9.000 | 140 | 9.000 | 140 | 9.000 | 140 | 7.000 | 80 | 6.500 | 60 | 4.500 | 40 | 5.400 | 40 | 4.500 | 40 |
| 2,0 | | 4.500 | 140 | 4.500 | 140 | 4.500 | 140 | 3.500 | 100 | 3.200 | 80 | 2.300 | 55 | 2.700 | 55 | 2.300 | 40 |
| 4,0 | | 2.250 | 200 | 2.250 | 200 | 2.250 | 200 | 1.750 | 120 | 1.600 | 100 | 1.200 | 60 | 1.350 | 50 | 1.200 | 35 |
| 6,0 | | 1.500 | 250 | 1.500 | 250 | 1.500 | 250 | 1.150 | 160 | 1.050 | 140 | 800 | 65 | 900 | 45 | 800 | 35 |
| 8,0 | | 1.100 | 220 | 1.100 | 220 | 1.100 | 220 | 850 | 160 | 800 | 130 | 600 | 65 | 660 | 45 | 600 | 35 |
| 10,0 | | 900 | 210 | 900 | 210 | 900 | 210 | 700 | 140 | 650 | 120 | 460 | 65 | 540 | 45 | 460 | 35 |
| 12,0 | | 750 | 200 | 750 | 200 | 750 | 200 | 580 | 140 | 520 | 110 | 400 | 65 | 450 | 45 | 400 | 35 |
| 16,0 | | 550 | 170 | 550 | 170 | 550 | 170 | 440 | 120 | 400 | 95 | 300 | 55 | 330 | 45 | 300 | 35 |
| 20,0 | | 450 | 150 | 450 | 150 | 450 | 150 | 350 | 100 | 320 | 80 | 240 | 50 | 270 | 45 | 240 | 35 |
| Shoulder cutting | $a_p$ | 3,5 DC | | | | | | | | | | 3,0 DC | | | | | |
| | $a_e$ | < ø3: 0,04 DC , 3 ≤ øD< 8: 0,08 DC , 8 ≤ øD: 0,1 DC | | | | | | | | | | 0,02 DC | | | | | |

# GSXVL 4000-2.5D Type



Coated Carbide Grades | GSX Coating

| Structual Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |





Grade: ACF20

## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSXVL 4020-2.5D | ● | 2,0 | 5 | 6,5 | 50 | 4 |
| GSXVL 4030-2.5D | ● | 3,0 | 8 | 9,5 | 50 | 6 |
| GSXVL 4040-2.5D | ● | 4,0 | 10 | 11,5 | 50 | 6 |
| GSXVL 4050-2.5D | ● | 5,0 | 13 | 14,5 | 60 | 6 |
| GSXVL 4060-2.5D | ● | 6,0 | 15 | – | 60 | 6 |
| GSXVL 4070-2.5D | ❍ | 7,0 | 18 | 20,0 | 70 | 8 |
| GSXVL 4080-2.5D | ● | 8,0 | 20 | – | 80 | 8 |
| GSXVL 4090-2.5D | ● | 9,0 | 23 | 25,0 | 90 | 10 |
| GSXVL 4100-2.5D | ● | 10,0 | 25 | – | 90 | 10 |
| GSXVL 4110-2.5D | ● | 11,0 | 28 | 30,5 | 90 | 12 |
| GSXVL 4120-2.5D | ● | 12,0 | 30 | – | 90 | 12 |
| GSXVL 4140-2.5D | ● | 14,0 | 35 | 37,5 | 110 | 16 |
| GSXVL 4150-2.5D | ● | 15,0 | 38 | 41,0 | 110 | 16 |
| GSXVL 4160-2.5D | ● | 16,0 | 40 | – | 115 | 16 |
| GSXVL 4180-2.5D | ● | 18,0 | 45 | 48,0 | 120 | 20 |
| GSXVL 4200-2.5D | ● | 20,0 | 50 | – | 125 | 20 |
| GSXVL 4250-2.5D | ❍ | 25,0 | 63 | – | 140 | 25 |

## SAFE-LOCK™ Applicable Endmills





## Endmills

(mm)


| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| GSXVL 4120S-2.5D | ❍ | 12,0 | 30 | – | 90 | 12 |
| GSXVL 4140S-2.5D | ❍ | 14,0 | 35 | 37,5 | 110 | 16 |
| GSXVL 4150S-2.5D | ❍ | 15,0 | 38 | 41,0 | 110 | 16 |
| GSXVL 4160S-2.5D | ❍ | 16,0 | 40 | – | 115 | 16 |
| GSXVL 4180S-2.5D | ❍ | 18,0 | 45 | 48,0 | 120 | 20 |
| GSXVL 4200S-2.5D | | 20,0 | 50 | – | 125 | 20 |
| GSXVL 4250S-2.5D | ❍ | 25,0 | 63 | – | 140 | 25 |

## Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.

### ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Carbon Steel, Cast Iron (150 to 250HB) | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (40 to 50HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy (20 to 45HRC) | |
|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 2,0 | 13.000 | 1.000 | 10.000 | 800 | 8.000 | 700 | 10.000 | 580 | 5.000 | 200 |
| 4,0 | 9.600 | 1.200 | 8.000 | 1.000 | 6.000 | 800 | 5.500 | 650 | 3.000 | 230 |
| 6,0 | 6.800 | 1.500 | 5.600 | 1.200 | 4.200 | 900 | 3.800 | 680 | 2.100 | 240 |
| 8,0 | 5.200 | 1.600 | 4.400 | 1.300 | 3.200 | 950 | 2.800 | 650 | 1.600 | 250 |
| 10,0 | 4.200 | 1.500 | 3.500 | 1.200 | 2.600 | 800 | 2.300 | 600 | 1.300 | 210 |
| 12,0 | 3.500 | 1.400 | 3.000 | 1.200 | 2.200 | 700 | 1.900 | 550 | 1.100 | 180 |
| 14,0 | 3.000 | 1.200 | 2.600 | 1.100 | 1.800 | 600 | 1.600 | 500 | 900 | 150 |
| 16,0 | 2.700 | 1.100 | 2.200 | 1.000 | 1.600 | 600 | 1.400 | 480 | 760 | 130 |
| 18,0 | 2.400 | 1.000 | 2.000 | 900 | 1.400 | 570 | 1.300 | 450 | 680 | 120 |
| 20,0 | 2.200 | 900 | 1.700 | 800 | 1.200 | 550 | 1.100 | 400 | 600 | 100 |
| 25,0 | 1.700 | 680 | 1.400 | 630 | 1.000 | 450 | 890 | 310 | 480 | 82 |
| Shoulder cutting ap | 1,5 DC | | | | | | | | | |
| Shoulder cutting ae | 0,1 DC | | | | 0,05 DC | | 0,1 DC | | 0,05 DC | |




### ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Carbon Steel, Cast Iron (150 to 250HB) | | Alloy Steel (25 to 35HRC) | | Tempered Steel, Hardened Steel (40 to 50HRC) | | Stainless Steel | | Heat Resistive Steel, Titanium Alloy (20 to 45HRC) | |
|---|---|---|---|---|---|---|---|---|---|---|
| | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 2,0 | 13.000 | 750 | 10.000 | 550 | 8.400 | 500 | 6.500 | 300 | 4.000 | 140 |
| 4,0 | 8.200 | 800 | 6.000 | 600 | 5.200 | 500 | 4.000 | 330 | 2.000 | 130 |
| 6,0 | 6.100 | 1.100 | 4.000 | 600 | 3.500 | 580 | 2.700 | 350 | 1.350 | 150 |
| 8,0 | 4.600 | 1.000 | 3.000 | 580 | 2.600 | 570 | 2.000 | 330 | 1.000 | 140 |
| 10,0 | 3.600 | 1.000 | 2.400 | 550 | 2.100 | 510 | 1.600 | 200 | 800 | 130 |
| 12,0 | 3.100 | 920 | 2.000 | 500 | 1.700 | 450 | 1.300 | 280 | 660 | 110 |
| 14,0 | 2.600 | 750 | 1.700 | 450 | 1.500 | 400 | 1.100 | 250 | 570 | 100 |
| 16,0 | 2.300 | 670 | 1.500 | 420 | 1.300 | 350 | 1.000 | 230 | 500 | 90 |
| 18,0 | 2.000 | 620 | 1.300 | 380 | 1.100 | 330 | 900 | 200 | 430 | 80 |
| 20,0 | 1.900 | 600 | 1.200 | 360 | 1.000 | 320 | 800 | 180 | 380 | 70 |
| 25,0 | 1.500 | 470 | 1.000 | 300 | 790 | 250 | 640 | 140 | 300 | 55 |
| Grooving ap | 1,0 DC | | | | 0,2 DC | | 0,3 DC | | 0,2 DC | |






● = Euro stock
❍ = Japan stock
❑ = Delivery on request

# Anti-Vibration MILL with R. Corner
# GSXVL 4000-R-2.5D Type

Coated Carbide Grades | GSX Coating

| Structal Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




## Endmills

SAFE-LOCK™

Applicable Endmills





## ■ Endmills (mm)

| Cat. No. | Stock | DC | RE | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|---|
| GSXVL 4030-R02-2.5D | ● | 3,0 | 0,2 | 8 | 9,5 | 50 | 6 |
| GSXVL 4030-R05-2.5D | ● | 3,0 | 0,5 | 8 | 9,5 | 50 | 6 |
| GSXVL 4040-R02-2.5D | ❍ | 4,0 | 0,2 | 10 | 11,5 | 50 | 6 |
| GSXVL 4040-R05-2.5D | ● | 4,0 | 0,5 | 10 | 11,5 | 50 | 6 |
| GSXVL 4040-R10-2.5D | ❍ | 4,0 | 1,0 | 10 | 11,5 | 50 | 6 |
| GSXVL 4050-R02-2.5D | ● | 5,0 | 0,2 | 13 | 14,5 | 60 | 6 |
| GSXVL 4050-R05-2.5D | ● | 5,0 | 0,5 | 13 | 14,5 | 60 | 6 |
| GSXVL 4050-R10-2.5D | | 5,0 | 1,0 | 13 | 14,5 | 60 | 6 |
| GSXVL 4060-R03-2.5D | ❍ | 6,0 | 0,3 | 15 | – | 60 | 6 |
| GSXVL 4060-R05-2.5D | ● | 6,0 | 0,5 | 15 | – | 60 | 6 |
| GSXVL 4060-R10-2.5D | ● | 6,0 | 1,0 | 15 | – | 60 | 6 |
| GSXVL 4060-R15-2.5D | ❍ | 6,0 | 1,5 | 15 | – | 60 | 6 |
| GSXVL 4080-R03-2.5D | ● | 8,0 | 0,3 | 20 | – | 80 | 8 |
| GSXVL 4080-R05-2.5D | ● | 8,0 | 0,5 | 20 | – | 80 | 8 |
| GSXVL 4080-R10-2.5D | ● | 8,0 | 1,0 | 20 | – | 80 | 8 |
| GSXVL 4080-R15-2.5D | ● | 8,0 | 1,5 | 20 | – | 80 | 8 |
| GSXVL 4080-R20-2.5D | ❍ | 8,0 | 2,0 | 20 | – | 80 | 8 |
| GSXVL 4100-R03-2.5D | ● | 10,0 | 0,3 | 25 | – | 90 | 10 |
| GSXVL 4100-R05-2.5D | ● | 10,0 | 0,5 | 25 | – | 90 | 10 |
| GSXVL 4100-R10-2.5D | ● | 10,0 | 1,0 | 25 | – | 90 | 10 |
| GSXVL 4100-R15-2.5D | | 10,0 | 1,5 | 25 | – | 90 | 10 |
| GSXVL 4100-R20-2.5D | ❍ | 10,0 | 2,0 | 25 | – | 90 | 10 |
| GSXVL 4120-R05-2.5D | ● | 12,0 | 0,5 | 30 | – | 90 | 12 |
| GSXVL 4120-R10-2.5D | ● | 12,0 | 1,0 | 30 | – | 90 | 12 |
| GSXVL 4120-R15-2.5D | ● | 12,0 | 1,5 | 30 | – | 90 | 12 |
| GSXVL 4120-R20-2.5D | ❍ | 12,0 | 2,0 | 30 | – | 90 | 12 |
| GSXVL 4120-R30-2.5D | ❍ | 12,0 | 3,0 | 30 | – | 90 | 12 |
| GSXVL 4160-R10-2.5D | ● | 16,0 | 1,0 | 40 | – | 115 | 16 |
| GSXVL 4160-R15-2.5D | ● | 16,0 | 1,5 | 40 | – | 115 | 16 |
| GSXVL 4160-R20-2.5D | ● | 16,0 | 2,0 | 40 | – | 115 | 16 |
| GSXVL 4160-R30-2.5D | | 16,0 | 3,0 | 40 | – | 115 | 16 |
| GSXVL 4200-R10-2.5D | ● | 20,0 | 1,0 | 50 | – | 125 | 20 |
| GSXVL 4200-R15-2.5D | ❍ | 20,0 | 1,5 | 50 | – | 125 | 20 |
| GSXVL 4200-R20-2.5D | ❍ | 20,0 | 2,0 | 50 | – | 125 | 20 |
| GSXVL 4200-R30-2.5D | ● | 20,0 | 3,0 | 50 | – | 125 | 20 |
| GSXVL 4250-R10-2.5D | ❍ | 25,0 | 1,0 | 63 | – | 140 | 25 |
| GSXVL 4250-R15-2.5D | ❍ | 25,0 | 1,5 | 63 | – | 140 | 25 |
| GSXVL 4250-R20-2.5D | ❍ | 25,0 | 2,0 | 63 | – | 140 | 25 |
| GSXVL 4250-R30-2.5D | ❍ | 25,0 | 3,0 | 63 | – | 140 | 25 |

Grade: ACF20


## ■ Endmills (mm)

| Cat. No. | Stock | DC | RE | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|---|
| GSXVL 4120S-R05-2.5D | ❍ | 12,0 | 0,5 | 30 | – | 90 | 12 |
| GSXVL 4120S-R10-2.5D | ❑ | 12,0 | 1,0 | 30 | – | 90 | 12 |
| GSXVL 4120S-R15-2.5D | ❑ | 12,0 | 1,5 | 30 | – | 90 | 12 |
| GSXVL 4120S-R20-2.5D | ❑ | 12,0 | 2,0 | 30 | – | 90 | 12 |
| GSXVL 4120S-R30-2.5D | ❑ | 12,0 | 3,0 | 30 | – | 90 | 12 |
| GSXVL 4160S-R10-2.5D | ❑ | 16,0 | 1,0 | 40 | – | 115 | 16 |
| GSXVL 4160S-R15-2.5D | ❑ | 16,0 | 1,5 | 40 | – | 115 | 16 |
| GSXVL 4160S-R20-2.5D | ❑ | 16,0 | 2,0 | 40 | – | 115 | 16 |
| GSXVL 4160S-R30-2.5D | ❑ | 16,0 | 3,0 | 40 | – | 115 | 16 |
| GSXVL 4200S-R10-2.5D | ❑ | 20,0 | 1,0 | 50 | – | 125 | 20 |
| GSXVL 4200S-R15-2.5D | ❑ | 20,0 | 1,5 | 50 | – | 125 | 20 |
| GSXVL 4200S-R20-2.5D | ❑ | 20,0 | 2,0 | 50 | – | 125 | 20 |
| GSXVL 4200S-R30-2.5D | ❑ | 20,0 | 3,0 | 50 | – | 125 | 20 |
| GSXVL 4250S-R10-2.5D | ❑ | 25,0 | 1,0 | 63 | – | 140 | 25 |
| GSXVL 4250S-R15-2.5D | ❑ | 25,0 | 1,5 | 63 | – | 140 | 25 |
| GSXVL 4250S-R20-2.5D | ❑ | 25,0 | 2,0 | 63 | – | 140 | 25 |
| GSXVL 4250S-R30-2.5D | ❍ | 25,0 | 3,0 | 63 | – | 140 | 25 |

Grade: ACF20

## ■ Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.




## ● Shoulder Milling and Grooving

| Work Material / Cond. / DC (mm) | | Carbon Steel, Cast Iron (150 to 250HB) Spindle Speed (rpm) | Carbon Steel, Cast Iron (150 to 250HB) Feed Rate (mm/min) | Alloy Steel (25 to 35HRC) Spindle Speed (rpm) | Alloy Steel (25 to 35HRC) Feed Rate (mm/min) | Tempered Steel, Hardened Steel (40 to 50HRC) Spindle Speed (rpm) | Tempered Steel, Hardened Steel (40 to 50HRC) Feed Rate (mm/min) | Stainless Steel Spindle Speed (rpm) | Stainless Steel Feed Rate (mm/min) | Heat Resistive Steel, Titanium Alloy (20 to 45HRC) Spindle Speed (rpm) | Heat Resistive Steel, Titanium Alloy (20 to 45HRC) Feed Rate (mm/min) |
|---|---|---|---|---|---|---|---|---|---|---|---|
| 2,0 | | 9.000 | 720 | 6.000 | 430 | 4.000 | 320 | 5.500 | 320 | 2.600 | 120 |
| 4,0 | | 6.600 | 800 | 4.500 | 450 | 3.000 | 380 | 4.000 | 320 | 2.000 | 120 |
| 6,0 | | 4.800 | 960 | 3.000 | 480 | 2.500 | 380 | 3.000 | 480 | 1.200 | 120 |
| 8,0 | | 3.600 | 1.000 | 2.200 | 610 | 2.000 | 400 | 2.000 | 520 | 1.000 | 140 |
| 10,0 | | 2.800 | 1.000 | 1.800 | 610 | 1.500 | 400 | 1.700 | 550 | 800 | 160 |
| 12,0 | | 2.400 | 950 | 1.500 | 550 | 1.200 | 380 | 1.500 | 500 | 700 | 140 |
| 14,0 | | 2.200 | 880 | 1.300 | 490 | 1.000 | 360 | 1.200 | 430 | 600 | 130 |
| 16,0 | | 1.800 | 650 | 1.100 | 420 | 800 | 300 | 1.000 | 360 | 500 | 120 |
| 18,0 | | 1.600 | 580 | 1.000 | 360 | 750 | 270 | 900 | 340 | 450 | 110 |
| 20,0 | | 1.400 | 500 | 900 | 330 | 700 | 250 | 820 | 300 | 400 | 100 |
| Shoulder cutting | $a_p$ | 1,5 DC | | | | | | | | | |
| | $a_e$ | 0,1 DC | | | | 0,05 DC | | 0,1 DC | | 0,05 DC | |
| Grooving | $a_p$ | 1,0 DC | | | | 0,2 DC | | 0,3 DC | | 0,2 DC | |

## ■ Corner Radius Selection

| DC | RE0,2 | RE0,3 | RE0,5 | RE1,0 | RE1,5 | RE2,0 | RE3,0 |
|---|---|---|---|---|---|---|---|
| 3 | ❑ | | ❑ | | | | |
| 4 | ❑ | | ❑ | ❑ | | | |
| 5 | ❑ | | ❑ | ❑ | | | |
| 6 | | ❑ | ❑ | ❑ | ❑ | | |
| 8 | | ❑ | ❑ | ❑ | ❑ | ❑ | |
| 10 | | ❑ | ❑ | ❑ | ❑ | ❑ | |
| 12 | | | ❑ | ❑ | ❑ | ❑ | ❑ |
| 16 | | | | ❑ | ❑ | ❑ | ❑ |
| 20 | | | | ❑ | ❑ | ❑ | ❑ |
| 25 | | | | ❑ | ❑ | ❑ | ❑ |

# EPMS Series


New



## Features

- Solid endmill EPMS-Series (**E**x **P**ress **M**ill S) for high-performance milling applications
- Higher efficiency and tool life due to new technology of latest developed carbide substrate and coating combined with the new optimized tool design
- Available with 4/5/6 flutes, different diameters and edge radii
- Excellent performance in machining of exotic alloys like Ti-alloys, super alloys and heat resistant steels
- Suitable for Titanium structure parts for airplane
- Anti-vibration design for reliable and efficient machining in a wide application range


## Anti-Vibration Design




**Irregular Pitch** + **Irregular Lead**

Reduce the vibration dramatically, especially for poor clamping and thin wall geometry, increase the parts accuracy and tool life for customers

## Optimized Flute Geometry





Smooth chip evacuation is realized to ensure stable and safe milling process for customers.

## Comparison with other Milling Cutters

| Description | Coating | Diameter | Peripheral Rake | Peripheral Relief | Helix Angle | Core Diameter | No. Edge | Radius Tolerance |
|---|---|---|---|---|---|---|---|---|
| GSXVL4000-R | GXS (TiAlCrN) | 1–25 | 3–5 | 16 | 40/43 | 0,6D | 4 | -0,01/0,01 |
| SSEHVL4000-R | GS Hard (TiAlCrSiCN) | 4,5–25 | 5–7 | 17 | 42/45 | 0,65D | 5 | -0,01/0,01 |
| EPMS4000-R | TiAlSiN | 10–26 | 5–7 | 14 | 42/45 | 0,7D | 6 | -0,01/0,01 |

## Suitable Applications




Side Milling | Slotting | Trochoidal Milling | Face Milling | Helical Milling | Ramping | Profiling

## Body

### EPMS 4000 Type








| Cat. No. | Stock | DC | RE | APMX | LU | DN | LF | DMM |
|---|---|---|---|---|---|---|---|---|
| EPMS 4100U2.5R10 | ● | 10 | 1,0 | 25 | 32 | 9,5 | 72 | 10 |
| 4100U2.5R30 | ● | 10 | 3,0 | 25 | 32 | 9,5 | 72 | 10 |
| EPMS 4120U2.5R10 | ● | 12 | 1,0 | 30 | 38 | 11,5 | 83 | 12 |
| 4120U2.5R30 | ● | 12 | 3,0 | 30 | 38 | 11,5 | 83 | 12 |
| 4120U2.5R40 | ● | 12 | 4,0 | 30 | 38 | 11,5 | 83 | 12 |
| EPMS 4160U2.5R30 | ● | 16 | 3,0 | 40 | 50 | 15,5 | 100 | 16 |
| 4160U2.5R40 | ● | 16 | 4,0 | 40 | 50 | 15,5 | 100 | 16 |

Grade: ECS300

### EPMS 5000 Type








| Cat. No. | Stock | DC | RE | APMX | LU | DN | LF | DMM |
|---|---|---|---|---|---|---|---|---|
| EPMS 5100U2.5R025 | ● | 10 | 0,25 | 25 | 32 | 9,5 | 72 | 10 |
| 5100U2.5R15 | ● | 10 | 1,5 | 25 | 32 | 9,5 | 72 | 10 |
| 5100U2.5R25 | ● | 10 | 2,5 | 25 | 32 | 9,5 | 72 | 10 |
| EPMS 5120U2.5R025 | ● | 12 | 0,25 | 30 | 38 | 11,5 | 83 | 12 |
| 5120U2.5R05 | ● | 12 | 0,5 | 30 | 38 | 11,5 | 83 | 12 |
| 5120U2.5R15 | ● | 12 | 1,5 | 30 | 38 | 11,5 | 83 | 12 |
| 5120U2.5R20 | ● | 12 | 2,0 | 30 | 38 | 11,5 | 83 | 12 |
| 5120U2.5R25 | ● | 12 | 2,5 | 30 | 38 | 11,5 | 83 | 12 |
| EPMS 5160U2.5R30 | ● | 16 | 3,0 | 40 | 50 | 15,5 | 100 | 16 |
| 5160U2.5R40 | ● | 16 | 4,0 | 40 | 50 | 15,5 | 100 | 16 |
| EPMS 5200U2.5R30 | ● | 20 | 3,0 | 50 | 62 | 19,5 | 125 | 20 |
| 5200U2.5R40 | ● | 20 | 4,0 | 50 | 62 | 19,5 | 125 | 20 |

Grade: ECS300

### EPMS 6000 Type




| Cat. No. | Stock | DC | RE | APMX | LU | DN | LF | DMM |
|---|---|---|---|---|---|---|---|---|
| EPMS 6100U2.5R10 | ● | 10 | 1,0 | 25 | 32 | 9,5 | 72 | 10 |
| 6100U2.5R30 | ● | 10 | 3,0 | 25 | 32 | 9,5 | 72 | 10 |
| EPMS 6120U2.5R10 | ● | 12 | 1,0 | 30 | 38 | 11,5 | 83 | 12 |
| 6120U2.5R30 | ● | 12 | 3,0 | 30 | 38 | 11,5 | 83 | 12 |
| 6120U2.5R40 | ● | 12 | 4,0 | 30 | 38 | 11,5 | 83 | 12 |
| EPMS 6160U2.5R15 | ● | 16 | 1,5 | 40 | 50 | 15,5 | 100 | 16 |
| 6160U2.5R30 | ● | 16 | 3,0 | 40 | 50 | 15,5 | 100 | 16 |
| 6160U2.5R40 | ● | 16 | 4,0 | 40 | 50 | 15,5 | 100 | 16 |
| EPMS 6200U2.5R30 | ● | 20 | 3,0 | 50 | 62 | 19,5 | 125 | 20 |
| 6200U2.5R40 | ● | 20 | 4,0 | 50 | 62 | 19,5 | 125 | 20 |

Grade: ECS300

## Cutting Conditions

### Side Milling

| Work Material | Titanum Alloy, Stainless Steel | | | |
|---|---|---|---|---|
| Cond. / DC (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | | |
| | | EPMS4000 | EPMS5000 | EPMS6000 |
| 10,0 | 3.200 | 1.280 | 1.920 | 3.840 |
| 12,0 | 2.700 | 1.080 | 1.620 | 3.240 |
| 16,0 | 2.000 | 800 | 1.200 | 2.400 |
| 20,0 | 1.600 | 640 | 960 | 1.920 |
| $a_e$ (mm), **Standard**–Max. | | **0,2**–0,4 DC | **0,1**–0,3 DC | **0,06**–0,1 DC |
| $a_p$ (mm), **Standard**–Max. | | **2,0**–2,5 DC | | |

| Work Material | Heat-resistant Alloy | | | |
|---|---|---|---|---|
| Cond. / DC (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | | |
| | | EPMS4000 | EPMS5000 | EPMS6000 |
| 10,0 | 1.600 | 380 | 640 | 960 |
| 12,0 | 1.300 | 310 | 520 | 780 |
| 16,0 | 1.000 | 240 | 400 | 600 |
| 20,0 | 800 | 190 | 320 | 480 |
| $a_e$ (mm), **Standard**–Max. | | **0,2**–0,4 DC | **0,1**–0,3 DC | **0,06**–0,1 DC |
| $a_p$ (mm), **Standard**–Max. | | **2,0**–2,5 DC | | |

### Slotting


| Work Material | Titanum Alloy, Stainless Steel | | | |
|---|---|---|---|---|
| Cond. / DC (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | | |
| | | EPMS4000 | EPMS5000 | EPMS6000 |
| 10,0 | 1.900 | 460 | 570 | Not recommended |
| 12,0 | 1.600 | 380 | 480 | |
| 16,0 | 1.200 | 290 | 360 | |
| 20,0 | 960 | 230 | 290 | |
| $a_p$ (mm), **Standard**–Max. | | **1,0**–1,5 DC | **0,5**–1,0 DC | |

| Work Material | Heat-resistant Alloy | | | |
|---|---|---|---|---|
| Cond. / DC (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | | |
| | | EPMS4000 | EPMS5000 | EPMS6000 |
| 10,0 | 960 | 230 | 290 | Not recommended |
| 12,0 | 800 | 190 | 240 | |
| 16,0 | 600 | 140 | 180 | |
| 20,0 | 480 | 120 | 140 | |
| $a_p$ (mm), **Standard**–Max. | | **0,3**–0,5 DC | **0,2**–0,4 DC | |


### Ramping / Helical Milling

| Body Type | EPMS4000 | EPMS5000 | EPMS6000 |
|---|---|---|---|
| RPMX, **Standard**–Max. | | **2,0°**–3,0° | |


Side Milling




Slotting




Ramping




## Identification Details

| EPMS | 4 | 100 | U2.5 | | R10 | CS300 |
|---|---|---|---|---|---|---|
| Series Code | Number of Teeth | Diameter | Neck Type<br>U: Under Neck<br>S: Straight+LxD | Other Options*<br>W: Weldon<br>B: Chip Breaker | Corner Radius<br>R10: = 1 mm<br>C: Chamfer | Grade |

* On request

# SSEH Series




## SSEH Radius

### ■ Characteristics and Applications

- Steep helix (45° helix) improves sharpness.
- Combination of unique flute design and semi-mirrored surface improves chip evacuation and adhesion resistance.
- Ultra-smooth coating with improved hardness and heat resistance combined with tough carbide substrate improves tool life when working with heat resistant alloys.
- Unique, smooth radius shape mitigates cutting impact and improves fracture resistance.
- Both coated and uncoated types are available in stock to meet various conditions.

### ■ Application Examples


- Inconel 718 (Side Milling)




Tool Diameter: ø 6 × R1
Cutting Conditions: $v_c$ = 20 m/min, $f_z$ = 0,025 mm/t, $a_p$ = 5 mm, $a_e$ = 0,5 mm, wet


- Inconel 713 (Side Milling)


| SSEH 4100W-R10 | Competitor's Product |
|---|---|
|  |  |




Tool Diameter : ø 10 x R1
Cutting Conditions : $v_c$= 32 m/min, $f_z$ = 0,018 mm/t
$a_p$ = 20 mm, $a_e$ = 0,8 m, Dry

In Sumitomo Electric Hardmetal tests, the special coating with excellent adhesion resistance provided less cutting edge adhesion than the competitor's product and enabled fracturefree machining.
The competitor's product suffered from edge adhesion leading to breakage.







## SSEH Radius Anti-vibration Type

### ■ Characteristics and Applications

- New anti-vibration type added to the SSEH type endmill for exotic alloys.
- Builds on the same features of existing endmills by adding an irregular lead for exceptionally good anti-vibration performance.
- Compatible with wide range of milling for exotic alloys including SUS, Inconel, and titanium.
- Reduces chattering for high-speed, high-feed cutting.
- Both coated and uncoated types are available in stock to meet various conditions.

Irregular Pitch + Irregular Lead





### ■ Application Examples

- Surface Roughness Comparison


**SSEH** Anti-vibration Type




Good Surface Quality
Ra 0,37 µm Rz 1,86 µm



Conventional Tool



Surface shows chattering
Ra 1,52 µm Rz 6,45 µm



Work Material: X5CrNi1810 (Surface Milling)
Tool Diameter: ø 12 mm
Cutting Conditions: n = 1.300 rpm, $v_f$ = 300 mm/min
$a_p$ = 18 mm, $a_e$ = 1,2 mm
Equipment: BT50






● = Euro stock
❍ = Japan stock
❑ = Delivery on request

# Anti-Vibration MILL with R. Corner

# SSEHVL 4000W-R Type

Coated Carbide Grades | GS HARD Coating

| Structual Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ○ | ○ | ○ | ○ | ○ | | | | ◎ | ◎ | | | | |




Grade: ACW52

## SAFE-λOCK™

Applicable Endmills





## ■ Endmills

(mm)

| Cat. No. | Stock | DC | RE | LU | LF | DMM |
|---|---|---|---|---|---|---|
| SSEHVL 4045W-R05 | ● | 4,5 | 0,5 | 12 | 50 | 6 |
| SSEHVL 4045W-R10 | ❍ | 4,5 | 1,0 | 12 | 50 | 6 |
| SSEHVL 4050W-R05 | | 5,0 | 0,5 | 13 | 60 | 6 |
| SSEHVL 4050W-R10 | ● | 5,0 | 1,0 | 13 | 60 | 6 |
| SSEHVL 4060W-R10 | ❍ | 6,0 | 1,0 | 13 | 60 | 6 |
| SSEHVL 4080W-R10 | ● | 8,0 | 1,0 | 19 | 80 | 8 |
| SSEHVL 4100W-R10 | ● | 10,0 | 1,0 | 22 | 90 | 10 |
| SSEHVL 4100W-R30 | ● | 10,0 | 3,0 | 22 | 90 | 10 |
| SSEHVL 4120W-R10 | ● | 12,0 | 1,0 | 26 | 90 | 12 |
| SSEHVL 4120W-R30 | ● | 12,0 | 3,0 | 26 | 90 | 12 |
| SSEHVL 4160W-R10 | ● | 16,0 | 1,0 | 32 | 115 | 16 |
| SSEHVL 4160W-R30 | ● | 16,0 | 3,0 | 32 | 115 | 16 |
| SSEHVL 4200W-R10 | | 20,0 | 1,0 | 40 | 125 | 20 |
| SSEHVL 4200W-R30 | ❍ | 20,0 | 3,0 | 40 | 125 | 20 |
| SSEHVL 4250W-R10 | | 25,0 | 1,0 | 50 | 140 | 25 |
| SSEHVL 4250W-R30 | ❍ | 25,0 | 3,0 | 50 | 140 | 25 |

## ■ Endmills

(mm)


| Cat. No. | Stock | DC | RE | LU | LF | DMM |
|---|---|---|---|---|---|---|
| SSEHVL 4120WS-R10 | ❑ | 12,0 | 1,0 | 26 | 90 | 12 |
| SSEHVL 4120WS-R30 | ❑ | 12,0 | 3,0 | 26 | 90 | 12 |
| SSEHVL 4160WS-R10 | ❑ | 16,0 | 1,0 | 32 | 115 | 16 |
| SSEHVL 4160WS-R30 | ❑ | 16,0 | 3,0 | 32 | 115 | 16 |
| SSEHVL 4200WS-R10 | ❑ | 20,0 | 1,0 | 40 | 125 | 20 |
| SSEHVL 4200WS-R30 | ❑ | 20,0 | 3,0 | 40 | 125 | 20 |
| SSEHVL 4250WS-R10 | ❑ | 25,0 | 1,0 | 50 | 140 | 25 |
| SSEHVL 4250WS-R30 | ❑ | 25,0 | 3,0 | 50 | 140 | 25 |

## ■ Diameter and Corner Radius Selection Range

| DC | RE0,5 | RE1,0 | RE3,0 |
|---|---|---|---|
| 4,5 | ● | ❍ | |
| 5 | | ● | |
| 6 | | ❍ | |
| 8 | | ● | |
| 10 | | ● | ● |
| 12 | | ● | ● |
| 16 | | ● | ● |
| 20 | | | ❑ |
| 25 | | | ❑ |

## ■ Recommended Cutting Conditions

1. For stable machining, a more rigid machine is recommended.
2. Wet machining is recommended for stainless steel and heat resistant alloy applications.
3. If cutting noise and vibration are present, please change the cutting conditions accordingly.




### ● Shoulder Milling

| Work Material / Cond. | | Stainless Steel | | Titanium Alloy | | Heat Resistive Steel | |
|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 4,5 | | 3.500 | 350 | 3.500 | 280 | 2.100 | 170 |
| 5,0 | | 3.200 | 380 | 3.200 | 320 | 1.900 | 190 |
| 6,0 | | 2.700 | 430 | 2.700 | 320 | 1.600 | 190 |
| 8,0 | | 2.000 | 400 | 2.000 | 280 | 1.200 | 170 |
| 10,0 | | 1.600 | 380 | 1.600 | 260 | 1.000 | 160 |
| 12,0 | | 1.300 | 360 | 1.300 | 230 | 800 | 140 |
| 16,0 | | 1.000 | 320 | 1.000 | 200 | 600 | 120 |
| 20,0 | | 800 | 260 | 800 | 160 | 480 | 100 |
| 25,0 | | 640 | 200 | 640 | 130 | 380 | 80 |
| Shoulder cutting | $a_p$ | 1,5 DC | | | | | |
| | $a_e$ | 0,1 DC | | 0,05 DC | | 0,05 DC | |


### ● Grooving

| Work Material / Cond. | | Stainless Steel | | Titanium Alloy | | Heat Resistive Steel | |
|---|---|---|---|---|---|---|---|
| DC(mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 4,5 | | 4,200 | 200 | 3,900 | 270 | 1,400 | 100 |
| 5,0 | | 3,800 | 240 | 3,500 | 300 | 1,300 | 120 |
| 6,0 | | 3,200 | 260 | 2,900 | 300 | 1,100 | 140 |
| 8,0 | | 2,400 | 240 | 2,200 | 270 | 800 | 120 |
| 10,0 | | 1,900 | 220 | 1,700 | 250 | 650 | 110 |
| 12,0 | | 1,600 | 200 | 1,400 | 230 | 550 | 100 |
| 16,0 | | 1,200 | 130 | 1,100 | 200 | 400 | 80 |
| 20,0 | | 950 | 95 | 890 | 90 | 320 | 60 |
| 25,0 | | 760 | 75 | 700 | 70 | 250 | 50 |
| Grooving | $a_p$ | 0,3 DC | | 0,2 DC | | 0,15 DC | |

# SSEH 4000W-R Type

4 Flutes Endmills with Radius Corner and HAIMER's SAFE-LOCK™ Applicable Endmills

| Coated Carbide Grades | GS HARD Coating | Structual Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | ○ | ○ | ○ | ○ | ○ | | | | ◎ | ◎ | | | | |





Grade: ACW52

## SAFE-LOCK™

Applicable Endmills





## ■ Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| SSEH 4045W-R05 | | 4,5 | 0,5 | 12 | 50 | 6 |
| SSEH 4050W-R05 | ❍ | 5,0 | 0,5 | 13 | 60 | 6 |
| SSEH 4060W-R10 | ● | 6,0 | 1,0 | 13 | 60 | 6 |
| SSEH 4080W-R10 | ● | 8,0 | 1,0 | 19 | 80 | 8 |
| SSEH 4100W-R10 | ● | 10,0 | 1,0 | 22 | 90 | 10 |
| SSEH 4100W-R30 | ❍ | 10,0 | 3,0 | 22 | 90 | 10 |
| SSEH 4120W-R10 | ● | 12,0 | 1,0 | 26 | 90 | 12 |
| SSEH 4120W-R30 | | 12,0 | 3,0 | 26 | 90 | 12 |
| SSEH 4160W-R10 | ● | 16,0 | 1,0 | 32 | 115 | 16 |
| SSEH 4160W-R30 | | 16,0 | 3,0 | 32 | 115 | 16 |
| SSEH 4200W-R10 | ❍ | 20,0 | 1,0 | 40 | 125 | 20 |
| SSEH 4200W-R30 | ❍ | 20,0 | 3,0 | 40 | 125 | 20 |
| SSEH 4250W-R10 | | 25,0 | 1,0 | 50 | 140 | 25 |
| SSEH 4250W-R30 | ❍ | 25,0 | 3,0 | 50 | 140 | 25 |


## ■ Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| SSEH 4120WS-R10 | ❑ | 12,0 | 1,0 | 26 | 90 | 12 |
| SSEH 4120WS-R30 | ❑ | 12,0 | 3,0 | 26 | 90 | 12 |
| SSEH 4160WS-R10 | ❑ | 16,0 | 1,0 | 32 | 115 | 16 |
| SSEH 4160WS-R30 | ❑ | 16,0 | 3,0 | 32 | 115 | 16 |
| SSEH 4200WS-R10 | ❑ | 20,0 | 1,0 | 40 | 125 | 20 |
| SSEH 4200WS-R30 | ❑ | 20,0 | 3,0 | 40 | 125 | 20 |
| SSEH 4250WS-R10 | ❑ | 25,0 | 1,0 | 50 | 140 | 25 |
| SSEH 4250WS-R30 | ❑ | 25,0 | 3,0 | 50 | 140 | 25 |

## ■ Diameter and Corner Radius Selection Range

| DC | RE0,5 | RE1,0 | RE3,0 |
|---|---|---|---|
| 4,5 | | | |
| 5 | ❍ | | |
| 6 | | ● | |
| 8 | | ● | |
| 10 | | ● | ❍ |
| 12 | | ● | |
| 16 | | ● | |
| 20 | | ❍ | ❍ |
| 25 | | | ❍ |




## ■ Recommended Cutting Conditions

1. For stable machining, a more rigid machine is recommended.
2. Wet machining is recommended for stainless steel and heat resistant alloy applications.
3. If cutting noise and vibration are present, please change the cutting conditions accordingly.

### ● Shoulder Milling

| Work Material / Cond. | | Stainless Steel | | Titanium Alloy | | Heat Resistive Steel | |
|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 4,5 | | 3.500 | 350 | 3.500 | 280 | 2.100 | 170 |
| 5,0 | | 3.200 | 380 | 3.200 | 320 | 1.900 | 190 |
| 6,0 | | 2.700 | 430 | 2.700 | 320 | 1.600 | 190 |
| 8,0 | | 2.000 | 400 | 2.000 | 280 | 1.200 | 170 |
| 10,0 | | 1.600 | 380 | 1.600 | 260 | 1.000 | 160 |
| 12,0 | | 1.300 | 360 | 1.300 | 230 | 800 | 140 |
| 16,0 | | 1.000 | 320 | 1.000 | 200 | 600 | 120 |
| 20,0 | | 800 | 260 | 800 | 160 | 480 | 100 |
| 25,0 | | 640 | 200 | 640 | 130 | 380 | 80 |
| Shoulder cutting | ap | 1,5 DC | | | | | |
| | ae | 0,1 DC | | 0,05 DC | | 0,05 DC | |

### ● Grooving

| Work Material / Cond. | | Stainless Steel | | Titanium Alloy | | Heat Resistive Steel | |
|---|---|---|---|---|---|---|---|
| DC (mm) | | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) | Spindle Speed (rpm) | Feed Rate (mm/min) |
| 4,5 | | 4,200 | 200 | 3,900 | 270 | 1,400 | 100 |
| 5,0 | | 3,800 | 240 | 3,500 | 300 | 1,300 | 120 |
| 6,0 | | 3,200 | 260 | 2,900 | 300 | 1,100 | 140 |
| 8,0 | | 2,400 | 240 | 2,200 | 270 | 800 | 120 |
| 10,0 | | 1,900 | 220 | 1,700 | 250 | 650 | 110 |
| 12,0 | | 1,600 | 200 | 1,400 | 230 | 550 | 100 |
| 16,0 | | 1,200 | 130 | 1,100 | 200 | 400 | 80 |
| 20,0 | | 950 | 95 | 890 | 90 | 320 | 60 |
| 25,0 | | 760 | 75 | 700 | 70 | 250 | 50 |
| Grooving | ap | 0,3 DC | | 0,2 DC | | 0,15 DC | |






● = Euro stock
❍ = Japan stock
❑ = Delivery on request

# GS MILL Series
# GSRE 4000SF Type

Coated carbide grade: **ACZ20W**




Helix angle : 40°

4



## Endmills


(mm)

| Cat. No. | Stock | DC | APMX | LF | CHW | DMM |
|---|---|---|---|---|---|---|
| GSRE 4060 SF | ● | 6,0 | 13 | 50 | 0,3 | 6 |
| 4070 SF | ● | 7,0 | 16 | 60 | 0,3 | 8 |
| 4080 SF | ● | 8,0 | 19 | 60 | 0,4 | 8 |
| 4090 SF | ● | 9,0 | 19 | 70 | 0,4 | 10 |
| 4100 SF | ● | 10,0 | 22 | 70 | 0,5 | 10 |
| GSRE 4110 SF | ● | 11,0 | 22 | 75 | 0,5 | 12 |
| 4120 SF | ● | 12,0 | 26 | 75 | 0,6 | 12 |
| 4140 SF | ● | 14,0 | 26 | 90 | 0,6 | 16 |
| 4160 SF | ● | 16,0 | 32 | 90 | 0,8 | 16 |
| 4180 SF | ● | 18,0 | 32 | 100 | 0,8 | 20 |
| GSRE 4200 SF | ● | 20,0 | 38 | 100 | 1,0 | 20 |

Recommended :

(1) Cutting performance is improved when using a high rigidity machine.


(2) Speeds and feeds should be reduced when there is any excessive vibration or strange noise during the operation.




## Recommended Cutting Conditions

### ● Shoulder cutting


| Material / Cutting data / Tool Dia. (mm) | Carbon steel ( HB150–250) Speed (rpm) | Carbon steel Feed (mm/min) | Cast iron Speed (rpm) | Cast iron Feed (mm/min) | Alloy steel, Prehardened steel (HRC25–35) Speed (rpm) | Alloy steel, Prehardened steel Feed (mm/min) | Hardened steel (HRC40–50) Speed (rpm) | Hardened steel Feed (mm/min) | Stainless steel Speed (rpm) | Stainless steel Feed (mm/min) | Heat resistant alloys Titanium alloy Speed (rpm) | Heat resistant alloys Titanium alloy Feed (mm/min) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | 4.800 | 1.200 | 5.800 | 1.500 | 3.200 | 380 | 2.600 | 400 | 4.300 | 250 | 1.600 | 90 |
| 2 | 4.100 | 1.200 | 5.000 | 1.500 | 2.700 | 380 | 2.200 | 400 | 4.500 | 250 | 1.350 | 90 |
| 3 | 3.600 | 1.200 | 4.500 | 1.500 | 2.400 | 380 | 2.000 | 400 | 4.000 | 250 | 1.250 | 90 |
| 4 | 3.200 | 1.200 | 4.000 | 1.500 | 2.100 | 380 | 1.800 | 400 | 3.500 | 250 | 1.050 | 90 |
| 5 | 2.800 | 1.200 | 2.500 | 1.500 | 1.900 | 380 | 1.600 | 400 | 3.200 | 250 | 1.000 | 100 |
| 6 | 2.600 | 1.200 | 3.000 | 1.400 | 1.700 | 380 | 1.500 | 400 | 2.900 | 250 | 900 | 100 |
| 8 | 2.400 | 1.200 | 2.900 | 1.400 | 1.600 | 400 | 1.300 | 400 | 2.600 | 250 | 800 | 100 |
| 10 | 2.200 | 1.100 | 2.600 | 1.300 | 1.300 | 380 | 1.100 | 350 | 2.200 | 200 | 700 | 100 |
| 12 | 1.800 | 900 | 2.200 | 1.100 | 1.200 | 380 | 1.000 | 350 | 2.000 | 180 | 600 | 100 |
| 16 | 1.400 | 700 | 1.800 | 900 | 1.000 | 380 | 900 | 350 | 1.800 | 150 | 550 | 100 |
| 20 | 1.400 | 700 | 1.700 | 800 | 850 | 380 | 800 | 350 | 1.600 | 150 | 500 | 100 |
| Shoulder cutting $a_p$ | | | 1,5 DC | | | | | | 1,5 DC | | | |
| Shoulder cutting $a_e$ | | | 0,5 DC | | | | | | 0,3 DC | | | |




### ● Slotting

| Material / Cutting data / Tool Dia. (mm) | Carbon steel ( HB150–250) Speed (rpm) | Carbon steel Feed (mm/min) | Cast iron Speed (rpm) | Cast iron Feed (mm/min) | Alloy steel, Prehardened steel (HRC25–35) Speed (rpm) | Alloy steel, Prehardened steel Feed (mm/min) | Hardened steel (HRC40–50) Speed (rpm) | Hardened steel Feed (mm/min) | Stainless steel Speed (rpm) | Stainless steel Feed (mm/min) | Heat resistant alloys Titanium alloy Speed (rpm) | Heat resistant alloys Titanium alloy Feed (mm/min) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | 3.600 | 900 | 4.300 | 1.100 | 2.400 | 300 | 1.700 | 260 | 4.200 | 250 | 1.100 | 60 |
| 2 | 3.000 | 900 | 3.700 | 1.100 | 2.000 | 280 | 1.500 | 260 | 3.600 | 250 | 900 | 60 |
| 3 | 2.700 | 900 | 3.400 | 1.100 | 1.800 | 280 | 1.350 | 260 | 3.200 | 250 | 800 | 60 |
| 4 | 2.400 | 900 | 3.000 | 1.100 | 1.600 | 280 | 1.200 | 260 | 2.800 | 250 | 700 | 60 |
| 5 | 2.100 | 900 | 2.600 | 1.100 | 1.400 | 280 | 1.100 | 270 | 2.500 | 250 | 650 | 65 |
| 6 | 2.000 | 900 | 2.300 | 1.100 | 1.300 | 280 | 1.000 | 270 | 2.300 | 250 | 600 | 70 |
| 8 | 1.800 | 900 | 2.200 | 1.100 | 1.200 | 300 | 900 | 270 | 2.100 | 250 | 550 | 70 |
| 10 | 1.600 | 800 | 2.000 | 1.100 | 1.000 | 290 | 750 | 240 | 1.800 | 180 | 450 | 65 |
| 12 | 1.350 | 650 | 1.650 | 850 | 900 | 280 | 700 | 240 | 1.600 | 160 | 400 | 65 |
| 16 | 1.200 | 550 | 1.500 | 750 | 800 | 280 | 600 | 230 | 1.400 | 140 | 350 | 60 |
| 20 | 1.050 | 500 | 1.350 | 700 | 700 | 280 | 550 | 210 | 1.250 | 125 | 300 | 60 |
| Slotting $a_p$ | | | 1,0 DC | | | | | | 0,5 DC | | | |

Coated carbide grade: **ACF07C**




Helix angle : 50˚
Corner : Edge with honing

| DC | Tolerance (mm) |
|---|---|
| D ≤ 3,0 | 0 – - 0,015 |
| 3,0 < D | 0 – - 0,030 |



## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| GSH 4010 SF | ● | 1,0 | 3 | 50 | 6 |
| 4015 SF | ● | 1,5 | 4 | 50 | 6 |
| 4020 SF | ● | 2,0 | 6 | 50 | 6 |
| GSH 6030 SF | ● | 3,0 | 8 | 50 | 6 |
| 6040 SF | ● | 4,0 | 11 | 50 | 6 |
| 6050 SF | ● | 5,0 | 12 | 50 | 6 |
| 6060 SF | ● | 6,0 | 13 | 50 | 6 |
| 6080 SF | ● | 8,0 | 19 | 60 | 8 |
| 6100 SF | ● | 10,0 | 22 | 70 | 10 |
| 6120 SF | ● | 12,0 | 26 | 75 | 12 |
| GSH 8160 SF | ● | 16,0 | 32 | 90 | 16 |
| 8200 SF | ● | 20,0 | 38 | 100 | 20 |

Recommended :

(1) Cutting performance is improved when using a high rigidity machine.

(2) Speeds and feeds should be reduced when there is any excessive vibration or strange noise during the operation.


## Recommended Cutting Conditions

### ● Conventional Milling Operations

| Material / Cutting data / Tool Dia. (mm) | Alloy steel, Prehardened steel (–HRC35) | | Heat treated alloy steel, hardened steel (HRC35–45) | | Hardened steel (HRC45–55) | | Hardened steel (HRC55–60) | | Hardened steel (HRC60–65) | | Hardened steel (HRC65– ) | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) |
| 1 | 20.000 | 540 | 20.000 | 390 | 15.600 | 260 | 12.300 | 160 | 11.100 | 140 | 7.800 | 95 |
| 2 | 19.000 | 1.100 | 17.200 | 770 | 13.400 | 530 | 10.500 | 320 | 9.500 | 270 | 6.700 | 190 |
| 3 | 15.000 | 2.150 | 13.400 | 1.540 | 10.400 | 1.050 | 8.200 | 650 | 7.400 | 540 | 5.200 | 380 |
| 4 | 11.200 | 2.400 | 10.000 | 1.740 | 7.800 | 1.180 | 6.100 | 730 | 5.600 | 600 | 3.900 | 420 |
| 5 | 9.000 | 2.700 | 8.000 | 1.930 | 6.200 | 1.300 | 4.900 | 810 | 4.400 | 670 | 3.100 | 470 |
| 6 | 7.500 | 2.700 | 6.700 | 1.930 | 5.200 | 1.300 | 4.100 | 810 | 3.700 | 670 | 2.600 | 470 |
| 8 | 5.600 | 2.700 | 5.000 | 1.930 | 3.900 | 1.300 | 3.050 | 810 | 2.800 | 670 | 1.950 | 470 |
| 10 | 4.500 | 2.700 | 4.000 | 1.930 | 3.100 | 1.300 | 2.450 | 810 | 2.200 | 670 | 1.550 | 470 |
| 12 | 3.750 | 2.700 | 3.350 | 1.930 | 2.600 | 1.300 | 2.050 | 810 | 1.850 | 670 | 1.300 | 470 |
| 16 | 2.800 | 2.500 | 2.500 | 1.800 | 1.950 | 1.220 | 1.530 | 760 | 1.400 | 630 | 980 | 440 |
| 20 | 2.250 | 2.100 | 2.000 | 1.540 | 1.550 | 1.050 | 1.230 | 650 | 1.100 | 540 | 780 | 380 |
| Shoulder cutting $a_p$ | 1–1,5 DC | | | | 1–1,5 DC | | | | 1–1,5 DC | | | |
| Shoulder cutting $a_e$ | 0,1 DC | | | | 0,05 DC | | | | 0,02 DC | | | |
| Slotting $a_p$ | 0,1 DC | | | | 0,05 DC | | | | –0,05 DC (Max 0,5) | | | |

### ● HSC Machining Centre Operations

| Material / Cutting data / Tool Dia. (mm) | Alloy steel, Prehardened steel (–HRC35) | | Heat treated alloy steel, hardened steel (HRC35–45) | | Hardened steel (HRC45–55) | | Hardened steel (HRC55–60) | | Hardened steel (HRC60–65) | |
|---|---|---|---|---|---|---|---|---|---|---|
| | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) |
| 1 | 48.000 | 1.250 | 48.000 | 1.250 | 48.000 | 1.250 | 48.000 | 930 | 38.000 | 700 |
| 2 | 48.000 | 2.850 | 48.000 | 2.850 | 48.000 | 2.850 | 36.000 | 1.600 | 24.000 | 1.000 |
| 3 | 32.000 | 4.900 | 32.000 | 4.900 | 32.000 | 4.900 | 24.000 | 2.740 | 16.000 | 1.700 |
| 4 | 24.000 | 5.200 | 24.000 | 5.200 | 24.000 | 5.200 | 18.000 | 2.900 | 12.000 | 1.800 |
| 5 | 19.200 | 5.800 | 19.200 | 5.800 | 19.200 | 5.800 | 14.300 | 3.200 | 9.600 | 2.000 |
| 6 | 16.000 | 5.800 | 16.000 | 5.800 | 16.000 | 5.800 | 12.000 | 3.200 | 8.000 | 2.000 |
| 8 | 12.000 | 5.800 | 12.000 | 5.800 | 12.000 | 5.800 | 9.000 | 3.200 | 6.000 | 2.000 |
| 10 | 9.600 | 5.800 | 9.600 | 5.800 | 9.600 | 5.800 | 7.200 | 3.200 | 4.800 | 2.000 |
| 12 | 8.000 | 5.800 | 8.000 | 5.800 | 8.000 | 5.800 | 6.000 | 3.200 | 4.000 | 2.000 |
| 16 | 6.000 | 5.400 | 6.000 | 5.400 | 6.000 | 5.400 | 4.500 | 3.000 | 3.000 | 1.900 |
| 20 | 4.800 | 4.600 | 4.800 | 4.600 | 4.800 | 4.600 | 3.600 | 2.580 | 2.400 | 1.600 |
| Shoulder cutting $a_p$ | 1–1,5 DC | | 1–1,5 DC | | | | 1–1,5 DC | | 1–1,5 DC | |
| Shoulder cutting $a_e$ | 0,1 DC | | 0,05 DC | | | | 0,02 DC | | 0,12 DC | |








● = Euro stock



## Features

Sumitomo Electric's "AURORA" COAT is a high hardness, low coefficient layer of "Diamond Like Carbon" (DLC).

Other than producing excellent surface finish for machining of Aluminium and non-ferrous metals, DLC coat can be used for dry cutting and is environmental friendly.


## Characteristics / Application

- Very smooth AURORA COAT results in low adhesion as well as good surface finish
- With lower cutting forces and high rigidity, this series is suitable for low rigidity machine
- Available in 2 and 4 flutes square type as well as ballnose type endmills


## Product Range

| Series | No. of teeth | Shape | Diameter |
|---|---|---|---|
| ASM2000DL | 2 | Square  | ø 2 – ø 16 |
| ASM4000DL | 4 | Square  | ø 2 – ø 16 |
| SNB2000DL | 2 | Ballnose  | ø 2 – ø 16 (R1 – R8) |

## Efficiency




### Performance Comparison




Work Material: A5052
Tool: ASM4100DL, ø 10 mm 4 teeth
Cutting Conditions: $v_c$ = 200 m/min, n = 6,300 rpm, $v_f$ = 1300 mm/min
$f_z$ = 0,05 mm/tooth, $a_p$ = 10 mm, $a_e$ = 1,0 mm
Down Cut

### Surface Finish Comparison





Work Material: A5052
Tool: ASM4100DL, ø 10 mm 4 teeth
Cutting Conditions: $v_c$ = 200 m/min, n = 6,300 rpm, $v_f$ = 1300 mm/min
$f_z$ = 0,05 mm/tooth, $a_p$ = 10 mm, $a_e$ = 1,0 mm
Down Cut

# AURORA Coated Spiral Endmills
# ASM 2000/4000 DL Type

2 4

DLC coated carbide grade: DL1000




## Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| ASM 2020 DL | ● | 2,0 | 6 | 40 | 4 |
| 2030 DL | ● | 3,0 | 10 | 45 | 6 |
| 2040 DL | ● | 4,0 | 12 | 45 | 6 |
| 2050 DL | ● | 5,0 | 15 | 50 | 6 |
| ASM 2060 DL | ● | 6,0 | 15 | 50 | 6 |
| 2080 DL | ● | 8,0 | 18 | 60 | 8 |
| 2100 DL | ● | 10,0 | 22 | 71 | 10 |
| ASM 2120 DL | ● | 12,0 | 25 | 75 | 12 |
| 2160 DL | ● | 16,0 | 32 | 90 | 16 |


| | | | | | |
|---|---|---|---|---|---|
| ASM 4020 DL | ● | 2,0 | 6 | 40 | 4 |
| 4030 DL | ● | 3,0 | 10 | 45 | 6 |
| 4040 DL | ● | 4,0 | 12 | 45 | 6 |
| 4050 DL | ● | 5,0 | 15 | 50 | 6 |
| ASM 4060 DL | ● | 6,0 | 15 | 50 | 6 |
| 4080 DL | ● | 8,0 | 18 | 60 | 8 |
| 4100 DL | ● | 10,0 | 22 | 71 | 10 |
| ASM 4120 DL | ● | 12,0 | 25 | 75 | 12 |
| 4160 DL | ● | 16,0 | 32 | 90 | 16 |

# AURORA Coated Spiral Endmills
# ASM 2000/4000 DL-R Type

With Radius Corner -R

2 4

DLC coated carbide grade: DL1000





## Endmills

(mm)

| Cat. No. | Stock | DC | RE | APMX | LF | DMM |
|---|---|---|---|---|---|---|
| ASM 2080 DL-R10 | ● | 8,0 | 1,0 | 18 | 60 | 8 |
| 2080 DL-R20 | ❑ | 8,0 | 2,0 | 18 | 60 | 8 |
| ASM 2100 DL-R10 | ❑ | 10,0 | 1,0 | 22 | 71 | 10 |
| 2100 DL-R20 | ❑ | 10,0 | 2,0 | 22 | 71 | 10 |
| ASM 2120 DL-R20 | ❑ | 12,0 | 2,0 | 25 | 75 | 12 |
| 2120 DL-R30 | ❑ | 12,0 | 3,0 | 25 | 75 | 12 |
| ASM 2160 DL-R30 | ❑ | 16,0 | 3,0 | 32 | 90 | 16 |

| | | | | | | |
|---|---|---|---|---|---|---|
| ASM 4080 DL-R10 | ❑ | 8,0 | 1,0 | 18 | 60 | 8 |
| 4080 DL-R20 | ❑ | 8,0 | 2,0 | 18 | 60 | 8 |
| ASM 4100 DL-R10 | ● | 10,0 | 1,0 | 22 | 71 | 10 |
| 4100 DL-R20 | ❑ | 10,0 | 2,0 | 22 | 71 | 10 |
| ASM 4120 DL-R20 | ❑ | 12,0 | 2,0 | 25 | 75 | 12 |
| 4120 DL-R30 | ❑ | 12,0 | 3,0 | 25 | 75 | 12 |
| ASM 4160 DL-R30 | ● | 16,0 | 3,0 | 32 | 90 | 16 |






## Recommended Cutting Conditions

Recommended :

(1) Cutting performance is improved when using a high rigidity machine.

(2) Speeds and feeds should be reduced when there is any excessive vibration or strange noise during the operation.

(3) In case of chatter first check the cutting conditions.

| Work Material | | Aluminium Alloy | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| Cutting data / DC (mm) | | Wet (Emulsion) | | | | Dry | | | |
| | | Side Milling (4 teeth) | | Groove Milling (4 teeth) | | Side Milling (4 teeth) | | Groove Milling (4 teeth) | |
| | | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) |
| 2,0 | | 40.000 | 1.400 | 28.000 | 280 | 40.000 | 980 | 28.000 | 200 |
| 3,0 | | 32.000 | 2.000 | 22.000 | 400 | 32.000 | 1.400 | 22.000 | 280 |
| 4,0 | | 26.000 | 2.600 | 18.000 | 520 | 26.000 | 1.800 | 18.000 | 360 |
| 5,0 | | 20.000 | 2.600 | 14.000 | 520 | 20.000 | 1.800 | 14.000 | 360 |
| 6,0 | | 17.000 | 2.700 | 12.000 | 540 | 17.000 | 1.900 | 12.000 | 370 |
| 8,0 | | 13.000 | 2.700 | 9.000 | 540 | 13.000 | 1.900 | 9.000 | 370 |
| 10,0 | | 11.000 | 2.800 | 7.200 | 560 | 11.000 | 2.000 | 7.200 | 390 |
| 12,0 | | 8.500 | 2.800 | 6.000 | 560 | 8.500 | 2.000 | 6.000 | 390 |
| 16,0 | | 6.400 | 2.800 | 4.500 | 560 | 6.400 | 2.000 | 4.500 | 390 |
| Depth and wide of cut | $a_p$ | 1,5 DC | | 1,0 DC | | 1,5 DC | | 0,5 DC | |
| | $a_e$ | 0,2 DC | | (DC) | | 0,2 DC | | (DC) | |




● = Euro stock
❍ = Japan stock
❑ = Delivery on request

# ZX Coated Long Fast Helix Endmills
# LHHM 4000/6000/8000 ZX Type

4 6 8

Coated carbide grade: ACZ10M





Helix angle : 45°
Corner : Edge with honing

| DC | Tolerance (mm) |
|---|---|
| D ≤ 6,0 | – 0,010 – 0,030 |
| 6,0 < D ≤ 10,0 | – 0,015 – 0,040 |
| 10,0 < D | – 0,020 – 0,050 |

## ■ Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| LHHM 4030 ZX | ❍ | 3,0 | 12 | 55 | 6 |
| 4040 ZX | ❍ | 4,0 | 15 | 60 | 6 |
| 4050 ZX | ❍ | 5,0 | 18 | 60 | 6 |
| LHHM 6060 ZX | ❍ | 6,0 | 18 | 60 | 6 |
| 6080 ZX | ❍ | 8,0 | 25 | 75 | 8 |
| 6100 ZX | ❍ | 10,0 | 30 | 80 | 10 |
| 6120 ZX | ❍ | 12,0 | 30 | 100 | 12 |
| LHHM 8160 ZX | ❍ | 16,0 | 50 | 105 | 16 |
| 8200 ZX | ❍ | 20,0 | 55 | 120 | 20 |
| 8250 ZX | ❍ | 25,0 | 65 | 140 | 25 |
| 8300 ZX | ❑ | 30,0 | 75 | 160 | 32 |





## Recommended conditions

(Shoulder processing) $a_p$ = 1,5 x øD

$a_e$ =0,025(HRC56~65) ~ 0,2(below HRC25) x øD

| DC \ Material | | Carbon steel, Alloy steel (BelowHRC25) | Carbon steel, Alloy steel (BelowHRC45) | Hardened steel (BelowHRC65) | Cast iron |
|---|---|---|---|---|---|
| 3,0–5,0 | $v_c$ | 200–**250**–300 | 100–**150**–200 | 80–**100**–120 | 60–**75**–90 |
| | $f_z$ | 0,030–0,060 | 0,022–0,037 | 0,007–0,015 | 0,030–0,060 |
| 6,0–12,0 | $v_c$ | 200–**250**–300 | 100–**150**–200 | 80–**100**–120 | 40–**50**–60 |
| | $f_z$ | 0,061–0,090 | 0,037–0,067 | 0,015–0,028 | 0,060–0,165 |
| 16,0–32,0 | $v_c$ | 200–**250**–300 | 100–**150**–200 | 80–**100**–120 | 40–**50**–60 |
| | $f_z$ | 0,090–0,098 | 0,067–0,075 | 0,028–0,038 | 0,187–0,262 |





$v_c$ = m/min $f_z$ = mm/tooth

# ZX Coated Extra Long Fast Helix Endmills
# EHHM 4000/6000/8000 ZX Type

4 6 8

Coated carbide grade: ACZ10M





Helix angle : 45°
Corner : Edge with honing

| DC | Tolerance (mm) |
|---|---|
| D ≤ 6,0 | – 0,010 – 0,030 |
| 6,0 < D ≤ 10,0 | – 0,015 – 0,040 |
| 10,0 < D | – 0,020 – 0,050 |

## ■ Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| EHHM 4030 ZX | ❍ | 3,0 | 20 | 60 | 6 |
| 4040 ZX | ❍ | 4,0 | 25 | 65 | 6 |
| 4050 ZX | ❍ | 5,0 | 30 | 70 | 6 |
| EHHM 6060 ZX | ❍ | 6,0 | 30 | 70 | 6 |
| 6080 ZX | ❍ | 8,0 | 40 | 90 | 8 |
| 6100 ZX | ❍ | 10,0 | 50 | 100 | 10 |
| 6120 ZX | ❍ | 12,0 | 50 | 120 | 12 |
| EHHM 8160 ZX | ❍ | 16,0 | 70 | 140 | 16 |
| 8200 ZX | ❍ | 20,0 | 85 | 165 | 20 |
| 8250 ZX | ❍ | 25,0 | 100 | 185 | 25 |
| 8300 ZX | ❍ | 30,0 | 110 | 205 | 32 |
| 8320 ZX | ❍ | 32,0 | 110 | 205 | 32 |





## Recommended conditions

(Shoulder processing) $a_p$ = 1,5 x øD

$a_e$ =0,025(HRC56~65) ~ 0,2(below HRC25) x øD

| DC \ Material | | Carbon steel, Alloy steel (BelowHRC25) | Carbon steel, Alloy steel (BelowHRC45) | Hardened steel (BelowHRC65) | Cast iron |
|---|---|---|---|---|---|
| 3,0–5,0 | $v_c$ | 200–**250**–300 | 100–**150**–200 | 80–**100**–120 | 100–**120**–150 |
| | $f_z$ | 0,020–0,040 | 0,015–0,025 | 0,005–0,010 | 0,020–0,040 |
| 6,0–12,0 | $v_c$ | 200–**250**–300 | 100–**150**–200 | 80–**100**–120 | 100–**120**–150 |
| | $f_z$ | 0,041–0,060 | 0,025–0,045 | 0,01 0–0,019 | 0,040–0,110 |
| 16,0–32,0 | $v_c$ | 200–**250**–300 | 100–**150**–200 | 80–**100**–120 | 100–**120**–150 |
| | $f_z$ | 0,060–0,065 | 0,045–0,050 | 0,019–0,025 | 0,125–0,175 |




$v_c$ = m/min $f_z$ = mm/tooth

# SSUP MILL Series



## Features

ZX coated general use endmill for high efficient slotting and side cutting of steels, stainless steels, high temperature alloys and cast irons.

Unique flute design and strong cutting edge ensure excellent chip control even when rough machining slots.

Feed rate up to 2000 mm/min with and without coolant

## Advantages



- Unique flute design for excellent chip removal
- Extra strong cutting edge
- 40° high helix angle for high feed rates
- New ZX coating for excellent wear resistance
- Smooth cutting
- Excellent rigid wide cutting land





SSUP 4000ZX-R Series
Diameter and Corner Radius Range

| DC \ RE | RE0,2 | RE0,3 | RE0,5 | RE1,0 | RE1,5 | RE2.0 | RE3.0 |
|---|---|---|---|---|---|---|---|
| 3 | ● | | ● | | | | |
| 4 | ● | | ● | ● | | | |
| 5 | ● | | ● | ● | | | |
| 6 | | ● | ● | ● | ● | | |
| 8 | | ● | ● | ● | ● | | |
| 10 | | ● | ● | ● | ● | ● | |
| 12 | | | ● | ● | ● | ● | ● |
| 16 | | | | ● | ● | ● | ● |
| 20 | | | | ● | ● | ● | ● |

## Performance


● Feed rate comparisons

<Results>
Stable milling at double the feed rate





| | |
|---|---|
| Work material:<br>X155CrVMo12 1 (HB220)<br>Tool : ø 10 mm, 4 flute<br>Cutting length: 10 m | Cutting conditions :<br>n = 2250 rpm, $v_c$ = 80 m/min<br>$a_p$ =10 mm, $a_e$ =10mm<br>Dry |

● Chip control




<Results>
Excellent chip control




| | |
|---|---|
| Work material:<br>X155CrVMo12 1 (HB220)<br>Tool : ø 10 mm, 4 flute | Cutting conditions :<br>n = 2250 rpm, $v_c$ = 80 m/min<br>$f_z$ = 0,147 mm/tooth ($v_f$ = 1500 mm/min)<br>$a_p$ = 10 mm, $a_e$ = 10 mm, Dry |


● Wear resistance comparison - slotting




<Results>
Half the edge wear - double the tool life

| | |
|---|---|
| Work material: 40CrMoV5 $H_RC40$<br>Tool : ø 10 mm, 4 flute<br>Cutting length: 7,5 m | Cutting conditions :<br>n = 1600 rpm, $v_c$ = 50m/min<br>$f_z$ = 0,04 mm/tooth ($v_f$ = 500 mm/min)<br>$a_p$ = 5mm, $a_e$ = 10 mm, Dry |

● Wear resistance comparison - shoulder cutting




<Results>
Half the edge wear - double the tool life

| | |
|---|---|
| Work material:<br>X155CrVMo12 1 (HB220)<br>Tool : ø 10mm, 4 flute<br>Cutting length: 15 m | Cutting conditions :<br>n = 1750 rpm, $v_c$ = 55 m/min<br>$f_z$ = 0,086 mm/tooth ($v_f$ = 600 mm/min)<br>$a_p$ =15 mm, $a_e$ = 1 mm, Dry |






● = Euro stock
❍ = Japan stock

# ZX Coated SSUP MILL
# SSUP 4000ZX Type

Coated carbide grade: ACZ50M




Helix angle : 40°
Corner : Sharp edge

| DC | Tolerance (mm) |
|---|---|
| D ≤ 3,0 | – 0,014 – 0,028 |
| 3,0 < D ≤ 6,0 | – 0,020 – 0,038 |
| 6,0 < D | – 0,025 – 0,047 |

## Endmills


(mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| SSUP 4020 ZX | ● | 2,0 | 6 | 50 | 4 |
| 4030 ZX | ● | 3,0 | 8 | 50 | 6 |
| 4040 ZX | ● | 4,0 | 11 | 50 | 6 |
| 4050 ZX | ● | 5,0 | 13 | 60 | 6 |
| SSUP 4060 ZX | ● | 6,0 | 13 | 60 | 6 |
| 4070 ZX | ● | 7,0 | 16 | 70 | 8 |
| 4080 ZX | ● | 8,0 | 19 | 80 | 8 |
| 4090 ZX | ● | 9,0 | 19 | 90 | 10 |
| 4100 ZX | ● | 10,0 | 22 | 90 | 10 |
| SSUP 4110 ZX | ● | 11,0 | 22 | 90 | 12 |
| 4120 ZX | ● | 12,0 | 26 | 90 | 12 |
| 4140 ZX | ● | 14,0 | 26 | 110 | 16 |
| 4150 ZX | ❍ | 15,0 | 26 | 110 | 16 |
| SSUP 4160 ZX | ● | 16,0 | 32 | 115 | 16 |
| 4180 ZX | ❍ | 18,0 | 32 | 120 | 20 |
| 4200 ZX | ● | 20,0 | 38 | 125 | 20 |

# ZX Coated SSUP MILL
# SSUP 4000ZX-R Type

With Radius Corner

Coated carbide grade: ACZ50M




Helix angle : 40°
Corner : Sharp edge

-R

| DC | Tolerance (mm) |
|---|---|
| D ≤ 3,0 | – 0,014 – 0,028 |
| 3,0 < D ≤ 6,0 | – 0,020 – 0,038 |
| 6,0 < D | – 0,025 – 0,047 |


## Endmills

(mm)

| Cat. No. | Stock | DC | RE | APMX | LF | DMM |
|---|---|---|---|---|---|---|
| SSUP 4030 ZX-R02 | ● | 3,0 | 0,2 | 8 | 50 | 6 |
| 4030 ZX-R05 | ❍ | 3,0 | 0,5 | 8 | 50 | 6 |
| SSUP 4040 ZX-R02 | ● | 4,0 | 0,2 | 11 | 50 | 6 |
| 4040 ZX-R05 | ● | 4,0 | 0,5 | 11 | 50 | 6 |
| 4040 ZX-R10 | | 4,0 | 1,0 | 11 | 50 | 6 |
| SSUP 4050 ZX-R02 | ● | 5,0 | 0,2 | 13 | 60 | 6 |
| 4050 ZX-R05 | ● | 5,0 | 0,5 | 13 | 60 | 6 |
| 4050 ZX-R10 | ❍ | 5,0 | 1,0 | 13 | 60 | 6 |
| SSUP 4060 ZX-R03 | ● | 6,0 | 0,3 | 13 | 60 | 6 |
| 4060 ZX-R05 | ● | 6,0 | 0,5 | 13 | 60 | 6 |
| 4060 ZX-R10 | ● | 6,0 | 1,0 | 13 | 60 | 6 |
| 4060 ZX-R15 | ❍ | 6,0 | 1,5 | 13 | 60 | 6 |
| SSUP 4080 ZX-R03 | ● | 8,0 | 0,3 | 13 | 80 | 8 |
| 4080 ZX-R05 | ● | 8,0 | 0,5 | 13 | 80 | 8 |
| 4080 ZX-R10 | ● | 8,0 | 1,0 | 19 | 80 | 8 |
| 4080 ZX-R15 | ❍ | 8,0 | 1,5 | 19 | 80 | 8 |
| 4080 ZX-R20 | ❍ | 8,0 | 2,0 | 19 | 80 | 8 |
| SSUP 4100 ZX-R03 | ● | 10,0 | 0,3 | 22 | 90 | 10 |
| 4100 ZX-R05 | ● | 10,0 | 0,5 | 22 | 90 | 10 |
| 4100 ZX-R10 | ● | 10,0 | 1,0 | 22 | 90 | 10 |
| 4100 ZX-R15 | ❍ | 10,0 | 1,5 | 22 | 90 | 10 |
| 4100 ZX-R20 | ❍ | 10,0 | 2,0 | 22 | 90 | 10 |
| SSUP 4120 ZX-R05 | ● | 12,0 | 0,5 | 26 | 90 | 12 |
| 4120 ZX-R10 | ● | 12,0 | 1,0 | 26 | 90 | 12 |
| 4120 ZX-R15 | ● | 12,0 | 1,5 | 26 | 90 | 12 |
| 4120 ZX-R20 | ❍ | 12,0 | 2,0 | 26 | 90 | 12 |
| 4120 ZX-R30 | ❍ | 12,0 | 3,0 | 26 | 90 | 12 |
| SSUP 4160 ZX-R10 | ● | 16,0 | 1,0 | 32 | 115 | 16 |
| 4160 ZX-R15 | ● | 16,0 | 1,5 | 32 | 115 | 16 |
| 4160 ZX-R20 | | 16,0 | 2,0 | 32 | 115 | 16 |
| 4160 ZX-R30 | ❍ | 16,0 | 3,0 | 32 | 115 | 16 |
| SSUP 4200 ZX-R10 | ● | 20,0 | 1,0 | 38 | 125 | 20 |
| 4200 ZX-R15 | | 20,0 | 1,5 | 38 | 125 | 20 |
| 4200 ZX-R20 | ❍ | 20,0 | 2,0 | 38 | 125 | 20 |
| 4200 ZX-R30 | | 20,0 | 3,0 | 38 | 125 | 20 |

## Recommended Cutting Conditions

| Material / Cutting data / DC (mm) | | Carbon steel, Cast iron (HB150–250) Speed (rpm) | Feed (mm/min) | Alloy steel, Prehardened steel (HRC25–35) Speed (rpm) | Feed (mm/min) | Hardened steel (HRC40–50) Speed (rpm) | Feed (mm/min) | Stainless steel Speed (rpm) | Feed (mm/min) | Heat resistant alloys Titanium alloy (HRC20–45) Speed (rpm) | Feed (mm/min) |
|---|---|---|---|---|---|---|---|---|---|---|---|
| 2 | | 9000 | 720 | 6000 | 430 | 4000 | 320 | 5500 | 320 | 2600 | 120 |
| 4 | | 6600 | 800 | 4500 | 450 | 3000 | 380 | 4000 | 320 | 2000 | 120 |
| 6 | | 4800 | 960 | 3000 | 480 | 2500 | 380 | 3000 | 480 | 1200 | 120 |
| 8 | | 3600 | 1000 | 2200 | 610 | 2000 | 400 | 2000 | 520 | 1000 | 140 |
| 10 | | 2800 | 1000 | 1800 | 610 | 1500 | 400 | 1700 | 550 | 800 | 160 |
| 12 | | 2400 | 950 | 1500 | 550 | 1200 | 380 | 1500 | 500 | 700 | 140 |
| 14 | | 2200 | 880 | 1300 | 490 | 1000 | 360 | 1200 | 430 | 600 | 130 |
| 16 | | 1800 | 650 | 1100 | 420 | 800 | 300 | 1000 | 360 | 500 | 120 |
| 18 | | 1600 | 580 | 1000 | 360 | 750 | 270 | 900 | 340 | 450 | 110 |
| 20 | | 1400 | 500 | 900 | 330 | 700 | 250 | 820 | 300 | 400 | 100 |
| Shoulder cutting | $a_p$ | 1,5 DC | | | | | | | | | |
| | $a_e$ | 0,1 DC | | | | 0,05 DC | | 0,1 DC | | 0,05 DC | |
| Slotting | $a_p$ | 1,0 DC | | | | 0,2 DC | | 0,3 DC | | 0,2 DC | |





(1) Cutting performance is improved when using a high rigidity machine.
(2) Speeds and feeds should be reduced when slotting some stainless steels.
(3) In case of chatter first check the cutting conditions.

# GSX MILL Ball Endmills
# GSXB 20000 Type

Coated Carbide Grades | GSX Coating

| Structual Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ○ | | ◎ | ○ | ○ | | | |




Coated carbide grade: **ACB20**

## Endmill Identification (GSXB Type)

**GSXB 2 0200**

| Series Code | No. of Teeth | Radius of Ballnose |
|---|---|---|
| GSXB | 2 | 0200 |

## Endmills

(mm)

| Cat. No. | Stock | RE | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|---|
| GSXB 20020 | ● | 0,20 | 0,4 | 0,6 | 0,8 | 50 | 4 |
| GSXB 20030 | ● | 0,30 | 0,6 | 0,9 | 1,2 | 50 | 4 |
| GSXB 20050 | ● | 0,50 | 1,0 | 1,5 | 2,0 | 50 | 4 |
| GSXB 20075 | ● | 0,75 | 1,5 | 2,5 | 3,0 | 50 | 4 |
| GSXB 20100 | ● | 1,00 | 2,0 | 3,0 | 4,0 | 60 | 6 |
| GSXB 20125 | ● | 1,25 | 2,5 | 4,0 | 5,0 | 60 | 6 |
| GSXB 20150 | ● | 1,50 | 3,0 | 4,5 | 6,0 | 60 | 6 |
| GSXB 20200 | ● | 2,00 | 4,0 | 6,0 | 8,0 | 70 | 6 |
| GSXB 20250 | ● | 2,50 | 5,0 | 7,5 | 10,0 | 80 | 6 |
| GSXB 20300 | ● | 3,00 | 6,0 | 9,0 | – | 80 | 6 |
| GSXB 20350 | ● | 3,50 | 7,0 | 11,0 | 20,0 | 90 | 8 |
| GSXB 20400 | ● | 4,00 | 8,0 | 12,0 | – | 90 | 8 |
| GSXB 20500 | ● | 5,00 | 10,0 | 15,0 | – | 100 | 10 |
| GSXB 20600 | ● | 6,00 | 12,0 | 18,0 | – | 110 | 12 |
| GSXB 20700 | ● | 7,00 | 14,0 | 21,0 | 38,0 | 110 | 16 |
| GSXB 20800 | ● | 8,00 | 16,0 | 24,0 | – | 140 | 16 |
| GSXB 20900 | ● | 9,00 | 18,0 | 27,0 | 50,0 | 140 | 20 |
| GSXB 21000 | ❍ | 10,00 | 20,0 | 30,0 | – | 160 | 20 |
| GSXB 21250 | | 12,50 | 25,0 | 38,0 | – | 180 | 25 |
| GSXB 21500 | | 15,00 | 30,0 | 45,0 | 80,0 | 180 | 32 |




New "Global Standard" Mills
Ball nose type with 2 teeth





## Recommended Cutting Conditions

(1) If cutting noise and vibration are present, please change the cutting conditions accordingly.
(2) If the machine is not designed to achieve the recommended spindle speed, please use the max. spindle speed available.




### ●Radius Milling

| Work Material / Cutting Conditions / RE (mm) | Carbon Steel, Alloy Steel (Below 25HRC) Spindle Speed (rpm) | Carbon Steel, Alloy Steel (Below 25HRC) Feed Rate (mm/min) | Carbon Steel, Alloy Steel (Below 50HRC) Spindle Speed (rpm) | Carbon Steel, Alloy Steel (Below 50HRC) Feed Rate (mm/min) | Cast Iron Special Cast Iron Spindle Speed (rpm) | Cast Iron Special Cast Iron Feed Rate (mm/min) | Stainless Steel Titanium Alloy Spindle Speed (rpm) | Stainless Steel Titanium Alloy Feed Rate (mm/min) |
|---|---|---|---|---|---|---|---|---|
| 0,20 | 50.000 | 2.100 | 35.000 | 1.150 | 50.000 | 2.100 | 50.000 | 1.750 |
| 0,30 | 50.000 | 2.500 | 35.000 | 1.350 | 50.000 | 2.500 | 50.000 | 2.100 |
| 0,50 | 50.000 | 3.000 | 35.000 | 1.600 | 50.000 | 3.000 | 50.000 | 2.500 |
| 0,75 | 35.000 | 3.000 | 24.000 | 1.650 | 35.000 | 3.200 | 34.000 | 2.500 |
| 1,00 | 27.500 | 3.000 | 19.000 | 1.700 | 35.000 | 3.900 | 26.000 | 2.500 |
| 1,25 | 22.500 | 3.000 | 15.500 | 1.700 | 28.000 | 3.900 | 21.000 | 2.500 |
| 1,50 | 19.000 | 3.000 | 13.000 | 1.700 | 24.000 | 3.900 | 17.500 | 2.500 |
| 2,00 | 17.000 | 3.800 | 12.000 | 2.100 | 20.000 | 4.100 | 15.000 | 2.700 |
| 2,50 | 15.500 | 4.300 | 11.000 | 2.200 | 18.000 | 4.600 | 12.000 | 2.500 |
| 3,00 | 14.000 | 4.700 | 10.500 | 2.500 | 16.500 | 5.300 | 10.500 | 2.500 |
| 3,50 | 12.500 | 4.200 | 9.000 | 2.100 | 14.000 | 4.500 | 9.000 | 2.200 |
| 4,00 | 11.000 | 3.500 | 7.900 | 1.900 | 12.500 | 4.000 | 7.800 | 1.900 |
| 5,00 | 9.000 | 2.800 | 6.300 | 1.500 | 10.500 | 3.300 | 6.300 | 1.500 |
| 6,00 | 7.500 | 2.400 | 5.200 | 1.250 | 8.700 | 2.800 | 5.200 | 1.250 |
| 7,00 | 6.400 | 2.100 | 4.500 | 1.100 | 7.400 | 2.400 | 4.500 | 1.100 |
| 8,00 | 5.600 | 1.800 | 3.900 | 950 | 6.500 | 2.100 | 3.900 | 950 |
| 9,00 | 5.000 | 1.600 | 3.500 | 850 | 5.800 | 1.900 | 3.500 | 850 |
| 10,00 | 4.500 | 1.450 | 3.100 | 750 | 5.200 | 1.700 | 3.150 | 750 |
| 12,50 | 3.600 | 1.150 | 2.500 | 600 | 4.200 | 1.350 | 2.500 | 600 |
| 15,00 | 3.000 | 960 | 2.100 | 500 | 3.500 | 1.150 | 2.100 | 500 |
| Depth and wide of cut $a_p$ | 0,02 DC | | 0,02 DC | | 0,02 DC | | 0,02 DC | |
| Depth and wide of cut $a_e$ | 0,05 DC | | 0,05 DC | | 0,05 DC | | 0,05 DC | |






● = Euro stock
❍ = Japan stock

## DLC (Diamond Like Carbon) Coating

2

DLC coated carbide grade: DL1200





## Endmills

(mm)

| Cat. No. | Stock | RE | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|---|
| SNB 2020 DL | ● | 1,0 | 2,0 | 3 | 5 | 60 | 6 |
| 2030 DL | ● | 1,5 | 3,0 | 4,5 | 8 | 80 | 6 |
| SNB 2040 DL | ● | 2,0 | 4,0 | 6 | 12 | 80 | 6 |
| 2050 DL | ● | 2,5 | 5,0 | 7,5 | 14 | 90 | 6 |
| SNB 2060 DL | ● | 3,0 | 6,0 | 9 | - | 100 | 6 |
| 2080 DL | ● | 4,0 | 8,0 | 12 | - | 100 | 8 |
| 2100 DL | ● | 5,0 | 10,0 | 15 | - | 120 | 10 |
| SNB 2120 DL | ● | 6,0 | 12,0 | 18 | - | 120 | 12 |
| 2160 DL | ● | 8,0 | 16,0 | 24 | - | 160 | 16 |

## Characteristics / Application

- Very smooth AURORA COAT results in low adhesion as well as good surface finish
- With lower cutting forces and high rigidity, this series is suitable for low rigidity machine







## Recommended Cutting Conditions

| Work Material | | Aluminum Alloy | | | |
|---|---|---|---|---|---|
| Cutting data / RE (mm) | | Wet (Emulsion) | | Dry | |
| | | Speed (rpm) | Feed (mm/min) | Speed (rpm) | Feed (mm/min) |
| 1,0 | | 48.000 | 1.500 | 48.000 | 1.000 |
| 1,5 | | 48.000 | 2.100 | 48.000 | 1.500 |
| 2,0 | | 31.000 | 2.800 | 31.000 | 2.000 |
| 2,5 | | 24.000 | 2.800 | 24.000 | 2.000 |
| 3,0 | | 20.000 | 2.800 | 20.000 | 2.000 |
| 4,0 | | 15.000 | 2.800 | 15.000 | 2.000 |
| 5,0 | | 13.000 | 3.000 | 13.000 | 2.100 |
| 6,0 | | 10.000 | 3.000 | 10.000 | 2.100 |
| 8,0 | | 7.700 | 3.000 | 7.700 | 2.100 |
| Depth and wide of cut | $a_p$ | 1,5 DC | | 1,0 DC | |
| | $a_e$ | 0,2 DC | | (DC) | |

# ASM 2000 Type

2

Carbide grade: H1 (Micrograin)




Helix angle : 30˚
Corner : Sharp edge

## ■ Endmills

(mm)


| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| ASM 2020 | ❍ | 2,0 | 6 | 40 | 4 |
| 2030 | ❍ | 3,0 | 10 | 45 | 6 |
| 2040 | ❍ | 4,0 | 12 | 45 | 6 |
| 2050 | ❍ | 5,0 | 15 | 50 | 6 |
| ASM 2060 | ❍ | 6,0 | 15 | 50 | 6 |
| 2080 | ❍ | 8,0 | 18 | 60 | 8 |
| 2100 | ❍ | 10,0 | 22 | 71 | 10 |
| ASM 2120 | ❍ | 12,0 | 25 | 75 | 12 |
| 2140 | ❍ | 14,0 | 32 | 90 | 16 |
| 2150 | ❍ | 15,0 | 32 | 90 | 16 |
| 2160 | ❍ | 16,0 | 32 | 90 | 16 |

## Recommended Conditions

(Shoulder processing) $a_p$ =1,5 x DC
$a_e$ =0,1 x DC

| DC \ Material | | Al-alloy | Cast iron |
|---|---|---|---|
| 1 – 2,5 | $v_c$ | 100-**200**-300 | 100-**120**-150 |
| | $f_z$ | 0,004–0,017 | 0,008–0,020 |
| 3 – 5 | $v_c$ | 100-**200**-300 | 100-**120**-150 |
| | $f_z$ | 0,018–0,036 | 0,027–0,060 |
| 6 – 12 | $v_c$ | 100-**200**-300 | 100-**120**-150 |
| | $f_z$ | 0,038–0,070 | 0,065–0,157 |
| 14 – 16 | $v_c$ | 100-**200**-300 | 100-**120**-150 |
| | $f_z$ | 0,075–0,125 | 0,160–0,250 |

$v_c$ =m/min $f_z$ =mm/tooth





● = Euro stock
❍ = Japan stock

## Anti-Vibration Type Radius Endmills for Exotic Alloys

# SSEHVL 4000-R Type

Uncoated Carbide | 4

| Structal Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | | | | ○ | ◎ | | | | |




| DC | Tolerance (mm) |
|---|---|
| D ≤ 6,0 | – 0,028 – 0,043 |
| 6,0 < D | – 0,033 – 0,052 |

Carbide grade: EH520

## ■ Endmills

(mm)


| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| SSEHVL 4045-R05 | | 4,5 | 0,5 | 12 | 50 | 6 |
| SSEHVL 4045-R10 | | 4,5 | 1,0 | 12 | 50 | 6 |
| SSEHVL 4050-R05 | | 5,0 | 0,5 | 13 | 60 | 6 |
| SSEHVL 4050-R10 | ❍ | 5,0 | 1,0 | 13 | 60 | 6 |
| SSEHVL 4060-R10 | ❍ | 6,0 | 1,0 | 13 | 60 | 6 |
| SSEHVL 4080-R10 | ❍ | 8,0 | 1,0 | 19 | 80 | 8 |
| SSEHVL 4100-R10 | ❍ | 10,0 | 1,0 | 22 | 90 | 10 |
| SSEHVL 4100-R30 | ❍ | 10,0 | 3,0 | 22 | 90 | 10 |
| SSEHVL 4120-R10 | ● | 12,0 | 1,0 | 26 | 90 | 12 |
| SSEHVL 4120-R30 | ● | 12,0 | 3,0 | 26 | 90 | 12 |
| SSEHVL 4160-R10 | ❍ | 16,0 | 1,0 | 32 | 115 | 16 |
| SSEHVL 4160-R30 | ● | 16,0 | 3,0 | 32 | 115 | 16 |

## Radius Endmills for Exotic Alloys

# SSEH 4000-R Type

Uncoated Carbide | 4

| Structal Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45~55 HRC | Hardened Steel 55~60 HRC | Hardened Steel 60~65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | Graphite |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | | | | ○ | ◎ | | | | |




| DC | Tolerance (mm) |
|---|---|
| D ≤ 6,0 | – 0,028 – 0,043 |
| 6,0 < D | – 0,033 – 0,052 |

Carbide grade: EH520


## ■ Endmills

(mm)

| Cat. No. | Stock | DC | APMX | LU | LF | DMM |
|---|---|---|---|---|---|---|
| SSEH 4045-R05 | | 4,5 | 0,5 | 12 | 50 | 6 |
| SSEH 4045-R10 | | 4,5 | 1,0 | 12 | 50 | 6 |
| SSEH 4050-R05 | | 5,0 | 0,5 | 13 | 60 | 6 |
| SSEH 4050-R10 | | 5,0 | 1,0 | 13 | 60 | 6 |
| SSEH 4060-R10 | ❍ | 6,0 | 1,0 | 13 | 60 | 6 |
| SSEH 4080-R10 | | 8,0 | 1,0 | 19 | 80 | 8 |
| SSEH 4100-R10 | | 10,0 | 1,0 | 22 | 90 | 10 |
| SSEH 4100-R30 | ❍ | 10,0 | 3,0 | 22 | 90 | 10 |
| SSEH 4120-R10 | ❍ | 12,0 | 1,0 | 26 | 90 | 12 |
| SSEH 4120-R30 | ❍ | 12,0 | 3,0 | 26 | 90 | 12 |
| SSEH 4160-R10 | | 16,0 | 1,0 | 32 | 115 | 16 |
| SSEH 4160-R30 | ● | 16,0 | 3,0 | 32 | 115 | 16 |

## ■ Characteristics / Application

1. For stable machining, a more rigid machine is recommended.
2. Wet machining is recommended for stainless steel and heat resistant alloy applications.
3. If cutting noise and vibration are present, please change the cutting conditions accordingly.




### ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Stainless Steel Spindle Speed (rpm) | Stainless Steel Feed Rate (mm/min) | Titanium Alloy Spindle Speed (rpm) | Titanium Alloy Feed Rate (mm/min) | Heat Resistive Steel Spindle Speed (rpm) | Heat Resistive Steel Feed Rate (mm/min) |
|---|---|---|---|---|---|---|
| 4.5 | 2.300 | 120 | 4.600 | 370 | 1.600 | 130 |
| 5.0 | 2.000 | 130 | 4.100 | 410 | 1.500 | 150 |
| 6.0 | 1.700 | 130 | 3.400 | 400 | 1.200 | 140 |
| 8.0 | 1.300 | 130 | 2.600 | 360 | 900 | 130 |
| 10.0 | 1.000 | 130 | 2.100 | 340 | 700 | 110 |
| 12.0 | 800 | 110 | 1.700 | 300 | 600 | 100 |
| 16.0 | 600 | 90 | 1.300 | 260 | 500 | 100 |
| Shoulder cutting $a_p$ | 1,5 DC | | | | | |
| Shoulder cutting $a_e$ | 0,1 DC | | 0,05 DC | | 0,05 DC | |

### ● Grooving

| Work Material / Cond. / DC (mm) | Stainless Steel Spindle Speed (rpm) | Stainless Steel Feed Rate (mm/min) | Titanium Alloy Spindle Speed (rpm) | Titanium Alloy Feed Rate (mm/min) | Heat Resistive Steel Spindle Speed (rpm) | Heat Resistive Steel Feed Rate (mm/min) |
|---|---|---|---|---|---|---|
| 4,5 | 1.800 | 50 | 3.200 | 250 | 1.300 | 110 |
| 5,0 | 1.600 | 50 | 2.900 | 290 | 1.200 | 120 |
| 6,0 | 1.400 | 50 | 2.400 | 290 | 1.000 | 120 |
| 8,0 | 1.000 | 50 | 1.800 | 250 | 700 | 90 |
| 10,0 | 800 | 50 | 1.400 | 230 | 600 | 100 |
| 12,0 | 600 | 50 | 1.200 | 210 | 500 | 90 |
| 16,0 | 500 | 40 | 900 | 180 | 400 | 80 |
| Grooving $a_p$ | 0,3 DC | | 0,2 DC | | 0,15 DC | |

### ● Shoulder Milling

| Work Material / Cond. / DC (mm) | Stainless Steel Spindle Speed (rpm) | Stainless Steel Feed Rate (mm/min) | Titanium Alloy Spindle Speed (rpm) | Titanium Alloy Feed Rate (mm/min) | Heat Resistive Steel Spindle Speed (rpm) | Heat Resistive Steel Feed Rate (mm/min) |
|---|---|---|---|---|---|---|
| 4,5 | 1.800 | 90 | 3.500 | 280 | 1.400 | 110 |
| 5,0 | 1.600 | 100 | 3.200 | 320 | 1.300 | 130 |
| 6,0 | 1.300 | 100 | 2.700 | 320 | 1.100 | 130 |
| 8,0 | 1.000 | 100 | 2.000 | 280 | 800 | 110 |
| 10,0 | 800 | 100 | 1.600 | 260 | 600 | 100 |
| 12,0 | 700 | 100 | 1.300 | 230 | 500 | 90 |
| 16,0 | 500 | 80 | 1.000 | 200 | 400 | 80 |
| Shoulder cutting $a_p$ | 1,5 DC | | | | | |
| Shoulder cutting $a_e$ | 0,1 DC | | 0,05 DC | | 0,05 DC | |


### ● Grooving

| Work Material / Cond. / DC (mm) | Stainless Steel Spindle Speed (rpm) | Stainless Steel Feed Rate (mm/min) | Titanium Alloy Spindle Speed (rpm) | Titanium Alloy Feed Rate (mm/min) | Heat Resistive Steel Spindle Speed (rpm) | Heat Resistive Steel Feed Rate (mm/min) |
|---|---|---|---|---|---|---|
| 4,5 | 1.400 | 40 | 2.500 | 200 | 1.100 | 90 |
| 5,0 | 1.300 | 40 | 2.200 | 220 | 1.000 | 100 |
| 6,0 | 1.100 | 40 | 1.900 | 230 | 800 | 100 |
| 8,0 | 800 | 40 | 1.400 | 200 | 600 | 80 |
| 10,0 | 600 | 40 | 1.100 | 180 | 500 | 80 |
| 12,0 | 500 | 40 | 900 | 160 | 400 | 70 |
| 16,0 | 400 | 30 | 700 | 140 | 300 | 60 |
| Grooving $a_p$ | 0,3 DC | | 0,2 DC | | 0,15 DC | |

# Solid Carbide Spiral Endmills
# SSM 2000 Type (ø0,2–ø4,3)

2

Carbide grade: A1 (Micrograin)




Helix angle : 30˚
Corner : Sharp edge

| DC | Tolerance (mm) |
|---|---|
| D ≤ 6,0 | – 0,010 – 0,030 |

## Endmills


(mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| SSM 2002 | ❍ | 0,2 | 0,5 | 40 | 3 |
| 2003 | ● | 0,3 | 1,0 | 40 | 3 |
| 2004 | ● | 0,4 | 1,0 | 40 | 3 |
| 2005 | ● | 0,5 | 1,5 | 40 | 3 |
| SSM 2006 | ● | 0,6 | 1,5 | 40 | 3 |
| 2007 | ● | 0,7 | 1,5 | 40 | 3 |
| 2008 | ● | 0,8 | 2,0 | 40 | 3 |
| 2009 | | 0,9 | 2,0 | 40 | 3 |
| 2010 | ● | 1,0 | 3,0 | 40 | 4 |
| SSM 2011 | ❍ | 1,1 | 3,0 | 40 | 4 |
| 2012 | ❍ | 1,2 | 3,0 | 40 | 4 |
| 2013 | | 1,3 | 3,0 | 40 | 4 |
| 2014 | ❍ | 1,4 | 3,0 | 40 | 4 |
| 2015 | ● | 1,5 | 5,0 | 40 | 4 |
| SSM 2016 | ❍ | 1,6 | 5,0 | 40 | 4 |
| 2017 | | 1,7 | 5,0 | 40 | 4 |
| 2018 | ❍ | 1,8 | 5,0 | 40 | 4 |
| 2019 | ❍ | 1,9 | 5,0 | 40 | 4 |
| 2020 | ● | 2,0 | 6,0 | 40 | 4 |
| SSM 2021 | | 2,1 | 6,0 | 40 | 4 |
| 2022 | ❍ | 2,2 | 6,0 | 40 | 4 |
| 2023 | ❍ | 2,3 | 6,0 | 40 | 4 |
| 2024 | ❍ | 2,4 | 6,0 | 40 | 4 |
| 2025 | ● | 2,5 | 8,0 | 40 | 4 |
| SSM 2026 | ❍ | 2,6 | 8,0 | 40 | 4 |
| 2027 | ● | 2,7 | 8,0 | 40 | 4 |
| 2028 | | 2,8 | 8,0 | 40 | 4 |
| 2029 | | 2,9 | 8,0 | 40 | 4 |
| 2030 | ● | 3,0 | 8,0 | 45 | 6 |
| SSM 2031 | | 3,1 | 8,0 | 45 | 6 |
| 2032 | ❍ | 3,2 | 8,0 | 45 | 6 |
| 2033 | | 3,3 | 8,0 | 45 | 6 |
| 2034 | ❍ | 3,4 | 8,0 | 45 | 6 |
| 2035 | ● | 3,5 | 8,0 | 45 | 6 |
| SSM 2036 | | 3,6 | 10,0 | 45 | 6 |
| 2037 | | 3,7 | 10,0 | 45 | 6 |
| 2038 | ❍ | 3,8 | 10,0 | 45 | 6 |
| 2039 | ❍ | 3,9 | 10,0 | 45 | 6 |
| 2040 | ● | 4,0 | 10,0 | 45 | 6 |
| SSM 2041 | | 4,1 | 10,0 | 45 | 6 |
| 2042 | ❍ | 4,2 | 10,0 | 45 | 6 |
| 2043 | | 4,3 | 10,0 | 45 | 6 |

## Recommended Conditions

(Slotting) DC < ø 3; $a_p$ =0,5 x DC
DC ≥ ø 3; $a_p$ =1,0 x DC

| DC | Material | Carbon steel, Alloy steel (BelowHRC30) | Carbon steel, Alloy steel (BelowHRC40) | Carbon steel, Alloy steel (BelowHRC45) | Cast iron |
|---|---|---|---|---|---|
| 0,2–0,9 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | –0,002 | –0,002 | –0,001 | 0,002–0,004 |
| 1,0–2,9 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,003–0,010 | 0,003–0,010 | 0,002–0,005 | 0,005–0,017 |
| 3,0–4,9 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,012–0,024 | 0,012–0,024 | 0,006–0,011 | 0,018–0,040 |





$v_c$ =m/min $f_z$ =mm/tooth

● = Euro stock
❍ = Japan stock

# Solid Carbide Spiral Endmills
# SSM 2000 Type (ø4,4–ø8,5)

2

Carbide grade: A1 (Micrograin)




Helix angle : 30˚
Corner : Sharp edge

| DC | Tolerance (mm) |
|---|---|
| D ≤ 6,0 | – 0,010 – 0,030 |

## Endmills


(mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| SSM 2044 | ❍ | 4,4 | 10 | 45 | 6 |
| 2045 | ❍ | 4,5 | 10 | 45 | 6 |
| SSM 2046 | | 4,6 | 12 | 50 | 6 |
| 2047 | | 4,7 | 12 | 50 | 6 |
| 2048 | ❍ | 4,8 | 12 | 50 | 6 |
| 2049 | ❍ | 4,9 | 12 | 50 | 6 |
| 2050 | ● | 5,0 | 12 | 50 | 6 |
| SSM 2051 | ❍ | 5,1 | 12 | 50 | 6 |
| 2052 | ❍ | 5,2 | 12 | 50 | |
| 2053 | | 5,3 | | 50 | |
| 2054 | | 5,4 | 12 | 50 | 6 |
| 2055 | | 5,5 | 12 | 50 | 6 |
| SSM 2056 | | 5,6 | 12 | 50 | 6 |
| 2057 | | 5,7 | 12 | 50 | 6 |
| 2058 | | 5,8 | 12 | 50 | 6 |
| 2059 | | 5,9 | 12 | 50 | 6 |
| 2060 | ● | 6,0 | 12 | 50 | 6 |
| SSM 2061 | | 6,1 | 12 | 50 | 6 |
| 2062 | ❍ | 6,2 | 12 | 50 | 6 |
| 2063 | ❍ | 6,3 | 12 | 50 | 6 |
| 2064 | ❍ | 6,4 | 12 | | 6 |
| 2065 | ❍ | 6,5 | 12 | 50 | 8 |
| SSM 2066 | ❍ | 6,6 | | 55 | 8 |
| 2067 | | 6,7 | 15 | 55 | 8 |
| 2068 | | 6,8 | 15 | 55 | 8 |
| 2069 | | 6,9 | 15 | 55 | 8 |
| 2070 | ● | 7,0 | 15 | 55 | 8 |
| SSM 2071 | ❍ | 7,1 | 15 | 55 | 8 |
| 2072 | | 7,2 | 15 | 55 | 8 |
| 2073 | | 7,3 | 15 | 55 | 8 |
| 2074 | | 7,4 | 15 | 55 | 8 |
| 2075 | ● | 7,5 | 15 | 55 | 8 |
| SSM 2076 | | 7,6 | 15 | 55 | 8 |
| 2077 | | 7,7 | 15 | 55 | 8 |
| 2078 | | 7,8 | 15 | 55 | 8 |
| 2079 | | 7,9 | 15 | 55 | 8 |
| 2080 | ● | 8,0 | 15 | 55 | 8 |
| SSM 2081 | ❍ | 8,1 | 15 | 55 | 8 |
| 2082 | ❍ | 8,2 | 15 | 55 | 8 |
| 2083 | | 8,3 | 15 | 55 | 8 |
| 2084 | | 8,4 | 15 | 55 | 8 |
| 2085 | ● | 8,5 | 15 | 55 | 10 |

## Recommended Conditions

(Slotting) DC ≥ ø3; $a_p$ =1,0 x DC

| DC | Material | Carbon steel, Alloy steel (BelowHRC30) | Carbon steel, Alloy steel (BelowHRC40) | Carbon steel, Alloy steel (BelowHRC45) | Cast iron |
|---|---|---|---|---|---|
| 5–5,9 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,012–0,024 | 0,012–0,024 | 0,006–0,011 | 0,018–0,040 |
| 6–8,9 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,025–0,050 | 0,025–0,050 | 0,013–0,025 | 0,045–0,105 |





$v_c$ =m/min $f_z$ = mm/tooth

# Solid Carbide Spiral Endmills
# SSM 2000 Type (ø8,6–ø30)

2

Carbide grade: A1 (Micrograin)




Helix angle : 30˚
Corner : Sharp edge

| DC | Tolerance (mm) |
|---|---|
| 6,0 < D ≤ 10,0 | – 0,015 – 0,040 |
| 10,0 < D | – 0,020 – 0,050 |


## ■ Endmills (mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| SSM 2086 | ❍ | 8,6 | 15 | 55 | 10 |
| 2087 | | 8,7 | 15 | 55 | 10 |
| 2088 | | 8,8 | 15 | 55 | 10 |
| 2089 | | 8,9 | 15 | 55 | 10 |
| 2090 | ● | 9,0 | 15 | 55 | 10 |
| SSM 2091 | | 9,1 | 15 | 55 | 10 |
| 2092 | ❍ | 9,2 | 15 | 55 | 10 |
| 2093 | | 9,3 | 15 | 55 | 10 |
| 2094 | | 9,4 | 15 | 55 | 10 |
| 2095 | | 9,5 | 15 | 55 | 10 |
| SSM 2096 | | 9,6 | 18 | 65 | 10 |
| 2097 | | 9,7 | 18 | 65 | 10 |
| 2098 | | 9,8 | 18 | 65 | 10 |
| 2099 | | 9,9 | 18 | 65 | 10 |
| 2100 | ● | 10,0 | 18 | 65 | 10 |
| SSM 2105 | | 10,5 | 18 | 70 | 12 |
| 2110 | | 11,0 | 18 | 70 | 12 |
| 2115 | ❍ | 11,5 | 18 | 70 | 12 |
| 2120 | ● | 12,0 | 18 | 70 | 12 |
| 2125 | | 12,5 | 20 | 80 | 16 |
| SSM 2130 | | 13,0 | 20 | 80 | 16 |
| 2135 | ❍ | 13,5 | | 80 | 16 |
| 2140 | ● | 14,0 | 20 | 80 | 16 |
| 2145 | | 14,5 | 25 | 80 | 16 |
| 2150 | | 15,0 | 25 | 80 | 16 |
| SSM 2155 | | 15,5 | 35 | 90 | 16 |
| 2160 | ● | 16,0 | 35 | 90 | 16 |
| 2165 | | 16,5 | 35 | 90 | 20 |
| 2170 | ● | 17,0 | 35 | 90 | 20 |
| 2175 | ❍ | 17,5 | 40 | 105 | 20 |
| SSM 2180 | | 18,0 | 40 | 105 | 20 |
| 2185 | | 18,5 | 40 | 105 | 20 |
| 2190 | | 19,0 | 40 | 105 | 20 |
| 2195 | | 19,5 | 40 | 105 | 20 |
| 2200 | ● | 20,0 | 40 | 105 | 20 |
| SSM 2210 | ❍ | 21,0 | 40 | 105 | 25 |
| 2220 | | 22,0 | 40 | | 25 |
| 2230 | | | 45 | 115 | 25 |
| 2240 | | 24,0 | 45 | 115 | 25 |
| 2250 | ❍ | | 50 | | 25 |
| SSM 2300 | | | 55 | 130 | 32 |

## Recommended Conditions

(Slotting) DC ≥ ø3; $a_p$ =1,0 x DC

| DC | | Carbon steel, Alloy steel (BelowHRC30) | Carbon steel, Alloy steel (BelowHRC40) | Carbon steel, Alloy steel (BelowHRC45) | Cast iron |
|---|---|---|---|---|---|
| 9–12,5 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,025–0,050 | 0,025–0,050 | 0,013–0,025 | 0,045–0,105 |
| 13–19,5 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,055–0,085 | 0,055–0,085 | 0,030–0,050 | 0,110–0,170 |
| 20–30 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,095–0,120 | 0,095–0,120 | 0,055–0,070 | 0,185–0,260 |





$v_c$ =m/min $f_z$ =mm/tooth

# Solid Carbide Spiral Endmills
# SSM 4000 Type (ø1,5–ø25)

4

Carbide grade: A1 (Micrograin)




Helix angle : 30˚
Corner : Sharp edge

| DC | Tolerance (mm) |
|---|---|
| D ≤ 6,0 | – 0,010 – 0,030 |
| 6,0 < D ≤ 10,0 | – 0,015 – 0,040 |
| 10,0 < D | – 0,020 – 0,050 |


## ■ Endmills (mm)

| Cat. No. | Stock | DC | APMX | LF | DMM |
|---|---|---|---|---|---|
| SSM 4015 | ● | 1,5 | 5 | 40 | 4 |
| 4020 | ● | 2,0 | 6 | 40 | 4 |
| 4025 | ❍ | 2,5 | 8 | 40 | 4 |
| 4030 | ● | 3,0 | 8 | 45 | 6 |
| 4035 | | 3,5 | 8 | 45 | 6 |
| SSM 4040 | ● | 4,0 | 10 | 45 | 6 |
| 4045 | | 4,5 | 10 | 45 | 6 |
| 4050 | ● | 5,0 | 12 | 50 | 6 |
| 4055 | | 5,5 | 12 | 50 | 6 |
| 4060 | ● | 6,0 | 12 | 50 | 6 |
| SSM 4065 | | 6,5 | 12 | 50 | 8 |
| 4070 | ● | 7,0 | 15 | 55 | 8 |
| 4075 | ● | 7,5 | 15 | 55 | 8 |
| 4080 | ● | 8,0 | 15 | 55 | 8 |
| 4085 | ❍ | 8,5 | 15 | 55 | 10 |
| SSM 4090 | ● | 9,0 | 15 | 55 | 10 |
| 4095 | ● | 9,5 | 15 | 55 | 10 |
| 4100 | ● | 10,0 | 18 | 65 | 10 |
| 4105 | | 10,5 | 18 | 65 | 12 |
| 4110 | | 11,0 | 18 | 70 | 12 |
| SSM 4120 | ● | 12,0 | 18 | 70 | 12 |
| 4130 | | 13,0 | 20 | 80 | 16 |
| 4140 | ● | 14,0 | 20 | 80 | 16 |
| 4150 | | 15,0 | 25 | 80 | 16 |
| 4160 | ● | 16,0 | 35 | 90 | 16 |
| SSM 4170 | | 17,0 | 35 | 90 | 20 |
| 4180 | | 18,0 | 40 | 105 | 20 |
| 4190 | | 19,0 | 40 | 105 | 20 |
| 4200 | ● | 20,0 | 40 | 105 | 20 |
| 4210 | | 21,0 | 40 | 105 | 25 |
| SSM 4220 | | 22,0 | 40 | 105 | 25 |
| 4230 | | 23,0 | 45 | 115 | 25 |
| 4240 | | 24,0 | 45 | 115 | 25 |
| 4250 | | 25,0 | 50 | 120 | 25 |

## Recommended Conditions

(Shoulder processing) $a_p$ =1,5 x DC
$a_e$ =0,1 x DC

| DC | | Carbon steel, Alloy steel (BelowHRC30) | Carbon steel, Alloy steel (BelowHRC40) | Carbon steel, Alloy steel (BelowHRC45) | Cast iron |
|---|---|---|---|---|---|
| 1 ~ 2,9 | $v_c$ | 40–**50**–60 | 30–**0**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,004–0,017 | 0,004–0,017 | 0,002–0,008 | 0,008–0,020 |
| 3 ~ 5,9 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,018–0,036 | 0,018–0,036 | 0,009–0,018 | 0,027–0,060 |
| 6 ~ 12,9 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,038–0,070 | 0,038–0,070 | 0,019–0,035 | 0,065–0,157 |
| 13 ~ 19,9 | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,075–0,125 | 0,075–0,125 | 0,040–0,075 | 0,160–0,250 |
| 20 ~ | $v_c$ | 40–**50**–60 | 30–**40**–50 | 20–**30**–40 | 40–**50**–60 |
| | $f_z$ | 0,135–0,170 | 0,135–0,170 | 0,085–0,110 | 0,257–0,390 |





$v_c$ =m/min $f_z$ =mm/tooth


# BNES Type

Spiral CBN Endmill for Hardened Steel






## ■ Endmills BNES Type with 1 Spiral Flute





Helix angle : 15°
right-hand cut, right-hand helix

| Cat. No. | Stock | Dimensions (mm) | | | | |
|---|---|---|---|---|---|---|
| | BN350 | DC | DMM | APMX | LU | LF |
| BNES 1060 | ❍ | 6,0 | 10 | 7,0 | 11 | 60 |
| 1080 | ❍ | 8,0 | 10 | 10,0 | 14 | 70 |
| 1100 | ❍ | 10,0 | 12 | 12,0 | 17 | 75 |
| 1120 | ❍ | 12,0 | 12 | 14,0 | 20 | 80 |
| 1140 | ❍ | 14,0 | 16 | 16,0 | 21,5 | 80 |

## ■ Recommended Cutting Conditions

Cutting speed: $v_c$ (m/min), Spindle revolutions: n (rpm), Feed per tooth: $f_z$ (mm/tooth), Feed speed: $v_f$ (mm/min)





Depth of cut : $a_p \leq D$


| Tooling example | DC | Hardened steel ($H_RC$ 50–57) $v_c$ = 100–170 m/min | | | Hardened steel ($H_RC$ 58–65) $v_c$ = 80–150 m/min | | |
|---|---|---|---|---|---|---|---|
| | 6–8 | $a_e \leq$ 0,1 mm | n = 4000–9000 | $v_f$ (mm/min) = 240–540 | $a_e \leq$ 0,08 mm | n = 3200–8000 | $v_f$ (mm/min) = 150–370 |
| | 10–12 | $a_e \leq$ 0,15 mm | n = 2700–5400 | $v_f$ (mm/min) = 180–360 | $a_e \leq$ 0,12 mm | n = 2100–4800 | $v_f$ (mm/min) 120–270 |
| | 14–16 | $a_e \leq$ 0,2 mm | n = 2000–3800 | $v_f$ (mm/min) = 140–260 | $a_e \leq$ 0,15 mm | n = 1600–3400 | $v_f$ (mm/min) = 110–230 |

Recommendation: Dry cutting (Air coolant)
Down-cut milling
Minimise the overhang
Use a rigid machine

## ■ Performance

### ● Long Tool Life and High Efficiency





Work material: X155CrVMo12-1
Hardness: $H_RC$ 60

Cutting data:
$v_c$ = 100 m/min (**Helical Master**)
$v_c$ = 40 m/min (Competitor's coated solid carbide endmill)
$v_f$ = 186 mm/min


Down-cut milling
Dry cutting


### ● Excellent Surface Roughness

"Helical Master" BNES 1080 ø 8,0




Conventional straight flute CBN endmill, ø 8,0




Work material: 15Cr3
Hardness: $H_RC$ 55–58
Cutting data: $v_c$ = 130 m/min
$v_f$ = 310 mm/min

Down-cut milling
Dry cutting





● = Euro stock
❍ = Japan stock

SUMIBORON "MOULD Finish Master"


# BNBP Type



## Characteristics / Application

- High precision machining of hardened steels < HRC70 with long tool life
- Super tough grade SUMIBORON BN350 prevents chipping of the cutting edge
- RE accuracy : ±0,005 mm

## Endmills




## Identification Details

**BNBP 2 R020 - 012 4**

- Endmill Series
- Number of teeth
- Radius of ball nose
- Neck length (LU)
- Shank Diam.


Dimensions (mm)

| Cat. No. | Stock | RE | DC | APMX | LU | LF | DN | DMM |
|---|---|---|---|---|---|---|---|---|
| BNBP 2R0200124 | ● | 0,20 | 0,4 | 0,3 | 1,2 | 50 | 0,37 | 4 |
| 2R0200126 | ● | 0,20 | 0,4 | 0,3 | 1,2 | 50 | 0,37 | 6 |
| 2R0200204 | ❍ | 0,20 | 0,4 | 0,3 | 2,0 | 50 | 0,37 | 4 |
| 2R0200304 | ❍ | 0,20 | 0,4 | 0,3 | 3,0 | 50 | 0,37 | 4 |
| 2R0200404 | ❍ | 0,20 | 0,4 | 0,3 | 4,0 | 50 | 0,37 | 4 |
| BNBP 2R0300154 | ● | 0,30 | 0,6 | 0,4 | 1,5 | 50 | 0,57 | 4 |
| 2R0300156 | ● | 0,30 | 0,6 | 0,4 | 1,5 | 50 | 0,57 | 6 |
| 2R0300304 | ❍ | 0,30 | 0,6 | 0,4 | 3,0 | 50 | 0,57 | 4 |
| 2R0300404 | ❍ | 0,30 | 0,6 | 0,4 | 4,0 | 50 | 0,57 | 4 |
| 2R0300504 | ❍ | 0,30 | 0,6 | 0,4 | 5,0 | 50 | 0,57 | 4 |
| 2R0300604 | ❍ | 0,30 | 0,6 | 0,4 | 0,6 | 50 | 0,57 | 4 |
| BNBP 2R0500254 | ● | 0,50 | 1,0 | 0,6 | 2,5 | 50 | 0,97 | 4 |
| 2R0500256 | ● | 0,50 | 1,0 | 0,6 | 2,5 | 50 | 0,97 | 6 |
| 2R0500304 | ❍ | 0,50 | 1,0 | 0,6 | 3,0 | 50 | 0,97 | 4 |
| 2R0500404 | ❍ | 0,50 | 1,0 | 0,6 | 4,0 | 50 | 0,97 | 4 |
| 2R0500604 | ❍ | 0,50 | 1,0 | 0,6 | 0,6 | 50 | 0,97 | 4 |
| 2R0500804 | ❍ | 0,50 | 1,0 | 0,6 | 8,0 | 50 | 0,97 | 4 |
| BNBP 2R0750404 | ❍ | 0,75 | 1,5 | 0,9 | 4,0 | 50 | 1,47 | 4 |
| 2R0750406 | ● | 0,75 | 1,5 | 0,9 | 4,0 | 50 | 1,47 | 6 |
| BNBP 2R1000554 | ● | 1,00 | 2,0 | 1,4 | 5,5 | 50 | 1,97 | 4 |
| 2R1000556 | ● | 1,00 | 2,0 | 1,4 | 5,5 | 50 | 1,97 | 6 |
| 2R1000804 | ❍ | 1,00 | 2,0 | 1,4 | 8,0 | 50 | 1,97 | 4 |

Grade: BN350

## Recommended Cutting Conditions

| Work Material | | STAVAX, NAK80, SKD61 (< 52HRC) | | | | ELMAX, DC53, SKD11 (< 62HRC) | | | | YXR3, SKH (< 70HRC) | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| RE (mm) | LU (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | ap (mm) | pf (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | ap (mm) | pf (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | ap (mm) | pf (mm) |
| 0,2 | 1,2 | 40.000 | 1.000 | 0,005 | 0,010 | 40.000 | 800 | 0,005 | 0,010 | 40.000 | 600 | 0,005 | 0,005 |
| | 2,0 | 40.000 | 800 | 0,005 | 0,010 | 40.000 | 600 | 0,005 | 0,010 | 40.000 | 400 | 0,005 | 0,005 |
| | 3,0 | 40.000 | 600 | 0,005 | 0,010 | 40.000 | 500 | 0,005 | 0,010 | 40.000 | 300 | 0,005 | 0,005 |
| | 4,0 | 40.000 | 500 | 0,005 | 0,010 | 40.000 | 400 | 0,005 | 0,005 | 40.000 | 200 | 0,005 | 0,005 |
| 0,3 | 1,5 | 40.000 | 1.600 | 0,020 | 0,020 | 40.000 | 1.400 | 0,010 | 0,020 | 40.000 | 1.200 | 0,010 | 0,020 |
| | 2,0 | 40.000 | 1.500 | 0,010 | 0,020 | 40.000 | 1.300 | 0,010 | 0,020 | 40.000 | 1.100 | 0,010 | 0,010 |
| | 3,0 | 40.000 | 1.400 | 0,010 | 0,020 | 40.000 | 1.200 | 0,010 | 0,020 | 40.000 | 1.000 | 0,010 | 0,010 |
| | 4,0 | 30.000 | 1.200 | 0,010 | 0,010 | 30.000 | 1.000 | 0,010 | 0,010 | 30.000 | 700 | 0,005 | 0,010 |
| | 5,0 | 30.000 | 800 | 0,010 | 0,010 | 30.000 | 700 | 0,005 | 0,010 | 30.000 | 600 | 0,005 | 0,005 |
| | 6,0 | 30.000 | 600 | 0,005 | 0,010 | 30.000 | 500 | 0,005 | 0,005 | 30.000 | 400 | 0,005 | 0,005 |
| 0,5 | 2,5 | 40.000 | 2.800 | 0,040 | 0,050 | 40.000 | 2.800 | 0,030 | 0,040 | 40.000 | 2.200 | 0,020 | 0,030 |
| | 3,0 | 40.000 | 2.600 | 0,040 | 0,050 | 40.000 | 2.600 | 0,030 | 0,040 | 40.000 | 2.100 | 0,020 | 0,030 |
| | 4,0 | 40.000 | 2.400 | 0,030 | 0,050 | 40.000 | 2.400 | 0,020 | 0,030 | 40.000 | 2.000 | 0,020 | 0,020 |
| | 6,0 | 25.000 | 1.500 | 0,020 | 0,030 | 25.000 | 1.500 | 0,010 | 0,020 | 25.000 | 1.300 | 0,010 | 0,010 |
| | 8,0 | 16.000 | 1.200 | 0,020 | 0,020 | 16.000 | 1.100 | 0,010 | 0,020 | 16.000 | 850 | 0,010 | 0,010 |
| 0,75 | 4,0 | 32.000 | 2.400 | 0,030 | 0,030 | 32.000 | 2.200 | 0,020 | 0,030 | 32.000 | 2.000 | 0,020 | 0,020 |
| 1,0 | 5,5 | 40.000 | 4.000 | 0,050 | 0,050 | 40.000 | 4.000 | 0,030 | 0,030 | 40.000 | 3.000 | 0,020 | 0,030 |
| | 8,0 | 32.000 | 3.000 | 0,030 | 0,050 | 32.000 | 2.600 | 0,020 | 0,030 | 32.000 | 2.200 | 0,010 | 0,020 |






Important Notes

(1) For stable machining, a more rigid machine is recommended.
(2) Air blast or oil mist coolant is recommended.
(3) Shorten overhang as much as possible.

# NPDRS Type

## SUMIDIA Binderless Radius Endmill **NPDRS** Type




## NPDRS Type Body (for Standard Finishing)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | Real effective length with respect to work material gradient angle | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | NPD10 | DC | RE | APMX | LU | LF | DN | DMM | 0,5° | 1° | 1,5° | 2° | 3° |
| NPDRS 1020 R002-006 | ❍ | 0,2 | 0,02 | 0,10 | 0,6 | 40 | 0,175 | 4 | 0,61 | 0,62 | 0,63 | 0,64 | 0,66 |
| 1020 R005-006 | ❍ | 0,2 | 0,05 | 0,10 | 0,6 | 40 | 0,175 | 4 | 0,61 | 0,62 | 0,63 | 0,64 | 0,66 |
| 1030 R002-010 | ❍ | 0,3 | 0,02 | 0,15 | 1,0 | 40 | 0,27 | 4 | 1,01 | 1,03 | 1,04 | 1,06 | 1,09 |
| 1030 R005-010 | ❍ | 0,3 | 0,05 | 0,15 | 1,0 | 40 | 0,27 | 4 | 1,01 | 1,03 | 1,04 | 1,06 | 1,09 |
| 1050 R005-015 | ❍ | 0,5 | 0,05 | 0,25 | 1,5 | 40 | 0,47 | 4 | 1,61 | 1,66 | 1,72 | 1,78 | 1,92 |
| NPDRS 1050 R010-015 | ❍ | 0,5 | 0,10 | 0,25 | 1,5 | 40 | 0,47 | 4 | 1,61 | 1,66 | 1,71 | 1,77 | 1,91 |
| 1100 R005-030 | ❍ | 1,0 | 0,05 | 0,55 | 3,0 | 40 | 0,95 | 4 | 3,40 | 3,52 | 3,65 | 3,78 | 4,08 |
| 1100 R010-030 | ❍ | 1,0 | 0,10 | 0,55 | 3,0 | 40 | 0,95 | 4 | 3,40 | 3,52 | 3,64 | 3,77 | 4,07 |
| 1100 R020-030 | ❍ | 1,0 | 0,20 | 0,55 | 3,0 | 40 | 0,95 | 4 | 3,40 | 3,51 | 3,63 | 3,76 | 4,05 |
| 1200 R005-040 | ❍ | 2,0 | 0,05 | 0,55 | 4,0 | 40 | 1,95 | 4 | 4,44 | 4,59 | 4,75 | 4,93 | 5,33 |
| NPDRS 1200 R010-040 | ❍ | 2,0 | 0,10 | 0,55 | 4,0 | 40 | 1,95 | 4 | 4,43 | 4,59 | 4,75 | 4,92 | 5,31 |
| 1200 R020-040 | ❍ | 2,0 | 0,20 | 0,55 | 4,0 | 40 | 1,95 | 4 | 4,43 | 4,58 | 4,74 | 4,91 | 5,29 |

## Identification Details

**NPDR** (Series Code) **S** (For standard finishing) **1** (No. of flutes) **020** (Cutting diameter) **R002** (Corner radius) **-** **006** (Length below neck)

## Cutting Diameter and Nose Radius Combinations

| DC | RE 0,02 | RE 0,05 | RE 0,1 | RE 0,2 |
|---|---|---|---|---|
| 0,2 | ❍ | ❍ | | |
| 0,3 | ❍ | ❍ | | |
| 0,5 | | ❍ | ❍ | |
| 1,0 | | ❍ | ❍ | ❍ |
| 2,0 | | ❍ | ❍ | ❍ |

## Recommended Cutting Conditions

- Use a machine with high rigidity for stable cutting.
- Non-water soluble coolant recommended. Supply as a mist or external coolant.
  Take fire prevention precautions to avoid fire hazards caused by sparks igniting during machining or tool breakage.
- Shorten overhang as much as possible.
- Adjust cutting conditions as necessary as machine rigidity and other conditions may vary.
- Depth of cut shown in the table of conditions are maximum depths. Adjust the actual depth of cut to the desired machined surface finish.


| Work Material | | Carbide | | | |
|---|---|---|---|---|---|
| DC (mm) | LU (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | $a_p$ (mm) | $p_f$ (mm) |
| 0,2 | 0,10 | 40.000 | 100 | 0,001 | 0,001 |
| 0,3 | 0,15 | 40.000 | 150 | 0,002 | 0,001 |
| 0,5 | 0,25 | 40.000 | 200 | 0,003 | 0,001 |
| 1,0 | 0,55 | 40.000 | 400 | 0,005 | 0,003 |
| 2,0 | 0,55 | 40.000 | 600 | 0,010 | 0,005 |





❍ = Japan stock

# NPDB(S) Type

## SUMIDIA Binderless Ballnose Endmill **NPDBS** Type / **NPDB** Type




### ■ NPDBS Type Body (for Standard Finishing)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | Real effective length with respect to work material gradient angle | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | NPD10 | RE | DC | APMX | LU | LF | DN | DMM | 0,5° | 1° | 1,5° | 2° | 3° |
| NPDBS 1010-004 | ❍ | 0,1 | 0,2 | 0,1 | 0,4 | 40 | 0,18 | 4 | 0,44 | 0,45 | 0,46 | 0,47 | 0,49 |
| 1020-008 | ❍ | 0,2 | 0,4 | 0,2 | 0,8 | 40 | 0,38 | 4 | 0,83 | 0,84 | 0,85 | 0,86 | 0,89 |
| 1030-010 | ❍ | 0,3 | 0,6 | 0,3 | 1,0 | 40 | 0,58 | 4 | 1,05 | 1,08 | 1,10 | 1,13 | 1,20 |
| 1050-020 | ❍ | 0,5 | 1,0 | 0,5 | 2,0 | 40 | 0,95 | 4 | 2,08 | 2,13 | 2,19 | 2,24 | 2,38 |
| 1100-030 | ❍ | 1,0 | 2,0 | 1,0 | 3,0 | 40 | 1,95 | 4 | 3,13 | 3,20 | 3,27 | 3,35 | 3,53 |

### ■ NPDB Type Body (for Precision Finishing)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | Real effective length with respect to work material gradient angle | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | NPD10 | RE | DC | APMX | LU | LF | DN | DMM | 0,5° | 1° | 1,5° | 2° | 3° |
| NPDB 1010-004 | ❍ | 0,1 | 0,2 | 0,1 | 0,4 | 40 | 0,18 | 4 | 0,44 | 0,45 | 0,46 | 0,47 | 0,49 |
| 1020-008 | ❍ | 0,2 | 0,4 | 0,2 | 0,8 | 40 | 0,38 | 4 | 0,83 | 0,84 | 0,85 | 0,86 | 0,89 |
| 1030-010 | ❍ | 0,3 | 0,6 | 0,3 | 1,0 | 40 | 0,58 | 4 | 1,05 | 1,08 | 1,10 | 1,13 | 1,20 |
| 1050-020 | ❍ | 0,5 | 1,0 | 0,5 | 2,0 | 40 | 0,95 | 4 | 2,08 | 2,13 | 2,19 | 2,24 | 2,38 |
| 1100-030 | ❍ | 1,0 | 2,0 | 1,0 | 3,0 | 40 | 1,95 | 4 | 3,13 | 3,20 | 3,27 | 3,35 | 3,53 |

### ■ Identification Details

| **NPDB** | **(S)** | **1** | **030** | **-** | **010** |
|---|---|---|---|---|---|
| Series Code | For standard finishing | No. of flutes | Ballnose radius | | Length below neck |

### ■ Recommended Cutting Conditions


- Use a machine with high rigidity for stable cutting.
- Non-water soluble coolant recommended. Supply as a mist or external coolant.
  Take fire prevention precautions to avoid fire hazards caused by sparks igniting during machining or tool breakage.
- Shorten overhang as much as possible.
- Adjust cutting conditions as necessary as machine rigidity and other conditions may vary.
- Depth of cut shown in the table of conditions are maximum depths. Adjust the actual depth of cut to the desired machined surface finish.

● Flat Surface Finishing

| Work Material | | Carbide | | | |
|---|---|---|---|---|---|
| RE (mm) | LU (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | $a_p$ (mm) | $p_f$ (mm) |
| 0,1 | 0,4 | 40.000 | 100 | 0,001 | 0,001 |
| 0,2 | 0,8 | 40.000 | 150 | 0,001 | 0,001 |
| 0,3 | 1,0 | 40.000 | 200 | 0,001 | 0,001 |
| 0,5 | 2,0 | 40.000 | 400 | 0,001 | 0,003 |
| 1,0 | 3,0 | 40.000 | 600 | 0,001 | 0,005 |

● Copy Finishing

| Work Material | | Carbide | | | |
|---|---|---|---|---|---|
| RE (mm) | LU (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | $a_p$ (mm) | $p_f$ (mm) |
| 0,1 | 0,4 | 40.000 | 100 | 0,001 | 0,001 |
| 0,2 | 0,8 | 40.000 | 150 | 0,002 | 0,001 |
| 0,3 | 1,0 | 40.000 | 200 | 0,003 | 0,001 |
| 0,5 | 2,0 | 40.000 | 400 | 0,005 | 0,003 |
| 1,0 | 3,0 | 40.000 | 600 | 0,010 | 0,005 |



# Multi-Drills

K

**K1–K68**






| | | |
|---|---|---|
| Selection Guide | **MULTI-DRILLs** | K2–5 |
| **Solid Type Drills** | **SDP** … U3/5/7-**HAK** | K6–13 |
| | **SDM** … U3/5 -**HAK** | K14–19 |
| | **MDW** … **GS** 2/4 | K20–23 |
| Flat MultiDrill | **MDF** | K24–31 |
| Deep Hole Drills | **MDW**… **XHG S / PHT** | K32–33 |
| for Steels | **MDW** … **XHG S** | K34 |
| for Aluminium | **MDW** … **XHT A** | K35 |
| Pilot Hole Drills | **MDW** … **PHT** | K34–35 |
| AURORA COAT Drills | **MDW** … **NHGS** | K36–37 |
| MINI-Drills | **MLDH** … **L/P** | K38–39 |
| | **MDUS / MDSS** | K40 |
| SUMIDIA Coated Drills | **MDS** … **SDC** | K41 |
| **Replaceable Head Type Drills** | **SMD** | K43 |
| Drill Holder | **SMDH** …(D) | K44/48/51 |
| Drill Head for Steels | **SMDT** …D **MTL** | K45 |
| for Stainless Steels | **SMDT** …D **MEL** | K46–47 |
| for Spot Facing | **SMDT** ….**MFS** | K48–49 |
| Large Holes | **SMDT**…..**MTL** | K50–51 |
| **Insert Type Drills** | Expansion **WDX** (2D, 3D, 4D, 5D) | K52–64 |
| Eccentric Sleeve | **WAS** | K65 |
| Plunge Drills | **PDL** (2D, 3D) | K66–68 |
| Multi-Function Mills | **PCT** (3D, 5D) | K67–68 |

# Multi-Drill Series



## General Features

MultiDrill series is Sumitomo's original brand of high performance drills that have a special cutting edge design coupled with an advance carbide substrate.
The series has a comprehensive selection of diameters and drill lengths to cover a wide range of work materials and require-ments, providing high efficiency, high precision and cost effectiveness.

## Solid Carbide Type Multi-Drills Selection

| | **SDP ...** | **SDM ...** | **MDW ...** | **MDF ...** | **MDW ... ○○○** | | | **MLDH** | **MDUS / MDSS** | **MDS ...** |
|---|---|---|---|---|---|---|---|---|---|---|
| Type | **...**U3/5/7 **-HAK** (DIN) | **...**U3/5 **-HAK** (DIN) | **GS** 2/4 | ...S2D, L2D<br>...H3D, H5D | ... **PHT** | ... **XHGS**<br>... **XHTA** | ... **NHGS** | ... P / L | – | ... **SDC** |
| Page | ⇨ K 6–13 | ⇨ K 14–19 | ⇨ K20–23 | ⇨ K24–31 | ⇨ K32–35 | | ⇨ K36–37 | ⇨ K38–39 | ⇨ K40 | ⇨ K41 |
| | | | | | Pilot drill | | | Pilot drill | | |
| Application | P K | P M | P | P | P M K N | | N | P M K | P M K H | N |
| Form | m7 drill DIN type | | h8 drill cylindric | h8 drill cylindric | Extra long DIN type | | Super Multi-Drill | Long Micro Drill | Mini Multi-Drill | Diamond Coated |
| Length (The ratio to øD) | 3D/5D/7D | 3D / 5D | 2 / 4D | S2D/ L2D | H3D/ H5D | 3D | 10D–30D | 3D / 5D / 10D | 5/12/20/30 D | 10D | 3D |
| Coolant holes | Yes | | No | No | Yes | Yes | | Yes | Yes | No | No |
| Coating | AlCrTiN | | DEX (TiAlCr/TiSi) | PVD | | TiAlN | – | DLC | TiAlN | TiAlN / ZX | SUMIDIA |
| Diameter range | 3,0–16,0 | | 2,0–16,0 | 0,3–20,0 | 3,0–16,0 | 4,0–8,0 | 3,0–12,0 | 3,0–16,0 | 0,8–2,0 | 0,03–1,0 | 2,0–10,0 |



## Advantages


- Unique curved flute design with proven enhanced chip formation and removal, resulting in better hole accuracy.
- High speed and high efficient drilling is made possible with the combination of a special substrate with an advanced PVD coating. (10x tool life of HSS drills, 5x the efficiency)
- Wide selection range (Diameter: 0,03–65 mm, Drilling depths L/D: 2–30)
- Other diameters and length can be asked and offered

## Brazed Carbide Type and Insert Type Multi-Drills Selection

| | **SMD** ... ⇨ K43 | | **WDX** ...○○<br>**WAS** ....-.. ⇨ K65 | **PDL** ...○○ | **PCT** ...○○ |
|---|---|---|---|---|---|
| Type |  **SMDT ...(D) MTL** | ⇨ K45, K59 | | | |
| Page |  **SMDT ...D MEL** | ⇨ K46–47 | ⇨ K52–66 | ⇨ K66–68 | ⇨ K67–68 |
| |  **SMDT ... MFS** | ⇨ K49 | | | |
| |  **SMDH ...M-3/5/8** | ⇨ K44, K48 | | | |
| | **SMDH ...M / L / D** | ⇨ K51 | | | |
| |  | |  |  | |
| Application | P M K | | P M K N | | |
| Form | SMDT type carbide head | | Indexable insert drill | Straight flute insert drill | Insert mill |
| Length (The ratio to øD) | 1.5D / 3D / 5D / 8D / 12D | | 2D / 3D / 4D / 5D | 2D / 3D | 3D / 5D |
| Coolant holes | Yes | | Yes | | |
| Coating | TiAlN | | WDXT type insert | | |
| Diameter range | 12,0–42,5 | | 13,0–65,0 | 16,0–40,0 | |

# Selection Guide

## ● According to Drill Types / Applications


| Application | General ⟷ Special | | |
|---|---|---|---|
| Solid Type | m7 DIN Type "Super Multi-Drill"<br>**SDP...U HAK Type**<br>AlCrTiN coated general purpose drill with coolant holes<br><br>Ø 3,0–16 mm<br>L/D: 3, 5, 7<br>⇨ K6–13 | "Super Multi-Drill"<br>**MDW...GS Type**<br>DEX (TiAlCr/TiSi) coated general purpose drill without coolant holes<br><br>Ø 2,0–16 mm<br>L/D:–2, –4<br>⇨ K20–23 | — |
| "Super Multi-Drill" **MDS / MDW** Type | — | — | "Super Multi-Drill"<br>**MDS...D Type**<br>Hardened Steel<br>Exotic Metals<br><br>Ø 1,0–16,1 mm<br>L/D: –3<br>(Stock in Japan) |





## ■ Recommended Cutting Conditions by Work Materials

| Drill \ Work | Steel | Stainless Steel | Cast Iron | Non-ferrous Metalls |
|---|---|---|---|---|
| Solid Type — **SDP...U HAK** **MDW...GS** | 50 ▬▬ 120 (0,2 ├──── 0,35) | 15 ▬▬ 70 (0,1 ├──── 0,2) | 50 ▬▬ 110 (0,2 ├── 0,35) | — |

▬▬ Cutting speed $v_c$ (m/min)
├──── Feed f (mm/rev)

## ● According to Drill Types / Applications

| Application | General ⟷ Special | | |
|---|---|---|---|
| Indexable Drills | Insert Type Drills<br>**WDX Type**<br>High Efficiency and Deep Holes<br><br>Ø 13,0–65,0 mm<br>L/D: 2, 3, 4, 5<br>➪ K52–64 | Replaceable Head Type Drills<br>**SMD Type**<br><br>Ø 12,0–42,5 mm<br>L/D: 3, 5, 8<br>➪ K43–51 | "Multi-Function" Types<br>**PDL & PCT**<br>Plunge Drills and Plunge Mills<br><br>Ø 16,0–40,0 mm<br>L/D: 2, 3, 5<br>➪ K66–68 |

| Application | Deep Hole | Very Small Hole | Precision Hole |
|---|---|---|---|
| Special Purpose Drills | "Super Long Multi-Drill"<br>**MDW...XHGS/XHTA Type**<br>New General Purpose Deep Hole Drill<br><br>Ø 4,0–12,0 mm<br>L/D: 10/15/20/25/30<br>➪ K32–35 | "Long Micro Drill"<br>**MLDH... P/L Type**<br>"P" type for pilot hole<br><br>Ø 0,8–2,0 mm<br>L/D: 5/12/20/30<br>➪ K38–39 | AURORA-Coat Drill<br>**MDW...NHGS Type**<br>For Aluminium Alloy<br><br>Ø 3,0–16,0 mm<br>L/D: 3 / 5 / 10<br>➪ K36–37 |
| | — | "Mini-MultiDrill"<br>**MDSS Type**<br><br>Ø 0,20–1,00 mm<br>L/D: 10<br>➪ K40 | "SUMI-DIA" coaed Drill<br>**MDS...SDC Type**<br>For Aluminium & CFRP*<br><br>CFRP* (Carbon FibreReinforced Plastic)<br>Ø 2–10 mm<br>L/D: –3<br>➪ K41 |
| | — | "Micro Drill"<br>**MDUS Type**<br>For Printed Circuit Boards<br>High precision holes<br><br>Ø 0,05–0,19 mm<br>L/D: –8<br>➪ K40 | — |

## ■ Recommended Cutting Conditions by Work Materials


| Drill \ Work | Steel | Stainless Steel | Cast Iron | Non-ferrous Metalls |
|---|---|---|---|---|
| **SMD** (Ø 20) | 50 ▬ 120<br>0,12 ⊢ 0,35 | 50 ▬ 90<br>0,1 ⊢ 0,25 | 50 ▬ 100<br>0,2 ⊢ 0,45 | 100 ▬ 180<br>0,2 ⊢ 0,4 |
| **WDX** (Ø 18) | 100 ▬ 220<br>0,15 ⊢ 0,25 | 80 ▬ 180<br>0,06 ⊢ 0,18 | 120 ▬ 200<br>0,1 ⊢ 0,32 | 100 ▬ 200<br>0,1 ⊢ 0,25 |
| **MDW...XHT** (Ø 5) | 80 ▬ 120<br>0,15 ⊢ 0,25 | 30 ▬ 60<br>0,08 ⊢ 0,15 | 50 ▬ 90<br>0,15 ⊢ 0,3 | 80 ▬ 160<br>0,12 ⊢ 0,35 |

▬ Cutting speed $v_c$ (m/min)
⊢ Feed f (mm/rev)

# SDP Type (DIN)



## General Features







**Stock Size**

Ø 3,0 – Ø 12,0
Increment 0,1 mm

Ø 12,1 – Ø 16,0
Standard diameter


### Coating Structure






## Advantages

- The specific and optimum solution for a wide range of application conditions
- Top performance parameters, maximum feed and stable long tool life
- Double margin design for high-precision holes
- Good balance of high wear resistance and toughness
- Curved cutting edge - ideal for removing chips
- Reliable and high productivity performance

## Application Range




## Maximum Feed Rate Result

| Feed Rate (mm/rev) | 0,30 | 0,40 | 0,50 | 0,55 | 0,60 | 0,65 | 0,70 | 0,75 | 0,80 |
|---|---|---|---|---|---|---|---|---|---|
| **SDP Type** | OK | OK | OK | OK | OK | OK | OK | OK | |
| Competitor | OK | Breakage! | | | | | | | |


Internal test conditions

| | |
|---|---|
| Drill: | Ø 4, L/D = 5 |
| Work Material: | Carbon Steel (C50) |
| Cutting Data: | $v_c$ = 80 m/rev, $a_p$ = 18 mm |

## Comparison of Tool Life




Competitor: Cut volume: 950 cm³ — SDP Type: Cut volume: 3800 cm³



500 Holes — Work: C50, Drill Dia: 8 mm, L/D = 5 — 2000 Holes

| | |
|---|---|
| Drill: | Ø 8, L/D = 5 |
| Work Material: | Carbon Steel (C50) |
| Cutting Data: | $v_c$=80m/min, f=0,15mm/rev, $a_p$=38mm, Through hole, Internal coolant |



**SDP Type**



Competitor




## Excellent Hole Accuracy


| | Hole Accuracy | Chip Shape |
|---|---|---|
| **SDP Type** |  | Compact cutting chips  |
| Competitor |  | Longer cutting chips  |





| | |
|---|---|
| Drill: | Ø 8, L/D = 5 |
| Workpiece: | Carbon Steel (C50) |
| Cutting Data: | $v_c$=80m/min, f=0,25mm/rev, $a_p$=24mm, Blind-hole, Internal coolant |

## ■ Solid Carbide Drill with Internal Coolant Supply, Ø 3,0–5,6 mm, 3D / 5D /7D





| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 3,0 | 3 | SDP 0300 U3 HAK | ● | 15,0 | 19,5 | 61,5 | 0,5 | 6,0 |
| | 5 | 0300 U5 HAK | ● | 22,0 | 26,5 | 65,5 | | |
| | 7 | 0300 U7 HAK | ● | 26,0 | 30,5 | 69,5 | | |
| 3,1 | 3 | SDP 0310 U3 HAK | ● | 15,0 | 19,6 | 61,6 | 0,6 | 6,0 |
| | 5 | 0310 U5 HAK | ● | 22,0 | 26,6 | 65,6 | | |
| | 7 | 0310 U7 HAK | ● | 26,0 | 30,6 | 69,6 | | |
| 3,2 | 3 | SDP 0320 U3 HAK | ● | 14,8 | 19,6 | 61,6 | 0,6 | 6,0 |
| | 5 | 0320 U5 HAK | ● | 21,8 | 26,6 | 65,6 | | |
| | 7 | 0320 U7 HAK | ● | 25,8 | 30,6 | 69,6 | | |
| 3,25 | 3 | SDP 0325 U3 HAK | ● | 14,7 | 19,6 | 61,6 | 0,6 | 6,0 |
| | 5 | 0325 U5 HAK | ● | 21,7 | 26,6 | 65,6 | | |
| | 7 | 0325 U7 HAK | ● | 25,7 | 30,6 | 69,6 | | |
| 3,3 | 3 | SDP 0330 U3 HAK | ● | 14,7 | 19,6 | 61,6 | 0,6 | 6,0 |
| | 5 | 0330 U5 HAK | ● | 21,7 | 26,6 | 65,6 | | |
| | 7 | 0330 U7 HAK | ● | 25,7 | 30,6 | 69,6 | | |
| 3,4 | 3 | SDP 0340 U3 HAK | ● | 14,5 | 19,6 | 61,6 | 0,6 | 6,0 |
| | 5 | 0340 U5 HAK | ● | 21,5 | 26,6 | 65,6 | | |
| | 7 | 0340 U7 HAK | ● | 31,0 | 36,1 | 74,6 | | |
| 3,5 | 3 | SDP 0350 U3 HAK | ● | 14,4 | 19,6 | 61,6 | 0,6 | 6,0 |
| | 5 | 0350 U5 HAK | ● | 21,4 | 26,6 | 65,6 | | |
| | 7 | 0350 U7 HAK | ● | 30,9 | 36,1 | 74,6 | | |
| 3,6 | 3 | SDP 0360 U3 HAK | ● | 14,3 | 19,7 | 61,7 | 0,7 | 6,0 |
| | 5 | 0360 U5 HAK | ● | 21,3 | 26,7 | 65,7 | | |
| | 7 | 0360 U7 HAK | ● | 30,8 | 36,2 | 74,7 | | |
| 3,7 | 3 | SDP 0370 U3 HAK | ● | 14,2 | 19,7 | 61,7 | 0,7 | 6,0 |
| | 5 | 0370 U5 HAK | ● | 21,2 | 26,7 | 65,7 | | |
| | 7 | 0370 U7 HAK | ● | 30,7 | 36,2 | 74,7 | | |
| 3,8 | 3 | SDP 0380 U3 HAK | ● | 18,0 | 23,7 | 65,7 | 0,7 | 6,0 |
| | 5 | 0380 U5 HAK | ● | 30,0 | 35,7 | 73,7 | | |
| | 7 | 0380 U7 HAK | ● | 32,5 | 38,2 | 74,7 | | |
| 3,9 | 3 | SDP 0390 U3 HAK | ● | 17,9 | 23,7 | 65,7 | 0,7 | 6,0 |
| | 5 | 0390 U5 HAK | ● | 29,9 | 35,7 | 73,7 | | |
| | 7 | 0390 U7 HAK | ● | 32,4 | 38,2 | 74,7 | | |
| 4,0 | 3 | SDP 0400 U3 HAK | ● | 17,7 | 23,7 | 65,7 | 0,7 | 6,0 |
| | 5 | 0400 U5 HAK | ● | 29,7 | 35,7 | 73,7 | | |
| | 7 | 0400 U7 HAK | ● | 32,2 | 38,2 | 74,7 | | |
| 4,1 | 3 | SDP 0410 U3 HAK | ● | 17,6 | 23,7 | 65,7 | 0,7 | 6,0 |
| | 5 | 0410 U5 HAK | ● | 29,6 | 35,7 | 73,7 | | |
| | 7 | 0410 U7 HAK | ● | 32,1 | 38,2 | 74,7 | | |
| 4,2 | 3 | SDP 0420 U3 HAK | ● | 17,5 | 23,8 | 65,8 | 0,8 | 6,0 |
| | 5 | 0420 U5 HAK | ● | 29,5 | 35,8 | 73,8 | | |
| | 7 | 0420 U7 HAK | ● | 32,0 | 38,3 | 74,8 | | |
| 4,3 | 3 | SDP 0430 U3 HAK | ● | 17,4 | 23,8 | 65,8 | 0,8 | 6,0 |
| | 5 | 0430 U5 HAK | ● | 29,4 | 35,8 | 73,8 | | |
| | 7 | 0430 U7 HAK | ● | 40,4 | 46,8 | 84,8 | | |

| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 4,4 | 3 | SDP 0440 U3 HAK | ● | 17,2 | 23,8 | 65,8 | 0,8 | 6,0 |
| | 5 | 0440 U5 HAK | ● | 29,2 | 35,8 | 73,8 | | |
| | 7 | 0440 U7 HAK | ● | 40,2 | 46,8 | 84,8 | | |
| 4,5 | 3 | SDP 0450 U3 HAK | ● | 17,1 | 23,8 | 65,8 | 0,8 | 6,0 |
| | 5 | 0450 U5 HAK | ● | 29,1 | 35,8 | 73,8 | | |
| | 7 | 0450 U7 HAK | ● | 40,1 | 46,8 | 84,8 | | |
| 4,6 | 3 | SDP 0460 U3 HAK | ● | 16,9 | 23,8 | 65,8 | 0,8 | 6,0 |
| | 5 | 0460 U5 HAK | ● | 28,9 | 35,8 | 73,8 | | |
| | 7 | 0460 U7 HAK | ● | 39,9 | 46,8 | 84,8 | | |
| 4,65 | 3 | SDP 0465 U3 HAK | ● | 16,8 | 23,8 | 65,8 | 0,8 | 6,0 |
| | 5 | 0465 U5 HAK | ● | 28,8 | 35,8 | 73,8 | | |
| | 7 | 0465 U7 HAK | ● | 39,8 | 46,8 | 84,8 | | |
| 4,7 | 3 | SDP 0470 U3 HAK | ● | 16,9 | 23,9 | 65,9 | 0,9 | 6,0 |
| | 5 | 0470 U5 HAK | ● | 28,9 | 35,9 | 73,9 | | |
| | 7 | 0470 U7 HAK | ● | 39,9 | 46,9 | 84,9 | | |
| 4,8 | 3 | SDP 0480 U3 HAK | ● | 20,7 | 27,9 | 65,9 | 0,9 | 6,0 |
| | 5 | 0480 U5 HAK | ● | 36,7 | 43,9 | 81,9 | | |
| | 7 | 0480 U7 HAK | ● | 44,7 | 51,9 | 89, | | |
| 4,9 | 3 | SDP 0490 U3 HAK | ● | 20,6 | 27,9 | 65,9 | 0,9 | 6,0 |
| | 5 | 0490 U5 HAK | ● | 36,6 | 43,9 | 81,9 | | |
| | 7 | 0490 U7 HAK | ● | 44,6 | 51,9 | 89,9 | | |
| 5,0 | 3 | SDP 0500 U3 HAK | ● | 20,4 | 27,9 | 65,9 | 0,9 | 6,0 |
| | 5 | 0500 U5 HAK | ● | 36,4 | 43,9 | 81,9 | | |
| | 7 | 0500 U7 HAK | ● | 44,4 | 51,9 | 89,9 | | |
| 5,1 | 3 | SDP 0510 U3 HAK | ● | 20,3 | 27,9 | 65,9 | 0,9 | 6,0 |
| | 5 | 0510 U5 HAK | ● | 36,3 | 43,9 | 81,9 | | |
| | 7 | 0510 U7 HAK | ● | 44,3 | 51,9 | 89,9 | | |
| 5,2 | 3 | SDP 0520 U3 HAK | ● | 20,1 | 27,9 | 65,9 | 0,9 | 6,0 |
| | 5 | 0520 U5 HAK | ● | 36,1 | 43,9 | 81,9 | | |
| | 7 | 0520 U7 HAK | ● | 44,1 | 51,9 | 89,9 | | |
| 5,3 | 3 | SDP 0530 U3 HAK | ● | 20,1 | 28,0 | 66,0 | 1,0 | 6,0 |
| | 5 | 0530 U5 HAK | ● | 36,1 | 44,0 | 82,0 | | |
| | 7 | 0530 U7 HAK | ● | 44,1 | 52,0 | 90,0 | | |
| 5,4 | 3 | SDP 0540 U3 HAK | ● | 19,9 | 28,0 | 66,0 | 1,0 | 6,0 |
| | 5 | 0540 U5 HAK | ● | 35,9 | 44,0 | 82,0 | | |
| | 7 | 0540 U7 HAK | ● | 50,9 | 59,0 | 97,0 | | |
| 5,5 | 3 | SDP 0550 U3 HAK | ● | 19,8 | 28,0 | 66,0 | 1,0 | 6,0 |
| | 5 | 0550 U5 HAK | ● | 35,8 | 44,0 | 82,0 | | |
| | 7 | 0550 U7 HAK | ● | 50,8 | 59,0 | 97,0 | | |
| 5,55 | 3 | SDP 0555 U3 HAK | ● | 19,7 | 28,0 | 66,0 | 1,0 | 6,0 |
| | 5 | 0555 U5 HAK | ● | 35,7 | 44,0 | 82,0 | | |
| | 7 | 0555 U7 HAK | ● | 50,7 | 59,0 | 97,0 | | |
| 5,6 | 3 | SDP 0560 U3 HAK | ● | 19,6 | 28,0 | 66,0 | 1,0 | 6,0 |
| | 5 | 0560 U5 HAK | ● | 35,6 | 44,0 | 82,0 | | |
| | 7 | 0560 U7 HAK | ● | 50,6 | 59,0 | 97,0 | | |

※ Remarks:
Non-Stock Items will be required minimum order quantity for 30 pcs.

● = Euro stock

## ■ Solid Carbide Drill with Internal Coolant Supply, Ø 5,7–8,6 mm, 3D / 5D / 7D





| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 5,7 | 3 | SDP 0570 U3 HAK | ● | 19,5 | 28,0 | 66,0 | 1,0 | 6,0 |
| | 5 | 0570 U5 HAK | ● | 35,5 | 44,0 | 82,0 | | |
| | 7 | 0570 U7 HAK | ● | 50,5 | 59,0 | 97,0 | | |
| 5,8 | 3 | SDP 0580 U3 HAK | ● | 19,4 | 28,1 | 66,1 | 1,1 | 6,0 |
| | 5 | 0580 U5 HAK | ● | 35,4 | 44,1 | 82,1 | | |
| | 7 | 0580 U7 HAK | ● | 50,4 | 59,1 | 97,1 | | |
| 5,9 | 3 | SDP 0590 U3 HAK | ● | 19,3 | 28,1 | 66,1 | 1,1 | 6,0 |
| | 5 | 0590 U5 HAK | ● | 35,3 | 44,1 | 82,1 | | |
| | 7 | 0590 U7 HAK | ● | 50,3 | 59,1 | 97,1 | | |
| 6,0 | 3 | SDP 0600 U3 HAK | ● | 19,1 | 28,1 | 66,1 | 1,1 | 6,0 |
| | 5 | 0600 U5 HAK | ● | 35,1 | 44,1 | 82,1 | | |
| | 7 | 0600 U7 HAK | ● | 50,1 | 59,1 | 97,1 | | |
| 6,1 | 3 | SDP 0610 U3 HAK | ● | 25,0 | 34,1 | 79,1 | 1,1 | 8,0 |
| | 5 | 0610 U5 HAK | ● | 44,0 | 53,1 | 91,1 | | |
| | 7 | 0610 U7 HAK | ● | 59,0 | 68,1 | 106,1 | | |
| 6,2 | 3 | SDP 0620 U3 HAK | ● | 24,8 | 34,1 | 79,1 | 1,1 | 8,0 |
| | 5 | 0620 U5 HAK | ● | 43,8 | 53,1 | 91,1 | | |
| | 7 | 0620 U7 HAK | ● | 58,8 | 68,1 | 106,1 | | |
| 6,3 | 3 | SDP 0630 U3 HAK | ● | 24,7 | 34,1 | 79,1 | 1,1 | 8,0 |
| | 5 | 0630 U5 HAK | ● | 43,7 | 53,1 | 91,1 | | |
| | 7 | 0630 U7 HAK | ● | 58,7 | 68,1 | 106,1 | | |
| 6,4 | 3 | SDP 0640 U3 HAK | ● | 24,6 | 34,2 | 79,2 | 1,2 | 8,0 |
| | 5 | 0640 U5 HAK | ● | 43,6 | 53,2 | 91,2 | | |
| | 7 | 0640 U7 HAK | ● | 58,6 | 68,2 | 106,2 | | |
| 6,5 | 3 | SDP 0650 U3 HAK | ● | 24,5 | 34,2 | 79,2 | 1,2 | 8,0 |
| | 5 | 0650 U5 HAK | ● | 43,5 | 53,2 | 91,2 | | |
| | 7 | 0650 U7 HAK | ● | 58,5 | 68,2 | 106,2 | | |
| 6,6 | 3 | SDP 0660 U3 HAK | ● | 24,3 | 34,2 | 79,2 | 1,2 | 8,0 |
| | 5 | 0660 U5 HAK | ● | 43,3 | 53,2 | 91,2 | | |
| | 7 | 0660 U7 HAK | ● | 58,3 | 68,2 | 106,2 | | |
| 6,7 | 3 | SDP 0670 U3 HAK | ● | 24,2 | 34,2 | 79,2 | 1,2 | 8,0 |
| | 5 | 0670 U5 HAK | ● | 43,2 | 53,2 | 91,2 | | |
| | 7 | 0670 U7 HAK | ● | 58,2 | 68,2 | 106,2 | | |
| 6,8 | 3 | SDP 0680 U3 HAK | ● | 24,0 | 34,2 | 79,2 | 1,2 | 8,0 |
| | 5 | 0680 U5 HAK | ● | 43,0 | 53,2 | 91,2 | | |
| | 7 | 0680 U7 HAK | ● | 58,0 | 68,2 | 106,2 | | |
| 6,9 | 3 | SDP 0690 U3 HAK | ● | 24,0 | 34,3 | 79,3 | 1,3 | 8,0 |
| | 5 | 0690 U5 HAK | ● | 43,0 | 53,3 | 91,3 | | |
| | 7 | 0690 U7 HAK | ● | 68,0 | 78,3 | 116,3 | | |
| 7,0 | 3 | SDP 0700 U3 HAK | ● | 23,8 | 34,3 | 79,3 | 1,3 | 8,0 |
| | 5 | 0700 U5 HAK | ● | 42,8 | 53,3 | 91,3 | | |
| | 7 | 0700 U7 HAK | ● | 67,8 | 78,3 | 116,3 | | |
| 7,1 | 3 | SDP 0710 U3 HAK | ● | 29,7 | 40,3 | 79,3 | 1,3 | 8,0 |
| | 5 | 0710 U5 HAK | ● | 42,7 | 53,3 | 91,3 | | |
| | 7 | 0710 U7 HAK | ● | 67,7 | 78,3 | 116,3 | | |

| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 7,2 | 3 | SDP 0720 U3 HAK | ● | 29,5 | 40,3 | 79,3 | 1,3 | 8,0 |
| | 5 | 0720 U5 HAK | ● | 42,5 | 53,3 | 91,3 | | |
| | 7 | 0720 U7 HAK | ● | 67,5 | 78,3 | 116,3 | | |
| 7,3 | 3 | SDP 0730 U3 HAK | ● | 29,4 | 40,3 | 79,3 | 1,3 | 8,0 |
| | 5 | 0730 U5 HAK | ● | 42,4 | 53,3 | 91,3 | | |
| | 7 | 0730 U7 HAK | ● | 67,4 | 78,3 | 116,3 | | |
| 7,4 | 3 | SDP 0740 U3 HAK | ● | 29,2 | 40,3 | 79,3 | 1,3 | 8,0 |
| | 5 | 0740 U5 HAK | ● | 42,2 | 53,3 | 91,3 | | |
| | 7 | 0740 U7 HAK | ● | 67,2 | 78,3 | 116,3 | | |
| 7,5 | 3 | SDP 0750 U3 HAK | ● | 29,2 | 40,4 | 79,4 | 1,4 | 8,0 |
| | 5 | 0750 U5 HAK | ● | 42,2 | 53,4 | 91,4 | | |
| | 7 | 0750 U7 HAK | ● | 67,2 | 78,4 | 116,4 | | |
| 7,6 | 3 | SDP 0760 U3 HAK | ● | 29,0 | 40,4 | 79,4 | 1,4 | 8,0 |
| | 5 | 0760 U5 HAK | ● | 42,0 | 53,4 | 91,4 | | |
| | 7 | 0760 U7 HAK | ● | 67,0 | 78,4 | 116,4 | | |
| 7,7 | 3 | SDP 0770 U3 HAK | ● | 28,9 | 40,4 | 79,4 | 1,4 | 8,0 |
| | 5 | 0770 U5 HAK | ● | 41,9 | 53,4 | 91,4 | | |
| | 7 | 0770 U7 HAK | ● | 66,9 | 78,4 | 116,4 | | |
| 7,8 | 3 | SDP 0780 U3 HAK | ● | 28,7 | 40,4 | 79,4 | 1,4 | 8,0 |
| | 5 | 0780 U5 HAK | ● | 41,7 | 53,4 | 91,4 | | |
| | 7 | 0780 U7 HAK | ● | 66,7 | 78,4 | 116,4 | | |
| 7,9 | 3 | SDP 0790 U3 HAK | ● | 28,6 | 40,4 | 79,4 | 1,4 | 8,0 |
| | 5 | 0790 U5 HAK | ● | 41,6 | 53,4 | 91,4 | | |
| | 7 | 0790 U7 HAK | ● | 66,6 | 78,4 | 116,4 | | |
| 8,0 | 3 | SDP 0800 U3 HAK | ● | 28,5 | 40,5 | 79,5 | 1,5 | 8,0 |
| | 5 | 0800 U5 HAK | ● | 41,5 | 53,5 | 91,5 | | |
| | 7 | 0800 U7 HAK | ● | 66,5 | 78,5 | 116,5 | | |
| 8,1 | 3 | SDP 0810 U3 HAK | ● | 34,4 | 46,5 | 88,5 | 1,5 | 10,0 |
| | 5 | 0810 U5 HAK | ● | 48,4 | 60,5 | 102,5 | | |
| | 7 | 0810 U7 HAK | ● | 76,4 | 88,5 | 130,5 | | |
| 8,2 | 3 | SDP 0820 U3 HAK | ● | 34,2 | 46,5 | 88,5 | 1,5 | 10,0 |
| | 5 | 0820 U5 HAK | ● | 48,2 | 60,5 | 102,5 | | |
| | 7 | 0820 U7 HAK | ● | 76,2 | 88,5 | 130,5 | | |
| 8,3 | 3 | SDP 0830 U3 HAK | ● | 34,1 | 46,5 | 88,5 | 1,5 | 10,0 |
| | 5 | 0830 U5 HAK | ● | 48,1 | 60,5 | 102,5 | | |
| | 7 | 0830 U7 HAK | ● | 76,1 | 88,5 | 130,5 | | |
| 8,4 | 3 | SDP 0840 U3 HAK | ● | 33,9 | 46,5 | 88,5 | 1,5 | 10,0 |
| | 5 | 0840 U5 HAK | ● | 47,9 | 60,5 | 102,5 | | |
| | 7 | 0840 U7 HAK | ● | 75,9 | 88,5 | 130,5 | | |
| 8,5 | 3 | SDP 0850 U3 HAK | ● | 33,8 | 46,5 | 88,5 | 1,5 | 10,0 |
| | 5 | 0850 U5 HAK | ● | 47,8 | 60,5 | 102,5 | | |
| | 7 | 0850 U7 HAK | ● | 75,8 | 88,5 | 130,5 | | |
| 8,6 | 3 | SDP 0860 U3 HAK | ● | 33,7 | 46,6 | 88,6 | 1,6 | 10,0 |
| | 5 | 0860 U5 HAK | ● | 47,7 | 60,6 | 102,6 | | |
| | 7 | 0860 U7 HAK | ● | 75,7 | 88,6 | 130,6 | | |

※ Remarks:
Non-Stock Items will be required minimum order quantity for 30 pcs.

## ■ Solid Carbide Drill with Internal Coolant Supply, Ø 8,7–11,5 mm, 3D / 5D /7D




| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 8,7 | 3 | SDP 0870 U3 HAK | ● | 33,6 | 46,6 | 88,6 | 1,6 | 10,0 |
| | 5 | 0870 U5 HAK | ● | 47,6 | 60,6 | 102,6 | | |
| | 7 | 0870 U7 HAK | ● | 75,6 | 88,6 | 130,6 | | |
| 8,8 | 3 | SDP 0880 U3 HAK | ● | 33,4 | 46,6 | 88,6 | 1,6 | 10,0 |
| | 5 | 0880 U5 HAK | ● | 47,4 | 60,6 | 102,6 | | |
| | 7 | 0880 U7 HAK | ● | 75,4 | 88,6 | 130,6 | | |
| 8,9 | 3 | SDP 0890 U3 HAK | ● | 33,3 | 46,6 | 88,6 | 1,6 | 10,0 |
| | 5 | 0890 U5 HAK | ● | 47,3 | 60,6 | 102,6 | | |
| | 7 | 0890 U7 HAK | ● | 75,3 | 88,6 | 130,6 | | |
| 9,0 | 3 | SDP 0900 U3 HAK | ● | 33,1 | 46,6 | 88,6 | 1,6 | 10,0 |
| | 5 | 0900 U5 HAK | ● | 47,1 | 60,6 | 102,6 | | |
| | 7 | 0900 U7 HAK | ● | 75,1 | 88,6 | 130,6 | | |
| 9,1 | 3 | SDP 0910 U3 HAK | ● | 33,1 | 46,7 | 88,7 | 1,7 | 10,0 |
| | 5 | 0910 U5 HAK | ● | 47,1 | 60,7 | 102,7 | | |
| | 7 | 0910 U7 HAK | ● | 83,1 | 96,7 | 138,7 | | |
| 9,2 | 3 | SDP 0920 U3 HAK | ● | 32,9 | 46,7 | 88,7 | 1,7 | 10,0 |
| | 5 | 0920 U5 HAK | ● | 46,9 | 60,7 | 102,7 | | |
| | 7 | 0920 U7 HAK | ● | 82,9 | 96,7 | 138,7 | | |
| 9,25 | 3 | SDP 0925 U3 HAK | ● | 32,8 | 46,7 | 88,7 | 1,7 | 10,0 |
| | 5 | 0925 U5 HAK | ● | 46,8 | 60,7 | 102,7 | | |
| | 7 | 0925 U7 HAK | ● | 82,8 | 96,7 | 138,7 | | |
| 9,3 | 3 | SDP 0930 U3 HAK | ● | 32,8 | 46,7 | 88,7 | 1,7 | 10,0 |
| | 5 | 0930 U5 HAK | ● | 46,8 | 60,7 | 102,7 | | |
| | 7 | 0930 U7 HAK | ● | 82,8 | 96,7 | 138,7 | | |
| 9,4 | 3 | SDP 0940 U3 HAK | ● | 32,6 | 46,7 | 88,7 | 1,7 | 10,0 |
| | 5 | 0940 U5 HAK | ● | 46,6 | 60,7 | 102,7 | | |
| | 7 | 0940 U7 HAK | ● | 82,6 | 96,7 | 138,7 | | |
| 9,5 | 3 | SDP 0950 U3 HAK | ● | 32,5 | 46,7 | 88,7 | 1,7 | 10,0 |
| | 5 | 0950 U5 HAK | ● | 46,5 | 60,7 | 102,7 | | |
| | 7 | 0950 U7 HAK | ● | 82,5 | 96,7 | 138,7 | | |
| 9,6 | 3 | SDP 0960 U3 HAK | ● | 32,3 | 46,7 | 88,7 | 1,7 | 10,0 |
| | 5 | 0960 U5 HAK | ● | 46,3 | 60,7 | 102,7 | | |
| | 7 | 0960 U7 HAK | ● | 82,3 | 96,7 | 138,7 | | |
| 9,7 | 3 | SDP 0970 U3 HAK | ● | 32,3 | 46,8 | 88,8 | 1,8 | 10,0 |
| | 5 | 0970 U5 HAK | ● | 46,3 | 60,8 | 102,8 | | |
| | 7 | 0970 U7 HAK | ● | 82,3 | 96,8 | 138,8 | | |
| 9,8 | 3 | SDP 0980 U3 HAK | ● | 32,1 | 46,8 | 88,8 | 1,8 | 10,0 |
| | 5 | 0980 U5 HAK | ● | 46,1 | 60,8 | 102,8 | | |
| | 7 | 0980 U7 HAK | ● | 82,1 | 96,8 | 138,8 | | |
| 9,9 | 3 | SDP 0990 U3 HAK | ● | 32,0 | 46,8 | 88,8 | 1,8 | 10,0 |
| | 5 | 0990 U5 HAK | ● | 46,0 | 60,8 | 102,8 | | |
| | 7 | 0990 U7 HAK | ● | 82,0 | 96,8 | 138,8 | | |
| 10,0 | 3 | SDP 1000 U3 HAK | ● | 31,8 | 46,8 | 88,8 | 1,8 | 10,0 |
| | 5 | 1000 U5 HAK | ● | 45,8 | 60,8 | 102,8 | | |
| | 7 | 1000 U7 HAK | ● | 81,8 | 96,8 | 138,8 | | |


| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 10,1 | 3 | SDP 1010 U3 HAK | ● | 39,7 | 54,8 | 101,8 | 1,8 | 12,0 |
| | 5 | 1010 U5 HAK | ● | 55,7 | 70,8 | 117,8 | | |
| | 7 | 1010 U7 HAK | ● | 92,7 | 107,8 | 154,8 | | |
| 10,2 | 3 | SDP 1020 U3 HAK | ● | 39,6 | 54,9 | 101,9 | 1,9 | 12,0 |
| | 5 | 1020 U5 HAK | ● | 55,6 | 70,9 | 117,9 | | |
| | 7 | 1020 U7 HAK | ● | 92,6 | 107,9 | 154,9 | | |
| 10,3 | 3 | SDP 1030 U3 HAK | ● | 39,5 | 54,9 | 101,9 | 1,9 | 12,0 |
| | 5 | 1030 U5 HAK | ● | 55,5 | 70,9 | 117,9 | | |
| | 7 | 1030 U7 HAK | ● | 92,5 | 107,9 | 154,9 | | |
| 10,4 | 3 | SDP 1040 U3 HAK | ● | 39,3 | 54,9 | 101,9 | 1,9 | 12,0 |
| | 5 | 1040 U5 HAK | ● | 55,3 | 70,9 | 117,9 | | |
| | 7 | 1040 U7 HAK | ● | 92,3 | 107,9 | 154,9 | | |
| 10,5 | 3 | SDP 1050 U3 HAK | ● | 39,2 | 54,9 | 101,9 | 1,9 | 12,0 |
| | 5 | 1050 U5 HAK | ● | 55,2 | 70,9 | 117,9 | | |
| | 7 | 1050 U7 HAK | ● | 92,2 | 107,9 | 154,9 | | |
| 10,6 | 3 | SDP 1060 U3 HAK | ● | 39,0 | 54,9 | 101,9 | 1,9 | 12,0 |
| | 5 | 1060 U5 HAK | ● | 55,0 | 70,9 | 117,9 | | |
| | 7 | 1060 U7 HAK | ● | 92,0 | 107,9 | 154,9 | | |
| 10,7 | 3 | SDP 1070 U3 HAK | ● | 38,9 | 54,9 | 101,9 | 1,9 | 12,0 |
| | 5 | 1070 U5 HAK | ● | 54,9 | 70,9 | 117,9 | | |
| | 7 | 1070 U7 HAK | ● | 91,9 | 107,9 | 154,9 | | |
| 10,8 | 3 | SDP 1080 U3 HAK | ● | 38,8 | 55,0 | 102,0 | 2,0 | 12,0 |
| | 5 | 1080 U5 HAK | ● | 54,8 | 71,0 | 118,0 | | |
| | 7 | 1080 U7 HAK | ● | 91,8 | 108,0 | 155,0 | | |
| 10,9 | 3 | SDP 1090 U3 HAK | ● | 38,7 | 55,0 | 102,0 | 2,0 | 12,0 |
| | 5 | 1090 U5 HAK | ● | 54,7 | 71,0 | 118,0 | | |
| | 7 | 1090 U7 HAK | ● | 91,7 | 108,0 | 155,0 | | |
| 11,0 | 3 | SDP 1100 U3 HAK | ● | 38,5 | 55,0 | 102,0 | 2,0 | 12,0 |
| | 5 | 1100 U5 HAK | ● | 54,5 | 71,0 | 118,0 | | |
| | 7 | 1100 U7 HAK | ● | 91,5 | 108,0 | 155,0 | | |
| 11,1 | 3 | SDP 1110 U3 HAK | ● | 38,4 | 55,0 | 102,0 | 2,0 | 12,0 |
| | 5 | 1110 U5 HAK | ● | 54,4 | 71,0 | 118,0 | | |
| | 7 | 1110 U7 HAK | ● | 99,4 | 116,0 | 163,0 | | |
| 11,2 | 3 | SDP 1120 U3 HAK | ● | 38,2 | 55,0 | 102,0 | 2,0 | 12,0 |
| | 5 | 1120 U5 HAK | ● | 54,2 | 71,0 | 118,0 | | |
| | 7 | 1120 U7 HAK | ● | 99,2 | 116,0 | 163,0 | | |
| 11,3 | 3 | SDP 1130 U3 HAK | ● | 38,2 | 55,1 | 102,1 | 2,1 | 12,0 |
| | 5 | 1130 U5 HAK | ● | 54,2 | 71,1 | 118,1 | | |
| | 7 | 1130 U7 HAK | ● | 99,2 | 116,1 | 163,1 | | |
| 11,4 | 3 | SDP 1140 U3 HAK | ● | 38,0 | 55,1 | 102,1 | 2,1 | 12,0 |
| | 5 | 1140 U5 HAK | ● | 54,0 | 71,1 | 118,1 | | |
| | 7 | 1140 U7 HAK | ● | 99,0 | 116,1 | 163,1 | | |
| 11,5 | 3 | SDP 1150 U3 HAK | ● | 37,9 | 55,1 | 102,1 | 2,1 | 12,0 |
| | 5 | 1150 U5 HAK | ● | 53,9 | 71,1 | 118,1 | | |
| | 7 | 1150 U7 HAK | ● | 98,9 | 116,1 | 163,1 | | |

※ Remarks:
Non-Stock Items will be required minimum order quantity for 30 pcs.



● = Euro stock
❑ = Delivery on request

## ■ Solid Carbide Drill with Internal Coolant Supply, Ø 11,6–14,5 mm, 3D / 5D / 7D





| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 11,6 | 3 | SDP 1160 U3 HAK | ● | 37,7 | 55,1 | 102,1 | 2,1 | 12,0 |
| | 5 | 1160 U5 HAK | ● | 53,7 | 71,1 | 118,1 | | |
| | 7 | 1160 U7 HAK | ● | 98,7 | 116,1 | 163,1 | | |
| 11,7 | 3 | SDP 1170 U3 HAK | ● | 37,6 | 55,1 | 102,1 | 2,1 | 12,0 |
| | 5 | 1170 U5 HAK | ● | 53,6 | 71,1 | 118,1 | | |
| | 7 | 1170 U7 HAK | ● | 98,6 | 116,1 | 163,1 | | |
| 11,8 | 3 | SDP 1180 U3 HAK | ● | 37,4 | 55,1 | 102,1 | 2,1 | 12,0 |
| | 5 | 1180 U5 HAK | ● | 53,4 | 71,1 | 118,1 | | |
| | 7 | 1180 U7 HAK | ● | 98,4 | 116,1 | 163,1 | | |
| 11,9 | 3 | SDP 1190 U3 HAK | ● | 37,4 | 55,2 | 102,2 | 2,2 | 12,0 |
| | 5 | 1190 U5 HAK | ● | 53,4 | 71,2 | 118,2 | | |
| | 7 | 1190 U7 HAK | ● | 98,4 | 116,2 | 163,2 | | |
| 12,0 | 3 | SDP 1200 U3 HAK | ● | 37,2 | 55,2 | 102,2 | 2,2 | 12,0 |
| | 5 | 1200 U5 HAK | ● | 53,2 | 71,2 | 118,2 | | |
| | 7 | 1200 U7 HAK | ● | 98,2 | 116,2 | 163,2 | | |
| 12,1 | 3 | SDP 1210 U3 HAK | ❑ | 42,1 | 60,2 | 107,2 | 2,2 | 14,0 |
| | 5 | 1210 U5 HAK | ● | 59,1 | 77,2 | 124,2 | | |
| | 7 | 1210 U7 HAK | ❑ | 117,1 | 135,2 | 182,2 | | |
| 12,2 | 3 | SDP 1220 U3 HAK | ● | 41,9 | 60,2 | 107,2 | 2,2 | 14,0 |
| | 5 | 1220 U5 HAK | ● | 58,9 | 77,2 | 124,2 | | |
| | 7 | 1220 U7 HAK | ● | 116,9 | 135,2 | 182,2 | | |
| 12,3 | 3 | SDP 1230 U3 HAK | ❑ | 41,8 | 60,2 | 107,2 | 2,2 | 14,0 |
| | 5 | 1230 U5 HAK | ● | 58,8 | 77,2 | 124,2 | | |
| | 7 | 1230 U7 HAK | ❑ | 116,8 | 135,2 | 182,2 | | |
| 12,4 | 3 | SDP 1240 U3 HAK | ❑ | 41,7 | 60,3 | 107,3 | 2,3 | 14,0 |
| | 5 | 1240 U5 HAK | ● | 58,7 | 77,3 | 124,3 | | |
| | 7 | 1240 U7 HAK | ❑ | 116,7 | 135,3 | 182,3 | | |
| 12,5 | 3 | SDP 1250 U3 HAK | ● | 41,6 | 60,3 | 107,3 | 2,3 | 14,0 |
| | 5 | 1250 U5 HAK | ● | 58,6 | 77,3 | 124,3 | | |
| | 7 | 1250 U7 HAK | ● | 116,6 | 135,3 | 182,3 | | |
| 12,6 | 3 | SDP 1260 U3 HAK | ❑ | 41,4 | 60,3 | 107,3 | 2,3 | 14,0 |
| | 5 | 1260 U5 HAK | ● | 58,4 | 77,3 | 124,3 | | |
| | 7 | 1260 U7 HAK | ❑ | 116,4 | 135,3 | 182,3 | | |
| 12,7 | 3 | SDP 1270 U3 HAK | ❑ | 41,3 | 60,3 | 107,3 | 2,3 | 14,0 |
| | 5 | 1270 U5 HAK | ● | 58,3 | 77,3 | 124,3 | | |
| | 7 | 1270 U7 HAK | ❑ | 116,3 | 135,3 | 182,3 | | |
| 12,8 | 3 | SDP 1280 U3 HAK | ❑ | 41,1 | 60,3 | 107,3 | 2,3 | 14,0 |
| | 5 | 1280 U5 HAK | ● | 58,1 | 77,3 | 124,3 | | |
| | 7 | 1280 U7 HAK | ❑ | 116,3 | 135,3 | 182,3 | | |
| 12,9 | 3 | SDP 1290 U3 HAK | ❑ | 41,0 | 60,3 | 107,3 | 2,3 | 14,0 |
| | 5 | 1290 U5 HAK | ● | 58,0 | 77,3 | 124,3 | | |
| | 7 | 1290 U7 HAK | ❑ | 116,0 | 135,3 | 182,3 | | |
| 13,0 | 3 | SDP 1300 U3 HAK | ● | 40,9 | 60,4 | 107,4 | 2,4 | 14,0 |
| | 5 | 1300 U5 HAK | ● | 57,9 | 77,4 | 124,4 | | |
| | 7 | 1300 U7 HAK | ● | 115,9 | 135,4 | 182,4 | | |

| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 13,1 | 3 | SDP 1310 U3 HAK | ❑ | 40,8 | 60,4 | 107,4 | 2,4 | 14,0 |
| | 5 | 1310 U5 HAK | ● | 57,8 | 77,4 | 124,4 | | |
| | 7 | 1310 U7 HAK | ❑ | 115,8 | 135,4 | 182,4 | | |
| 13,2 | 3 | SDP 1320 U3 HAK | ❑ | 40,6 | 60,4 | 107,4 | 2,4 | 14,0 |
| | 5 | 1320 U5 HAK | ● | 57,6 | 77,4 | 124,4 | | |
| | 7 | 1320 U7 HAK | ❑ | 115,6 | 135,4 | 182,4 | | |
| 13,3 | 3 | SDP 1330 U3 HAK | ❑ | 40,5 | 60,4 | 107,4 | 2,4 | 14,0 |
| | 5 | 1330 U5 HAK | ● | 57,5 | 77,4 | 124,4 | | |
| | 7 | 1330 U7 HAK | ❑ | 115,5 | 135,4 | 182,4 | | |
| 13,4 | 3 | SDP 1340 U3 HAK | ❑ | 40,3 | 60,4 | 107,4 | 2,4 | 14,0 |
| | 5 | 1340 U7 HAK | ● | 57,3 | 77,4 | 124,4 | | |
| | 7 | 1340 U7 HAK | ❑ | 115,3 | 135,4 | 182,4 | | |
| 13,5 | 3 | SDP 1350 U3 HAK | ● | 40,3 | 60,5 | 107,5 | 2,5 | 14,0 |
| | 5 | 1350 U5 HAK | ● | 57,3 | 77,5 | 124,5 | | |
| | 7 | 1350 U7 HAK | ● | 115,3 | 135,5 | 182,5 | | |
| 13,6 | 3 | SDP 1360 U3 HAK | ❑ | 40,1 | 60,5 | 107,5 | 2,5 | 14,0 |
| | 5 | 1360 U5 HAK | ● | 57,1 | 77,5 | 124,5 | | |
| | 7 | 1360 U7 HAK | ❑ | 115,1 | 135,5 | 182,5 | | |
| 13,7 | 3 | SDP 1370 U3 HAK | ● | 40,0 | 60,5 | 107,5 | 2,5 | 14,0 |
| | 5 | 1370 U5 HAK | ● | 57,0 | 77,5 | 124,5 | | |
| | 7 | 1370 U7 HAK | ● | 115,0 | 135,5 | 182,5 | | |
| 13,8 | 3 | SDP 1380 U3 HAK | ❑ | 39,8 | 60,5 | 107,5 | 2,5 | 14,0 |
| | 5 | 1380 U5 HAK | ● | 56,8 | 77,5 | 124,5 | | |
| | 7 | 1380 U7 HAK | ❑ | 114,8 | 135,5 | 182,5 | | |
| 13,9 | 3 | SDP 13900 U3 HAK | ❑ | 39,7 | 60,5 | 107,5 | 2,5 | 14,0 |
| | 5 | 1390 U5 HAK | ● | 56,7 | 77,5 | 124,5 | | |
| | 7 | 1390 U7 HAK | ❑ | 114,7 | 135,5 | 182,5 | | |
| 14,0 | 3 | SDP 1400 U3 HAK | ● | 39,5 | 60,5 | 107,5 | 2,5 | 14,0 |
| | 5 | 1400 U5 HAK | ● | 56,5 | 77,5 | 124,5 | | |
| | 7 | 1400 U7 HAK | ● | 114,5 | 135,5 | 182,5 | | |
| 14,1 | 3 | SDP 1410 U3 HAK | ❑ | 43,5 | 64,6 | 114,6 | 2,6 | 16,0 |
| | 5 | 1410 U5 HAK | ● | 61,5 | 82,6 | 132,6 | | |
| | 7 | 1410 U7 HAK | ❑ | 132,5 | 153,6 | 203,6 | | |
| 14,2 | 3 | SDP 1420 U3 HAK | ● | 43,3 | 64,6 | 114,6 | 2,6 | 16,0 |
| | 5 | 1420 U5 HAK | ● | 61,3 | 82,6 | 132,6 | | |
| | 7 | 1420 U7 HAK | ● | 132,3 | 153,6 | 203,6 | | |
| 14,3 | 3 | SDP 1430 U3 HAK | ❑ | 43,2 | 64,6 | 114,6 | 2,6 | 16,0 |
| | 5 | 1430 U5 HAK | ● | 61,2 | 82,6 | 132,6 | | |
| | 7 | 1430 U7 HAK | ❑ | 132,2 | 153,6 | 203,6 | | |
| 14,4 | 3 | SDP 1440 U3 HAK | ❑ | 43,0 | 64,6 | 114,6 | 2,6 | 16,0 |
| | 5 | 1440 U5 HAK | ● | 61,0 | 82,6 | 132,6 | | |
| | 7 | 1440 U7 HAK | ❑ | 132,0 | 153,6 | 203,6 | | |
| 14,5 | 3 | SDP 1450 U3 HAK | ● | 42,9 | 64,6 | 114,6 | 2,6 | 16,0 |
| | 5 | 1450 U5 HAK | ● | 60,9 | 82,6 | 132,6 | | |
| | 7 | 1450 U7 HAK | ● | 131,9 | 153,6 | 203,6 | | |

※ Remarks:
❑ Non-Stock Items will be required minimum order quantity for 30 pcs.

## ■ Solid Carbide Drill with Internal Coolant Supply, Ø 14,6–16,0 mm, 3D / 5D / 7D




| DC | L/D | Cat. No. | Stock | LU | LCF | OAL | PL | DCON |
|---|---|---|---|---|---|---|---|---|
| 14,6 | 3 | SDP 1460 U3 HAK | ❑ | 42,8 | 64,7 | 114,7 | 2,7 | 16,0 |
| | 5 | 1460 U5 HAK | ● | 60,8 | 82,7 | 132,7 | | |
| | 7 | 1460 U7 HAK | ❑ | 131,8 | 153,7 | 203,7 | | |
| 14,7 | 3 | SDP 1470 U3 HAK | ● | 42,7 | 64,7 | 114,7 | 2,7 | 16,0 |
| | 5 | 1470 U5 HAK | ● | 60,7 | 82,7 | 132,7 | | |
| | 7 | 1470 U7 HAK | ● | 131,7 | 153,7 | 203,7 | | |
| 14,8 | 3 | SDP 1480 U3 HAK | ❑ | 42,5 | 64,7 | 114,7 | 2,7 | 16,0 |
| | 5 | 1480 U5 HAK | ● | 60,5 | 82,7 | 132,7 | | |
| | 7 | 1480 U7 HAK | ❑ | 131,5 | 153,7 | 203,7 | | |
| 14,9 | 3 | SDP 1490 U3 HAK | ❑ | 42,4 | 64,7 | 114,7 | 2,7 | 16,0 |
| | 5 | 1490 U5 HAK | ● | 60,4 | 82,7 | 132,7 | | |
| | 7 | 1490 U7 HAK | ❑ | 131,4 | 153,7 | 203,7 | | |
| 15,0 | 3 | SDP 1500 U3 HAK | ● | 42,2 | 64,7 | 114,7 | 2,7 | 16,0 |
| | 5 | 1500 U5 HAK | ● | 60,2 | 82,7 | 132,7 | | |
| | 7 | 1500 U7 HAK | ● | 131,2 | 153,7 | 203,7 | | |
| 15,1 | 3 | SDP 1510 U3 HAK | ❑ | 42,1 | 64,7 | 114,7 | 2,7 | 16,0 |
| | 5 | 1510 U5 HAK | ● | 60,1 | 82,7 | 132,7 | | |
| | 7 | 1510 U7 HAK | ❑ | 131,1 | 153,7 | 203,7 | | |
| 15,2 | 3 | SDP 1520 U3 HAK | ● | 42,0 | 64,8 | 114,8 | 2,8 | 16,0 |
| | 5 | 1520 U5 HAK | ● | 60,0 | 82,8 | 132,8 | | |
| | 7 | 1520 U7 HAK | ● | 131,0 | 153,8 | 203,8 | | |
| 15,3 | 3 | SDP 1530 U3 HAK | ❑ | 41,9 | 64,8 | 114,8 | 2,8 | 16,0 |
| | 5 | 1530 U5 HAK | ● | 59,9 | 82,8 | 132,8 | | |
| | 7 | 1530 U7 HAK | ❑ | 130,9 | 153,8 | 203,8 | | |
| 15,4 | 3 | SDP 1540 U3 HAK | ❑ | 41,7 | 64,8 | 114,8 | 2,8 | 16,0 |
| | 5 | 1540 U5 HAK | ● | 59,7 | 82,8 | 132,8 | | |
| | 7 | 1540 U7 HAK | ❑ | 130,7 | 153,8 | 203,8 | | |
| 15,5 | 3 | SDP 1550 U3 HAK | ● | 41,6 | 64,8 | 114,8 | 2,8 | 16,0 |
| | 5 | 1550 U5 HAK | ● | 59,6 | 82,8 | 132,8 | | |
| | 7 | 1550 U7 HAK | ● | 130,6 | 153,8 | 203,8 | | |
| 15,6 | 3 | SDP 1560 U3 HAK | ❑ | 41,4 | 64,8 | 114,8 | 2,8 | 16,0 |
| | 5 | 1560 U5 HAK | ● | 59,4 | 82,8 | 132,8 | | |
| | 7 | 1560 U7 HAK | ❑ | 130,4 | 153,8 | 203,8 | | |
| 15,7 | 3 | SDP 1570 U3 HAK | ● | 41,4 | 64,9 | 114,9 | 2,9 | 16,0 |
| | 5 | 1570 U5 HAK | ● | 59,4 | 82,9 | 132,9 | | |
| | 7 | 1570 U7 HAK | ● | 130,4 | 153,9 | 203,9 | | |
| 15,8 | 3 | SDP 1580 U3 HAK | ❑ | 41,2 | 64,9 | 114,9 | 2,9 | 16,0 |
| | 5 | 1580 U5 HAK | ● | 59,2 | 82,9 | 132,9 | | |
| | 7 | 1580 U7 HAK | ❑ | 130,2 | 153,9 | 203,9 | | |
| 15,9 | 3 | SDP 1590 U3 HAK | ❑ | 41,1 | 64,9 | 114,9 | 2,9 | 16,0 |
| | 5 | 1590 U5 HAK | ● | 59,1 | 82,9 | 132,9 | | |
| | 7 | 1590 U7 HAK | ❑ | 130,1 | 153,9 | 203,9 | | |
| 16,0 | 3 | SDP 1600 U3 HAK | ● | 40,9 | 64,9 | 114,9 | 2,9 | 16,0 |
| | 5 | 1600 U5 HAK | ● | 58,9 | 82,9 | 132,9 | | |
| | 7 | 1600 U7 HAK | ● | 129,9 | 153,9 | 203,9 | | |

※ Remarks:
❑ Non-Stock Items will be required minimum order quantity for 30 pcs.





● = Euro stock
❑ = Delivery on request

## Recommended Cutting Conditions

| Material Group | | | | | | SDP_____U_HAK PCX70 | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| ISO 513 | Work Material | Type/ Structure | $R_m$ N/mm² | Hardness HB30 | Fitness | Ø 3,0–6,0 mm | | Ø 6,1–10,0 mm | | Ø 10,1–16,0 mm | |
| | | | | | | $v_c$=m/min | Feed rate (mm/rev) | $v_c$=m/min | Feed rate (mm/rev) | $v_c$=m/min | Feed rate (mm/rev) |
| P | Carbon steel Cast steel | free cutting steel construction steel case-hardened steel heat-treatable steel spring steel | 420 | 125 | ◎ | 50–**80**–120 | 0,15–**0,20**–0,31 | 70–**110**–140 | 0,20–**0,25**–0,42 | 80–**120**–160 | 0,25–**0,30**–0,53 |
| | | | 650 | 190 | ◎ | 50–**80**–120 | 0,15–**0,20**–0,31 | 70–**110**–140 | 0,20–**0,25**–0,42 | 80–**120**–160 | 0,25–**0,30**–0,53 |
| | | | 850 | 250 | ◎ | 50–**80**–120 | 0,15–**0,20**–0,31 | 70–**110**–140 | 0,20–**0,25**–0,42 | 80–**120**–160 | 0,25–**0,30**–0,53 |
| | | | 750 | 270 | ◎ | 50–**80**–120 | 0,15–**0,20**–0,31 | 70–**110**–140 | 0,20–**0,25**–0,42 | 80–**120**–160 | 0,25–**0,30**–0,50 |
| | | | 1000 | 300 | ◎ | 10–**20**–30 | 0,05–**0,06**–0,11 | 15–**22**–30 | 0,08–**0,09**–0,14 | 20–**28**–35 | 0,08–**0,09**–0,16 |
| | Low alloy steel Cast steel | case-hardened steel heat-treatable steel bearing steel nitriding steel cold work steel | 600 | 180 | ◎ | 50–**70**–90 | 0,10–**0,14**–0,24 | 60–**80**–110 | 0,15–**0,20**–0,32 | 70–**100**–120 | 0,20–**0,25**–0,40 |
| | | | 930 | 275 | ◎ | 45–**65**–85 | 0,10–**0,14**–0,24 | 60–**80**–110 | 0,15–**0,22**–0,34 | 65–**95**–120 | 0,20–**0,25**–0,37 |
| | | | 1000 | 300 | ○ | 40–**60**–80 | 0,10–**0,15**–0,26 | 60–**80**–110 | 0,15–**0,20**–0,32 | 60–**90**–120 | 0,20–**0,25**–0,37 |
| | | | 1200 | 350 | ◎ | 35–**55**–75 | 0,10–**0,15**–0,26 | 55–**75**–110 | 0,15–**0,22**–0,32 | 55–**80**–110 | 0,20–**0,27**–0,38 |
| | High alloy steel | tool steel hot work steel | 680 | 200 | ○ | 30–**40**–50 | 0,10–**0,15**–0,25 | 30–**40**–50 | 0,12–**0,20**–0,28 | 30–**40**–50 | 0,12–**0,20**–0,32 |
| | | | 1100 | 325 | ○ | 20–**30**–40 | 0,10–**0,12**–0,23 | 20–**30**– 40 | 0,12–**0,15**–0,27 | 20–**30**–40 | 0,14–**0,18**–0,32 |
| M | Stainless steel Cast steel | martensitic/ferritic | 680 | 200 | ○ | 40–**55**–70 | 0,08–**0,10**–0,21 | 40–**60**–75 | 0,10–**0,12**–0,25 | 50–**70**–80 | 0,10–**0,12**–0,25 |
| | | martensitic | 820 | 240 | ⊙ | 30–**45**–60 | 0,08–**0,10**–0,20 | 40–**60**–70 | 0,10–**0,12**–0,24 | 50–**60**–80 | 0,10–**0,12**–0,24 |
| | | austenitic | 600 | 180 | ⊙ | 30–**45**–60 | 0,08–**0,10**–0,20 | 40–**60**–70 | 0,10–**0,12**–0,24 | 50–**60**–80 | 0,10–**0,12**–0,24 |
| | | Duplex | 740 | 230 | ⊙ | 30–**45**–60 | 0,06–**0,08**–0,18 | 40–**60**–70 | 0,08–**0,10**–0,23 | 50–**60**–80 | 0,10–**0,10**–0,23 |
| K | Cast iron GG | ferritic/pearlitic | | 180 | ◎ | 50–**70**–90 | 0,15–**0,20**–0,36 | 60–**80**–100 | 0,20–**0,25**–0,40 | 70–**100**–120 | 0,25–**0,30**–0,42 |
| | | pearlitic | | 260 | ◎ | 40–**60**–80 | 0,15–**0,20**–0,36 | 50–**70**–90 | 0,20–**0,25**–0,40 | 60–**80**–100 | 0,25–**0,30**–0,42 |
| | Cast iron GGG | ferritic | | 160 | ◎ | 50–**70**–90 | 0,15–**0,18**–0,31 | 60–**80**–100 | 0,20–**0,25**–0,40 | 70–**100**–120 | 0,25–**0,30**–0,42 |
| | | pearlitic | | 250 | ◎ | 40–**60**–80 | 0,15–**0,18**–0,31 | 50–**70**–90 | 0,20–**0,25**–0,40 | 70–**80**–100 | 0,25–**0,30**–0,42 |
| S | Heat resisting alloys | Fe-based | | | ○ | 10–**20**–30 | 0,08–**0,09**–0,13 | 15–**22**–32 | 0,08–**0,10**–0,15 | 20–**28**–35 | 0,10–**0,12**–0,19 |
| | | Ni / Co-based | | | ○ | 10–**20**–30 | 0,08–**0,09**–0,13 | 15–**22**–32 | 0,08–**0,10**–0,15 | 20–**28**–35 | 0,10–**0,12**–0,19 |
| | Titanium Titanium alloys | pure Titanium | 430 | | | | | | | | |
| | | Ti-Basis | | | ○ | 10–**20**–30 | 0,05–**0,06**–0,12 | 15–**22**–32 | 0,08–**0,09**–0,17 | 20–**28**–35 | 0,08–**0,09**–0,17 |
| N | Aluminium Al-wrought alloys | pure aluminium | | | | | | | | | |
| | | wrought alloys | | | | | | | | | |
| | Aluminium Cast alloys | Si ≤ 12% | | | | | | | | | |
| | | Si ≥ 12% | | | ⊙ | 70–**90**–100 | 0,15–**0,20**–0,25 | 80–**100**–120 | 0,20–**0,25**–0,30 | 100–**120**–140 | 0,25–**0,30**–0,35 |
| | | Al - Mg alloys | | | | | | | | | |
| | Zinc die-cast | Zn alloys | | | | | | | | | |
| | Copper alloys | Copper | | | | | | | | | |
| | | Brass | | | ○ | 80–**100**–120 | 0,15–**0,20**–0,25 | 110–**130**–180 | 0,20–**0,25**–0,30 | 160–**180**–200 | 0,25–**0,30**–0,35 |
| | | Bronze | | | | | | | | | |
| H | Hardened steel | 45 HRC | | | ○ | 10–**20**–30 | 0,08–**0,09**–0,10 | 15–**22**–32 | 0,08–**0,10**–0,12 | 20–**28**–35 | 0,12–**0,15**–0,20 |
| | | 55 HRC | | | | | | | | | |
| | | 60 HRC | | | | | | | | | |
| | | > 60 HRC | | | | | | | | | |

◎ Preferred choice ○ Suitable ⊙ Possible


## SDP-Identification

**SDP** **0800** **U** **3** **HAK** PCX70

- **SDP**: **S**umi-**D**rill **P**ower Type
- **0800**: Drill Diameter 8,0 mm
- **U**: Universal
- **3**: Drilling Depth 3D/5D/7D
- **HAK**: DIN 6535 Form HAK
- PCX70: Grade

# SDM Type

## General Features





**Stock Size**

Ø 3,0 – Ø 12,0
Increment 0,1 mm

Ø 12,1 – Ø 16,0
Standard diameter

## Advantages

- High process reliability in stainless steel and low carbon steel
- Can be used on low-performance machines! (→avoids overload!)
- High surface quality in the bore
- Sharp cutting edge
- High adhesion resistance by Sumi-Power Coating



# SDM Type

## Chip Control


| | |
|---|---|
| Drill: | Ø 8 mm, L/D = 5 |
| Work Material: | X5CrNiS18 10 (1.4301) |
| Cutting D ata: | $v_c$=60m/min, f=0,10mm/rev, $a_p$=19mm<br>Internal coolant (2,0MPa) |

**SDM**




Short chips,
good chip evacuation

Competitor A



Partial long chips,
risk of tool breakage
by poor chip evacuation




## Optimal Cutting Forces


| | |
|---|---|
| Drill: | Ø 8 mm, L/D = 5 |
| Work Material: | X5CrNiS18 10 (1.4301) |
| Cutting Data: | $v_c$=60m/min, f=0,20mm/rev, $a_p$=40mm<br>Internal coolant (2,0MPa) |

10 % lower than competitor A


**SDM**




Competitor




## Low Burr Formation




| | |
|---|---|
| Drill: | Ø 8 mm, L/D = 5 |
| Work Material: | X5CrNiS18 10 (1.4301) |
| Cutting Data: | $v_c$=60m/min, f=0,20mm/rev, $a_p$=40mm<br>Internal coolant (2,0MPa) |

**SDM** Competitor A Competitor B



# SDM Type

## Recommended Cutting Conditions

| Material Group | | | | | | SDM_____U_HAK PCX70 | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| ISO 513 | Work Material | Type/ Structure | $R_m$ N/mm² | Hardness HB30 | Fitness | Ø 3,0–6,0 mm | | Ø 6,1–10,0 mm | | Ø 10,1–16,0 mm | |
| | | | | | | $v_c$=m/min | Feed rate (mm/rev) | $v_c$=m/min | Feed rate (mm/rev) | $v_c$=m/min | Feed rate (mm/rev) |
| P | Carbon steel Cast steel | free cutting steel construction steel case-hardened steel heat-treatable steel spring steel | 420 | 125 | ○ | 80–**100**–120 | 0,08–**0,11**–0,14 | 80–**100**–120 | 0,10–**0,15**–0,20 | 80–**100**–120 | 0,20–**0,25**–0,30 |
| | | | 650 | 190 | ○ | 80–**100**–120 | 0,08–**0,11**–0,14 | 80–**100**–120 | 0,10–**0,15**–0,20 | 80–**100**–120 | 0,20–**0,25**–0,30 |
| | | | 850 | 250 | ○ | 80–**100**–120 | 0,08–**0,11**–0,14 | 80–**100**–120 | 0,10–**0,15**–0,20 | 80–**100**–120 | 0,20–**0,25**–0,30 |
| | | | 750 | 270 | ○ | 40–**60**–100 | 0,08–**0,10**–0,12 | 40–**60**–100 | 0,10–**0,12**–0,16 | 40–**60**–100 | 0,15–**0,17**–0,20 |
| | | | 1000 | 300 | | | | | | | |
| | Low alloy steel Cast steel | case-hardened steel heat-treatable steel bearing steel nitriding steel cold work steel | 600 | 180 | ○ | 80–**100**–120 | 0,08–**0,11**–0,14 | 80–**100**–120 | 0,10–**0,15**–0,20 | 80–**100**–120 | 0,20–**0,25**–0,30 |
| | | | 930 | 275 | ○ | 40–**60**–100 | 0,08–**0,10**–0,12 | 40–**60**–100 | 0,10–**0,12**–0,16 | 40–**60**–100 | 0,15–**0,17**–0,20 |
| | | | 1000 | 300 | | | | | | | |
| | | | 1200 | 350 | | | | | | | |
| | High alloy steel / Cast steel | tool steel hot work steel | 680 | 200 | ○ | 40–**60**–100 | 0,08–**0,10**–0,12 | 40–**60**–100 | 0,10–**0,12**–0,16 | 40–**60**–100 | 0,15–**0,17**–0,20 |
| | | | 1100 | 325 | | | | | | | |
| M | Stainless steel Cast steel | martensitic/ferritic | 680 | 200 | ◉ | 40–**60**–100 | 0,08–**0,10**–0,12 | 40–**60**–100 | 0,10–**0,14**–0,18 | 40–**60**–100 | 0,15–**0,20**–0,25 |
| | | martensitic/ferritic | | >200 | ◉ | 30–**50**–80 | 0,08–**0,10**–0,12 | 30–**50**–80 | 0,10–**0,14**–0,18 | 30–**50**–80 | 0,15–**0,20**–0,25 |
| | | martensitic | 820 | 240 | ◉ | 30–**50**–80 | 0,08–**0,10**–0,12 | 30–**50**–80 | 0,10–**0,14**–0,18 | 30–**50**–80 | 0,15–**0,20**–0,25 |
| | | austenitic | 600 | 180 | ◉ | 40–**60**–100 | 0,08–**0,10**–0,12 | 40–**60**–100 | 0,10–**0,14**–0,18 | 40–**60**–100 | 0,15–**0,20**–0,25 |
| | | austenitic | | >200 | ◉ | 30–**50**–80 | 0,08–**0,10**–0,12 | 30–**50**–80 | 0,10–**0,14**–0,18 | 30–**50**–80 | 0,15–**0,20**–0,25 |
| | | Duplex | 740 | 230 | ◉ | 30–**45**–70 | 0,08–**0,10**–0,12 | 30–**45**–70 | 0,10–**0,14**–0,18 | 30–**45**–70 | 0,15–**0,20**–0,25 |
| | | Precipation hardened | | ≤450 | ◉ | 30–**45**–70 | 0,08–**0,10**–0,12 | 30–**45**–70 | 0,10–**0,14**–0,18 | 30–**45**–70 | 0,15–**0,20**–0,25 |
| K | Cast iron GG | ferritic/pearlitic | | 180 | | | | | | | |
| | | pearlitic | | 260 | | | | | | | |
| | Cast iron GGG | ferritic | | 160 | | | | | | | |
| | | pearlitic | | 250 | | | | | | | |
| S | Heat resisting alloys | Fe-based | | | ○ | 20–**30**–40 | 0,06–**0,08**–0,10 | 20–**30**–40 | 0,08–**0,10**–0,12 | 20–**30**–40 | 0,10–**0,12**–0,15 |
| | | Ni / Co-based | | | ○ | 20–**30**–40 | 0,06–**0,08**–0,10 | 20–**30**–40 | 0,08–**0,10**–0,12 | 20–**30**–40 | 0,10–**0,12**–0,15 |
| | Titanium Titanium alloys | pure Titanium | 430 | | | | | | | | |
| | | Ti-Basis | | | ○ | 20–**30**–40 | 0,06–**0,08**–0,10 | 20–**30**–40 | 0,08–**0,10**–0,12 | 20–**30**–40 | 0,10–**0,12**–0,15 |
| N | Aluminium | pure aluminium | | | | | | | | | |
| | | wrought alloys | | | | | | | | | |
| | Aluminium Cast alloys | Si ≤ 12% | | | | | | | | | |
| | | Si ≥ 12% | | | | | | | | | |
| | | Al - Mg alloys | | | | | | | | | |
| | Zinc die-cast | Zn alloys | | | | | | | | | |
| | Copper alloys | Copper | | | | | | | | | |
| | | Brass | | | | | | | | | |
| | | Bronze | | | | | | | | | |
| H | Hardened steel | 45 HRC | | | | | | | | | |
| | | 55 HRC | | | | | | | | | |
| | | 60 HRC | | | | | | | | | |
| | | >60 HRC | | | | | | | | | |

◉ Preferred choice ○ Possible

## SDM-Identification

**SDM** **0800** **U** **3** **HAK** PCX70


- **SDM**: **S**umi-**D**rill **M** (ISO-Code)
- **0800**: Drill Diameter 8,0 mm
- **U**: Universal
- **3**: Drilling Depth 3D/5D
- **HAK**: DIN 6535 Form HAK
- PCX70: Grade





● = Euro stock
❑ = Delivery on request


## ■ Solid Carbide Drill with Internal Coolant Supply, Ø 3,0–7,5 mm, 3D / 5D




| DC (mm) | DMM (mm) | Cat. No. (L/D) 3/5 | 3D Type | | | 5D Type | | |
|---|---|---|---|---|---|---|---|---|
| | | | Stock | Dimensions (mm) | | Stock | Dimensions (mm) | |
| | | | 3 | OAL | LCF | 5 | OAL | LCF |
| 3,0 | 6 | SDM 0300 U □ HAK | ● | 62 | 17 | ● | 66 | 24 |
| 3,1 | | SDM 0310 U □ HAK | ● | | | ● | | |
| 3,2 | | SDM 0320 U □ HAK | ● | | | ● | | |
| 3,25 | | SDM 0325 U □ HAK | ❑ | | | ❑ | | |
| 3,3 | | SDM 0330 U □ HAK | ● | | | ● | | |
| 3,4 | | SDM 0340 U □ HAK | ● | | | ● | | |
| 3,5 | | SDM 0350 U □ HAK | ● | | | ● | | |
| 3,6 | | SDM 0360 U □ HAK | ● | | | ● | | |
| 3,7 | | SDM 0370 U □ HAK | ● | | | ● | | |
| 3,8 | | SDM 0380 U □ HAK | ● | 66 | 21 | ● | 74 | 33 |
| 3,9 | | SDM 0390 U □ HAK | ● | | | ● | | |
| 4,0 | | SDM 0400 U □ HAK | ● | | | ● | | |
| 4,1 | | SDM 0410 U □ HAK | ● | | | ● | | |
| 4,2 | | SDM 0420 U □ HAK | ● | | | ● | | |
| 4,3 | | SDM 0430 U □ HAK | ● | | | ● | | |
| 4,4 | | SDM 0440 U □ HAK | ● | | | ● | | |
| 4,5 | | SDM 0450 U □ HAK | ● | | | ● | | |
| 4,6 | | SDM 0460 U □ HAK | ● | | | ● | | |
| 4,65 | | SDM 0465 U □ HAK | ❑ | | | ❑ | | |
| 4,7 | | SDM 0470 U □ HAK | ● | | | ● | | |
| 4,8 | | SDM 0480 U □ HAK | ● | | 25 | ● | 82 | 41 |
| 4,9 | | SDM 0490 U □ HAK | ● | | | ● | | |
| 5,0 | | SDM 0500 U □ HAK | ● | | | ● | | |
| 5,1 | | SDM 0510 U □ HAK | ● | | | ● | | |
| 5,2 | | SDM 0520 U □ HAK | ● | | | ● | | |
| 5,3 | | SDM 0530 U □ HAK | ● | | | ● | | |
| 5,4 | | SDM 0540 U □ HAK | ● | | | ● | | |
| 5,5 | | SDM 0550 U □ HAK | ● | | | ● | | |
| 5,55 | | SDM 0555 U □ HAK | ❑ | | | ❑ | | |
| 5,6 | | SDM 0560 U □ HAK | ● | | | ● | | |
| 5,7 | | SDM 0570 U □ HAK | ● | | | ● | | |
| 5,8 | | SDM 0580 U □ HAK | ● | | | ● | | |
| 5,9 | | SDM 0590 U □ HAK | ● | | | ● | | |
| 6,0 | | SDM 0600 U □ HAK | ● | | | ● | | |
| 6,1 | 8 | SDM 0610 U □ HAK | ● | 79 | 31 | ● | 91 | 50 |
| 6,2 | | SDM 0620 U □ HAK | ● | | | ● | | |
| 6,3 | | SDM 0630 U □ HAK | ● | | | ● | | |
| 6,4 | | SDM 0640 U □ HAK | ● | | | ● | | |
| 6,5 | | SDM 0650 U □ HAK | ● | | | ● | | |
| 6,6 | | SDM 0660 U □ HAK | ● | | | ● | | |
| 6,7 | | SDM 0670 U □ HAK | ● | | | ● | | |
| 6,8 | | SDM 0680 U □ HAK | ● | | | ● | | |
| 6,9 | | SDM 0690 U □ HAK | ● | | | ● | | |
| 7,0 | | SDM 0700 U □ HAK | ● | | | ● | | |
| 7,1 | | SDM 0710 U □ HAK | ● | | 37 | ● | | |
| 7,2 | | SDM 0720 U □ HAK | ● | | | ● | | |
| 7,3 | | SDM 0730 U □ HAK | ● | | | ● | | |
| 7,4 | | SDM 0740 U □ HAK | ● | | | ● | | |
| 7,5 | | SDM 0750 U □ HAK | ● | | | ● | | |

# SDM Type

## ■ Solid Carbide Drill with Internal Coolant Supply, Ø 7,6–12,0 mm, 3D / 5D





| DC (mm) | DMM (mm) | Cat. No. (L/D) 3/5 | 3D Type Stock 3 | 3D Type Dimensions (mm) OAL | 3D Type Dimensions (mm) LCF | 5D Type Stock 5 | 5D Type Dimensions (mm) OAL | 5D Type Dimensions (mm) LCF |
|---|---|---|---|---|---|---|---|---|
| 7,6 | 8 | SDM 0760 U □ HAK | ● | 79 | 37 | ● | 91 | 50 |
| 7,7 | | SDM 0770 U □ HAK | ● | | | ● | | |
| 7,8 | | SDM 0780 U □ HAK | ● | | | ● | | |
| 7,9 | | SDM 0790 U □ HAK | ● | | | ● | | |
| 8,0 | | SDM 0800 U □ HAK | ● | | | ● | | |
| 8,1 | 10 | SDM 0810 U □ HAK | ● | 89 | 43 | ● | 103 | 57 |
| 8,2 | | SDM 0820 U □ HAK | ● | | | ● | | |
| 8,3 | | SDM 0830 U □ HAK | ● | | | ● | | |
| 8,4 | | SDM 0840 U □ HAK | ● | | | ● | | |
| 8,5 | | SDM 0850 U □ HAK | ● | | | ● | | |
| 8,6 | | SDM 0860 U □ HAK | ● | | | ● | | |
| 8,7 | | SDM 0870 U □ HAK | ● | | | ● | | |
| 8,8 | | SDM 0880 U □ HAK | ● | | | ● | | |
| 8,9 | | SDM 0890 U □ HAK | ● | | | ● | | |
| 9,0 | | SDM 0900 U □ HAK | ● | | | ● | | |
| 9,1 | | SDM 0910 U □ HAK | ● | | | ● | | |
| 9,2 | | SDM 0920 U □ HAK | ● | | | ● | | |
| 9,25 | | SDM 0925 U □ HAK | ❑ | | | ❑ | | |
| 9,3 | | SDM 0930 U □ HAK | ● | | | ● | | |
| 9,4 | | SDM 0940 U □ HAK | ● | | | ● | | |
| 9,5 | | SDM 0950 U □ HAK | ● | | | ● | | |
| 9,6 | | SDM 0960 U □ HAK | ● | | | ● | | |
| 9,7 | | SDM 0970 U □ HAK | ● | | | ● | | |
| 9,8 | | SDM 0980 U □ HAK | ● | | | ● | | |
| 9,9 | | SDM 0990 U □ HAK | ● | | | ● | | |
| 10,0 | | SDM 1000 U □ HAK | ● | | | ● | | |
| 10,1 | 12 | SDM 1010 U □ HAK | ● | 102 | 51 | ● | 118 | 67 |
| 10,2 | | SDM 1020 U □ HAK | ● | | | ● | | |
| 10,3 | | SDM 1030 U □ HAK | ● | | | ● | | |
| 10,4 | | SDM 1040 U □ HAK | ● | | | ● | | |
| 10,5 | | SDM 1050 U □ HAK | ● | | | ● | | |
| 10,6 | | SDM 1060 U □ HAK | ● | | | ● | | |
| 10,7 | | SDM 1070 U □ HAK | ● | | | ● | | |
| 10,8 | | SDM 1080 U □ HAK | ● | | | ● | | |
| 10,9 | | SDM 1090 U □ HAK | ● | | | ● | | |
| 11,0 | | SDM 1100 U □ HAK | ● | | | ● | | |
| 11,1 | | SDM 1110 U □ HAK | ● | | | ● | | |
| 11,2 | | SDM 1120 U □ HAK | ● | | | ● | | |
| 11,3 | | SDM 1130 U □ HAK | ● | | | ● | | |
| 11,4 | | SDM 1140 U □ HAK | ● | | | ● | | |
| 11,5 | | SDM 1150 U □ HAK | ● | | | ● | | |
| 11,6 | | SDM 1160 U □ HAK | ● | | | ● | | |
| 11,7 | | SDM 1170 U □ HAK | ● | | | ● | | |
| 11,8 | | SDM 1180 U □ HAK | ● | | | ● | | |
| 11,9 | | SDM 1190 U □ HAK | ● | | | ● | | |
| 12,0 | | SDM 1200 U □ HAK | ● | | | ● | | |





● = Euro stock
❑ = Delivery on request

## ■ Solid Carbide Drill with Internal Coolant Supply, Ø 12,0–16,0 mm, 3D / 5D




| DC (mm) | DMM (mm) | Cat. No. (L/D) 3/5 | 3D Type | | | 5D Type | | |
|---|---|---|---|---|---|---|---|---|
| | | | Stock | Dimensions (mm) | | Stock | Dimensions (mm) | |
| | | | 3 | OAL | LCF | 5 | OAL | LCF |
| 12,1 | 14 | SDM 1210 U □ HAK | ❑ | 107 | 56 | ❑ | 124 | 73 |
| 12,2 | | SDM 1220 U □ HAK | ❑ | | | ❑ | | |
| 12,3 | | SDM 1230 U □ HAK | ❑ | | | ❑ | | |
| 12,4 | | SDM 1240 U □ HAK | ❑ | | | ❑ | | |
| 12,5 | | SDM 1250 U □ HAK | ● | | | ● | | |
| 12,6 | | SDM 1260 U □ HAK | ❑ | | | ❑ | | |
| 12,7 | | SDM 1270 U □ HAK | ❑ | | | ❑ | | |
| 12,8 | | SDM 1280 U □ HAK | ❑ | | | ❑ | | |
| 12,9 | | SDM 1290 U □ HAK | ❑ | | | ❑ | | |
| 13,0 | | SDM 1300 U □ HAK | ● | | | ● | | |
| 13,1 | | SDM 1310 U □ HAK | ❑ | | | ❑ | | |
| 13,2 | | SDM 1320 U □ HAK | ❑ | | | ❑ | | |
| 13,3 | | SDM 1330 U □ HAK | ❑ | | | ❑ | | |
| 13,4 | | SDM 1340 U □ HAK | ❑ | | | ❑ | | |
| 13,5 | | SDM 1350 U □ HAK | ● | | | ● | | |
| 13,6 | | SDM 1360 U □ HAK | ❑ | | | ❑ | | |
| 13,7 | | SDM 1370 U □ HAK | ❑ | | | ❑ | | |
| 13,8 | | SDM 1380 U □ HAK | ❑ | | | ❑ | | |
| 13,9 | | SDM 1390 U □ HAK | ❑ | | | ❑ | | |
| 14,0 | | SDM 1400 U □ HAK | ● | | | ● | | |
| 14,1 | 16 | SDM 1410 U □ HAK | ❑ | 115 | 60 | ❑ | 133 | 78 |
| 14,2 | | SDM 1420 U □ HAK | ❑ | | | ❑ | | |
| 14,3 | | SDM 1430 U □ HAK | ❑ | | | ❑ | | |
| 14,4 | | SDM 1440 U □ HAK | ❑ | | | ❑ | | |
| 14,5 | | SDM 1450 U □ HAK | ● | | | ● | | |
| 14,6 | | SDM 1460 U □ HAK | ❑ | | | ❑ | | |
| 14,7 | | SDM 1470 U □ HAK | ❑ | | | ❑ | | |
| 14,8 | | SDM 1480 U □ HAK | ❑ | | | ❑ | | |
| 14,9 | | SDM 1490 U □ HAK | ❑ | | | ❑ | | |
| 15,0 | | SDM 1500 U □ HAK | ● | | | ● | | |
| 15,1 | | SDM 1510 U □ HAK | ❑ | | | ❑ | | |
| 15,2 | | SDM 1520 U □ HAK | ❑ | | | ❑ | | |
| 15,3 | | SDM 1530 U □ HAK | ❑ | | | ❑ | | |
| 15,4 | | SDM 1540 U □ HAK | ❑ | | | ❑ | | |
| 15,5 | | SDM 1550 U □ HAK | ● | | | ● | | |
| 15,6 | | SDM 1560 U □ HAK | ❑ | | | ❑ | | |
| 15,7 | | SDM 1570 U □ HAK | ❑ | | | ❑ | | |
| 15,8 | | SDM 1580 U □ HAK | ❑ | | | ❑ | | |
| 15,9 | | SDM 1590 U □ HAK | ❑ | | | ❑ | | |
| 16,0 | | SDM 1600 U □ HAK | ● | | | ● | | |

# DEX Coating




## General Features


- Sumitomo Electric Hardmetal's next-generation drill coating utilises nano-coating technology to provide more than double the tool life of conventional coatings.
- Silicon and chrome improve usure, heat, and adhesion resistance.
- New super multi-layered structure offers significantly improved chip resistance (coating strength).

## Characteristics

- Coating Design
  World's first combined super multi-layered coating is made from alternate layers of super multilayered substrates.




- Characteristics of Films




## DEX Coat Application Examples

- MultiDrill GS Type Drilling Examples

### Comparison of Usure Resistance


Edge Usure Comparison for 70 m Drilling

Shoulder and rake face feature improved usure resistance enabling long tool life.

**DEX** Coating MultiDrill GS Type

Concurrent A Dril






| | |
|---|---|
| Tool: | MDW 0800 GS4 |
| Work Material: | C50 (HB200) |
| Cutting Conditions: | $v_c$ = 70 m/min, f = 0,25 mm/rev, $a_p$ = 32 mm<br>External coolant (Water soluble) |


### Comparison of Adhesion Resistance


Edge Usure Comparison for 100 m Drilling

Offers significantly improved fracture resistance to counter problems caused by shoulder and flute adhesion in soft steel drilling.

**DEX** Coating MultiDrill GS Type

Competitor B Dril






| | |
|---|---|
| Tool: | MDW 0600 GS4 |
| Work Material: | 15CrMo5 (HB120) |
| Cutting Conditions: | $v_c$ = 60 m/min, f = 0,18 mm/rev, $a_p$ = 18 mm<br>External coolant (Water soluble) |

- Long MultiDrill XHT Type Drilling Examples

Reduced margin usure during deep hole MQL drilling increases number of regrinds.

**DEX** Coating


Conventional Coating



| | |
|---|---|
| Tool: | MDW 0497 XHT20 (Ø 4,97 L/D = 29) |
| Work Material: | 42CrMo4 (HB275) Crank Shaft |
| Cutting Conditions: | $v_c$= 70 m/min, f = 0,23 mm/rev, $a_p$ = 75 mm<br>MQL |

- MultiDrill SMD Type Drilling Examples

Offers longer tool life with SEC MultiDrills as well.




| | |
|---|---|
| Tool: | SMDH 210 M (Ø 21,0) |
| Work Material: | 36Mn5 (HB350) Construction Mashine Componemt |
| Cutting Conditions: | $v_c$ = 60 m/min, f = 0,25 mm/rev, $a_p$ = 25 mm<br>Water soluble Coolant |

# SUPER MULTI-DRILLS
# GS Type



## General Features

Super MultiDrill GS types are solid carbide drills that employ a new flute design and wide chip pocket to achieve excellent chip management and evacuation.
DEX coating enables stable and long tool life over a wide range of work materials and applications.

## Characteristics and Applications

- **Long tool life**
  New cutting edge design and special DEX coating provide long tool life with a wide variety of work materials.
- **Stable chip evacuation**
  New flute shape significantly improves chip management and evacuation.
- **Quiet cutting and stable cutting resistance**
  Stable drilling with little wobble even in small machine applications.
- **Environmentally-friendly**
  Compatible with the MQL (Minimum Quantity Lubrication) system.


## Series

| Coolant Supply | Type | Diameter Range (mm) | Hole Depth (L/D) |
|---|---|---|---|
| External (GS Type) | MDW □□□□ GS2 | Ø 0,8 – 16,0 | –2 |
| | MDW □□□□ GS4 | | –4 |

## Performance


### Chip Management

MDW … **GS** | Conventional Type



### Performance Comparison

MDW … **GS** | Conventional Type





GS type provides stable drill behaviour throughout the drilling process.

Tool: MDW 0800 GS4
Work Material: C50 (HB200)
Cutting Conditions: $v_c$ = 80 m/min, f = 0,25 mm/rev, $a_p$ = 24 mm
External Coolant (Water Soluble)

## Application Examples


● Automotive Component
C43 (HB250)

Drill: MDW 0970 GS4 (Ø 9,7 mm)
Cutting Data: $v_c$ = 80 m/min, f = 0,25 mm/rev
$a_p$ = 25 mm
External Coolant (Water Soluble)





● Boron Steel Machine Component
(HRC30)

Drill: MDW 0980 GS2 (Ø 9,8 mm)
Cutting Data: $v_c$ = 70 m/min, f = 0,15 mm/rev
$a_p$ = 7 mm
External Coolant (Water Soluble)




● Machine Component
USt.42-2

Drill: MDW 0800 GS4 (Ø 8,0 mm)
Cutting Data: $v_c$ = 80 m/min, f = 0,25 mm/rev
$a_p$ =25 mm
Internal Coolant (Water Soluble)




# MDW ... GS Type

Without Coolant Holes (2D/4D)

"Super Multi-Layer" DEX (TiAlCr/TiSi) Coated Solid Carbide Drills






Helix angle: 30°
$\ell_1$ = Effective drilling length

## ● Diameter Ø 2,0–6,0 mm

(mm)

| Dimensions DC | ød | Cat. No. 2, 4 | Short Type (2D) Stock 2 | Short Type (2D) Dimensions L | $\ell_1$ | $\ell_2$ | Long Type (4D) Stock 4 | Long Type (4D) Dimensions L | $\ell_1$ | $\ell_2$ |
|---|---|---|---|---|---|---|---|---|---|---|
| **2,0** | 3,0 | MDW 0200 GS☐ | ❍ | 45,4 | 6,0 | 8,4 | ❍ | 49,4 | 13,0 | 15,4 |
| 2,1 | 3,0 | MDW 0210 GS☐ | ❍ | 45,6 | 7,3 | 10,5 | ❍ | 49,6 | 14,5 | 17,5 |
| 2,2 | | MDW 0220 GS☐ | ❍ | | | | ❍ | | | |
| 2,3 | | MDW 0230 GS☐ | ❍ | | | | ❍ | | | |
| 2,4 | | MDW 0240 GS☐ | ❍ | | | | ❍ | | | |
| 2,5 | | MDW 0250 GS☐ | ● | | | | ❍ | | | |
| 2,6 | | MDW 0260 GS☐ | ● | | 9,8 | 13,6 | ❍ | | 16,0 | 19,6 |
| 2,7 | | MDW 0270 GS☐ | ❍ | | | | ❍ | | | |
| 2,8 | | MDW 0280 GS☐ | ● | | | | ❍ | | | |
| 2,9 | | MDW 0290 GS☐ | ❍ | | | | ❍ | | | |
| **3,0** | | MDW 0300 GS☐ | ● | | | | ❍ | | | |
| 3,1 | 4,0 | MDW 0310 GS☐ | ● | 54,8 | 15,5 | 19,7 | ❍ | 60,8 | 20,5 | 24,7 |
| 3,2 | | MDW 0320 GS☐ | ❍ | | | | ❍ | | | |
| 3,3 | | MDW 0330 GS☐ | ❍ | | | | ❍ | | | |
| 3,4 | | MDW 0340 GS☐ | ● | | | | ❍ | | | |
| 3,5 | | MDW 0350 GS☐ | ● | | | | ❍ | | | |
| 3,6 | | MDW 0360 GS☐ | ❍ | | 17,0 | 21,8 | ❍ | | 23,0 | 27,8 |
| 3,7 | | MDW 0370 GS☐ | ❍ | | | | ❍ | | | |
| 3,8 | | MDW 0380 GS☐ | ❍ | | | | ❍ | | | |
| 3,9 | | MDW 0390 GS☐ | ❍ | | | | ❍ | | | |
| **4,0** | | MDW 0400 GS☐ | ● | | | | ❍ | | | |
| 4,1 | 5,0 | MDW 0410 GS☐ | ❍ | 62,0 | 18,5 | 23,9 | ❍ | 77,0 | 25,5 | 31,9 |
| 4,2 | | MDW 0420 GS☐ | ❍ | | | | ❍ | | | |
| 4,3 | | MDW 0430 GS☐ | ❍ | | | | ❍ | | | |
| 4,4 | | MDW 0440 GS☐ | ❍ | | | | ❍ | | | |
| 4,5 | | MDW 0450 GS☐ | ❍ | | | | ❍ | | | |
| 4,6 | | MDW 0460 GS☐ | ❍ | | 20,0 | 26,0 | ❍ | | 33,0 | 39,0 |
| 4,7 | | MDW 0470 GS☐ | ❍ | | | | ❍ | | | |
| 4,8 | | MDW 0480 GS☐ | ❍ | | | | ❍ | | | |
| 4,9 | | MDW 0490 GS☐ | ❍ | | | | ❍ | | | |
| **5,0** | | MDW 0500 GS☐ | ● | | | | ● | | | |
| 5,1 | 6,0 | MDW 0510 GS☐ | ❍ | 66,2 | 19,5 | 26,1 | ● | 82,2 | 33,5 | 40,1 |
| 5,2 | | MDW 0520 GS☐ | ❍ | | | | ❍ | | | |
| 5,3 | | MDW 0530 GS☐ | ❍ | | | | ❍ | | | |
| 5,4 | | MDW 0540 GS☐ | ❍ | | | | ❍ | | | |
| 5,5 | | MDW 0550 GS☐ | ● | | | | ● | | | |
| 5,6 | | MDW 0560 GS☐ | ❍ | | 21,0 | 28,2 | ❍ | | 35,0 | 42,2 |
| 5,7 | | MDW 0570 GS☐ | ❍ | | | | ❍ | | | |
| 5,8 | | MDW 0580 GS☐ | ❍ | | | | ❍ | | | |
| 5,9 | | MDW 0590 GS☐ | ❍ | | | | ❍ | | | |
| **6,0** | | MDW 0600 GS☐ | ● | | | | ● | | | |

## ● Diameter Ø 6,1–10,0 mm

(mm)

| Dimensions DC | ød | Cat. No. 2, 4 | Short Type (2D) Stock 2 | Short Type (2D) Dimensions L | $\ell_1$ | $\ell_2$ | Long Type (4D) Stock 4 | Long Type (4D) Dimensions L | $\ell_1$ | $\ell_2$ |
|---|---|---|---|---|---|---|---|---|---|---|
| 6,1 | 7,0 | MDW 0610 GS☐ | ❍ | 74,5 | 24,5 | 32,3 | ❍ | 84,3 | 35,5 | 43,3 |
| 6,2 | | MDW 0620 GS☐ | ❍ | | | | ❍ | | | |
| 6,3 | | MDW 0630 GS☐ | ❍ | | | | ❍ | | | |
| 6,4 | | MDW 0640 GS☐ | ❍ | | | | ❍ | | | |
| 6,5 | | MDW 0650 GS☐ | ● | | | | ❍ | | | |
| 6,6 | | MDW 0660 GS☐ | ❍ | | 26,1 | 34,5 | | | 36,1 | 44,5 |
| 6,7 | | MDW 0670 GS☐ | ❍ | | | | ❍ | | | |
| 6,8 | | MDW 0680 GS☐ | ❍ | | | | ● | | | |
| 6,9 | | MDW 0690 GS☐ | ❍ | | | | ❍ | | | |
| **7,0** | | MDW 0700 GS☐ | ● | | | | ❍ | | | |
| 7,1 | 8,0 | MDW 0710 GS☐ | ❍ | 79,7 | 25,6 | 34,6 | ❍ | 91,7 | 37,6 | 46,6 |
| 7,2 | | MDW 0720 GS☐ | ❍ | | | | ❍ | | | |
| 7,3 | | MDW 0730 GS☐ | ❍ | | | | ❍ | | | |
| 7,4 | | MDW 0740 GS☐ | ❍ | | | | ❍ | | | |
| 7,5 | | MDW 0750 GS☐ | ● | | | | ❍ | | | |
| 7,6 | | MDW 0760 GS☐ | ❍ | | 28,1 | 37,7 | ❍ | | 40,1 | 49,7 |
| 7,7 | | MDW 0770 GS☐ | ❍ | | | | ❍ | | | |
| 7,8 | | MDW 0780 GS☐ | ❍ | | | | ❍ | | | |
| 7,9 | | MDW 0790 GS☐ | ❍ | | | | ❍ | | | |
| **8,0** | | MDW 0800 GS☐ | ● | | | | ● | | | |
| 8,1 | 9,0 | MDW 0810 GS☐ | ❍ | 83,9 | 27,4 | 37,8 | ❍ | 99,9 | 34,4 | 54,8 |
| 8,2 | | MDW 0820 GS☐ | ❍ | | | | ❍ | | | |
| 8,3 | | MDW 0830 GS☐ | ❍ | | | | ❍ | | | |
| 8,4 | | MDW 0840 GS☐ | ❍ | | | | ❍ | | | |
| 8,5 | | MDW 0850 GS☐ | ❍ | | | | ● | | | |
| 8,6 | | MDW 0860 GS☐ | ❍ | | 29,1 | 39,9 | ❍ | | 46,1 | 56,9 |
| 8,7 | | MDW 0870 GS☐ | ❍ | | | | ❍ | | | |
| 8,8 | | MDW 0880 GS☐ | ❍ | | | | ❍ | | | |
| 8,9 | | MDW 0890 GS☐ | ❍ | | | | ❍ | | | |
| **9,0** | | MDW 0900 GS☐ | ❍ | | | | ❍ | | | |
| 9,1 | 10,0 | MDW 0910 GS☐ | ❍ | 89,0 | 28,6 | 40,0 | ❍ | 107,0 | 48,6 | 60,0 |
| 9,2 | | MDW 0920 GS☐ | ❍ | | | | ❍ | | | |
| 9,3 | | MDW 0930 GS☐ | ❍ | | | | ❍ | | | |
| 9,4 | | MDW 0940 GS☐ | ❍ | | | | ❍ | | | |
| 9,5 | | MDW 0950 GS☐ | | | | | ❍ | | | |
| 9,6 | | MDW 0960 GS☐ | ❍ | | 30,0 | 42,0 | ❍ | | 50,0 | 62,0 |
| 9,7 | | MDW 0970 GS☐ | ❍ | | | | ❍ | | | |
| 9,8 | | MDW 0980 GS☐ | ❍ | | | | ❍ | | | |
| 9,9 | | MDW 0990 GS☐ | ❍ | | | | ❍ | | | |
| **10,0** | | MDW 1000 GS☐ | ● | | | | ● | | | |

## ■ Recommended Cutting Conditions for Multi-Drills GS Type

| Diameter (mm) | | Soft Steels (–200 HB) | General Steels (–300 HB) | Stainless Steels (–200 HB) | Grey Cast Irons | Ductile Cast Irons |
|---|---|---|---|---|---|---|
| –Ø 3 | $v_c$ | 30–**50**–70 | 30–**45**–60 | 10–**30**–40 | 40–**70**–90 | 35–**55**–75 |
| | f | 0,12–0,20 | 0,10–0,20 | 0,06–0,12 | 0,15–0,30 | 0,12–0,20 |
| –Ø 5 | $v_c$ | 40–**70**–100 | 40–**60**–80 | 15–**40**–55 | 40–**70**–90 | 40–**60**–80 |
| | f | 0,15–0,25 | 0,15–0,25 | 0,08–0,15 | 0,15–0,30 | 0,15–0,25 |
| –Ø 10 | $v_c$ | 50–**80**–130 | 50–**70**–110 | 15–**45**–60 | 50–**80**–120 | 50–**70**–100 |
| | f | 0,20–0,35 | 0,20–0,35 | 0,10–0,20 | 0,20–0,35 | 0,20–0,35 |
| –Ø 16 | $v_c$ | 60–**90**–140 | 60–**80**–120 | 20–**50**–60 | 60–**90**–120 | 50–**70**–100 |
| | f | 0,25–0,35 | 0,25–0,35 | 0,10–0,20 | 0,25–0,35 | 0,25–0,35 |

( $v_c$ : Cutting Speed (m/min), f : Feed Rate (mm/rev)) (Min – **Standard** – Max)

● = Euro stock
○ = Japan stock

# MDW ... GS Type

## GS Type for General Purpose Drilling of Steels

● GS Type



Grade: ACX70

### ● Diameter Ø 10,1–13,0 mm

(mm)

| Dimensions | | Cat. No. | Short Type (2D) | | | | Long Type (4D) | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | Stock | Dimensions | | | Stock | Dimensions | | |
| DC (mm) | ød | 2, 4 ↘ | 2 | L | $\ell_1$ | $\ell_2$ | 4 | L | $\ell_1$ | $\ell_2$ |
| 10,1 | 11,0 | MDW 1010 GS☐ | ❍ | 95,3 | 30,6 | 43,2 | ❍ | 116,2 | 55,6 | 68,2 |
| 10,2 | | MDW 1020 GS☐ | ● | | | | ● | | | |
| 10,3 | | MDW 1030 GS☐ | ❍ | | | | ❍ | | | |
| 10,4 | | MDW 1040 GS☐ | ❍ | | | | ❍ | | | |
| 10,5 | | MDW 1050 GS☐ | ● | | | | | | | |
| 10,6 | | MDW 1060 GS☐ | ❍ | | 34,1 | 47,3 | ❍ | | 57,1 | 70,3 |
| 10,7 | | MDW 1070 GS☐ | ❍ | | | | ❍ | | | |
| 10,8 | | MDW 1080 GS☐ | ❍ | | | | ❍ | | | |
| 10,9 | | MDW 1090 GS☐ | ❍ | | | | ❍ | | | |
| **11,0** | | MDW 1100 GS☐ | ❍ | | | | ● | | | |
| 11,1 | 12,0 | MDW 1110 GS☐ | ❍ | 102,5 | 33,6 | 47,4 | ❍ | 123,5 | 59,6 | 73,4 |
| 11,2 | | MDW 1120 GS☐ | ❍ | | | | ❍ | | | |
| 11,3 | | MDW 1130 GS☐ | ❍ | | | | ❍ | | | |
| 11,4 | | MDW 1140 GS☐ | ❍ | | | | ❍ | | | |
| 11,5 | | MDW 1150 GS☐ | | | | | | | | |
| 11,6 | | MDW 1160 GS☐ | ❍ | | 35,1 | 49,5 | ❍ | | 61,1 | 75,5 |
| 11,7 | | MDW 1170 GS☐ | ❍ | | | | ❍ | | | |
| 11,8 | | MDW 1180 GS☐ | ❍ | | | | ❍ | | | |
| 11,9 | | MDW 1190 GS☐ | ❍ | | | | ❍ | | | |
| **12,0** | | MDW 1200 GS☐ | ● | | | | ● | | | |
| 12,1 | 13,0 | MDW 1210 GS☐ | ❍ | 102,7 | 34,6 | 49,6 | ❍ | 139,7 | 63,6 | 78,6 |
| 12,2 | | MDW 1220 GS☐ | ❍ | | | | ❍ | | | |
| 12,3 | | MDW 1230 GS☐ | ❍ | | | | ❍ | | | |
| 12,4 | | MDW 1240 GS☐ | ❍ | | | | ❍ | | | |
| 12,5 | | MDW 1250 GS☐ | ❍ | | | | ❍ | | | |
| 12,6 | | MDW 1260 GS☐ | ❍ | | 36,1 | 51,7 | ❍ | | 65,1 | 80,7 |
| 12,7 | | MDW 1270 GS☐ | ❍ | | | | ❍ | | | |
| 12,8 | | MDW 1280 GS☐ | ❍ | | | | ❍ | | | |
| 12,9 | | MDW 1290 GS☐ | ❍ | | | | ❍ | | | |
| **13,0** | | MDW 1300 GS☐ | ❍ | | | | ❍ | | | |

### ● Diameter Ø 13,1–16,0 mm

(mm)

| Dimensions | | Cat. No. | Short Type (2D) | | | | Long Type (4D) | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | Stock | Dimensions | | | Stock | Dimensions | | |
| DC (mm) | ød | 2, 4 ↘ | 2 | L | $\ell_1$ | $\ell_2$ | 4 | L | $\ell_1$ | $\ell_2$ |
| 13,1 | 14,0 | MDW 1310 GS☐ | ❍ | 107,9 | 36,6 | 52,8 | ❍ | 149,9 | 70,2 | 86,8 |
| 13,2 | | MDW 1320 GS☐ | ❍ | | | | ❍ | | | |
| 13,3 | | MDW 1330 GS☐ | ❍ | | | | ❍ | | | |
| 13,4 | | MDW 1340 GS☐ | ❍ | | | | ❍ | | | |
| 13,5 | | MDW 1350 GS☐ | ❍ | | | | ❍ | | | |
| 13,6 | | MDW 1360 GS☐ | ❍ | | 38,1 | 54,9 | ❍ | | 72,1 | 88,9 |
| 13,7 | | MDW 1370 GS☐ | ❍ | | | | ❍ | | | |
| 13,8 | | MDW 1380 GS☐ | ❍ | | | | ❍ | | | |
| 13,9 | | MDW 1390 GS☐ | ❍ | | | | ❍ | | | |
| **14,0** | | MDW 1400 GS☐ | ❍ | | | | ❍ | | | |
| 14,1 | 15,0 | MDW 1410 GS☐ | ❍ | 111,1 | 37,6 | 55,0 | ❍ | 156,1 | 74,6 | 92,0 |
| 14,2 | | MDW 1420 GS☐ | ❍ | | | | ❍ | | | |
| 14,3 | | MDW 1430 GS☐ | ❍ | | | | ❍ | | | |
| 14,4 | | MDW 1440 GS☐ | ❍ | | | | ❍ | | | |
| 14,5 | | MDW 1450 GS☐ | ❍ | | | | ❍ | | | |
| 14,6 | | MDW 1460 GS☐ | ❍ | | 38,1 | 56,1 | ❍ | | 76,1 | 94,1 |
| 14,7 | | MDW 1470 GS☐ | ❍ | | | | ❍ | | | |
| 14,8 | | MDW 1480 GS☐ | ❍ | | | | ❍ | | | |
| 14,9 | | MDW 1490 GS☐ | ❍ | | | | ❍ | | | |
| **15,0** | | MDW 1500 GS☐ | ❍ | | | | ❍ | | | |
| 15,1 | 16,0 | MDW 1510 GS☐ | ❍ | 115,5 | 37,6 | 56,2 | ❍ | 169,3 | 78,6 | 97,2 |
| 15,2 | | MDW 1520 GS☐ | ❍ | | | | ❍ | | | |
| 15,3 | | MDW 1530 GS☐ | ❍ | | | | ❍ | | | |
| 15,4 | | MDW 1540 GS☐ | ❍ | | | | ❍ | | | |
| 15,5 | | MDW 1550 GS☐ | ❍ | | | | ❍ | | | |
| 15,6 | | MDW 1560 GS☐ | ❍ | | 39,1 | 58,3 | ❍ | | 80,1 | 99,3 |
| 15,7 | | MDW 1570 GS☐ | ❍ | | | | ❍ | | | |
| 15,8 | | MDW 1580 GS☐ | ❍ | | | | ❍ | | | |
| 15,9 | | MDW 1590 GS☐ | ❍ | | | | ❍ | | | |
| **16,0** | | MDW 1600 GS☐ | ❍ | | | | ❍ | | | |

## ■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs.
Please specify the Cat. No. For example, if the diameter of the drill is 10,2 mm, please indicate as follow.

**E.g.**, **MDW 1020 GS 2/4**, ACX70 (Grade)

- **MDW**: SUPER MULTI-DRILLS
- **1020**: Drill diameter **10,2** mm
- **GS**: **GS** type MULTI-DRILLS
- **2/4**: Drilling depth (The ratio to ØD): –2 / –4



## General Features

The flat MultiDrill MDF type is a solid carbide drill that can be used for various purposes including high-efficiency spot facing and drilling in inclined and curved surfaces.





## Advantages

- Can be used in a variety of drilling applications thanks to its point angle of 180°
  Applicable to high-efficiency spot facing, drilling in non-horizontal surfaces such as inclined and cylindrical surfaces and interrupted drilling. It also reduces burrs at hole exits.
- Improved machining stability
  Achieves high rigidity by employing RS THINNING, which ensures web thickness on the bottom face.
- Excellent chip evacuation performance
  Achieves excellent chip evacuation thanks to its wide chip pocket and high-quality rake face shape.
- Excellent cutting edge strength
  Achieves excellent cutting edge strength thanks to optimized cutting edge design.
- Expanded lineup of long type
  An expanded lineup of long type drills with diameters between ø 3,0 and ø 20,0 mm that are capable of drilling with an overhang length up to L/D = 10.
- Expanded lineup of types with oil hole
  Supports internal coolant. For deeper drilling (3D, 5D).

Improves drilling stability by ensuring web thickness.




## Reduction of Burrs at Hole Exit





Work Material: 15CrMo5
Drill: MDF0500S2D (Ø 5,0 mm, 2D)
Cutting Conditions: $v_c$ = 65 m/min, f = 0,12 mm/rev
H = 10 mm, 150 holes, wet
Equipment: Vertical machining center


**Reduces exit burrs by more than half compared to general-purpose drills**



Burr height: 0,18 mm
Flat MultiDrill MDF type



Burr height: 0,44 mm
Conventional general type


## Applications



High-efficient spot facing


Hole expansion drilling



Drilling in non-horizontal surfaces (such as inclined and cylindrical)


Interrupted drilling



Cross drilling



Pre-tap hole drilling in thin sheets



Deep spot facing




Avoiding interference with work materials

# Flat MultiDrill
# MDF Type

## Long Type (L2D)

For flat base drilling in long overhang conditions, hole expansion, burr prevention.
For deep flat base drilling and to avoid interference with workpiece.
Drilling that uses the long shank type requires a guide hole of the same diameter or a centering hole larger than the tool diameter.

Two types
Ⓐ ØDC < 6 mm Stepped Shank Products
Ⓑ ØDC ≥ 6 mm Relief Shank Products





## With Oil Hole (H3D Type / H5D Type)

Support for internal coolant allows for deeper flat hole drilling.
Drilling that uses oil hole L/D = 5 requires a guide hole of the same diameter or a centering hole larger than the tool diameter.




### Deep Spot Facing




Tool: MDF0600H5D
Work Material: C50, Ø 6 mm
Cutting Conditions: $v_c$ = 140 m/min,
f = 0,15 mm/rev
H = 30 mm (5D)
Internal Coolant
Overhang 45 mm
Prepared Hole 3 mm (0,5D)

### Long Overhang Spot Facing




Tool: MDF0600H3D
Work Material: C50,
Cutting Conditions: $v_c$ = 90 m/min,
f = 0,1 mm/rev
H = 18mm (3D)
Internal Coolant
Overhang 35 mm


① Entrance ② Hole Bottom

### Inclined Surface Drilling






Tool: MDF0500S2D
Work Material: 15CrMo5
Cutting Conditions: $v_c$ = 65 m/min,
f = 0,08 mm/rev
H = 10mm
External MQL

### Controlling Burrs and Chips when Withdrawn



Tool: MDF1000S2D
Work Material: St 42-3
Cutting Conditions: $v_c$ = 75 m/min,
f = 0,12 mm/rev
H = 5mm
External MQL

## Using Flat Drills, General-Purpose Drills and Endmills

| Tool | Flat Drill **MDF Type** | | General Purpose Drill GS/HGS Type | | Endmill for Spot Facing GSX MILL Slot | |
|---|---|---|---|---|---|---|
| Hole Bottom Shape |   | |   | |   | |
| Drilling in horizontal surfaces | ⊙ | Feed rate approximately half of a general-purpose drill | ○ | Optimal | X | Within 1D, limited to low feed rate<br>Feed rate one-fifth or lower of a general-purpose drill |
| Drilling in non-horizontal surfaces | ○ | Optimal (within 2D is recommended) | X | Unusable | ⊙ | Within 1D, limited to low feed rate<br>Feed rate half or lower of a flat drill |
| Traversing | X | Unusable | X | Unusable | ○ | Optimal |

## Series


| Application | Series | Diameter Range (mm) | Hole Depth (L/D) |
|---|---|---|---|
| External | MDF □□□□ S2D | Ø 0,3 – 20,0 | ≤ 2,0 |
| | MDF □□□□ L2D | Ø 0,3 – 20,0 | ≤ 2,0 |
| Internal | MDF □□□□ H3D | Ø 0,3 – 16,0 | ≤ 3,0 |
| | MDF □□□□ H5D | Ø 0,3 – 16,0 | ≤ 5,0 |

## External Coolant Supply (MDF S2D Type)

| Carbon Steel <0,28% | Alloy Steel >0,28% | Tempered Steel | Hardened Steel <45HRC | Hardened Steel >45HRC | Stainless-Steel | Cast Iron | Ductile Cast Iron | Aluminium Alloy |
|---|---|---|---|---|---|---|---|---|
| ◎ | ◎ | ◎ | ○ | | ○ | ○ | ○ | ○ |

PVD 2D

● MDF Type




### ● Diameter Ø 0,3–7,0 mm

| Diameter ØDc (mm) | Shank ØDs (mm) | Cat. No. | Stock | Dimensions (mm) L | ℓ1 | ℓ2 |
|---|---|---|---|---|---|---|
| 0,3* | 3,0 | MDF 0030S2D | ❍ | 40 | 1,0 | 1,3 |
| 0,4* | | 0040S2D | ❍ | | 1,4 | 1,8 |
| 0,5 | 3,0 | MDF 0050S2D | ❍ | 40 | 2,0 | 2,2 |
| 0,6 | | 0060S2D | ❍ | | 2,4 | 2,6 |
| 0,7 | | 0070S2D | ❍ | | 2,8 | 3,1 |
| 0,8 | | 0080S2D | ❍ | | 3,2 | 3,5 |
| 0,9 | | 0090S2D | ❍ | | 3,6 | 4,0 |
| 1,0 | 3,0 | MDF 0100S2D | ● | 45 | 4,0 | 4,4 |
| 1,1 | | 0110S2D | ❍ | | 4,4 | 4,8 |
| 1,2 | | 0120S2D | ❍ | | 4,8 | 5,3 |
| 1,3 | | 0130S2D | ❍ | | 5,2 | 5,7 |
| 1,4 | | 0140S2D | ❍ | | 5,6 | 6,2 |
| 1,5 | 3,0 | MDF 0150S2D | ● | 45 | 6,0 | 6,6 |
| 1,6 | | 0160S2D | ❍ | | 6,4 | 7,0 |
| 1,7 | | 0170S2D | ❍ | | 6,8 | 7,5 |
| 1,8 | | 0180S2D | ❍ | | 7,2 | 7,9 |
| 1,9 | | 0190S2D | ❍ | | 7,6 | 8,4 |
| 2,0 | 4,0 | MDF 0200S2D | ● | 50 | 8,0 | 8,8 |
| 2,1 | | 0210S2D | ● | | 8,4 | 9,2 |
| 2,2 | | 0220S2D | ● | | 8,8 | 9,7 |
| 2,3 | | 0230S2D | ● | | 9,2 | 10,1 |
| 2,4 | | 0240S2D | ● | | 9,6 | 10,6 |
| 2,5 | 4,0 | MDF 0250S2D | ● | 50 | 10,0 | 11,0 |
| 2,6 | | 0260S2D | ● | | 10,4 | 11,4 |
| 2,7 | | 0270S2D | ● | | 10,8 | 11,9 |
| 2,8 | | 0280S2D | ● | | 11,2 | 12,3 |
| 2,9 | | 0290S2D | ● | | 11,6 | 12,8 |
| 3,0 | 6,0 | MDF 0300S2D | ● | 50 | 12,0 | 13,2 |
| 3,1 | | 0310S2D | ● | | 12,4 | 13,6 |
| 3,2 | | 0320S2D | ● | | 12,8 | 14,1 |
| 3,3 | | 0330S2D | ● | | 13,2 | 14,5 |
| 3,4 | | 0340S2D | ● | | 13,6 | 15,0 |
| 3,5 | | 0350S2D | ● | | 14,0 | 15,4 |
| 3,6 | 6,0 | MDF 0360S2D | ● | 50 | 14,4 | 15,8 |
| 3,7 | | 0370S2D | ● | | 14,8 | 16,3 |
| 3,8 | | 0380S2D | ● | | 15,2 | 16,7 |
| 3,9 | | 0390S2D | ● | | 15,6 | 17,2 |
| 4,0 | | 0400S2D | ● | | 16,0 | 17,6 |
| 4,1 | 6,0 | MDF 0410S2D | ● | 60 | 16,4 | 18,0 |
| 4,2 | | 0420S2D | ● | | 16,8 | 18,5 |
| 4,3 | | 0430S2D | ● | | 17,2 | 18,9 |
| 4,4 | | 0440S2D | ● | | 17,6 | 19,4 |
| 4,5 | | 0450S2D | ● | | 18,0 | 19,8 |
| 4,6 | 6,0 | MDF 0460S2D | ● | 60 | 18,4 | 20,2 |
| 4,7 | | 0470S2D | ● | | 18,8 | 20,7 |
| 4,8 | | 0480S2D | ● | | 19,2 | 21,1 |
| 4,9 | | 0490S2D | ● | | 19,6 | 21,6 |
| 5,0 | | 0500S2D | ● | | 20,0 | 22,0 |
| 5,1 | 6,0 | MDF 0510S2D | ● | 60 | 20,4 | 22,4 |
| 5,2 | | 0520S2D | ● | | 20,8 | 22,9 |
| 5,3 | | 0530S2D | ● | | 21,2 | 23,3 |
| 5,4 | | 0540S2D | ● | | 21,6 | 23,8 |
| 5,5 | | 0550S2D | ● | | 22,0 | 24,2 |
| 5,6 | 6,0 | MDF 0560S2D | ● | 60 | 22,4 | 24,6 |
| 5,7 | | 0570S2D | ● | | 22,8 | 25,1 |
| 5,8 | | 0580S2D | ● | | 23,2 | 25,5 |
| 5,9 | | 0590S2D | ● | | 23,6 | 26,0 |
| 6,0 | | 0600S2D | ● | | 24,0 | 26,4 |
| 6,1 | 8,0 | MDF 0610S2D | ● | 70 | 24,4 | 26,8 |
| 6,2 | | 0620S2D | ● | | 24,8 | 27,3 |
| 6,3 | | 0630S2D | ● | | 25,2 | 27,7 |
| 6,4 | | 0640S2D | ● | | 25,6 | 28,2 |
| 6,5 | | 0650S2D | ● | | 26,0 | 28,6 |
| 6,6 | 8,0 | MDF 0660S2D | ● | 70 | 26,4 | 29,0 |
| 6,7 | | 0670S2D | ● | | 26,8 | 29,5 |
| 6,8 | | 0680S2D | ● | | 27,2 | 29,9 |
| 6,9 | | 0690S2D | ● | | 27,6 | 30,4 |
| 7,0 | | 0700S2D | ● | | 28,0 | 30,8 |

### ● Diameter Ø 7,1–20,0 mm

| Diameter ØDc (mm) | Shank ØDs (mm) | Cat. No. | Stock | Dimensions (mm) L | ℓ1 | ℓ2 |
|---|---|---|---|---|---|---|
| 7,1 | 8,0 | MDF 0710S2D | ● | 70 | 28,4 | 31,2 |
| 7,2 | | 0720S2D | ● | | 28,8 | 31,7 |
| 7,3 | | 0730S2D | ● | | 29,2 | 32,1 |
| 7,4 | | 0740S2D | ● | | 29,6 | 32,6 |
| 7,5 | | 0750S2D | ● | | 30,0 | 33,0 |
| 7,6 | 8,0 | MDF 0760S2D | ● | 70 | 30,4 | 33,4 |
| 7,7 | | 0770S2D | ● | | 30,8 | 33,9 |
| 7,8 | | 0780S2D | ● | | 31,2 | 34,3 |
| 7,9 | | 0790S2D | ● | | 31,6 | 34,8 |
| 8,0 | | 0800S2D | ● | | 32,0 | 35,2 |
| 8,1 | 10,0 | MDF 0810S2D | ❍ | 80 | 32,4 | 35,6 |
| 8,2 | | 0820S2D | ❍ | | 32,8 | 36,1 |
| 8,3 | | 0830S2D | ❍ | | 33,2 | 36,5 |
| 8,4 | | 0840S2D | ❍ | | 33,6 | 37,0 |
| 8,5 | | 0850S2D | ● | | 34,0 | 37,4 |
| 8,6 | 10,0 | MDF 0860S2D | ❍ | 80 | 34,4 | 37,8 |
| 8,7 | | 0870S2D | ❍ | | 34,8 | 38,3 |
| 8,8 | | 0880S2D | ❍ | | 35,2 | 38,7 |
| 8,9 | | 0890S2D | ❍ | | 35,6 | 39,2 |
| 9,0 | | 0900S2D | ● | | 36,0 | 39,6 |
| 9,1 | 10,0 | MDF 0910S2D | ❍ | 80 | 36,4 | 40,0 |
| 9,2 | | 0920S2D | ❍ | | 36,8 | 40,5 |
| 9,3 | | 0930S2D | ❍ | | 37,2 | 40,9 |
| 9,4 | | 0940S2D | ❍ | | 37,6 | 41,4 |
| 9,5 | | 0950S2D | ● | | 38,0 | 41,8 |
| 9,6 | 10,0 | MDF 0960S2D | ❍ | 80 | 38,4 | 42,2 |
| 9,7 | | 0970S2D | ● | | 38,8 | 42,7 |
| 9,8 | | 0980S2D | ❍ | | 39,2 | 43,1 |
| 9,9 | | 0990S2D | ❍ | | 39,6 | 43,6 |
| 10,0 | | 1000S2D | ● | | 40,0 | 44,0 |
| 10,1 | 12,0 | MDF 1010S2D | ❍ | 90 | 40,4 | 44,4 |
| 10,2 | | 1020S2D | ❍ | | 40,8 | 44,9 |
| 10,3 | | 1030S2D | ❍ | | 41,2 | 45,3 |
| 10,4 | | 1040S2D | ❍ | | 41,6 | 45,8 |
| 10,5 | | 1050S2D | ● | | 42,0 | 46,2 |
| 10,6 | 12,0 | MDF 1060S2D | ❍ | 90 | 42,4 | 46,6 |
| 10,7 | | 1070S2D | ❍ | | 42,8 | 47,1 |
| 10,8 | | 1080S2D | ❍ | | 43,2 | 47,5 |
| 10,9 | | 1090S2D | ❍ | | 43,6 | 48,0 |
| 11,0 | | 1100S2D | ● | | 44,0 | 48,4 |
| 11,1 | 12,0 | MDF 1110S2D | ❍ | 90 | 44,4 | 48,8 |
| 11,2 | | 1120S2D | ❍ | | 44,8 | 49,3 |
| 11,3 | | 1130S2D | ❍ | | 45,2 | 49,7 |
| 11,4 | | 1140S2D | ❍ | | 45,6 | 50,2 |
| 11,5 | | 1150S2D | ● | | 46,0 | 50,6 |
| 11,6 | 12,0 | MDF 1160S2D | ❍ | 90 | 46,4 | 51,0 |
| 11,7 | | 1170S2D | ❍ | | 46,8 | 51,5 |
| 11,8 | | 1180S2D | ● | | 47,2 | 51,9 |
| 11,9 | | 1190S2D | ❍ | | 47,6 | 52,4 |
| 12,0 | | 1200S2D | ● | | 48,0 | 52,8 |
| 12,5 | 14,0 | MDF 1250S2D | ❍ | 100 | 50,0 | 54,0 |
| 13,0 | | 1300S2D | ❍ | | 52,0 | 56,8 |
| 13,5 | | 1350S2D | ❍ | 110 | 54,0 | 59,6 |
| 14,0 | | 1400S2D | ❍ | | 56,0 | 62,4 |
| 14,5 | 16,0 | MDF 1450S2D | ❍ | 110 | 58,0 | 65,2 |
| 15,0 | | 1500S2D | ❍ | | 60,0 | 68,0 |
| 15,5 | | 1550S2D | ❍ | 115 | 62,0 | 70,8 |
| 16,0 | | 1600S2D | ❍ | | 64,0 | 73,6 |
| 16,5 | 18,0 | MDF 1650S2D | ❍ | 125 | 66,0 | 72,4 |
| 17,0 | | 1700S2D | ❍ | | 68,0 | 75,2 |
| 17,5 | | 1750S2D | ❍ | 130 | 70,0 | 78,0 |
| 18,0 | | 1800S2D | ❍ | | 72,0 | 80,8 |
| 18,5 | 20,0 | MDF 1850S2D | ❍ | 140 | 74,0 | 83,6 |
| 19,0 | | 1900S2D | ❍ | | 76,0 | 86,4 |
| 19,5 | | 1950S2D | ❍ | | 78,0 | 89,2 |
| 20,0 | | 2000S2D | ❍ | | 80,0 | 92,0 |

*RS Thinning is used for ØDc ≥ 0,5mm.

Grade: ACF75

● = Euro stock
❍ = Japan stock


# Flat MultiDrill
# MDF Type

## External Coolant Supply (L2D Type, Long Type)


| Carbon Steel, Alloy Steel <0,28% | Carbon Steel, Alloy Steel >0,28% | Tempered Steel | Hardened Steel <45HRC | Hardened Steel >45HRC | Stainless-Steel | Cast Iron | Ductile Cast Iron | Aluminium Alloy |
|---|---|---|---|---|---|---|---|---|
| ◎ | ◎ | ◎ | ○ | | ○ | ○ | ○ | ○ |

PVD 2D

● ø DC ≤ ø DMM




● ø DC > ø DMM




### ● Diameter Ø 3,0–9,5 mm

| Diameter ØDc (mm) | Shank ØDs (mm) | Cat. No. | Stock | Dimensions (mm) L | ℓ1 | ℓ2 |
|---|---|---|---|---|---|---|
| 3,0 | 6,0 | MDF 0300L2D | ❍ | 100 | 13,5 | 30,0 |
| 3,1 | | 0310L2D | ❍ | | 14,0 | 31,0 |
| 3,2 | | 0320L2D | ❍ | | 14,4 | 32,0 |
| 3,3 | | 0330L2D | ❍ | | 14,9 | 33,0 |
| 3,4 | | 0340L2D | ❍ | | 15,3 | 34,0 |
| 3,5 | | 0350L2D | ❍ | | 15,8 | 35,0 |
| 3,6 | 6,0 | MDF 0360L2D | ❍ | 100 | 16,2 | 36,0 |
| 3,7 | | 0370L2D | ❍ | | 16,7 | 37,0 |
| 3,8 | | 0380L2D | ❍ | | 17,1 | 38,0 |
| 3,9 | | 0390L2D | ❍ | | 17,6 | 39,0 |
| 4,0 | | 0400L2D | ❍ | | 18,0 | 40,0 |
| 4,1 | 6,0 | MDF 0410L2D | ❍ | 100 | 18,5 | 41,0 |
| 4,2 | | 0420L2D | ❍ | | 18,9 | 42,0 |
| 4,3 | | 0430L2D | ❍ | | 19,4 | 43,0 |
| 4,4 | | 0440L2D | ❍ | | 19,8 | 44,0 |
| 4,5 | | 0450L2D | ❍ | | 20,3 | 45,0 |
| 4,6 | 6,0 | MDF 0460L2D | ❍ | 100 | 20,7 | 46,0 |
| 4,7 | | 0470L2D | ❍ | | 21,2 | 47,0 |
| 4,8 | | 0480L2D | ❍ | | 21,6 | 48,0 |
| 4,9 | | 0490L2D | ❍ | | 22,1 | 49,0 |
| 5,0 | | 0500L2D | ❍ | | 22,5 | 50,0 |
| 5,1 | 6,0 | MDF 0510L2D | ❍ | 110 | 23,0 | 51,0 |
| 5,2 | | 0520L2D | ❍ | | 23,4 | 52,0 |
| 5,3 | | 0530L2D | ❍ | | 23,9 | 53,0 |
| 5,4 | | 0540L2D | ❍ | | 24,3 | 54,0 |
| 5,5 | | 0550L2D | ❍ | | 24,8 | 55,0 |
| 5,6 | 6,0 | MDF 0560L2D | ❍ | 110 | 25,2 | 56,0 |
| 5,7 | | 0570L2D | ❍ | | 25,7 | 57,0 |
| 5,8 | | 0580L2D | ❍ | | 26,1 | 58,0 |
| 5,9 | | 0590L2D | ❍ | | 26,6 | 59,0 |
| **6,0** | 5,0 | MDF 0600L2DS5 | ❍ | 110 | 27,0 | 30,0 |
| **6,0** | 6,0 | MDF 0600L2D | ❍ | 110 | 27,0 | 60,0 |
| 6,1 | 6,0 | MDF 0610L2D | ❍ | 120 | 27,5 | 30,5 |
| 6,2 | | 0620L2D | ❍ | | 27,9 | 30,9 |
| 6,3 | | 0630L2D | ❍ | | 28,4 | 31,4 |
| 6,4 | | 0640L2D | ❍ | | 28,8 | 31,8 |
| 6,5 | | 0650L2D | ❍ | | 29,3 | 32,3 |
| 6,6 | 6,0 | MDF 0660L2D | ❍ | 120 | 29,7 | 32,7 |
| 6,7 | | 0670L2D | ❍ | | 30,2 | 33,2 |
| 6,8 | | 0680L2D | ❍ | | 30,6 | 33,6 |
| 6,9 | | 0690L2D | ❍ | | 31,1 | 34,1 |
| 7,0 | | 0700L2D | ❍ | | 31,5 | 34,5 |
| 7,1 | 6,0 | MDF 0710L2D | ❍ | 130 | 32,0 | 35,0 |
| 7,2 | | 0720L2D | ❍ | | 32,4 | 35,4 |
| 7,3 | | 0730L2D | ❍ | | 32,9 | 35,9 |
| 7,4 | | 0740L2D | ❍ | | 33,3 | 36,3 |
| 7,5 | | 0750L2D | ❍ | | 33,8 | 36,8 |
| 7,6 | 6,0 | MDF 0760L2D | ❍ | 130 | 34,2 | 37,2 |
| 7,7 | | 0770L2D | ❍ | | 34,7 | 37,7 |
| 7,8 | | 0780L2D | ❍ | | 35,1 | 38,1 |
| 7,9 | | 0790L2D | ❍ | | 35,6 | 38,6 |
| **8,0** | 6,0 | MDF 0800L2DS6 | ❍ | 130 | 36,0 | 39,0 |
| **8,0** | 8,0 | MDF 0800L2D | ❍ | 130 | 36,0 | 80,0 |
| 8,1 | 8,0 | MDF 0810L2D | ❍ | 140 | 36,5 | 39,5 |
| 8,2 | | 0820L2D | ❍ | | 36,9 | 39,9 |
| 8,3 | | 0830L2D | ❍ | | 37,4 | 40,4 |
| 8,4 | | 0840L2D | ❍ | | 37,8 | 40,8 |
| 8,5 | | 0850L2D | ❍ | | 38,3 | 41,3 |
| 8,6 | 8,0 | MDF 0860L2D | ❍ | 140 | 38,7 | 41,7 |
| 8,7 | | 0870L2D | ❍ | | 39,2 | 42,2 |
| 8,8 | | 0880L2D | ❍ | | 39,6 | 42,6 |
| 8,9 | | 0890L2D | ❍ | | 40,1 | 43,1 |
| 9,0 | | 0900L2D | ❍ | | 40,5 | 43,5 |
| 9,1 | 8,0 | MDF 0910L2D | ❍ | 150 | 41,0 | 41,0 |
| 9,2 | | 0920L2D | ❍ | | 41,4 | 41,4 |
| 9,3 | | 0930L2D | ❍ | | 41,9 | 41,9 |
| 9,4 | | 0940L2D | ❍ | | 42,3 | 42,3 |
| 9,5 | | 0950L2D | ❍ | | 42,8 | 42,8 |

### ● Diameter Ø 9,6–20,0 mm

| Diameter ØDc (mm) | Shank ØDs (mm) | Cat. No. | Stock | Dimensions (mm) L | ℓ1 | ℓ2 |
|---|---|---|---|---|---|---|
| 9,6 | 8,0 | MDF 0960L2D | ❍ | 150 | 43,2 | 46,2 |
| 9,7 | | 0970L2D | ❍ | | 43,7 | 46,7 |
| 9,8 | | 0980L2D | ❍ | | 44,1 | 47,1 |
| 9,9 | | 0990L2D | ❍ | | 44,6 | 47,6 |
| **10,0** | 8,0 | MDF 1000L2DS8 | ❍ | 150 | 45,0 | 48,0 |
| **10,0** | 10,0 | MDF 1000L2D | ❍ | 150 | 45,0 | 100,0 |
| 10,1 | 10,0 | MDF 1010L2D | ❍ | 160 | 45,5 | 48,5 |
| 10,2 | | 1020L2D | ❍ | | 45,9 | 48,9 |
| 10,3 | | 1030L2D | ❍ | | 46,4 | 49,4 |
| 10,4 | | 1040L2D | ❍ | | 46,8 | 49,8 |
| 10,5 | | 1050L2D | ❍ | | 47,3 | 50,3 |
| 10,6 | 10,0 | MDF 1060L2D | ❍ | 160 | 47,7 | 50,7 |
| 10,7 | | 1070L2D | ❍ | | 48,2 | 51,2 |
| 10,8 | | 1080L2D | ❍ | | 48,6 | 51,6 |
| 10,9 | | 1090L2D | ❍ | | 49,1 | 52,1 |
| 11,0 | | 1100L2D | ❍ | | 49,5 | 52,5 |
| 11,1 | 10,0 | MDF 1110L2D | ❍ | 170 | 50,0 | 53,0 |
| 11,2 | | 1120L2D | ❍ | | 50,4 | 53,4 |
| 11,3 | | 1130L2D | ❍ | | 50,9 | 53,9 |
| 11,4 | | 1140L2D | ❍ | | 51,3 | 54,3 |
| 11,5 | | 1150L2D | ❍ | | 51,8 | 54,8 |
| 11,6 | 10,0 | MDF 1160L2D | ❍ | 170 | 52,2 | 55,2 |
| 11,7 | | 1170L2D | ❍ | | 52,7 | 55,7 |
| 11,8 | | 1180L2D | ❍ | | 53,1 | 56,1 |
| 11,9 | | 1190L2D | ❍ | | 53,6 | 56,6 |
| **12,0** | 10,0 | MDF 1200L2DS10 | ❍ | 170 | 54,0 | 57,0 |
| **12,0** | 12,0 | MDF 1200L2D | ❍ | 170 | 54,0 | 120,0 |
| 12,5 | 12,0 | MDF 1250L2D | ❍ | 180 | 56,3 | 59,3 |
| 13,0 | | 1300L2D | ❍ | | 58,5 | 61,5 |
| 13,5 | | 1350L2D | ❍ | 190 | 60,8 | 63,8 |
| **14,0** | 12,0 | MDF 1400L2DS12 | ❍ | 190 | 63,0 | 66,0 |
| **14,0** | 14,0 | MDF 1400L2D | ❍ | 190 | 63,0 | 140,0 |
| 14,5 | 14,0 | MDF 1450L2D | ❍ | 200 | 65,3 | 68,3 |
| 15,0 | | 1500L2D | ❍ | | 67,5 | 70,5 |
| 15,5 | | 1550L2D | ❍ | 210 | 69,8 | 72,8 |
| **16,0** | 14,0 | MDF 1600L2DS14 | ❍ | 210 | 72,0 | 75,0 |
| **16,0** | 16,0 | MDF 1600L2D | ❍ | 210 | 72,0 | 160,0 |
| 16,5 | 16,0 | MDF 1650L2D | ❍ | 220 | 74,3 | 77,3 |
| 17,0 | | 1700L2D | ❍ | | 76,5 | 79,5 |
| 17,5 | | 1750L2D | ❍ | 230 | 78,8 | 81,8 |
| **18,0** | 16,0 | MDF 1800L2DS16 | ❍ | 230 | 81,0 | 84,0 |
| **18,0** | 18,0 | MDF 1800L2D | ❍ | 230 | 81,0 | 180,0 |
| 18,5 | 18,0 | MDF 1850L2D | ❍ | 240 | 83,3 | 86,3 |
| 19,0 | | 1900L2D | ❍ | | 85,5 | 88,5 |
| 19,5 | | 1950L2D | ❍ | 250 | 87,8 | 90,8 |
| **20,0** | 18,0 | MDF 2000L2DS18 | ❍ | 250 | 90,0 | 93,0 |
| **20,0** | 20,0 | MDF 2000L2D | ❍ | 250 | 90,0 | 200,0 |

Grade: ACF75

Drilling that uses this tool requires a guide hole of the same diameter or a centering hole larger than the tool diameter.

## ■ Recommended Cutting Conditions

### ● MDF S2D Type

1. The recommended hole depth is 2 x DC. The depth shall be the depth from the highest point of the hole when drilling inclined surfaces.
2. The recommended cutting conditions are those for drilling in flat horizontal surfaces.
3. Adjust the feed rate according to the inclination angle when drilling in an inclined surface.
3.1 Set the feed rate at ≤ 70% when the inclination angle is ≤ 30°
3.2 Set the feed rate at ≤ 50% when the inclination angle is:> 30°
4. This product is a drilling tool. Do not use it for traversing or helical milling

($v_c$: Cutting Speed m/min f: Feed Rate mm/rev)

| Drill Diam. ØDC (mm) | Cutting Conditions | Soft Steel / General Steel (–250 HB) | Alloy Steel (–300 HB) | Hardened Steel (–50 HRC) | Stainless Steel (–200 HB) | Gray Cast Iron FC250 | Ductile Cast Iron | Aluminium Alloy |
|---|---|---|---|---|---|---|---|---|
| –Ø 0,5 | $v_c$ | 30–**40**–50 | 30–**35**–40 | 15–**20**–25 | 15–**20**–25 | 30–**40**–50 | 20–**30**–40 | 60–**80**–100 |
| | f | 0,004–**0,005**–0,006 | 0,004–**0,005**–0,006 | 0,001–**0,002**–0,003 | 0,003–**0,004**–0,005 | 0,004–**0,005**–0,006 | 0,001–**0,003**–0,005 | 0,003–**0,005**–0,007 |
| –Ø 1,0 | $v_c$ | 45–**55**–65 | 35–**45**–55 | 20–**30**–40 | 20–**25**–30 | 45–**55**–65 | 30–**40**–50 | 80–**100**–120 |
| | f | 0,01–**0,03**–0,05 | 0,01–**0,03**–0,05 | 0,002–**0,006**–0,01 | 0,005–**0,007**–0,01 | 0,01–**0,03**–0,05 | 0,005–**0,01**–0,015 | 0,01–**0,02**–0,03 |
| –Ø 2,0 | $v_c$ | 50–**60**–70 | 40–**50**–60 | 20–**30**–40 | 20–**30**–40 | 50–**60**–70 | 45–**55**–65 | 90–**110**–130 |
| | f | 0,02–**0,04**–0,06 | 0,02–**0,04**–0,06 | 0,01–**0,018**–0,025 | 0,01–**0,015**–0,02 | 0,02–**0,04**–0,06 | 0,015–**0,03**–0,045 | 0,03–**0,05**–0,07 |
| –Ø 4,0 | $v_c$ | 60–**75**–90 | 50–**65**–80 | 20–**30**–40 | 20–**30**–40 | 60–**75**–90 | 55–**65**–75 | 90–**110**–130 |
| | f | 0,06–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,06–**0,08**–0,10 | 0,04–**0,06**–0,08 | 0,06–**0,08**–0,10 |
| –Ø 6,0 | $v_c$ | 60–**75**–90 | 50–**65**–80 | 20–**30**–40 | 20–**30**–50 | 60–**75**–90 | 60–**70**–80 | 90–**110**–130 |
| | f | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,04–**0,06**–0,08 | 0,03–**0,04**–0,05 | 0,05–**0,10**–0,15 | 0,06–**0,09**–0,12 | 0,05–**0,10**–0,15 |
| –Ø 8,0 | $v_c$ | 60–**75**–90 | 50–**65**–80 | 20–**30**–40 | 20–**30**–50 | 60–**75**–90 | 60–**70**–80 | 90–**110**–130 |
| | f | 0,10–**0,15**–0,20 | 0,10–**0,15**–0,20 | 0,06–**0,08**–0,10 | 0,04–**0,06**–0,08 | 0,10–**0,15**–0,20 | 0,10–**0,12**–0,15 | 0,10–**0,15**–0,20 |
| –Ø 10,0 | $v_c$ | 60–**75**–90 | 50–**65**–80 | 20–**30**–40 | 20–**30**–50 | 60–**75**–90 | 60–**70**–80 | 90–**110**–130 |
| | f | 0,12–**0,17**–0,22 | 0,12–**0,17**–0,22 | 0,08–**0,10**–0,12 | 0,06–**0,08**–0,10 | 0,12–**0,17**–0,22 | 0,12–**0,15**–0,18 | 0,12–**0,17**–0,22 |
| –Ø 12,0 | $v_c$ | 60–**75**–90 | 50–**65**–80 | 20–**30**–40 | 20–**30**–50 | 60–**75**–90 | 60–**70**–80 | 90–**110**–130 |
| | f | 0,15–**0,20**–0,25 | 0,15–**0,20**–0,25 | 0,12–**0,15**–0,18 | 0,08–**0,10**–0,12 | 0,15–**0,20**–0,25 | 0,15–**0,18**–0,20 | 0,15–**0,20**–0,25 |
| –Ø 16,0 | $v_c$ | 60–**75**–90 | 50–**65**–80 | 20–**30**–40 | 20–**30**–50 | 60–**75**–90 | 60–**70**–80 | 90–**110**–130 |
| | f | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,30 | 0,14–**0,17**–0,20 | 0,10–**0,15**–0,20 | 0,17–**0,22**–0,27 | 0,15–**0,20**–0,25 | 0,20–**0,25**–0,30 |
| –Ø 20,0 | $v_c$ | 60–**75**–90 | 50–**65**–80 | 20–**30**–40 | 20–**30**–50 | 60–**75**–90 | 60–**70**–80 | 90–**110**–130 |
| | f | 0,25–**0,30**–0,35 | 0,25–**0,30**–0,35 | 0,16–**0,19**–0,22 | 0,15–**0,20**–0,25 | 0,25–**0,30**–0,35 | 0,20 - **0,25** - 0,30 | 0,25–**0,30**–0,35 |

Min. - **Optimum** - Max.

### ● MDF L2D Type, Long Type

1. Drilling that uses this tool requires a guide hole of the same diameter.
2. The cutting conditions are the recommended conditions with a guide hole.
3. The recommended hole depth is 5 x DC. The depth is measured from the highest point of the hole on drilling in inclined surfaces.
4. This product is a drilling tool. Do not use it for traversing or helical milling.

($v_c$: Cutting Speed m/min f: Feed Rate mm/rev)

| Drill Diam. ØDC (mm) | Cutting Conditions | Soft Steel / General Steel (–250 HB) | Alloy Steel (–300 HB) | Hardened Steel (–50 HRC) | Stainless Steel (–200 HB) | Gray Cast Iron FC250 | Ductile Cast Iron | Aluminium Alloy |
|---|---|---|---|---|---|---|---|---|
| –Ø 4,0 | $v_c$ | 60–**80**–100 | 50–**70**–90 | 20–**30**–40 | 20–**30**–40 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,06–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,06–**0,08**–0,10 | 0,04–**0,06**–0,08 | 0,06–**0,08**–0,10 |
| –Ø 6,0 | $v_c$ | 60–**80**–100 | 50–**70**–90 | 20–**30**–40 | 20–**30**–50 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,04–**0,06**–0,08 | 0,03–**0,04**–0,05 | 0,05–**0,10**–0,15 | 0,06–**0,09**–0,12 | 0,05–**0,10**–0,15 |
| –Ø 8,0 | $v_c$ | 60–**80**–100 | 50–**70**–90 | 20–**30**–40 | 20–**30**–50 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,10–**0,15**–0,20 | 0,10–**0,15**–0,20 | 0,06–**0,08**–0,10 | 0,04–**0,06**–0,08 | 0,10–**0,15**–0,20 | 0,10–**0,12**–0,15 | 0,10–**0,15**–0,20 |
| –Ø 10,0 | $v_c$ | 60–**80**–100 | 50–**70**–90 | 20–**30**–40 | 20–**30**–50 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,15–**0,20**–0,25 | 0,15–**0,20**–0,25 | 0,08–**0,10**–0,12 | 0,06–**0,08**–0,10 | 0,15–**0,20**–0,25 | 0,12–**0,15**–0,18 | 0,15–**0,20**–0,25 |
| –Ø 12,0 | $v_c$ | 60–**80**–100 | 50–**70**–90 | 20–**30**–40 | 20–**30**–50 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,30 | 0,12–**0,15**–0,18 | 0,08–**0,10**–0,12 | 0,17–**0,22**–0,27 | 0,15–**0,20**–0,25 | 0,20–**0,25**–0,30 |
| –Ø 16,0 | $v_c$ | 60–**80**–100 | 50–**70**–90 | 20–**30**–40 | 20–**30**–50 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,30 | 0,14–**0,17**–0,20 | 0,10–**0,15**–0,20 | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,30 | 0,25–**0,30**–0,35 |
| –Ø 20,0 | $v_c$ | 60–**80**–100 | 50–**70**–90 | 20–**30**–40 | 20–**30**–50 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,25–**0,30**–0,35 | 0,25–**0,30**–0,35 | 0,16–**0,19**–0,22 | 0,15–**0,20**–0,25 | 0,30–**0,35**–0,40 | 0,25–**0,30**–0,35 | 0,35–**0,40**–0,45 |

Min. - **Optimum** - Max.





● = Euro stock
❍ = Japan stock


# Flat MultiDrill
# MDF Type

## Internal Coolant Supply (MDF H3D/H5D Type)


| Carbon Steel <0,28% | Alloy Steel >0,28% | Tempered Steel | Hardened Steel <45HRC | Hardened Steel >45HRC | Stainless-Steel | Cast Iron | Ductile Cast Iron | Aluminium Alloy |
|---|---|---|---|---|---|---|---|---|
| ◎ | ◎ | ◎ | ○ | | ○ | ○ | ○ | ○ |

PVD 3D 5D

● MDF Type 3D Single Margin




● MDF Type 5D Double Margin




### ● Diameter Ø 3,0–6,0 mm

| Diameter ØDc (mm) | Shank ØDs (mm) | Hole Depth (L/D) | Cat. No. | Stock | Dimensions (mm) L | ℓ1 | ℓ2 |
|---|---|---|---|---|---|---|---|
| 3,0 | 3 | 3 | MDF 0300H3D | ● | 68 | 13,5 | 16,5 |
| | | 5 | 0300H5D | ● | 78 | 20,1 | 23,1 |
| 3,1 | 4 | 3 | MDF 0310H3D | ❍ | 72 | 14,0 | 17,0 |
| | | 5 | 0310H5D | ❍ | 86 | 20,8 | 23,8 |
| 3,2 | 4 | 3 | 0320H3D | ❍ | 72 | 14,4 | 17,4 |
| | | 5 | 0320H5D | ❍ | 86 | 21,4 | 24,4 |
| 3,3 | 4 | 3 | 0330H3D | ❍ | 72 | 14,9 | 17,9 |
| | | 5 | 0330H5D | ❍ | 86 | 22,1 | 25,1 |
| 3,4 | 4 | 3 | 0340H3D | ❍ | 72 | 15,3 | 18,3 |
| | | 5 | 0340H5D | ❍ | 86 | 22,8 | 25,8 |
| 3,5 | 4 | 3 | 0350H3D | ● | 72 | 15,8 | 18,8 |
| | | 5 | 0350H5D | ● | 86 | 23,5 | 26,5 |
| 3,6 | 4 | 3 | MDF 0360H3D | ❍ | 72 | 16,2 | 19,2 |
| | | 5 | 0360H5D | ❍ | 86 | 24,1 | 27,1 |
| 3,7 | 4 | 3 | 0370H3D | ❍ | 72 | 16,7 | 19,7 |
| | | 5 | 0370H5D | ❍ | 86 | 24,8 | 27,8 |
| 3,8 | 4 | 3 | 0380H3D | ❍ | 72 | 17,1 | 20,1 |
| | | 5 | 0380H5D | ❍ | 86 | 25,5 | 28,5 |
| 3,9 | 4 | 3 | 0390H3D | ❍ | 72 | 17,6 | 20,6 |
| | | 5 | 0390H5D | ❍ | 86 | 26,1 | 29,1 |
| 4,0 | 4 | 3 | 0400H3D | ● | 72 | 18,0 | 21,0 |
| | | 5 | 0400H5D | ● | 86 | 26,8 | 29,8 |
| 4,1 | 5 | 3 | MDF 0410H3D | ❍ | 80 | 18,5 | 21,5 |
| | | 5 | 0410H5D | ❍ | 98 | 27,5 | 30,5 |
| 4,2 | 5 | 3 | 0420H3D | ❍ | 80 | 18,9 | 21,9 |
| | | 5 | 0420H5D | ❍ | 98 | 28,1 | 31,1 |
| 4,3 | 5 | 3 | 0430H3D | ❍ | 80 | 19,4 | 22,4 |
| | | 5 | 0430H5D | ❍ | 98 | 28,8 | 31,8 |
| 4,4 | 5 | 3 | 0440H3D | ❍ | 80 | 19,8 | 22,8 |
| | | 5 | 0440H5D | ❍ | 98 | 29,5 | 32,5 |
| 4,5 | 5 | 3 | 0450H3D | ● | 80 | 20,3 | 23,3 |
| | | 5 | 0450H5D | ● | 98 | 30,2 | 33,2 |
| 4,6 | 5 | 3 | MDF 0460H3D | ❍ | 80 | 20,7 | 23,7 |
| | | 5 | 0460H5D | ❍ | 98 | 30,8 | 33,8 |
| 4,7 | 5 | 3 | 0470H3D | ❍ | 80 | 21,2 | 24,2 |
| | | 5 | 0470H5D | ❍ | 98 | 31,5 | 34,5 |
| 4,8 | 5 | 3 | 0480H3D | ❍ | 80 | 21,6 | 24,6 |
| | | 5 | 0480H5D | ❍ | 98 | 32,2 | 35,2 |
| 4,9 | 5 | 3 | 0490H3D | ❍ | 80 | 22,1 | 25,1 |
| | | 5 | 0490H5D | ❍ | 98 | 32,8 | 35,8 |
| 5,0 | 5 | 3 | 0500H3D | ● | 80 | 22,5 | 25,5 |
| | | 5 | 0500H5D | ● | 98 | 33,5 | 36,5 |
| 5,1 | 6 | 3 | MDF 0510H3D | ❍ | 82 | 23,0 | 26,0 |
| | | 5 | 0510H5D | ❍ | 100 | 34,2 | 37,2 |
| 5,2 | 6 | 3 | 0520H3D | ❍ | 82 | 23,4 | 26,4 |
| | | 5 | 0520H5D | ❍ | 100 | 34,8 | 37,8 |
| 5,3 | 6 | 3 | 0530H3D | ❍ | 82 | 23,9 | 26,9 |
| | | 5 | 0530H5D | ❍ | 100 | 35,5 | 38,5 |
| 5,4 | 6 | 3 | 0540H3D | ❍ | 82 | 24,3 | 27,3 |
| | | 5 | 0540H5D | ❍ | 100 | 36,2 | 39,2 |
| 5,5 | 6 | 3 | 0550H3D | ● | 82 | 24,8 | 27,8 |
| | | 5 | 0550H5D | ● | 100 | 36,9 | 39,9 |
| 5,6 | 6 | 3 | MDF 0560H3D | ❍ | 82 | 25,2 | 28,2 |
| | | 5 | 0560H5D | ❍ | 100 | 37,5 | 40,5 |
| 5,7 | 6 | 3 | 0570H3D | ❍ | 82 | 25,7 | 28,7 |
| | | 5 | 0570H5D | ❍ | 100 | 38,2 | 41,2 |
| 5,8 | 6 | 3 | 0580H3D | ❍ | 82 | 26,1 | 29,1 |
| | | 5 | 0580H5D | ❍ | 100 | 38,9 | 41,9 |
| 5,9 | 6 | 3 | 0590H3D | ❍ | 82 | 26,6 | 29,6 |
| | | 5 | 0590H5D | ❍ | 100 | 39,5 | 42,5 |
| 6,0 | 6 | 3 | 0600H3D | ● | 82 | 27,0 | 30,0 |
| | | 5 | 0600H5D | ● | 100 | 40,2 | 43,2 |

### ● Diameter Ø 6,1–9,0 mm

| Diameter ØDc (mm) | Shank ØDs (mm) | Hole Depth (L/D) | Cat. No. | Stock | Dimensions (mm) L | ℓ1 | ℓ2 |
|---|---|---|---|---|---|---|---|
| 6,1 | 7 | 3 | MDF 0610H3D | ❍ | 88 | 27,5 | 30,5 |
| | | 5 | 0610H5D | ❍ | 109 | 40,9 | 43,9 |
| 6,2 | 7 | 3 | 0620H3D | ❍ | 88 | 27,9 | 30,9 |
| | | 5 | 0620H5D | ❍ | 109 | 41,5 | 44,5 |
| 6,3 | 7 | 3 | 0630H3D | ❍ | 88 | 28,4 | 31,4 |
| | | 5 | 0630H5D | ❍ | 109 | 42,2 | 45,2 |
| 6,4 | 7 | 3 | 0640H3D | ❍ | 88 | 28,8 | 31,8 |
| | | 5 | 0640H5D | ❍ | 109 | 42,9 | 45,9 |
| 6,5 | 7 | 3 | 0650H3D | ● | 88 | 29,3 | 32,3 |
| | | 5 | 0650H5D | ● | 109 | 43,6 | 46,6 |
| 6,6 | 7 | 3 | MDF 0660H3D | ❍ | 88 | 29,7 | 32,7 |
| | | 5 | 0660H5D | ❍ | 109 | 44,2 | 47,2 |
| 6,7 | 7 | 3 | 0670H3D | ❍ | 88 | 30,2 | 33,2 |
| | | 5 | 0670H5D | ❍ | 109 | 44,9 | 47,9 |
| 6,8 | 7 | 3 | 0680H3D | ❍ | 88 | 30,6 | 33,6 |
| | | 5 | 0680H5D | ❍ | 109 | 45,6 | 48,6 |
| 6,9 | 7 | 3 | 0690H3D | ❍ | 88 | 31,1 | 34,1 |
| | | 5 | 0690H5D | ❍ | 109 | 46,2 | 49,2 |
| 7,0 | 7 | 3 | 0700H3D | ● | 88 | 31,5 | 34,5 |
| | | 5 | 0700H5D | ● | 109 | 46,9 | 49,9 |
| 7,1 | 8 | 3 | MDF 0710H3D | ❍ | 94 | 32,0 | 35,0 |
| | | 5 | 0710H5D | ❍ | 118 | 47,6 | 50,6 |
| 7,2 | 8 | 3 | 0720H3D | ❍ | 94 | 32,4 | 35,4 |
| | | 5 | 0720H5D | ❍ | 118 | 48,2 | 51,2 |
| 7,3 | 8 | 3 | 0730H3D | ❍ | 94 | 32,9 | 35,9 |
| | | 5 | 0730H5D | ❍ | 118 | 48,9 | 51,9 |
| 7,4 | 8 | 3 | 0740H3D | ❍ | 94 | 33,3 | 36,3 |
| | | 5 | 0740H5D | ❍ | 118 | 49,6 | 52,6 |
| 7,5 | 8 | 3 | 0750H3D | ● | 94 | 33,8 | 36,8 |
| | | 5 | 0750H5D | ● | 118 | 50,3 | 53,3 |
| 7,6 | 8 | 3 | MDF 0760H3D | ❍ | 94 | 34,2 | 37,2 |
| | | 5 | 0760H5D | ❍ | 118 | 50,9 | 53,9 |
| 7,7 | 8 | 3 | 0770H3D | ❍ | 94 | 34,7 | 37,7 |
| | | 5 | 0770H5D | ❍ | 118 | 51,6 | 54,6 |
| 7,8 | 8 | 3 | 0780H3D | ❍ | 94 | 35,1 | 38,1 |
| | | 5 | 0780H5D | ❍ | 118 | 52,3 | 55,3 |
| 7,9 | 8 | 3 | 0790H3D | ❍ | 94 | 35,6 | 38,6 |
| | | 5 | 0790H5D | ❍ | 118 | 52,9 | 55,9 |
| 8,0 | 8 | 3 | 0800H3D | ● | 94 | 36,0 | 39,0 |
| | | 5 | 0800H5D | ● | 118 | 53,6 | 56,6 |
| 8,1 | 9 | 3 | MDF 0810H3D | ❍ | 100 | 36,5 | 39,5 |
| | | 5 | 0810H5D | ❍ | 127 | 54,3 | 57,3 |
| 8,2 | 9 | 3 | 0820H3D | ❍ | 100 | 36,9 | 39,9 |
| | | 5 | 0820H5D | ❍ | 127 | 54,9 | 57,9 |
| 8,3 | 9 | 3 | 0830H3D | ❍ | 100 | 37,4 | 40,4 |
| | | 5 | 0830H5D | ❍ | 127 | 55,6 | 58,6 |
| 8,4 | 9 | 3 | 0840H3D | ❍ | 100 | 37,8 | 40,8 |
| | | 5 | 0840H5D | ❍ | 127 | 56,3 | 59,3 |
| 8,5 | 9 | 3 | 0850H3D | ● | 100 | 38,3 | 41,3 |
| | | 5 | 0850H5D | ● | 127 | 57,0 | 60,0 |
| 8,6 | 9 | 3 | MDF 0860H3D | ❍ | 100 | 38,7 | 41,7 |
| | | 5 | 0860H5D | ❍ | 127 | 57,6 | 60,6 |
| 8,7 | 9 | 3 | 0870H3D | ❍ | 100 | 39,2 | 42,2 |
| | | 5 | 0870H5D | ❍ | 127 | 58,3 | 61,3 |
| 8,8 | 9 | 3 | 0880H3D | ❍ | 100 | 39,6 | 42,6 |
| | | 5 | 0880H5D | ❍ | 127 | 59,0 | 62,0 |
| 8,9 | 9 | 3 | 0890H3D | ❍ | 100 | 40,1 | 43,1 |
| | | 5 | 0890H5D | ❍ | 127 | 59,6 | 62,6 |
| 9,0 | 9 | 3 | 0900H3D | ● | 100 | 40,5 | 43,5 |
| | | 5 | 0900H5D | ● | 127 | 60,3 | 63,3 |


Grade: ACF75

## Internal Coolant Supply (MDF H3D/H5D Type)


| Carbon Steel, Alloy Steel <0,28% | Carbon Steel, Alloy Steel >0,28% | Tempered Steel | Hardened Steel <45HRC | Hardened Steel >45HRC | Stainless-Steel | Cast Iron | Ductile Cast Iron | Aluminium Alloy |
|---|---|---|---|---|---|---|---|---|
| ◎ | ◎ | ◎ | ○ | | ○ | ○ | ○ | ○ |

PVD 3D 5D

● MDF Type 3D Single Margin




● MDF Type 5D Double Margin




### ● Diameter Ø 9,1–12,0 mm

| Diameter ØDc (mm) | Shank ØDs (mm) | Hole Depth (L/D) | Cat. No. | Stock | Dimensions (mm) | | |
|---|---|---|---|---|---|---|---|
| | | | | | *L* | $\ell_1$ | $\ell_2$ |
| 9,1 | 10 | 3 | MDF 0910H3D | ❍ | 106 | 41,0 | 44,0 |
| | | 5 | 0910H5D | ❍ | 136 | 61,0 | 64,0 |
| 9,2 | 10 | 3 | 0920H3D | ❍ | 106 | 41,4 | 44,4 |
| | | 5 | 0920H5D | ❍ | 136 | 61,6 | 64,6 |
| 9,3 | 10 | 3 | 0930H3D | ❍ | 106 | 41,9 | 44,9 |
| | | 5 | 0930H5D | ❍ | 136 | 62,3 | 65,3 |
| 9,4 | 10 | 3 | 0940H3D | ❍ | 106 | 42,3 | 45,3 |
| | | 5 | 0940H5D | ❍ | 136 | 63,0 | 66,0 |
| 9,5 | 10 | 3 | 0950H3D | ● | 106 | 42,8 | 45,8 |
| | | 5 | 0950H5D | ● | 136 | 63,7 | 66,7 |
| 9,6 | 10 | 3 | MDF 0960H3D | ❍ | 106 | 43,2 | 46,2 |
| | | 5 | 0960H5D | ❍ | 136 | 64,3 | 67,3 |
| 9,7 | 10 | 3 | 0970H3D | ❍ | 106 | 43,7 | 46,7 |
| | | 5 | 0970H5D | ❍ | 136 | 65,0 | 68,0 |
| 9,8 | 10 | 3 | 0980H3D | ❍ | 106 | 44,1 | 47,1 |
| | | 5 | 0980H5D | ❍ | 136 | 65,7 | 68,7 |
| 9,9 | 10 | 3 | 0990H3D | ❍ | 106 | 44,6 | 47,6 |
| | | 5 | 0990H5D | ❍ | 136 | 66,3 | 69,3 |
| 10,0 | 10 | 3 | 1000H3D | ● | 106 | 45,0 | 48,0 |
| | | 5 | 1000H5D | ● | 136 | 67,0 | 70,0 |
| 10,1 | 11 | 3 | MDF 1010H3D | ❍ | 116 | 45,5 | 48,5 |
| | | 5 | 1010H5D | ❍ | 149 | 67,7 | 70,7 |
| 10,2 | 11 | 3 | 1020H3D | ❍ | 116 | 45,9 | 48,9 |
| | | 5 | 1020H5D | ❍ | 149 | 68,3 | 71,3 |
| 10,3 | 11 | 3 | 1030H3D | ❍ | 116 | 46,4 | 49,4 |
| | | 5 | 1030H5D | ❍ | 149 | 69,0 | 72,0 |
| 10,4 | 11 | 3 | 1040H3D | ❍ | 116 | 46,8 | 49,8 |
| | | 5 | 1040H5D | ❍ | 149 | 69,7 | 72,7 |
| 10,5 | 11 | 3 | 1050H3D | ● | 116 | 47,3 | 50,3 |
| | | 5 | 1050H5D | ● | 149 | 70,4 | 73,4 |
| 10,6 | 11 | 3 | MDF 1060H3D | ❍ | 116 | 47,7 | 50,7 |
| | | 5 | 1060H5D | ❍ | 149 | 71,0 | 74,0 |
| 10,7 | 11 | 3 | 1070H3D | ❍ | 116 | 48,2 | 51,2 |
| | | 5 | 1070H5D | ❍ | 149 | 71,7 | 74,7 |
| 10,8 | 11 | 3 | 1080H3D | ❍ | 116 | 48,6 | 51,6 |
| | | 5 | 1080H5D | ❍ | 149 | 72,4 | 75,4 |
| 10,9 | 11 | 3 | 1090H3D | ❍ | 116 | 49,1 | 52,1 |
| | | 5 | 1090H5D | ❍ | 149 | 73,0 | 76,0 |
| 11,0 | 11 | 3 | 1100H3D | ● | 116 | 49,5 | 52,5 |
| | | 5 | 1100H5D | ● | 149 | 73,7 | 76,7 |
| 11,1 | 12 | 3 | MDF 1110H3D | ❍ | 122 | 50,0 | 53,0 |
| | | 5 | 1110H5D | ❍ | 158 | 74,4 | 77,4 |
| 11,2 | 12 | 3 | 1120H3D | ❍ | 122 | 50,4 | 53,4 |
| | | 5 | 1120H5D | ❍ | 158 | 75,0 | 78,0 |
| 11,3 | 12 | 3 | 1130H3D | ❍ | 122 | 50,9 | 53,9 |
| | | 5 | 1130H5D | ❍ | 158 | 75,7 | 78,7 |
| 11,4 | 12 | 3 | 1140H3D | ❍ | 122 | 51,3 | 54,3 |
| | | 5 | 1140H5D | ❍ | 158 | 76,4 | 79,4 |
| 11,5 | 12 | 3 | 1150H3D | ● | 122 | 51,8 | 54,8 |
| | | 5 | 1150H5D | ● | 158 | 77,1 | 80,1 |
| 11,6 | 12 | 3 | MDF 1160H3D | ❍ | 122 | 52,2 | 55,2 |
| | | 5 | 1160H5D | ❍ | 158 | 77,7 | 80,7 |
| 11,7 | 12 | 3 | 1170H3D | ❍ | 122 | 52,7 | 55,7 |
| | | 5 | 1170H5D | ❍ | 158 | 78,4 | 81,4 |
| 11,8 | 12 | 3 | 1180H3D | ❍ | 122 | 53,1 | 56,1 |
| | | 5 | 1180H5D | ❍ | 158 | 79,1 | 82,1 |
| 11,9 | 12 | 3 | 1190H3D | ❍ | 122 | 53,6 | 56,6 |
| | | 5 | 1190H5D | ❍ | 158 | 79,7 | 82,7 |
| 12,0 | 12 | 3 | 1200H3D | ● | 122 | 54,0 | 57,0 |
| | | 5 | 1200H5D | ● | 158 | 80,4 | 83,4 |

### ● Diameter Ø 12,5–16,0 mm

| Diameter ØDc (mm) | Shank ØDs (mm) | Hole Depth (L/D) | Cat. No. | Stock | Dimensions (mm) | | |
|---|---|---|---|---|---|---|---|
| | | | | | *L* | $\ell_1$ | $\ell_2$ |
| 12,5 | 13 | 3 | MDF 1250H3D | ❍ | 128 | 56,3 | 59,3 |
| | | 5 | 1250H5D | ❍ | 167 | 83,8 | 86,8 |
| 13,0 | 13 | 3 | 1300H3D | ❍ | 128 | 58,5 | 61,5 |
| | | 5 | 1300H5D | ❍ | 167 | 87,1 | 90,1 |
| 13,5 | 14 | 3 | MDF 1350H3D | ❍ | 134 | 60,8 | 63,8 |
| | | 5 | 1350H5D | ❍ | 176 | 90,5 | 93,5 |
| 14,0 | 14 | 3 | 1400H3D | ❍ | 134 | 63,0 | 66,0 |
| | | 5 | 1400H5D | ❍ | 176 | 93,8 | 96,8 |
| 14,5 | 15 | 3 | MDF 1450H3D | ❍ | 140 | 65,3 | 68,3 |
| | | 5 | 1450H5D | ❍ | 185 | 97,2 | 100,2 |
| 15,0 | 15 | 3 | 1500H3D | ❍ | 140 | 67,5 | 70,5 |
| | | 5 | 1500H5D | ❍ | 185 | 100,5 | 103,5 |
| 15,5 | 16 | 3 | MDF 1550H3D | ❍ | 146 | 69,8 | 72,8 |
| | | 5 | 1550H5D | ❍ | 194 | 103,9 | 106,9 |
| 16,0 | 16 | 3 | 1600H3D | ❍ | 146 | 72,0 | 75,0 |
| | | 5 | 1600H5D | ❍ | 194 | 107,2 | 110,2 |

Grade: ACF75





● = Euro stock
❍ = Japan stock

## ■ Recommended Cutting Conditions

### ● MDF H3D Type with Oil Hole

1. The recommended hole depth is 3 x DC. The depth is measured from the highest point of the hole on drilling in inclined surfaces.
2. The recommended cutting conditions are those for drilling on flat horizontal surfaces.
3. Adjust the feed rate according to the inclination angle when drilling in an inclined surface.
3.1 Set the feed rate at ≤ 70 % when the inclination angle is ≤ 30°.
3.2 Set the feed rate at ≤ 50 % when the inclination angle is > 30°.
4. This product is a drilling tool. Do not use it for traversing or helical milling.
5. A guide hole of the same diameter is recommended when drilling stainless steel.

($v_c$: Cutting Speed m/min f: Feed Rate mm/rev)

| Drill Diam. ØDC(mm) | Cutting Conditions | Soft Steel / General Steel (–250 HB) | Alloy Steel (–300 HB) | Hardened Steel (–50 HRC) | Stainless Steel (–200 HB) | Gray Cast Iron FC250 | Ductile Cast Iron | Aluminium Alloy |
|---|---|---|---|---|---|---|---|---|
| –Ø 4,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,06–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,06–**0,08**–0,10 | 0,04–**0,06**–0,08 | 0,06–**0,08**–0,10 |
| –Ø 6,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 70–**80**–90 | 90–**120**–150 |
| | f | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,04–**0,06**–0,08 | 0,03–**0,04**–0,05 | 0,05–**0,10**–0,15 | 0,06–**0,09**–0,12 | 0,05–**0,10**–0,15 |
| –Ø 8,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 70–**80**–90 | 90–**120**–150 |
| | f | 0,10–**0,15**–0,20 | 0,10–**0,15**–0,20 | 0,06–**0,08**–0,10 | 0,04–**0,06**–0,08 | 0,10–**0,15**–0,20 | 0,10–**0,12**–0,15 | 0,10–**0,15**–0,20 |
| –Ø 10,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 70–**80**–90 | 90–**120**–150 |
| | f | 0,12–**0,17**–0,22 | 0,12–**0,17**–0,22 | 0,08–**0,10**–0,12 | 0,06–**0,08**–0,10 | 0,12–**0,17**–0,22 | 0,12–**0,15**–0,18 | 0,15–**0,20**–0,25 |
| –Ø 12,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 70–**80**–90 | 90–**120**–150 |
| | f | 0,15–**0,20**–0,25 | 0,15–**0,20**–0,25 | 0,12–**0,15**–0,18 | 0,08–**0,10**–0,12 | 0,15–**0,20**–0,25 | 0,15–**0,18**–0,20 | 0,20–**0,25**–0,30 |
| –Ø 16,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 70–**80**–90 | 90–**120**–150 |
| | f | 0,15–**0,20**–0,25 | 0,15–**0,20**–0,25 | 0,12–**0,15**–0,18 | 0,10–**0,15**–0,20 | 0,17–**0,22**–0,27 | 0,15–**0,20**–0,25 | 0,25–**0,30**–0,40 |

Min. - **Optimum** - Max.

### ● MDF H5D Type with Oil Hole

1. Drilling that uses this tool requires a guide hole of the same diameter.
2. The cutting conditions are the recommended conditions with a guide hole.
3. The recommended hole depth is 5 x DC. The depth is measured from the highest point of the hole on drilling in inclined surfaces.
4. This product is a drilling tool. Do not use it for traversing or helical milling.

($v_c$: Cutting Speed m/min f: Feed Rate mm/rev)

| Drill Diam. ØDC(mm) | Cutting Conditions | Soft Steel / General Steel (–250 HB) | Alloy Steel (–300 HB) | Hardened Steel (–50 HRC) | Stainless Steel (–200 HB) | Gray Cast Iron FC250 | Ductile Cast Iron | Aluminium Alloy |
|---|---|---|---|---|---|---|---|---|
| –Ø 4,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,06–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,06–**0,08**–0,10 | 0,04–**0,06**–0,08 | 0,06–**0,08**–0,10 |
| –Ø 6,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70– **85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,04–**0,06**–0,08 | 0,03–**0,04**–0,05 | 0,05–**0,10**–0,15 | 0,06–**0,09**–0,12 | 0,05–**0,10**–0,15 |
| –Ø 8,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,10–**0,15**–0,20 | 0,10–**0,15**–0,20 | 0,06–**0,08**–0,10 | 0,04–**0,06**–0,08 | 0,10–**0,15**–0,20 | 0,10–**0,12**–0,15 | 0,10–**0,15**–0,20 |
| –Ø 10,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,15–**0,20**–0,25 | 0,15–**0,20**–0,25 | 0,08–**0,10**–0,12 | 0,06–**0,08**–0,10 | 0,15–**0,20**–0,25 | 0,12–**0,15**–0,18 | 0,15–**0,20**–0,25 |
| –Ø 12,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,30 | 0,12–**0,15**–0,18 | 0,08–**0,10**–0,12 | 0,17–**0,22**–0,27 | 0,15–**0,20**–0,25 | 0,20–**0,25**–0,30 |
| –Ø 16,0 | $v_c$ | 70–**85**–100 | 60–**75**–90 | 30–**40**–50 | 25–**35**–45 | 70–**85**–100 | 65–**75**–85 | 90–**120**–150 |
| | f | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,30 | 0,14–**0,17**–0,20 | 0,10–**0,15**–0,20 | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,30 | 0,25–**0,30**–0,35 |

Min. - **Optimum** - Max.



## XGHS Series

| Applications | Series | Diameter Range (mm) | Hole Depth (L/D) |
|---|---|---|---|
| Deep Hole Drilling | MDW□□□□XHGS12 | Ø 3,0 – 12,0 | –12 |
| | MDW□□□□XHGS15 | Ø 3,0 – 12,0 | –15 |
| | MDW□□□□XHGS20 | Ø 3,0 – 12,0 | –20 |
| | MDW□□□□XHGS25 | Ø 3,0 – 12,0 | –25 |
| | MDW□□□□XHGS30 | Ø 3,0 – 10,0 | –30 |
| Pilot Hole Drilling | MDW□□□□PHT | Ø 3,0 – 12,0 | –2 |

## General Features


Super MultiDrill XHGS series is a next-generation drill for deep hole drilling, features stable chip control and improved strength to further enhance efficiency of deep hole drilling.

## Characteristics and Applications


### Low Cutting Resistance

The application of a new special thinning shape „RX thinning“ reduces cutting resistance during high efficiency drilling.


**RX** THINNING



Conventional Drill




XHGS Series




Work Material: C45
Tools: MDW050XHT20 (conventional), MDW0500XHGS20 (Ø 5,0 mm, 20D)
Cutting Cond.: $v_c$ = 80 m/min, f = 0,35 mm/rev, (⇨ at the time of entry penetration f = 0,08 mm/rev), H = 90 mm
Coolant: MQL

### Chip Control

New groove shape „J flute“ with improved chip control stability when drilling deep holes.

***J*-flute**



Improved chip evacuation makes it possible to reduce spindle load fluctuation, ensuring stable, long tool life.

Consistant Chips

XHGS Series



Conv. Drill



f = 0,35 mm/rev | f = 0,40 mm/rev | f = 0,45 mm/rev


Work Material: C45
Tools: MDW050XHT20 (conventional), MDW0500XHGS20 (Ø 5,0 mm, 20D)
Cutting Cond.: $v_c$= 80 m/min, H = 90 mm
Coolant: MQL

### High Precision & Stability

The XHGS series provides excellent guide performance due to the unique design when compared to the conventional drill.

Excellent Guide Performance

Conventional Drill



XHGS Series

## Recommended Cutting Conditions

Min. - **Optimum** - Max.


| Drill Diameter DC (mm) | Cutting Conditions | Soft Steel (–200 HB) | General Steel (–250 HB) | Alloy Steel (–300 HB) | Hardened Steel (–40 HRC) | Cast Iron FC FCD |
|---|---|---|---|---|---|---|
| –Ø 3,0 | $v_c$ | 50–**60**–80 | 60–**80**–100 | 40–**55**–70 | 30–**40**–50 | 40–**55**–70 |
| | f | 0,12–**0,15**–0,20 | 0,12–**0,15**–0,20 | 0,10–**0,13**–0,16 | 0,06–**0,08**–0,12 | 0,15–**0,18**–0,23 |
| –Ø 5,0 | $v_c$ | 50–**60**–80 | 60–**80**–100 | 50–**60**–70 | 30–**45**–55 | 50–**60**–70 |
| | f | 0,15–**0,20**–0,25 | 0,15–**0,23**–0,30 | 0,12–**0,15**–0,20 | 0,08–**0,10**–0,14 | 0,17–**0,25**–0,35 |
| –Ø 10,0 | $v_c$ | 50–**70**–90 | 60–**80**–110 | 50–**65**–80 | 30–**50**–60 | 50–**65**–80 |
| | f | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,32 | 0,15–**0,20**–0,25 | 0,10–**0,15**–0,20 | 0,25–**0,28**–0,35 |
| –Ø 12,0 | $v_c$ | 60–**80**–100 | 60–**90**–120 | 50–**65**–80 | 40–**55**–70 | 50–**65**–80 |
| | f | 0,25–**0,30**–0,35 | 0,25–**0,30**–0,35 | 0,15–**0,23**–0,27 | 0,12–**0,15**–0,23 | 0,25–**0,30**–0,35 |

Note: Use lower speed when using MQL coolant and higher speed when using internal coolant. Vc: Cutting speed (m/min), f: Feed Rate (mm/rev)

## Recommended Drilling Method


### 1. Drill a pilot hole using the dedicated PHT

Select the same nominal diameter for the dedicated pilot hole drill PHT type as the deep hole drill XHGS type.
(The pilot drill diameter is designed +0,02 mm to +0,05 mm larger than the long drill diameter)





### 2. Enter the pilot hole at reduced cutting data

Rotation speed: 500 $min^{-1}$
Feed rate: 1000 to 2000 mm/min




Important:
DO NOT enter pilot hole at higher cutting data, this will cause damage to the drill.


### 3. Increase rotation speed until the set cutting speed is reached, and start normal drilling operation




When using a NC machine, only begin drilling operation once full rotation speed is reached.

### 4. After drilling rotation speed is reduced and the drill is retracted from the work material


Rotation speed: 500 $min^{-1}$
Feed rate: 1.000 to 2.000 mm/min




Retracting a drill from the work material at a high rotation speed is dangerous as doing so may result in breakage due to run-out.

### 5. Other Notes

A flat base should be prepared when the surface for the pilot tool is slanted. Spot face using:

☑ 
MultiDrill MDF type

☑ 
Flat endmill

When the deep hole drill exits through an angle surface, decrease the feed rate to f = 0,05 mm/rev just before drilling through.

## Coolant


### 1. Internal coolant supply


Use suitable coolant / emulsion
Pump pressure: Steel: 1,5 to 2,0 MPa (cooling effect increases at higher pressure, affecting chips/wear)
Cast iron & aluminium alloy: 4,0 to 6,0 MPa (priority on cooling)

### 2. Internal MQL

Airpressure: 0,5 MPa or higher
Discharge volume: It is recommended to set the maximum discharge volume possible on the machine.
*Consult the manufacturer before using with aluminium alloy.

● MDW ... XHG S ... HAK



Coated grade: ACX70

## P ●MDW…XHG S Type for Deep Hole Drilling, Diameter Ø 3,0–12,0 mm


(mm)

| Dimensions DC (mm) | Dimensions ød (mm) | Cat. No. 12, 15, 20, 25, 30 → | For 12 x D Stock | For 12 x D Dimensions L | For 12 x D Dimensions ℓ | For 15 x D Stock | For 15 x D Dimensions L | For 15 x D Dimensions ℓ | For 20 x D Stock | For 20 x D Dimensions L | For 20 x D Dimensions ℓ | For 25 x D Stock | For 25 x D Dimensions L | For 25 x D Dimensions ℓ | For 30 x D Stock | For 30 x D Dimensions L | For 30 x D Dimensions ℓ |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 3,0 | 4,0 | MDW 0300XHGS □□ HAK | ● | 85 | 57 | ● | 94 | 66 | ● | 109 | 81 | ● | 124 | 96 | ● | 139 | 111 |
| 3,5 | | 0350XHGS □□ HAK | ● | 89 | 61 | ● | 100 | 72 | ● | 117 | 89 | ● | 135 | 107 | ● | 152 | 124 |
| 4,0 | | 0400XHGS □□ HAK | ● | 95 | 67 | ● | 107 | 79 | ● | 127 | 99 | ● | 147 | 119 | ● | 167 | 139 |
| 4,5 | 5,0 | MDW 0450XHGS □□ HAK | ● | 104 | 76 | ● | 118 | 90 | ● | 140 | 112 | ● | 163 | 135 | ● | 184 | 156 |
| 5,0 | | 0500XHGS □□ HAK5* | ● | 108 | 80 | ● | 123 | 95 | ● | 148 | 120 | ● | 173 | 145 | ● | 198 | 170 |
| 5,0 | 6,0 | MDW 0500XHGS □□ HAK | ● | 116 | 80 | ● | 131 | 95 | ● | 156 | 120 | ● | 181 | 145 | ● | 206 | 170 |
| 5,5 | | 0550XHGS □□ HAK | ● | 124 | 88 | ● | 141 | 105 | ● | 168 | 132 | ● | 196 | 160 | ● | 223 | 187 |
| 6,0 | | 0600XHGS □□ HAK | ● | 130 | 94 | ● | 148 | 112 | ● | 178 | 142 | ● | 208 | 172 | ● | 238 | 202 |
| 6,5 | 8,0 | MDW 0650XHGS □□ HAK | ● | 138 | 102 | ● | 158 | 122 | ● | 190 | 154 | ● | 223 | 187 | ● | 255 | 219 |
| 6,8 | | 0680XHGS □□ HAK | ● | 144 | 108 | ● | 164 | 128 | ● | 198 | 162 | ● | 236 | 200 | ● | 266 | 230 |
| 7,0 | | 0700XHGS □□ HAK | ● | 145 | 109 | ● | 166 | 130 | ● | 201 | 165 | ● | 236 | 200 | ● | 271 | 235 |
| 7,5 | | 0750XHGS □□ HAK | | 151 | 115 | ● | 174 | 138 | | 211 | 175 | ● | 249 | 213 | | 286 | 250 |
| 8,0 | | 0800XHGS □□ HAK | ● | 157 | 121 | ● | 181 | 145 | ● | 221 | 185 | ● | 261 | 225 | ● | 301 | 265 |
| 8,5 | 10,0 | MDW 0850XHGS □□ HAK | ● | 171 | 131 | ● | 197 | 157 | ● | 239 | 199 | ● | 282 | 242 | ● | 324 | 284 |
| 9,0 | | 0900XHGS □□ HAK | ● | 177 | 137 | ● | 204 | 164 | ● | 249 | 209 | ● | 294 | 254 | ● | 339 | 299 |
| 9,5 | | 0950XHGS □□ HAK | ● | 183 | 143 | ● | 212 | 172 | ● | 259 | 219 | | 305 | 265 | | 352 | 312 |
| 10,0 | | 1000XHGS □□ HAK | ● | 187 | 147 | ● | 217 | 177 | ● | 267 | 227 | ● | 317 | 277 | ● | 367 | 327 |
| 10,5 | 12,0 | MDW 1050XHGS □□ HAK | ● | 202 | 157 | ● | 234 | 189 | ● | 286 | 241 | ● | 339 | 294 | – | – | – |
| 11,0 | | 1100XHGS □□ HAK | ● | 208 | 163 | ● | 241 | 196 | ● | 296 | 251 | ● | 351 | 306 | – | – | – |
| 11,5 | | 1150XHGS □□ HAK | ● | 213 | 168 | ● | 248 | 203 | ● | 305 | 260 | ● | 363 | 318 | – | – | – |
| 12,0 | | 1200XHGS □□ HAK | ● | 219 | 174 | ● | 255 | 210 | ● | 315 | 270 | ● | 375 | 330 | – | – | – |

(*) Cat. No. description: Drill-Ø = 5 mm, shank-Ø = 5 mm (E.g. for 20 x D: MDW050XHGS20HAK5)
Non-standard diamters and lengths on request (Ø 2,5–16,0 mm possible)



## ● MDW…PHT Type for Pilot Hole




| Dimensions DC (mm) | Dimensions ød (mm) | Cat. No. | For Pilot Hole Stock | L | ℓ1 | ℓ2 | ℓ3 |
|---|---|---|---|---|---|---|---|
| 3,03 | 4,0 | MDW 0303 PHT | ● | 52 | 9 | 22 | 28 |
| 3,53 | | 0353 PHT | ● | 52 | 9 | 22 | 28 |
| 4,03 | 5,0 | MDW 0403 PHT | ● | 59 | 12 | 29 | 28 |
| 4,53 | | 0453 PHT | ● | 59 | 12 | 29 | 28 |
| 5,03 | 6,0 | MDW 0503 PHT | ● | 71 | 15 | 33 | 36 |
| 5,53 | | 0553 PHT | ● | 71 | 15 | 33 | 36 |
| 6,03 | 8,0 | MDW 0603 PHT | ● | 76 | 18 | 38 | 36 |
| 6,53 | | 0653 PHT | ● | 76 | 18 | 38 | 36 |
| 6,83 | | 0683 PHT | ● | 76 | 18 | 38 | 36 |
| 7,03 | | 0703 PHT | ● | 82 | 21 | 43 | 36 |
| 7,53 | | 0753 PHT | ● | 82 | 21 | 43 | 36 |
| 8,03 | 10,0 | MDW 0803 PHT | ● | 88 | 24 | 46 | 40 |
| 8,53 | | 0853 PHT | ● | 88 | 24 | 46 | 40 |
| 9,03 | | 0903 PHT | ● | 88 | 24 | 46 | 40 |
| 9,53 | | 0953 PHT | ● | 88 | 24 | 46 | 40 |
| 10,03 | 12,0 | MDW 1003 PHT | ● | 104 | 30 | 55 | 45 |
| 10,53 | | 1053 PHT | ● | 104 | 30 | 55 | 45 |
| 11,03 | | 1103 PHT | ● | 104 | 30 | 55 | 45 |
| 11,53 | | 1153 PHT | ● | 104 | 30 | 55 | 45 |
| 12,03 | 14,0 | MDW 1203 PHT | ● | 117 | 42 | 68 | 45 |

## ■ How to Order

Non stock items – minimum order 6 pieces
Always specify the catalogue number and drill diameter as shown
- eg drill diameter 5,0 mm = MDW 050

E.g., **MDW 050 X H G S 30 HAK ACX70** (Grade)

- Super MULTI-DRILL
- DC = 5,0 mm
- Extra long type
- With spiral coolant holes
- Special shape (RX thinning) + J flute
- Cutting edges for steel with double margin
- Drilling depth (L/D ratio)
- Shank type to DIN6535







● = Euro stock

# Extra Long SUPER MULTI-DRILLs
# MDW ... XHTA/PHT Type

● MDW ... XHT A ... HAK



Helix angle: 30°
Uncoated grade: KH03

## N ●MDW…XHT A Type for Aluminium and Copper Alloys

(mm)

| Dimensions | | Cat. No. | For 20 x D | | | For 30 x D | | |
|---|---|---|---|---|---|---|---|---|
| DC (mm) | ød (mm) | 20, 30 → | Stock | Dimensions | | Stock | Dimensions | |
| | | | 20 | L | $\ell_1$ | 30 | L | $\ell_1$ |
| 4,0 | 4,0 | MDW 040XHT A□□ HAK | ● | 127 | 97 | ● | 167 | 137 |
| 5,0 | 6,0 | MDW 050XHT A□□ HAK | ● | 156 | 118 | ● | 206 | 168 |
| 6,0 | | 060XHT A□□ HAK | ● | 178 | 138 | ● | 238 | 198 |
| 7,0 | 8,0 | MDW 070XHT A□□ HAK | | 201 | 162 | ● | 271 | 232 |
| 8,0 | | 080XHT A□□ HAK | ● | 221 | 182 | ● | 301 | 262 |
| 9,0 | 10,0 | MDW 090XHT A□□ HAK | ● | 249 | 205 | ● | 339 | 295 |
| 10,0 | | 100XHT A□□ HAK | ● | 267 | 225 | ● | 367 | 325 |

⇨ All Long Drill series include an allowance to accomodate regrinding!
⇨ Uncoated carbide grade: KH03

## ■ How to Order

Non stock items – minimum order 6 pieces
Always specify the catalogue number and drill diameter as shown
- eg drill diameter 5,0 mm = MDW 050

E.g.,

**MDW 050 X H T A 30 HAK** (KH03) (Grade)

- Super MULTI-DRILL
- DC = 5,0 mm
- Extra long type
- with spiral coolant holes
- Shank type to DIN6535
- Drilling depth (L/D ratio)
- Cutting edges for Al and Cu alloys
- Special shape of clearance face


## ■ Recommended Cutting Conditions

Vc: Cutting speed (m/min), f: Feed Rate (mm/rev)

| Drill Ø (mm) \ Work material | | Aluminium Alloy |
|---|---|---|
| –Ø 5,0 | $v_c$ | 80–160 |
| | f | 0,08–0,30 |
| –Ø 6,0 | $v_c$ | 80–160 |
| | f | 0,12–0,35 |
| –Ø 8,0 | $v_c$ | 80–180 |
| | f | 0,15–0,40 |
| –Ø 10,0 | $v_c$ | 80–180 |
| | f | 0,20–0,50 |
| –Ø 12,0 | $v_c$ | 80–180 |
| | f | 0,20–0,45 |



## ● MDW…PHT Type for Pilot Hole




Helix angle: 30°
$\ell_1$ = Effective drilling length
Coated grade: ACW70

| Dimensions | | Cat. No. | For Pilot Hole | | | | |
|---|---|---|---|---|---|---|---|
| DC (mm) | ød (mm) | | Stock | Dimensions (mm) | | | |
| | | | | L | $\ell_1$ | $\ell_2$ | $\ell_3$ |
| 3,03 | 4,0 | MDW 0303 PHT | ● | 52 | 9 | 22 | 28 |
| 3,53 | | 0353 PHT | ● | 52 | 9 | 22 | 28 |
| 4,03 | 5,0 | MDW 0403 PHT | ● | 59 | 12 | 29 | 28 |
| 4,53 | | 0453 PHT | ● | 59 | 12 | 29 | 28 |
| 5,03 | 6,0 | MDW 0503 PHT | ● | 71 | 15 | 33 | 36 |
| 5,53 | | 0553 PHT | ● | 71 | 15 | 33 | 36 |
| 6,03 | 8,0 | MDW 0603 PHT | ● | 76 | 18 | 38 | 36 |
| 6,53 | | 0653 PHT | ● | 76 | 18 | 38 | 36 |
| 6,83 | | 0683 PHT | ● | 76 | 18 | 38 | 36 |
| 7,03 | | 0703 PHT | ● | 82 | 21 | 43 | 36 |
| 7,53 | | 0753 PHT | ● | 82 | 21 | 43 | 36 |
| 8,03 | 10,0 | MDW 0803 PHT | ● | 88 | 24 | 46 | 40 |
| 8,53 | | 0853 PHT | ● | 88 | 24 | 46 | 40 |
| 9,03 | | 0903 PHT | ● | 88 | 24 | 46 | 40 |
| 9,53 | | 0953 PHT | ● | 88 | 24 | 46 | 40 |
| 10,03 | 12,0 | MDW 1003 PHT | ● | 104 | 30 | 55 | 45 |
| 10,53 | | 1053 PHT | ● | 104 | 30 | 55 | 45 |
| 11,03 | | 1103 PHT | ● | 104 | 30 | 55 | 45 |
| 11,53 | | 1153 PHT | ● | 104 | 30 | 55 | 45 |
| 12,03 | 14,0 | MDW 1203 PHT | ● | 117 | 42 | 68 | 45 |

## ■ How to Order

Non stock items – minimum order 6 pieces
Always specify the catalogue number and drill diameter as shown -
eg. drill diameter 5,03 mm = MDW 0503

E.g.,

**MDW 0503 PHT**, ACW70


- Super MULTI-DRILL
- DC = 5,03 mm
- TiAlN coated grade
- Pilot drill with spiral coolant holes

# MDW ... NHGS Type

DLC (Diamond Like Carbon) Coated Multi-Drills

## With Coolant Holes (3D/5D/10D)






## Characteristics

- **High efficiency drilling**
  AURORA COAT and strong helix design reduces cutting forces and improves edge sharpness.
- **Precision drilling**
  Special cutting edge design improves hole precision and quality.
- **Longer tool life**
  With AURORA COAT coupled with the cutting edge design, long and stable tool life can be achieved.
- **Deep hole (L/D = 20) drilling**
  Drills for deep hole drilling can be custom-made.
  Production range: Ø 3,0–16,0 mm
  total length: 50 times drill diameter (max. 290 mm)

## Applicable Work Materials

- Aluminium Die Casting
- Aluminium Alloy
- Aluminium Alloy Casting
- Brass Casting
- Bronze Casting

## Comparison of Cutting Force (Thrust Force)




## Recommended Cutting Conditions

| Diameter (mm) | | Aluminium Alloy | Aluminium Die Casting | Copper Alloy |
|---|---|---|---|---|
| –Ø 5 | $v_c$ | 80–160 | 80–180 | 80–160 |
| | f | 0,08–0,30 | 0,10–0,30 | 0,08–0,15 |
| –Ø 10 | $v_c$ | 80–180 | 80–200 | 60–180 |
| | f | 0,10–0,30 | 0,10–0,35 | 0,10–0,20 |
| –Ø 16 | $v_c$ | 80–200 | 80–200 | 80–200 |
| | f | 0,15–0,40 | 0,10–0,40 | 0,10–0,25 |

( $v_c$ : Cutting Speed (m/min), f : Feed rate (mm/rev), Min–Max )

## Diameter Ø 3,0–8,0 mm

(mm)

| Dimensions | | Cat. No. | 3D Type | | | 5D Type | | | 10D Type | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | |
| øD | ød | 3, 5, 10 ↘ | 3 | L | ℓ | 5 | L | ℓ | 10 | L | ℓ |
| **3,0** | 3,0 | MDW 0300 NHGS□□ | ❍ | 68,6 | 18,1 | ❍ | 78,6 | 28,6 | ❍ | 92,6 | 42,6 |
| 3,1 | | MDW 0310 NHGS□□ | | | | ❍ | | | | | |
| 3,2 | | MDW 0320 NHGS□□ | ❍ | | | ❑ | | | ❍ | | |
| 3,3 | | MDW 0330 NHGS□□ | ❍ | | 20,7 | ❍ | | 32,7 | | | 49,7 |
| 3,4 | | MDW 0340 NHGS□□ | | | | ❍ | | | ❍ | | |
| 3,5 | | MDW 0350 NHGS□□ | ❑ | | | ❍ | | | ❍ | | |
| 3,6 | | MDW 0360 NHGS□□ | | | | ❍ | | | ❍ | | |
| 3,65 | 4,0 | MDW 0365 NHGS□□ | ❑ | 72,8 | | ❍ | 86,8 | | | 106,8 | |
| 3,66 | | MDW 0366 NHGS□□ | | | | ❍ | | | | | |
| 3,7 | | MDW 0370 NHGS□□ | | | 23,3 | ❍ | | 36,8 | | | 56,8 |
| 3,8 | | MDW 0380 NHGS□□ | | | | ❍ | | | | | |
| 3,9 | | MDW 0390 NHGS□□ | | | | ❑ | | | ❍ | | |
| **4,0** | | MDW 0400 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 4,1 | | MDW 0410 NHGS□□ | ❍ | | | ❍ | | | | | |
| 4,2 | | MDW 0420 NHGS□□ | ❍ | | | ❍ | | | | | |
| 4,3 | | MDW 0430 NHGS□□ | | | 25,9 | ❍ | | 40,9 | | | 63,9 |
| 4,4 | | MDW 0440 NHGS□□ | | | | ❑ | | | | | |
| 4,5 | | MDW 0450 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 4,6 | 5,0 | MDW 0460 NHGS□□ | ❍ | 81,0 | | ❍ | 99,0 | | | 125,0 | |
| 4,7 | | MDW 0470 NHGS□□ | | | | ❍ | | | | | |
| 4,8 | | MDW 0480 NHGS□□ | | | 28,5 | ❍ | | 45,0 | | | 71,0 |
| 4,9 | | MDW 0490 NHGS□□ | | | | ❍ | | | ❍ | | |
| **5,0** | | MDW 0500 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 5,1 | | MDW 0510 NHGS□□ | | | | ❍ | | | ❑ | | |
| 5,2 | | MDW 0520 NHGS□□ | ❑ | | | ❑ | | | | | |
| 5,3 | | MDW 0530 NHGS□□ | ❍ | | 28,6 | ❑ | | 45,1 | | | 88,1 |
| 5,4 | | MDW 0540 NHGS□□ | | | | ❑ | | | | | |
| 5,5 | | MDW 0550 NHGS□□ | ❍ | | | ❑ | | | ❍ | | |
| 5,6 | 6,0 | MDW 0560 NHGS□□ | | 83,2 | | ❍ | 101,2 | | | 137,2 | |
| 5,7 | | MDW 0570 NHGS□□ | | | | ❍ | | | | | |
| 5,8 | | MDW 0580 NHGS□□ | | | 31,2 | ❍ | | 49,2 | | | 85,2 |
| 5,9 | | MDW 0590 NHGS□□ | ❑ | | | ❑ | | | | | |
| **6,0** | | MDW 0600 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 6,1 | | MDW 0610 NHGS□□ | | | | ❍ | | | ❍ | | |
| 6,2 | | MDW 0620 NHGS□□ | | | | ❍ | | | | | |
| 6,3 | | MDW 0630 NHGS□□ | | | 33,8 | ❍ | | 53,3 | | | 92,3 |
| 6,4 | | MDW 0640 NHGS□□ | | | | ❍ | | | | | |
| 6,5 | | MDW 0650 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 6,6 | 7,0 | MDW 0660 NHGS□□ | | 89,5 | | ❑ | 110,5 | | | 152,5 | |
| 6,7 | | MDW 0670 NHGS□□ | ❑ | | | ❍ | | | ❑ | | |
| 6,8 | | MDW 0680 NHGS□□ | ❍ | | 36,5 | ❍ | | 57,5 | ❍ | | 99,5 |
| 6,9 | | MDW 0690 NHGS□□ | | | | ❑ | | | | | |
| **7,0** | | MDW 0700 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 7,1 | | MDW 0710 NHGS□□ | | | | ❑ | | | | | |
| 7,2 | | MDW 0720 NHGS□□ | | | | ❑ | | | ❑ | | |
| 7,3 | | MDW 0730 NHGS□□ | | | 39,1 | ❑ | | 61,6 | | | 116,6 |
| 7,35 | | MDW 0735 NHGS□□ | ❍ | | | ❑ | | | | | |
| 7,4 | | MDW 0740 NHGS□□ | ❍ | | | ❍ | | | | | |
| 7,5 | 8,0 | MDW 0750 NHGS□□ | ❑ | 95,7 | | ❍ | 119,7 | | ❑ | 167,7 | |
| 7,6 | | MDW 0760 NHGS□□ | | | | ❑ | | | | | |
| 7,7 | | MDW 0770 NHGS□□ | | | | ❍ | | | | | |
| 7,8 | | MDW 0780 NHGS□□ | ❍ | | 41,7 | ❍ | | 65,7 | ❑ | | 113,7 |
| 7,9 | | MDW 0790 NHGS□□ | | | | ❍ | | | | | |
| **8,0** | | MDW 0800 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |

AURORA Coated NHGS Type, Grade: DL1300







❍ = Japan stock
❑ = Delivery on request

# AURORA COAT SERIES
# MDW ... NHGS Type

● NHGS 3/5 Type (Ø 3,0–16,0 mm)




● NHGS 10 Type (Ø 3,0–16,0 mm)




## ●Diameter Ø 8,1–13,0 mm

(mm)

| Dimensions | | Cat. No. | 3D Type | | | 5D Type | | | 10D Type | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | |
| øD | ød | 3, 5, 10 ↘ | 3 | L | | 5 | L | ℓ | 10 | L | ℓ |
| 8,1 | | MDW 0810 NHGS□□ | | | | ❒ | | | | | |
| 8,2 | | MDW 0820 NHGS□□ | | | | ❍ | | | | | |
| 8,3 | | MDW 0830 NHGS□□ | | | 44,3 | ❍ | | 69,8 | | | 118,8 |
| 8,4 | | MDW 0840 NHGS□□ | | | | ❍ | | | | | |
| 8,5 | 9,0 | MDW 0850 NHGS□□ | ❍ | 101,9 | | ❍ | 128,9 | | ❍ | 182,9 | |
| 8,6 | | MDW 0860 NHGS□□ | ❒ | | | ❍ | | | | | |
| 8,7 | | MDW 0870 NHGS□□ | | | | ❒ | | | | | |
| 8,8 | | MDW 0880 NHGS□□ | ❍ | | 46,9 | ❒ | | 73,9 | | | 127,9 |
| 8,9 | | MDW 0890 NHGS□□ | | | | ❒ | | | | | |
| **9,0** | | MDW 0900 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 9,1 | | MDW 0910 NHGS□□ | | | | ❒ | | | | | |
| 9,2 | | MDW 0920 NHGS□□ | | | | ❒ | | | | | |
| 9,21 | | MDW 0921 NHGS□□ | ❒ | | | ❒ | | | | | |
| 9,3 | | MDW 0930 NHGS□□ | | | 49,5 | ❍ | | 78,0 | | | 135,0 |
| 9,4 | | MDW 0940 NHGS□□ | ❒ | | | ❒ | | | | | |
| 9,5 | 10,0 | MDW 0950 NHGS□□ | ❒ | 108,0 | | ❍ | 138,0 | | ❒ | 198,0 | |
| 9,6 | | MDW 0960 NHGS□□ | | | | ❒ | | | | | |
| 9,7 | | MDW 0970 NHGS□□ | | | | ❒ | | | | | |
| 9,8 | | MDW 0980 NHGS□□ | | | 52,0 | ❍ | | 82,0 | ❍ | | 142,0 |
| 9,9 | | MDW 0990 NHGS□□ | | | | ❍ | | | | | |
| **10,0** | | MDW 1000 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 10,1 | | MDW 1010 NHGS□□ | ❒ | | | | | | | | |
| 10,2 | | MDW 1020 NHGS□□ | | | | | | | | | |
| 10,3 | | MDW 1030 NHGS□□ | ❒ | | 54,7 | ❒ | | 86,2 | | | 149,2 |
| 10,4 | | MDW 1040 NHGS□□ | | | | ❒ | | | | | |
| 10,5 | | MDW 1050 NHGS□□ | ❍ | | | ❒ | | | ❒ | | |
| 10,6 | 11,0 | MDW 1060 NHGS□□ | ❒ | 168,3 | | ❒ | 151,3 | | | 217,3 | |
| 10,7 | | MDW 1070 NHGS□□ | | | | | | | | | |
| 10,8 | | MDW 1080 NHGS□□ | | | 57,3 | | | 90,3 | | | 156,3 |
| 10,9 | | MDW 1090 NHGS□□ | | | | | | | | | |
| **11,0** | | MDW 1100 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 11,08 | | MDW 1108 NHGS□□ | ❒ | | | ❒ | | | | | |
| 11,1 | | MDW 1110 NHGS□□ | ❒ | | | ❒ | | | | | |
| 11,2 | | MDW 1120 NHGS□□ | ❍ | | 59,9 | ❒ | | 94,4 | | | 163,4 |
| 11,3 | | MDW 1130 NHGS□□ | | | | | | | | | |
| 11,4 | | MDW 1140 NHGS□□ | ❒ | | | ❒ | | | | | |
| 11,5 | 12,0 | MDW 1150 NHGS□□ | ❍ | 124,5 | | ❒ | 160,5 | | ❒ | 232,5 | |
| 11,6 | | MDW 1160 NHGS□□ | | | | | | | | | |
| 11,7 | | MDW 1170 NHGS□□ | | | | | | | | | |
| 11,8 | | MDW 1180 NHGS□□ | | | 62,5 | | | 98,5 | | | 170,5 |
| 11,9 | | MDW 1190 NHGS□□ | | | | | | | | | |
| **12,0** | | MDW 1200 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |
| 12,1 | | MDW 1210 NHGS□□ | ❒ | | | ❒ | | | | | |
| 12,2 | | MDW 1220 NHGS□□ | | | | | | | | | |
| 12,3 | | MDW 1230 NHGS□□ | ❒ | | 65,1 | ❒ | | 102,6 | | | 177,6 |
| 12,4 | | MDW 1240 NHGS□□ | | | | | | | | | |
| 12,5 | | MDW 1250 NHGS□□ | ❒ | | | ❍ | | | ❒ | | |
| 12,6 | 13,0 | MDW 1260 NHGS□□ | | 130,7 | | | 169,7 | | | 247,7 | |
| 12,7 | | MDW 1270 NHGS□□ | | | | | | | | | |
| 12,8 | | MDW 1280 NHGS□□ | | | 67,7 | | | 106,7 | | | 184,7 |
| 12,9 | | MDW 1290 NHGS□□ | | | | | | | | | |
| 12,96 | | MDW 1296 NHGS□□ | ❒ | | | ❒ | | | | | |
| **13,0** | | MDW 1300 NHGS□□ | ❍ | | | ❍ | | | ❍ | | |

## ●Diameter Ø 13,1–16,0 mm

(mm)

| Dimensions | | Cat. No. | 3D Type | | | 5D Type | | | 10D Type | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | |
| øD | ød | 3, 5, 10 ↘ | 3 | L | ℓ | 5 | L | ℓ | 10 | L | ℓ |
| 13,1 | | MDW 1310 NHGS□□ | | | | | | | | | |
| 13,2 | | MDW 1320 NHGS□□ | | | | | | | | | |
| 13,3 | | MDW 1330 NHGS□□ | | | 70,8 | | | 110,8 | | | 191,8 |
| 13,4 | | MDW 1340 NHGS□□ | | | | | | | | | |
| 13,5 | 14,0 | MDW 1350 NHGS□□ | ❍ | 136,9 | | ❍ | 178,9 | | | 262,9 | |
| 13,6 | | MDW 1360 NHGS□□ | | | | | | | | | |
| 13,7 | | MDW 1370 NHGS□□ | | | | | | | | | |
| 13,8 | | MDW 1380 NHGS□□ | | | 72,9 | | | 114,9 | | | 198,9 |
| 13,9 | | MDW 1390 NHGS□□ | | | | | | | | | |
| **14,0** | | MDW 1400 NHGS□□ | ❍ | | | ❍ | | | | | |
| 14,1 | | MDW 1410 NHGS□□ | ❒ | | | ❒ | | | | | |
| 14,2 | | MDW 1420 NHGS□□ | | | | | | | | | |
| 14,3 | | MDW 1430 NHGS□□ | | | 75,5 | | | 119,0 | | | 206 |
| 14,4 | | MDW 1440 NHGS□□ | | | | | | | | | |
| 14,5 | | MDW 1450 NHGS□□ | ❍ | | | ❍ | | | | | |
| 14,6 | 15,0 | MDW 1460 NHGS□□ | | 141,1 | | | 188,1 | | | 278,1 | |
| 14,7 | | MDW 1470 NHGS□□ | | | | | | | | | |
| 14,8 | | MDW 1480 NHGS□□ | | | 78,1 | | | 123,1 | | | 213,1 |
| 14,9 | | MDW 1490 NHGS□□ | ❒ | | | ❒ | | | | | |
| 14,96 | | MDW 1496 NHGS□□ | ❒ | | | ❒ | | | | | |
| **15,0** | | MDW 1500 NHGS□□ | ❍ | | | ❍ | | | | | |
| 15,1 | | MDW 1510 NHGS□□ | | | | | | | | | |
| 15,2 | | MDW 1520 NHGS□□ | | | | | | | | | |
| 15,3 | | MDW 1530 NHGS□□ | | | 80,7 | | | 127,2 | | | 220,2 |
| 15,4 | | MDW 1540 NHGS□□ | | | | | | | | | |
| 15,5 | 16,0 | MDW 1550 NHGS□□ | ❍ | 149,3 | | ❒ | 197,3 | | | 293,3 | |
| 15,6 | | MDW 1560 NHGS□□ | | | | | | | | | |
| 15,7 | | MDW 1570 NHGS□□ | | | | | | | | | |
| 15,8 | | MDW 1580 NHGS□□ | | | 83,3 | | | 131,3 | | | 227,3 |
| 15,9 | | MDW 1590 NHGS□□ | | | | | | | | | |
| **16,0** | | MDW 1600 NHGS□□ | ❍ | | | ❍ | | | | | |

AURORA Coated NHGS Type, Grade: DL1300

## ■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs.
Please specify the Cat. No.
For example, if the diameter of the drill is 10,3 mm and the ratio to øD is 5, please indicate as follow.

E.g.,

**MDW 1030 NHGS 5** , DL1300 (Grade)

- MDW: Super MULTI-DRILL
- 1030: DC = 10,3 mm
- H: Applicable work materials
- GS: with spiral coolant holes
- 5: Drilling depth (The ratio to øD): –3 / –**5** / –10
- NHGS: NHGS type Multi-Drills

# Micro Long Drills
# MLDH ....L/P Type



## General Features

Micro Long Drills are oil-hole drills for high efficiency drilling that were developed for drilling deep, small-diameter holes. These next-generation, small-diameter hole drills feature improved strength - often a problem area with small-diameter drills.

## Characteristics and Applications

● Deep-hole drilling
New groove shape ensures good drill rigidity and chip evacuation.
High efficiency drilling to depths of over 20 x drill diameter at over $v_f$ = 500 mm/min (drill diameter 1,3 mm, X12CrS13 equivalent).
Optimal thinning and edge balance for stable chip control.

● Long tool life
Special coating provides long tool life with a wide variety of work materials.
Improved chip evacuation makes it possible to reduce spindle load fluctuation, ensuring stable tool life.

## Series

| Application | Type | Diameter Range (mm) | Hole Depth (L/D) |
|---|---|---|---|
| Guide Hole Drilling | MLDH □□□□ P | Ø 0,8 – 2,0 | –2 |
| Deep Hole Drilling | MLDH □□□□ L5 | Ø 0,8 – 2,0 | –5 |
| | MLDH □□□□ L12 | Ø 0,8 – 2,0 | –12 |
| | MLDH □□□□ L20 | Ø 0,8 – 2,0 | –20 |
| | MLDH □□□□ L30 | Ø 0,8 – 2,0 | –30 |

## Recommended Cutting Conditions

● MLDH .... P / L5

( $v_c$ : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max )

| Drill-ø (mm) | Cutting Cond. | Soft Steel ( –200 HB) | General Steel (200–250 HB) | Alloy Steel (250–300 HB) | Stainless Steel (–200 HB) | Cast Iron | Aluminium Alloy | Heat-Resistant Steels |
|---|---|---|---|---|---|---|---|---|
| –Ø 1,0 | $v_c$ | 40–**50**–60 | 40–**50**–60 | 40–**50**–60 | 20–**30**–40 | 40–**50**–60 | 50–**60**–70 | 5–**10**–15 |
| | f | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,02–**0,03**–0,04 | 0,03–**0,04**–0,06 | 0,005–**0,01**–0,02 |
| –Ø 1,5 | $v_c$ | 40–**50**–60 | 40–**50**–60 | 40–**50**–60 | 20–**30**–40 | 40–**50**–60 | 50–**60**–70 | 5–**10**–15 |
| | f | 0,04–**0,08**–0,12 | 0,04–**0,08**–0,12 | 0,04–**0,08**–0,12 | 0,02–**0,05**–0,10 | 0,04–**0,08**–0,12 | 0,05–**0,10**–0,15 | 0,01–**0,03**–0,05 |
| –Ø 2,0 | $v_c$ | 40–**50**–60 | 40–**50**–60 | 40–**50**–60 | 20–**30**–40 | 40–**50**–60 | 50–**60**–70 | 5–**10**–15 |
| | f | 0,06–**0,08**–0,12 | 0,06–**0,08**–0,12 | 0,06–**0,08**–0,12 | 0,04–**0,06**–0,10 | 0,06–**0,08**–0,12 | 0,08–**0,12**–0,15 | 0,01–**0,03**–0,05 |

● MLDH .... L12 / L20 / L30

( $v_c$ : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max )

| Drill-ø (mm) | Cutting Cond. | Soft Steel ( –200 HB) | General Steel (200–250 HB) | Alloy Steel (250–300 HB) | Stainless Steel (–200 HB) | Cast Iron | Aluminium Alloy | Heat-Resistant Steels |
|---|---|---|---|---|---|---|---|---|
| –Ø 1,0 | $v_c$ | 40–**50**–60 | 40–**50**–60 | 40–**50**–60 | 20–**30**–40 | 40–**50**–60 | 50–**60**–70 | 5–**10**–15 |
| | f | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,01–**0,02**–0,03 | 0,02–**0,03**–0,04 | 0,03–**0,04**–0,06 | 0,005–**0,01**–0,02 |
| –Ø 1,5 | $v_c$ | 40–**50**–60 | 40–**50**–60 | 40–**50**–60 | 20–**30**–40 | 40–**50**–60 | 50–**60**–70 | 5–**10**–15 |
| | f | 0,03–**0,05**–0,07 | 0,03–**0,05**–0,07 | 0,03–**0,05**–0,07 | 0,02–**0,04**–0,07 | 0,04–**0,07**–0,10 | 0,05–**0,08**–0,12 | 0,01–**0,02**–0,03 |
| –Ø 2,0 | $v_c$ | 40–**50**–60 | 40–**50**–60 | 40–**50**–60 | 20–**30**–40 | 40–**50**–60 | 50–**60**–70 | 5–**10**–15 |
| | f | 0,04–**0,06**–0,08 | 0,04–**0,06**–0,08 | 0,04–**0,06**–0,08 | 0,04–**0,06**–0,08 | 0,04–**0,07**–0,10 | 0,05–**0,08**–0,12 | 0,01–**0,02**–0,03 |





○ = Japan stock







# Micro Long Drills
# MLDH ....L/P Type

## Internal Coolant Supply

● MLDH-P For Pilot Hole Drilling




● MLDH-L For Deep Hole Drilling




## Stock

(mm)

| ØD (mm) | P Type for Pilot Hole Drilling | | | | L Type for Deep Hole Drilling | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Cat. No. | Stock | Dimensions | | Cat. No. 5,12,20,30 | 5x D | | | 12x D | | | 20x D | | | 30x D | | |
| | | | | | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | |
| | | | L | ℓ | | 5 | L | ℓ | 1 2 | L | ℓ | 2 0 | L | ℓ | 3 0 | L | ℓ |
| **0,80** | MLDH 0800P | ❍ | 45 | 3,2 | MLDH 0800L□□ | ❍ | 50 | 8 | ❍ | 55 | 14 | ❍ | 60 | 19 | ❍ | 70 | 28 |
| **0,81** | 0810P | ❍ | | | 0810L□□ | ❍ | | 9 | ❍ | | | ❍ | | | ❍ | | |
| **0,82** | MLDH 0820P | ❍ | | 3,3 | MLDH 0820L□□ | ❍ | | | ❍ | | | ❍ | | 20 | ❍ | | |
| **0,83** | 0830P | ❍ | | | 0830L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **0,84** | MLDH 0840P | ❍ | | 3,4 | MLDH 0840L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | 29 |
| **0,85** | 0850P | ❍ | | | 0850L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **0,86** | 0860P | ❍ | | | 0860L□□ | ❍ | | | ❍ | | 15 | ❍ | 65 | 21 | ❍ | | |
| **0,87** | MLDH 0870P | ❍ | | 3,5 | MLDH 0870L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | 30 |
| **0,88** | 0880P | ❍ | | | 0880L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **0,89** | MLDH 0890P | ❍ | | 3,6 | MLDH 0890L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **0,90** | 0900P | ❍ | | | 0900L□□ | ❍ | | | ❍ | | | ❍ | | 22 | ❍ | 75 | 31 |
| **0,91** | 0910P | ❍ | | | 0910L□□ | ❍ | | 10 | ❍ | | | ❍ | | | ❍ | | |
| **0,92** | MLDH 0920P | ❍ | | 3,7 | MLDH 0920L□□ | ❍ | | | ❍ | 60 | 16 | ❍ | | | ❍ | | 32 |
| **0,93** | 0930P | ❍ | | | 0930L□□ | ❍ | | | ❍ | | | ❍ | | 23 | ❍ | | |
| **0,94** | MLDH 0940P | ❍ | | 3,8 | MLDH 0940L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **0,95** | 0950P | ❍ | | | 0950L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | 33 |
| **0,96** | 0960P | ❍ | | | 0960L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **0,97** | MLDH 0970P | ❍ | | 3,9 | MLDH 0970L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **0,98** | 0980P | ❍ | | | 0980L□□ | ❍ | | | ❍ | | 17 | ❍ | | 24 | ❍ | | 34 |
| **0,99** | MLDH 0990P | ❍ | | 4,0 | MLDH 0990L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **1,00** | 1000P | ❍ | | | 1000L□□ | ❍ | | | ❍ | | | ❍ | | | ❍ | | |
| **1,05** | MLDH 1050P | ❍ | | 4,2 | MLDH 1050L□□ | ❍ | 55 | 12 | ❍ | 65 | 18 | ❍ | 70 | 25 | ❍ | 80 | 36 |
| **1,10** | MLDH 1100P | ❍ | | 4,4 | MLDH 1100L□□ | ❍ | | | ❍ | | 19 | ❍ | | 26 | ❍ | | 37 |
| **1,15** | MLDH 1150P | ❍ | | 4,6 | MLDH 1150L□□ | ❍ | | | ❍ | | 20 | ❍ | | 28 | ❍ | | 39 |
| **1,20** | MLDH 1200P | ❍ | | 4,8 | MLDH 1200L□□ | ❍ | | | ❍ | | | ❍ | | 29 | ❍ | 85 | 41 |
| **1,25** | MLDH 1250P | ❍ | | 5,0 | MLDH 1250L□□ | ❍ | | 14 | ❍ | | 21 | ❍ | | 30 | ❍ | | 43 |
| **1,30** | MLDH 1300P | ❍ | | 5,2 | MLDH 1300L□□ | ❍ | | | ❍ | | 22 | ❍ | 75 | 31 | ❍ | | 44 |
| **1,35** | MLDH 1350P | ❍ | | 5,4 | MLDH 1350L□□ | ❍ | | | ❍ | | 23 | ❍ | | 32 | ❍ | 90 | 46 |
| **1,40** | MLDH 1400P | ❍ | | 5,6 | MLDH 1400L□□ | ❍ | | | ❍ | 65 | 24 | ❍ | | 34 | ❍ | | 48 |
| **1,45** | MLDH 1450P | ❍ | | 5,8 | MLDH 1450L□□ | ❍ | | | ❍ | | 25 | ❍ | | 35 | ❍ | | 49 |
| **1,50** | MLDH 1500P | ❍ | | 6,0 | MLDH 1500L□□ | ❍ | | 16 | ❍ | | 26 | ❍ | | 36 | ❍ | | 51 |
| **1,55** | MLDH 1550P | ❍ | | 6,2 | MLDH 1550L□□ | ❍ | | | ❍ | | | ❍ | 80 | 37 | ❍ | 95 | 53 |
| **1,60** | MLDH 1600P | ❍ | | 6,4 | MLDH 1600L□□ | ❍ | | | ❍ | | 27 | ❍ | | 38 | ❍ | | 54 |
| **1,65** | MLDH 1650P | ❍ | 50 | 6,6 | MLDH 1650L□□ | ❍ | 60 | 18 | ❍ | 70 | 28 | ❍ | | 40 | ❍ | | 56 |
| **1,70** | MLDH 1700P | ❍ | | 6,8 | MLDH 1700L□□ | ❍ | | | ❍ | | 29 | ❍ | | 41 | ❍ | 100 | 58 |
| **1,75** | MLDH 1750P | ❍ | | 7,0 | MLDH 1750L□□ | ❍ | | | ❍ | | 30 | ❍ | | 42 | ❍ | | 60 |
| **1,80** | MLDH 1800P | ❍ | | 7,2 | MLDH 1800L□□ | ❍ | | | ❍ | | 31 | ❍ | 85 | 43 | ❍ | | 61 |
| **1,85** | MLDH 1850P | ❍ | | 7,4 | MLDH 1850L□□ | ❍ | | 20 | ❍ | | | ❍ | | 44 | ❍ | 103 | 63 |
| **1,90** | MLDH 1900P | ❍ | | 7,6 | MLDH 1900L□□ | ❍ | | | ❍ | 75 | 32 | ❍ | | 46 | ❍ | | 65 |
| **1,95** | MLDH 1950P | ❍ | | 7,8 | MLDH 1950L□□ | ❍ | | | ❍ | | 33 | ❍ | | 47 | ❍ | | 66 |
| **2,00** | MLDH 2000P | ❍ | | 8,0 | MLDH 2000L□□ | ❍ | | | ❍ | | 34 | ❍ | 90 | 48 | ❍ | | 68 |

PVD Coated Grade: ACV70

# MDUS / MDSS Type

Fig.1 Helix angle: 30°





Fig.2






Fig.3




## ●Diameter Ø 0,03–0,19 mm

| øD (mm) | Cat. No. | Stock | Dimensions ℓ1 | Dimensions ℓ2 | Fig. | Pcs./Packing |
|---|---|---|---|---|---|---|
| 0,030 | MDUS 0030-30C | ❍ | 0,3 | 28 | 1 | 5 |
| 0,035 | MDUS 0035-30C | | 0,4 | | | |
| 0,040 | MDUS 0040-30C | ❍ | | | | |
| 0,045 | MDUS 0045-30C | | 0,5 | | | |
| **0,050** | MDUS 0050-30C | ❍ | | | | |
| 0,055 | MDUS 0055-30C | | 0,6 | | | |
| 0,060 | MDUS 0060-30C | | | | | |
| 0,065 | MDUS 0065-30C | | 0,7 | | | |
| 0,070 | MDUS 0070-30C | | | | | |
| 0,075 | MDUS 0075-30C | | 0,8 | | | |
| 0,080 | MDUS 0080-30C | ❍ | | | | |
| 0,085 | MDUS 0085-30C | | 1,0 | | | |
| 0,090 | MDUS 0090-30C | | | | | |
| 0,095 | MDUS 0095-30C | | | | | |
| **0,100** | MDUS 0100-30C | ❍ | | | | |
| 0,110 | MDUS 0110-30C | ❍ | 1,2 | | | 1 |
| 0,120 | MDUS 0120-30C | | | | | |
| 0,120 | MDUS 0130-30C | ❍ | 1,5 | | | |
| 0,140 | MDUS 0140-30C | | | | | |
| 0,150 | MDUS 0150-30C | | | | | |
| 0,160 | MDUS 0160-30C | ❍ | 1,8 | | | |
| 0,170 | MDUS 0170-30C | | | | | |
| 0,180 | MDUS 0180-30C | | | | | |
| 0,190 | MDUS 0190-30C | | 1,9 | | | |

## ●Diameter Ø 0,20–0,59 mm

| øD (mm) | Cat. No. | Stock | Dimensions ℓ1 | Dimensions ℓ2 | Fig. | Pcs./Packing |
|---|---|---|---|---|---|---|
| **0,20** | MDSS 0020 | ❍ | 2,5 | 28 | 2 | 1 |
| 0,21 | MDSS 0021 | ❍ | | | | |
| 0,22 | MDSS 0022 | ❍ | | | | |
| 0,23 | MDSS 0023 | ❍ | | | | |
| 0,24 | MDSS 0024 | ❍ | | | | |
| 0,25 | MDSS 0025 | ❍ | | | | |
| 0,26 | MDSS 0026 | ❍ | | | | |
| 0,27 | MDSS 0027 | ❍ | | | | |
| 0,28 | MDSS 0028 | ❍ | | | | |
| 0,29 | MDSS 0029 | ❒ | | | | |
| **0,30** | MDSS 0030 | ❍ | 3 | | | |
| 0,31 | MDSS 0031 | ❍ | | | | |
| 0,32 | MDSS 0032 | ❍ | | | | |
| 0,33 | MDSS 0033 | ❍ | | | | |
| 0,34 | MDSS 0034 | ❍ | | | | |
| 0,35 | MDSS 0035 | ❍ | 4 | | 3 | |
| 0,36 | MDSS 0036 | ❍ | | | | |
| 0,37 | MDSS 0037 | ❍ | | | | |
| 0,38 | MDSS 0038 | ❍ | | | | |
| 0,39 | MDSS 0039 | ❍ | | | | |
| **0,40** | MDSS 0040 | ❍ | 5 | | | |
| 0,41 | MDSS 0041 | ❍ | | | | |
| 0,42 | MDSS 0042 | ❍ | | | | |
| 0,43 | MDSS 0043 | ❍ | | | | |
| 0,44 | MDSS 0044 | ❍ | | | | |
| 0,45 | MDSS 0045 | ❍ | | | | |
| 0,46 | MDSS 0046 | ❍ | | | | |
| 0,47 | MDSS 0047 | ❍ | | | | |
| 0,48 | MDSS 0048 | ❍ | | | | |
| 0,49 | MDSS 0049 | ❍ | | | | |
| **0,50** | MDSS 0050 | ❍ | 6 | 27 | | |
| 0,51 | MDSS 0051 | ❍ | | | | |
| 0,52 | MDSS 0052 | ❍ | | | | |
| 0,53 | MDSS 0053 | ❍ | | | | |
| 0,54 | MDSS 0054 | ❍ | | | | |
| 0,55 | MDSS 0055 | ❍ | | | | |
| 0,56 | MDSS 0056 | ❍ | | | | |
| 0,57 | MDSS 0057 | ❍ | | | | |
| 0,58 | MDSS 0058 | ❍ | | | | |
| 0,59 | MDSS 0059 | ❍ | | | | |

## ●Diameter Ø 0,60–1,00 mm

| øD (mm) | Cat. No. | Stock | Dimensions ℓ1 | Dimensions ℓ2 | Fig. | Pcs./Packing |
|---|---|---|---|---|---|---|
| **0,60** | MDSS 0060 | ❍ | 7 | 26 | 3 | 1 |
| 0,61 | MDSS 0061 | ❍ | | | | |
| 0,62 | MDSS 0062 | ❍ | | | | |
| 0,63 | MDSS 0063 | ❍ | | | | |
| 0,64 | MDSS 0064 | ❍ | | | | |
| 0,65 | MDSS 0065 | ❍ | | | | |
| 0,66 | MDSS 0066 | ❍ | | | | |
| 0,67 | MDSS 0067 | ❍ | | | | |
| 0,68 | MDSS 0068 | ❍ | | | | |
| 0,69 | MDSS 0069 | ❍ | | | | |
| **0,70** | MDSS 0070 | ❍ | 9 | 24 | | |
| 0,71 | MDSS 0071 | ❍ | | | | |
| 0,72 | MDSS 0072 | ❍ | | | | |
| 0,73 | MDSS 0073 | ❍ | | | | |
| 0,74 | MDSS 0074 | ❒ | | | | |
| 0,75 | MDSS 0075 | ❍ | | | | |
| 0,76 | MDSS 0076 | ❍ | | | | |
| 0,77 | MDSS 0077 | ❍ | | | | |
| 0,78 | MDSS 0078 | ❍ | | | | |
| 0,79 | MDSS 0079 | ❍ | | | | |
| **0,80** | MDSS 0080 | ❍ | 10 | 23 | | |
| 0,81 | MDSS 0081 | ❍ | | | | |
| 0,82 | MDSS 0082 | ❍ | | | | |
| 0,83 | MDSS 0083 | ❍ | | | | |
| 0,84 | MDSS 0084 | ❍ | | | | |
| 0,85 | MDSS 0085 | ❍ | | | | |
| 0,86 | MDSS 0086 | ❍ | | | | |
| 0,87 | MDSS 0087 | ❍ | | | | |
| 0,88 | MDSS 0088 | ❍ | | | | |
| 0,89 | MDSS 0089 | ❍ | | | | |
| **0,90** | MDSS 0090 | ❍ | 11 | 22 | | |
| 0,91 | MDSS 0091 | ❍ | | | | |
| 0,92 | MDSS 0092 | ❍ | | | | |
| 0,93 | MDSS 0093 | ❍ | | | | |
| 0,94 | MDSS 0094 | ❍ | | | | |
| 0,95 | MDSS 0095 | ❍ | | | | |
| 0,96 | MDSS 0096 | ❍ | | | | |
| 0,97 | MDSS 0097 | ❍ | | | | |
| 0,98 | MDSS 0098 | ❍ | | | | |
| 0,99 | MDSS 0099 | ❍ | | | | |
| **1,00** | MDSS 0100 | ❍ | 12 | 21 | | |



## ■ MDSS Recommended Cutting Conditions (Wet)

| Work / Cond. / Drill-ø (mm) | Alloy Steel, Pre-hardened Steel: Spindle (rpm) | Feed rate (mm/min) | Step-feed (mm) | Die Steel, Tempered Steel ($H_RC$ 30–40): Spindle (rpm) | Feed rate (mm/min) | Step-feed (mm) | Stainless Steel: Spindle (rpm) | Feed rate (mm/min) | Step-feed (mm) |
|---|---|---|---|---|---|---|---|---|---|
| Ø 0,2 | 26500 | 50 | 0,1D | 21200 | 40 | 0,1D | 10600 | 20 | 0,1D |
| Ø 0,3 | 26500 | 80 | | 21200 | 60 | | 10600 | 30 | |
| Ø 0,4 | 25900 | 100 | | 19900 | 80 | | 9500 | 40 | |
| Ø 0,5 | 25500 | 150 | | 19100 | 110 | | 9500 | 50 | |
| Ø 1,0 | 15900 | 240 | 0,2D–0,5D※ | 12700 | 190 | 0,2D–0,5D※ | 5600 | 80 | |

1. The above conditions are recommended under wet conditions, using water-soluble coolant.
2. If machine noises and vibrations are present, please adjust the cutting conditions accordingly.
3. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.

※ Step feed is recommended for drilling of holes deeper than 3xD.



❍ = Japan stock
❑ = Delivery on request



# SUMIDIA Coated Drills
# SDC Type



## General Features

SUMIDIA Coated SDC type drills for Carbon Fibre Reinforced Plastic (CFRP) employ Sumitomo Electric Hardmetal's proprietary multi-step point angle.
Combined with a diamond coating, this technology improves the quality of machined surfaces and extends tool life.


## Characteristics and Applications

- Excellent drilled-hole quality
  - Sharp cutting edge shape reduces delamination of fibre layers and burrs.
  - Continuously changing point angle disperses load placed on cutting edge and prevents breakage.
- Long tool life
  - Use of high-strength diamond coating with excellent adhesion delivers high quality and long tool life.

## Performance

### Comparison of Machined Surface Finish


Excellent Machined Face Quality
(Prevents Delamination And Burrs)





| | |
|---|---|
| Tool: | SUMIDIA coated drill SDC type, Ø 6,375<br>Competitor A B C´s drill Ø 6,35 & Ø 6,5 |
| Work Material: | CFRP |
| Cutting Conditions: | n = 6.000 rpm, f=0,1 mm/rev, $a_p$ =28 mm (Through)<br>Dry |

### Tool Life Comparison

Effects of Diamond Coating

| SDC type (After drilling 600 holes) | Competitor's product (After drilling 50 holes) |
|---|---|
|  |  |
| No delamination<br>Low flank wear | More delamination<br>from cutting edge to flank |

Stable diamond layer adhesion prevents delamination.
Excellent wear resistance enables high-quality drilling with long tool life.




| | |
|---|---|
| Tool: | SUMIDIA coated drill SDC type, Ø 6,375<br>Competitor A B C´s drill Ø 6,35 & Ø 6,5 |
| Work Material: | CFRP |
| Cutting Conditions: | n = 6.000 rpm, f=0,1 mm/rev, $a_p$ =28 mm (Through)<br>Dry |

## Series


| Type | Diameter Range (mm) | Point angle | Hole Depth ($^{L}/_{D}$) |
|---|---|---|---|
| MDS□□□□□SDC3 | Ø 2,0 – 4,0 | 90° | –3 |
| | Ø 4,851 – 10,0 | 130° | |

DCX20 Grade | SUMI-DIA Coating


| Structual Steel | Carbon Steel | Alloy Steel | Pre-hardened Steel | Tempered Die Steel | Hardened Steel 45–55 HRC | Hardened Steel 55–60 HRC | Hardened Steel 60–65 HRC | Stainless Steel | Ti Alloy / Heat Resistant Alloy | Cast iron | Al Alloy | Cu Alloy | CFRP * |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | | | | | | | ○ | | ◎ |

* CFRP (Carbon Fibre Reinforced Plastic)

● Diameter Ø 2,0–4,0 mm




● Diameter Ø 4,851–10,0 mm




## ●Diameter ø 2,0–10,0 mm

(mm)

| Dimensions DC (mm) | Dimensions Ød (mm) | Cat. No. | 3D Type Stock | 3D Type Dimensions L | 3D Type Dimensions ℓ |
|---|---|---|---|---|---|
| **2,0** | 3,0 | MDS 02000SDC3 | ❍ | 49 | 12,5 |
| 2,489 | | 02489SDC3 | ❍ | | 15,0 |
| **3,0** | | 03000SDC3 | ❍ | | 17,5 |
| 3,3 | 3,3 | MDS 03300SDC3 | ❍ | 60 | 20,0 |
| **4,0** | 4,0 | 04000SDC3 | ❍ | | 22,5 |
| 4,851 | 4,851 | MDS 04851SDC3 | ❍ | 76 | 27,5 |
| **5,0** | 5,0 | 05000SDC3 | ❍ | | |
| **5,6** | 5,6 | MDS 05600SDC3 | ❍ | 81 | 30,0 |
| **6,0** | 6,0 | 06000SDC3 | ❍ | | |
| 6,375 | 6,375 | MDS 06375SDC3 | ❍ | 83 | 32,5 |
| **7,0** | 7,0 | 07000SDC3 | ❍ | | 35,0 |
| 7,938 | 7,938 | MDS 07938SDC3 | ❍ | 90 | 40,0 |
| **8,0** | 8,0 | 08000SDC3 | ❍ | | |
| **9,0** | 9,0 | MDS 09000SDC3 | ❍ | 98 | 45,0 |
| 9,550 | 9,550 | MDS 09550SDC3 | ❍ | 105 | 50,0 |
| **10,0** | 10,0 | 10000SDC3 | ❍ | | |

## Recommended Cutting Conditions

| ØD \ Work Cond. | | CFRP Only (Dry Machining) | Stacked Plates of CFRP, Aluminium Alloys (Dry Machining) |
|---|---|---|---|
| –Ø 6,0 | $v_c$ | 80–**120**–150 | 40–**60**–80 |
| | f | 0,05–**0,08**–0,10 | 0,05–**0,05**–0,10 |
| –Ø10,0 | $v_c$ | 80–**100**–120 | 40–**60**–80 |
| | f | 0,05–**0,08**–0,10 | 0,05–**0,05**–0,10 |

( $v_c$ : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max )

# SMD Type



## General Features

Fast accurate and ideal for drilling steels, this newly developed drill from SUMITOMO gives similar hole accuracy to that of regrindable drills renowned within the industry as being the ultimate hole making tool.

## Advantages

- Available in diameters ranging from 12,0–42,5 mm
- Drilling Depths 1,5–12 x Diameter
- Optimised heat dissipation via precisely located coolant holes
- Maximised rigidity from newly developed clamping system
- High performance drilling of precision holes from solid
- 3 different types of head for general and smooth cutting (MTL type, MEL type) and new MFS type for drilling in non-flat surfaces.


The newly developed tungsten carbide substrate with it's ultra hard smooth coating proved that against competition users can expect to see holes with tolerances similar to that of reaming and tool life almost doubled.




Edge security comes from replaceable drilling heads bolted to fixed radial serrations which provide a rigid and precise clamping platform.

Specially treated toughened steel body to resist wear and rust

Through coolant holes positioned to optimise coolant pressure and direction.




## Drilling Precision




Drill: Ø 18,0 mm
Work material: C50
Conditions: $v_c$ = 70 m/min, f = 0,25 mm/rev
$a_p$ = 38 mm (through), Water soluble

## Application Example





Work material: 34CrMo4 ($H_B$235–302)
Drill: Ø 18,0 mm
Conditions: $v_c$ = 70 m/min, f = 0,25 mm/rev
$a_p$ = 38 mm (through), Water soluble

# SMDH Type


● Holder 3D / 5D / 8D

Shank Type:
Whistle notch type





● Holder **1,5D**

Shank Type:
Weldon type




● Holder **12D**

Shank Type:
Cylindrical type




$\ell_2$ = Effective drilling length

## ■ Holder

(mm)

| Dimensions | | | | Cat. No. | Series (1,5D) | | | | Series (3D) | | | Series (5D) | | | Series (8D) | | | Series (12D) | | | | Related Drill Heads DMTL / DMEL |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Drill Head | | Shank | | | Stock | Dimensions | | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | | | |
| ø D | $\ell_1$ | ød | $\ell_3$ | | S | L | $\ell_2$ | ød2 | M3 | L | $\ell_2$ | M5 | L | $\ell_2$ | M8 | L | $\ell_2$ | 12D | L | $\ell_2$ | ød2 | |
| 12,0 | 2,2 | 16 | 48 | SMDH 120□□ | ● | 91 | 25,5 | 20 | ● | 107,2 | 43,5 | ● | 132,2 | 68,5 | | | | | | | | 1200–1249 |
| 12,5 | 2,3 | | | SMDH 125□□ | ● | 91 | 25,5 | 20 | ● | 107,3 | 43,5 | ● | 132,3 | 68,5 | | | | | | | | 1250–1299 |
| 13,0 | 2,4 | | | SMDH 130□□ | ● | 92 | 27,5 | 20 | ● | 112,4 | 46,5 | ● | 142,4 | 73,5 | | | | | | | | 1300–1349 |
| 14,0 | 2,5 | | | SMDH 140□□□ | ● | 96 | 31,5 | 20 | ● | 119,0 | 52,5 | ● | 149,0 | 81,5 | ● | 194,0 | 124,5 | ● | 238,5 | 168,5 | 20 | 1350–1450 |
| 15,0 | 2,7 | 20 | 50 | SMDH 150□□□ | ● | 100 | 32,0 | 25 | ● | 129,2 | 55,0 | ● | 159,2 | 86,0 | ● | 204,2 | 133,0 | ● | 253,0 | 180,0 | 25 | 1451–1550 |
| 16,0 | 2,9 | | | SMDH 160□□□ | ● | 103 | 35,0 | 25 | ● | 134,4 | 59,0 | ● | 169,4 | 92,0 | | 214,4 | 141,0 | ● | 265,5 | 192,0 | 25 | 1551–1650 |
| 17,0 | 3,1 | | | SMDH 170□□□ | ● | 105 | 35,5 | 25 | ● | 139,6 | 62,5 | ● | 174,6 | 97,5 | ● | 224,6 | 150,5 | ● | 278,1 | 203,5 | 25 | 1651–1750 |
| 18,0 | 3,3 | | | SMDH 180□□□ | ● | 107 | 39,7 | 25 | ● | 144,8 | 66,5 | ● | 179,8 | 103,5 | ● | 229,8 | 158,5 | ● | 290,5 | 215,5 | 25 | 1751–1850 |
| 19,0 | 3,5 | 25 | 56 | SMDH 190□□□ | | 115 | 40,5 | 30 | ● | 160,1 | 69,5 | ● | 195,0 | 108,5 | ● | 255,0 | 167,5 | ● | 309,1 | 228,5 | 30 | 1851–1950 |
| 20,0 | 3,6 | | | SMDH 200□□□ | ● | 118 | 43,0 | 30 | ● | 160,1 | 73,0 | ● | 200,1 | 114,0 | ● | 265,1 | 175,0 | ● | 321,4 | 240,0 | 30 | 1951–2050 |
| 21,0 | 3,8 | | | SMDH 210□□□ | ● | 119 | 44,0 | 30 | ● | 160,3 | 76,0 | ● | 200,3 | 119,0 | ● | 270,3 | 184,0 | ● | 333,9 | 252,0 | 30 | 2051–2150 |
| 22,0 | 4,0 | | | SMDH 220□□□ | ● | 121 | 47,0 | 30 | ● | 165,1 | 80,0 | ● | 205,1 | 125,0 | ● | 275,1 | 192,0 | ● | 347,0 | 264,0 | 30 | 2151–2280 |
| 23,0 | 4,2 | | | SMDH 230□□□ | ● | 122 | 46,5 | 30 | ● | 164,8 | 82,5 | ● | 214,8 | 129,5 | ● | 284,8 | 200,5 | ● | 359,0 | 275,5 | 30 | 2281–2380 |
| 24,0 | 4,4 | 32 | 60 | SMDH 240□□□ | ● | 129 | 49,5 | 37 | ● | 174,6 | 86,5 | ● | 224,6 | 135,5 | ● | 299,6 | 208,5 | ● | 376,1 | 284,5 | 37 | 2381–2480 |
| 25,0 | 4,6 | | | SMDH 250□□□ | ● | 129 | 49,0 | 37 | ● | 174,6 | 88,0 | ● | 229,6 | 140,0 | ● | 304,6 | 217,0 | ● | 388,4 | 300,0 | 37 | 2481–2580 |
| 26,0 | 4,7 | | | SMDH 260□□ | ● | 132 | 52,0 | 37 | ● | 179,7 | 92,0 | ● | 234,7 | 146,0 | ● | 314,7 | 225,0 | | | | | 2581–2680 |
| 27,0 | 4,9 | | | SMDH 270□□ | ● | 133 | 53,0 | 37 | ● | 179,9 | 94,0 | ● | 239,9 | 151,0 | ● | 324,9 | 234,0 | | | | | 2681–2780 |
| 28,0 | 5,1 | | | SMDH 280□□ | ● | 135 | 54,5 | 37 | ● | 185,1 | 96,5 | ● | 245,1 | 156,5 | ● | 330,1 | 241,5 | | | | | 2781–2880 |
| 29,0 | 5,3 | | | SMDH 290□□ | ● | 136 | 55,5 | 37 | ● | 190,3 | 99,5 | ● | 250,3 | 161,5 | ● | 340,3 | 250,5 | | | | | 2881–2980 |
| 30,0 | 5,5 | | | SMDH 300□□ | ● | 139 | 58,5 | 37 | ● | 190,5 | 104,5 | ● | 260,5 | 167,5 | ● | 350,5 | 259,5 | | | | | 2981–3050 |

Drill order description example: SMDH210M3, drill heads ➪ K59/H60



## ■ Recommended Torque

| Screw | | Applicable Insert |
|---|---|---|
|  | N·m | |
| BXD 02208 IP | 0,8–1,0 | SMDT 1200 – 1550 D M □L |
| BXD 02509 IP | 0,9–1,2 | SMDT 1551 – 1850 D M □L |
| BXD 03011 IP | 1,8–2,4 | SMDT 1851 – 2150 D M □L |
| BXD 03512 IP | 2,8–3,7 | SMDT 2151 – 2480 D M □L |
| BXD 04014 IP | 4,1–5,5 | SMDT 2481 – 2780 D M □L |
| BXD 04515 IP | 5,0–6,6 | SMDT 2781 – 3050 D M □L |

## ■ Spare Parts

| Screw | Wrench | Applicable Holder |
|---|---|---|
|  |  | |
| BXD 02208 IP | TRDR 08 IP | SMDT 120 – 150 M □ |
| BXD 02509 IP | TRDR 10 IP | SMDT 160 – 180 M □ |
| BXD 03011 IP | TRDR 15 IP | SMDT 190 – 210 M □ |
| BXD 03512 IP | TRDR 15 IP | SMDT 220 – 240 M □ |
| BXD 04014 IP | TRDR 20 IP | SMDT 250 – 270 M □ |
| BXD 04515 IP | TRDR 25 IP | SMDT 280 – 300 M □ |





● = Euro stock


N·m Recommended Tightening Torque (N·m)

# Regrindable Drill Head Insert
# SMDT... D MTL Type

PVD coated grade: **ACX70**

Type MTL








## Drill Head (Insert)

### ● Ø 12,0–15,3 mm

| DC (mm) | Cat. No. | Stock | PL | LF |
|---|---|---|---|---|
| 12,0 | SMDT 1200 D MTL | ● | 2,2 | 6,9 |
| 12,1 | 1210 D MTL | ● | 2,2 | |
| 12,2 | 1220 D MTL | ● | 2,2 | |
| 12,3 | 1230 D MTL | ● | 2,2 | |
| 12,4 | 1240 D MTL | ● | 2,3 | |
| 12,5 | SMDT 1250 D MTL | ● | 2,3 | 7,1 |
| 12,6 | 1260 D MTL | ● | 2,3 | |
| 12,7 | 1270 D MTL | ● | 2,3 | |
| 12,8 | 1280 D MTL | ● | 2,3 | |
| 12,9 | 1290 D MTL | ● | 2,3 | |
| 13,0 | SMDT 1300 D MTL | ● | 2,4 | 7,3 |
| 13,1 | 1310 D MTL | ● | 2,4 | |
| 13,2 | 1320 D MTL | ● | 2,4 | |
| 13,3 | 1330 D MTL | ● | 2,4 | |
| 13,4 | 1340 D MTL | ● | 2,4 | |
| 13,5 | SMDT 1350 D MTL | ● | 2,5 | 7,8 |
| 13,6 | 1360 D MTL | ● | 2,5 | |
| 13,7 | 1370 D MTL | ● | 2,5 | |
| 13,8 | 1380 D MTL | ● | 2,5 | |
| 13,9 | 1390 D MTL | ● | 2,5 | |
| 14,0 | 1400 D MTL | ● | 2,5 | |
| 14,1 | 1410 D MTL | ● | 2,6 | |
| 14,2 | 1420 D MTL | ● | 2,6 | |
| 14,3 | 1430 D MTL | ● | 2,6 | |
| 14,4 | 1440 D MTL | ● | 2,6 | |
| 14,5 | 1450 D MTL | ● | 2,6 | |
| 14,6 | SMDT 1460 D MTL | ● | 2,7 | 8,3 |
| 14,7 | 1470 D MTL | ● | 2,7 | |
| 14,8 | 1480 D MTL | ● | 2,7 | |
| 14,9 | 1490 D MTL | ● | 2,7 | |
| 15,0 | 1500 D MTL | ● | 2,7 | |
| 15,1 | 1510 D MTL | ● | 2,7 | |
| 15,2 | 1520 D MTL | ● | 2,8 | |
| 15,3 | 1530 D MTL | ● | 2,8 | |

### ● Ø 15,4–18,7 mm

| DC (mm) | Cat. No. | Stock | PL | LF |
|---|---|---|---|---|
| 15,4 | SMDT 1540 D MTL | ● | 2,8 | 8,3 |
| 15,5 | 1550 D MTL | ● | 2,8 | |
| 15,6 | SMDT 1560 D MTL | ● | 2,8 | 8,7 |
| 15,7 | 1570 D MTL | ● | 2,9 | |
| 15,8 | 1580 D MTL | ● | 2,9 | |
| 15,9 | 1590 D MTL | ● | 2,9 | |
| 16,0 | 1600 D MTL | ● | 2,9 | |
| 16,1 | 1610 D MTL | ● | 2,9 | |
| 16,2 | 1620 D MTL | ● | 2,9 | |
| 16,3 | 1630 D MTL | ● | 3,0 | |
| 16,4 | 1640 D MTL | ● | 3,0 | |
| 16,5 | 1650 D MTL | ● | 3,0 | |
| 16,6 | SMDT 1660 D MTL | ● | 3,0 | 9,2 |
| 16,7 | 1670 D MTL | ● | 3,0 | |
| 16,8 | 1680 D MTL | ● | 3,1 | |
| 16,9 | 1690 D MTL | ● | 3,1 | |
| 17,0 | 1700 D MTL | ● | 3,1 | |
| 17,1 | 1710 D MTL | ● | 3,1 | |
| 17,2 | 1720 D MTL | ● | 3,1 | |
| 17,3 | 1730 D MTL | ● | 3,1 | |
| 17,4 | 1740 D MTL | ● | 3,2 | |
| 17,5 | 1750 D MTL | ● | 3,2 | |
| 17,6 | SMDT 1760 D MTL | ● | 3,2 | 9,6 |
| 17,7 | 1770 D MTL | ● | 3,2 | |
| 17,8 | 1780 D MTL | ● | 3,2 | |
| 17,9 | 1790 D MTL | ● | 3,3 | |
| 18,0 | 1800 D MTL | ● | 3,3 | |
| 18,1 | 1810 D MTL | ● | 3,3 | |
| 18,2 | 1820 D MTL | ● | 3,3 | |
| 18,3 | 1830 D MTL | ● | 3,3 | |
| 18,4 | 1840 D MTL | | 3,3 | |
| 18,5 | 1850 D MTL | ● | 3,4 | |
| 18,6 | SMDT 1860 D MTL | ● | 3,4 | 10,1 |
| 18,7 | 1870 D MTL | ● | 3,4 | |

### ● Ø 18,8–30,5 mm

| DC (mm) | Cat. No. | Stock | PL | LF |
|---|---|---|---|---|
| 18,8 | SMDT 1880 D MTL | ● | 3,4 | 10,1 |
| 18,9 | 1890 D MTL | ● | 3,4 | |
| 19,0 | 1900 D MTL | ● | 3,5 | |
| 19,1 | 1910 D MTL | ● | 3,5 | |
| 19,2 | 1920 D MTL | ● | 3,5 | |
| 19,3 | 1930 D MTL | ● | 3,5 | |
| 19,4 | 1940 D MTL | ● | 3,5 | |
| 19,5 | 1950 D MTL | ● | 3,5 | |
| 19,6 | SMDT 1960 D MTL | ● | 3,6 | 10,5 |
| 19,7 | 1970 D MTL | ● | 3,6 | |
| 19,8 | 1980 D MTL | ● | 3,6 | |
| 19,9 | 1990 D MTL | ● | 3,6 | |
| 20,0 | 2000 D MTL | ● | 3,6 | |
| 20,5 | SMDT 2050 D MTL | ● | 3,7 | |
| 21,0 | SMDT 2100 D MTL | ● | 3,8 | 11,0 |
| 21,5 | 2150 D MTL | ● | 3,9 | |
| 22,0 | SMDT 2200 D MTL | ● | 4,0 | 11,0 |
| 22,5 | 2250 D MTL | ● | 4,1 | |
| 23,0 | SMDT 2300 D MTL | ● | 4,2 | 11,0 |
| 23,5 | 2350 D MTL | ● | 4,3 | |
| 24,0 | SMDT 2400 D MTL | | 4,4 | 11,0 |
| 24,5 | 2450 D MTL | ● | 4,5 | |
| 25,0 | SMDT 2500 D MTL | ● | 4,5 | 11,3 |
| 25,5 | 2550 D MTL | ● | 4,6 | |
| 26,0 | SMDT 2600 D MTL | ● | 4,7 | 11,7 |
| 26,5 | 2650 D MTL | ● | 4,8 | |
| 27,0 | SMDT 2700 D MTL | ● | 4,9 | 12,2 |
| 27,5 | 2750 D MTL | ● | 5,0 | |
| 28,0 | SMDT 2800 D MTL | ● | 5,1 | 12,6 |
| 28,5 | 2850 D MTL | ● | 5,2 | |
| 29,0 | SMDT 2900 D MTL | ● | 5,3 | 13,1 |
| 29,5 | 2950 D MTL | ● | 5,4 | |
| 30,0 | SMDT 3000 D MTL | ● | 5,5 | 13,5 |
| 30,5 | 3050 D MTL | ● | 5,6 | |

## Recommended Cutting Conditions

● For using **3 x D** and **5 x D** type drills

| Drill Ø (mm) \ Work material | | General steel (HB250–320) | Harden steel (HRC45) | Nodular cast iron |
|---|---|---|---|---|
| ~ 16,0 | $v_c$ | 70 – **100** – 120 | 40 – **60** – 90 | 50 – **60** – 80 |
| | f | 0,15 – **0,2** – 0,3 | 0,1 – **0,15** – 0,2 | 0,2 – **0,25** – 0,3 |
| ~ 20,0 | $v_c$ | 70 – **100** – 120 | 40 – **70** – 90 | 50 – **70** – 90 |
| | f | 0,15 – **0,25** – 0,35 | 0,15 – **0,2** – 0,25 | 0,2 – **0,25** – 0,35 |
| ~ 30,8 | $v_c$ | 70 – **100** – 120 | 40 – **60** – 90 | 50 – **70** – 90 |
| | f | 0,2 – **0,25** – 0,35 | 0,15 – **0,2** – 0,25 | 0,25 – **0,3** – 0,35 |

Note: High cutting performance is enhanced when using a high quality machine and rigid set up.

● For using **8 x D** and **12 x D** type drills

| Drill Ø (mm) \ Work material | | General steel (HB250–320) | Harden steel (HRC45) | Nodular cast iron |
|---|---|---|---|---|
| ~ 16,0 | $v_c$ | 50 – **70** – 80 | 30 – **50** – 70 | 40 – **50** – 70 |
| | f | 0,15 – **0,2** – 0,3 | 0,1 – **0,15** – 0,2 | 0,2 – **0,25** – 0,3 |
| ~ 20,0 | $v_c$ | 50 – **70** – 80 | 30 – **50** – 70 | 40 – **60** – 80 |
| | f | 0,15 – **0,25** – 0,35 | 0,15 – **0,2** – 0,25 | 0,2 – **0,25** – 0,35 |
| ~ 25,0 (12D) ~ 30,5 (8D) | $v_c$ | 50 – **70** – 80 | 30 – **50** – 70 | 40 – **60** – 80 |
| | f | 0,2 – **0,25** – 0,35 | 0,15 – **0,2** – 0,25 | 0,25 – **0,3** – 0,35 |

[ $v_c$ : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max ]

# SMDT... D MEL Type


MEL Type for Smooth Cutting

(Soft Steel, Stainless Steel, Grey Cast Iron)

PVD coated grade: **ACX80**

Type MEL








## Drill Head (Insert)

### ● Ø 12,0–15,3 mm

| DC (mm) | Cat. No. | Stock | PL | LF |
|---|---|---|---|---|
| 12,0 | SMDT 1200 D MEL | ● | 2,2 | |
| 12,1 | 1210 D MEL | ● | 2,2 | |
| 12,2 | 1220 D MEL | ● | 2,2 | 6,9 |
| 12,3 | 1230 D MEL | ● | 2,2 | |
| 12,4 | 1240 D MEL | ● | 2,3 | |
| 12,5 | SMDT 1250 D MEL | | 2,3 | |
| 12,6 | 1260 D MEL | ● | 2,3 | |
| 12,7 | 1270 D MEL | ● | 2,3 | 7,1 |
| 12,8 | 1280 D MEL | ● | 2,3 | |
| 12,9 | 1290 D MEL | ● | 2,3 | |
| 13,0 | SMDT 1300 D MEL | ● | 2,4 | |
| 13,1 | 1310 D MEL | ● | 2,4 | |
| 13,2 | 1320 D MEL | ● | 2,4 | 7,3 |
| 13,3 | 1330 D MEL | ● | 2,4 | |
| 13,4 | 1340 D MEL | ● | 2,4 | |
| 13,5 | SMDT 1350 D MEL | ● | 2,5 | |
| 13,6 | 1360 D MEL | ● | 2,5 | |
| 13,7 | 1370 D MEL | ● | 2,5 | |
| 13,8 | 1380 D MEL | ● | 2,5 | |
| 13,9 | 1390 D MEL | ● | 2,5 | |
| 14,0 | 1400 D MEL | ● | 2,5 | 7,8 |
| 14,1 | 1410 D MEL | ● | 2,6 | |
| 14,2 | 1420 D MEL | ● | 2,6 | |
| 14,3 | 1430 D MEL | ● | 2,6 | |
| 14,4 | 1440 D MEL | ● | 2,6 | |
| 14,5 | 1450 D MEL | ● | 2,6 | |
| 14,6 | SMDT 1460 D MEL | ● | 2,7 | |
| 14,7 | 1470 D MEL | ● | 2,7 | |
| 14,8 | 1480 D MEL | ● | 2,7 | |
| 14,9 | 1490 D MEL | ● | 2,7 | |
| 15,0 | 1500 D MEL | ● | 2,7 | 8,3 |
| 15,1 | 1510 D MEL | ● | 2,7 | |
| 15,2 | 1520 D MEL | ● | 2,8 | |
| 15,3 | 1530 D MEL | ● | 2,8 | |

### ● Ø 15,4–18,7 mm

| DC (mm) | Cat. No. | Stock | PL | LF |
|---|---|---|---|---|
| 15,4 | SMDT 1540 D MEL | ● | 2,8 | 8,3 |
| 15,5 | 1550 D MEL | ● | 2,8 | |
| 15,6 | SMDT 1560 D MEL | ● | 2,8 | |
| 15,7 | 1570 D MEL | ● | 2,9 | |
| 15,8 | 1580 D MEL | ● | 2,9 | |
| 15,9 | 1590 D MEL | ● | 2,9 | |
| 16,0 | 1600 D MEL | ● | 2,9 | 8,7 |
| 16,1 | 1610 D MEL | ● | 2,9 | |
| 16,2 | 1620 D MEL | ● | 2,9 | |
| 16,3 | 1630 D MEL | ● | 3,0 | |
| 16,4 | 1640 D MEL | ● | 3,0 | |
| 16,5 | 1650 D MEL | ● | 3,0 | |
| 16,6 | SMDT 1660 D MEL | ● | 3,0 | |
| 16,7 | 1670 D MEL | ● | 3,0 | |
| 16,8 | 1680 D MEL | ● | 3,1 | |
| 16,9 | 1690 D MEL | ● | 3,1 | |
| 17,0 | 1700 D MEL | ● | 3,1 | 9,2 |
| 17,1 | 1710 D MEL | ● | 3,1 | |
| 17,2 | 1720 D MEL | ● | 3,1 | |
| 17,3 | 1730 D MEL | ● | 3,1 | |
| 17,4 | 1740 D MEL | ● | 3,2 | |
| 17,5 | 1750 D MEL | ● | 3,2 | |
| 17,6 | SMDT 1760 D MEL | ● | 3,2 | |
| 17,7 | 1770 D MEL | ● | 3,2 | |
| 17,8 | 1780 D MEL | ● | 3,2 | |
| 17,9 | 1790 D MEL | ● | 3,3 | |
| 18,0 | 1800 D MEL | ● | 3,3 | 9,6 |
| 18,1 | 1810 D MEL | ● | 3,3 | |
| 18,2 | 1820 D MEL | ● | 3,3 | |
| 18,3 | 1830 D MEL | ● | 3,3 | |
| 18,4 | 1840 D MEL | ● | 3,3 | |
| 18,5 | 1850 D MEL | ● | 3,4 | |
| 18,6 | SMDT 1860 D MEL | ● | 3,4 | 10,1 |
| 18,7 | 1870 D MEL | ● | 3,4 | |

### ● Ø 18,8–30,5 mm

| DC (mm) | Cat. No. | Stock | PL | LF |
|---|---|---|---|---|
| 18,8 | SMDT 1880 D MEL | ● | 3,4 | |
| 18,9 | 1890 D MEL | ● | 3,4 | |
| 19,0 | 1900 D MEL | ● | 3,5 | |
| 19,1 | 1910 D MEL | ● | 3,5 | 10,1 |
| 19,2 | 1920 D MEL | ● | 3,5 | |
| 19,3 | 1930 D MEL | ● | 3,5 | |
| 19,4 | 1940 D MEL | ● | 3,5 | |
| 19,5 | 1950 D MEL | ● | 3,5 | |
| 19,6 | SMDT 1960 D MEL | ● | 3,6 | |
| 19,7 | 1970 D MEL | ● | 3,6 | |
| 19,8 | 1980 D MEL | ● | 3,6 | 10,5 |
| 19,9 | 1990 D MEL | ● | 3,6 | |
| 20,0 | 2000 D MEL | ● | 3,6 | |
| 20,5 | SMDT 2050 D MEL | ● | 3,7 | |
| 21,0 | SMDT 2100 D MEL | ● | 3,8 | 11,0 |
| 21,5 | 2150 D MEL | ● | 3,9 | |
| 22,0 | SMDT 2200 D MEL | ● | 4,0 | 11,0 |
| 22,5 | 2250 D MEL | ● | 4,1 | |
| 23,0 | SMDT 2300 D MEL | ● | 4,2 | 11,0 |
| 23,5 | 2350 D MEL | ● | 4,3 | |
| 24,0 | SMDT 2400 D MEL | ● | 4,4 | 11,0 |
| 24,5 | 2450 D MEL | ● | 4,5 | |
| 25,0 | SMDT 2500 D MEL | ● | 4,5 | 11,3 |
| 25,5 | 2550 D MEL | ● | 4,6 | |
| 26,0 | SMDT 2600 D MEL | ● | 4,7 | 11,7 |
| 26,5 | 2650 D MEL | ● | 4,8 | |
| 27,0 | SMDT 2700 D MEL | ● | 4,9 | 12,2 |
| 27,5 | 2750 D MEL | ● | 5,0 | |
| 28,0 | SMDT 2800 D MEL | ● | 5,1 | 12,6 |
| 28,5 | 2850 D MEL | ● | 5,2 | |
| 29,0 | SMDT 2900 D MEL | ● | 5,3 | 13,1 |
| 29,5 | 2950 D MEL | ● | 5,4 | |
| 30,0 | SMDT 3000 D MEL | ● | 5,5 | 13,5 |
| 30,5 | 3050 D MEL | ● | 5,6 | |

## Recommended Cutting Conditions

● For using **3 x D** and **5 x D** type drills

| Drill Ø (mm) \ Work material | | Soft steel (–HB250) | Stainless steel (–HB200) | Grey cast iron |
|---|---|---|---|---|
| ~ 16,0 | $v_c$ | 80 – **100** – 120 | 50 – **60** – 80 | 50 – **70** – 90 |
| | f | 0,15 – **0,2** – 0,35 | 0,1 – **0,15** – 0,2 | 0,2 – **0,25** – 0,3 |
| ~ 20,0 | $v_c$ | 80 – **100** – 120 | 60 – **70** – 90 | 60 – **80** – 100 |
| | f | 0,15 – **0,25** – 0,35 | 0,15 – **0,2** – 0,25 | 0,25 – **0,3** – 0,35 |
| ~ 30,8 | $v_c$ | 80 – **100** – 120 | 60 – **70** – 90 | 60 – **80** – 100 |
| | f | 0,2 – **0,3** – 0,35 | 0,15 – **0,2** – 0,25 | 0,2 – **0,35** – 0,40 |

Note: High cutting performance is enhanced when using a high quality machine and rigid set up.

● For using **8 x D** and **12 x D** type drills

| Drill Ø (mm) \ Work material | | Soft steel (–HB250) | Stainless steel (–HB200) | Grey cast iron |
|---|---|---|---|---|
| ~ 16,0 | $v_c$ | 50 – **70** – 80 | 40 – **50** – 60 | 40 – **60** – 80 |
| | f | 0,15 – **0,2** – 0,35 | 0,1 – **0,15** – 0,2 | 0,2 – **0,25** – 0,3 |
| ~ 20,0 | $v_c$ | 50 – **70** – 80 | 40 – **60** – 70 | 50 – **70** – 90 |
| | f | 0,15 – **0,25** – 0,35 | 0,15 – **0,2** – 0,25 | 0,25 – **0,3** – 0,35 |
| ~ 25,0 (12D) ~ 30,5 (8D) | $v_c$ | 60 – **70** – 80 | 40 – **60** – 70 | 50 – **70** – 90 |
| | f | 0,2 – **0,3** – 0,35 | 0,15 – **0,2** – 0,25 | 0,2 – **0,35** – 0,4 |

[ $v_c$ : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max ]

● = Euro stock

# SMDT... MEL Type




## Advantages

- Replaceable and regrindable drill head
- New design decreases cutting force by 25 %
- Ideal for stainless steels - soft steels etc
- Excellent tool life when drilling cast iron
- Improves drilling performance on low powered machines
- Increases productivity


## Performance (Stainless steel machinig)

### Comparison of cutting force




Work Material: X5CrNi1810 (1.4301)
Drill Diameter: Ø 16,5 x 5D
Conditions: $v_c$ = 60 m/min


### Chip comparison




Work Material: X5CrNi1810 (1.4301)
Drill Diameter: Ø 16,5 x 5D
Conditions: $v_c$ = 60 m/min, f = 0,15 mm/rev


## Performance (Cast iron machinig)

### Comparison of cutting force




Work Material: GGG45
Drill Diameter: Ø 18 x 5D
Conditions: $v_c$ = 80 m/min

### Comparison of wear resistance





Work Material: GG25
Drill Diameter: Ø 14 x 5D
Cutting Length: 34,7 m

Conditions: $v_c$ = 100 m/min
f = 0,2 mm/rev
Wet

## **MFS Type** Ideal for Drilling in Non-Flat Surfaces and Less Burr

DEX Coating




### Advantages


- **Various Drilling Operations Thanks to a Point Angle of 180°**

  Applicable to high-efficiency spot facing, drilling in non-flat surfaces such as inclined and cylindrical surfaces and interrupted drilling.
  Also reduces burrs st the hole exit.

- **Improves Machining Stability**

  Achieves high rigidity by employing RS Thinning, which ensures thick web at the bottom.

● Holder




No flat face for side lock clamping on the shank of 12D holders.

### Holder

| Dimensions | | | Cat. No. | Series (1,5D) | | | | Series (3D) | | | Series (5D) | | | Series (8D) | | | Series (12D) | | | | Related Drill Heads MFS |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Drill Head | Shank | | | Stock | Dimensions | | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | | Stock | Dimensions | | | |
| DC | DCON | LS | | S | OAL | LU | DCSFMS | M3 | OAL | LU | M5 | OAL | LU | M8 | OAL | LU | 12D | OAL | LU | DCSFMS | |
| 12,0 | 16 | 48 | SMDH 120□□ | ● | 91 | 25,5 | 20 | ● | 107,2 | 43,5 | ● | 132,2 | 68,5 | | | | | | | | 1200–1249 |
| 12,5 | | | SMDH 125□□ | ● | 91 | 25,5 | 20 | ● | 107,3 | 43,5 | ● | 132,3 | 68,5 | | | | | | | | 1250–1299 |
| 13,0 | | | SMDH 130□□ | ● | 92 | 27,5 | 20 | ● | 112,4 | 46,5 | ● | 142,4 | 73,5 | | | | | | | | 1300–1349 |
| 14,0 | | | SMDH 140□□□ | ● | 96 | 31,5 | 20 | ● | 119,0 | 52,5 | ● | 149,0 | 81,5 | ● | 194,0 | 124,5 | ● | 238,5 | 168,5 | 20 | 1350–1450 |
| 15,0 | 20 | 50 | SMDH 150□□□ | ● | 100 | 32,0 | 25 | ● | 129,2 | 55,0 | ● | 159,2 | 86,0 | ● | 204,2 | 133,0 | ● | 253,0 | 180,0 | 25 | 1451–1550 |
| 16,0 | | | SMDH 160□□□ | ● | 103 | 35,0 | 25 | ● | 134,4 | 59,0 | ● | 169,4 | 92,0 | | 214,4 | 141,0 | ● | 265,5 | 192,0 | 25 | 1551–1650 |
| 17,0 | | | SMDH 170□□□ | ● | 105 | 35,5 | 25 | ● | 139,6 | 62,5 | ● | 174,6 | 97,5 | ● | 224,6 | 150,5 | ● | 278,1 | 203,5 | 25 | 1651–1750 |
| 18,0 | | | SMDH 180□□□ | ● | 107 | 39,7 | 25 | ● | 144,8 | 66,5 | ● | 179,8 | 103,5 | ● | 229,8 | 158,5 | ● | 290,5 | 215,5 | 25 | 1751–1850 |
| 19,0 | 25 | 56 | SMDH 190□□□ | | 115 | 40,5 | 30 | ● | 160,1 | 69,5 | ● | 195,0 | 108,5 | ● | 255,0 | 167,5 | ● | 309,1 | 228,5 | 30 | 1851–1950 |
| 20,0 | | | SMDH 200□□□ | ● | 118 | 43,0 | 30 | ● | 160,1 | 73,0 | ● | 200,1 | 114,0 | ● | 265,1 | 175,0 | ● | 321,4 | 240,0 | 30 | 1951–2050 |
| 21,0 | | | SMDH 210□□□ | ● | 119 | 44,0 | 30 | ● | 160,3 | 76,0 | ● | 200,3 | 119,0 | ● | 270,3 | 184,0 | ● | 333,9 | 252,0 | 30 | 2051–2150 |
| 22,0 | | | SMDH 220□□□ | ● | 121 | 47,0 | 30 | ● | 165,1 | 80,0 | ● | 205,1 | 125,0 | ● | 275,1 | 192,0 | ● | 347,0 | 264,0 | 30 | 2151–2280 |
| 23,0 | | | SMDH 230□□□ | ● | 122 | 46,5 | 30 | ● | 164,8 | 82,5 | ● | 214,8 | 129,5 | ● | 284,8 | 200,5 | ● | 359,0 | 275,5 | 30 | 2281–2380 |
| 24,0 | 32 | 60 | SMDH 240□□□ | ● | 129 | 49,5 | 37 | ● | 174,6 | 86,5 | ● | 224,6 | 135,5 | ● | 299,6 | 208,5 | ● | 376,1 | 284,5 | 37 | 2381–2480 |
| 25,0 | | | SMDH 250□□□ | ● | 129 | 49,0 | 37 | ● | 174,6 | 88,0 | ● | 229,6 | 140,0 | ● | 304,6 | 217,0 | ● | 388,4 | 300,0 | 37 | 2481–2580 |
| 26,0 | | | SMDH 260□□ | ● | 132 | 52,0 | 37 | ● | 179,7 | 92,0 | ● | 234,7 | 146,0 | ● | 314,7 | 225,0 | | | | | 2581–2680 |
| 27,0 | | | SMDH 270□□ | ● | 133 | 53,0 | 37 | ● | 179,9 | 94,0 | ● | 239,9 | 151,0 | ● | 324,9 | 234,0 | | | | | 2681–2780 |
| 28,0 | | | SMDH 280□□ | ● | 135 | 54,5 | 37 | ● | 185,1 | 96,5 | ● | 245,1 | 156,5 | ● | 330,1 | 241,5 | | | | | 2781–2880 |
| 29,0 | | | SMDH 290□□ | ● | 136 | 55,5 | 37 | ● | 190,3 | 99,5 | ● | 250,3 | 161,5 | ● | 340,3 | 250,5 | | | | | 2881–2980 |
| 30,0 | | | SMDH 300□□ | ● | 139 | 58,5 | 37 | ● | 190,5 | 104,5 | ● | 260,5 | 167,5 | ● | 350,5 | 259,5 | | | | | 2981–3050 |

Drill order description example: SMDH210M3, drill heads ⇨ K63

### Recommended Torque

| Screw | | Applicable Insert |
|---|---|---|
|  | N·m | |
| BXD 02208 IP | 0,8–1,0 | SMDT 1200 – 1550 MFS |
| BXD 02509 IP | 0,9–1,2 | SMDT 1551 – 1850 MFS |
| BXD 03011 IP | 1,8–2,4 | SMDT 1851 – 2150 MFS |
| BXD 03512 IP | 2,8–3,7 | SMDT 2151 – 2480 MFS |
| BXD 04014 IP | 4,1–5,5 | SMDT 2481 – 2780 MFS |
| BXD 04515 IP | 5,0–6,6 | SMDT 2781 – 3050 MFS |

### Spare Parts

| Screw | Wrench | Applicable Holder |
|---|---|---|
|  |  | |
| BXD 02208 IP | TRDR 08 IP | SMDT 120 – 150 □□ |
| BXD 02509 IP | TRDR 10 IP | SMDT 160 – 180 □□ |
| BXD 03011 IP | TRDR 15 IP | SMDT 190 – 210 □□ |
| BXD 03512 IP | TRDR 15 IP | SMDT 220 – 240 □□ |
| BXD 04014 IP | TRDR 20 IP | SMDT 250 – 270 □□ |
| BXD 04515 IP | TRDR 25 IP | SMDT 280 – 300 □□ |




● = Euro stock

N·m Recommended Tightening Torque (N·m)

# Drill Head Insert
# SMDT... MFS Type

Type MFS






PVD coated grade: **ACX70**

## ■ Drill Head (Insert)




### ● ø 12,0 ~ 21,5 mm

| DC (mm) | Cat. No. | Stock | LF (mm) | Applicable Holders |
|---|---|---|---|---|
| 12,0 | SMDT 1200 MFS | ● | 7,1 | SMDH120 □□ |
| 12,5 | SMDT 1250 MFS | ● | 7,2 | SMDH125 □□ |
| 13,0 | SMDT 1300 MFS | ● | 7,5 | SMDH130 □□ |
| 13,5 | SMDT 1350 MFS | ● | 7,9 | SMDH140 □□ |
| 14,0 | SMDT 1400 MFS | ● | | |
| 14,5 | SMDT 1450 MFS | ● | | |
| 15,0 | SMDT 1500 MFS | ● | 8,3 | SMDH150 □□ |
| 15,5 | SMDT 1550 MFS | ● | | |
| 16,0 | SMDT 1600 MFS | ● | 8,8 | SMDH160 □□ |
| 16,5 | SMDT 1650 MFS | ● | | |
| 17,0 | SMDT 1700 MFS | ● | 9,3 | SMDH170 □□ |
| 17,5 | SMDT 1750 MFS | ● | | |
| 18,0 | SMDT 1800 MFS | ● | 9,8 | SMDH180 □□ |
| 18,5 | SMDT 1850 MFS | ● | | |
| 19,0 | SMDT 1900 MFS | ● | 10,2 | SMDH190 □□ |
| 19,5 | SMDT 1950 MFS | ● | | |
| 20,0 | SMDT 2000 MFS | ● | 10,7 | SMDH200 □□ |
| 20,5 | SMDT 2050 MFS | ● | | |
| 21,0 | SMDT 2100 MFS | ● | 11,2 | SMDH210 □□ |
| 21,5 | SMDT 2150 MFS | ● | | |

### ● ø 22,0 ~ 30,0 mm

| DC (mm) | Cat. No. | Stock | LF (mm) | Applicable Holders |
|---|---|---|---|---|
| 22,0 | SMDT 2200 MFS | ● | 11,2 | SMDH220 □□ |
| 22,5 | SMDT 2250 MFS | ● | | |
| 23,0 | SMDT 2300 MFS | ● | 11,2 | SMDH230 □□ |
| 23,5 | SMDT 2350 MFS | ● | | |
| 24,0 | SMDT 2400 MFS | ● | 11,3 | SMDH240 □□ |
| 24,5 | SMDT 2450 MFS | ● | | |
| 25,0 | SMDT 2500 MFS | ● | 11,7 | SMDH250 □□ |
| 25,5 | SMDT 2550 MFS | ● | | |
| 26,0 | SMDT 2600 MFS | ● | 12,2 | SMDH260 □□ |
| 26,5 | SMDT 2650 MFS | ● | | |
| 27,0 | SMDT 2700 MFS | ● | 12,7 | SMDH270 □□ |
| 27,5 | SMDT 2750 MFS | ● | | |
| 28,0 | SMDT 2800 MFS | ● | 13,2 | SMDH280 □□ |
| 28,5 | SMDT 2850 MFS | ● | | |
| 29,0 | SMDT 2900 MFS | ● | 13,6 | SMDH290 □□ |
| 29,5 | SMDT 2950 MFS | ● | | |
| 30,0 | SMDT 3000 MFS | ● | 14,1 | SMDH300 □□ |

## ■ MFS Type Head Important Notes

| | No Guide Hole (Solid Workpiece Hole Drilling) | With Guide Hole | Flat Finishing of Hole Bottom |
|---|---|---|---|
| Application |  Flat Surface Non-Flat Surface |  Guide Holes |  |
| 1,5D Holder | ○ | ○ (Guide Hole not required) | ○ |
| 3D–12D Holder | X | X | ○ |

## ■ Recommended Cutting Conditions

$v_c$: Cutting speed (m/min)
f: Feed rate (mm/rev)

| Work Material | | Soft Steel (<250 HB) | General Steel (250–320HB) | Hardened Steel (45HRC) | Stainless Steel (<200 HB) | Gray Cast Iron | Ductile Cast Iron | Aluminum Alloy (*) |
|---|---|---|---|---|---|---|---|---|
| Drill Diameter DC (mm) | Cutting Conditions | Min.-**Optimum**-Max. | Min.-**Optimum**-Max. | Min.-**Optimum**-Max. | Min.-**Optimum**-Max. | Min.-**Optimum**-Max. | Min.-**Optimum**-Max. | Min.-**Optimum**-Max. |
| –Ø 16,0 | $v_c$ | 60–**100**–120 | 70–**100**–120 | 40–**60**–90 | 50–**60**–80 | 50–**70**–90 | 50–**60**–80 | 200–**240**–260 |
| | f | 0,15–**0,20**–0,35 | 0,15–**0,20**–0,30 | 0,10–**0,15**–0,20 | 0,10–**0,15**–0,20 | 0,20–**0,25**–0,30 | 0,20–**0,25**–0,30 | 0,35–**0,45**–0,55 |
| –Ø 20,0 | $v_c$ | 80–**100**–120 | 70–**100**–120 | 40–**60**–90 | 60–**70**–90 | 60–**80**–100 | 50–**70**–90 | 200–**240**–260 |
| | f | 0,15–**0,25**–0,35 | 0,15–**0,25**–0,35 | 0,15–**0,20**–0,25 | 0,15–**0,20**–0,25 | 0,20–**0,30**–0,35 | 0,20–**0,25**–0,35 | 0,35–**0,50**–0,60 |
| –Ø 30,8 | $v_c$ | 80–**100**–120 | 70–**100**–120 | 40–**60**–90 | 60–**70**–90 | 60–**80**–100 | 50–**70**–90 | 200–**240**–260 |
| | f | 0,20–**0,30**–0,35 | 0,20–**0,25**–0,35 | 0,15–**0,20**–0,25 | 0,15–**0,20**–0,25 | 0,20–**0,30**–0,40 | 0,25–**0,30**–0,35 | 0,35–**0,50**–0,60 |

Note: The recommended hole depth is 2 x DC. The depth is measured from the highest point of the hole when drilling on inclined surfaces. The recommended cutting conditions above are for drilling on flat horizontal surfaces.
Adjust the feed rate according to the inclination angle when drilling on an inclined surface. Set the feed rate at 70 % ot lower when inclination angle is 30° or less. Set the feed rate at 50 % or lower when the inclination angle is larger than 30°. This product is a drilling tool. Do not use it for traverse or helical milling.

(*) Inquire about drills specifically for aluminum alloy.

# SMD Type

## Large Hole MTL Type


## For Large Holes



Tool edge design ideal for malleable material used for large casings, etc.
Edge design suitable for malleable material commonly used for large hole drilling.




Improved chip management
for highly malleable materials
**Large Helix Angle Design**




## Machined Surface Accuracy

Work Material: St 52-3 (Base substrate for construction use)
Drill Size: Ø 33,0 mm x 5D
Cutting Conditions: $v_c$ = 120 m/min, f = 0,25 mm/rev
Cutting Environment: Emulsion Type


### High drilling accuracy with large diameters




## Cutting Force Comparison (Thrust)

Work Material: St 42-2 (Laminated plates)
Drill Size: Ø 37,5 mm x 5D
Cutting Conditions: $v_c$ = 90 m/min, f = 0,35 mm/rev
Cutting Environment: Emulsion Type

### Stable even when machining laminated plates




## Recommended Cutting Conditions

$v_C$=Cutting Speed (m/min) f=Feed Rate (mm/rev)

| Work Material | | Soft Steel (–250 HB) | General Steel (250–320 HB) | Hardened Steel (45 HRC) | Stainless Steel (–200 HB) | Grey Cast Iron | Ductil Cast Iron |
|---|---|---|---|---|---|---|---|
| Recommended Head | | **MTL** Type | **MTL** Type | **MTL** Type | **MTL** Type | **MTL** Type | **MTL** Type |
| Drill Ø (mm) | Cutt. Conditions | | | | | | |
| –36,5 | $v_c$ | **60–120** (40–80) | **60–120** (40–80) | **40–80** (30–60) | **40–80** (30–60) | **50–100** (40–90) | **50–90** (40–70) |
| | f | 0,25–0,4 | 0,2–0,35 | 0,15– 0,3 | 0,15–0,25 | 0,25–0,45 | 0,25–0,35 |
| –42,5 | $v_c$ | **60–120** (40–80) | **60–120** (40–80) | **40–80** (30–60) | **40–80** (30–60) | **50–100** (40–90) | **50–90** (40–70) |
| | f | 0,25–0,4 | 0,2–0,35 | 0,15–0,3 | 0,15–0,25 | 0,25–0,45 | 0,25–0,35 |

Note: Where machining and work clamp rigidity are good, conditions may be increased up to the maximum.
For 8D drills, please use feed rates stated within the ( ). Before drilling 8D holes, a guide hole of similar diameter must be made.






○ = Japan stock
❑ = Delivery on request


Recommended Tightening Torque (N·m)

# Regrindable Drill Head Insert
# SMDT... MTL Type

● Indexable Head MTL Type




● Toolholder





## ■ Drill Head (Ø 31,0–42,5 mm), Grade MTL Type - ACX80

## ■ Holders M (3D), L (5D), D (8D)

| Drill Diameter ØD | Heads | | | Toolholder | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| | MTL Type | | h1 | M (3D) | | L (5D) | | D (8D) | |
| | Cat. No. | Stock | | Cat. No. | Stock | Cat. No. | Stock | Cat. No. | Stock |
| **31,0** | **SMDT 3100 MTL** | ❒ | | | | | | | |
| 31,5 | **SMDT 3150 MTL** | ❒ | 15,2 | **SMDH 320 M** | ❍ | **SMDH 320 L** | ❍ | **SMDH 320 D** | ❍ |
| **32,0** | **SMDT 3200 MTL** | ❍ | | | | | | | |
| 32,5 | **SMDT 3250 MTL** | ❒ | | | | | | | |
| **33,0** | **SMDT 3300 MTL** | ❍ | 15,2 | **SMDH 335 M** | ❍ | **SMDH 335 L** | ❍ | **SMDH 335 D** | ❍ |
| 33,5 | **SMDT 3350 MTL** | ❒ | | | | | | | |
| **34,0** | **SMDT 3400 MTL** | ❍ | | | | | | | |
| 34,5 | **SMDT 3450 MTL** | ❒ | 16,6 | **SMDH 350 M** | ❍ | **SMDH 350 L** | ❍ | **SMDH 350 D** | ❍ |
| **35,0** | **SMDT 3500 MTL** | ❍ | | | | | | | |
| 35,5 | **SMDT 3550 MTL** | ❒ | | | | | | | |
| **36,0** | **SMDT 3600 MTL** | ❍ | 16,4 | **SMDH 365 M** | ❍ | **SMDH 365 L** | ❍ | **SMDH 365 D** | ❍ |
| 36,5 | **SMDT 3650 MTL** | ❒ | | | | | | | |
| **37,0** | **SMDT 3700 MTL** | ❍ | | | | | | | |
| 37,5 | **SMDT 3750 MTL** | ❍ | 18,1 | **SMDH 380 M** | ❍ | **SMDH 380 L** | ❍ | **SMDH 380 D** | ❍ |
| **38,0** | **SMDT 3800 MTL** | ❍ | | | | | | | |
| 38,5 | **SMDT 3850 MTL** | ❒ | | | | | | | |
| **39,0** | **SMDT 3900 MTL** | ❍ | 17,8 | **SMDH 395 M** | ❍ | **SMDH 395 L** | ❍ | **SMDH 395 D** | ❍ |
| 39,5 | **SMDT 3950 MTL** | ❒ | | | | | | | |
| **40,0** | **SMDT 4000 MTL** | ❍ | | | | | | | |
| 40,5 | **SMDT 4050 MTL** | ❍ | 19,5 | **SMDH 410 M** | ❍ | **SMDH 410 L** | ❍ | **SMDH 410 D** | ❍ |
| **41,0** | **SMDT 4100 MTL** | ❍ | | | | | | | |
| 41,5 | **SMDT 4150 MTL** | ❒ | | | | | | | |
| **42,0** | **SMDT 4200 MTL** | ❍ | 19,3 | **SMDH 425 M** | ❍ | **SMDH 425 L** | ❍ | **SMDH 425 D** | ❍ |
| 42,5 | **SMDT 4250 MTL** | ❒ | | | | | | | |

● Mounted Figure




Only use the special MTL Type head with a M, L or D type holder

| Dimensions (mm) | | M (3D) | | L (5D) | | D (8D) | | Shank | | Cap Screw | Wrench | N·m |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Drill Head | | Dimensions (mm) | | Dimensions (mm) | | Dimensions (mm) | | Dimensions (mm) | |  |  | |
| øD | $\ell_1$ | $\ell_2$ | L | $\ell_2$ | L | $\ell_2$ | L | $\ell_3$ | ød | | | |
| **31,0** | | | | | | | | | | | | |
| 31,5 | 5,7 | 97,9 | 200,7 | 163 | 265,7 | 257,9 | 360,7 | 60 | 32,0 | BXD04515IP | TRDR25IP | 5–6,6 |
| **32,0** | | | | | | | | | | | | |
| 32,5 | | | | | | | | | | | | |
| **33,0** | 6,0 | 103,3 | 206,0 | 171,5 | 276,0 | 273,3 | 376,0 | 60 | 32,0 | | | |
| 33,5 | | | | | | | | | | | | |
| **34,0** | | | | | | | | | | | | |
| 34,5 | 6,3 | 106,8 | 221,3 | 182 | 296,3 | 287 | 401,3 | 70 | 40,0 | | | |
| **35,0** | | | | | | | | | | | | |
| 35,5 | | | | | | | | | | | | |
| **36,0** | 6,6 | 112,3 | 226,6 | 187,5 | 301,6 | 297,3 | 411,6 | 70 | 40,0 | | | |
| 36,5 | | | | | | | | | | | | |
| **37,0** | | | | | | | | | | | | |
| 37,5 | 6,8 | 115,8 | 231,8 | 195,8 | 311,8 | 310,8 | 426,8 | 70 | 40,0 | | | |
| **38,0** | | | | | | | | | | | | |
| 38,5 | | | | | | | | | | | | |
| **39,0** | 7,1 | 121,3 | 237,1 | 206,3 | 322,1 | 321,3 | 437,1 | 70 | 40,0 | BX0515 | HD040 | 7,2 |
| 39,5 | | | | | | | | | | | | |
| **40,0** | | | | | | | | | | | | |
| 40,5 | 7,4 | 129,8 | 252,4 | 209,8 | 332,4 | 334,8 | 457,4 | 70 | 40,0 | | | |
| **41,0** | | | | | | | | | | | | |
| 41,5 | | | | | | | | | | | | |
| **42,0** | 7,6 | 135,3 | 257,6 | 220,3 | 342,6 | 345,3 | 467,6 | 70 | 40,0 | | | |
| 42,5 | | | | | | | | | | | | |

# WDX Type



## General Features

The SumiDrill WDX type has excellent cutting balance that provides stable hole drilling on a wide range of work materials from general steel to stainless steel and aluminium alloy.
Available in four original chipbreaker styles, the inserts feature improved chip control and reduced cutting force for use in low rigidity contexts.

## Series Configuration

| Depth of Machined Hole | Holder Diameter (mm) |
|---|---|
| 2D | Ø 13,0 – Ø 68,0 |
| 3D | Ø 13,0 – Ø 68,0 |
| 4D | Ø 13,0 – Ø 63,0 |
| 5D | Ø 13,0 – Ø 55,0 |

## Features and Applications

### Design

Cutting force during drilling is balanced between central insert and peripheral insert. The relative position of each insert is optimised to provide stable drilling.

### Excellent Chip Control

The chip evacuation direction can be controlled with the chip control groove at the centre of the breaker, enabling good chip control.

### Versatile Tool for a Variety of Machining Applications


Select among four types of breakers for different applications, allowing optimal drilling for a variety of work materials and conditions. Suitable for a wide range of applications including hole expansion, spot facing, external turning and internal boring.


### Economical Four-Cornered Insert




Inserts can be used in either central or peropheral positions with two corners for each position - a total of four corners.

Design

Cutting force of central insert = that periphal insert





| Type | L | G | | H | M New |
|---|---|---|---|---|---|
| Features | For low feed with chip control | General Purpose | For non-ferrous metal drilling | Strong edge type | **For stainless steel drilling** |
| Appearance |  |  |  |  |  |
| Figure |  |  |  |  |  |

## Performance


Balanced Design
(Comparison of Horizontal Component Values)

Balance is maintained at the strong hole entry and exit points and drilling is stable.

**SumiDrill WDX Type**




Conventional and Competitor's Products




Improved Chip Control

Work Material: X5CrNiS18 10
Holder: WDX 200D3S25 (Ø 20,0)
Cutting Data: $v_c$ = 130 m/min, f = 0,06 mm/rev, H = 50 mm, wet

**SumiDrill WDX Type**




Conventional and Competitor's Products



## Multi-Purpose Functionality


Applications for Machining Centre




Recommended conditions - reduce feed rate to 70 %

## Chipbreaker **M** Type / **ACM300** New
**For Machining of Stainless Steel**




### Features
Chip control by the newly developed M chip breaker for stainless steel machining achieves stable hole quality.

| Holder | **WDX** **M** Type | **WDX** **G** Type | Competitor's Product |
|---|---|---|---|
| Hole |  |  |  |
| Chips |  |  |  |

Work Material: X2CrNiMo17 13 2
Holder: WDX200D3S25
Insert: WDXT063006 M (ACM300)
Cutting Data: $v_c$ = 150 m/min, f = 0,08 mm/rev, H = 60 mm, wet

## ACP100
**For High-speed Drilling of Steel and Cast Iron**

### Features
Provides excellent wear resistance and high reliability thanks to our coating stress control technology and the ultra-fine crystal grain coating film of the Super FF Coat achieved through our proprietary technology.

| | | **ACP100** | Competitor's Product |
|---|---|---|---|
| Peripheral Insert | Rake Face |  |  |
| | Flank |  |  |
| Central Insert | Rake Face |  |  |
| | Flank |  |  |

Work Material: C50
Holder: WDX250D3S25
Insert: WDXT063006 G (ACP100)
Cutting Data: $v_c$ = 200 m/min, f = 0,12 mm/rev, H = 50 mm through hole, wet

## Drills for Deep Hole Drilling L/D = 5


### Features
The SumiDrill WDX type for 5xD drilling features a specially designed flute shape and enlarged coolant hole for excellent chip evacuation even during hole drilling.

Large coolant hole







Coolant supply guidehole

Special flute shape for L/D = 5



### Performance

| Characteristics | Figure | Cutting Resistance | Machined Surface (Exit) |
|---|---|---|---|
| **WDX260D5S32** **L/D = 5** Flutedesign<br>Designed with emphasis on chip evacuation<br>Expanded flute design improves chip evacuation for stable drilling performance even with holes up to 5xD. |  |  | Produces an excellent surface finish - full hole depth<br> |
| Comparison Tool<br>Flutedesign L/D = 4<br>Designed with emphasis on drill rigidity<br>Flute design for greater rigidity of the drill enables stable drilling of deep holes up to 4xD. |  |  | Poor machined surface due to chip blockage at bottom of hole (near 5xD)<br> |

Insert: WDXT073506-G Work Material: X5CrNiS18 10
Cutting Data: $v_c$ = 150 m/min, f = 0,05 mm/rev, H = 130 mm, through hole, wet


# WDX Type

## Insert Selection Guide – The WDX Insert Series has a Variety of Options

### 5 Grades

| | ACP100 | ACP300 | ACM300 | ACK300 | DL1500 |
|---|---|---|---|---|---|
| P High-speed Drilling | ○ | | | | |
| P General Drilling | | ○ | | | |
| M Stainless Steel | | ○ | ○ | | |
| K High-speed Drilling | ○ | | | | |
| K General Drilling | | | | ○ | |
| N Non-ferrous Metal | | | | | ○ |

### 4 Types of Chipbreakers




### 11 Combinations

| ACP100 | ACP300 | ACM300 | ACK300 | DL1500 |
|---|---|---|---|---|
| PK L | P L | | PK L | |
| PK G | PM G | | PK G | N G |
| PK H | P H | | K H | |
| | | M M | | |

---

**2nd Recommendation** — P

**P — For low feed with chip control**

**L ACP300**

For drilling of St 42-3, 15,CrMo5, 20CrMo5, etc.

High speed and low feed is recommended if there are issues with chip control.

Decrease the feed if vibration occurs due to burnt chips.

**P — General Purpose**

**G ACP100**

For drilling of general steel and alloy steel, when prone to significantly large flank wear.

**P — For low feed with chip control**

**L ACP100**

For low-feed conditions.

**P — Strong Edge Type**

**H ACP300**

For drilling with interruptions (entry/through) due to slanted entry, reduce the feed rate in the interrupted area (around f = 0,05).

For insufficient cutting edge strength due to drilling of hardened steel (heat treated).

**P** Improved chip control (low carbon steel, etc.)

**P** Insufficient wear resistance

**P** Initial chipping measures (interruption, high hardness, etc.)

---

**1st Recommendation** — P M K N

**General Purpose — G**

For general steel and alloy steel drilling
**P ACP300**

For cast iron drilling
**K ACK300**

For non-ferrous metal drilling
**N DL1500**

For stainless steel drilling
**M ACM300**

Dedicated for stainless steel — **M**

**K** insufficient wear resistance (high-speed machining)

**K** Initial chipping measures (interruption, high feed, etc.)

**M** Lack of chip evacuation (extension)

---

**2nd Recommendation** — K M

**K — General Purpose**

**G ACP100**

When heavy flank wear occurs in cast iron drilling.

To limit wear in high-speed, low to medium feed conditions.

**K — Strong Edge Type**

**H ACK300**

When interrupted drilling is performed due to slanted entry, etc. as with steel drilling.

For machining of St44-2, 18CrMo4, 20CrMo4


**M — General Purpose**

**G ACP300**

When chips extend and clog.


ACP100 is the first recommendation for steel with a hardness of 200HB or greater or for high-speed drilling of steel.

## Application Examples





Work Material: Machine component (GGG-40.3)
Holder: WDX205D3S25
Insert: WDXT063006 G (ACK300)
Cutting Data: $v_c$ = 122 m/min, f = 0,15 mm/rev, H = 33 mm, through, wet

Significant increase in tool life; twice that conventional tools.
Stable cutting with minimal cutting force.





Work Material: Plate (C15)
Holder: WDX430D3S40
Insert: WDXT125012 H (ACP300)
Cutting Data: $v_c$ = 136 m/min, f = 0,15 mm/rev, H = 60+50 mm (semicircle area), through, wet

Enables drilling even in unstable conditions (interrupted cutting at deepest point)
Quieter cutting than conventional tools.





Work Material: Machine component (42CrMo4)
Holder: WDX200D3S25
Insert: WDXT063006 G (ACP300)
Cutting Data: $v_c$ = 157 m/min, f = 0,19 mm/rev, H = 19 mm, through, wet
Competitor B: $v_c$ = 157 m/min, f = 0,15 mm/rev, H = 19 mm, through, wet

Good chip control even in high-efficiency conditions. Good stability with low vibration during cutting. 25% greater efficiency and 20% longer tool life.





Work Material: Piping parts (X5CrNiS18 10)
Holder: WDX210D3S25
Insert: WDXT063006 M (ACM300)
Cutting Data: $v_c$ = 105 m/min, f = 0,08 mm/rev, H = 34 mm, wet

Improved chip control and better stable machining.





Work Material: Plate (C48)
Holder: WDX600D3S40
Insert: WDXT186012 G (ACP300)
Cutting Data: $v_c$ = 150 m/min, f = 0,16 mm/rev, H = 60 mm, through, wet
Competitor D: $v_c$ = 30 m/min, f = 0,20 mm/rev, H = 60 mm, through, wet

Achieves steady machining even at large diameters.
Achieves 4 times the efficiency of conventional tools.





Work Material: Machine component (15CrMo5)
Holder: WDX200D5S25
Insert: WDXT063006 G (ACP300)
Cutting Data: $v_c$ = 185 m/min, f = 0,12 mm/rev, H = 87mm, through, wet

Good machined surface.
Consistent bore diameter.




Work Material: Tractor links (35MnBM)
Holder: WDX205D5S25
Insert: WDXT063006 G (ACP300)
Cutting Data: $v_c$ = 100 m/min, f = 0,11 mm/rev, H = 60 mm, through, wet

Achieves steady machining even at L/D = 5.
Reduces insert chipping and wear for stable tool life.




Work Material: Bearing for wind power generator (equivalent to 42CrMo4)
Holder: WDX330D5S40
Insert: WDXT094008 L (ACP300)
Cutting Data: $v_c$ = 146 m/min, f = 0,10 mm/rev, H = 158 mm, through, wet

Eliminates defects in workpieces caused by insert chipping.

# WDX Type (2D)

## Max. Depth: 2D

Machining tolerances -0.05 to +0.15 mm

Fig. 1





Fig. 2






Fig. 3




## Holder Diameter Ø 13,0 mm – Ø 45,0 mm

| DC | Stock | Cat. No. | LUX | LPR | OAL | LS | DCSFMS | DCON | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 13,0 | ● | WDX 130D2S20 | 29 | 44 | 88 | | | | 1 |
| 13,5 | ● | 135D2S20 | 30 | 45 | 89 | | | | 1 |
| 14,0 | ● | 140D2S20 | 31 | 46 | 90 | 44 | 28,0 | 20 | 1 |
| 14,5 | ● | 145D2S20 | 32 | 47 | 91 | | | | 1 |
| 15,0 | ● | 150D2S20 | 33 | 48 | 92 | | | | 1 |
| 15,5 | ● | WDX 155D2S20 | 34 | 49 | 93 | | | | 1 |
| 16,0 | ● | 160D2S20 | 35 | 50 | 94 | 44 | 30,0 | 20 | 1 |
| 16,5 | ● | 165D2S20 | 36 | 51 | 95 | | | | 1 |
| 17,0 | ● | 170D2S20 | 37 | 52 | 96 | | | | 1 |
| 17,5 | ● | WDX 175D2S25 | 38 | 53 | 109 | 56 | 32,0 | 25 | 1 |
| 18,0 | ● | 180D2S25 | 39 | 54 | 110 | | | | 1 |
| 18,5 | ● | WDX 185D2S25 | 40 | 55 | 111 | | | | 1 |
| 19,0 | ● | 190D2S25 | 41 | 56 | 112 | | | | 1 |
| 19,5 | ● | 195D2S25 | 42 | 57 | 113 | | | | 1 |
| 20,0 | ● | 200D2S25 | 43 | 58 | 114 | | | | 1 |
| 20,5 | ● | 205D2S25 | 44 | 59 | 115 | 56 | 33,0 | 25 | 1 |
| 21,0 | ● | 210D2S25 | 45 | 60 | 116 | | | | 1 |
| 21,5 | ● | 215D2S25 | 46 | 61 | 117 | | | | 1 |
| 22,0 | ● | 220D2S25 | 47 | 62 | 118 | | | | 1 |
| 22,5 | ● | 225D2S25 | 48 | 63 | 119 | | | | 1 |
| 23,0 | ● | WDX 230D2S25 | 49 | 67 | 123 | | | | 1 |
| 23,5 | ● | 235D2S25 | 50 | 68 | 124 | | | | 1 |
| 24,0 | ● | 240D2S25 | 51 | 69 | 125 | 56 | 37,0 | 25 | 1 |
| 24,5 | ● | 245D2S25 | 52 | 70 | 126 | | | | 1 |
| 25,0 | ● | 250D2S25 | 53 | 71 | 127 | | | | 1 |
| 25,5 | ● | WDX 255D2S32 | 54 | 74 | 134 | | | | 2 |
| 26,0 | ● | 260D2S32 | 55 | 75 | 135 | | | | 2 |
| 26,5 | ● | 265D2S32 | 56 | 76 | 136 | | | | 2 |
| 27,0 | ● | 270D2S32 | 57 | 77 | 137 | 60 | 41,0 | 32 | 2 |
| 27,5 | ● | 275D2S32 | 58 | 78 | 138 | | | | 2 |
| 28,0 | ● | 280D2S32 | 59 | 79 | 139 | | | | 2 |
| 28,5 | ● | 285D2S32 | 60 | 80 | 140 | | | | 2 |
| 29,0 | ● | WDX 290D2S32 | 62 | 83 | 143 | | 50,0 | | 2 |
| 29,5 | ● | 295D2S32 | 63 | 84 | 144 | | | | 2 |
| 30,0* | ❍ | 300D2S32 | 64 | 88 | 148 | 60 | | 32 | 2 |
| 31,0* | | 310D2S32 | 66 | 90 | 150 | | 54,0 | | 2 |
| 32,0* | ❍ | 320D2S32 | 68 | 92 | 152 | | | | 2 |
| 30,0* | ● | WDX 300D2S40 | 64 | 88 | 158 | | | | 2 |
| 31,0* | ● | 310D2S40 | 66 | 90 | 160 | | | | 2 |
| 32,0* | ● | 320D2S40 | 68 | 92 | 162 | | | | 2 |
| 33,0 | ● | 330D2S40 | 70 | 94 | 164 | 70 | 54,0 | 40 | 2 |
| 34,0 | ● | 340D2S40 | 72 | 96 | 166 | | | | 2 |
| 35,0 | ● | 350D2S40 | 74 | 98 | 168 | | | | 2 |
| 36,0 | ● | 360D2S40 | 76 | 100 | 170 | | | | 2 |
| 37,0 | ● | WDX 370D2S40 | 79 | 109 | 179 | | | | 2 |
| 38,0 | ● | 380D2S40 | 81 | 111 | 181 | | | | 2 |
| 39,0 | ● | 390D2S40 | 83 | 113 | 183 | | | | 2 |
| 40,0 | ● | 400D2S40 | 85 | 115 | 185 | | | | 2 |
| 41,0 | ● | 410D2S40 | 87 | 117 | 187 | 70 | 49,5 | 40 | 2 |
| 42,0 | ● | 420D2S40 | 89 | 119 | 189 | | | | 2 |
| 43,0 | ● | 430D2S40 | 91 | 121 | 191 | | | | 2 |
| 44,0 | ● | 440D2S40 | 93 | 123 | 193 | | | | 2 |
| 45,0 | ● | 450D2S40 | 95 | 125 | 195 | | | | 2 |

* Diameter Ø 30, Ø 31, Ø 32 are in stock with shank diameters of Ø 32 and Ø 40.

## Holder Diameter Ø 46,0 mm – Ø 68,0 mm

| DC | Stock | Cat. No. | LUX | LPR | OAL | LS | DCSFMS | DCON | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 46,0 | ● | WDX 460D2S40 | 97 | 127 | 197 | | | | 2 |
| 47,0 | ● | 470D2S40 | 99 | 129 | 199 | | | | 2 |
| 48,0 | ● | 480D2S40 | 101 | 131 | 201 | | 49,5 | | 2 |
| 49,0 | ● | 490D2S40 | 103 | 133 | 203 | | | | 2 |
| 50,0 | ● | 500D2S40 | 105 | 135 | 205 | 70 | | 40 | 2 |
| 51,0 | ● | 510D2S40 | 107 | 137 | 207 | | | | 3 |
| 52,0 | ● | 520D2S40 | 109 | 139 | 209 | | 50,5 | | 3 |
| 53,0 | ● | 530D2S40 | 111 | 141 | 211 | | 51,5 | | 3 |
| 54,0 | ● | 540D2S40 | 113 | 143 | 213 | | 52,5 | | 3 |
| 55,0 | ● | 550D2S40 | 115 | 145 | 215 | | 53,5 | | 3 |
| 56,0 | ❍ | WDX 560D2S40 | 120 | 152 | 222 | | 54,0 | | 3 |
| 57,0 | ❍ | 570D2S40 | 122 | 154 | 224 | | 55,0 | | 3 |
| 58,0 | ❍ | 580D2S40 | 124 | 156 | 226 | | 56,0 | | 3 |
| 59,0 | ❍ | 590D2S40 | 126 | 158 | 228 | | 57,0 | | 3 |
| 60,0 | ❍ | 600D2S40 | 128 | 160 | 230 | | 58,0 | | 3 |
| 61,0 | ❍ | 610D2S40 | 130 | 162 | 232 | | 59,0 | | 3 |
| 62,0 | ❍ | 620D2S40 | 132 | 164 | 234 | 70 | 60,0 | 40 | 3 |
| 63,0 | ❍ | 630D2S40 | 134 | 166 | 236 | | 61,0 | | 3 |
| 64,0 | ❍ | 640D2S40 | 136 | 168 | 238 | | 62,0 | | 3 |
| 65,0 | ❍ | 650D2S40 | 138 | 170 | 240 | | 63,0 | | 3 |
| 66,0 | ❍ | 660D2S40 | 140 | 172 | 242 | | 64,0 | | 3 |
| 67,0 | ❍ | 670D2S40 | 142 | 174 | 244 | | 65,0 | | 3 |
| 68,0 | ❍ | 680D2S40 | 144 | 176 | 246 | | 66,0 | | 3 |

## Parts

| Applicable Holder | Flat Screw | N·m | Wrench | Wrench |
|---|---|---|---|---|
| WDX130D2S20–WDX150D2S20 | BFTX01604N | **0,3** | TRX06 | – |
| WDX155D2S20–WDX180D2S25 | BFTX0204N | **0,5** | TRX06 | – |
| WDX185D2S25–WDX225D2S25 | BFTY02206 | **1,0** | – | TRD07 |
| WDX230D2S25–WDX285D2S32 | BFTX02506N | **1,5** | – | TRD08 |
| WDX290D2S32–WDX360D2S40 | BFTX03584 | **3,5** | – | TRD15 |
| WDX370D2S40–WDX450D2S40 | BFTX0511N | **5,0** | – | TRD20 |
| WDX460D2S40–WDX680D2S40 | BFTX0615N | **5,0** | – | TRD25 |

## Identification Details - Holder

**WDX 200 D2 S25**

- 200: Diameter DC (Ø 20,0 mm)
- D2: Flute Length L/D (2D)
- S25: Shank Diameter DCON (Ø 25,0 mm)

## Identification Details - Inserts

**WDXT 06 30 06 -G**

- 06: Width across Flats (6,0 mm)
- 30: Thickness (3,0 mm)
- 06: Nose Radius (0,6 mm)
- -G: Breaker Type





● = Euro stock
○ = Japan stock


N·m Recommended Tightening Torque (N·m)

## Inserts

| Application | Coated Carbide | | | | |
|---|---|---|---|---|---|
| High-Speed / Light | PK | | | | N |
| General Purpose | | P | M | | |
| Roughing | | P | | K | |


| Cat. No. | ACP100 | ACP300 | ACM300 | ACK300 | DL1500 | Fig | W1 | S | RE1 | RE2 | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WDXT 042004 L | ❍ | ● | | ● | | 1 | 4,2 | 2,0 | 0,4 | 0,4 | WDX130D2S20 – WDX150D2S20 |
| 042004 G | ● | ● | | ● | ● | 2 | | | | | |
| 042004 H | ● | ● | | ● | | 3 | | | | | |
| 042004 M | | | ● | | | 4 | | | | 0,8 | |
| WDXT 052504 L | ❍ | ● | | ● | | 1 | 5,0 | 2,5 | 0,4 | 0,4 | WDX155D2S20 – WDX180D2S25 |
| 052504 G | ● | ● | | ● | ● | 2 | | | | | |
| 052504 H | ● | ● | | ● | | 3 | | | | | |
| 052504 M | | | ● | | | 4 | | | | 1,0 | |
| WDXT 063006 L | ● | ● | | ● | | 1 | 6,0 | 3,0 | 0,6 | 0,6 | WDX185D2S25 – WDX225D2S25 |
| 063006 G | ● | ● | | ● | ● | 2 | | | | | |
| 063006 H | ● | ● | | ● | | 3 | | | | | |
| 063006 M | | | ● | | | 4 | | | | 1,4 | |
| WDXT 073506 L | ● | ● | | ● | | 1 | 7,5 | 3,5 | 0,6 | 0,6 | WDX230D2S25 – WDX285D2S32 |
| 073506 G | ● | ● | | ● | ● | 2 | | | | | |
| 073506 H | ● | ● | | ● | | 3 | | | | | |
| 073506 M | | | ● | | | 4 | | | | 1,6 | |
| WDXT 094008 L | ● | ● | | ● | | 1 | 9,6 | 4,0 | 0,8 | 0,8 | WDX290D2S32 – WDX360D2S40 |
| 094008 G | ● | ● | | ● | ● | 2 | | | | | |
| 094008 H | ● | ● | | ● | | 3 | | | | | |
| 094008 M | | | ● | | | 4 | | | | 2,4 | |
| WDXT 125012 L | ● | ● | | ● | | 1 | 12,4 | 5,0 | 1,2 | 1,2 | WDX370D2S40 – WDX450D2S40 |
| 125012 G | ● | ● | | ● | ● | 2 | | | | | |
| 125012 H | ● | ● | | ● | | 3 | | | | | |
| 125012 M | | | ● | | | 4 | | | | 3,2 | |
| WDXT 156012 L | ● | ● | | ● | | 1 | 15,2 | 6,0 | 1,2 | 1,2 | WDX460D2S40 – WDX550D2S40 |
| 156012 G | ● | ● | | ● | ● | 2 | | | | | |
| 156012 H | ● | ● | | ● | | 3 | | | | | |
| WD-XT 186012 L | ● | ❍ | | ❍ | | 1 | 18,0 | 6,0 | 1,2 | 1,2 | WDX560D2S40 – WDX680D2S40 |
| 186012 G | ● | ● | | ● | | 2 | | | | | |
| 186012 H | ❍ | ❍ | | ❍ | | 3 | | | | | |

Fig. 1





For low feed with chip control

Fig. 2





General purpose

Fig. 3




Strong edge

Fig. 4




For stainless steel

## Recommended Cutting Conditions (2D)

(min. - **optimal** - max.)

| ISO | Material Group / Work material | | | Hardness (HB) | Chipbreaker | Grade | Cutting Speed (m/min) | Feed rate (mm/rev) Ø 13,0–Ø 18,0 | Ø 18,5–Ø 29,0 | Ø 29,5– Ø 36,0 | Ø 37,0–Ø 55,0 | Ø 56,0–Ø 68,0 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| P | Carbon steel | St 42-3 | | 125 | G | ACP300 | 120–**180**–240 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,12 | 0,06–**0,09**–0,13 |
| | | C15 | | 125 | L | ACP300 | 130–**170**–220 | 0,04–**0,08**–0,12 | 0,04–**0,08**–0,12 | 0,04–**0,08**–0,13 | 0,05–**0,10**–0,15 | 0,06–**0,11**–0,17 |
| | | C45 | | 190 | G | ACP300 | 100–**150**–200 | 0,08–**0,13**–0,24 | 0,08–**0,13**–0,24 | 0,08–**0,14**–0,26 | 0,09–**0,16**–0,29 | 0,10–**0,17**–0,32 |
| | | C45 | Hardened | 250 | G | ACP100 | 100–**170**–240 | 0,05–**0,09**–0,14 | 0,05–**0,09**–0,14 | 0,05–**0,09**–0,14 | 0,05–**0,10**–0,17 | 0,06–**0,11**–0,18 |
| | | C75 | | 270 | G | ACP100 | 120–**180**–240 | 0,06–**0,10**–0,17 | 0,06–**0,10**–0,17 | 0,06–**0,10**–0,17 | 0,07–**0,12**–0,19 | 0,08–**0,13**–0,21 |
| | | C75 | Hardened | 300 | G | ACP100 | 80–**150**–210 | 0,05–**0,09**–0,14 | 0,05–**0,09**–0,14 | 0,05–**0,09**–0,14 | 0,05–**0,10**–0,15 | 0,06–**0,11**–0,17 |
| | Low alloyed steel | Cr-Mo, Ni-Cr-Mo | | 180 | L | ACP300 | 100–**140**–180 | 0,05–**0,08**–0,14 | 0,05–**0,08**–0,14 | 0,05–**0,08**–0,16 | 0,06–**0,09**–0,17 | 0,07–**0,10**–0,19 |
| | Low alloyed steel | Cr-Mo, Ni-Cr-Mo | Hardened | 275 | G | ACP100 | 100–**170**–240 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,07–**0,11**–0,16 | 0,08–**0,11**–0,17 |
| | | | | 300 | G | ACP100 | 90–**150**–210 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,07–**0,11**–0,16 | 0,08–**0,11**–0,17 |
| | | | | 350 | G | ACP100 | 75–**120**–165 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,07–**0,11**–0,16 | 0,08–**0,11**–0,17 |
| | High alloyed steel | | Sintered | 200 | G | ACP100 | 120–**180**–240 | 0,08–**0,12**–0,17 | 0,08–**0,12**–0,17 | 0,08–**0,12**–0,18 | 0,09–**0,12**–0,21 | 0,10–**0,13**–0,22 |
| | | | | 325 | G | ACP100 | 100–**140**–180 | 0,06–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,15 | 0,07–**0,11**–0,16 | 0,08–**0,11**–0,17 |
| M | Stainless steel | Martensitic/Ferritic | | 200 | M | ACM300 | 120–**150**–180 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,07–**0,10**–0,16 | 0,08–**0,12**–0,16 |
| | | Martensitic/Hardened | | 240 | M | ACM300 | 90–**120**–150 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,07–**0,10**–0,16 | 0,08–**0,12**–0,16 |
| | | Austenitic | | 180 | M | ACM300 | 120–**150**–180 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,07–**0,10**–0,16 | 0,08–**0,12**–0,16 |
| K | Cast iron | | | | H | ACK300 | 120–**160**–200 | 0,09–**0,20**–0,32 | 0,10–**0,22**–0,36 | 0,11–**0,24**–0,39 | 0,12–**0,26**–0,44 | 0,13–**0,29**–0,48 |
| | Ductile Cast iron | | | | H | ACK300 | 90–**120**–150 | 0,09–**0,20**–0,32 | 0,10–**0,22**–0,36 | 0,11–**0,24**–0,39 | 0,12–**0,26**–0,44 | 0,13–**0,29**–0,48 |
| S | Exotic Alloy (Heat resistant alloy, Super Alloy, etc) | | | 200 | G | ACP300 | 25–**50**–70 | 0,06–**0,11**–0,18 | 0,06–**0,11**–0,18 | 0,06–**0,12**–0,19 | 0,07–**0,13**–0,22 | 0,08–**0,14**–0,24 |
| N | Aluminium Alloy | | | | G | DL1500 | 200–**260**–320 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 | 0,08–**0,14**–0,22 |
| | Copper Alloy | | | | G | DL1500 | 180–**230**–280 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 | 0,08–**0,14**–0,22 |

*For the P and K grades for which ACP300 and ACK300 are the first recommendation, ACP100 inserts are the second recommendation.
The recommended cutting conditions are a cutting speed $v_c$ of 130% of the above table and a feed rate f of 75%.

# WDX Type (3D)

## Max. Depth: 3D

Machining tolerances 0 to +0.20 mm

Fig. 1





Fig. 2






Fig. 3




## Holder Diameter Ø 13,0 mm – Ø 45,0 mm

| DC | Stock | Cat. No. | LUX | LPR | OAL | LS | DCSFMS | DCON | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 13,0 | ● | WDX 130D3S20 | 42,0 | 57,0 | 101,0 | | | | 1 |
| 13,5 | ● | 135D3S20 | 43,5 | 58,5 | 102,5 | | | | 1 |
| 14,0 | ● | 140D3S20 | 45,0 | 60,0 | 104,0 | 44 | 28,0 | 20 | 1 |
| 14,5 | ● | 145D3S20 | 46,5 | 61,5 | 105,5 | | | | 1 |
| 15,0 | ● | 150D3S20 | 48,0 | 63,0 | 107,0 | | | | 1 |
| 15,5 | ● | WDX 155D3S20 | 49,5 | 64,5 | 108,5 | | | | 1 |
| 16,0 | ● | 160D3S20 | 51,0 | 66,0 | 110,0 | 44 | 30,0 | 20 | 1 |
| 16,5 | ● | 165D3S20 | 52,5 | 67,5 | 111,5 | | | | 1 |
| 17,0 | ● | 170D3S20 | 54,0 | 69,0 | 113,0 | | | | 1 |
| 17,5 | ● | WDX 175D3S25 | 55,5 | 70,5 | 126,5 | 56 | 32,0 | 25 | 1 |
| 18,0 | ● | 180D3S25 | 57,0 | 72,0 | 128,0 | | | | 1 |
| 18,5 | ● | WDX 185D3S25 | 58,5 | 73,5 | 129,5 | | | | 1 |
| 19,0 | ● | 190D3S25 | 60,0 | 75,0 | 131,0 | | | | 1 |
| 19,5 | ● | 195D3S25 | 61,5 | 76,5 | 132,5 | | | | 1 |
| 20,0 | ● | 200D3S25 | 63,0 | 78,0 | 134,0 | | | | 1 |
| 20,5 | ● | 205D3S25 | 64,5 | 79,5 | 135,5 | 56 | 33,0 | 25 | 1 |
| 21,0 | ● | 210D3S25 | 66,0 | 81,0 | 137,0 | | | | 1 |
| 21,5 | ● | 215D3S25 | 67,5 | 82,5 | 138,5 | | | | 1 |
| 22,0 | ● | 220D3S25 | 69,0 | 84,0 | 140,0 | | | | 1 |
| 22,5 | ● | 225D3S25 | 70,5 | 85,5 | 141,5 | | | | 1 |
| 23,0 | ● | WDX 230D3S25 | 72,0 | 90,0 | 146,0 | | | | 1 |
| 23,5 | ● | 235D3S25 | 73,5 | 91,5 | 147,5 | | | | 1 |
| 24,0 | ● | 240D3S25 | 75,0 | 93,0 | 149,0 | 56 | 37,0 | 25 | 1 |
| 24,5 | ● | 245D3S25 | 76,5 | 94,5 | 150,5 | | | | 1 |
| 25,0 | ● | 250D3S25 | 78,0 | 96,0 | 152,0 | | | | 1 |
| 25,5 | ● | WDX 255D3S32 | 79,5 | 99,5 | 159,5 | | | | 2 |
| 26,0 | ● | 260D3S32 | 81,0 | 101,0 | 161,0 | | | | 2 |
| 26,5 | ● | 265D3S32 | 82,5 | 102,5 | 162,5 | | | | 2 |
| 27,0 | ● | 270D3S32 | 84,0 | 104,0 | 164,0 | 60 | 41,0 | 32 | 2 |
| 27,5 | ● | 275D3S32 | 85,5 | 105,5 | 165,5 | | | | 2 |
| 28,0 | ● | 280D3S32 | 87,0 | 107,0 | 167,0 | | | | 2 |
| 28,5 | ● | 285D3S32 | 88,5 | 108,5 | 168,5 | | | | 2 |
| 29,0 | ● | WDX 290D3S32 | 91,0 | 112,0 | 172,0 | | 50,0 | | 2 |
| 29,5 | ● | 295D3S32 | 92,5 | 113,5 | 173,5 | | | | 2 |
| 30,0* | ❍ | 300D3S32 | 94,0 | 118,0 | 178,0 | 60 | | 32 | 2 |
| 31,0* | | 310D3S32 | 97,0 | 121,0 | 181,0 | | 54,0 | | 2 |
| 32,0* | ❍ | 320D3S32 | 100,0 | 124,0 | 184,0 | | | | 2 |
| 30,0* | ● | WDX 300D3S40 | 94,0 | 118,0 | 188,0 | | | | 2 |
| 31,0* | ● | 310D3S40 | 97,0 | 121,0 | 191,0 | | | | 2 |
| 32,0* | ● | 320D3S40 | 100,0 | 124,0 | 194,0 | | | | 2 |
| 33,0 | ● | 330D3S40 | 103,0 | 127,0 | 197,0 | 70 | 54,0 | 40 | 2 |
| 34,0 | ● | 340D3S40 | 106,0 | 130,0 | 200,0 | | | | 2 |
| 35,0 | ● | 350D3S40 | 109,0 | 133,0 | 203,0 | | | | 2 |
| 36,0 | ● | 360D3S40 | 112,0 | 136,0 | 206,0 | | | | 2 |
| 37,0 | ● | WDX 370D3S40 | 116,0 | 146,0 | 216,0 | | | | 2 |
| 38,0 | ● | 380D3S40 | 119,0 | 149,0 | 219,0 | | | | 2 |
| 39,0 | ● | 390D3S40 | 122,0 | 152,0 | 222,0 | | | | 2 |
| 40,0 | ● | 400D3S40 | 125,0 | 155,0 | 225,0 | | | | 2 |
| 41,0 | ● | 410D3S40 | 128,0 | 158,0 | 228,0 | 70 | 49,5 | 40 | 2 |
| 42,0 | ● | 420D3S40 | 131,0 | 161,0 | 231,0 | | | | 2 |
| 43,0 | ● | 430D3S40 | 134,0 | 164,0 | 234,0 | | | | 2 |
| 44,0 | ● | 440D3S40 | 137,0 | 167,0 | 237,0 | | | | 2 |
| 45,0 | ● | 450D3S40 | 140,0 | 170,0 | 240,0 | | | | 2 |

* Diameter Ø 30, Ø 31, Ø 32 are in stock with shank diameters of Ø 32 and Ø 40.

## Holder Diameter Ø 46,0 mm – Ø 68,0 mm

| DC | Stock | Cat. No. | LUX | LPR | OAL | LS | DCSFMS | DCON | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 46,0 | ● | WDX 460D3S40 | 143,0 | 173,0 | 243,0 | | | | 2 |
| 47,0 | ● | 470D3S40 | 146,0 | 176,0 | 246,0 | | | | 2 |
| 48,0 | ● | 480D3S40 | 149,0 | 179,0 | 249,0 | | | | 2 |
| 49,0 | ● | 490D3S40 | 152,0 | 182,0 | 252,0 | | 49,5 | | 2 |
| 50,0 | ● | 500D3S40 | 155,0 | 185,0 | 255,0 | 70 | | 40 | 2 |
| 51,0 | ● | 510D3S40 | 158,0 | 188,0 | 258,0 | | | | 3 |
| 52,0 | ● | 520D3S40 | 161,0 | 191,0 | 261,0 | | 50,5 | | 3 |
| 53,0 | ● | 530D3S40 | 164,0 | 194,0 | 264,0 | | 51,5 | | 3 |
| 54,0 | ● | 540D3S40 | 167,0 | 197,0 | 267,0 | | 52,5 | | 3 |
| 55,0 | ● | 550D3S40 | 170,0 | 200,0 | 270,0 | | 53,5 | | 3 |
| 56,0 | ❍ | WDX 560D3S40 | 176,0 | 208,0 | 278,0 | | 54,0 | | 3 |
| 57,0 | ❍ | 570D3S40 | 179,0 | 211,0 | 281,0 | | 55,0 | | 3 |
| 58,0 | ❍ | 580D3S40 | 182,0 | 214,0 | 284,0 | | 56,0 | | 3 |
| 59,0 | ❍ | 590D3S40 | 185,0 | 217,0 | 287,0 | | 57,0 | | 3 |
| 60,0 | ❍ | 600D3S40 | 188,0 | 220,0 | 290,0 | | 58,0 | | 3 |
| 61,0 | ❍ | 610D3S40 | 191,0 | 223,0 | 293,0 | | 59,0 | | 3 |
| 62,0 | ❍ | 620D3S40 | 194,0 | 226,0 | 296,0 | 70 | 60,0 | 40 | 3 |
| 63,0 | ❍ | 630D3S40 | 197,0 | 229,0 | 299,0 | | 61,0 | | 3 |
| 64,0 | ❍ | 640D3S40 | 200,0 | 232,0 | 302,0 | | 62,0 | | 3 |
| 65,0 | ❍ | 650D3S40 | 203,0 | 235,0 | 305,0 | | 63,0 | | 3 |
| 66,0 | ❍ | 660D3S40 | 206,0 | 238,0 | 308,0 | | 64,0 | | 3 |
| 67,0 | ❍ | 670D3S40 | 209,0 | 241,0 | 311,0 | | 65,0 | | 3 |
| 68,0 | ❍ | 680D3S40 | 212,0 | 244,0 | 314,0 | | 66,0 | | 3 |

## Parts

| Applicable Holder | Flat Screw | N·m | Wrench | Wrench |
|---|---|---|---|---|
| WDX130D3S20–WDX150D3S20 | BFTX01604N | **0,3** | TRX06 | – |
| WDX155D3S20–WDX180D3S25 | BFTX0204N | **0,5** | TRX06 | – |
| WDX185D3S25–WDX225D3S25 | BFTY02206 | **1,0** | – | TRD07 |
| WDX230D3S25–WDX285D3S32 | BFTX02506N | **1,5** | – | TRD08 |
| WDX290D3S32–WDX360D3S40 | BFTX03584 | **3,5** | – | TRD15 |
| WDX370D3S40–WDX450D3S40 | BFTX0511N | **5,0** | – | TRD20 |
| WDX460D3S40–WDX680D3S40 | BFTX0615N | **5,0** | – | TRD25 |

## Identification Details - Holder

**WDX 200 D3 S25**

- 200: Diameter DC (Ø 20,0 mm)
- D3: Flute Length L/D (3D)
- S25: Shank Diameter DCON (Ø 25,0 mm)

## Identification Details - Inserts

**WDXT 06 30 06 -G**

- 06: Width across Flats (6,0 mm)
- 30: Thickness (3,0 mm)
- 06: Nose Radius (0,6 mm)
- -G: Breaker Type





● = Euro stock
○ = Japan stock


N·m Recommended Tightening Torque (N·m)

## Inserts

| Application | Coated Carbide | | | | |
|---|---|---|---|---|---|
| High-Speed / Light | PK | | | | N |
| General Purpose | | P | M | | |
| Roughing | | P | | K | |


| Cat. No. | ACP100 | ACP300 | ACM300 | ACK300 | DL1500 | Fig | W1 | S | RE1 | RE2 | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WDXT 042004 L | ❍ | ● | | ● | | 1 | 4,2 | 2,0 | 0,4 | 0,4 | WDX130D3S20 – WDX150D3S20 |
| 042004 G | ● | ● | | ● | ● | 2 | | | | | |
| 042004 H | ● | ● | | ● | | 3 | | | | | |
| 042004 M | | | ● | | | 4 | | | | 0,8 | |
| WDXT 052504 L | ❍ | ● | | ● | | 1 | 5,0 | 2,5 | 0,4 | 0,4 | WDX155D3S20 – WDX180D3S25 |
| 052504 G | ● | ● | | ● | ● | 2 | | | | | |
| 052504 H | ● | ● | | ● | | 3 | | | | | |
| 052504 M | | | ● | | | 4 | | | | 1,0 | |
| WDXT 063006 L | ● | ● | | ● | | 1 | 6,0 | 3,0 | 0,6 | 0,6 | WDX185D3S25 – WDX225D3S25 |
| 063006 G | ● | ● | | ● | ● | 2 | | | | | |
| 063006 H | ● | ● | | ● | | 3 | | | | | |
| 063006 M | | | ● | | | 4 | | | | 1,4 | |
| WDXT 073506 L | ● | ● | | ● | | 1 | 7,5 | 3,5 | 0,6 | 0,6 | WDX230D3S25 – WDX285D3S32 |
| 073506 G | ● | ● | | ● | ● | 2 | | | | | |
| 073506 H | ● | ● | | ● | | 3 | | | | | |
| 073506 M | | | ● | | | 4 | | | | 1,6 | |
| WDXT 094008 L | ● | ● | | ● | | 1 | 9,6 | 4,0 | 0,8 | 0,8 | WDX290D3S32 – WDX360D3S40 |
| 094008 G | ● | ● | | ● | ● | 2 | | | | | |
| 094008 H | ● | ● | | ● | | 3 | | | | | |
| 094008 M | | | ● | | | 4 | | | | 2,4 | |
| WDXT 125012 L | ● | ● | | ● | | 1 | 12,4 | 5,0 | 1,2 | 1,2 | WDX370D3S40 – WDX450D3S40 |
| 125012 G | ● | ● | | ● | ● | 2 | | | | | |
| 125012 H | ● | ● | | ● | | 3 | | | | | |
| 125012 M | | | ● | | | 4 | | | | 3,2 | |
| WDXT 156012 L | ● | ● | | ● | | 1 | 15,2 | 6,0 | 1,2 | 1,2 | WDX460D3S40 – WDX550D3S40 |
| 156012 G | ● | ● | | ● | ● | 2 | | | | | |
| 156012 H | ● | ● | | ● | | 3 | | | | | |
| WDXT 186012 L | ● | ❍ | | ❍ | | 1 | 18,0 | 6,0 | 1,2 | 1,2 | WDX560D3S40 – WDX680D3S40 |
| 186012 G | ● | ● | | ● | | 2 | | | | | |
| 186012 H | ❍ | ❍ | | ❍ | | 3 | | | | | |

Fig. 1





For low feed with chip control

Fig. 2





General purpose

Fig. 3




Strong edge

Fig. 4




For stainless steel

## Recommended Cutting Conditions (3D)

(min. - **optimal** - max.)

| Material Group | | | Hardness (HB) | Chipbreaker | Grade | Cutting Speed (m/min) | Feed rate (mm/rev) | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| ISO | Work material | | | | | | Ø 13,0–Ø 18,0 | Ø 18,5–Ø 29,0 | Ø 29,5– Ø 36,0 | Ø 37,0–Ø 55,0 | Ø 56,0–Ø 68,0 |
| P | Carbon steel | St 42-3 | 125 | G | ACP300 | 120–**180**–240 | 0,05–**0,07**–0,10 | 0,05–**0,07**–0,10 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,12 | 0,06–**0,09**–0,13 |
| | | C15 | 125 | L | ACP300 | 130–**170**–220 | 0,04–**0,07**–0,10 | 0,04–**0,07**–0,10 | 0,04–**0,08**–0,11 | 0,05–**0,09**–0,12 | 0,06–**0,10**–0,13 |
| | | C45 | 190 | G | ACP300 | 100–**150**–200 | 0,08–**0,12**–0,20 | 0,08–**0,12**–0,20 | 0,08–**0,13**–0,22 | 0,09–**0,14**–0,24 | 0,10–**0,16**–0,27 |
| | | C45 Hardened | 250 | G | ACP100 | 100–**170**–240 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,12 | 0,05–**0,09**–0,14 | 0,06–**0,10**–0,15 |
| | | C75 | 270 | G | ACP100 | 120–**180**–240 | 0,06–**0,09**–0,14 | 0,06–**0,09**–0,17 | 0,06–**0,10**–0,14 | 0,07–**0,11**–0,17 | 0,08–**0,12**–0,18 |
| | | C75 Hardened | 300 | G | ACP100 | 80–**150**–210 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,11 | 0,05–**0,09**–0,14 | 0,06–**0,10**–0,14 |
| | Low alloyed steel | Cr-Mo, Ni-Cr-Mo | 180 | L | ACP300 | 100–**140**–180 | 0,05–**0,07**–0,12 | 0,05–**0,07**–0,12 | 0,05–**0,08**–0,13 | 0,06–**0,08**–0,13 | 0,07–**0,09**–0,16 |
| | Low alloyed steel | Cr-Mo, Ni-Cr-Mo Hardened | 275 | G | ACP100 | 100–**170**–240 | 0,06–**0,08**–0,11 | 0,06–**0,08**–0,11 | 0,06–**0,08**–0,11 | 0,07–**0,10**–0,12 | 0,08–**0,10**–0,13 |
| | | | 300 | G | ACP100 | 90–**150**–210 | 0,06–**0,08**–0,11 | 0,06–**0,08**–0,11 | 0,06–**0,08**–0,11 | 0,07–**0,10**–0,12 | 0,08–**0,10**–0,13 |
| | | | 350 | G | ACP100 | 75–**120**–165 | 0,06–**0,08**–0,11 | 0,06–**0,08**–0,11 | 0,06–**0,08**–0,11 | 0,07–**0,10**–0,12 | 0,08–**0,10**–0,13 |
| | High alloyed steel | Sintered | 200 | G | ACP100 | 120–**180**–240 | 0,08–**0,11**–0,14 | 0,08–**0,12**–0,15 | 0,08–**0,12**–0,16 | 0,09–**0,14**–0,18 | 0,10–**0,14**–0,19 |
| | | | 325 | G | ACP100 | 100–**140**–180 | 0,06–**0,09**–0,11 | 0,06–**0,09**–0,11 | 0,06–**0,09**–0,11 | 0,07–**0,10**–0,12 | 0,08–**0,10**–0,13 |
| M | Stainless steel | Martensitic/Ferritic | 200 | M | ACM300 | 120–**150**–180 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,07–**0,10**–0,16 | 0,08–**0,12**–0,16 |
| | | Martensitic/Hardened | 240 | M | ACM300 | 90–**120**–150 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,07–**0,10**–0,16 | 0,08–**0,12**–0,16 |
| | | Austenitic | 180 | M | ACM300 | 120–**150**–180 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,06–**0,08**–0,15 | 0,07–**0,10**–0,16 | 0,08–**0,12**–0,16 |
| K | Cast iron | | | H | ACK300 | 120–**160**–200 | 0,09–**0,18**–0,27 | 0,10–**0,20**–0,30 | 0,11–**0,22**–0,32 | 0,12–**0,24**–0,36 | 0,13–**0,26**–0,40 |
| | Ductile Cast iron | | | H | ACK300 | 90–**120**–150 | 0,09–**0,18**–0,27 | 0,10–**0,20**–0,30 | 0,11–**0,22**–0,32 | 0,12–**0,24**–0,36 | 0,13–**0,26**–0,40 |
| S | Exotic Alloy (Heat resistant alloy, Super Alloy, etc) | | 200 | G | ACP300 | 25–**50**–70 | 0,06–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,07–**0,12**–0,18 | 0,08–**0,13**–0,20 |
| N | Aluminium Alloy | | | G | DL1500 | 200–**260**–320 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 | 0,08–**0,14**–0,22 |
| | Copper Alloy | | | G | DL1500 | 180–**230**–280 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 | 0,08–**0,14**–0,22 |

*For the P and K grades for which ACP300 and ACK300 are the first recommendation, ACP100 inserts are the second recommendation.
The recommended cutting conditions are a cutting speed $v_c$ of 130% of the above table and a feed rate f of 75%.

# WDX Type (4D)

Max. Depth: 4D

Machining tolerances 0 to +0.25 mm

Fig. 1





Fig. 2






Fig. 3




## Holder Diameter Ø 13,0 mm – Ø 45,0 mm

| DC | Stock | Cat. No. | LUX | LPR | OAL | LS | DCSFMS | DCON | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 13,0 | ● | WDX 130D4S20 | 55 | 70 | 114 | | | | 1 |
| 13,5 | ● | 135D4S20 | 57 | 72 | 116 | | | | 1 |
| 14,0 | ● | 140D4S20 | 59 | 74 | 118 | 44 | 28,0 | 20 | 1 |
| 14,5 | ● | 145D4S20 | 61 | 76 | 120 | | | | 1 |
| 15,0 | ● | 150D4S20 | 63 | 78 | 122 | | | | 1 |
| 15,5 | ● | WDX 155D4S20 | 65 | 80 | 124 | | | | 1 |
| 16,0 | ● | 160D4S20 | 67 | 82 | 126 | 44 | 30,0 | 20 | 1 |
| 16,5 | ● | 165D4S20 | 69 | 84 | 128 | | | | 1 |
| 17,0 | ● | 170D4S20 | 71 | 86 | 130 | | | | 1 |
| 17,5 | ● | WDX 175D4S25 | 73 | 88 | 144 | 56 | 32,0 | 25 | 1 |
| 18,0 | ● | 180D4S25 | 75 | 90 | 146 | | | | 1 |
| 18,5 | ● | WDX 185D4S25 | 77 | 92 | 148 | | | | 1 |
| 19,0 | ● | 190D4S25 | 79 | 94 | 150 | | | | 1 |
| 19,5 | ● | 195D4S25 | 81 | 96 | 152 | | | | 1 |
| 20,0 | ● | 200D4S25 | 83 | 98 | 154 | | | | 1 |
| 20,5 | ● | 205D4S25 | 85 | 100 | 156 | 56 | 33,0 | 25 | 1 |
| 21,0 | ● | 210D4S25 | 87 | 102 | 158 | | | | 1 |
| 21,5 | ● | 215D4S25 | 89 | 104 | 160 | | | | 1 |
| 22,0 | ● | 220D4S25 | 91 | 106 | 162 | | | | 1 |
| 22,5 | ● | 225D4S25 | 93 | 108 | 164 | | | | 1 |
| 23,0 | ● | WDX 230D4S25 | 95 | 113 | 169 | | | | 1 |
| 23,5 | ● | 235D4S25 | 97 | 115 | 171 | | | | 1 |
| 24,0 | ● | 240D4S25 | 99 | 117 | 173 | 56 | 37,0 | 25 | 1 |
| 24,5 | ● | 245D4S25 | 101 | 119 | 175 | | | | 1 |
| 25,0 | ● | 250D4S25 | 103 | 121 | 177 | | | | 1 |
| 25,5 | ● | WDX 255D4S32 | 105 | 125 | 185 | | | | 2 |
| 26,0 | ● | 260D4S32 | 107 | 127 | 187 | | | | 2 |
| 26,5 | ● | 265D4S32 | 109 | 129 | 189 | | | | 2 |
| 27,0 | ● | 270D4S32 | 111 | 131 | 191 | 60 | 41,0 | 32 | 2 |
| 27,5 | ● | 275D4S32 | 113 | 133 | 193 | | | | 2 |
| 28,0 | ● | 280D4S32 | 115 | 135 | 195 | | | | 2 |
| 28,5 | ● | 285D4S32 | 117 | 137 | 197 | | | | 2 |
| 29,0 | ● | WDX 290D4S32 | 120 | 141 | 201 | | 50,0 | | 2 |
| 29,5 | ● | 295D4S32 | 122 | 143 | 203 | | | | 2 |
| 30,0* | ❍ | 300D4S32 | 124 | 148 | 208 | 60 | | 32 | 2 |
| 31,0* | | 310D4S32 | 128 | 152 | 212 | | 54,0 | | 2 |
| 32,0* | ❍ | 320D4S32 | 132 | 156 | 216 | | | | 2 |
| 30,0* | ● | WDX 300D4S40 | 124 | 148 | 218 | | | | 2 |
| 31,0* | ● | 310D4S40 | 128 | 152 | 222 | | | | 2 |
| 32,0* | ● | 320D4S40 | 132 | 156 | 226 | | | | 2 |
| 33,0 | ● | 330D4S40 | 136 | 160 | 230 | 70 | 54,0 | 40 | 2 |
| 34,0 | ● | 340D4S40 | 140 | 164 | 234 | | | | 2 |
| 35,0 | ● | 350D4S40 | 144 | 168 | 238 | | | | 2 |
| 36,0 | ● | 360D4S40 | 148 | 172 | 242 | | | | 2 |
| 37,0 | ● | WDX 370D4S40 | 153 | 183 | 253 | | | | 2 |
| 38,0 | ● | 380D4S40 | 157 | 187 | 257 | | | | 2 |
| 39,0 | ● | 390D4S40 | 161 | 191 | 261 | | | | 2 |
| 40,0 | ● | 400D4S40 | 165 | 195 | 265 | | | | 2 |
| 41,0 | ● | 410D4S40 | 169 | 199 | 269 | 70 | 49,5 | 40 | 2 |
| 42,0 | ● | 420D4S40 | 173 | 203 | 273 | | | | 2 |
| 43,0 | ● | 430D4S40 | 177 | 207 | 277 | | | | 2 |
| 44,0 | ● | 440D4S40 | 181 | 211 | 281 | | | | 2 |
| 45,0 | ● | 450D4S40 | 185 | 215 | 285 | | | | 2 |

* Diameter Ø 30, Ø 31, Ø 32 are in stock with shank diameters of Ø 32 and Ø 40.

## Holder Diameter Ø 46,0 mm – Ø 63,0 mm

| DC | Stock | Cat. No. | LUX | LPR | OAL | LS | DCSFMS | DCON | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 46,0 | ● | WDX 460D4S40 | 189 | 219 | 289 | | | | 2 |
| 47,0 | ● | 470D4S40 | 193 | 223 | 293 | | | | 2 |
| 48,0 | ● | 480D4S40 | 197 | 227 | 297 | | 49,5 | | 2 |
| 49,0 | ● | 490D4S40 | 201 | 231 | 301 | | | | 2 |
| 50,0 | ● | 500D4S40 | 205 | 235 | 305 | 70 | | 40 | 2 |
| 51,0 | ● | 510D4S40 | 209 | 239 | 309 | | | | 3 |
| 52,0 | ● | 520D4S40 | 213 | 243 | 313 | | 50,5 | | 3 |
| 53,0 | ● | 530D4S40 | 217 | 247 | 317 | | 51,5 | | 3 |
| 54,0 | ● | 540D4S40 | 221 | 251 | 321 | | 52,5 | | 3 |
| 55,0 | ● | 550D4S40 | 225 | 255 | 325 | | 53,5 | | 3 |
| 56,0 | ❍ | WDX 560D4S40 | 232 | 264 | 334 | | 54,0 | | 3 |
| 57,0 | ❍ | 570D4S40 | 236 | 268 | 338 | | 55,0 | | 3 |
| 58,0 | ❍ | 580D4S40 | 240 | 272 | 342 | | 56,0 | | 3 |
| 59,0 | ❍ | 590D4S40 | 244 | 276 | 346 | 70 | 57,0 | 40 | 3 |
| 60,0 | ❍ | 600D4S40 | 248 | 280 | 350 | | 58,0 | | 3 |
| 61,0 | ❍ | 610D4S40 | 252 | 284 | 354 | | 59,0 | | 3 |
| 62,0 | ❍ | 620D4S40 | 256 | 288 | 358 | | 60,0 | | 3 |
| 63,0 | | 630D4S40 | 260 | 292 | 362 | | 61,0 | | 3 |

## Parts

| Applicable Holder | Flat Screw | | Wrench | Wrench |
|---|---|---|---|---|
| |  | N·m |  |  |
| WDX130D4S20–WDX150D4S20 | BFTX01604N | **0,3** | TRX06 | – |
| WDX155D4S20–WDX180D4S25 | BFTX0204N | **0,5** | TRX06 | – |
| WDX185D4S25–WDX225D4S25 | BFTY02206 | **1,0** | – | TRD07 |
| WDX230D4S25–WDX285D4S32 | BFTX02506N | **1,5** | – | TRD08 |
| WDX290D4S32–WDX360D4S40 | BFTX03584 | **3,5** | – | TRD15 |
| WDX370D4S40–WDX450D4S40 | BFTX0511N | **5,0** | – | TRD20 |
| WDX460D4S40–WDX630D4S40 | BFTX0615N | **5,0** | – | TRD25 |

## Identification Details - Holder

**WDX 200 D4 S25**

- 200: Diameter DC (Ø 20,0 mm)
- D4: Flute Length L/D (4D)
- S25: Shank Diameter DCON (Ø 25,0 mm)

## Identification Details - Inserts

**WDXT 06 30 06 -G**

- 06: Width across Flats (6,0 mm)
- 30: Thickness (3,0 mm)
- 06: Nose Radius (0,6 mm)
- -G: Breaker Type





● = Euro stock
○ = Japan stock


N·m Recommended Tightening Torque (N·m)

## Inserts

| Application | Coated Carbide | | | | |
|---|---|---|---|---|---|
| High-Speed / Light | PK | | | | N |
| General Purpose | | P | M | | |
| Roughing | | P | | K | |


| Cat. No. | ACP100 | ACP300 | ACM300 | ACK300 | DL1500 | Fig | W1 | S | RE1 | RE2 | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WDXT 042004 L | ❍ | ● | | ● | | 1 | 4,2 | 2,0 | 0,4 | 0,4 | WDX130D4S20 – WDX150D4S20 |
| 042004 G | ● | ● | | ● | ● | 2 | | | | | |
| 042004 H | ● | ● | | ● | | 3 | | | | | |
| 042004 M | | | ● | | | 4 | | | | 0,8 | |
| WDXT 052504 L | ❍ | ● | | ● | | 1 | 5,0 | 2,5 | 0,4 | 0,4 | WDX155D4S20 – WDX180D4S25 |
| 052504 G | ● | ● | | ● | ● | 2 | | | | | |
| 052504 H | ● | ● | | ● | | 3 | | | | | |
| 052504 M | | | ● | | | 4 | | | | 1,0 | |
| WDXT 063006 L | ● | ● | | ● | | 1 | 6,0 | 3,0 | 0,6 | 0,6 | WDX185D4S25 – WDX225D4S25 |
| 063006 G | ● | ● | | ● | ● | 2 | | | | | |
| 063006 H | ● | ● | | ● | | 3 | | | | | |
| 063006 M | | | ● | | | 4 | | | | 1,4 | |
| WDXT 073506 L | ● | ● | | ● | | 1 | 7,5 | 3,5 | 0,6 | 0,6 | WDX230D4S25 – WDX285D4S32 |
| 073506 G | ● | ● | | ● | ● | 2 | | | | | |
| 073506 H | ● | ● | | ● | | 3 | | | | | |
| 073506 M | | | ● | | | 4 | | | | 1,6 | |
| WDXT 094008 L | ● | ● | | ● | | 1 | 9,6 | 4,0 | 0,8 | 0,8 | WDX290D4S32 – WDX360D4S40 |
| 094008 G | ● | ● | | ● | ● | 2 | | | | | |
| 094008 H | ● | ● | | ● | | 3 | | | | | |
| 094008 M | | | ● | | | 4 | | | | 2,4 | |
| WDXT 125012 L | ● | ● | | ● | | 1 | 12,4 | 5,0 | 1,2 | 1,2 | WDX370D4S40 – WDX450D4S40 |
| 125012 G | ● | ● | | ● | ● | 2 | | | | | |
| 125012 H | ● | ● | | ● | | 3 | | | | | |
| 125012 M | | | ● | | | 4 | | | | 3,2 | |
| WDXT 156012 L | ● | ● | | ● | | 1 | 15,2 | 6,0 | 1,2 | 1,2 | WDX460D4S40 – WDX550D4S40 |
| 156012 G | ● | ● | | ● | ● | 2 | | | | | |
| 156012 H | ● | ● | | ● | | 3 | | | | | |
| WDXT 186012 L | ● | ❍ | | ❍ | | 1 | 18,0 | 6,0 | 1,2 | 1,2 | WDX560D4S40 – WDX630D4S40 |
| 186012 G | ● | ● | | ● | | 2 | | | | | |
| 186012 H | ❍ | ❍ | | ❍ | | 3 | | | | | |

Fig. 1





For low feed with chip control

Fig. 2





General purpose

Fig. 3




Strong edge

Fig. 4




For stainless steel

## Recommended Cutting Conditions (4D)

(min. - **optimal** - max.)

| Material Group ISO | Work material | | | Hardness (HB) | Chipbreaker | Grade | Cutting Speed (m/min) | Feed rate (mm/rev) Ø 13,0–Ø 18,0 | Ø 18,5–Ø 29,0 | Ø 29,5– Ø 36,0 | Ø 37,0–Ø 55,0 | Ø 56,0–Ø 63,0 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| P | Carbon steel | St 42-3 | | 125 | G | ACP300 | 120–**180**–240 | 0,05–**0,07**–0,10 | 0,05–**0,07**–0,10 | 0,05–**0,07**–0,10 | 0,05–**0,08**–0,10 | 0,06–**0,09**–0,11 |
| | | C15 | | 125 | L | ACP300 | 130–**170**–220 | 0,04–**0,07**–0,09 | 0,04–**0,07**–0,09 | 0,04–**0,07**–0,09 | 0,05–**0,08**–0,10 | 0,06–**0,09**–0,11 |
| | | C45 | | 190 | G | ACP300 | 100–**150**–200 | 0,08–**0,11**–0,17 | 0,08–**0,11**–0,17 | 0,08–**0,12**–0,18 | 0,09–**0,14**–0,21 | 0,10–**0,15**–0,23 |
| | | C45 | Hardened | 250 | G | ACP100 | 100–**170**–240 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,11 | 0,06–**0,09**–0,13 |
| | | C75 | | 270 | G | ACP100 | 120–**180**–240 | 0,06–**0,08**–0,11 | 0,06–**0,08**–0,11 | 0,06–**0,09**–0,13 | 0,07–**0,11**–0,14 | 0,08–**0,11**–0,15 |
| | | C75 | Hardened | 300 | G | ACP100 | 85–**150**–210 | 0,05–**0,07**–0,09 | 0,05–**0,07**–0,09 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,11 | 0,06–**0,09**–0,12 |
| | Low alloyed steel | Cr-Mo, Ni-Cr-Mo | | 180 | L | ACP300 | 100–**140**–180 | 0,05–**0,07**–0,10 | 0,05–**0,07**–0,10 | 0,05–**0,07**–0,11 | 0,06–**0,08**–0,12 | 0,07–**0,09**–0,14 |
| | Low alloyed steel | Cr-Mo, Ni-Cr-Mo | Hardened | 275 | G | ACP100 | 100–**170**–240 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,11 | 0,06–**0,08**–0,11 |
| | | | | 300 | G | ACP100 | 90–**150**–210 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,11 | 0,06–**0,08**–0,11 |
| | | | | 350 | G | ACP100 | 75–**120**–165 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,11 | 0,06–**0,08**–0,11 |
| | High alloyed steel | | | 200 | G | ACP100 | 120–**180**–240 | 0,06–**0,10**–0,13 | 0,07–**0,11**–0,14 | 0,07–**0,11**–0,15 | 0,08–**0,12**–0,16 | 0,09–**0,13**–0,17 |
| | | | Sintered | 325 | G | ACP100 | 100–**140**–180 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,11 | 0,06–**0,08**–0,11 |
| M | Stainless steel | Martensitic/Ferritic | | 200 | M | ACM300 | 120–**150**–180 | 0,06–**0,08**–0,13 | 0,06–**0,08**–0,13 | 0,06–**0,08**–0,14 | 0,07–**0,09**–0,14 | 0,06–**0,11**–0,14 |
| | | Martensitic/Hardened | | 240 | M | ACM300 | 90–**120**–150 | 0,06–**0,08**–0,13 | 0,06–**0,08**–0,13 | 0,06–**0,08**–0,14 | 0,07–**0,09**–0,14 | 0,06–**0,11**–0,14 |
| | | Austenitic | | 180 | M | ACM300 | 120–**150**–180 | 0,06–**0,08**–0,13 | 0,06–**0,08**–0,13 | 0,06–**0,08**–0,14 | 0,07–**0,09**–0,14 | 0,06–**0,11**–0,14 |
| K | Cast iron | | | | H | ACK300 | 120–**160**–200 | 0,09–**0,17**–0,23 | 0,10–**0,19**–0,26 | 0,11–**0,21**–0,28 | 0,12–**0,23**–0,31 | 0,13–**0,25**–0,34 |
| | Ductile Cast iron | | | | H | ACK300 | 90–**120**–150 | 0,09–**0,17**–0,23 | 0,10–**0,19**–0,26 | 0,11–**0,21**–0,28 | 0,12–**0,23**–0,31 | 0,13–**0,25**–0,34 |
| S | Exotic Alloy (Heat resistant alloy, Super Alloy, etc) | | | 200 | G | ACP300 | 25–**50**–70 | 0,06–**0,10**–0,13 | 0,06–**0,10**–0,13 | 0,06–**0,10**–0,14 | 0,07–**0,11**–0,15 | 0,08–**0,12**–0,17 |
| N | Aluminium Alloy | | | | G | DL1500 | 200–**260**–320 | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |
| | Copper Alloy | | | | G | DL1500 | 180–**230**–280 | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |

*For the P and K grades for which ACP300 and ACK300 are the first recommendation, ACP100 inserts are the second recommendation.
The recommended cutting conditions are a cutting speed $v_c$ of 130% of the above table and a feed rate f of 75%.

# WDX Type (5D)

## Max. Depth: 5D

Machining tolerances 0 to +0.25 mm

Fig. 1





Fig. 2






Fig. 3




## Holder Diameter Ø 13,0 mm – Ø 45,0 mm

| DC | Stock | Cat. No. | LUX | LPR | OAL | LS | DCSFMS | DCON | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 13,0 | ● | WDX 130D5S20 | 68,0 | 83,0 | 127,0 | | | | 1 |
| 13,5 | ● | 135D5S20 | 70,5 | 85,5 | 129,5 | | | | 1 |
| 14,0 | ● | 140D5S20 | 73,0 | 88,0 | 132,0 | 44 | 28,0 | 20,0 | 1 |
| 14,5 | ● | 145D5S20 | 75,5 | 90,5 | 134,5 | | | | 1 |
| 15,0 | ● | 150D5S20 | 78,0 | 93,0 | 137,0 | | | | 1 |
| 15,5 | ● | WDX 155D5S20 | 80,5 | 95,5 | 139,5 | | | | 1 |
| 16,0 | ● | 160D5S20 | 83,0 | 98,0 | 142,0 | 44 | 30,0 | 20,0 | 1 |
| 16,5 | ● | 165D5S20 | 85,5 | 100,5 | 144,5 | | | | 1 |
| 17,0 | ● | 170D5S20 | 88,0 | 103,0 | 147,0 | | | | 1 |
| 17,5 | ● | WDX 175D5S25 | 90,5 | 105,5 | 161,5 | 56 | 32,0 | 25,0 | 1 |
| 18,0 | ● | 180D5S25 | 93,0 | 108,0 | 164,0 | | | | 1 |
| 18,5 | ● | WDX 185D5S25 | 95,5 | 110,5 | 166,5 | | | | 1 |
| 19,0 | ● | 190D5S25 | 98,0 | 113,0 | 169,0 | | | | 1 |
| 19,5 | ● | 195D5S25 | 100,5 | 115,5 | 171,5 | | | | 1 |
| 20,0 | ● | 200D5S25 | 103,0 | 118,0 | 174,0 | | | | 1 |
| 20,5 | ● | 205D5S25 | 105,5 | 120,5 | 176,5 | 56 | 33,0 | 25,0 | 1 |
| 21,0 | ● | 210D5S25 | 108,0 | 123,0 | 179,0 | | | | 1 |
| 21,5 | ● | 215D5S25 | 110,5 | 125,5 | 181,5 | | | | 1 |
| 22,0 | ● | 220D5S25 | 113,0 | 128,0 | 184,0 | | | | 1 |
| 22,5 | ● | 225D5S25 | 115,5 | 130,5 | 186,5 | | | | 1 |
| 23,0 | ● | WDX 230D5S25 | 118,0 | 136,0 | 192,0 | | | | 1 |
| 23,5 | ● | 235D5S25 | 120,5 | 138,5 | 194,5 | | | | 1 |
| 24,0 | ● | 240D5S25 | 123,0 | 141,0 | 197,0 | 56 | 37,0 | 25,0 | 1 |
| 24,5 | ● | 245D5S25 | 125,5 | 143,5 | 199,5 | | | | 1 |
| 25,0 | ● | 250D5S25 | 128,0 | 146,0 | 202,0 | | | | 1 |
| 26,0 | ● | WDX 260D5S32 | 133,0 | 153,0 | 213,0 | | | | 2 |
| 27,0 | ● | 270D5S32 | 138,0 | 158,0 | 218,0 | 60 | 41,0 | 32,0 | 2 |
| 28,0 | ● | 280D5S32 | 143,0 | 163,0 | 223,0 | | | | 2 |
| 29,0 | ● | WDX 290D5S32 | 149,0 | 170,0 | 230,0 | | 50,0 | | 2 |
| 30,0* | ● | 300D5S32 | 154,0 | 178,0 | 238,0 | 60 | | 32,0 | 2 |
| 31,0* | ● | 310D5S32 | 159,0 | 183,0 | 243,0 | | 54,0 | | 2 |
| 32,0* | ❍ | 320D5S32 | 164,0 | 188,0 | 248,0 | | | | 2 |
| 30,0* | ● | WDX 300D5S40 | 154,0 | 178,0 | 248,0 | | | | 2 |
| 31,0* | ● | 310D5S40 | 159,0 | 183,0 | 253,0 | | | | 2 |
| 32,0* | ● | 320D5S40 | 164,0 | 188,0 | 258,0 | | | | 2 |
| 33,0 | ● | 330D5S40 | 169,0 | 193,0 | 263,0 | 70 | 54,0 | 40,0 | 2 |
| 34,0 | ● | 340D5S40 | 174,0 | 198,0 | 268,0 | | | | 2 |
| 35,0 | ● | 350D5S40 | 179,0 | 203,0 | 273,0 | | | | 2 |
| 36,0 | ● | 360D5S40 | 184,0 | 208,0 | 278,0 | | | | 2 |
| 37,0 | ❍ | WDX 370D5S40 | 190,0 | 220,0 | 290,0 | | | | 2 |
| 38,0 | ❍ | 380D5S40 | 195,0 | 225,0 | 295,0 | | | | 2 |
| 39,0 | ❍ | 390D5S40 | 200,0 | 230,0 | 300,0 | | | | 2 |
| 40,0 | ❍ | 400D5S40 | 205,0 | 235,0 | 305,0 | | | | 2 |
| 41,0 | ❍ | 410D5S40 | 210,0 | 240,0 | 310,0 | 70 | 49,5 | 40,0 | 2 |
| 42,0 | ❍ | 420D5S40 | 215,0 | 245,0 | 315,0 | | | | 2 |
| 43,0 | ❍ | 430D5S40 | 220,0 | 250,0 | 320,0 | | | | 2 |
| 44,0 | ❍ | 440D5S40 | 225,0 | 255,0 | 325,0 | | | | 2 |
| 45,0 | ❍ | 450D5S40 | 230,0 | 260,0 | 330,0 | | | | 2 |

* Diameter Ø 30, Ø 31, Ø 32 are in stock with shank diameters of Ø 32 and Ø 40.

## Holder Diameter Ø 46,0 mm – Ø 55,0 mm

| DC | Stock | Cat. No. | LUX | LPR | OAL | LS | DCSFMS | DCON | Fig |
|---|---|---|---|---|---|---|---|---|---|
| 46,0 | ❍ | WDX 460D5S40 | 235,0 | 265,0 | 335,0 | | | | 2 |
| 47,0 | ❍ | 470D5S40 | 240,0 | 270,0 | 340,0 | | | | 2 |
| 48,0 | ❍ | 480D5S40 | 245,0 | 275,0 | 345,0 | | 49,5 | | 2 |
| 49,0 | ❍ | 490D5S40 | 250,0 | 280,0 | 350,0 | | | | 2 |
| 50,0 | ❍ | 500D5S40 | 255,0 | 285,0 | 355,0 | 70 | | 40,0 | 2 |
| 51,0 | ❍ | 510D5S40 | 260,0 | 290,0 | 360,0 | | | | 3 |
| 52,0 | ❍ | 520D5S40 | 265,0 | 295,0 | 365,0 | | 50,5 | | 3 |
| 53,0 | ❍ | 530D5S40 | 270,0 | 300,0 | 370,0 | | 51,5 | | 3 |
| 54,0 | ❍ | 540D5S40 | 275,0 | 305,0 | 375,0 | | 52,5 | | 3 |
| 55,0 | ❍ | 550D5S40 | 280,0 | 310,0 | 380,0 | | 53,5 | | 3 |

## Parts

| Applicable Holder | Flat Screw | | Wrench | Wrench |
|---|---|---|---|---|
| |  | N·m |  |  |
| WDX130D5S20–WDX150D5S20 | BFTX01604N | **0,3** | TRX06 | – |
| WDX155D5S20–WDX180D5S25 | BFTX0204N | **0,5** | TRX06 | – |
| WDX185D5S25–WDX225D5S25 | BFTY02206 | **1,0** | – | TRD07 |
| WDX230D5S25–WDX280D5S32 | BFTX02506N | **1,5** | – | TRD08 |
| WDX290D5S32–WDX360D5S40 | BFTX03584 | **3,5** | – | TRD15 |
| WDX370D5S40–WDX450D5S40 | BFTX0511N | **5,0** | – | TRD20 |
| WDX460D5S40–WDX550D5S40 | BFTX0615N | **5,0** | – | TRD25 |

## Identification Details - Holder

**WDX 200 D5 S25**

- 200: Diameter DC (Ø 20,0 mm)
- D5: Flute Length L/D (5D)
- S25: Shank Diameter DCON (Ø 25,0 mm)

## Identification Details - Inserts

**WDXT 06 30 06 -G**

- 06: Width across Flats (6,0 mm)
- 30: Thickness (3,0 mm)
- 06: Nose Radius (0,6 mm)
- -G: Breaker Type





● = Euro stock
○ = Japan stock


N·m Recommended Tightening Torque (N·m)

## Inserts

| Application | Coated Carbide | | | | |
|---|---|---|---|---|---|
| High-Speed / Light | PK | | | | N |
| General Purpose | | P | M | | |
| Roughing | | P | | K | |


| Cat. No. | ACP100 | ACP300 | ACM300 | ACK300 | DL1500 | Fig | W1 | S | RE1 | RE2 | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WDXT 042004 L | ❍ | ● | | ● | | 1 | 4,2 | 2,0 | 0,4 | 0,4 | WDX130D5S20 – WDX150D5S20 |
| 042004 G | ● | ● | | ● | ● | 2 | | | | | |
| 042004 H | ● | ● | | ● | | 3 | | | | | |
| 042004 M | | | ● | | | 4 | | | | 0,8 | |
| WDXT 052504 L | ❍ | ● | | ● | | 1 | 5,0 | 2,5 | 0,4 | 0,4 | WDX155D5S20 – WDX180D5S25 |
| 052504 G | ● | ● | | ● | ● | 2 | | | | | |
| 052504 H | ● | ● | | ● | | 3 | | | | | |
| 052504 M | | | ● | | | 4 | | | | 1,0 | |
| WDXT 063006 L | ● | ● | | ● | | 1 | 6,0 | 3,0 | 0,6 | 0,6 | WDX185D5S25 – WDX225D5S25 |
| 063006 G | ● | ● | | ● | ● | 2 | | | | | |
| 063006 H | ● | ● | | ● | | 3 | | | | | |
| 063006 M | | | ● | | | 4 | | | | 1,4 | |
| WDXT 073506 L | ● | ● | | ● | | 1 | 7,5 | 3,5 | 0,6 | 0,6 | WDX230D5S25 – WDX280D5S32 |
| 073506 G | ● | ● | | ● | ● | 2 | | | | | |
| 073506 H | ● | ● | | ● | | 3 | | | | | |
| 073506 M | | | ● | | | 4 | | | | 1,6 | |
| WDXT 094008 L | ● | ● | | ● | | 1 | 9,6 | 4,0 | 0,8 | 0,8 | WDX290D5S32 – WDX360D5S40 |
| 094008 G | ● | ● | | ● | ● | 2 | | | | | |
| 094008 H | ● | ● | | ● | | 3 | | | | | |
| 094008 M | | | ● | | | 4 | | | | 2,4 | |
| WDXT 125012 L | ● | ● | | ● | | 1 | 12,4 | 5,0 | 1,2 | 1,2 | WDX370D5S40 – WDX450D5S40 |
| 125012 G | ● | ● | | ● | ● | 2 | | | | | |
| 125012 H | ● | ● | | ● | | 3 | | | | | |
| 125012 M | | | ● | | | 4 | | | | 3,2 | |
| WDXT 156012 L | ● | ● | | ● | | 1 | 15,2 | 6,0 | 1,2 | 1,2 | WDX460D5S40 – WDX550D5S40 |
| 156012 G | ● | ● | | ● | ● | 2 | | | | | |
| 156012 H | ● | ● | | ● | | 3 | | | | | |

Fig. 1





For low feed with chip control

Fig. 2





General purpose

Fig. 3




Strong edge

Fig. 4




For stainless steel

## Recommended Cutting Conditions (5D)

(min. - **optimal** - max.)


| ISO | Material Group | Work material | | Hardness (HB) | Chipbreaker | Grade | Cutting Speed (m/min) | Feed rate (mm/rev) Ø 13,0–Ø 18,0 | Ø 18,5–Ø 29,0 | Ø 29,5– Ø 36,0 | Ø 37,0–Ø 55,0 |
|---|---|---|---|---|---|---|---|---|---|---|---|
| P | Carbon steel | St 42-3 | | 125 | G | ACP300 | 120–**180**–240 | 0,05–**0,06**–0,09 | 0,05–**0,06**–0,09 | 0,05–**0,06**–0,09 | 0,05–**0,07**–0,09 |
| | | C15 | | 125 | L | ACP300 | 130–**170**–220 | 0,04–**0,06**–0,08 | 0,04–**0,06**–0,08 | 0,04–**0,06**–0,08 | 0,05–**0,07**–0,09 |
| | | C45 | | 190 | G | ACP300 | 100–**150**–200 | 0,07–**0,10**–0,15 | 0,07–**0,10**–0,15 | 0,08–**0,11**–0,17 | 0,09–**0,12**–0,19 |
| | | C45 | Hardened | 250 | G | ACP100 | 100–**170**–240 | 0,04–**0,07**–0,08 | 0,04–**0,07**–0,08 | 0,05–**0,07**–0,09 | 0,05–**0,08**–0,11 |
| | | C75 | | 270 | G | ACP100 | 120–**180**–240 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,11 | 0,06–**0,08**–0,11 | 0,07–**0,09**–0,13 |
| | | C75 | Hardened | 300 | G | ACP100 | 80–**150**–210 | 0,04–**0,07**–0,08 | 0,04–**0,07**–0,08 | 0,05–**0,07**–0,09 | 0,05–**0,08**–0,10 |
| | Low alloyed steel | Cr-Mo, Ni-Cr-Mo | | 180 | L | ACP300 | 100–**140**–180 | 0,05–**0,06**–0,09 | 0,05–**0,06**–0,09 | 0,05–**0,06**–0,10 | 0,05–**0,07**–0,11 |
| | Low alloyed steel | Cr-Mo, Ni-Cr-Mo | Hardened | 275 | G | ACP100 | 100–**170**–240 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 | 0,05–**0,07**–0,10 |
| | | | | 300 | G | ACP100 | 90–**150**–210 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 | 0,05–**0,07**–0,10 |
| | | | | 350 | G | ACP100 | 75–**120**–165 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 | 0,05–**0,07**–0,10 |
| | High alloyed steel | | Sintered | 200 | G | ACP100 | 120–**180**–240 | 0,05–**0,08**–0,12 | 0,06–**0,09**–0,12 | 0,06–**0,09**–0,13 | 0,07–**0,10**–0,14 |
| | | | | 325 | G | ACP100 | 100–**140**–180 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 | 0,04–**0,06**–0,09 |
| M | Stainless steel | Martensitic/Ferritic | | 200 | M | ACM300 | 120–**150**–180 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,12 | 0,05–**0,08**–0,12 | 0,06–**0,09**–0,12 |
| | | Martensitic/Hardened | | 240 | M | ACM300 | 90–**120**–150 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,12 | 0,05–**0,08**–0,12 | 0,06–**0,09**–0,12 |
| | | Austenitic | | 180 | M | ACM300 | 120–**150**–180 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,12 | 0,05–**0,08**–0,12 | 0,06–**0,09**–0,12 |
| K | Cast iron | | | | H | ACK300 | 120–**160**–200 | 0,08–**0,15**–0,21 | 0,09–**0,17**–0,23 | 0,09–**0,18**–0,25 | 0,11–**0,20**–0,28 |
| | Ductile Cast iron | | | | H | ACK300 | 90–**120**–150 | 0,08–**0,15**–0,21 | 0,09–**0,17**–0,23 | 0,09–**0,18**–0,25 | 0,11–**0,20**–0,28 |
| S | Exotic Alloy (Heat resistant alloy, Super Alloy, etc) | | | 200 | G | ACP300 | 25–**50**–70 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,14 |
| N | Aluminium Alloy | | | | G | DL1500 | 200–**260**–320 | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,06–**0,12**–0,18 |
| | Copper Alloy | | | | G | DL1500 | 180–**230**–280 | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,06–**0,12**–0,18 |

*For the P and K grades for which ACP300 and ACK300 are the first recommendation, ACP100 inserts are the second recommendation.
The recommended cutting conditions are a cutting speed $v_c$ of 130% of the above table and a feed rate f of 75%.

# WDX Type


## Hole Profile

Bottom of hole after drilling with
**WDX200D3S25**




| Drill Diameter DC (mm) | a (mm) |
|---|---|
| Ø 13,0– Ø 18,0 | 0,4 |
| Ø 18,5– Ø 28,5 | 0,6 |
| Ø 29,0– Ø 36,0 | 0,8 |
| Ø 37,0– Ø 55,0 | 1,2 |
| Ø 56,0– Ø 68,0 | 1,4 |

Bottom of hole after drilling with
conventional tool





Finishing is easy because the hole bottom is almost flat.

## Applications for Lathes


### Setting Instruction

Ensure the face of the drill flange is hard against the face of the tool holder.
Axis offset: Difference between workpiece axis and the Y-axis.
Align the centreline of the drill to the centreline of the lathes Y axis.




### Drilling Over Holes

Offset the lathes X axis within the maximum amount stated in the table.





| Drill | Max. Offset (mm) | Drill | Max. Offset (mm) |
|---|---|---|---|
| WDX130... | 0,35 | WDX330... | 0,55 |
| WDX135... | 0,30 | WDX340... | 0,45 |
| WDX140... | 0,25 | WDX350... | 0,35 |
| WDX145... | 0,20 | WDX360... | 0,20 |
| WDX150... | 0,15 | WDX370... | 1,00 |
| WDX155... | 0,40 | WDX380... | 1,00 |
| WDX160... | 0,40 | WDX390... | 0,90 |
| WDX165... | 0,35 | WDX400... | 0,80 |
| WDX170... | 0,30 | WDX410... | 0,70 |
| WDX175... | 0,25 | WDX420... | 0,60 |
| WDX180... | 0,20 | WDX430... | 0,50 |
| WDX185... | 0,50 | WDX440... | 0,50 |
| WDX190... | 0,45 | WDX450... | 0,40 |
| WDX195... | 0,40 | WDX460... | 1,50 |
| WDX200... | 0,30 | WDX470... | 1,40 |
| WDX205... | 0,30 | WDX480... | 1,30 |
| WDX210... | 0,20 | WDX490... | 1,20 |
| WDX215... | 0,15 | WDX500... | 1,10 |
| WDX220... | 0,10 | WDX510... | 1,00 |
| WDX225... | 0,05 | WDX520... | 0,90 |
| WDX230... | 0,70 | WDX530... | 0,80 |
| WDX235... | 0,70 | WDX540... | 0,60 |
| WDX240... | 0,60 | WDX550... | 0,50 |
| WDX245... | 0,50 | WDX560... | 2,00 |
| WDX250... | 0,50 | WDX570... | 1,80 |
| WDX255... | 0,45 | WDX580... | 1,70 |
| WDX260... | 0,40 | WDX590... | 1,60 |
| WDX265... | 0,35 | WDX600... | 1,50 |
| WDX270... | 0,25 | WDX610... | 1,40 |
| WDX275... | 0,20 | WDX620... | 1,30 |
| WDX280... | 0,15 | WDX630... | 1,20 |
| WDX285... | 0,10 | WDX640... | 1,00 |
| WDX290... | 1,00 | WDX650... | 0,90 |
| WDX295... | 0,95 | WDX660... | 0,70 |
| WDX300... | 0,90 | WDX670... | 0,60 |
| WDX310... | 0,80 | WDX680... | 0,50 |
| WDX320... | 0,70 | | |


Recommended conditions - reduce feed rate to 30 %

## Turning by Lathes

Outer turning (max. 2xD)



Inner turning (max. 2xD)



Recommended conditions - reduce feed rate to 50 %






● = Euro stock

# Eccentric Sleeve **WAS** Type

The Eccentric Sleeve WAS Type, exclusively designed for "SumiDrill" WDX Type, provides up to ± 0,3 mm of hole size adjustment.







## Dimensions

## Parts

Dimensions (mm)

| Cat. No. | Stock | DCB | DCON | BDX | LS | L2 | L3 | L4 | Diameter Adjustment Range (max.) | Screw | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|
| WAS 2025-48 | ● | 20 | 25 | 33 | 43 | 5 | 32 | 5 | +0,3 – -0,2 | BT306 | LH015 |
| WAS 2532-60 | ● | 25 | 32 | 42 | 60 | 7 | 46 | 6 | +0,3 – -0,3 | BT406 | LH020 |
| WAS 3240-70 | ● | 32 | 40 | 55 | 70 | 7 | 57 | 6 | +0,3 – -0,3 | BT408 | LH020 |
| WAS 4050-85 | ● | 40 | 50 | 60 | 70 | 7 | 54 | 6 | +0,5 – -0,5 | BT408 | LH020 |

## Diameter Adjustment




Note 1: The dial is for reference purposes. Always measure the actual drilling diameter and adjust accordingly.
Note 2: Not usable with collet chuck type holders. Only use with a side-locking holder like Weldon.

# PDL Type / PCT Type





## Description

The tool cuts in the Z axis direction where tool rigidity is highest, allowing high efficiency roughing for aeronautic components and dies with long tool overhang must be used to machine deep holes and pockets.

## Characteristics

- The flat cutting edge design produces near-flat bottom profiles to reduce depth of cut variation during finishing.
- All sizes come with an air hole for supplying coolant internally to improve chip evacuation.
- Durable body with special surface treatment offers improved tool life and reliability.
- The tools use SumiDrill WDX type inserts for handling a wide range of work materials, from steel to non-ferrous metals and exotic alloys.


- The PDL type has a central insert making it possible to make radial cuts beyond the tool's radius, pitch feed cutting, and drilling. (Pocket milling, etc.)





Keep the value of $P_f$ for PDL type tools to less than 70 % of the tool diameter (DC).



- Although the PCT type has limited radial cutting ability, the tool has many effective teeth enabling it to perform high feed cutting. (Medium finishing of corners, hole expansion, deep grooving, etc.)





Keep the value of $P_f$ for PCT type tools to less than 50 % of the tool diameter (DC).
For $a_e$ refer to the dimension under "$a_e$ max" in the stock / dimensions tables titled "Holders Max, Depth: 3D/5D".




## Application examples

**PDL Pocketing**
Work Material: Ti Alloy



Tool: PDL400D2S40 (Ø 40)
Insert: WDXT125012-G
Grade: ACK300
Cutting Conditions:
$v_c$ = 40 m/min
$f$ = 0,07 mm/rev
($v_f$ = 22,3 mm/min)
$P_f$ = 25 mm

**PCT Corner Finishing**
Work Material: Ti Alloy




Tool:
PCT320D3S32 (Ø 32)
PCT250D3S25 (Ø 25)
PCT200D3S20 (Ø 20)
Grade: ACK300
Insert:
WDXT094008-G
WDXT073506-G
WDXT063006-G
Cutting Conditions:
$v_c$ = 50 m/min
$f_t$ = 0,08 mm/tooth
($v_f$ = 80–127 mm/min)
$a_e$ = 3,2–6,5 mm

**PCT Grooving**
Work Material: Ti Alloy




Tool: PCT320D5S32 (Ø 32)
Insert: WDXT094008-G
Grade: ACK300
Cutting Conditions:
$v_c$ = 40 m/min
$f_t$ = 0,07 mm/tooth
($v_f$ = 56 mm/min)
$P_f$ = 5,0 mm

**PDL Drilling**
Work Material: X4 CrNiMo 17 12 2




Tool: PDL200D3S25 (Ø 20)
Insert: WDXT063006-G
Grade: ACP300
Cutting Conditions:
$v_c$ = 180 m/min
$f$ = 0,10 mm/rev
($v_f$ = 286 mm/min)
DC = 20 mm

**PCT Aeronautic Components**
Work Material: X5 CrNi 18 10



Tool: PCT320D3S32 (Ø 32)
Insert: WDXT094008-G
Grade: ACP300
Cutting Conditions:
$v_c$ = 180 m/min
$f_t$ = 0,15 mm/tooth
($v_f$ = 537 mm/min)
$a_e$ = 7,0 mm, $P_f$ = 5,0 mm

**PCT Machine Components**
Work Material: 34 Cr Ni 4



Tool: PCT200D5S20 (Ø 20)
Insert: WDXT063006-G
Grade: ACK300
Cutting Conditions:
$v_c$ = 150 m/min
$f_t$ = 0,15 mm/tooth
($v_f$ = 716 mm/min)
$a_e$ = 3,5 mm





● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

# Indexable Plunge Drill
# PDL Type (2D, 3D)



| 2D | 3D | Carbon Steel, Alloy Steel C≤0,28% | Carbon Steel, Alloy Steel C>0,28% | Tempered Steel | Hardened Steel HRC≤45 | Hardened Steel HRC>45 | Stainless Steel | Ti Alloy | Heat Resistant Alloy | Cast iron | Ductile Cast Iron | Al Alloy | Cu Alloy | Composite CFRP * |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| W | | | | | | | | | | | | | | |

Fig 1






Fig 2




## Holder (Max $a_p$: 2D)

| Cat. No. | Stock | Dimensions (mm) DC | OAL | LU | LUX | LPR | LS | DCON | DCSFMS | Applicable Insert | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|
| PDL 160D2S20 | ● | 16,0 | 94 | 32 | 35 | 50 | 44 | 20 | 28 | WDXT052504 | 1 |
| 200D2S25 | ● | 20,0 | 114 | 40 | 43 | 58 | 56 | 25 | 33 | WDXT063006 | |
| 250D2S25 | ● | 25,0 | 127 | 50 | 53 | 71 | 56 | 25 | 37 | WDXT073506 | |
| PDL 320D2S40 | ● | 32,0 | 162 | 64 | 68 | 92 | 70 | 40 | 54 | WDXT094008 | 2 |
| 400D2S40 | ● | 40,0 | 185 | 80 | 85 | 115 | 70 | 40 | 54 | WDXT125012 | |


## Holder (Max $a_p$: 3D)

| Cat. No. | Stock | Dimensions (mm) DC | OAL | LU | LUX | LPR | LS | DCON | DCSFMS | Applicable Insert | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|
| PDL 160D3S20 | ● | 16,0 | 110 | 48 | 51 | 66 | 44 | 20 | 28 | WDXT052504 | 1 |
| 200D3S25 | ● | 20,0 | 134 | 60 | 63 | 78 | 56 | 25 | 33 | WDXT063006 | |
| 250D3S25 | ● | 25,0 | 152 | 75 | 78 | 96 | 56 | 25 | 37 | WDXT073506 | |
| PDL 320D3S40 | ● | 32,0 | 194 | 96 | 100 | 124 | 70 | 40 | 54 | WDXT094008 | 2 |
| 400D3S40 | ● | 40,0 | 225 | 120 | 125 | 155 | 70 | 40 | 54 | WDXT125012 | |

## Spare Parts

| Screw | Wrench | Wrench | N·m | Applicable Holders |
|---|---|---|---|---|
| BFTX0204N | TRX06 | – | 0,5 | PDL 160 D2 S20, PDL 160 D3 S20<br>PCT 160 D3 S16, PCT 160 D5 S16 |
| BFTY02206 | – | TRD07 | 1,0 | PDL 200 D2 S25, PDL 200 D3 S25<br>PCT 200 D3 S20, PCT 200 D5 S20 |
| BFTX02506N | – | TRD08 | 1,5 | PDL 250 D2 S25, PDL 250 D3 S25<br>PCT 250 D3 S25, PCT 250 D5 S25 |
| BFTX03584 | – | TRD15 | 3,5 | PDL 320 D2 S40, PDL 320 D3 S40<br>PCT 320 D3 S32, PCT 320 D5 S32 |
| BFTX0511N | – | TRD20 | 5,0 | PDL 400 D2 S40, PDL 400 D3 S40<br>PCT 400 D3 S42, PCT 400 D5 S42 |

## Notes about Mounting Inserts




PDL type: Inserts can be used on either the centre or the outside.
Inserts used on the outside cannot be used in the centre,. Similarly, inserts used in the centre cannot be used on the outside.
PCT type: 2 corners can be used only for the outer inserts.


# Indexable Plunge Mill
# PCT Type (3D, 5D)



| 3D | 5D | Carbon Steel, Alloy Steel C≤0,28% | Carbon Steel, Alloy Steel C>0,28% | Tempered Steel | Hardened Steel HRC≤45 | Hardened Steel HRC>45 | Stainless Steel | Ti Alloy | Heat Resistant Alloy | Cast iron | Ductile Cast Iron | Al Alloy | Cu Alloy | Composite CFRP * |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ◎ | ◎ | | | ○ | | ○ | ◎ | | ◎ | ◎ | ◎ | ○ | | |

* CFRP (Carbon Fibre Reinforced Plastic)

Fig 3




## Holder (Max $a_p$: 3D)

| Cat. No. | Stock | Dimensions (mm) DC | $a_e$ max | OAL | LH | LS | DCON | No. of teeth | Applicable Insert | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|
| PCT 160D3S16 | ● | 16,0 | 4,0 | 123 | 53 | 70 | 16 | 2 | WDXT052504 | 3 |
| 200D3S20 | ● | 20,0 | 5,0 | 145 | 65 | 80 | 20 | 2 | WDXT063006 | |
| 250D3S25 | ● | 25,0 | 6,5 | 160 | 80 | 80 | 25 | 2 | WDXT073506 | |
| 320D3S32 | ● | 32,0 | 8,5 | 191 | 101 | 90 | 32 | 2 | WDXT094008 | |
| 400D3S42 | ● | 40,0 | 11,0 | 225 | 125 | 100 | 42 | 3 | WDXT125012 | |


## Holder (Max $a_p$: 5D)

| Cat. No. | Stock | Dimensions (mm) øD | $a_e$ max | OAL | LH | LS | DCON | No. of teeth | Applicable Insert | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|
| PCT 160D5S16 | ● | 16,0 | 4,0 | 155 | 85 | 70 | 16 | 2 | WDXT052504 | 3 |
| 200D5S20 | ● | 20,0 | 5,0 | 185 | 105 | 80 | 20 | 2 | WDXT063006 | |
| 250D5S25 | ● | 25,0 | 6,5 | 210 | 130 | 80 | 25 | 2 | WDXT073506 | |
| 320D5S32 | ● | 32,0 | 8,5 | 255 | 165 | 90 | 32 | 2 | WDXT094008 | |
| 400D5S42 | ● | 40,0 | 11,0 | 305 | 205 | 100 | 42 | 3 | WDXT125012 | |

## Inserts


(mm)

Fig. 4





**L** Type
Excellent chip control at low feed rates

Fig. 5




**G** Type
General purpose chipbreaker

Fig. 6




**H** Type
Strong cutting edge at higher feed rates

| Application | Coated | | | |
|---|---|---|---|---|
| High Speed / Light Cutting | | | | N |
| General Purpose | | M | | |
| Roughing | | PM | K | |

| Cat. No. | ACP100 | ACP300 | ACK300 | DL1500 | Fig. | Dimensions (mm) W1 | Thickness | RE | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|
| WDXT 052504-L | ❍ | ● | ● | | 4 | 5,0 | 2,5 | 0,4 | PDL160D2S20<br>PDL160D3S20<br>PCT160D3S16<br>PCT160D5S16 |
| 052504-G | ● | ● | ● | ● | 5 | | | | |
| 052504-H | ● | ● | ● | | 6 | | | | |
| WDXT 063006-L | ● | ● | ● | | 4 | 6,0 | 3,0 | 0,6 | PDL200D2S25<br>PDL200D3S25<br>PCT200D3S20<br>PCT200D5S20 |
| 063006-G | ● | ● | ● | ● | 5 | | | | |
| 063006-H | ● | ● | ● | | 6 | | | | |
| WDXT 073506-L | ● | ● | ● | | 4 | 7,5 | 3,5 | 0,6 | PDL250D2S25<br>PDL250D3S25<br>PCT250D3S25<br>PCT250D5S25 |
| 073506-G | ● | ● | ● | ● | 5 | | | | |
| 073506-H | ● | ● | ● | | 6 | | | | |
| WDXT 094008-L | ● | ● | ● | | 4 | 9,6 | 4,0 | 0,8 | PDL320D2S40<br>PDL320D3S40<br>PCT320D3S32<br>PCT320D5S32 |
| 094008-G | ● | ● | ● | ● | 5 | | | | |
| 094008-H | ● | ● | ● | | 6 | | | | |
| WDXT 125012-L | ● | ● | ● | | 4 | 12,4 | 5,0 | 1,2 | PDL400D2S40<br>PDL400D3S40<br>PCT400D3S42<br>PCT400D5S42 |
| 125012-G | ● | ● | ● | ● | 5 | | | | |
| 125012-H | ● | ● | ● | | 6 | | | | |

## Identification Details

PCT, PDL Type

**PCT 250 D3 S25**


- 250: Tool Diameter (Ø 25,0)
- D3: Max Depth L/D (3D)
- S25: Shank Size (Ø 25,0)

PCT, PDL Type Insert Identification

**WDXT 07 35 06 -G**

- 07: Width Across Flats (7,5)
- 35: Thickness x 10 (3,5)
- 06: Corner Radius x 10 (R0,6)
- -G: Breaker Type

# Recommended Cutting Conditions
# PDL Type / PCT Type




## Recommended Cutting Conditions (2D)

[ min. - **optimal** - max. ]

| ISO | Work material | Hardness (HB) | Chip breaker & Grade | | Cutting Speed Vc (m/min) | PDL Type: f (mm/rev) Ø 16,0 | Ø 20,0–25,0 | Ø 32,0 | Ø 40,0 |
|---|---|---|---|---|---|---|---|---|---|
| P | Carbon steel | 125 | G | ACP300 | 120–**180**–240 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,10 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,12 |
| | | 125 | L | ACP300 | 130–**170**–220 | 0,04–**0,08**–0,12 | 0,04–**0,08**–0,12 | 0,04–**0,08**–0,13 | 0,05–**0,10**–0,15 |
| | | 190 | G | ACP300 | 100–**150**–200 | 0,08–**0,13**–0,24 | 0,08–**0,13**–0,24 | 0,08–**0,14**–0,26 | 0,09–**0,16**–0,29 |
| | | 250 | G | ACP300 | 80–**120**–160 | 0,06–**0,11**–0,18 | 0,06–**0,11**–0,18 | 0,06–**0,12**–0,19 | 0,07–**0,13**–0,22 |
| | | 270 | G | ACP300 | 100–**130**–160 | 0,08–**0,13**–0,22 | 0,08–**0,13**–0,22 | 0,08–**0,14**–0,23 | 0,09–**0,16**–0,26 |
| | | 300 | G | ACP300 | 70–**100**–140 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |
| | Low alloyed steel | 180 | L | ACP300 | 100–**140**–180 | 0,05–**0,08**–0,14 | 0,05–**0,08**–0,14 | 0,05–**0,08**–0,16 | 0,06–**0,09**–0,17 |
| | | 275 | G | ACP300 | 80–**120**–160 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |
| | | 300 | G | ACP300 | 75–**110**–140 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |
| | | 350 | G | ACP300 | 60–**85**–110 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |
| | High alloyed steel | 200 | G | ACP300 | 100–**130**–160 | 0,08–**0,13**–0,24 | 0,08–**0,13**–0,24 | 0,08–**0,14**–0,26 | 0,09–**0,16**–0,29 |
| | | 325 | G | ACP300 | 80–**100**–120 | 0,06–**0,11**–0,18 | 0,06–**0,11**–0,18 | 0,06–**0,12**–0,19 | 0,07–**0,13**–0,22 |
| M | Stainless steel, martensitic / ferritic | 200 | G | ACP300 | 100–**140**–180 | 0,06–**0,11**–0,18 | 0,06–**0,11**–0,18 | 0,06–**0,12**–0,19 | 0,07–**0,13**–0,22 |
| | Stainless steel, martensitic / tempered | 240 | G | ACP300 | 90–**120**–150 | 0,06–**0,11**–0,18 | 0,06–**0,11**–0,18 | 0,06–**0,12**–0,19 | 0,07–**0,13**–0,22 |
| | Stainless steel, austenitic / quenched | 180 | G | ACP300 | 100–**140**–180 | 0,06–**0,08**–0,18 | 0,06–**0,11**–0,18 | 0,06–**0,12**–0,19 | 0,07–**0,13**–0,22 |
| | Stainless steel, austenitic / ferritic (Duplex) | 230 | G | ACP300 | 80–**120**–150 | 0,04–**0,08**–0,18 | 0,06–**0,11**–0,18 | 0,06–**0,12**–0,19 | 0,07–**0,13**–0,22 |
| K | Cast iron (GG) | 180 | H | ACK300 | 120–**160**–200 | 0,09–**0,20**–0,32 | 0,10–**0,22**–0,36 | 0,11–**0,24**–0,39 | 0,12–**0,26**–0,44 |
| | Nodular cast iron (GGG) | 260 | H | ACP300 | 90–**120**–150 | 0,09–**0,20**–0,32 | 0,10–**0,22**–0,36 | 0,11–**0,24**–0,39 | 0,12–**0,26**–0,44 |
| S | Heat resistant alloy | 200 | G | ACP300 | 25–**50**–70 | 0,06–**0,11**–0,18 | 0,06–**0,11**–0,18 | 0,06–**0,12**–0,19 | 0,07–**0,13**–0,22 |
| N | Aluminium alloy | | G | DL1500 | 200–**260**–320 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |
| | Copper alloy | | G | DL1500 | 180–**230**–280 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |

## Recommended Cutting Conditions (3D)

[ min. - **optimal** - max. ]

| ISO | Work material | Hardness (HB) | Chip breaker & Grade | | Cutting Speed Vc (m/min) | PDL Type: f (mm/rev) / PCT Type: $f_t$ (mm/tooth) Ø 16,0 | Ø 20,0–25,0 | Ø 32,0 | Ø 40,0 |
|---|---|---|---|---|---|---|---|---|---|
| P | Carbon steel | 125 | G | ACP300 | 120–**180**–240 | 0,05–**0,07**–0,10 | 0,05–**0,07**–0,10 | 0,05–**0,08**–0,11 | 0,05–**0,08**–0,12 |
| | | 125 | L | ACP300 | 130–**170**–220 | 0,04–**0,07**–0,10 | 0,04–**0,07**–0,10 | 0,04–**0,08**–0,11 | 0,05–**0,09**–0,12 |
| | | 190 | G | ACP300 | 100–**150**–200 | 0,08–**0,12**–0,20 | 0,08–**0,12**–0,20 | 0,08–**0,13**–0,22 | 0,09–**0,14**–0,24 |
| | | 250 | G | ACP300 | 80–**120**–160 | 0,06–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,07–**0,12**–0,18 |
| | | 270 | G | ACP300 | 100–**130**–160 | 0,08–**0,12**–0,18 | 0,08–**0,12**–0,18 | 0,08–**0,13**–0,19 | 0,09–**0,14**–0,22 |
| | | 300 | G | ACP300 | 70–**100**–140 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,06–**0,11**–0,15 | 0,07–**0,12**–0,17 |
| | Low alloyed steel | 180 | L | ACP300 | 100–**140**–180 | 0,05–**0,07**–0,12 | 0,05–**0,07**–0,12 | 0,05–**0,07**–0,13 | 0,06–**0,07**–0,15 |
| | | 275 | G | ACP300 | 80–**120**–160 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,06–**0,11**–0,15 | 0,07–**0,12**–0,17 |
| | | 300 | G | ACP300 | 75–**110**–140 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,06–**0,11**–0,15 | 0,07–**0,12**–0,17 |
| | | 350 | G | ACP300 | 60–**85**–110 | 0,06–**0,10**–0,14 | 0,06–**0,10**–0,14 | 0,06–**0,11**–0,15 | 0,07–**0,12**–0,17 |
| | High alloyed steel | 200 | G | ACP300 | 100–**130**–160 | 0,08–**0,12**–0,20 | 0,08–**0,12**–0,20 | 0,08–**0,13**–0,22 | 0,09–**0,14**–0,24 |
| | | 325 | G | ACP300 | 80–**100**–120 | 0,06–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,07–**0,12**–0,18 |
| M | Stainless steel, martensitic / ferritic | 200 | G | ACP300 | 100–**140**–180 | 0,06–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,07–**0,12**–0,18 |
| | Stainless steel, martensitic / tempered | 240 | G | ACP300 | 90–**120**–150 | 0,06–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,07–**0,12**–0,18 |
| | Stainless steel, austenitic / quenched | 180 | G | ACP300 | 100–**140**–180 | 0,06–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,07–**0,12**–0,18 |
| | Stainless steel, austenitic / ferritic (Duplex) | 230 | G | ACP300 | 80–**120**–150 | 0,04–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,07–**0,12**–0,18 |
| K | Cast iron (GG) | 180 | H | ACK300 | 120–**160**–200 | 0,09–**0,18**–0,27 | 0,10–**0,20**–0,30 | 0,11–**0,22**–0,32 | 0,12–**0,24**–0,36 |
| | Nodular cast iron (GGG) | 260 | H | ACP300 | 90–**120**–150 | 0,09–**0,18**–0,27 | 0,10–**0,20**–0,30 | 0,11–**0,22**–0,32 | 0,12–**0,24**–0,36 |
| S | Heat resistant alloy | 200 | G | ACP300 | 25–**50**–70 | 0,06–**0,10**–0,15 | 0,06–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,07–**0,12**–0,18 |
| N | Aluminium alloy | | G | DL1500 | 200–**260**–320 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |
| | Copper alloy | | G | DL1500 | 180–**230**–280 | 0,06–**0,11**–0,17 | 0,06–**0,11**–0,17 | 0,06–**0,12**–0,18 | 0,07–**0,13**–0,20 |

## Recommended Cutting Conditions (5D)


[ min. - **optimal** - max. ]

| ISO | Work material | Hardness (HB) | Chip breaker & Grade | | Cutting Speed Vc (m/min) | PCT Type: $f_t$ (mm/tooth) Ø 16,0 | Ø 20,0–25,0 | Ø 32,0 | Ø 40,0 |
|---|---|---|---|---|---|---|---|---|---|
| P | Carbon steel | 125 | G | ACP300 | 120–**180**–240 | 0,05–**0,06**–0,09 | 0,05–**0,06**–0,09 | 0,05–**0,06**–0,09 | 0,05–**0,07**–0,09 |
| | | 125 | L | ACP300 | 130–**170**–220 | 0,04–**0,06**–0,08 | 0,04–**0,06**–0,08 | 0,04–**0,06**–0,08 | 0,05–**0,07**–0,09 |
| | | 190 | G | ACP300 | 100–**150**–200 | 0,07–**0,10**–0,15 | 0,07–**0,10**–0,15 | 0,08–**0,11**–0,17 | 0,09–**0,12**–0,19 |
| | | 250 | G | ACP300 | 80–**120**–160 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,14 |
| | | 270 | G | ACP300 | 100–**130**–160 | 0,07–**0,10**–0,14 | 0,07–**0,10**–0,14 | 0,08–**0,11**–0,15 | 0,09–**0,12**–0,17 |
| | | 300 | G | ACP300 | 70–**100**–140 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,13 |
| | Low alloyed steel | 180 | L | ACP300 | 100–**140**–180 | 0,05–**0,06**–0,09 | 0,05–**0,06**–0,09 | 0,05–**0,06**–0,10 | 0,05–**0,07**–0,11 |
| | | 275 | G | ACP300 | 80–**120**–160 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,13 |
| | | 300 | G | ACP300 | 75–**110**–140 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,13 |
| | | 350 | G | ACP300 | 60–**85**–110 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,13 |
| | High alloyed steel | 200 | G | ACP300 | 100–**130**–160 | 0,07–**0,10**–0,15 | 0,07–**0,10**–0,15 | 0,08–**0,11**–0,17 | 0,09–**0,12**–0,19 |
| | | 325 | G | ACP300 | 80–**100**–120 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,14 |
| M | Stainless steel, martensitic / ferritic | 200 | G | ACP300 | 100–**140**–180 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,14 |
| | Stainless steel, martensitic / tempered | 240 | G | ACP300 | 90–**120**–150 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,14 |
| | Stainless steel, austenitic / quenched | 180 | G | ACP300 | 100–**140**–180 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,14 |
| | Stainless steel, austenitic / ferritic (Duplex) | 230 | G | ACP300 | 80–**120**–150 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,14 |
| K | Cast iron (GG) | 180 | H | ACK300 | 120–**160**–200 | 0,08–**0,15**–0,21 | 0,09–**0,17**–0,23 | 0,09–**0,18**–0,25 | 0,11–**0,20**–0,28 |
| | Nodular cast iron (GGG) | 260 | H | ACP300 | 90–**120**–150 | 0,08–**0,15**–0,21 | 0,09–**0,17**–0,23 | 0,09–**0,18**–0,25 | 0,11–**0,20**–0,28 |
| S | Heat resistant alloy | 200 | G | ACP300 | 25–**50**–70 | 0,05–**0,09**–0,11 | 0,05–**0,09**–0,11 | 0,06–**0,09**–0,12 | 0,06–**0,10**–0,14 |
| N | Aluminium alloy | | G | DL1500 | 200–**260**–320 | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,06–**0,12**–0,18 |
| | Copper alloy | | G | DL1500 | 180–**230**–280 | 0,05–**0,10**–0,15 | 0,05–**0,10**–0,15 | 0,06–**0,11**–0,16 | 0,06–**0,12**–0,18 |

# SUMIBORON SUMIDIA

L1–L32






| | | |
|---|---|---|
| SUMIBORON | **SUMIBORON Series** | L2 |
| Guidance for SUMIBORON Grades | **Coated SUMIBORON Series** | L3 |
| | **Grade Guidance** - Cutting Hardened Steel | L4 |
| | **Grade Guidance** - Cutting Cast Iron | L5 |
| | **Grade Guidance** - Cutting Sintered Components/Titanium Alloy | L6 |
| | **Grade Guidance** - Cutting Rolls/Hard Facing/Heat resistant Alloys | L7 |
| SUMIBORON Inserts | **SUMIBORON Cutting Edge Specification** | L8 |
| | **SUMIBORON Break Master NFV$_{Type}$/NLV$_{Type}$/NSV$_{Type}$** | L10 |
| | **SUMIBORON One-Use Wiper Inserts WG$_{Type}$/WH$_{Type}$** | L11 |
| SUMIBORON Grades | **SUMIBORON BN1000/BN2000** New New | L12 |
| | **Coated SUMIBORON BNC2115/BNC2125/BNC2010/BNC2020** | L14 |
| | **Coated SUMIBORON BNC300/SUMIBORON BN350** | L17 |
| | **SUMIBORON BN7000/BN7115** New | L18 |
| | **Coated SUMIBORON BNC8115/ SUMIBORON BNS8125** New New | L20 |
| | **Coated SUMIBORON BNC500** | L22 |
| SUMIBORON Binderless | **SUMIBORON Binderless NCB100** | L24 |
| SUMIDIA | **Production Process** | L26 |
| SUMIDIA Grades | **SUMIDIA Binderless NPD10/SUMIDIA DA90** | L28 |
| | **SUMIDIA DA1000** | L30 |
| SUMIDIA Inserts | **SUMIDIA NF$_{Type}$** | L30 |
| | **SUMIDIA Break Master NLD$_{Type}$/NGD$_{Type}$** | L31 |
| | **SUMIDIA Break Master L/R DM$_{Type}$** | L32 |








## New generation Sumiboron inserts – an even better way to machine hardened steels



### General


Building on its global success machining hardened steels with Sumiboron inserts the addition of heat and wear resistant coatings to a variety of tough new CBN substrates has resulted in a new generation of high performance grades. With economy in mind the new inserts are multi cornered.
Choose the coated insert suitable for your application and take your hard part machining operations to the new industry standard.
The sintered CBN tool SUMIBORON is mainly used for the machining of ferrous metals due to its low chemical reactivity with iron. There are 4 different classifications of SUMIBORON as follows:

### Classifications / Applications

| Classifications | Structure | Diagram | Grade | Work Material |
|---|---|---|---|---|
| With a high CBN content, where each grain is fused together, this group can be used for the machining of high-hardness materials like cast iron, heat-resistant alloys and sintered alloys. |  |  | BN700 | K (FC) Sintered Alloy S |
| | | | BN7000 | |
| | | | **BN7115** New | Sintered Alloy |
| | | | BN7500 | Sintered Alloy |
| | | | **BNS8115** New | K (FC/FCD) S |
| | | | BNS800 | K (FC) S |
| | |  | **BNC8115** New | K (FC/FCD) S H |
| The group where CBN grains are held together by a special ceramic binder with a strong binding force provides excellent wear resistance and toughness in the machining of hardened steel and cast iron. |  |  | BN1000 | H |
| | | | BN2000 | |
| | | | BN350 | |
| | | | BNX10 | |
| | | | BNX20 | |
| | | | BNX25 | |
| | | | BN500 | K (FC/FCD) |
| SUMIBORON with special ceramic coating.<br>The CBN and coating exhibit the hardness, toughness, thermal resistance and oxidation resistance that tool material requires for excellent cutting performance. |  |  | **BNC2115** New | H |
| | | | **BNC2125** New | |
| | | | BNC2010 | |
| | | | BNC2020 | |
| | | | BNC300 | |
| | | | BNC100 | |
| | | | BNC160 | |
| | | | BNC200 | |
| | | | BNC500 | K (FC) |
| Products containing no binder, with a structure of directly bonded nano-to sub-micron CBN particles which provides excellent hardness and thermal conductivity, making them highly efficient with long tool life when machining exotic alloys such as titanium alloys and cobalt-chrome alloys. |  |  | NCB100 | K (FC) S Cemented Carbide Brittle Materials |

Sintered Alloy  Cemented Carbide  Hard Brittle Material

# Characteristics




New Coated SUMIBORON Series achieving
- higher speed
- higher efficiency and
- higher precision

## General Features


Using a high heat resistant and tough CBN substrate coupled with a special ceramic coating, this series caters to a wide variety of applications with improved precision and longer tool life as compared to conventional CBN.

There is a comprehensive lineup of economical and easy-to-use insert selection, such as the cost effective double-sided, multi-cornered, one-use type inserts.

## Features




## Cutting Edge Management




The edge numbers are still visible after machining, which makes the management of used cutting edges easy.

# Grade Guidance

## H Hardened Steel Machining

### Advantages of Using CBN

In terms of cost investment, it is much lower in machine cost and overhead cost due to the fact that a CNC lathe is cheaper than a grinding machine.
As for the quality of finish, inserts can machine different profiles and the finishing is also commendable as compared to grinding.
Environmentally, sludge treatment for grinding is a hazard to the environment but for turning, the chips can be collected and recycled.


### Recommended Grades

| | Grade | Binder | CBN Content (%) | Grain Size (µm) | Hardness HV (GPa) | TRS (GPa) | Main Coating Components | Coating Thickness (µm) | Features |
|---|---|---|---|---|---|---|---|---|---|
| Coated | New BNC2115 | TiN | 60–65 | 3 | 31–33 | 1,3–1,4 | TiAlSiN Super Multi-layered Coating | 3 | Maintains excellent surface roughness thanks to coating with high notch wear resistance and tough CBN substrate. |
| | New BNC2125 | TiN | 65–70 | 4 | 33–35 | 1,5–1,6 | TiAlSiN Super Multi-layered Coating | 3 | Along with a tough CBN substrate, the coating combines wear resistance and toughness to achieve even more stable machining. |
| | BNC2010 | TiCN | 50–55 | 2 | 30–32 | 1,1–1,2 | TiCN Multiple Layers | 2 | Improved wear resistance from coating and substrate, achieves excellent and consistent surface finish. |
| | BNC2020 | TiN | 70–75 | 5 | 34–36 | 1,4–1,5 | TiCN Multiple Layers | 2 | Utilising a tough substrate along with a highly wear-resistant and adhesive coating layer, to achieve long tool life in general-purpose to high-efficiency machining. |
| | BNC300 | TiN | 60–65 | 1 | 33–35 | 1,5–1,6 | TiAlN | 1 | Suitable for finishing work materials combining continuous and interrupted cutting. |
| | BNC100 | TiN | 40–45 | 1 | 29–32 | 1,0–1,1 | TiAlN/TiCN | 3 | Suitable for high-speed finishing thanks to highly wear-resistant coating. |
| | BNC160 | TiN | 60–65 | 3 | 31–33 | 1,2–1,3 | TiAlN/TiCN | 3 | Achieves stable, high-precision finishing of hardened steel. |
| | BNC200 | TiN | 65–70 | 4 | 33–35 | 1,4–1,5 | TiAlN | 3 | Provides long tool life thanks to tough substrate and highly wear-resistant coating. |
| | New BNC8115 | Al Alloy | 85–90 | 8 | 39–42 | 0,95–1,15 | TiAlN | 2 | Grade with 100% solid CBN structure, using PVD coating with excellent wear resistance to enable roughing operations. |
| Uncoated | BN1000 | TiCN | 40–45 | 1 | 27–31 | 0,9–1,0 | – | – | Achieves ultimate wear and fracture resistance. Suitable for high-speed cutting. |
| | BN2000 | TiN | 50–55 | 2 | 31–34 | 1,1–1,2 | – | – | General-purpose grade for hardened steel machining with a high degree of fracture and wear resistance. |
| | BNX20 | TiN | 55–60 | 3 | 31–33 | 1,0–1,1 | – | – | Achieves excellent crater wear resistance. Suitable for high-efficiency cutting under high-temperature conditions. |
| | BN350 | TiN | 60–65 | 1 | 33–35 | 1,5–1,6 | – | – | Achieves ultimate cutting edge strength. Suitable for heavy interrupted cutting. |
| | BNX10 | TiCN | 40–45 | 3 | 27–31 | 0,9–1,0 | – | – | Excellent wear resistance. Suited to continuous high-speed cutting. |
| | BNX25 | | | | 29–31 | 1,0–1,1 | – | – | High efficiency cutting (continuous-interrupted). Excellent fracture resistance in interrupted cutting at high cutting speed. |

### Application Range


#### Coated SUMIBORON

● Induction Hardened Steel (C45, C55, etc.), Carburised Steel





#### Uncoated SUMIBORON

● Induction Hardened Steel (C45, C55, etc.), Carburised Steel




● Die Steel (X155CrVMo12-1, X40CrVMo5-1, etc.), HSS




# K Cast Iron Machining

## Advantages of Using CBN

Following charts show merits of using CBN in cast iron machining compared with conventional tools, such as carbide, cermet or ceramics. SumiBoron performs longer tool life than conventional tools in high speed machining and brings higher efficiency and superior precision.


### High Speed Machining

● Grey Cast Iron





### High Speed Machining

● Ductile Cast Iron




### High Precision Machining





## Recommended Grades


| | Grade | Binder | CBN Content (%) | Grain Size (µm) | Hardness HV (GPa) | TRS (GPa) | Main Coating Components | Coating Thickness (µm) | Features |
|---|---|---|---|---|---|---|---|---|---|
| Uncoated | New BNS8125 | Al Alloy | 85–90 | 8 | 39–42 | 0,95–1,15 | – | – | Grade with 100% solid CBN structure that exhibits excellent wear and fracture resistance. |
| | BNS800 | Al Alloy | 85–90 | 8 | 39–42 | 0,9–1,1 | – | – | Grade with solid CBN structure that has excellent thermal shock resistance. |
| | BN7000 | Co Compounded | 90–95 | 2 | 41–44 | 1,8–1,9 | – | – | Grade exhibiting wear and fracture resistance in cutting of cast iron and exotic alloys. |
| | BN500 | TiC | 65–70 | 6 | 32–34 | 1,0–1,1 | – | – | Grade optimised for cast iron cutting. Provides superior wear and fracture resistance. |
| Coated | New BNC8115 | Al Alloy | 85–90 | 8 | 39–42 | 0,95–1,15 | TiAlN | 2 | Grade with 100% solid CBN structure, using PVD coating with excellent wear resistance that enables roughing operations. |
| | BNC500 | TiC | 85–90 | 4 | 32–34 | 1,1–1,2 | TiAlN | 3 | Suitable for machining of hard-to-cut cast iron, thanks to the highly wear-resistant substrate and coating. |

## Application Range

● Grey Cast Iron




● Ductile Cast Iron




● Special Cast Iron

| Work Material | Hardness (HB) | Work Material Structure | Examples | Cutting Speed $v_c$ (m/min) 100 200 300 350 400 500 |
|---|---|---|---|---|
| Ni-resistant cast iron | 150–200 | Austenite | Piston ring | BNC500 |
| High-Cr cast iron | 250–350 | Austenite | Pump part | BNS8125/BNS800 |
| FCV (CGI) | 400–580 | Pearlite | Engine blocks Cylinder heads Brake discs | BNC500 |

# Grade Guidance



## Sintered Component Machining

### Advantages

SUMIBORON has much smaller edge wear than cemented carbide or cermet. It also has better wear resistance and can form a shape edge easily. SUMIBORON is able to prevent burrs and chipping on the edges of the workpiece, achieving good machined precision and surface roughness.


### Recommended Grades

| | Grade | Binder | CBN Content (%) | Grain Size (μm) | Hardness HV (GPa) | TRS* (GPa) | Main Coating Components | Coating Thickness (μm) | Features |
|---|---|---|---|---|---|---|---|---|---|
| Uncoated | BN7115 New | Co Compounded | 90–95 | 1 | 41–44 | 2,2–2,3 | – | – | Grade balancing ultimate cutting edge sharpness with fracture resistance, suitable for finishing of sintered alloy. |
| | BN7500 | Co Compounded | 90–95 | 1 | 41–44 | 2,0–2,1 | – | – | Grade maintaining good cutting edge sharpness, suitable for finishing of sintered alloy. |
| | BN7000 | Co Compounded | 90–95 | 2 | 41–44 | 1,8–1,9 | – | – | Grade exhibiting improved wear and fracture resistance in roughing of sintered materials. |


*Tranverse rupture strength measured with test piece equivalent to insert CBN layer.

### Application Range

● General Sintered Alloy




● High Density/Sintered Alloy




## S Titanium Alloy Cutting

### Advantages


SUMIBORON enables high speed machining of titanium alloys that were previously difficult to machine with conventional tools, drastically improving machining efficiency.

### Recommended Grades

| Grade | Binder | CBN Content (%) | Grain Size (μm) | Hardness HV (GPa) | TRS* (GPa) | Main Coating Components | Coating Thickness (μm) | Features |
|---|---|---|---|---|---|---|---|---|
| NCB100 | – | 100 | ≤ 0,5 | 51–54 | 1,8–1,9 | – | – | Ideal for high-efficiency finishing of titanium alloy. |

*Tranverse rupture strength measured with test piece equivalent to insert CBN layer.

### Cutting Performance




Work Material: Titanium Alloy (Ti-6Al-4V)
Insert: CNGA120408
Cutting Data: $v_c$ = 150 m/min, f = 0,15 mm/rev, $a_p$ = 0,5 mm
wet (high pressure coolant)

### Recommended Cutting Conditions


| Work Material | | Grade | Recommended Cutting Conditions | | |
|---|---|---|---|---|---|
| Composition | Hardness (HRC) | | Cutting Speed $v_c$ (m/min) 50 100 150 200 250 300 | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm) |
| Ti-6Al-4V | 30–35 | NCB100 | ——— | 0,05–0,15–0,20 | 0,10–0,30–0,50 |
| Ti-5Al-5V-5Mo-3Cr | 32–38 | NCB100 | ——— | 0,05–0,10–0,20 | 0,10–0,30–0,50 |
| Ti-10V-2Fe-3Al | 32–38 | NCB100 | ——— | 0,05–0,10–0,20 | 0,10–0,30–0,50 |

## Roll Machining

### Advantages

SUMIBORON enables the machining of high-hardness rolls that were previously difficult to machine with conventional tools, drastically improving machining efficiency.

### Recommended Grades




Finishing to Medium to Roughing

Rolled stand (example of rolled steel bar)

### Recommended Cutting Conditions


| Work Material | | Recommended Cutting Conditions | | |
|---|---|---|---|---|
| Category | Hardness (HS) | Cutting Speed $v_c$ (m/min) 20 40 60 80 100 120 140 | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm) |
| Adamite | ≥ 40 | | 0,1–0,5 | 0,2–3,0 |
| Chilled cast iron | ≥ 60 | | 0,1–0,5 | 0,2–3,0 |
| High-alloy cast iron | ≥ 60 | | 0,1–0,5 | 0,2–3,0 |
| HSS | ≥ 70 | | 0,1–0,4 | 0,1–3,0 |

## Hard Facing Alloy Machining

### Advantages

SUMIBORON enables the machining of high-hardness facing alloys that were previously difficult to machine with conventional tools, drastically improving machining efficiency. The first recommended grade is BN7000, followed by BNS8125.

### Cutting Performance




| | |
|---|---|
| Work Material: | Colmomoy No. 6 (Ni-based self-fluxing alloy) |
| Insert: | SNGN090308 |
| Cutting Data: | f = 0,1 mm/rev, $a_p$ = 0,2 mm dry |

BN7000 has a long tool life and minimal wear with high speed cutting.

### Recommended Cutting Conditions


| Work Material | | Recommended Cutting Conditions | | |
|---|---|---|---|---|
| Category | Material | Cutting Speed $v_c$ (m/min) 50 100 200 300 | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm) |
| Ni-based self-fluxing alloy | Colmonoy No. 6 | | 0,05–0,2 | 0,1–3,0 |
| Co-based self-fluxing alloy | Stellite | | 0,05–0,2 | 0,1–1,0 |

## Heat Resistant Alloy Machining

### Advantages

SUMIBORON provides long tool life in the finishing of heat-resistant alloys.

### Recommended Grades




SUMIBORON is best suited for finishing of heat-resistant steel.


### Recommended Cutting Conditions

| Work Material | | Recommended Cutting Conditions | | |
|---|---|---|---|---|
| Category | Material | Cutting Speed $v_c$ (m/min) 50 100 150 200 | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm) |
| Ni-based heat-resistant alloy | Inconel 718 | | 0,05–0,2 | 0,1–1,0 |
| Co-based heat-resistant alloy | Stellite | | 0,05–0,2 | 0,1–1,0 |


## Sumiboron Inserts and Edge Preparation

All SUMIBORON inserts are enhanced with the optimum cutting edge preparation for various grades and geometries (shown on the rigth).
This is to avoid cutting edge fracture caused by the heavy loads generated during the machining of high hardness materials such as Hardened Steel.
As the pioneer of CBN tools „SUMIBORON“, various selection of grades and edge preparation combinations is our strong point for Hardened Steel machining.

Close-up of Cutting Edge




Section A - A‘




### SUMIBORON Insert Cutting Edge Specification

| Series | Work Material | Grade | Negative / Positive | Standard | | | | Low Cutting Force **L** / High Efficiency Type **E** | | | | | Strong Edge Type **H** | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | Identification Code | α | W | Honing | Notation | Identification Code | α | W | Honing | Notation | Identification Code | α | W | Honing |
| Uncoated SUMIBORON | Hardened Steel | BNX10 | Neg./Pos. | T01225 | 25° | 0,12 | No | – | – | – | – | – | – | – | – | – | – |
| | | BNX20 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LT** | T01215* | 15° | 0,12 | No | – | – | – | – | – |
| | | BNX25 | Neg./Pos. | S01725 | 25° | 0,17 | Yes | – | – | – | – | – | – | – | – | – | – |
| | | BN1000 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | – | – | – | – | – | – | – | – | – | – |
| | | BN2000 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LT** | T01215 | 15° | 0,12 | No | **HS** | S01235 | 35° | 0,12 | Yes |
| | | BN350 | Neg. | T01225 | 25° | 0,12 | No | – | – | – | – | – | **HT** | T01235 | 35° | 0,12 | No |
| | | | Pos. | T01235 | 35° | 0,12 | No | | | | | | – | – | – | – | – |
| | Cast Iron / Sintered Alloy / Exotic Alloy | BN700 | Neg./Pos. | T01215 | 15° | 0,12 | No | **LF** | (Sharp edge) | 0° | 0 | No | **HS** | S01225 | 25° | 0,12 | Yes |
| | | BN7000 | Neg./Pos. | T01215 | 15° | 0,12 | No | **LF** | (Sharp edge) | 0° | 0 | No | **HS** | S01225 | 25° | 0,12 | Yes |
| | | BN7115 | Neg./Pos. | T01215 | 15° | 0,12 | No | **LF** | (Sharp edge) | 0° | 0 | No | **HS** | S00525 | 25° | 0,05 | Yes |
| | | | | | | | Yes | **LE** | (Sharp edge) | 0° | 0 | Yes | **US** | S01225 | 25° | 0,12 | Yes |
| | | | | | | | – | **LS** | S00715 | 15° | 0,05 | – | – | – | – | – | – |
| | | BN7500 | Neg./Pos. | T01215 | 15° | 0,12 | No | **LF** | (Sharp edge) | 0° | 0 | No | **HS** | S00525 | 25° | 0,05 | Yes |
| | | | | | | | Yes | **LE** | (Sharp edge) | 0° | 0 | Yes | | | | | |
| | | | | | | | Yes | **LS** | S00715 | 15° | 0,07 | Yes | | | | | |
| | | BNS8125 | Neg. | T02020 | 20° | 0,20 | – | – | – | – | – | – | – | – | – | – | – |
| | | BNS800 | Neg. | T02020 | 20° | 0,20 | No | **LF** | (Sharp edge) | 0° | 0 | No | – | – | – | – | – |
| Coated SUMIBORON | Hardened Steel | BNC2115 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LS** | S00515 | 15° | 0,05 | Yes | **HS** | S01730 | 30° | 0,17 | Yes |
| | | BNC2125 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LS** | S00515 | 15° | 0,05 | Yes | **HS** | S02735 | 35° | 0,27 | Yes |
| | | BNC2010 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LE** | (Sharp edge) | 0° | 0 | Yes | **HS** | S01730 | 30° | 0,17 | Yes |
| | | BNC2020 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LT** | T00515 | 15° | 0,05 | No | **HS** | S02735 | 35° | 0,27 | Yes |
| | | | | | | | | **ES** | S00535 | 35° | 0,05 | Yes | | | | | |
| | | BNC100 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LS** | S01715 | 15° | 0,17 | Yes | – | – | – | – | – |
| | | BNC160 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LS** | S01020 | 20° | 0,10 | Yes | **HS** | S01730 | 30° | 0,17 | Yes |
| | | BNC200 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LS** | S01015 | 15° | 0,10 | Yes | **HS** | S01735 | 35° | 0,17 | Yes |
| | | BNC300 | Neg./Pos. | S01225 | 25° | 0,12 | Yes | **LS** | S00515 | 15° | 0,05 | Yes | **HS** | S01735 | 35° | 0,17 | Yes |
| | Cast Iron | BNC500 | Neg./Pos. | S01215 | 15° | 0,12 | Yes | – | – | – | – | – | **HS** | S01225 | 25° | 0,12 | Yes |
| | Cast Iron, Hardened Steel | BNC8115 | Neg. | S02020 | 20° | 0,20 | Yes | – | – | – | – | – | – | – | – | – | – |
| Binder-less CBN | Cast Iron, Exotic Alloy, Carbide, Cermet | NCB100 | Neg./Pos. | T01215 | 15° | 0,12 | No | – | – | – | – | – | – | – | – | – | – |

* BNX20 Identification code will be T00715 for insers with inscribed circle of less than Ø 4,76.


### Cutting Edge Preparation of Inserts with Wiper / Chipbreakers

| Type | Notation | Edge Specification Identification Code | α | W | Honing | Uncoated SUMIBORON | | | Coated SUMIBORON | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | | BN2000 | BNS8125 | BNS800 | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC500 | BNC8115 |
| Wiper | **WG** | S01215 | 15° | 0,12 | Yes | ● | | | ● | ● | ● | ● | | ● | ● | | |
| | **WH** | S01215 | 15° | 0,12 | Yes | ● | | | ● | ● | ● | ● | | ● | ● | | |
| | **W** | S01215 | 15° | 0,12 | Yes | | | | | | | | | ● | ● | ● | |
| | | S01715 | 15° | 0,17 | Yes | | | | | | | | ● | | | | |
| | | S02020 | 20° | 0,20 | Yes | | | | | | | | | | | | ● |
| | | T02020 | 20° | 0,20 | No | | ● | ● | | | | | | | | | |
| Wiper Sharp Edge | **LFW** | Sharp Edge | 0° | 0 | No | | | ● | | | | | | | | | |
| With Chipbreaker | **N-FV** | – | 0° | 0 | Yes | ● | | | ● | ● | ● | ● | | ● | ● | | |
| | **N-LV** | S00535 | 35° | 0,05 | Yes | ● | | | ● | ● | ● | ● | | ● | ● | | |
| | **N-SV** | S01235 | 35° | 0,12 | Yes | | | | ● | ● | ● | ● | | ● | ● | | |

### Cutting Edge Specification Identification Code

| Notation of Edge Preparation | | | | |
|---|---|---|---|---|
| No. | Standard Type | | | |
| L | Low cutting forces | + | F | Sharp edge |
| E | High efficiency | | E | Honing |
| | | | T | Negative land |
| H | Strong edge type | | S | Negative land + honing |
| WG / WH / W | Wiper | | | |
| N-FV / N-LV N-SV | With Chipbreaker | | | |

### Edge Preparation Identification Code




**S** **0** **1** **2** **2** **5**


**W**: Negative land width **α**: Negative land angle

Cutting edge: **T** - Negative land
**S** - Negative land + **R** - Honing

Example: **S01225**
→ 25°/0,12 mm width negative land with honing

## Insert Types and Cutting Edge Geometries

### Multi Cornered One-Use Type Inserts




■ Characteristics


- One-use type inserts improve machining efficiency by using each cutting edge to its full potential following the numbering system on each cutting edge then throwing the insert away.
- Multi cornered inserts have a single piece of Sumiboron mounted on every useable corner. Single sided inserts use the top corners whilst double sided inserts use both top and bottom corners. Diamond shaped inserts have 4 corners and triangular inserts have 6 corners.
- A variety of Sumiboron coated grades readily replace expensive grinding operations for high precision tolerances outstanding surface finish, heavy interrupted cutting and efficient cost effective machining of hardened parts.

### Cutting Edge Preparation

Machining of Hardened Steel




Sintered Alloy Machining





### One-Use Wiper Insert



■ Characteristics

- New lineup includes:
  **WG** Type ⇨ for low-feed cutting
  **WH** Type ⇨ for high-feed cutting
- SUMIBORON one-use insert with wiper edge for hardened steel machining
- Excellent surface finish similar to grinding
- Improved efficiency with higher speeds and feeds

### Break Master N - FV, N - LV, N - SV




Break Master N-SV Type

■ Characteristics

- N-SV type is perfect for carburised layer removal while N-FV / N-LV types are best suited to finishing of hardened steel.
- First CBN insert to feature an integral chipbreaker
- Ideal for removing carburised layer - can be used on both hardened and unhardened materals.
- Effective chip control solution protects component from swarf damage.


# N-**FV** /N-**LV** /N-**SV**



## Characteristics

- SUMIBORON one-use insert with chipbreaker.
- N-SV type is perfect for carburised layer removal while N-FV/N-LV types are best suited to finishing of hardened steel.
- Breaker included on the CBN edge, chipbreaking effect can be maintained throughout machining process.
- Unique breaker design can be applied to both hardened and non-hardened parts with effective chip control.

## Application Range





N-SV




**N-SV For Carburised Layer Removal**

Ideal for carburised layer removal.





N-LV



**N-LV For Light Cutting**

Excellent chip evacuation under conditions with depth of cut at ≤ 0,3 mm.





N-FV




**N-FV For Finishing**

Excellent chip evacuation under finishing conditions with depth of cut at ≤ 0,2 mm.




## Application Examples

### External Carburised Layer Removal



No constant stopages or incorrect part dimension problem and the chips are small.

Double the tool life of competitor's CBN


Work material: 42CrMo4, Carburised steel (shaft)
Insert: CNGG 120408 N-SV NC4 (BNC200)
Conditions: $v_c$ = 150 m/min, f = 0,15 mm/rev, $a_p$ = 0,5mm, x 2 passes, wet



Break Master N-SV
Tool life = 200 pcs




BNC200 (no breaker)
Tool life = 200 pcs




Comp. CBN (no breaker)
Tool life = 100 pcs

### Carburised Face Layer Removal



Break Master N-SV type improves chip control with increased productivity until the pre-set tool life.




Work material: 42CrMo4 (HRC30-62)
Insert: CNGG 120408 N-SV NC4 (BNC200)
Conditions: $v_c$ = 140 m/min, f = 0,15 mm/rev, $a_p$ = 0,3 mm, wet




## Characteristics

- SUMIBORON one-use insert with wiper edge for hardened steel machining
- Excellent surface finish similar to grinding
- Improved efficiency with higher speeds and feeds
- New lineup includes:
  **WG** type ⇨ for low-feed cutting
  **WH** type ⇨ for high-feed cutting




## Application Range




**WH** type:
→ for high-rigidity workpieces and equipment

**WG** type:
→ for issues of undulation or chatter


## Finished Surface Roughness




The wiper insert offers good finished surface roughness and improved machining efficiency.

| | |
|---|---|
| Work Material: | 15CrMo5 (60 HRC) |
| Insert: | CNGA120408NC4 |
| Cutting Data: | vc = 135 m/min, ap = 0,1 mm, dry |

## Wiper Insert Operation





## Tool-Setup WG / WH Wiper


### CNGA / CCGW / WNGA Type Wiper

1. Use a holder with a 95° approach angle.
2. Tool compensation required.

CNGA / CCGW / WNGA type wiper inserts do not follow the ISO standard. Correction of the tool offset of the cutting edge as explained on the right.




Cutting Edge Position Compensation, Outer Processing





| Nose Radius | Type | X-Direction | Z-Direction |
|---|---|---|---|
| RE 0,4 | WG | -0,02 | -0,02 |
| | WH | -0,06 | -0,06 |
| RE 0,8/1,2 | WG | -0,01 | -0,01 |
| | WH | -0,06 | -0,06 |


### DNGA / DCGW Type Wiper

1. Use a holder with a 93° approach angle.
2. Tool compensation required.


DNGA / DCGW type wiper inserts do not follow the ISO standard. Correction of the tool offset of the cutting edge as explained on the right.
Note: DNGA/DCGW type wiper inserts are only possible for external and internal turning, not for facing.




Cutting Edge Position Compensation, Outer Processing




| Nose Radius | Type | X-Direction | Z-Direction |
|---|---|---|---|
| RE 0,4 | WG | -0,17 | -0,01 |
| | WH | -0,70 | -0,06 |
| RE 0,8 | WG | -0,05 | 0 |
| | WH | -0,58 | -0,05 |



## Uncoated CBN grades for hardened steel machining

### ■ General Features

A new uncoated type of SUMIBORON that has a newly developed high-purity ceramic binder.
Both fracture and wear resistance are combined to achieve a stable tool life in a wide variety of hardened steel machining.


Available in single corner and multi-corner type inserts.

### ■ Characteristics

● BN1000
- Superior high-speed machining grade with the highest wear resistance of any uncoated SUMIBORON.
  Delivers excellent tool life in continuous cutting to light-interrupted cutting.
- Improved fracture resistance while also emphasizing wear resistance.
  Improved hardness and heat resistance from the high-purity TiCN ceramic binder.

● BN2000
- General purpose grade suitable for typical hardened steel machining applications.
  Provides stable tool life in everything from continuous cutting to light-to-medium interrupted cutting.
- High degrees of both fracture resistance and wear resistance.
  Significant improvements in the performance of both by employing a high-purity ceramic binder.
- Stable surface roughness by increasing sharpness (Figure on right).


Sharpness Comparison




Compared to conventional grades, small cutting edge roundness


### ■ Newly Developed High-Purity Ceramic Binder

Conventional Grade




The impurities contained in the ceramic binder for conventional grades cause a weakening in the sintered body and a decrease in heat resistance, which becomes the cause of cracks (chipping) and wear.


BN1000/BN2000





With the newly developed high-purity **ceramic binder**, the BN1000 / BN2000 achieve toughness and improved heat resistance by decreasing impurities to an extreme!

### ■ Recommended Application Range

Continuous Cutting




Interrupted Cutting




### ■ Cutting Conditions

BN1000

| $v_c$ (m/min) | f (mm/rev) | $a_p$ (mm) |
|---|---|---|
| 100 150 200 250 300<br>120 | 0,03–0,15 | 0,03–0,2 |

BN2000


| $v_c$ (m/min) | f (mm/rev) | $a_p$ (mm) |
|---|---|---|
| 50 100 150 200 250<br>80 120 | 0,03–0,2 | 0,0–0,3 |

❄ Coolant ... Continuous cutting: dry or wet
Interrupted cutting: dry


# Uncoated SUMIBORON
# BN1000 / BN2000

## ■ Cutting Performance

BN1000




Wear Resistance Comparison





Work material: 100Cr6 ($H_RC58$-62), Round Bar
Insert: CNGA 120408 NU-2
Cutting data: $v_c$ = 150 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry

BN1000




Chipping Resistance Comparison





Work material: 15CrMo5 ($H_RC58$-62), 8 Grooves
Insert: CNGA 120408 NU-2
Cutting data: $v_c$ = 150 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry

BN2000




Wear Resistance Comparison





Work material: 15CrMo5 ($H_RC58$-62), Round Bar
Insert: CNGA 120408 NU-2
Cutting data: $v_c$ = 100 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry

BN2000




Chipping Resistance Comparison





Work material: 15CrMo5 ($H_RC58$-62), 8 Grooves
Insert: CNGA 120408 NU-2
Cutting data: $v_c$ = 150 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry

## ■ Machining Precision

BN1000




Accuracy Comparison





Work material: 15CrMo5 ($H_RC58$-62), Round Bar Ø 130
Insert: CNGA 120408 NU-2
Cutting data: $v_c$ = 200 m/min, f = 0,1 mm/rev, $a_p$ = 0,1 mm, wet

BN2000



Surface Roughness Comparison




Work material: 15CrMo5 ($H_RC58$-62), Round Bar
Insert: CNGA 120408 NU-2
Cutting data: $v_c$ = 100 m/min, f = 0,08 mm/rev, $a_p$ = 0,2 mm, dry

# BNC2115/BNC2125/BNC2010/BNC2020 New





## General Features

BNC2115/BNC2125 have been added to our coated SUMIBORON series and are our first recommendations for hardened steel machining, for even higher efficiency machining. It's the pinnacle of high accuracy and high efficiency cutting.
In combination with BNC2010/BNC2020, which emphasize stable tool life, they improve productivity in all kinds of hardened steel machining.


## Features

### BNC2115 New




- The definitive grade in high-accuracy machining
  Realises long tool life with excellent surface roughness and stable machining.
- Further maintains excellent surface roughness
  Maintains excellent surface roughness thanks to a coating with high notch wear resistance and tough CBN substrate.

### BNC2125 New



- First recommendation for hardened steel machining
  Superb wear and fracture resistance.
- Achieves long, stable tool life even in high-efficiency and interrupted machining
  Along with a tough CBN substrate, the coating combines wear resistance and toughness to realise stable machining.

### BNC2010




- Grade for high-precision machining with excellent surface roughness and finished surface accuracy
  Grade ideal for high-precision machining, with highly wear-resistant CBN substrate and coating.

### BNC2020




- General-purpose grade suitable for typical hardened steel machining applications
  Achieves further stability in machining of a wide range of hardened steel components.

## Application Range







## Differentiation



## CBN Substrate und Coating Structure

### BNC2115


High-Precision Machining
(Medium- to high-speed)




Thick layer of laminated high-strength TiAlSiN super multi-layered coating and highly heat-resistant TiCN coating. Achieves excellent surface fnish quality with application to a tough substrate.

### BNC2125


General Machining
(Medium- to high-speed)




Thick layer of super-multilayered ultra-fine TiAlBN coating with high strength and high hardness. High performance in a wide range of cutting through application to a tough substrate.

### BNC2010


High-Precision Machining
(Low- to medium-speed)




Laminated high-strength AlCrN multi-layered coating and highly heat-resistant TiCN coating is applied to a highly wear-resistant substrate to maintain excellent surface finish quality.

### BNC2020

General Purpose Machining
(Low to medium speed, unstable cutting)




Application of highly wear-resistant TiAlN coating to a tough substrate. Machining stability in low-rigidity environments and high-load cutting is dramatically improved.

## Recommended Cutting Conditions


| Grade | Cutting Speed $v_c$ (m/min) Min.–**Optimum**–Max. | Feed Rate f (mm/rev) Min.–**Optimum**–Max. | Depth of Cut $a_p$ (min) Min.–**Optimum**–Max. |
|---|---|---|---|
| BNC2115 | 110–**180**–300 | 0,03–**0,10**–0,20 | 0,03–**0,20**–0,35 |
| BNC2125 | 110–**160**–300 | 0,05–**0,20**–0,40 | 0,05–**0,30**–0,50 |
| BNC2010 | 50–**140**–180 | 0,03–**0,10**–0,20 | 0,03–**0,20**–0,35 |
| BNC2020 | 50–**120**–180 | 0,03–**0,20**–0,40 | 0,05–**0,30**–0,50 |
| BNC300 | 50–**100**–150 | 0,03–**0,10**–0,20 | 0,03–**0,20**–0,30 |

# BNC2115/BNC2125/BNC2010/BNC2020

## ■ Cutting Performance


### BNC2115

#### Continuous Cutting, Wear Resistance




| | |
|---|---|
| Work Material: | 16CrMo4 (58–62 HRC) |
| Insert: | DNGA150408NC4 |
| Cutting Data: | $v_c$ = 200 m/min, f = 0,1 mm/rev, $a_p$ = 0,15 mm, wet |


#### Continuous Cutting, Machined Surface Roughness




| | |
|---|---|
| Work Material: | 16CrMo4 (58–62 HRC) |
| Insert: | DNGA150408NC4 |
| Cutting Data: | $v_c$ = 200 m/min, f = 0,1 mm/rev, $a_p$ = 0,15 mm, wet |


### BNC2125

#### Continuous Cutting, Wear Resistance




| | |
|---|---|
| Work Material: | 100Cr6 (58–62 HRC) |
| Insert: | DNGA150408NC4 |
| Cutting Data: | $v_c$ = 150 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, wet |


#### High-Load Cutting, Fracture Resistance




| | |
|---|---|
| Work Material: | 100Cr6 (58–62 HRC) |
| Insert: | DNGA150408NC4 |
| Cutting Data: | $v_c$ = 150 m/min, f = 0,15 mm/rev, $a_p$ = 0,5 mm, 63 m/times, wet |

### BNC2010


#### Continuous Cutting, Machined Surface Roughness




| | |
|---|---|
| Work Material: | 16CrMo4 (58–62 HRC) |
| Insert: | DNGA150408NC4 |
| Cutting Data: | $v_c$ = 120 m/min, f = 0,14 mm/rev, $a_p$ = 0,15mm, wet |

### BNC2020


#### Interrupted Cutting, Fracture Resistance




| | |
|---|---|
| Work Material: | 16CrMo4 with 5 grooves (58–62 HRC) |
| Insert: | DNGA1204012NC4 |
| Cutting Data: | $v_c$ = 130 m/min, f = 0,1 mm/rev, $a_p$ = 0,6 mm, dry |

# Coated SUMIBORON
# BNC300 / BN350

## The ultimate grades BNC300 and BN350 in interrupted machining of hardened steel




## General Features

- BNC300
  CBN substrate that emphasizes on toughness coupled with a highly wear resistant TiAlN based coating layer that has improved adhesion strength. With a good balance of fracture and wear resistance, stable and longer tool life can be achieve in interrupted cut or in a mixture of continuous and interrupted cutting.

- BN350
  SUMIBORON series highest fracture resistance and toughest CBN. Reliable grade for achieving stable tool life in heavy interrupted cutting conditions.

## Characteristics

**BNC300**


- Stable and long tool life in interrupted cutting
  Achieving stable and long tool life in heavy interrupted cutting, with superior fracture resistance.
- Superior dimensional precision
  Good adhesion strength, TiAlN based, high wear resistance coating. Achieving superior dimensional precision even in interrupted cutting.
- Suitable for different types of workpieces
  Achieving significantly longer tool life even on workpieces that have a mixture of continuous and interrupted cutting.

**BN350**

- Stable and long tool life in interrupted cutting
  Stable and long tool life with superior fracture resistance, that prevents fractures which commonly occurs during interrupted cutting.


## Performance

Continuous ~ Light Interrupted Machining
(Frequency of Interruption 50%)




Work material: 15CrMo5 ($H_RC58$-62)
Insert type: CNGA 120408 NC-4
Cutting data: $v_c$ = 120 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry


Heavy Interrupted Machining
(Frequency of Interruption 100%)





Work material: 15CrMo5 ($H_RC58$-62)
Insert type: CNGA 120408 NU-2
Cutting data: $v_c$ = 100 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, dry

## Recommended Application Range

Coated SUMIBORON




Uncoated SUMIBORON





## Recommended Cutting Conditions (BNC300, BN350)

| $v_c$ (m/min) | f (mm/rev) | $d_{oc}$ (mm) |
|---|---|---|
| 50 100 150 200<br>80 120 | 0,03–0,2 | 0,03–0,3 |

Coolant ... Interrupted cutting: dry


SUMIBORON



## General Features

Good wear resistance through high CBN content also delivers superior fracture resistance by increasing the binding strength between CBN particles.
BN7115 provides stable performance for high-speed finishing work and is ideal for finishing of sintered alloys.

New cutting edge treatment with an emphasis on fracture resistance: “US” type chipbreaker now available.




Removal of binder → comparison of CBN particles ‘ binding strength

## Features

**BN7000**


- Achieves high-efficiency machining of sintered alloys of various shapes with a standard and two types of cutting edge variations. Also exhibits high performance for difficult-to-cut materials such as rolls, high speed steel and heat resistive alloys. Exhibits good thermal resistance in high-speed machining of cast iron.

**BN7115** New

- With improved CBN particle/binder boundary strength due to the special binder and improved binding strength between CBN particles thanks to our proprietary sintering process, the edge sharpness in sintered alloy machining is excellent and burrs and tearing are suppressed.

## Application Range

### Sintered Alloy (50–95 HRB/90–200 HV)




## Recommended Cutting Conditions

### Cast Iron


| Work material | Grade | Cutting conditions (min.–optimum–max.) | | |
|---|---|---|---|---|
| | | Cutting speed Vc (m/min) | Feed rate f (mm/rev) | Depth of cut ap (mm) |
| Cast Iron | **BN7000** | 100–**1.000**–2.500 | 0,05–**0,30**–0,60 | 0,05–**0,50**–1,00 |

### Sintered Alloy

| Work material | Grade | Cutting conditions (min.–optimum–max.) | | |
|---|---|---|---|---|
| | | Cutting speed Vc (m/min) | Feed rate f (mm/rev) | Depth of cut ap (mm) |
| General sintered alloy | **BN7115** | 10–**150**–300 | 0,01–**0,08**–0,15 | 0,05–**0,13**–0,25 |
| | BN7000 | 10–**150**–300 | 0,01–**0,15**–0,30 | 0,05–**0,25**–0,50 |
| High-density sintered alloy | **BN7115** | 10–**100**–200 | 0,01–**0,06**–0,12 | 0,05–**0,10**–0,20 |
| | BN7000 | 10–**100**–200 | 0,01–**0,15**–0,30 | 0,05–**0,25**–0,50 |

## Recommended Edge Treatment

**BN7000**





- Negative Land


| Type | α | W (mm) | Honing |
|---|---|---|---|
| Standard | 15° | 0,12 | No |
| **LF** | – | – | No |
| **HS** | 25° | 0,12 | Yes |




**BN7115**





| Type | α° | W (mm) | Honing |
|---|---|---|---|
| Standard | 15° | 0,12 | no |
| **LF** | Standard edge | | no |
| **LE** | Standard edge | | yes |
| **LS** | 15° | 0,07 | yes |
| **HS** | 25° | 0,05 | yes |
| **US** | 25° | 0,12 | yes |




New **US** type emphasises fracture resistance, ideal for heavy interrupted cutting.

## ■ Cutting Performance (Cast Iron)

### ● BN7000 Continuous Cutting (Flank Wear)






Conventional CBN


BN7000

Work material: FC3000 (Pearlite)
Insert: CNGA 120408 NU2
Cutting conditions: $v_c$ = 800 m/min, f = 0,12 mm/rev, $a_p$ = 0,3 mm, wet


## ■ Cutting Performance (Sintered Alloy)


### ● **BN7115** Continuous Cutting (Surface Roughness)





Work material: Sinterred ferrous alloy F-08C2 equivalent (150 HV)
Insert: CNGA 120408 NU2
Cutting conditions: $v_c$ = 200 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, wet

### ● **BN7115** Continuous Cutting (Wear Resistance)




Conventional CBN



**BN7115 Maintains cutting edge line**


Work material: Sinterred ferrous alloy F-08C2 equivalent (150 HV)
Insert: CNGA 120408 NU2
Cutting conditions: $v_c$ = 200 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, wet

### ● **BN7115** Interrupted Cutting (Fracture Resistance)





Work material: Sinterred ferrous alloy FLA-07C2M equivalent (500 HV)
Insert: CNGA 120408 NU2
Cutting conditions: $v_c$ = 175 m/min, f = 0,09 mm/rev, $a_p$ = 0,15 mm, dry

### ● BN7000 Interrupted Cutting (Fracture Resistance)





Work material: Sintered ferrous alloy, SMF4040 equivalent (HRB70, Interrupted Machining)
Insert type: CNGA 120408
Cutting data: $v_c$ = 250 m/min, f = 0,1 mm/rev, $a_p$ = 0,3 mm, wet

# BNC8115/BNS8125 K H New



## General Features

Enables a wide range of machining from roughing to finishing of cast iron, exotic alloy cast iron and hardened steel.
100% solid CBN structure enables depth-of-cut of 0,5 mm and above.



## Features

**BNC8115** New


- PVD coating with excellent wear resistance suppresses flank wear when machining difficult-to-cut cast iron and hardened steel. Ideal for roughing and depth-of-cut of 0,5 to 3,0 mm. Can also be used for roughing and finishing of grey cast iron. Gold-colored coating improves visibility of used corners.

**BNS8125** New

- Optimising the particle size distribution of the CBN particles has resulted in improved chipping resistance and longer life while machining wear resistance during grey cast iron machining.


## Application Range

### Grey Cast Iron





Wet machining is recommendet for grey cast iron. In case of dry machining, our 1st recommendation are BNC8115/ BNS8125 for both roughing and finishing.

### Ductile Cast Iron




### Hardened Steel




## Recommended Cutting Conditions

### Cast Iron (Turning) K

| Work Material | Grade | Cutting Conditions Min.–**Optimum**–Max. | | |
|---|---|---|---|---|
| | | Cutting Speed $v_c$ (m/min) | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm) |
| Grey Cast Iron | BNC8115 | 200–**1.000**–2.000 | 0,10–**0,50**–1,00 | ≤ 4,0 |
| | BNS8125 | 200–**1.000**–2.000 | 0,10–**0,50**–1,00 | ≤ 4,0 |
| Ductile Cast Iron | BNC8115 | 80–**160**–300 | 0,10–**0,30**–0,50 | ≤ 3,0 |
| | BNS8125 | 80–**120**–200 | 0,10–**0,30**–0,50 | ≤ 3,0 |

### Hardened Steel (Turning) H


| Work Material | Grade | Cutting Conditions Min.–**Optimum**–Max. | | |
|---|---|---|---|---|
| | | Cutting Speed $v_c$ (m/min) | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm) |
| Hardened Steel | BNC8115 | 50–**100**–150 | 0,10–**0,25**–0,40 | ≤ 3,0 |

### Cast Iron (Milling) K

| Work Material | Grade | Cutting Conditions Min.–**Optimum**–Max. | | |
|---|---|---|---|---|
| | | Cutting Speed (m/min) | Feed Rate (mm/rev) | Depth of Cut (mm) |
| Grey Cast Iron | BNC8115 | 800–**1.400**–2.000 | 0,10–**0,50**–1,00 | ≤ 4,0 |
| | BNS8125 | 800–**1.400**–2.000 | 0,10–**0,50**–1,00 | ≤ 4,0 |


## ■ BNC8115 Cutting Performance

### ● Wear Resistance (Ductile Cast Iron Machining) K




Work Material: GGG-40.3, (Round Bar)
Insert: SNGN090308
Cutting Conditions: $v_c$ = 300 m/min, f = 0,2 mm/rev, $a_p$ = 0,2 mm, wet


### ● Wear Resistance (Hardened Steel Machining) H




Work Material: SUJ2 58-62 HRC, (Round Bar)
Insert: SNGN090308
Cutting Conditions: $v_c$ = 150 m/min, f = 0,2 mm/rev, $a_p$ = 0,3 mm, wet


## ■ BNS8125 Cutting Performance

### ● Wear Resistance (Grey Cast Iron Machining) K




Work Material: GGG-30 (Round Bar)
Insert: SNGN090308
Cutting Conditions: $v_c$ = 800 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, wet

### ● Fracture Resistance (Ductile Cast Iron Machining) K





Work Material: GGG-40.3, (Round Bar with 2 V-grooves)
Insert: SNGN120408
Cutting Conditions: $v_c$ = 200 m/min, f = 0,2 mm/rev, $a_p$ = 0,5 mm, wet

## ■ Choosing between BNC8115 and BNS8125 (Cast Iron/Hardened Steel)

| | Work Material | Coated SUMIBORON BNC8115 Turning | | Coated SUMIBORON BNC8115 Milling | | SUMIBORON BNS8125 Turning | | SUMIBORON BNS8125 Milling | | SUMIBORON BN7000 Turning | | SUMIBORON BN7000 Milling | | Coated SUMIBORON BNC500 Turning | | Coated SUMIBORON BNC2125 Turning | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| K | Grey Cast Iron | ○ | Best | | | ○ | Best Economical | | | ○ | Depth of cut ≤ 1,0 mm High-speed-finishing | | | × | Not available | × | Not available |
| K | Ductile Cast Iron | ○ | Depth of cut ≥ 0,5 mm | | | ○ | Interrupted machining | | | ○ | Depth of cut ≤ 0,5 mm Low-speed-machining | | | ○ | Depth of cut ≤ 0,5 mm | × | Not available |
| H | Hardened Steel | ○ | Depth of cut ≥ 0,5 mm | | | × | Not available | | | × | Not available | | | × | Not available | ○ | Depth of cut ≤ 0,5 mm High-speed machining |

○ Recommendation × Not available

## Coated CBN grade for ductile cast iron machining




### General Features

Further improvements in the toughness of the sintered CBN and wear resistance from the application of a newly developed high-purity TiC binder. In addition, it demonstrates exceptional wear resistance by combining a ceramic coating with excellent heat resistance. High-speed and high-precision machining is achieved when finishing ductile cast iron. It also provides a long, stable tool life in machining high-strength ductile cast iron, special cast irons such as vermicular cast iron, and centrifugally cast iron.


### Characteristics

- Achieves a Long, Stable Tool Life at $v_c$ = 400 m/min
  Superior wear resistance, makes stable machining possible under high-speed conditions.
- Supports High-precision Machining
  Can maintain excellent dimensional tolerance and surface roughness.





### Cutting Performance

Cast Iron Continuous Cutting





Work material: GGG70, Round Bar
Insert type: CNGA 120408 NC-4
Cutting data: $v_c$ = 400 m/min, f = 0,2 mm/rev, $a_p$ = 0,2 mm
Wet

Machined Surface Quality





Work material: GGG70
Cutting data: $v_c$ = 400 m/min, f = 0,2 mm/rev, $a_p$ = 0,2 mm
Wet


### Application Range




### High Precision Machining




### Recommended Cutting Conditions




| f (mm/rev) | $a_p$ (mm) |
|---|---|
| 0,1–0,4 | 0,03–0,5 |


❄ Coolant ... Wet



## Feattures

SUMIBORON Binderless is a polycrystalline cubic boron nitrid (CBN) that directly binds nanometer- or sub-micron-level CBN particles without binder materials.
Binderless CBN is harder and has better thermal conductivity. Therefore, it enables higher efficiency and longer tool life in machining of hard-to-cut materials, such as titanium alloy and cobalt-chromium alloy.

## Mikrostructure of Sintered Body




## Physical Properties

| | Binderless CBN | Conventional CBN |
|---|---|---|
| CBN Content (%) | 100 | 90–95 |
| Binder Material | – | WC–Co |
| Hardness (GPa) | 51–54 | 41–44 |
| Thermal Conductivity (W/m·K) | 180–200 | 100–120 |


## SUMIBORON Binderless CBN

## Advantages


– Higher efficient machining and longer tool life have been realized by the effects of higher hardness and thermal conductivity than conventional CBN grades.
– Achieves high precise machining and better surface integrity because of less adhesion by not containing any binder materials.
– Ideal tool material for high-efficient finishing of hard-to-cut materials, such as titanium alloy and cobalt-chromium alloy, cemented carbides and cermets.
– NBC100 is able to maintain excellent dimensional accuracy and surface roughness for a long period.
– Shows improved work efficiency and cost reduction by less frequency of exchanging inserts compared to conventional tool grades.

## Application Range and Performance

Turning of Titanium Alloy (Ti-6Al-4V)





Turning of Cobalt-Chromium Alloy (Co-Cr)



# SUMIBORON Binderless
# NCB100


## Turning of Titanium Alloy (Ti-6Al-4V)

### Wear Resistance





Work Material: Ti-6Al-4V
Insert: CNGA 120408 NU
Cutting Conditions: $v_c$ = 150 m/min, f = 0,15 mm/rev, $a_p$ = 0,5 mm, wet

### Surface Roughness





Work Material: Ti-6Al-4V
Insert: CNGA 120408 NU
Cutting Conditions: $v_c$ = 150 m/min, f = 0,15 mm/rev, $a_p$ = 0,5 mm, wet





## Turning of Cobalt-Chromium Alloy (Co-Cr)

### Wear Resistance





Work Material: Co-Cr
Insert: VNGA 160408 NU
Cutting Conditions: $v_c$ = 60, 150 m/min, f = 0,1 mm/rev, $a_p$ = 0,4 mm, wet

### Surface Roughness




Work Material: Co-Cr
Insert: VNGA 160408 NU
Cutting Conditions: $v_c$ = 60, 150 m/min, f = 0,1 mm/rev, $a_p$ = 0,4 mm, wet




## ■ Recommended Cutting Conditions

### Titanium Alloys

Min. - **Optimum** - Max.

| Work Material | | Grade | Cutting Conditions | | |
|---|---|---|---|---|---|
| Composition | Hardness (HRC) | | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (m/min) |
| Ti-6Al-4V | 30–35 | NCB100 | 0,1–**0,3**–0,5 | 0,05–**0,15**–0,20 | 50–**200**–300 |
| Ti-5Al-5V-5Mo-3Cr | 32–38 | NCB100 | 0,1–**0,3**–0,5 | 0,05–**0,10**–0,20 | 50–**150**–250 |
| Ti-10V-2Fe-3Al | 32–38 | NCB100 | 0,1–**0,3**–0,5 | 0,05–**0,10**–0,20 | 50–**150**–250 |

### Cobalt-Chromium Alloys

Min. - **Optimum** - Max.

| Work Material | | Grade | Cutting Conditions | | |
|---|---|---|---|---|---|
| Composition | Hardness (HRC) | | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (m/min) |
| Co-30Cr-5Mo | 35–45 | NCB100 | 0,10–**0,15**–0,30 | 0,05–**0,15**–0,20 | 50–**200**–300 |

### Carbides

Min. - **Optimum** - Max.

| Work Material | | Grade | Cutting Conditions | | |
|---|---|---|---|---|---|
| Composition | Hardness (HRC) | | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (m/min) |
| WC-20Co | <85 | NCB100 | 0,03–**0,10**–0,20 | 0,03–**0,10**–0,20 | 5–**20**–40 |

SUMIDIA BINDERLESS NPD10 is recommended for: > 85 HRA

### Other Work Materials

Min. - **Optimum** - Max.

| Work Material | | Grade | Cutting Conditions | | |
|---|---|---|---|---|---|
| Composition | Hardness (HRC) | | Depth of Cut (mm) | Feed Rate (mm/rev) | Cutting Speed (m/min) |
| Pure Titanium | 130–230 | NCB100 | 0,1–**0,3**–0,5 | 0,05–**0,10**–0,20 | 100–**250**–400 |
| Cermet | 1.000–1.500 | NCB100 | 0,1–**0,2**–0,3 | 0,05–**0,10**–0,20 | 10–**30**–50 |

# Production Process



## General

Since 1970s, Sumitomo has pioneered the development of sintered cubic boron nitride (CBN) and sintered diamond (PCD) tools successfully used in the tool making industries. These tool materials can be epoch-making in a sence of broadening the cutting application range.

## Production Process

In the production process of **SUMIBORON / SUMIDIA**, CBN powder / diamond powder is firstly synthesized under the ultra - high pressure, and secondly, the synthesized crystalline grains are sintered.

Fig. 2 shows a diagram of high temperature high pressure apparatus for processing the ultra - high pressure sintering operation.
This apparatus is basically composed of a piston and a cylinder to generate ultra - high pressure as high as 5000 N/mm$^2$ with a special device. The piston and cylinder are made of cemented carbide.

To manufacture final products round discs of SUMIBORON and SUMIDIA material are cut into specific shapes and brazed on to tool bodies made of cemented carbide, or steel, etc., and after that finished by grinding the edge.
In another process the final product can be obtained only by cutting blanks and finishing them.

Fig. 1







Fig. 2




## SumiBoron / SumiDia Grinding Method

| Items | | SumiBoron | SumiDia |
|---|---|---|---|
| Grinding machine | – | 1) Carbide grinding machine is applicable.<br>2) R Pointer should be used.<br>3) Should be wet grinding. | 1) Special-purpose high rigidity grinding machine is desirable.<br>2) Be sure of applying with wet system. |
| Wheel | Abrasive | Diamond | Diamond |
| | Grain size | D 25 - medium, D20 - fine (#400–800) | Rough grinding: D 35 (#400 mesh)<br>Finish grinding: D 25 (#800–1500 mesh) |
| | Bond | Resinoid or vitrified | Special-purpose metal bond for diamond sintered tool or vitrified |
| | Concentration | 100 | 100–125 |
| | Dressing | Use #400 WA stick | Execute dressing with a WA stick of about 400 mesh. |
| Grinding condition | Wheel speed | 800–1000 m/min. | 800–1000 m/min. |
| | Table cycle | 30–60 cycles/min. | 30–60 cycles/min. |
| | Grinding oil | Water soluble grinding coolant oil | Water soluble grinding coolant (Solution type) |
| Others | – | 1) Check chipping of the cutting edge with microscope after finishing.<br>2) Blank surface cut by EDM should be ground more than 0,05 mm | 1) Rake surface is lapped generally<br>2) Inspect with microscope of magnification of 30–50 times if there is edge chipping.<br>3) Edge treatment of tool should be sharp for cutting non-ferrous metals.<br>4) Remove the wire-cut surface of blank by 0,05 mm or more in grinding operation. |



## General Features

SUMIDIA sintered diamond series has 3 grades (DA1000, DA150, DA90) with individual features depending on the optimum combination of diamond particle size and binder, as well as the NPD10 grade (nano-polycrystalline diamond) where nano-order diamond particles are directly bound with high strength without using binders.
This series is suited to a wide range of applications from machining of aluminium alloy to machining of hard brittle materials and cemented carbide.

## Series • Features • Application

| Grade | | Features | Application | Average size of Diamond grains (μm) | Hardness Hv | TRS (GPa) |
|---|---|---|---|---|---|---|
| SUMIDIA | DA1000 | High density sintered material made of ultra-fine diamond particles that demonstrates optimum wear resistance and excellent edge sharpness. | • High silicon aluminum alloy cutting<br>• Rough, interrupted and finishing of Al-alloy<br>• Wood or wooden board cutting<br>• Non-ferrous metal finishing (aluminium, copper alloy) | < 0,5 | 50<br>60 | ≈ 2,60 |
| SUMIDIA | DA150 | Micro-grained sintered diamond grade with strong diamond-to-diamond bonding. It is suitable for the machining of non-ferrous metals and other very hard materials. | • Non-ferrous metal finishing (aluminium, copper alloy)<br>• Green or semi-sintered carbide & ceramic roughing<br>• FRP, hard rubber & carbon cutting<br>• Wooden or Inorganic Material Board Cutting | 5 | 50<br>~<br>60 | ≈ 1,95 |
| SUMIDIA | **DA90** | Contains coarser diamond particles than other grades, giving it good wear resistance suitable for the machining of carbides and high-silicon aluminium. Shows the highest diamond content for excellent wear resistance. | • Machining of high-silicon<br>• Machining of aluminium composite (MMC)<br>• Green or semi-sintered carbide & ceramic roughing<br>• Machining of sintered ceramics/stone/rock | < 50 | 50<br>~<br>60 | ≈ 1,10 |
| SUMIDIA Binderless | **NPD10** | A 100% diamond grade made by nano-level diamond grains with direct conversion sintering. Has the highest wear resistance and fracture resistance and the best edge sharpness. | • Surface finishing of carbide<br>• Machining brittle materials (ceramics) | < 0,05 | 120<br>~<br>130 | ≈ 3,15 |

## Application Range

Aluminium


| Machinability | Work Material | Turning: Roughing | Turning: Finishing | Milling | Example Part |
|---|---|---|---|---|---|
| Good ↕ Difficult | Sintered aluminium | DA1000 | DA1000 | DA1000 | Cylinder liner |
| | Die cast aluminium (ADC12) | DA1000 | DA1000 | DA1000 | Transmission case, oil pan cylinder block, aluminium wheel |
| | Low silicon (AC2B-T6, AC4C-T6) | DA1000 | DA1000 | DA1000 | Cylinder head |
| | High silicon (T6) | DA1000 | DA150 | DA1000 | Cylinder block |

Non-Aluminium

| Machinability | Work Material | Turning: Roughing | Turning: Finishing | Milling | Example Part |
|---|---|---|---|---|---|
| Good ↕ Difficult | Non-ferrous sintered alloy | DA1000 | DA1000 | DA1000 | Bushing |
| | Gunmetal carbon | DA1000 | DA1000 | DA1000 | Connection rod |
| | Carbide | DA90 | NPD10 | NPD10 | Punches, dies, rolls |
| | Iron combined | DA90 | DA90 | DA150 | Cylinder block, bearing cap |


## Cutting Performance

Continuous Cutting





Work Material: MMC (Al-20% SIC)
Insert: CNMX 120408, Holder: PCLN2525
Cutting Cond.: $v_c$ = 350 m/min, f = 0,2 mm/rev, $a_p$ = 0,18 mm, wet

Continuous Cutting




Work Material: Cemented Carbide (87 HRA)
Insert: DCMW 070204 NF
Cutting Cond.: $v_c$ = 20 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, wet

Continuous Cutting




Work Material: Cemented Carbide (91 HRA)
Insert: DCMW 11T304 RH (NPD10)
DCMW 11T304 NF (DA90)
Cutting Cond.: $v_c$ = 20 m/min, f = 0,05 mm/rev, $a_p$ = 0,05 mm, dry

## Recommended Cutting Conditions

| Cutting Conditions \ Work Materials | | Aluminium Alloys | Copper Alloy | Reinforced Plastics | Wood or Organic Materials | Carbide | Carbon |
|---|---|---|---|---|---|---|---|
| Cutting Speed | $v_c$ (m/min) | ~ 3.000 | ~ 1.000 | ~ 1.000 | ~ 4.000 | 10 ~ 30 | 100 ~ 600 |
| Feed rate | f (mm/rev) | ~ 0,2 | ~ 0,2 | ~ 0,4 | ~ 0,4 | ~ 0,2 | ~ 1,0 |
| Depth of cut | $a_p$ (mm) | ~ 3,0 | ~ 3,0 | ~ 2,0 | – | ~ 0,5 | ~ 2,0 |

## Nano-Polycristalline Diamond




### General Features

Nano-polycristalline diamond is a type of polycristalline diamond, produced by directly binding nano-level diamond grains without using any binders.
This material is unique to our company and as compared to conventional diamond grades containing binders, it exhibits higher strength, excellent wear resistance and fracture resistance.
SUMIDIA Binderless is the series of tools with cutting edges made from this high performance nano-polycristalline diamond.


### Micro-Structure Comparison

**Nano-Polycristalline Diamond**
SEM Structure





Diamond particle average grain diameter
(30 - 50 nm)

Conventional PCD
SEM Structure




Diamond particle average grain diameter
(1 - 10 μm)


### Hardness




## SUMIDIA Binderless

### Application Examples

- Ballnose Endmill / Radius Endmill (Carbide Machining)



- Indexable Inserts (Carbide Machining)






## General Features

NPD10 is made from high-hardness nano-polycrystalline diamond.
This is a pure diamond material, but unlike single-crystal diamonds, it has no anisotropy.
It achieves extended tool life and machining accuracy superior to conventional diamond tools when machining hard brittle materials such as cemented carbide.
DA90 is a polycrystalline diamond grade in which coarse diamond particles have been sintered to form a dense structure. The high diamond content, with high wear resistance, makes it ideal for roughing of cemented carbide and hard brittle material.
Optimized design and mass production technology have been developed, achieving the same performance as conventional tools with higher cost performance.

## Characteristics

- Ideal for Finishing of Hard Brittle Materials Including Cemented Carbide (NPD10)
  High-precision cutting of cemented carbide thanks to the outstanding wear resistance of nano-polycrystalline diamond.
- Superior Dimensional Tolerance Maintained for a Long Time (NPD10)
  Tool replacement count can be drastically reduced compared to conventional diamond tools, enabling work efficiency to be improved and total costs to be reduced.
- Ideal for Roughing of Hard Brittle Materials Including Cemented Carbide (DA90)
  Stable tool life in sintered surface machining of cemented carbide and roughing of hard brittle materials thanks to the outstanding wear resistance of the coarse-grained polycrystalline diamond.
- Uses SUMIDIA NF Insert (DA90)
  Optimized design and mass production technology have been developed, achieving the same performance as conventional tools with higher cost-performance.

## Applicable Range (Cemented Carbide)




## Applications of NPD10 and DA90 (Cemented Carbide)

| Grade | SUMIDIA Binderless NPD10 | | SUMIDIA DA90 | |
|---|---|---|---|---|
| Dimensional Tolerance | ◎ | Best | △ | The first recommendation is NPD10 |
| Tool Life (Wear Resistance) | ◎ | Best $a_p \le 0,2$ mm, $f \le 0,1$mm/rev | ○ | ap ≥ 0,2 mm can also be used |
| Sintered Surface Machining of Cemented Carbide | × | Impossible | ◎ | Best |
| Machined Surface Quality | ◎ | Best | △ | The first recommendation is NPD10 |


## Recommended Cutting Conditions (Carbide Machining)


| Work Material | | | | Grade | Cutting Conditions | | |
|---|---|---|---|---|---|---|---|
| Class | | Hardness (HRA) | SEI Grades | | Cutting Speed $v_c$ (m/min) | Feed Rate f (mm/rev) | Depth of Cut $a_p$ (mm/rev) |
| VM, VC | 40 | ≥ 88 | G5, D2 | NPD10 | 5–**15**–20 | 0,03–**0,05**–0,07 | 0,03–**0,05**–0,07 |
| VM, VC | 70, 60, 50 | 83 – <88 | G7, G6 | NPD10 | 5–**20**–30 | 0,03–**0,10**–0,20 | 0,03–**0,10**–0,20 |
| VM, VC | – | ≥ 83 | G7, G6, G5, D2 | DA90 | 5–**20**–30 | 0,03–**0,10**–0,20 | 0,03–**0,20**–0,50 |

Min. - **Optimum** - Max., Cutting conditions: NPD10: dry, DA90: wet

## Machining Precision of NPD10)

Boring of Carbide VM30 (91HRA)








NPD10 has no dimension variation even with cutting distance of 1.100 m.

Work Material: Carbide VM30 (91HRA)
Insert: DCMW 11T304 RH
Cutting Conditions: $v_c$ = 20 m/min, f = 0,05 mm/rev, $a_p$ = 0,05 mm, dry

## Wear Resistance of DA90

External Machining of Cemented Carbide VC50 (87HRA)




Work Material: Carbide VC50 (87HRA)
Insert: DCMW 070204 NF
Cutting Conditions: $v_c$ = 20 m/min, f = 0,1 mm/rev, $a_p$ = 0,2 mm, wet




## General Features

SumiDia DA1000 is a high density, ultra fine grained sintered PCD with high toughness similar to that of cemented carbides.

SumiDia DA1000, with its great improvement in fracture resistance, eliminates the breakage problems faced by conventional PCD tools especially during the milling of Aluminium alloys and achieves a longer and more stable tool life.


Furthermore, the NF type inserts makes it even more cost effective.

## Cutting Performance




Work Material: 17 % Al-Si alloy
Insert: TPGW 160308
Cutting conditions: $v_c$= 1.000 m/min, f = 0,15 mm/rev, $a_p$ = 0,2 mm, wet

### Wear Resistance in Turning Application




Work Material: 17 % Si-Al alloy
Insert: TPGN 160304
Cutting Conditions: $v_c$=800 m/min, f = 0,12 mm/rev, $a_p$=0,5 mm, wet

# NF Type Inserts

## General Features


- **Total Cost Effectiveness with High Performance and Lower Price**
  - Optimum design utilizing improved mass production techniques provides a relatively lower cost.
  - Regrindable type results in huge total cost reduction.

- **Wide Application Range**
  - Wide range of stocked items for small hole boring, OD turning to milling processes.
  - Negative and positive type inserts that are applicable on standard lever-lock, pin-lock type holders.

## Efficiency

SumiDia NF-type inserts preserve the excellent basic performance of DA1000 while achieving high cost performance through optimal design and development of mass production technology. These inserts achieve the high performance of SUMIDIA DA1000, including excellent fracture resistance, wear resistance and smooth work material surface finishing.


● NF-Type Edge



(NF-type is precision ground just like conventional inserts.)


## Application Examples

### Milling of Aluminum Oil Pump Cover





Work Material: ADC12 (Al-12% Si alloy)
Insert: TEEN32R NF
Cutting conditions: $v_c$ = 3.000 m/min, $f_t$ = 0,06 mm/rev, $a_p$ = 0,2 mm

### Boring of Aluminum Valve Bore




Work Material: ADC12 (Al-12% Si alloy)
Insert: TPGN 110304 NF
Cutting conditions: $v_c$ = 530 m/min, f = 0,05 mm/rev, $a_p$ = 0,2 mm

# SUMIDIA Inserts
# Break Master N-LD / -GD Type




## Characteristics


- Provides excellent chip control in semi finishing and finishing of aluminium alloy.
- Solves chip control problems and dramatically improves work efficiency.
- Achieves stable tool life by employing high toughness grade DA1000.

## Applications Range

Wrought Aluminium Alloy (A6061)




Casted Aluminium Alloy (ADC12)





### **NLD** Type Chipbreaker

Achieves excellent chip control for finishing.



### **NGD** Type Chipbreaker


Achieves excellent chip control for semi finishing.



## Application Examples

### Internal Turning of Machine Component

Provides good chip control in small-depth cutting of wrought Al alloy.






Breakmaster **NLD** type





Without chip breaker

Work Material: A6061
Insert: VCMT110302 **NLD** NF (DA1000)
Cutting Conditions: $v_c$ = 200 m/min, f = 0,20 mm/rev, $a_p$ = 0,10 mm, wet

### Internal Turning of Transmission Component

Offers good chip control in casted material.
Small chips - easy to remove.



Breakmaster **NGD** type




Without chip breaker

Work Material: ADC12
Insert: TPMT110304 **NGD** NF (DA1000)
Cutting Conditions: $v_c$ = 400 m/min, f = 0,23 mm/rev, $a_p$ = 1,20 mm, wet

# Break Master DM Type





## General Features

Economy One-Use Insert

- Similar to SumiBoron One-Use type inserts

With Built-in Chipbreaker for Effective Chip Removal


- Solving chip control problems and improving efficiency with DM-type chipbreaker.

Extensive Insert Range for External and Facing Operation

- 80° and 55° diamond shaped inserts are added to expand the application range of this series.


## Application Range

Triangular Type Insert (Boring)




(Internal turning, Wet cut, Work material: ADC12)

CCMT/DCMT Type (External Turning & Facing)





(Internal turning, Wet cut, Work material: ADC12)



## Chip Control

Break Master



No Chipbreaker



## Application

| Machining Details | Cutting Conditions | Results |
|---|---|---|
| Work Material: AC2A-T6<br><br>Operation: Internal Boring | $v_c$ = 300 m/min<br>f = 0,06 mm/rev<br>$a_p$ = 0,35 mm<br>Wet cut | Surface finish of the bore hole was less than Ra = 1 µm.<br>Chips formed was of a uniform curl of about 2 mm in length.<br>There was almost no chips left inside the bore hole. |

## Recommended Conditions

Boring (Triangular Insert)

| Feed Rate | Depth of Cut | Type |
|---|---|---|
| –0.15 mm/rev. | –0,7 mm | Wet cut |

External Copying (55°, 80° Diamond Shaped Inserts)

| Feed Rate | Depth of Cut | Type |
|---|---|---|
| –0.15 mm/rev. | –0,5 mm | Wet cut |

For facing process, D.O.C. should be less than 0,4 mm

## Series

| External Turning & Facing | | Boring | |
|---|---|---|---|
|  | CCMT 0602_ _ L/R-DM NU |  | TPMT 0802_ _ L/R-DM NU |
| | CCMT 09T3_ _ L/R-DM NU | | TPMT 0902_ _ L/R-DM NU |
|  | DCMT 0702_ _ L/R-DM NU |  | TPMR 1103_ _ L/R-DM NU(*) |
| | DCMT 11T3_ _ L/R-DM NU | | TPMR 1603_ _ L/R-DM NU(*) |

(*) Stock in Japan
Delivery on request


# SUMIBORON / SUMIDIA
## Indexable Inserts & Tools

**M1–M80**

M








SUMIBORON / SUMIDIA Insert
C / 80° Diamond
Insert Identi ication ..... M2-3
**CC**_ _ 7° pos. Type ..... M4-6,8
**CP**_ _ 11° pos. Type ..... M7
**CN**_ _ neg. Type ..... M9-13

D / 55° Diamond
**DC**_ _ 7° pos. Type ..... M14-17
**DN**_ _ neg. Type ..... M18-21

R / Round
**RN**_ _ neg. Type ..... M22

S / Square
**SC**_ _ 7° pos. Type ..... M23
**SN**_ _ neg. Type ..... M24

T / Triangle
**TB**_ _ 5° pos. Type ..... M25
**TC**_ _ 7° pos. Type ..... M26
**TN**_ _ neg. Type ..... M27-30
**TP**_ _ 11° pos. Type (Without Hole) ..... M31
**TP**_ _ 11° pos. Type (With Hole) ..... M32-35

V / 35° Diamond
**VB**_ _ 5° pos. Type ..... M36-37
**VC**_ _ 7° pos. Type ..... M38-39
**VN**_ _ neg. Type ..... M40-42

W / Polygon
**WN**_ _ neg. Type ..... M43

Special
**ZNEX** neg.-pos. Type ..... M44

SUMIDIA Binderless
Neg.-pos. Type ..... M45

SUMIBORON / SUMIDIA Precision Tools
Guidance ..... M46-47

SUMIBORON
**BSME / SEXC** Type Small Hole Boring Bars ..... M48-51
**BNBB** Type Small Hole Boring Bars ..... M52
**BNZ / BNB** Type Small Hole Boring Bars ..... M53
**GWB / PSC** Type Grooving Holder ..... M54-55
**BNGG** Type Threading Holder ..... M56

SUMIDIA
**DABB** Type Small Hole Boring Bars ..... M57

High Speed Non-Ferrous Mill Expansion
**ANX** Type Face Mill ..... M58-69
**RF** Type Face Mill ..... M70
**SRF** Type Face Mill ..... M71

SUMIBORON "BN Finish Mill"
**FMU** Type Face Mill ..... M72-73
"Helical Master"
**BNES** Type Endmill ..... M74
"Mould Finish Master"
**BNBP** Type Micro Ball Nose Endmill ..... M75
SUMIDIA "Mould Finish Master" Binderless
**NPDRS / NPDB(S)** Type ..... M76-77
SUMIDIA Drills
**DAL / DDL / DML** Type Drills ..... M78-79


C D R S T V W Z

Sumiboron / SumiDia Inserts/Tools

# Insert Identification

## Regrindable Type

**CNMA 120408 B**

① Insert ISO Code: ISO ⇨ C2/C3

② Additional Information: Chart 1

Chart 1

| Symbol | Description |
|---|---|
| B | Full-top CBN insert |

## One-Use Type

**CNGG 120408 N-SV NC WG 4**

① Insert ISO Code: ISO ⇨ C2/C3

② Chip Breaker: Chart 2

③ One-Use Type: Chart 3

④ Wiper Insert: Chart 4

⑤ No. of Cutting Edges: Chart 5

Chart 2

| Symbol | Description |
|---|---|
| – | Standard Type |
| LF<br>LE | Sharp cutting edge |
| LT | Small edge treatment type |
| LS | Low cutting force |
| ES | High efficiency type |
| HS | Strong cutting edge |
| US | Strong cutting edge |
| N-FV<br>N-LV<br>N-SV | Chipbreaker Type |

Chart 3

| Symbol | One-Use Type | Grade |
|---|---|---|
| NC | Coated SUMIBORON | BNC2115, BNC2125<br>BNC2010, BNC2020<br>BNC100, BNC160<br>BNC200, BNC300<br>BNC500 |
| NU | Uncoated CBN | BNX10, BNX20<br>BN1000, BN2000<br>BN350, BN7000,<br>BN7115,7500 |
| | SUMIBORON binderless | NCB100 |
| NS | Uncoated CBN | BNX25 |

Chart 4

| Symbol | Wiper Insert |
|---|---|
| WG | Finishing<br>0,05 ≤ f ≤ 0,20 |
| WH | High feed cutting<br>0,20 ≤ f < 0,40 |
| W | Surface Roughness<br>Standard: $R_z$ 1,6–3,2µm |

f : Feed Rate (mm/rev)

Chart 5

| Symbol | No. of Cutting Edges | Type |
|---|---|---|
| – | 1 cutting edge | Single-corner |
| 2 | 2 cutting edges | Multi-corner |
| 3 | 3 cutting edges | |
| 4 | 4 cutting edges | |
| 6 | 6 cutting edges | |

## Regrindable Type

# CNMA 120408 RH

① Insert ISO Code: ISO ⇨ C2/C3

② Additional Information: Chart 1

Chart 1

| Symbol | Description |
|---|---|
| RH | Honing specification (treated cutting edge) |

## One-Use Type

# CNMA 120408 N-LD NF

① Insert ISO Code: ISO ⇨ C2/C3

② Additional Information: Chart 2

③ Type: Chart 3

Chart 2

| Symbol | Description |
|---|---|
| N-LD | Chipbreaker type (neutral) |
| N-GD | |
| R-DM | Chipbreaker type (right handed) |
| L-DM | Chipbreaker type (left handed) |

Chart 3

| Symbol | Description |
|---|---|
| NF | NF insert ⇨ L26 |
| NU | One use insert |

80° Diamond Type | 7° Relief / With Insert Hole










| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CC_ _ | L | IC | S | $D_1$ |
| 0602-- | 6,45 | 6,35 | 2,38 | 2,8 |
| 09T3-- | 9,7 | 9,525 | 3,97 | 4,4 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

Coated

## CCGT / CCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | H Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | KKH BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | KPMKH BN7000 | BN7115 | S Binderless CBN BNS8125 | NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Break Master - FV, LV<br><br>CBN with chipbreaker | <br>with 2 CBN cutting edges | **CCGT 060204 N-FV NC2** | 0,4 | ❍ | ❍ | ● | ● | | ● | ❍ | | | | | | | | | | | | | | | | | | |
| | | **CCGT 09T304 N-FV NC2** | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CCGT 09T308 N-FV NC2** | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CCGT 09T304 N-LV NC2** | 0,4 | ● | ● | ● | ● | | ❍ | ● | | | | | | | | | | | | | | | | | | |
| | | **CCGT 09T308 N-LV NC2** | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| <br>Standard -<br>Normal cut geometry | <br>with 2 CBN cutting edges | **CCGW 060202 NC2** | 0,2 | ● | ● | ● | ● | ● | ● | ● | | ❍ | | | | | | | | | | | | | | | | |
| | | **CCGW 060204 NC2** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| | | **CCGW 060208 NC2** | 0,8 | ● | ● | | ● | | | ● | ● | ❍ | | | | | | | | | | | | | | | | |
| | | **CCGW 09T302 NC2** | 0,2 | ● | ● | ❍ | ● | | | ● | | ❍ | | | | | | | | | | | | | | | | |
| | | **CCGW 09T304 NC2** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| | | **CCGW 09T308 NC2** | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| | <br>(Wiper Type) | **CCGW 09T304 NC-W2** | 0,4 | | ● | | | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T308 NC-W2** | 0,8 | | ● | | | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T304 NC-WG2** | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T308 NC-WG2** | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T304 NC-WH2** | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T308 NC-WH2** | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| <br>**LE** - Type<br>Low cutting force | <br>with 2 CBN cutting edges | **CCGW 060202 LE-NC2** | 0,2 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 060204 LE-NC2** | 0,4 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T302 LE-NC2** | 0,2 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T304 LE-NC2** | 0,4 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T308 LE-NC2** | 0,8 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| <br>**LT** - Type<br>Sharp cutting edge | <br>with 2 CBN cutting edges | **CCGW 060202 LT-NC2** | 0,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 060204 LT-NC2** | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T302 LT-NC2** | 0,2 | | | | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T304 LT-NC2** | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T308 LT-NC2** | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| <br>**LS** - Type<br>Low cutting force | <br>with 2 CBN cutting edges | **CCGW 060202 LS-NC2** | 0,2 | ● | ● | | | ● | ● | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 060204 LS-NC2** | 0,4 | ● | ● | | | ● | ● | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 060208 LS-NC2** | 0,8 | ❍ | ❍ | | | | ● | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T302 LS-NC2** | 0,2 | ❍ | ❍ | | | | ❍ | | | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T304 LS-NC2** | 0,4 | ● | ● | | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T308 LS-NC2** | 0,8 | ❍ | ● | | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| <br>**HS** - Type<br>Strong cutting edge | <br>with 2 CBN cutting edges | **CCGW 060208 HS-NC2** | 0,8 | | | | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T304 HS-NC2** | 0,4 | | ● | | ● | | | ● | ● | | | | | | | | | | | | | | | | | |
| | | **CCGW 09T308 HS-NC2** | 0,8 | | ● | | ● | | | ● | ● | | | | | | | | | | | | | | | | | |

● = Euro stock
❍ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 7° Relief With Insert Hole

Uncoated

# CCEW / CCGW


| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CC_ _ | L | IC | S | $D_1$ |
| 0602-- | 6,45 | 6,35 | 2,38 | 2,8 |
| 09T3-- | 9,7 | 9,525 | 3,97 | 4,4 |
| 03X1-- | | 3,5 | 1,4 | 1,9 |
| 04X1-- | | 4,3 | 1,8 | 2,3 |
| 1204-- | 12,9 | 12,7 | 4,76 | 5,5 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material







## ● SumiBoron (CBN, One-Use Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  **LF** - Type Low cutting force |  | **CCEW 03X102 LF-NU** | 0,2 | | | | | | | | | | | | | | | | | | ❍ | ❍ | | | | | | |
|  **LT** - Type Sharp cutting edge |  | **CCEW 03X102 LT-NU** | 0,2 | | | | | | | | | | | | | | ● | | | | | | | | | | | |
| | | **CCEW 03X104 LT-NU** | 0,4 | | | | | | | | | | | | | | ❍ | | | | | | | | | | | |
| | | **CCEW 04X102 LT-NU** | 0,2 | | | | | | | | | | | | | | ❍ | | | | | | | | | | | |
| | | **CCEW 04X104 LT-NU** | 0,4 | | | | | | | | | | | | | | ❍ | | | | | | | | | | | |

## ● G-Class SumiBoron (CBN, Regrindable Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  |  | **CCGW 09T304** | 0,4 | | | | | | | | | | | | | | | ▲ | | | | | | | | | | |
| | | **CCGW 09T308** | 0,8 | | | | | | | | | | | | | | ● | | | | | | | | | | | |

## ● G-Class SumiBoron (CBN, One-Use Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| |  | **CCGW 060204 NS** | 0,4 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | | **CCGW 09T304 NS** | 0,4 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | | **CCGW 09T308 NS** | 0,8 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
|  |  | **CCGW 060202 NU** | 0,2 | | | | | | | | | | | | ● | | ● | | | | ● | | | | | | | |
| | | **CCGW 060204 NU** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | ❍ | | | | | |
| | | **CCGW 060208 NU** | 0,8 | | | | | | | | | | | | ● | | ● | | | | ● | | | | | | | | |
| | | **CCGW 09T302 NU** | 0,2 | | | | | | | | | | | | ❍ | | ● | | | | | | | | | | | | |
| | | **CCGW 09T304 NU** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | ❍ | | | | | |
| | | **CCGW 09T308 NU** | 0,8 | | | | | | | | | | | ● | ❍ | ▲ | ● | | ▲ | ● | ● | | | ❍ | | | | | |
| | | **CCGW 120408 NU** | 0,8 | | | | | | | | | | | ● | | ▲ | ● | | | | | | | | | | | | |
|  **LT** - Type Sharp cutting edge |  | **CCGW 060202 LT-NU** | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 060204 LT-NU** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 060208 LT-NU** | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 09T302 LT-NU** | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 09T304 LT-NU** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 09T308 LT-NU** | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
|  **HS** - Type Strong cutting edge |  | **CCGW 060202 HS-NU** | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 060204 HS-NU** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 09T302 HS-NU** | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 09T304 HS-NU** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **CCGW 09T308 HS-NU** | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 7° Relief With Insert Hole




| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CC_ _ | L | IC | S | $D_1$ |
| 0602-- | 6,45 | 6,35 | 2,38 | 2,8 |
| 09T3-- | 9,7 | 9,525 | 3,97 | 4,4 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

Uncoated

## CCGT / CCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | H Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | KH BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | K PM KH BN7000 | BN7115 | S BNS8125 | Binderless CBN NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Break Master - FV, LV  CBN with chipbreaker |  with 2 CBN cutting edges | **CCGT 060204 N-FV NU2** | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | **CCGT 09T304 N-FV NU2** | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | **CCGT 09T308 N-FV NU2** | 0,8 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | **CCGT 09T304 N-LV NU2** | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
|  |  with 2 CBN cutting edges | **CCGW 060204 NU2** | 0,4 | | | | | | | | | | | | | | | | | | ❍ | ● | | | | | | |
| | | **CCGW 09T304 NU2** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ❍ | ● | | | | | | |
| | | **CCGW 09T308 NU2** | 0,8 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ❍ | ● | | | | | | |
| |  (Wiper Type) | **CCGW 09T304 NU-WG2** | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | **CCGW 09T308 NU-WG2** | 0,8 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | **CCGW 09T304 NU-WH2** | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | **CCGW 09T308 NU-WH2** | 0,8 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
|  **HS** - Type Strong cutting edge |  with 2 CBN cutting edges | **CCGW 09T308 HS-NU2** | 0,8 | | | | | | | | | | | | | | | | | | | ● | | | | | | |

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 11° Relief / With Insert Hole


| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CP-- | L | IC | S | $D_1$ |
| 0602-- | 6,45 | 6,35 | 2,38 | 2,8 |
| 0802-- | | 7,94 | 2,38 | 3,4 |
| 0903-- | | 9,525 | 3,18 | 4,4 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## Coated

## CPGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  |  with 2 CBN cutting edges | **CPGW 080202 NC2** | 0,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CPGW 080204 NC2** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CPGW 090302 NC2** | 0,2 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CPGW 090304 NC2** | 0,4 | | | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |

## Uncoated

## CPMW ●●●●●●

● M-Class SumiDia (PCD, NF Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  |  | **CPMW 060208 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 7° Relief With Insert Hole


| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CC_ _ | L | IC | S | $D_1$ |
| 0602-- | 6,45 | 6,35 | 2,38 | 2,8 |
| 09T3-- | 9,7 | 9,525 | 3,97 | 4,4 |
| 03X1-- | | 3,5 | 1,4 | 1,9 |
| 04X1-- | | 4,3 | 1,8 | 2,3 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material


Uncoated

## CCMT / CCMW ●●●●●●






● M-Class SumiDia (PCD, Regrindable Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   | CCMT 060202 | 0,2 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| | CCMT 060204 | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| | CCMT 09T302 | 0,2 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| | CCMT 09T304 | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ○ | | |


● M-Class SumiDia (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   | CCMT 060201 NF | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | CCMT 060202 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | CCMT 060204 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | CCMT 09T301 NF | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | CCMT 09T302 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | CCMT 09T304 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | CCMT 09T308 NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |


● M-Class SumiDia (PCD, One-Use "Break Master" Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Break Master - DM   | CCMT 060204 L-DM NU | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| | CCMT 09T302 L-DM NU | 0,2 | | | | | | | | | | | | | | | | | | | | | | | ○ | | |
| | CCMT 09T304 L-DM NU | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| | CCMT 060202 R-DM NU | 0,2 | | | | | | | | | | | | | | | | | | | | | | | ○ | | |
| | CCMT 060204 R-DM NU | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| | CCMT 09T304 R-DM NU | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| Break Master - LD   | CCMT 060202 N-LD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | CCMT 060204 N-LD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | CCMT 09T302 N-LD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | CCMT 09T304 N-LD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | CCMT 09T308 N-LD NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| Break Master - GD   | CCMT 060202 N-GD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | CCMT 060204 N-GD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | CCMT 09T302 N-GD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | CCMT 09T304 N-GD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | CCMT 09T308 N-GD NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |

● M-Class SumiDia (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  | CCMW 03X102 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | CCMW 03X104 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | CCMW 04X102 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | CCMW 04X104 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | CCMW 060202 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | CCMW 060204 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | CCMW 09T302 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | CCMW 09T304 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | CCMW 09T308 NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |

● M-Class SumiDia (PCD, Binderless)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  | CCMW 03X102 RH | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | CCMW 03X104 RH | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | CCMW 04X102 RH | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | CCMW 04X104 RH | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | CCMW 060202 RH | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | CCMW 060204 RH | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | CCMW 09T302 RH | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | CCMW 09T304 RH | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | CCMW 09T308 RH | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 0° Relief / With Insert Hole

Coated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN-- | L | IC | S | $D_1$ |
| | | | | |
| 1204-- | 12,9 | 12,7 | 4,76 | 5,16 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# CNGA ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | H Coated CBN | | | | | | | | | | H Uncoated CBN | | | | | | | K PM KH | | | S Binderless CBN | N Uncoated PCD | | | N Binderless Sumidia |
| Standard - Normal cut geometry | with 2 CBN cutting edges | **CNGA 120404 NC2** | 0,4 | | ○ | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 NC2** | 0,8 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 NC2** | 1,2 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120416 NC2** | 1,6 | | | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNGA 120420 NC2** | 2,0 | | | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNGA 120424 NC2** | 2,4 | | | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| | with 4 CBN cutting edges | **CNGA 120402 NC4** | 0,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120404 NC4** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 NC4** | 0,8 | ● | ● | ○ | ● | ● | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 NC4** | 1,2 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | | | | | | | | | | | | | | | | | |
| | | **CNGA 120416 NC4** | 1,6 | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **CNGA 120420 NC4** | 2,0 | ○ | ○ | | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120424 NC4** | 2,4 | ○ | ○ | ○ | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | with 2 CBN cutting edges | **CNGA 120404 NC-W4** | 0,4 | ● | ● | | | ● | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 NC-W4** | 0,8 | ● | ● | | | ● | ● | ● | | ● | | | | | | | | | | | | | | | | |
| | (Wiper Type) | **CNGA 120404 NC-WG4** | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 NC-WG4** | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 NC-WG4** | 1,2 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120404 NC-WH4** | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 NC-WH4** | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 NC-WH4** | 1,2 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| **LE** - Type Low cutting force | with 2 CBN cutting edges | **CNGA 120404 LE-NC2** | 0,4 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 LE-NC2** | 0,8 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 LE-NC2** | 1,2 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| **LT** - Type Sharp cutting edge | with 2 CBN cutting edges | **CNGA 120402 LT-NC2** | 0,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120404 LT-NC2** | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 LT-NC2** | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 LT-NC2** | 1,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| **LS** - Type Low cutting force | with 2 CBN cutting edges | **CNGA 120402 LS-NC2** | 0,2 | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120404 LS-NC2** | 0,4 | | | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 LS-NC2** | 0,8 | | | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 LS-NC2** | 1,2 | | | ● | ● | ● | ● | | ○ | | | | | | | | | | | | | | | | | |
| | with 4 CBN cutting edges | **CNGA 120404 LS-NC4** | 0,4 | | | | | | ○ | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 LS-NC4** | 0,8 | | | | | | ○ | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 LS-NC4** | 1,2 | | | | | | | ○ | | | | | | | | | | | | | | | | | | |
| **ES** - Type Crater wear stability | with 4 CBN cutting edges | **CNGA 120404 ES-NC4** | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120408 ES-NC4** | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **CNGA 120412 ES-NC4** | 1,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 0° Relief / With Insert Hole




Coated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN_ _ | L | IC | S | $D_1$ |
| | | | | |
| 1204-- | 12,9 | 12,7 | 4,76 | 5,16 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## CNGA / CNGG

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | H | | | | | | | | | K KH | H | | | | | | | K PM | KH | S | N | | | | |
| | | | | Coated | | | | | | | | | | Uncoated | | | | | | | | | | Binderless CBN | Uncoated PCD | | | Binderless Sumidia |
| | | | | CBN | | | | | | | | | | | | | | | | | | | | | | | | |
|  HS - Type Strong cutting edge |  with 2 CBN cutting edges | **CNGA 120404 HS-NC2**<br>**CNGA 120408 HS-NC2**<br>**CNGA 120412 HS-NC2** | 0,4<br>0,8<br>1,2 | | ●<br>●<br>● | ●<br>●<br>● | ●<br>●<br>● | | ●<br>●<br>● | <br>●<br>● | ●<br>●<br>● | | | | | | | | | | | | | | | | |
| |  with 4 CBN cutting edges | **CNGA 120404 HS-NC4**<br>**CNGA 120408 HS-NC4**<br>**CNGA 120412 HS-NC4** | 0,4<br>0,8<br>1,2 | ❍<br>❍<br>❍ | ❍<br>❍<br>❍ | | ❍<br>❍<br>❍ | | | ❍<br>❍ | ❍<br>❍ | ❍<br>❍<br>❍ | | | | | | | | | | | | | | | |
| Break Master - FV, LV, SV  CBN with chipbreaker |  with 4 CBN cutting edges | **CNGG 120404 N-FV NC4**<br>**CNGG 120408 N-FV NC4**<br>**CNGG 120412 N-FV NC4** | 0,4<br>0,8<br>1,2 | ●<br>●<br>● | ●<br>●<br>● | ●<br>●<br>● | ●<br>●<br>● | | | ●<br>●<br>● | | | | | | | | | | | | | | | | |
| | | **CNGG 120404 N-LV NC4**<br>**CNGG 120408 N-LV NC4**<br>**CNGG 120412 N-LV NC4** | 0,4<br>0,8<br>1,2 | ●<br>●<br>● | ●<br>●<br>● | ●<br>●<br>● | ●<br>●<br>● | | ●<br>●<br>● | ●<br>●<br>● | | | | | | | | | | | | | | | | |
| | | **CNGG 120408 N-SV NC4**<br>**CNGG 120412 N-SV NC4** | 0,8<br>1,2 | ●<br>● | ●<br>● | | ●<br>● | | ❍ | ●<br>● | | | | | | | | | | | | | | | | |

● ≡ Euro stock
❍ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 0° Relief / With Insert Hole




Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN_ _ | L | IC | S | $D_1$ |
| | | | | |
| 1204-- | 12,9 | 12,7 | 4,76 | 5,16 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# CNGA ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | H Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | K KH BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | K PM KH BN7000 | BN7115 | BNS8125 | S Binderless CBN NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  |  with 2 CBN cutting edges | **CNGA 120404 NS2**<br>**CNGA 120408 NS2**<br>**CNGA 120412 NS2** | 0,4<br>0,8<br>1,2 | | | | | | | | | | | | | | | ●<br>●<br>● | | | | | | | | | | |
| | | **CNGA 120404 NU2**<br>**CNGA 120408 NU2**<br>**CNGA 120412 NU2** | 0,4<br>0,8<br>1,2 | | | | | | | | | | | ❍<br>●<br>● | ●<br>●<br>● | <br>▲<br>▲ | ●<br>●<br>● | <br>▲<br>▲ | ▲<br>●<br>● | ❍<br>●<br>❍ | ❍<br>●<br>❍ | | | | | | | |
| |  (Wiper Type) | **CNGA 120404 NU-W2**<br>**CNGA 120408 NU-W2** | 0,4<br>0,8 | | | | | | | | | | | ●<br>● | ●<br>● | | | | | | | | | | | | | |
| | | **CNGA 120404 NU-WG2**<br>**CNGA 120408 NU-WG2**<br>**CNGA 120412 NU-WG2** | 0,4<br>0,8<br>1,2 | | | | | | | | | | | | ●<br>●<br>❍ | | | | | | | | | | | | | |
| | | **CNGA 120404 NU-WH2**<br>**CNGA 120408 NU-WH2** | 0,4<br>0,8 | | | | | | | | | | | | ●<br>● | | | | | | | | | | | | | |
|  **LF** - Type Sharp cutting edge |  with 2 CBN cutting edges | **CNGA 120404 LF-NU2**<br>**CNGA 120408 LF-NU2** | 0,4<br>0,8 | | | | | | | | | | | | | | | | | | ❍<br>❍ | ❍<br>❍ | | | | | | |
|  **LE** - Type Low cutting force |  with 2 CBN cutting edges | **CNGA 120404 LE-NU2**<br>**CNGA 120408 LE-NU2** | 0,4<br>0,8 | | | | | | | | | | | | | | | | | | | ❍<br>❍ | | | | | | |
|  **LT** - Type Sharp cutting edge |  with 2 CBN cutting edges | **CNGA 120404 LT-NU2**<br>**CNGA 120408 LT-NU2**<br>**CNGA 120412 LT-NU2** | 0,4<br>0,8<br>1,2 | | | | | | | | | | | | ❍<br>❍<br>❍ | | | | | | | | | | | | | |
|  **LS** - Type Low cutting force |  with 2 CBN cutting edges | **CNGA 120404 LS-NU2** | 0,4 | | | | | | | | | | | | | | | | | | | ❍ | | | | | | |
|  **HT** - Type Strong cutting edge |  with 2 CBN cutting edges | **CNGA 120408 HT-NU2**<br>**CNGA 120412 HT-NU2** | 0,8<br>1,2 | | | | | | | | | | | | | | | | | ❍<br>❍ | | | | | | | | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 0° Relief / With Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN_ _ | L | IC | S | $D_1$ |
| | | | | |
| 1204-- | 12,9 | 12,7 | 4,76 | 5,16 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# CNGA / CNGM

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | H Coated CBN | | | | | | | | | | H Uncoated CBN | | | | | | | K PM Uncoated CBN | | K H Uncoated CBN | S Binderless CBN | N Uncoated PCD | | | N Binderless Sumidia |
|  **HS** - Type Strong cutting edge |  with 2 CBN cutting edges | **CNGA 120404 HS-NU2**<br>**CNGA 120408 HS-NU2**<br>**CNGA 120412 HS-NU2** | 0,4<br>0,8<br>1,2 | | | | | | | | | | | | ○<br>○<br>○ | | | | | | ○<br>○<br>○ | ○ | | | | | | |
|  **US** - Type Strong cutting edge |  with 2 CBN cutting edges | **CNGA 120404 US-NU2** | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| Break Master - LV  CBN with chipbreaker |  with 2 CBN cutting edges | **CNGM 120404 N-LV NU2**<br>**CNGM 120412 N-LV NU2** | 0,4<br>1,2 | | | | | | | | | | | | ●<br>● | | | | | | | | | | | | | |

● G-Class SumiBoron (CBN, Binderless)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  | | **CNGA 120404 NU**<br>**CNGA 120408 NU**<br>**CNGA 120412 NU** | 0,4<br>0,8<br>1,2 | | | | | | | | | | | | | | | | | | | | ○<br>○<br>○ | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 0° Relief | ---

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| CN_ _ | L | IC | S | $D_1$ |
| 0903-- | 9,7 | 9,525 | 3,18 | 4,4 |
| 1204-- | 12,9 | 12,7 | 4,76 | 5,16 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## CNGN / CNGX

● G-Class SumiBoron (Solid CBN Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **CNGN 090308** | 0,8 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | | **CNGN 090312** | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | | **CNGN 120408** | 0,8 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | | **CNGN 120412** | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | | **CNGN 120416** | 1,6 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |

● G-Class SumiBoron (Solid CBN, "Dimple" Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **CNGX 120412** | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | | **CNGX 120416** | 1,6 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |

## CNMA / CNMX

● M-Class SumiBoron (CBN, Regrindable Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **CNMA 120404** | 0,4 | | | | | | | | | | | | | | ● | | ▲ | | | | | | | | | |
| | | **CNMA 120408** | 0,8 | | | | | | | | | | | | | | ● | | ▲ | | ○ | | | | | | | |
| | | **CNMA 120412** | 1,2 | | | | | | | | | | | | | | ● | | | | | | | | | | | |

● M-Class SumiBoron (CBN, One-use Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **CNMA 120404 NS** | 0,4 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | | **CNMA 120408 NS** | 0,8 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | | **CNMA 120412 NS** | 1,2 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | | **CNMA 120404 NU** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | | | | | |
| | | **CNMA 120408 NU** | 0,8 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | | | | | |
| | | **CNMA 120412 NU** | 1,2 | | | | | | | | | | | ● | | ▲ | ● | | ▲ | ● | ● | | | | | | | |
| (Wiper Type) | | **CNMA 120408 NU-W** | 0,8 | | | | | | | | | | | | | ▲ | ● | | | | | | | | | | | |

● M-Class SumiDia (PCD, NF Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **CNMX 120402 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | **CNMX 120404 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | **CNMX 120408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | **CNMX 120412 NF** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 7° Relief With Insert Hole






Coated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DC__ | L | IC | S | $D_1$ |
| 0702-- | 7,75 | 6,35 | 2,38 | 2,8 |
| 11T3-- | 11,6 | 9,525 | 3,97 | 4,4 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## DCGT / DCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | H K KH | | | | | | | | | | H K PM KH | | | | | | | | | S | N | | | | |
| | | | | Coated | | | | | | | | | | Uncoated | | | | | | | | | Binderless CBN | Uncoated PCD | | | Binderless Sumidia |
| | | | | CBN | | | | | | | | | | | | | | | | | | | | | | | | |
| Break Master - FV, LV | | DCGT 070204 N-FV NC2 | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
|  |  | DCGT 11T304 N-FV NC2 | 0,4 | ❍ | ❍ | ● | ● | | ● | ❍ | | | | | | | | | | | | | | | | | | |
| CBN with chipbreaker | with 2 CBN cutting edges | DCGT 11T308 N-FV NC2 | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | DCGT 11T304 N-LV NC2 | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | DCGT 11T308 N-LV NC2 | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| |  | DCGW 070202 NC2 | 0,2 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | DCGW 070204 NC2 | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | with 2 CBN cutting edges | DCGW 070208 NC2 | 0,8 | ❍ | ❍ | ❍ | ● | | | ● | ● | | | | | | | | | | | | | | | | | |
|  | | DCGW 11T302 NC2 | 0,2 | ● | ● | ● | ● | ● | ● | ● | ● | ❍ | | | | | | | | | | | | | | | | |
| | | DCGW 11T304 NC2 | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| Standard - Normal cut geometry | | DCGW 11T308 NC2 | 0,8 | ❍ | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| | | DCGW 11T304 NC-WG2 | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| |  | DCGW 11T308 NC-WG2 | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | (Wiper Type) | DCGW 11T304 NC-WH2 | 0,4 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | DCGW 11T308 NC-WH2 | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
|  |  | DCGW 11T302 LE-NC2 | 0,2 | | | ❍ | | | | | | | | | | | | | | | | | | | | | | |
| | | DCGW 11T304 LE-NC2 | 0,4 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| LE - Type Low cutting force | with 2 CBN cutting edges | DCGW 11T308 LE-NC2 | 0,8 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
|  |  | DCGW 070202 LT-NC2 | 0,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | DCGW 070204 LT-NC2 | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | DCGW 11T302 LT-NC2 | 0,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| LT - Type Sharp cutting edge | with 2 CBN cutting edges | DCGW 11T304 LT-NC2 | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | DCGW 11T308 LT-NC2 | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
|  |  | DCGW 070202 LS-NC2 | 0,2 | ● | ● | | | ● | ● | ● | | | | | | | | | | | | | | | | | | |
| | | DCGW 070204 LS-NC2 | 0,4 | ● | ● | | | ● | ● | ● | | | | | | | | | | | | | | | | | | |
| | | DCGW 070208 LS-NC2 | 0,8 | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | DCGW 11T302 LS-NC2 | 0,2 | ❍ | ❍ | | | | ● | ❍ | | | | | | | | | | | | | | | | | | |
| LS - Type Low cutting force | with 2 CBN cutting edges | DCGW 11T304 LS-NC2 | 0,4 | ● | ● | | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | DCGW 11T308 LS-NC2 | 0,8 | ● | ● | | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
|  |  | DCGW 11T304 HS-NC2 | 0,4 | | ● | | ● | | | ● | ● | | | | | | | | | | | | | | | | | |
| | | DCGW 11T308 HS-NC2 | 0,8 | | ● | | ● | | | ● | ● | | | | | | | | | | | | | | | | | |
| HS - Type Strong cutting edge | with 2 CBN cutting edges | | | | | | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
❍ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 7° Relief With Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DC_ _ | L | IC | S | $D_1$ |
| 0702-- | 7,75 | 6,35 | 2,38 | 2,8 |
| 11T3-- | 11,6 | 9,525 | 3,97 | 4,4 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# DCGT / DCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | H Coated CBN | | | | | | | | K H | | H Uncoated CBN | | | | | | | K PM | KH | S Binderless CBN | N Uncoated PCD | | | Binderless Sumidia |
| Break Master - FV, LV | | DCGT 070204 N-FV NU2 | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | DCGT 11T304 N-FV NU2 | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | DCGT 11T308 N-FV NU2 | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| CBN with chipbreaker | with 2 CBN cutting edges | DCGT 11T304 N-LV NU2 | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | DCGT 11T308 N-LV NU2 | 0,8 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | DCGW 070202 NU2 | 0,2 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | DCGW 070204 NU2 | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | | ○ | | | | | | |
| | with 2 CBN cutting edges | DCGW 070208 NU2 | 0,8 | | | | | | | | | | | | ● | | ● | | | | | ● | | | | | | |
| | | DCGW 11T302 NU2 | 0,2 | | | | | | | | | | | | | | | | | | ○ | ● | | | | | | |
| | | DCGW 11T304 NU2 | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | ○ | | | | | | |
| | | DCGW 11T308 NU2 | 0,8 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | ● | | | | | | |
| | | DCGW 11T304 NU-WG2 | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | DCGW 11T308 NU-WG2 | 0,8 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | (Wiper Type) | DCGW 11T304 NU-WH2 | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| **LF** - Type Sharp cutting edge | with 2 CBN cutting edges | DCGW 11T302 LF-NU2 | 0,2 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | DCGW 11T304 LF-NU2 | 0,4 | | | | | | | | | | | | | | | | | | | ● | | | | | | |
| | | DCGW 11T308 LF-NU2 | 0,8 | | | | | | | | | | | | | | | | | | ○ | ● | | | | | | |
| **LE** - Type Low cutting force | with 2 CBN cutting edges | DCGW 11T302 LE-NU2 | 0,2 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | DCGW 11T304 LE-NU2 | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | DCGW 11T308 LE-NU2 | 0,8 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| **LS** - Type Low cutting force | with 2 CBN cutting edges | DCGW 11T302 LS-NU2 | 0,2 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | DCGW 11T304 LS-NU2 | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | DCGW 11T308 LS-NU2 | 0,8 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| **HS** - Type Strong cutting edge | with 2 CBN cutting edges | DCGW 070208 HS-NU2 | 0,8 | | | | | | | | | | | | | | | | | | | ● | | | | | | |
| | | DCGW 11T304 HS-NU2 | 0,4 | | | | | | | | | | | | | | | | | | | ● | | | | | | |
| | | DCGW 11T308 HS-NU2 | 0,8 | | | | | | | | | | | | | | | | | | | ● | | | | | | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 7° Relief | With Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DC_ _ | L | IC | S | $D_1$ |
| 0702-- | 7,75 | 6,35 | 2,38 | 2,8 |
| 11T3-- | 11,6 | 9,525 | 3,97 | 4,4 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## DCGT / DCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **DCGW 11T304 NS** | 0,4 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | | **DCGW 11T308 NS** | 0,8 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | | **DCGW 070202 NU** | 0,2 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | | | | | |
| | | **DCGW 070204 NU** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | | ● | | | ❍ | | | | |
| | | **DCGW 070208 NU** | 0,8 | | | | | | | | | | | | ● | ▲ | ● | | | | ● | | | | | | | |
| | | **DCGW 11T301 NU** | 0,1 | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **DCGW 11T302 NU** | 0,2 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | ● | | | | |
| | | **DCGW 11T304 NU** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | ❍ | | | | |
| | | **DCGW 11T308 NU** | 0,8 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | ❍ | | | | |
| | | **DCGW 11T312 NU** | 1,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| **LF** - Type<br>Low cutting force | | **DCGW 11T302 LF-NU** | 0,2 | | | | | | | | | | | | | | | | | | ❍ | | | | | | | |
| **LT** - Type<br>Sharp cutting edge | | **DCGW 070202 LT-NU** | 0,2 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 070204 LT-NU** | 0,4 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 070208 LT-NU** | 0,8 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 11T302 LT-NU** | 0,2 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 11T304 LT-NU** | 0,4 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 11T308 LT-NU** | 0,8 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 11T312 LT-NU** | 1,2 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| **HS** - Type<br>Strong cutting edge | | **DCGW 070202 HS-NU** | 0,2 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 070204 HS-NU** | 0,4 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 11T302 HS-NU** | 0,2 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 11T304 HS-NU** | 0,4 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |
| | | **DCGW 11T308 HS-NU** | 0,8 | | | | | | | | | | | | | ❍ | | | | | | | | | | | | |

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9

55° Diamond Type | 7° Relief With Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DC-- | L | IC | S | $D_1$ |
| 0702-- | 7,75 | 6,35 | 2,38 | 2,8 |
| 11T3-- | 11,6 | 9,525 | 3,97 | 4,4 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# DCMT / DCMW


H K KH H K PM KH S N

Coated | Uncoated | Binderless CBN | Uncoated | Binderless Sumidia


CBN | PCD

BNC2115 BNC2125 BNC2010 BNC2020 BNC100 BNC160 BNC200 BNC300 BNC500 BNC8115 BN1000 BN2000 BNX10 BNX20 BNX25 BN300 BN350 BN7000 BN7115 BNS8125 NCB100 DA90 DA150 DA1000 NPD10





● M-Class SumiDia (PCD, Regrindable Type)

| Shape | ISO Cat. No. | RE | BNC2115 BNC2125 BNC2010 BNC2020 BNC100 BNC160 BNC200 BNC300 BNC500 BNC8115 BN1000 BN2000 BNX10 BNX20 BNX25 BN300 BN350 BN7000 BN7115 BNS8125 NCB100 DA90 DA150 DA1000 NPD10 |
|---|---|---|---|
|   | DCMT 070201 | 0,1 | ○ |
| | DCMT 070202 | 0,2 | ● |
| | DCMT 070204 | 0,4 | ● |
| | DCMT 11T302 | 0,2 | ● |
| | DCMT 11T304 | 0,4 | ● |
| | DCMT 11T308 | 0,8 | ● |


● M-Class SumiDia (PCD, NF Type)

| Shape | ISO Cat. No. | RE | BNC2115 BNC2125 BNC2010 BNC2020 BNC100 BNC160 BNC200 BNC300 BNC500 BNC8115 BN1000 BN2000 BNX10 BNX20 BNX25 BN300 BN350 BN7000 BN7115 BNS8125 NCB100 DA90 DA150 DA1000 NPD10 |
|---|---|---|---|
|   | DCMT 070201 NF | 0,1 | ● |
| | DCMT 070202 NF | 0,2 | ● |
| | DCMT 070204 NF | 0,4 | ● |
| | DCMT 070208 NF | 0,8 | ● |
| | DCMT 11T301 NF | 0,1 | ● |
| | DCMT 11T302 NF | 0,2 | ● |
| | DCMT 11T304 NF | 0,4 | ● |
| | DCMT 11T308 NF | 0,8 | ● |

● M-Class SumiDIA (PCD, One-Use "Break Master" Type)

| Shape | ISO Cat. No. | RE | BNC2115 BNC2125 BNC2010 BNC2020 BNC100 BNC160 BNC200 BNC300 BNC500 BNC8115 BN1000 BN2000 BNX10 BNX20 BNX25 BN300 BN350 BN7000 BN7115 BNS8125 NCB100 DA90 DA150 DA1000 NPD10 |
|---|---|---|---|
| Break Master - DM   | DCMT 070202 L-DM NU | 0,2 | ○ |
| | DCMT 070204 L-DM NU | 0,4 | ○ |
| | DCMT 11T304 L-DM NU | 0,4 | ● |
| Break Master - DM   | DCMT 070202 R-DM NU | 0,2 | ○ |
| | DCMT 070204 R-DM NU | 0,4 | ● |
| | DCMT 11T302 R-DM NU | 0,2 | ● |
| | DCMT 11T304 R-DM NU | 0,4 | ● |
| Break Master - LD   | DCMT 070202 N-LD NF | 0,2 | ○ |
| | DCMT 070204 N-LD NF | 0,4 | ○ |
| | DCMT 11T302 N-LD NF | 0,2 | ○ |
| | DCMT 11T304 N-LD NF | 0,4 | ○ |
| | DCMT 11T308 N-LD NF | 0,8 | ○ |
| Break Master - GD   | DCMT 070202 N-GD NF | 0,2 | ○ |
| | DCMT 070204 N-GD NF | 0,4 | ○ |
| | DCMT 11T302 N-GD NF | 0,2 | ○ |
| | DCMT 11T304 N-GD NF | 0,4 | ○ |
| | DCMT 11T308 N-GD NF | 0,8 | ○ |

● M-Class SumiDia (PCD, NF Type)

| Shape | ISO Cat. No. | RE | BNC2115 BNC2125 BNC2010 BNC2020 BNC100 BNC160 BNC200 BNC300 BNC500 BNC8115 BN1000 BN2000 BNX10 BNX20 BNX25 BN300 BN350 BN7000 BN7115 BNS8125 NCB100 DA90 DA150 DA1000 NPD10 |
|---|---|---|---|
|  | DCMW 070202 NF | 0,2 | ○ |
| | DCMW 070204 NF | 0,4 | ○ |
| | DCMW 11T302 NF | 0,2 | ○ |
| | DCMW 11T304 NF | 0,4 | ○ |
| | DCMW 11T308 NF | 0,8 | ○ |

● M-Class SumiDia (PCD, Binderless)

| Shape | ISO Cat. No. | RE | BNC2115 BNC2125 BNC2010 BNC2020 BNC100 BNC160 BNC200 BNC300 BNC500 BNC8115 BN1000 BN2000 BNX10 BNX20 BNX25 BN300 BN350 BN7000 BN7115 BNS8125 NCB100 DA90 DA150 DA1000 NPD10 |
|---|---|---|---|
|  | DCMW 070202 RH | 0,2 | ○ |
| | DCMW 070204 RH | 0,4 | ○ |
| | DCMW 11T302 RH | 0,2 | ○ |
| | DCMW 11T304 RH | 0,4 | ○ |
| | DCMW 11T308 RH | 0,8 | ○ |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 0° Relief / With Insert Hole


Coated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN_ _ | L | IC | S | $D_1$ |
| 1104-- | 11,6 | 9,525 | 4,76 | 3,81 |
| 1504-- | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506-- | 15,5 | 12,7 | 6,35 | 5,16 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## DNGA ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | H Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | KH BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | K PM BN7000 | BN7115 | KH BNS8125 | S Binderless CBN NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  Standard - Normal cut geometry |  with 2 CBN cutting edges | **DNGA 110404 NC2** | 0,4 | ● | ● | ○ | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGA 110408 NC2** | 0,8 | ● | ● | ○ | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGA 110412 NC2** | 1,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150404 NC2** | 0,4 | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 NC2** | 0,8 | | ○ | ○ | ○ | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150412 NC2** | 1,2 | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150416 NC2** | 1,6 | | | ○ | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150420 NC2** | 2,0 | | | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150424 NC2** | 2,4 | | | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| |  with 4 CBN cutting edges | **DNGA 150402 NC4** | 0,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150404 NC4** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 NC4** | 0,8 | ○ | ○ | ○ | | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNGA 150412 NC4** | 1,2 | ○ | ○ | ○ | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150416 NC4** | 1,6 | ○ | ○ | ○ | ○ | | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150420 NC4** | 2,0 | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150424 NC4** | 2,4 | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150604 NC4** | 0,4 | | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| | | **DNGA 150608 NC4** | 0,8 | | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| | | **DNGA 150612 NC4** | 1,3 | | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| |  (Wiper Type) | **DNGA 150404 NC-WG4** | 0,4 | ○ | ○ | | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 NC-WG4** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150604 NC-WG4** | 0,4 | | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150608 NC-WG4** | 0,8 | | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150612 NC-WG4** | 1,2 | | | ● | ● | | ● | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150404 NC-WH4** | 0,4 | ○ | ○ | | | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 NC-WH4** | 0,8 | ○ | ○ | | | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150604 NC-WH4** | 0,4 | | ● | ● | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150608 NC-WH4** | 0,8 | | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150612 NC-WH4** | 1,2 | | ● | ● | ● | | | ● | | | | | | | | | | | | | | | | | | |
|  **LE** - Type Low cutting force |  with 2 CBN cutting edges | **DNGA 150404 LE-NC2** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 LE-NC2** | 0,8 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150412 LE-NC2** | 1,2 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150604 LE-NC2** | 0,4 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150608 LE-NC2** | 0,8 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150612 LE-NC2** | 1,2 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
|  **LT** - Type Sharp cutting edge |  with 2 CBN cutting edges | **DNGA 150402 LT-NC2** | 0,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150404 LT-NC2** | 0,4 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 LT-NC2** | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150412 LT-NC2** | 1,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150604 LT-NC2** | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150608 LT-NC2** | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150612 LT-NC2** | 1,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

To be replaced y new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 0° Relief / With Insert Hole




Coated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN_ _ | L | IC | S | $D_1$ |
| | | | | |
| 1504-- | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506-- | 15,5 | 12,7 | 6,35 | 5,16 |

- H Hardened Steel
- K Cast Iron
- N Non-Ferrous Metal
- S Exotic Alloy
- PM Sintered Component
- Carbide/Hard Brittle Material

# DNGA / DNGG

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | H Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | K PM KH Uncoated CBN BN7000 | BN7115 | BNS8125 | S Binderless CBN NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  **LS** - Type Low cutting force |  with 2 CBN cutting edges | **DNGA 150402 LS-NC2** | 0,2 | | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150404 LS-NC2** | 0,4 | ○ | ○ | | | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 LS-NC2** | 0,8 | ○ | ○ | | | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150412 LS-NC2** | 1,2 | ○ | ○ | | | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150604 LS-NC2** | 0,4 | | ● | | | ● | ● | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150608 LS-NC2** | 0,8 | | ● | | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | **DNGA 150612 LS-NC2** | 1,2 | | ● | | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | |
| |  with 4 CBN cutting edges | **DNGA 150408 LS-NC4** | 0,8 | | | | | | ○ | | | | | | | | | | | | | | | | | | | |
|  **ES** - Type Crater wear stability |  with 2 CBN cutting edges | **DNGA 150604 ES-NC2** | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150608 ES-NC2** | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150612 ES-NC2** | 1,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| |  with 4 CBN cutting edges | **DNGA 150404 ES-NC4** | 0,4 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 ES-NC4** | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGA 150412 ES-NC4** | 1,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
|  **HS** - Type Strong cutting edge |  with 2 CBN cutting edges | **DNGA 150604 HS-NC2** | 0,4 | | ● | ● | ● | | ● | | ● | | | | | | | | | | | | | | | | | |
| | | **DNGA 150608 HS-NC2** | 0,8 | | ● | ● | ● | | ● | ● | ● | | | | | | | | | | | | | | | | | |
| | | **DNGA 150612 HS-NC2** | 1,2 | | ● | ● | ● | | ● | ● | ● | | | | | | | | | | | | | | | | | |
| |  with 4 CBN cutting edges | **DNGA 150404 HS-NC4** | 0,4 | ○ | ○ | | | | ○ | | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGA 150408 HS-NC4** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | **DNGA 150412 HS-NC4** | 1,2 | ○ | ○ | | | | | | ○ | | | | | | | | | | | | | | | | | |
| Break Master - FV, LV, SV  CBN with chipbreaker |  with 4 CBN cutting edges | **DNGG 150404 N-FV NC4** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | |
| | | **DNGG 150408 N-FV NC4** | 0,8 | ○ | ○ | | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150412 N-FV NC4** | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150604 N-FV NC4** | 0,4 | | ● | ● | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150608 N-FV NC4** | 0,8 | | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150612 N-FV NC4** | 1,2 | | | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150404 N-LV NC4** | 0,4 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150408 N-LV NC4** | 0,8 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150412 N-LV NC4** | 1,2 | ○ | ○ | ○ | ○ | | ○ | ○ | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150604 N-LV NC4** | 0,4 | | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150608 N-LV NC4** | 0,8 | | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150612 N-LV NC4** | 1,2 | | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150408 N-SV NC4** | 0,8 | ○ | ○ | ○ | ○ | | ○ | | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150412 N-SV NC4** | 1,2 | ○ | ○ | ○ | ○ | | ○ | | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150608 N-SV NC4** | 0,8 | | ● | | ● | | ● | | | | | | | | | | | | | | | | | | | |
| | | **DNGG 150612 N-SV NC4** | 1,2 | | ● | ● | ● | | ● | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 0° Relief / With Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN_ _ | L | IC | S | $D_1$ |
| 1504-- | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506-- | 15,5 | 12,7 | 6,35 | 5,16 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# DNGA / DNGM

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | with 2 CBN cutting edges | DNGA 150404 NU2 | 0,4 | | | | | | | | | | | | ❍ | | | | | ❍ | | ❍ | | | | | | |
| | | DNGA 150408 NU2 | 0,8 | | | | | | | | | | | | ❍ | | ❍ | | | ❍ | ❍ | ❍ | | | | | | |
| | | DNGA 150412 NU2 | 1,2 | | | | | | | | | | | | ❍ | | | | | | ❍ | | | | | | | |
| | | DNGA 150604 NU2 | 0,4 | | | | | | | | | | | | ● | | ● | | ▲ | ● | | | | | | | | |
| | | DNGA 150608 NU2 | 0,8 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | | | | | | | | |
| | | DNGA 150612 NU2 | 1,2 | | | | | | | | | | | | | ▲ | | | | | | | | | | | | |
| | (Wiper Type) | DNGA 150404 NU-WG2 | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | DNGA 150404 NU-WH2 | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | DNGA 150408 NU-WH2 | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| **LF** - Type<br>Low cutting force | with 2 CBN cutting edges | DNGA 150408 LF-NU2 | 0,8 | | | | | | | | | | | | | | | | | | ❍ | | | | | | | |
| **LT** - Type<br>Sharp cutting edge | with 2 CBN cutting edges | DNGA 150404 LT-NU2 | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | DNGA 150408 LT-NU2 | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | DNGA 150412 LT-NU2 | 1,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| **HS** - Type<br>Strong cutting edge | with 2 CBN cutting edges | DNGA 150404 HS-NU2 | 0,4 | | | | | | | | | | | | ❍ | | | | | | ❍ | | | | | | | |
| | | DNGA 150408 HS-NU2 | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | DNGA 150412 HS-NU2 | 1,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| Break Master - LV<br>CBN with chipbreaker | with 2 CBN cutting edges | DNGM 150404 N-LV NU2 | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | DNGM 150408 N-LV NU2 | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | DNGM 150412 N-LV NU2 | 1,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | DNGM 150608 N-LV NU2 | 0,8 | | | | | | | | | | | | ● | | | | | | | | | | | | | |

● G-Class SumiBoron (CBN, Binderless)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DNGA 150404 NU | 0,4 | | | | | | | | | | | | | | | | | | | | | ❍ | | | | |
| | | DNGA 150408 NU | 0,8 | | | | | | | | | | | | | | | | | | | | | ❍ | | | | |
| | | DNGA 150412 NU | 1,2 | | | | | | | | | | | | | | | | | | | | | ❍ | | | | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 0° Relief

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| DN_ _ | L | IC | S | $D_1$ |
| 1103-- | | 9,525 | 3,18 | - |
| 1506-- | 15,5 | 12,7 | 4,76 | 5,16 |
| 1506-- | 15,5 | 12,7 | 6,35 | 5,16 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## DNGN

● G-Class SumiBoron (Solid CBN Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **DNGN 110308** | 0,8 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **DNGN 110312** | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |

## DNMA

● M-Class SumiBoron (CBN, Regrindable Type)

| | | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **DNMA 150404** | 0,4 | | | | | | | | | | | | | | ❍ | | | | | | | | | | | |
| | **DNMA 150604** | 0,4 | | | | | | | | | | | | | | ● | | ▲ | | | | | | | | | |
| | **DNMA 150608** | 0,8 | | | | | | | | | | | | | | ● | | ▲ | | | | | | | | | |
| | **DNMA 150612** | 1,2 | | | | | | | | | | | | | | ● | | ▲ | | | | | | | | | |

● M-Class SumiBoron (CBN, One-use Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **DNMA 150408 NS** | 0,8 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | |
| | **DNMA 150604 NS** | 0,4 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | **CNMA 150608 NS** | 0,8 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | **DNMA 150401 NU** | 0,1 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | **DNMA 150402 NU** | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | **DNMA 150404 NU** | 0,4 | | | | | | | | | | | | ❍ | ▲ | ❍ | | | | | | | | | | | |
| | **DNMA 150408 NU** | 0,8 | | | | | | | | | | | | ❍ | ▲ | ❍ | | | | | | | | | | | |
| | **DNMA 150412 NU** | 1,2 | | | | | | | | | | | | | | | | | | ❍ | | | | | | | |
| | **DNMA 150604 NU** | 0,4 | | | | | | | | | | | | ● | | ● | | ▲ | | ● | | | | | | | |
| | **DNMA 150608 NU** | 0,8 | | | | | | | | | | | | ● | ▲ | ● | | ▲ | ● | ● | | | | | | | |
| | **DNMA 150612 NU** | 1,2 | | | | | | | | | | | | | ● | ● | | | | | | | | | | | |

● M-Class SumiDia (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **DNMA 150408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ❍ | | | |
| | **DNMA 150412 NF** | 1,2 | | | | | | | | | | | | | | | | | | | | | | ❍ | | | |

● M-Class SumiBoron (CBN, Binderless)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **DNMA 150408 RH** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | ❍ |
| | **DNMA 150412 RH** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | | ❍ |

● = Euro stock
❍ = Stock item in Japan

▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

Round Type | 0° Relief / Without Insert Hole


Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| RN__ | L | IC | S | $D_1$ |
| 0903-- | 9,525 | 9,525 | 3,18 | – |
| 1203-- | 12,7 | 12,7 | 3,18 | – |
| 1204-- | 12,7 | 12,7 | 4,76 | – |


H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# RNGN ●●●●●●

● G-Class SumiBoron (CBN, Full Top Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   Solid CBN | **RNGN 090300** | – | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **RNGN 120300** | – | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **RNGN 120400** | – | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |

● M-Class SumiBoron (CBN, One-Use Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   Solid CBN | **RNGN 090300 B** | – | | | | | | | ● | ● | | | | | | | | | | | | | | | | | |
| | **RNGN 120400 B** | – | | | | | | | | | | | | | | | | | | ○ | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

# SUMIBORON / SUMIDIA
# Indexable Inserts

**Square Type** | 7°/ 0° Relief / With Insert Hole

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 09T3-- | 9,525 | 9,525 | 3,97 | 4,4 |
| 1204-- | 12,7 | 12,7 | 4,76 | 5,16 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## SCGW / SNGA ●●●●●●

### ● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | with 2 CBN cutting edges | **SNGA 120408 NC2** | 0,8 | | | | | | | | | ○ | | | | | | | | | | | | | | | | |
| Standard - Normal cut geometry | with 4 CBN cutting edges | **SNGA 120404 NC4** | 0,4 | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **SNGA 120408 NC4** | 0,8 | ○ | ● | | ● | | | ● | ● | | | | | | | | | | | | | | | | | |
| | | **SNGA 120412 NC4** | 1,2 | ● | ● | | ○ | | | ● | ● | | | | | | | | | | | | | | | | | |
| **HS** - Type Strong cutting edge | with 2 CBN cutting edges | **SNGA 120408 HS-NC2** | 0,8 | | ● | | | | | | ● | | | | | | | | | | | | | | | | | |
| | | **SNGA 120412 HS-NC2** | 1,2 | | ● | | | | | ● | ● | | | | | | | | | | | | | | | | | |

### ● G-Class SumiBoron (CBN, One-Use Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **SCGW 09T304 NU** | 0,4 | | | | | | | | | | | | | | ● | | | | ● | | | | | | | |
| | | **SCGW 09T308 NU** | 0,8 | | | | | | | | | | | | | | ● | | | | ● | | | | | | | |

### ● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | with 2 CBN cutting edges | **SNGA 120404 NU2** | 0,4 | | | | | | | | | | | ○ | | | | | | | ○ | | | | | | | |
| | | **SNGA 120408 NU2** | 0,8 | | | | | | | | | | | ○ | | | ○ | | | | ○ | | | | | | | |
| | | **SNGA 120412 NU2** | 1,2 | | | | | | | | | | | ○ | | | | | | | ○ | | | | | | | |
| **LT** - Type Sharp cutting edge | with 2 CBN cutting edges | **SNGA 120404 LT-NU2** | 0,4 | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **SNGA 120408 LT-NU2** | 0,8 | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **SNGA 120412 LT-NU2** | 1,2 | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| **HS** - Type Strong cutting edge | with 2 CBN cutting edges | **SNGA 120404 HS-NU2** | 0,4 | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **SNGA 120408 HS-NU2** | 0,8 | | | | | | | | | | | ○ | | | | | | | | | | | | | | |
| | | **SNGA 120412 HS-NU2** | 1,2 | | | | | | | | | | | ○ | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

## Square Type — 0° Relief / Without Insert Hole


Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 0903-- | 9,525 | 9,525 | 3,18 | – |
| 1204-- | 12,7 | 12,7 | 4,76 | – |


H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## SNGN / SNGX ●●●●●●

● G-Class SumiBoron (Solid CBN Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   | **SNGN 090308** | 0,8 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **SNGN 090312** | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **SNGN 120308** | 0,8 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **SNGN 120312** | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **SNGN 120408** | 0,8 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **SNGN 120412** | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **SNGN 120416** | 1,6 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **SNGN 120420** | 2,0 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |

● G-Class SumiBoron (Solid CBN, "Dimple" Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   | **SNGX 120412** | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | **SNGX 120416** | 1,6 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |


## Square Type — 0° Relief / With Insert Hole

Uncoated


| | | | | | |
|---|---|---|---|---|---|
| SN_ _ | L | IC | S | $D_1$ |
| 0903-- | 9,525 | 9,525 | 3,18 | – |
| 1204-- | 12,7 | 12,7 | 4,76 | – |

## SNMA ●●●●●●


● M-Class SumiBoron (CBN, One-Use Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   | **SNMA 120408 NS** | 0,8 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | **SNMA 120412 NS** | 1,2 | | | | | | | | | | | | | | | ● | | | | | | | | | | |
| | **SNMA 120408 NU** | 0,8 | | | | | | | | | | | | ● | | ○ | | ▲ | | ● | | | | | | | |
| | **SNMA 120412 NU** | 1,2 | | | | | | | | | | | | ● | | ● | | ▲ | ● | ● | | | | | | | |

● M-Class SumiDia (PCD, NF Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  | **SNMA 120408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |
| | **SNMA 120412 NF** | 1,2 | | | | | | | | | | | | | | | | | | | | | | ○ | | | |

● M-Class SumiDIA (PCD, Binderless)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  | **SNMA 120408 RH** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **SNMA 120412 RH** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 5° Relief

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TBGN | L | IC | S | $D_1$ |
| 0601-- | 6,9 | 3,97 | 1,59 | – |
| TBGW | | | | |
| 0601-- | 6,9 | 3,97 | 1,59 | 2,8 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# TBGN / TBGW

● G-Class SumiBoron (CBN, Full Top Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **TBGN 060102 B** | 0,2 | | | | | | | ● | | | | | ● | | ● | | | | | | | | | | ○ | |
| | | **TBGN 060104 B** | 0,4 | | | | | | | ● | | | | | ● | ▲ | ● | | ▲ | | ○ | | | | | | | |

● G-Class SumiDIA (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **TBGN 060102 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | ○ | | |
| | | **TBGN 060104 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | | |

● G-Class SumiDIA (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **TBGW 060102 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| | | **TBGW 060104 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 7° Relief / With Insert Hole




Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TC_ _ | L | IC | S | $D_1$ |
| 0902-- | 9,62 | 5,56 | 2,38 | 2,5 |
| 1102-- | 11,0 | 6,35 | 2,38 | 2,8 |
| 16T3-- | 16,5 | 9,525 | 3,97 | 4,3 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## TCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Type+Multi-Corner)

| Shape | ISO Cat. No. | RE | H Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | K KH BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | K PM BN7000 | BN7115 | KH BNS8125 | S Binderless CBN NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   | **TCGW 090204 NC** | 0,4 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | **TCGW 090208 NC** | 0,8 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | **TCGW 110202 NC** | 0,2 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | **TCGW 110204 NC** | 0,4 | | ● | | ● | | | ● | | ● | | | | | | | | | | | | | | | | |
| | **TCGW 110208 NC** | 0,8 | ● | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
|   with 3 CBN cutting edges | **TCGW 16T304 NC3** | 0,4 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | **TCGW 16T308 NC3** | 0,8 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
|   | **TCGW 090204 NU** | 0,4 | | | | | | | | | | | | | | | | | | ● | | | | | | | |
| | **TCGW 090208 NU** | 0,8 | | | | | | | | | | | | | | | | | | ● | | | | | | | |
| | **TCGW 110202 NU** | 0,2 | | | | | | | | | | | | | ▲ | ● | | | | ● | | | | | | | |
| | **TCGW 110204 NU** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | | | ● | | | | | | | |
| | **TCGW 110208 NU** | 0,8 | | | | | | | | | | | | | ▲ | | | | | ● | | | | | | | |
| | **TCGW 16T304 NU** | 0,4 | | | | | | | | | | | | | ▲ | ● | | | | ● | | | | | | | |
| | **TCGW 16T308 NU** | 0,8 | | | | | | | | | | | | | | ● | | | | ● | | | | | | | |

## TCMT ●●●●●●

● M-Class SumiDia (PCD, NF Type)

| Shape | ISO Cat. No. | RE | H Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | K KH BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | K PM BN7000 | BN7115 | KH BNS8125 | S Binderless CBN NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   | **TCMT 090202 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **TCMT 090204 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TCMT 110201 NF** | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TCMT 110202 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TCMT 110204 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 0° Relief With Insert Hole









Coated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| | | | | |
| 1604-- | 16,5 | 9,525 | 4,76 | 3,81 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# TNGA ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | H Coated CBN | | | | | | | | K KH | | H Uncoated CBN | | | | | | | K PM | | KH | S Binderless CBN | N Uncoated PCD | | | N Binderless Sumidia |
|  Standard - Normal cut geometry |  with 3 CBN cutting edges | TNGA 160404 NC3 | 0,4 | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160408 NC3 | 0,8 | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160412 NC3 | 1,2 | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160416 NC3 | 1,6 | | | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | TNGA 160420 NC3 | 2,0 | | | ○ | ○ | | ○ | | ○ | | | | | | | | | | | | | | | | |
| | | TNGA 160424 NC3 | 2,4 | | | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| |  with 6 CBN cutting edges | TNGA 160402 NC6 | 0,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160404 NC6 | 0,4 | ● | ● | ● | ● | ○ | ● | ● | ● | | | | | | | | | | | | | | | | |
| | | TNGA 160408 NC6 | 0,8 | ● | ● | ● | ● | ● | ● | ● | ● | ○ | | | | | | | | | | | | | | | |
| | | TNGA 160412 NC6 | 1,2 | ● | ● | ● | ● | | ● | ● | ● | ○ | | | | | | | | | | | | | | | |
| | | TNGA 160416 NC6 | 1,6 | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | TNGA 160420 NC6 | 2,0 | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | TNGA 160424 NC6 | 2,4 | ○ | ○ | ○ | ○ | | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
|  LE - Type Low cutting force |  with 3 CBN cutting edges | TNGA 160404 LE-NC3 | 0,4 | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160408 LE-NC3 | 0,8 | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160412 LE-NC3 | 1,2 | | | ○ | | | | | | | | | | | | | | | | | | | | | |
|  LT - Type Sharp cutting edge |  with 3 CBN cutting edges | TNGA 160402 LT-NC3 | 0,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160404 LT-NC3 | 0,4 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160408 LT-NC3 | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160412 LT-NC3 | 1,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
|  LS - Type Low cutting force |  with 3 CBN cutting edges | TNGA 160402 LS-NC3 | 0,2 | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160404 LS-NC3 | 0,4 | ● | ● | | | ● | | ● | ● | | | | | | | | | | | | | | | | |
| | | TNGA 160408 LS-NC3 | 0,8 | ● | ● | | | ● | ● | | ● | | | | | | | | | | | | | | | | |
| | | TNGA 160412 LS-NC3 | 1,2 | ○ | ○ | | | | ● | | ○ | | | | | | | | | | | | | | | | |
|  ES - Type Crater wear stability |  with 6 CBN cutting edges | TNGA 160404 ES-NC6 | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160408 ES-NC6 | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160412 ES-NC6 | 1,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
|  HS - Type Strong cutting edge |  with 3 CBN cutting edges | TNGA 160404 HS-NC3 | 0,4 | | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | |
| | | TNGA 160408 HS-NC3 | 0,8 | | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | |
| | | TNGA 160412 HS-NC3 | 1,2 | | ● | ● | ● | | | | ● | | | | | | | | | | | | | | | | |
| |  with 6 CBN cutting edges | TNGA 160404 HS-NC6 | 0,4 | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | TNGA 160408 HS-NC6 | 0,8 | ○ | ○ | | ○ | | | | | | ○ | | | | | | | | | | | | | | |
| | | TNGA 160412 HS-NC6 | 1,2 | ○ | ○ | | ○ | | | | ○ | | ○ | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 0° Relief With Insert Hole


Coated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| | | | | |
| 1604-- | 16,5 | 9,525 | 4,76 | 3,81 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# TNGG ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | H K KH Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | K PM KH BN7000 | BN7115 | BNS8125 | S Binderless CBN NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Break Master - FV, LV, SV | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|  CBN with chipbreaker |  with 6 CBN cutting edges | **TNGG 160404 N-FV NC6** | 0,4 | ❍ | ❍ | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNGG 160408 N-FV NC6** | 0,8 | ❍ | ❍ | | ● | | ● | | | | | | | | | | | | | | | | | | | |
| | | **TNGG 160412 N-FV NC6** | 1,2 | ❍ | ❍ | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TNGG 160404 N-LV NC6** | 0,4 | ❍ | ❍ | | ● | | | ❍ | | | | | | | | | | | | | | | | | | |
| | | **TNGG 160408 N-LV NC6** | 0,8 | ● | ● | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **TNGG 160412 N-LV NC6** | 1,2 | ● | ● | ● | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **TNGG 160408 N-SV NC6** | 0,8 | ● | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **TNGG 160412 N-SV NC6** | 1,2 | ❍ | ❍ | | ❍ | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
❍ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 0° Relief

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| 1103-- | | 6,35 | 3,18 | - |
| 1604-- | 16,5 | 9,525 | 4,76 | 3,81 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# TNGA / TNGM

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | with 3 CBN cutting edges | TNGA 160404 NU3 | 0,4 | | | | | | | | | | | | ○ | | ○ | | | | | ○ | | | | | | |
| | | TNGA 160408 NU3 | 0,8 | | | | | | | | | | | | ○ | | ○ | | | ○ | ○ | ○ | | | | | | |
| | | TNGA 160412 NU3 | 1,2 | | | | | | | | | | | | | | ○ | | | | ○ | ○ | | | | | | |
| | with 3 CBN cutting edges | TNGA 160404 T NU3 | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | | TNGA 160408 T NU3 | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| LF / LE - Type Sharp cutting edge | with 3 CBN cutting edges | TNGA 160404 LF-NU3 | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | | |
| | | TNGA 160408 LF-NU3 | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | | |
| | with 3 CBN cutting edges | TNGA 160404 LE NU3 | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | TNGA 160408 LE NU3 | 0,8 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| LS - Type Low cutting force | with 3 CBN cutting edges | TNGA 160404 LS NU3 | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | with 3 CBN cutting edges | TNGA 160408 HT NU3 | 0,8 | | | | | | | | | | | | | | | | | ○ | | | | | | | | |
| HT, HS, US - Type Strong cutting edge | | TNGA 160404 HS NU3 | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | | TNGA 160408 HS NU3 | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | | | | | |
| | | TNGA 160416 HS NU3 | 1,6 | | | | | | | | | | | | | | | | | | | ● | | | | | | |
| | | TNGA 160404 US NU3 | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| Break Master - LV CBN with chipbreaker | with 3 CBN cutting edges | TNGM 160404 N-LV NU3 | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |

# TNGN

● G-Class SumiBoron (Solid CBN Type, without Hole)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | TNGN 110308 | 0,8 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | TNGN 110312 | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | TNGN 160408 | 0,8 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | TNGN 160412 | 1,2 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | TNGN 160416 | 1,6 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |
| | TNGN 160420 | 2,0 | | | | | | | | | | ● | | | | | | | | | | ● | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 0° Relief | With Insert Hole


Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TN__ | L | IC | S | $D_1$ |
| | | | | |
| 1604-- | 16,5 | 9,525 | 4,76 | 3,81 |
| | | | | |



H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## TNMA

● M-Class SumiBoron (CBN, Regrindable Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  |  | **TNMA 160404** | 0,4 | | | | | | | | | | | | | ● | | ▲ | | | | | | | | | |
| | | **TNMA 160408** | 0,8 | | | | | | | | | | | | | | | ▲ | | | | | | | | | |

● M-Class SumiBoron (CBN, One-Use Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  |  | **TNMA 160401 NU** | 0,1 | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | | **TNMA 160402 NU** | 0,2 | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | | **TNMA 160404 NU** | 0,4 | | | | | | | | | | | ● | ▲ | ● | | | | | | | | | | | |
| | | **TNMA 160408 NU** | 0,8 | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | | | | | | | | |
| | | **TNMA 160412 NU** | 1,2 | | | | | | | | | | | ○ | ▲ | ● | | | | ○ | | | | | | | |
|  |  | **TNMA 160408 NS** | 0,8 | | | | | | | | | | | | | | ○ | | | | | | | | | |

## TNMX

● M-Class SumiDia (PCD, NF Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  | | **TNMX 160404 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | **TNMX 160408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | ○ | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 11° Relief | Without Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| TP__ | L | IC | S | $D_1$ |
| 1103-- | 11,0 | 6,35 | 3,18 | |
| 1603-- | 16,5 | 9,525 | 3,18 | |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# TPGN ●●●●●●

● G-Class SumiBoron (CBN, Regrindable Type)

| | | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | TPGN 110304 | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | TPGN 160304 | 0,4 | | | | | | | | | | | | | | ❍ | | | | | | | | | | | |
| | TPGN 160308 | 0,8 | | | | | | | | | | | | | | ❍ | | | | | | | | | | | |

● G-Class SumiBoron (CBN, One-Use Type)

| | | | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | TPGN 110302 NU | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 110304 NU | 0,4 | | | | | | | | | | | | ❍ | | ● | | | ❍ | | | | | | | | |
| | | TPGN 110308 NU | 0,8 | | | | | | | | | | | | ❍ | | ● | | | | | | | | | | | |
| | | TPGN 160302 NU | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 160304 NU | 0,4 | | | | | | | | | | | | | | ● | | | | | ❍ | | | | | | |
| | | TPGN 160308 NU | 0,8 | | | | | | | | | | | | ❍ | | ● | | | | | ❍ | | | | | | |
| | | TPGN 110302 LT NU | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 110304 LT NU | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 110308 LT NU | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 160304 LT NU | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 160308 LT NU | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 110304 HS NU | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 110308 HS NU | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 160304 HS NU | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | TPGN 160308 HS NU | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |

● G-Class SumiDia (PCD, NF Type)

| | | | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | TPGN 110302 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ❍ | |
| | | TPGN 110304 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | TPGN 110308 NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | TPGN 160302 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | TPGN 160304 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | TPGN 160308 NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | P: Full-length cutting edge type | TPGN 110304 P NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ❍ | |
| | P: Full-length cutting edge type | TPGN 160304 P NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ❍ | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 11° Relief With Insert Hole

Coated

Dimensions (mm)

| TP__ | L | IC | S | $D_1$ |
|---|---|---|---|---|
| 0802-- | 8,2 | 4,76 | 2,39 | 2,3 |
| 0902-- | 9,62 | 5,56 | 2,38 | 2,5 |
| 1102-- | 11,0 | 6,35 | 2,38 | 2,8 |
| 1103-- | | | 3,18 | 3,4 |
| 1604-- | 16,5 | 9,525 | 4,76 | 4,3 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## TPGT / TPGW

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Break Master - FV | | | | H | H | H | H | H | H | H | H | K | KH | H | H | H | H | H | H | H | K | PM | KH | S | N | N | N | |
| | | | | Coated | | | | | | | | | | Uncoated | | | | | | | | | | | Binderless CBN | Uncoated | | | Binderless Sumidia |
| | | | | CBN | | | | | | | | | | | | | | | | | | | | | PCD | | | |
| CBN with chipbreaker | with 3 CBN cutting edges | **TPGT 110304 N-FV NC3** | 0,4 | ● | ● | ○ | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **TPGT 110308 N-FV NC3** | 0,8 | ○ | ○ | ○ | ● | | ● | ○ | | | | | | | | | | | | | | | | | | |

● G-Class SumiBoron (CBN, One-Use Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Standard - Normal cut geometry | | **TPGW 080202 NC** | 0,2 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **TPGW 080204 NC** | 0,4 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110304 NC** | 0,4 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110308 NC** | 0,8 | | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Standard Type | with 3 CBN cutting edges | **TPGW 080202 NC3** | 0,2 | ○ | ○ | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 080204 NC3** | 0,4 | ○ | ○ | ● | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 090202 NC3** | 0,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 090204 NC3** | 0,4 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110302 NC3** | 0,2 | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110304 NC3** | 0,4 | ○ | ○ | | | | | ○ | | ○ | | | | | | | | | | | | | | | | |
| | | **TPGW 110308 NC3** | 0,8 | ○ | ○ | | | | | ○ | | ○ | | | | | | | | | | | | | | | | |
| | | **TPGW 160404 NC3** | 0,4 | ○ | ○ | | | | | | | ○ | | | | | | | | | | | | | | | | |
| | | **TPGW 160408 NC3** | 0,8 | ○ | ○ | | | | | | | ○ | | | | | | | | | | | | | | | | |
| **LE** - Type Low cutting force | with 3 CBN cutting edges | **TPGW 110302 LE-NC3** | 0,2 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110304 LE-NC3** | 0,4 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110308 LE-NC3** | 0,8 | | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| **LT** - Type Sharp cutting edge | with 3 CBN cutting edges | **TPGW 110302 LT-NC3** | 0,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110304 LT-NC3** | 0,4 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110308 LT-NC3** | 0,8 | | | | ○ | | | | | | | | | | | | | | | | | | | | | |
| **LS** - Type Low cutting force | with 3 CBN cutting edges | **TPGW 110302 LS-NC3** | 0,2 | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **TPGW 110304 LS-NC3** | 0,4 | ○ | ○ | | | | | | ○ | | | | | | | | | | | | | | | | | |
| | | **TPGW 110308 LS-NC3** | 0,8 | ○ | ○ | | | ○ | ○ | | ○ | | | | | | | | | | | | | | | | | |
| **HS** - Type Sharp cutting edge | with 3 CBN cutting edges | **TPGW 160404 HS-NC3** | 0,4 | | ○ | | | | | ○ | | | | | | | | | | | | | | | | | | |
| | | **TPGW 160408 HS-NC3** | 0,8 | | ○ | | | | | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 11° Relief With Insert Hole

Uncoated

Dimensions (mm)

| TP__ | L | IC | S | $D_1$ |
|---|---|---|---|---|
| 0802-- | 8,2 | 4,76 | 2,39 | 2,3 |
| 0902-- | 9,62 | 5,56 | 2,38 | 2,5 |
| 1102-- | 11,0 | 6,35 | 2,38 | 2,8 |
| 1103-- | | | 3,18 | 3,4 |
| 1604-- | 16,5 | 9,525 | 4,76 | 4,3 |





H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# TPGT / TPGW

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

● G-Class SumiBoron (CBN, Regrindable Type)

● G-Class SumiBoron (CBN, One-Use Type)

| Shape | | ISO Cat. No. | RE |
|---|---|---|---|
| Break Master - FV<br><br>CBN with chipbreaker | <br>with 3 CBN cutting edges | **TPGT 110304 N-FV NU3** | 0,4 |
|  |  | **TPGW 110304** | 0,4 |
| | | **TPGW 110308** | 0,8 |
|  |  | **TPGW 080202 NU** | 0,2 |
| | | **TPGW 080204 NU** | 0,4 |
| | | **TPGW 090204 NU** | 0,4 |
| | | **TPGW 110202 NU** | 0,2 |
| | | **TPGW 110204 NU** | 0,4 |
| | | **TPGW 110302 NU** | 0,2 |
| | | **TPGW 110304 NU** | 0,4 |
| | | **TPGW 110308 NU** | 0,8 |
| | | **TPGW 160404 NU** | 0,4 |
|  |  | **TPGW 110308 LF NU** | 0,8 |
|  |  | **TPGW 080202 LT NU** | 0,2 |
| | | **TPGW 080204 LT NU** | 0,4 |
| | | **TPGW 090202 LT NU** | 0,2 |
| | | **TPGW 090204 LT NU** | 0,4 |
| | | **TPGW 110202 LT NU** | 0,2 |
| | | **TPGW 110204 LT NU** | 0,4 |
| | | **TPGW 110302 LT NU** | 0,2 |
| | | **TPGW 110304 LT NU** | 0,4 |
| | | **TPGW 110308 LT NU** | 0,8 |

| | H | | | | | | | | K | K | H | H | | | | | | | K | PM | K | H | S | N | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Coated | | | | | | | | | | | Uncoated | | | | | | | | | | | Binderless CBN | Uncoated | | Binderless Sumidia |
| | CBN | | | | | | | | | | | | | | | | | | | | | | | PCD | | |
| | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
| | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | ● | | | | | | | | | | | |
| | | | | | | | | | | | | | | ● | | | | | | | | | | | |
| | | | | | | | | | | | ❍ | ● | | ● | | | | | ❍ | | | | | | |
| | | | | | | | | | | | ● | ● | ▲ | ● | | | | | ❍ | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | | | | | | | | | | | ❍ | ▲ | | | | | | ❍ | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | | | | | | | | | | | ● | ▲ | ● | | ▲ | ● | | | | | | | | |
| | | | | | | | | | | | | ● | ▲ | ● | | ▲ | ● | ❍ | | | | | | | |
| | | | | | | | | | | | | | | ❍ | | | | | ● | | | | | | |
| | | | | | | | | | | | | | | | | | | ❍ | | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 11° Relief With Insert Hole

Uncoated

Dimensions (mm)

| TP_ _ | L | IC | S | $D_1$ |
|---|---|---|---|---|
| 0802-- | 8,2 | 4,76 | 2,39 | 2,3 |
| 0902-- | 9,62 | 5,56 | 2,38 | 2,5 |
| 1102-- | 11,0 | 6,35 | 2,38 | 2,8 |
| 1103-- | | | 3,18 | 3,4 |
| 1604-- | 16,5 | 9,525 | 4,76 | 4,3 |




H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# TPGT / TPGW

● G-Class SumiBoron (CBN, One-Use Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **TPGW 080202 HS NU** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **TPGW 080204 HS NU** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **TPGW 080208 HS NU** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **TPGW 110204 HS NU** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **TPGW 110302 HS NU** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **TPGW 110304 HS NU** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **TPGW 110308 HS NU** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   with 3 CBN cutting edges | **TPGW 110204 NU3** | 0,4 | | | | | | | | | | | | | | | | | | ○ | | | | | | | |
| | **TPGW 110208 NU3** | 0,8 | | | | | | | | | | | | | | | | | | ○ | | | | | | | |
| | **TPGW 110304 NU3** | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
| | **TPGW 110308 NU3** | 0,8 | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | | |
|   with 3 CBN cutting edges | **TPGW 110302 LF NU3** | 0,2 | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | | |
| | **TPGW 110304 LF NU3** | 0,4 | | | | | | | | | | | | | | | | | | ○ | ○ | | | | | | |
| | **TPGW 110308 LF NU3** | 0,8 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |
|   with 3 CBN cutting edges | **TPGW 110304 LE NU3** | 0,4 | | | | | | | | | | | | | | | | | | | ○ | | | | | | |

● G-Class SumiDia (PCD, NF Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|   | **TPGW 080202 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TPGW 080204 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TPGW 090204 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **TPGW 110202 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **TPGW 110208 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TPGW 110302 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TPGW 110304 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TPGW 110308 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TPGW 160304 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **TPGW 160402 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TPGW 160404 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **TPGW 160408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 11° Relief With Insert Hole

Uncoated

Dimensions (mm)

| TP_ _ | L | IC | S | $D_1$ |
|---|---|---|---|---|
| 0802-- | 8,2 | 4,76 | 2,39 | 2,3 |
| 0902-- | 9,62 | 5,56 | 2,38 | 2,5 |
| 1102-- | 11,0 | 6,35 | 2,38 | 2,8 |
| 1103-- | | | 3,18 | 3,4 |
| 1604-- | 16,5 | 9,525 | 4,76 | 4,3 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# TPMT / TPMW

● M-Class SumiDia (PCD, One-Use "Break Master" Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Break Master - DM | | TPMT 090204 L-DM NU | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | | |
| Break Master - LD | | TPMT 080202 N-LD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 080204 N-LD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 090202 N-LD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 090204 N-LD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110202 N-LD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110204 N-LD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110302 N-LD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110304 N-LD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110308 N-LD NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 160402 N-LD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 160404 N-LD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 160408 N-LD NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| Break Master - GD | | TPMT 080202 N-GD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 080204 N-GD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 090202 N-GD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 090204 N-GD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110202 N-GD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110204 N-GD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110302 N-GD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110304 N-GD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 110308 N-GD NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 160402 N-GD NF | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 160404 N-GD NF | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | | TPMT 160408 N-GD NF | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |

● M-Class SumiDia (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | TPMW 080202 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | TPMW 080204 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | TPMW 110302 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | TPMW 110304 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | TPMW 110308 NF | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | TPMW 160402 NF | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | TPMW 160404 NF | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | | TPMW 160408 NF | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |

● M-Class SumiDia (PCD, Binderless)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | TPMW 080202 RH | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | TPMW 080204 RH | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | TPMW 110302 RH | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | TPMW 110304 RH | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | TPMW 110308 RH | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | TPMW 160402 RH | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | TPMW 160404 RH | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | | TPMW 160408 RH | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 5° Relief With Insert Hole

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VB_ _ | L | IC | S | $D_1$ |
| 1102-- | 11,0 | 6,35 | 2,38 | 2,8 |
| 1103-- | | | 3,18 | |
| 1604-- | 16,6 | 9,525 | 4,76 | 4,4 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## VBGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | H | | | | | | | | K | KH | H | | | | | | | K | PM | KH | S | N | | | |
| | | | Coated | | | | | | | | | | Uncoated | | | | | | | | | | Binderless CBN | Uncoated PCD | | | Binderless Sumidia |
| | | | CBN | | | | | | | | | | | | | | | | | | | | | | | | |
| Standard - Normal cut geometry | **VBGW 110202 NC** | 0,2 | ● | | ● | | | | ● | | | | | | | | | | | | | | | | | | |
| | **VBGW 110204 NC** | 0,4 | ● | | ● | | | | ● | | | | | | | | | | | | | | | | | | |
| | **VBGW 110208 NC** | 0,8 | ● | | ● | | | | ● | | | | | | | | | | | | | | | | | | |
| | **VBGW 110202 NU** | 0,2 | | | | | | | | | | | | | | ● | | | | | | | | | | | |
| | **VBGW 110204 NU** | 0,4 | | | | | | | | | | | | ● | | ● | | | | | | | | | | | |
| | **VBGW 110208 NU** | 0,8 | | | | | | | | | | | | | | ● | | | | | | | | | | | |
| | **VBGW 110302 NU** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 110304 NU** | 0,4 | | | | | | | | | | | ○ | ○ | | | | | | ○ | | | ○ | | | | |
| | **VBGW 110308 NU** | 0,8 | | | | | | | | | | | | ○ | | | | | | ○ | | | ○ | | | | |
| | **VBGW 160402 NU** | 0,2 | | | | | | | | | | | | ○ | | ● | | | | | | | | | | | |
| | **VBGW 160404 NU** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | ▲ | ● | ● | | | ○ | | | | |
| | **VBGW 160408 NU** | 0,8 | | | | | | | | | | | ● | ● | | ● | | ▲ | ● | ● | | | ○ | | | | |
| **LT** - Type Sharp cutting edge | **VBGW 110302 LT NU** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 110304 LT NU** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 110308 LT NU** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 160402 LT NU** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 160404 LT NU** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 160408 LT NU** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| **HS** - Type Strong cutting edge | **VBGW 110302 HS NU** | 0,2 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 110304 HS NU** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 110308 HS NU** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 160404 HS NU** | 0,4 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |
| | **VBGW 160408 HS NU** | 0,8 | | | | | | | | | | | | ○ | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 5° Relief With Insert Hole

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VB_ _ | L | IC | S | $D_1$ |
| 1102-- | 11,0 | 6,35 | 2,38 | 2,8 |
| 1103-- | | | 3,18 | |
| 1604-- | 16,6 | 9,525 | 4,76 | 4,4 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# VBGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | H Coated CBN | | | | | | | | K KH | | H Uncoated CBN | | | | | | | K PM | | KH | S Binderless CBN | N Uncoated PCD | | | Binderless Sumidia |
| | with 2 CBN cutting edges | **VBGW 110304 NU2** | 0,4 | | | | | | | | | | | | | | | | | | | ❍ | | | | | | |
| | | **VBGW 160404 NU2** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | | | | ● | | | | | | |
| | | **VBGW 160408 NU2** | 0,8 | | | | | | | | | | | ● | ● | ▲ | ● | | | | ❍ | ❍ | | | | | | |
| Standard - Normal cut geometry | with 2 CBN cutting edges | **VBGW 110302 NC2** | 0,2 | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 110304 NC2** | 0,4 | ❍ | ❍ | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 110308 NC2** | 0,8 | ❍ | ❍ | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160402 NC2** | 0,2 | ❍ | ❍ | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160404 NC2** | 0,4 | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| | | **VBGW 160408 NC2** | 0,8 | ❍ | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | | | | | | | | | | | |
| | | **VBGW 160412 NC2** | 1,2 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| LE - Type Low cutting force | with 2 CBN cutting edges | **VBGW 160408 LE NU2** | 0,8 | | | | | | | | | | | | | | | | | | | ● | | | | | | |
| | | **VBGW 160402 LE-NC2** | 0,2 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160404 LE-NC2** | 0,4 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160408 LE-NC2** | 0,8 | | | ● | | | | | | | | | | | | | | | | | | | | | | |
| LT - Type Sharp cutting edge | with 2 CBN cutting edges | **VBGW 110302 LT-NC2** | 0,2 | | | | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 110304 LT-NC2** | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160402 LT-NC2** | 0,2 | | | | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160404 LT-NC2** | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160408 LT-NC2** | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | | |
| LS - Type Low cutting force | with 2 CBN cutting edges | **VBGW 110302 LS-NC2** | 0,2 | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 110304 LS-NC2** | 0,4 | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 110308 LS-NC2** | 0,8 | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160402 LS-NC2** | 0,2 | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160404 LS-NC2** | 0,4 | ● | ● | | | ● | ● | ● | | | | | | | | | | | | | | | | | | |
| | | **VBGW 160408 LS-NC2** | 0,8 | ❍ | ● | | | ● | ● | ● | | | | | | | | | | | | | | | | | | |
| HS - Type Strong cutting edge | with 2 CBN cutting edges | **VBGW 160404 HS-NC2** | 0,4 | | ● | | ● | | | ● | ● | | | | | | | | | | | | | | | | | |
| | | **VBGW 160408 HS-NC2** | 0,8 | | ● | | ● | | | ● | ● | | | | | | | | | | | | | | | | | |

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 7° Relief With Insert Hole

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VC-- | L | IC | S | $D_1$ |
| 0802-- | 8,3 | 4,76 | 2,38 | 2,3 |
| 1103-- | 11,0 | 6,35 | 3,18 | 2,8 |
| 1604-- | 16,6 | 9,525 | 4,76 | 4,4 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## VCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **VCGW 080202 NU** | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **VCGW 080204 NU** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **VCGW 110301 NU** | 0,1 | | | | | | | | | | | | | | | | | | | | | ● | | | | |
| | | **VCGW 110302 NU** | 0,2 | | | | | | | | | | | ❍ | ❍ | | | | | | | | | ● | | | | |
| | | **VCGW 110304 NU** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **VCGW 160404 NU** | 0,4 | | | | | | | | | | | | | | | | | | | | | ❍ | | | | |
| | | **VCGW 160408 NU** | 0,8 | | | | | | | | | | | | | | | | | | | | | ❍ | | | | |
| | | **VCGW 080202 LT NU** | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **VCGW 080204 LT NU** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **VCGW 080208 LT NU** | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Standard - Normal cut geometry | with 2 CBN cutting edges | **VCGW 080202 NC2** | 0,2 | | | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | | **VCGW 080204 NC2** | 0,4 | | | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | | **VCGW 160404 NC2** | 0,4 | ❍ | ❍ | | | | ❍ | | | | | | | | | | | | | | | | | | | |
| | | **VCGW 160408 NC2** | 0,8 | ❍ | ❍ | | ❍ | | | | | | | | | | | | | | | | | | | | | |
| **LS** - Type Low cutting force | with 2 CBN cutting edges | **VCGW 160404 LS NC2** | 0,4 | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **VCGW 160408 LS NC2** | 0,8 | ❍ | ❍ | | | | | ❍ | | | | | | | | | | | | | | | | | | |
| **HS** - Type Strong cutting edge | with 2 CBN cutting edges | **VCGW 160404 HS NC2** | 0,4 | | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | | **VCGW 160408 HS NC2** | 0,8 | | ❍ | | ❍ | | | ❍ | | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 7° Relief With Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VC-- | L | IC | S | $D_1$ |
| 0802-- | 8,3 | 4,76 | 2,38 | 2,3 |
| 1103-- | 11,0 | 6,35 | 3,18 | 2,8 |
| 1604-- | 16,6 | 9,525 | 4,76 | 4,4 |
| 2205-- | | 12,7 | 5,56 | 5,5 |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# VCMT / VCGW

● M-Class (Regrindable Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **VCMT 220530** | 3,0 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMW 160404** | 0,4 | | | | | | | | | | | | | | ○ | | | | | | | | | | | |

● M-Class SumiDia (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **VCMT 110301 NF** | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **VCMT 110302 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **VCMT 110304 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **VCMT 160404 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **VCMT 160408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **VCMT 160412 NF** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | **VCMT 110302 N-LD NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 110304 N-LD NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 160404 N-LD NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 160408 N-LD NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 160412 N-LD NF** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 110302 N-GD NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 110304 N-GD NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 160404 N-GD NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 160408 N-GD NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |
| | **VCMT 160412 N-GD NF** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | ○ | |

● M-Class SumiDia (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **VCMW 080202 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | **VCMW 080204 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | **VCMW 110302 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | **VCMW 110304 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | **VCMW 160402 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | **VCMW 160404 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | **VCMW 160408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |
| | **VCMW 160412 NF** | 1,2 | | | | | | | | | | | | | | | | | | | | | ○ | | | | |

● M-Class SumiDia (PCD, Binderless)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **VCMW 080201 RH** | 0,1 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **VCMW 080202 RH** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **VCMW 080204 RH** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **VCMW 110302 RH** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **VCMW 110304 RH** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **VCMW 160402 RH** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **VCMW 160404 RH** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **VCMW 160408 RH** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |
| | **VCMW 160412 RH** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | | ○ |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 0° Relief / With Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VN__ | L | IC | S | $D_1$ |
| | | | | |
| 1604-- | 16,6 | 9,525 | 4,76 | 3,81 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## VNGA ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  |  with 2 CBN cutting edges | **VNGA 160404 NU2** | 0,4 | | | | | | | | | | | ❍ | ● | | ❍ | | | ❍ | ❍ | ● | ❍ | | | | |
| | | **VNGA 160408 NU2** | 0,8 | | | | | | | | | | | ● | ● | | ● | | | | ❍ | ● | | | | | | |
|  |  with 2 CBN cutting edges | **VNGA 160404 LT NU2** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **VNGA 160408 LT NU2** | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
|  |  with 2 CBN cutting edges | **VNGA 160404 HS NU2** | 0,4 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |
| | | **VNGA 160408 HS NU2** | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |

● G-Class SumiBoron (CBN, One-Use Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
|  | | **VNGA 160404 NU** | 0,4 | | | | | | | | | | | | | | | | | | | | ❍ | | | | | |
| | | **VNGA 160408 NU** | 0,8 | | | | | | | | | | | | | | | | | | | | ❍ | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 0° Relief / With Insert Hole

Coated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VN-- | L | IC | S | $D_1$ |
| | | | | |
| 1604-- | 16,6 | 9,525 | 4,76 | 3,81 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# VNGA / VNGG

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | H Coated CBN BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | K KH CBN BNC500 | BNC8115 | H Uncoated CBN BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | K PM KH CBN BN7000 | BN7115 | BNS8125 | S Binderless CBN NCB100 | N Uncoated PCD DA90 | DA150 | DA1000 | Binderless Sumidia NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | with 2 CBN cutting edges | VNGA 160404 NC2 | 0,4 | | ○ | ○ | ● | | | ○ | | | | | | | | | | | | | | | | | |
| | | VNGA 160408 NC2 | 0,8 | | ○ | ○ | ● | | | ○ | | | | | | | | | | | | | | | | | |
| | | VNGA 160412 NC2 | 1,2 | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | with 4 CBN cutting edges | VNGA 160402 NC4 | 0,2 | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160404 NC4 | 0,4 | ○ | ○ | ○ | ● | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | | |
| | | VNGA 160408 NC4 | 0,8 | ● | ● | ○ | ● | | ○ | ○ | ○ | ○ | | | | | | | | | | | | | | | |
| | | VNGA 160412 NC4 | 1,2 | ○ | ○ | | | | | ○ | | | | | | | | | | | | | | | | | |
| LT - Type Sharp cutting edge | with 2 CBN cutting edges | VNGA 160402 LT-NC2 | 0,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160404 LT-NC2 | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160408 LT-NC2 | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160412 LT-NC2 | 1,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
| LS - Type Low cutting force | with 2 CBN cutting edges | VNGA 160402 LS-NC2 | 0,2 | | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160404 LS-NC2 | 0,4 | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160408 LS-NC2 | 0,8 | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160412 LS-NC2 | 1,2 | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | with 4 CBN cutting edges | VNGA 160404 LS-NC4 | 0,4 | | | | | ○ | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160408 LS-NC4 | 0,8 | | | | | ○ | | ○ | | | | | | | | | | | | | | | | | |
| | | VNGA 160412 LS-NC4 | 1,2 | | | | | | | ○ | | | | | | | | | | | | | | | | | |
| HS - Type Strong cutting edge | with 4 CBN cutting edges | VNGA 160404 HS-NC4 | 0,4 | ○ | ○ | | | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160408 HS-NC4 | 0,8 | ○ | ○ | | | | | ○ | ○ | | | | | | | | | | | | | | | | |
| | | VNGA 160412 HS-NC4 | 1,2 | ○ | ○ | | ○ | | | ○ | | | | | | | | | | | | | | | | | |
| ES - Type Crater wear stability | with 4 CBN cutting edges | VNGA 160404 ES-NC4 | 0,4 | | | | ● | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160408 ES-NC4 | 0,8 | | | | ● | | | | | | | | | | | | | | | | | | | | |
| | | VNGA 160412 ES-NC4 | 1,2 | | | | ○ | | | | | | | | | | | | | | | | | | | | |
| Break Master - FV, - LV CBN with chipbreaker | with 4 CBN cutting edges | VNGG 160404 N-FV NC4 | 0,4 | ● | | ○ | ● | | ● | ● | | | | | | | | | | | | | | | | | |
| | | VNGG 160408 N-FV NC4 | 0,8 | ● | | ● | ● | | ● | ● | | | | | | | | | | | | | | | | | |
| | | VNGG 160404 N-LV NC4 | 0,4 | ● | | ● | ● | | ○ | ● | | | | | | | | | | | | | | | | | |
| | | VNGG 160408 N-LV NC4 | 0,8 | ● | | ● | ● | | | ● | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

## 35° Diamond Type — 0° Relief — With Insert Hole

Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| VN__ | L | IC | S | $D_1$ |
| | | | | |
| 1604-- | 16,6 | 9,525 | 4,76 | 3,81 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## VNGM / VNMA

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Break Master - LV | | **VNGM 160404 N-LV NU2** | 0,4 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| | | **VNGM 160408 N-LV NU2** | 0,8 | | | | | | | | | | | | ● | | | | | | | | | | | | | |
| CBN with chipbreaker | with 2 CBN cutting edges | | | | | | | | | | | | | | | | | | | | | | | | | | | |

● M-Class SumiBoron (CBN, Regrindable Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **VNMA 160404** | 0,4 | | | | | | | | | | | | | | ● | | ▲ | | | | | | | | | | |
| | | **VNMA 160408** | 0,8 | | | | | | | | | | | | ❍ | | ❍ | | ▲ | | | | | | | | | | |

● M-Class SumiBoron (CBN, One-Use Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **VNMA 160401 NU** | 0,1 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | | |
| | | **VNMA 160402 NU** | 0,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | | |
| | | **VNMA 160404 NU** | 0,4 | | | | | | | | | | | | ● | ▲ | ● | | ▲ | ● | | | | | | | | | |
| | | **VNMA 160408 NU** | 0,8 | | | | | | | | | | | | ● | ▲ | ● | | ▲ | ● | | | | | | | | | |
| | | **VNMA 160412 NU** | 1,2 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | | |
| | | **VNMA 160408 NS** | 0,8 | | | | | | | | | | | | | | | ❍ | | | | | | | | | | | |

● M-Class SumiDia (PCD, NF Type)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **VNMA 160408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | ❍ | | | | |
| | | **VNMA 160412 NF** | 1,2 | | | | | | | | | | | | | | | | | | | | | | ❍ | | | | |

● M-Class SumiDia (PCD, Binderless)

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **VNMA 160408 RH** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | | | | ❍ |
| | | **VNMA 160412 RH** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | | | | ❍ |

## VNMX

● M-Class SumiDia (PCD, Regrindable Type)

| Shape | | ISO Cat. No. | RE | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN250 | BN300 | BN350 | BN700 | BN7000 | BN7500 | BNS800 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **VNMX 160402 NF** | 0,2 | | | | | | | | | | | | | | | | | | | | | | | ❍ | |
| | | **VNMX 160404 NF** | 0,4 | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | **VNMX 160408 NF** | 0,8 | | | | | | | | | | | | | | | | | | | | | | | ● | |
| | | **VNMX 160412** | 1,2 | | | | | | | | | | | | | | | | | | | | | | | ❍ | |

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Trigon Type | 0° Relief With Insert Hole

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WN_ _ | L | IC | S | $D_1$ |
| | | | | |
| 0804-- | 8,69 | 12,7 | 4,76 | 5,16 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

# WNGA ○○○○○○

● M-Class SumiBoron (CBN, One-Use Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | **WNMA 080408 NU** | 0,8 | | | | | | | | | | | | ❍ | | | | | | | | | | | | | |

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

| Shape | | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | with 6 CBN cutting edges | **WNGA 080404 NC6** | 0,4 | ● | ● | ❍ | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **WNGA 080408 NC6** | 0,8 | ● | ● | | ● | | | ● | | | | | | | | | | | | | | | | | | |
| | | **WNGA 080412 NC6** | 1,2 | ● | ● | ❍ | ● | | | ● | | | | | | | | | | | | | | | | | | |
| **LT** - Type Sharp cutting edge | with 3 CBN cutting edges | **WNGA 080408 LT-NC3** | 0,8 | | | | ❍ | | | | | | | | | | | | | | | | | | | | | |
| **LS** - Type Low cutting force | with 3 CBN cutting edges | **WNGA 080408 LS NC3** | 0,8 | ❍ | ❍ | | | | | | | | | | | | | | | | | | | | | | | |
| | with 6 CBN cutting edges | **WNGA 080408 LS NC6** | 0,8 | | | | | | ❍ | | | | | | | | | | | | | | | | | | | |
| **HS** - Type Strong cutting edge | with 6 CBN cutting edges | **WNGA 080408 HS NC6** | 0,8 | ❍ | ❍ | | | | | ❍ | | | | | | | | | | | | | | | | | | |
| | (Wiper Type) | **WNGA 080408 NC-WG6** | 0,8 | ❍ | ❍ | ● | ● | | ❍ | ❍ | | | | | | | | | | | | | | | | | | |
| | (Wiper Type) | **WNGA 080408 NC-WH6** | 0,8 | ❍ | ❍ | ● | ● | | ❍ | ❍ | | | | | | | | | | | | | | | | | | |

● = Euro stock
○ = Stock item in Japan

☞ L8, L9 Edge Specification of SUMIBORON Inserts

80° Special Type | 7° Relief With Insert Hole

Coated / Uncoated

| Dimensions (mm) | | | | |
|---|---|---|---|---|
| WN_ _ | L | IC | S | $D_1$ |
| | | | | |
| 0401-- | - | 4,76 | 1,69 | 2,3 |
| | | | | |

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

## ZNEX ●●●●●●

● SumiBoron (CBN, One-Use Type)

| Shape | ISO Cat. No. | RE | BNC2115 | BNC2125 | BNC2010 | BNC2020 | BNC100 | BNC160 | BNC200 | BNC300 | BNC500 | BNC8115 | BN1000 | BN2000 | BNX10 | BNX20 | BNX25 | BN300 | BN350 | BN7000 | BN7115 | BNS8125 | NCB100 | DA90 | DA150 | DA1000 | NPD10 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | **ZNEX 040102 NC** | 0,2 | | | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | |
| | **ZNEX 040104 NC** | 0,4 | | | | ● | ● | ● | ● | | | | | | | | | | | | | | | | | | |
| | **ZNEX 040102 LE-NC** | 0,2 | | | ❍ | | | | | | | | | | | | | | | | | | | | | | |
| | **ZNEX 040104 LE-NC** | 0,4 | | | ❍ | | | | | | | | | | | | | | | | | | | | | | |
| | **ZNEX 040102 LT-NC** | 0,2 | | | | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | **ZNEX 040104 LT-NC** | 0,4 | | | | ❍ | | | | | | | | | | | | | | | | | | | | | |
| | **ZNEX 040102 NU** | 0,2 | | | | | | | | | | | ● | ● | ▲ | ● | | | | | | | | | | | |
| | **ZNEX 040104 NU** | 0,4 | | | | | | | | | | | ● | ● | ▲ | ● | | | | ❍ | | | | | | | |



● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item

☞ L8, L9 Edge Specification of SUMIBORON Inserts

# SUMIDIA Binderless PCD - Insert Grade NPD10

## Negative Inserts




Application: Hard brittle material

| | Shape | ISO Cat. No. | Dimensions (mm) Inscribed Circle (IC) | Thick-ness | Hole Size | Nose Radius | Cutting Edge Length | NPD10 |
|---|---|---|---|---|---|---|---|---|
| 55° Diamond Type |  | **DNMA 150408 RH** | 12,70 | 4,76 | 5,16 | 0,8 | 1,8 | ❍ |
| | | **150412 RH** | | | | 1,2 | 1,8 | ❍ |
| Square Type |  | **SNMA 120408 RH** | 12,70 | 4,76 | 5,16 | 0,8 | 1,7 | ❍ |
| | | **120412 RH** | | | | 1,2 | 1,7 | ❍ |
| 35° Diamond Type |  | **VNMA 160408 RH** | 9,525 | 4,76 | 3,81 | 0,8 | 1,8 | ❍ |
| | | **160412 RH** | | | | 1,2 | 1,5 | ❍ |

Note: Clearance angle of cutting edge tip can show deviation due to the production process.

## Positive Inserts

Application: Hard brittle material

| | Rake Angle | Shape | ISO Cat. No. | Dimensions (mm) Inscribed Circle (IC) | Thick-ness | Hole Size | Nose Radius | Cutting Edge Length | NPD10 |
|---|---|---|---|---|---|---|---|---|---|
| 80° Diamond Type | 7° |  | **CCMW 03X102 RH** | 3,50 | 1,40 | 1,9 | 0,2 | 1,3 | ❍ |
| | | | **03X104 RH** | | | | 0,4 | 1,3 | ❍ |
| | | | **CCMW 04X102 RH** | 4,30 | 1,80 | 2,3 | 0,2 | 1,7 | ❍ |
| | | | **04X104 RH** | | | | 0,4 | 1,7 | ❍ |
| | |  | **CCMW 060202 RH** | 6,35 | 2,38 | 2,8 | 0,2 | 1,7 | ❍ |
| | | | **060204 RH** | | | | 0,4 | 1,7 | ❍ |
| | | | **CCMW 09T302 RH** | 9,525 | 3,97 | 4,4 | 0,2 | 1,7 | ❍ |
| | | | **09T304 RH** | | | | 0,4 | 1,7 | ❍ |
| | | | **09T308 RH** | | | | 0,8 | 1,6 | ❍ |
| 55° Diamond Type | 7° |  | **DCMW 070202 RH** | 6,35 | 2,38 | 2,8 | 0,2 | 2,1 | ❍ |
| | | | **070204 RH** | | | | 0,4 | 2,0 | ❍ |
| | | | **DCMW 11T302 RH** | 9,525 | 3,97 | 4,4 | 0,2 | 2,1 | ❍ |
| | | | **11T304 RH** | | | | 0,4 | 1,9 | ❍ |
| | | | **11T308 RH** | | | | 0,8 | 1,6 | ❍ |
| Triangular Type | 11° |  | **TPMW 080202 RH** | 4,76 | 2,38 | 2,3 | 0,2 | 1,2 | ❍ |
| | | | **080204 RH** | | | | 0,4 | 1,0 | ❍ |
| | | | **TPMW 110302 RH** | 6,35 | 3,18 | 3,4 | 0,2 | 1,5 | ❍ |
| | | | **110304 RH** | | | | 0,4 | 1,3 | ❍ |
| | | | **110308 RH** | | | | 0,8 | 1,0 | ❍ |
| | | | **TPMW 160402 RH** | 9,525 | 4,76 | 4,4 | 0,2 | 2,2 | ❍ |
| | | | **160404 RH** | | | | 0,4 | 2,0 | ❍ |
| | | | **160408 RH** | | | | 0,8 | 1,6 | ❍ |
| 35° Diamond Type | 7° |  | **VCMW 080201 RH** | 4,76 | 2,38 | 2,3 | 0,1 | 2,2 | ❍ |
| | | | **080202 RH** | | | | 0,2 | 1,9 | ❍ |
| | | | **080204 RH** | | | | 0,4 | 1,5 | ❍ |
| | | | **VCMW 110302 RH** | 6,35 | 3,18 | 2,8 | 0,2 | 2,1 | ❍ |
| | | | **110304 RH** | | | | 0,4 | 1,7 | ❍ |
| | | | **VCMW 160402 RH** | 9,525 | 4,76 | 4,4 | 0,2 | 2,1 | ❍ |
| | | | **160404 RH** | | | | 0,4 | 1,7 | ❍ |
| | | | **160408 RH** | | | | 0,8 | 1,8 | ❍ |
| | | | **160412 RH** | | | | 1,2 | 1,5 | ❍ |

Note: Clearance angle of cutting edge tip can show deviation due to the production process.

# Precision Tools



**BSME** → M48-50

**Very small boring bar - brazed type**

- Solid carbide shank boring bar with brazed CBN tip and inner coolant supply.
- For tiny hole diameter boring in hardened steel.
- Min. boring dia. is ø 2,5 mm.



**SEXC** → M48-51

**CBN boring tool for small diameter boring**

- Solid carbide shank boring bar with indexable CBN insert and inner coolant supply.
- For small hole diameter boring in hardened steel.
- Min. boring dia. is ø 4,0 mm.



**BNBB** → M52

**Small hole boring tools**

- CBN cutting edge is brazed on to a solid carbide shank.
- Small hole boring for hardened steels.
- Min. boring dia. is ø 3,5 mm.



**BNZ** → M53

**Small hole boring bars**

- Solid carbide boring bars with economical CBN insert.
- Small hole boring for hardened steels.
- Min. boring dia. is ø 7,0 mm.



**BNB** → M53

**Small hole boring bars**

- Solid carbide boring bars with economical CBN and PCD insert.
- Min. boring dia. is ø 10,0 mm.



**GWB / PSC** → M54-55

**CBN Grooving System for Hardened Steels**


- Tangential Inserts – Double clamp holder
- Groove Widths from 1,5 – 6,0mm
- New CBN grade for interrupted grooving
- ISO-PSC polygon modular grooving system



**BNGG** → M56

**Threading holders**

- CBN cutting edge for hardened steel
- Adjustable threading after regrinding.




**DABB** → M57

**Small hole boring tools**

- PCD cutting edge for finishing of small non-ferrous parts
- Min. boring dia. is ø 3,0 mm.
- DABB-C for boring
  DABB-N for profiling and corner grooving



## ANX
→ M58-69

**High speed cutter for Non-ferrous Metal**

- Achieves feeds of over vf = 30.000 mm/min
- 6 different edge preparations
- Simple screw-fastening structure enables fine adjustments to be made easily
- Precise applications of coolant to the machining point
- Milling cutter range with diameter from Ø 32-160 mm



## RF
→ M70

**High speed face mill for Aluminium**

- Finishing and roughing aluminium alloys and non-ferrous materials
- High precision and highspeed machining vc = 5000 m/min
- Alumimum alloy body Run-out less than 10 µm
- Easy assembling



## SRF
→ M71

**High speed face mill for Aluminium**


- Small diameter cutter for small machines
- High speed roughing and finishing with SumiDia DA2200
- High speed capability of rpm = 20.000
- Economical PCD insert NF type



## FMU
→ M72-73

**"BN Finish Mill" for finishing grey cast iron**


- High speed machining vc = 1500 m/min
- Excellent surface roughness Rz = 3,2
- Run-out less than 10 µm
- Easy assembling



## BNES
→ M74

**"Helical Master" SUMIBORON Endmill**

- Spiral CBN brazed cutting edge for super finishing hardened steel (HRC 50 – 60)
- Dry machining
- Stable cutting
- High accuracy
- Excellent swarf evacuation



## BNBP
→ M75

**"Mould Finish Master" SUMIBORON Micro Ball Nose Endmills**


- High precision machining of hardened steels < HRC 70 with long tool life
- Super tough grade SUMIBORON BN350 prevents chipping of the cutting edge
- R accuracy : ±0,005 mm



## NPDRS / NPDB(S)
→ M76-77

**"Mould Finish Master" SUMIDIA Binderless Endmills**

- NPDRS - radius endmills
- NPDB(S) - ball nose endmills
- For finishing of carbide and brittle materials
- High precision machining and long tool life



## DAL / DDL / DML
→ M78-79

**High precision SUMIDIA Drills**

- PCD cutting edge is brazed on to a solid carbide shank.
- From general to high precision drilling of Aluminium alloys
- DML type is suitable for chamfering and stepped drilling


# BSME/SEXC Series

## Features






- New ultra small boring bar with CBN cutting edge
- Internal coolant
- Easy setting and handling
- High accuracy
- Carbide body for high rigidity
- One sleeve for different diameters




## Basic System




## 2 Types of CBN Small Hole Boring Bar System

| BSME - CBN Brazed Cutting Edge Type | SEXC - Indexable CBN Insert Type |
|---|---|
| Min. bore diameter: Ø 2,5 – 5,0 mm | Min. bore diameter: Ø 4,0 – 6,0 mm |
| Unique cutting edge shape with high quality and sharpness  Internal coolant hole (standard) | 2 corner inserts  Internal coolant hole (standard) |
|   |   |
| Excellent repeatability of boring bar (deviation within 0,020 mm)  Clamp screws<br>Location pin for controlled cutting edge position | |


## Application Range




## Recommended Cutting Conditions


| | | |
|---|---|---|
| Spindle Speed (*n*) | >2000 $min^{-1}$ | Low speed may cause chattering and chipping on the cutting edge. |
| Depth of Cut ($a_p$) | 0,01 – 0,15 mm | Excessive depth of cut may cause larger tool deflection resulting in deterioration of bore accuracy. |
| Feed Rate (f) | 0,01 – 0,1 mm/rev | - |

## Accessories




## Mounting Instruction

1. Insert alignment tool into the sleeve until you connect with the pin inside.
   Gently lock the screws to hold.



2. Locate the sleeve into your tool-holding system.
   Gently lock the screws to hold.






3. Clock the flat of the alignment tool into a straight position.



After adjustment, equipped boring bar has automatically cutting peak height of zero on the center of tool.





4. Use pre setting machine to set the diameter of the boring bar.

## Application Example

### BSME Hardened Alloy Steel Valve Component

The BSME type provides stable machining.
Tool life is over 2 times longer than competitor´s CBN tool.









| | |
|---|---|
| Work Material: | Hardened alloy steel valve component (automotive component) |
| Tool: | BSME R50020D2S6 |
| Grade: | BN2000 |
| Cutting Conditions: | $v_c$ = 135 m/min |
| | f = 0,02 mm/rev |
| | $a_p$ = 0,10 mm |
| | Dry |

### SEXC Bearing Steel Small Automotive Component

The SEXC type provides drastically reduced tool costs.
Tool life is 1,5 times longer than competitor´s brazed CBN tool.




| | |
|---|---|
| Work Material: | Bearing steel small automotive component (60 HRC) |
| Holder: | E06D2 SEXC R/L03-04P |
| Insert: | ECXA 030X02LF (BN2000) |
| Cutting Conditions: | $v_c$ = 50 m/min (4.000 rpm) |
| | f = 0,02 mm/rev |
| | $a_p$ = 0,02 mm |
| | Wet |

# BSME Series

## BSME-Type with Internal Coolant

**BSME**
General, Facing




Fig. 1






Fig. 2





Sharp edge (no honing)


## ■ Boring Bar

| Description | Grade | | Dimensions (mm) | | | | | | | Fig. | Applicable Sleeve |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | BN2000 | | DMIN | DN | WF | CDX | LF | DCON | RE | | |
| | R | L | | | | | | | | | |
| BSME R/L 25020D2S6 | ● | ● | 2,5 | 2,0 | 1,20 | 5,3 | 32,0 | 6,0 | 0,2 | 1 | HBSM6020 |
| BSME R/L 25020D3S6 | ● | ● | | | | 7,8 | 34,5 | | | | |
| BSME R/L 25020D4S6 | ❑ | ❑ | | | | 10,3 | 37,0 | | | | |
| BSME R/L 30020D2S6 | ● | ● | 3,0 | 2,5 | 1,45 | 6,3 | 32,8 | | | 2 | |
| BSME R/L 30020D3S6 | ● | ● | | | | 9,3 | 35,8 | | | | |
| BSME R/L 30020D4S6 | ❑ | ❑ | | | | 12,3 | 38,8 | | | | |
| BSME R/L 35020D2S6 | ● | ● | 3,5 | 3,0 | 1,70 | 7,3 | 33,5 | | | | |
| BSME R/L 35020D3S6 | ● | ● | | | | 10,8 | 37,0 | | | | |
| BSME R/L 35020D4S6 | ❑ | ❑ | | | | 14,3 | 40,5 | | | | |
| BSME R/L 40020D2S6 | ● | ● | 4,0 | 3,5 | 1,95 | 8,3 | 33,9 | | | | |
| BSME R/L 40020D3S6 | ● | ● | | | | 12,3 | 37,9 | | | | |
| BSME R/L 40020D4S6 | ❑ | ❑ | | | | 16,3 | 41,9 | | | | |
| BSME R/L 45020D2S6 | ● | ● | 4,5 | 4,0 | 2,20 | 9,3 | 35,0 | | | | |
| BSME R/L 45020D3S6 | ● | ● | | | | 13,8 | 39,5 | | | | |
| BSME R/L 45020D4S6 | ❑ | ❑ | | | | 18,3 | 44,0 | | | | |
| BSME R/L 50020D2S6 | ● | ❑ | 5,0 | 4,5 | 2,45 | 10,3 | 35,8 | | | | |
| BSME R/L 50020D3S6 | ● | ● | | | | 15,3 | 40,8 | | | | |
| BSME R/L 50020D4S6 | ❑ | ❑ | | | | 20,3 | 45,8 | | | | |

## ■ Adapter Sleeve and Parts






| Description | Stock | Dimensions (mm) | | Sleeve Screw | Wrench |
|---|---|---|---|---|---|
| | | DCB | LF | | |
| HBSM6020 | ● | 6,0 | 80 | BT0506 | TH025 |

## ■ Alignment Tool



| Description | Stock |
|---|---|
| AFBSM60 | ● |

## ■ Identification Details

| B S M | E | R/L | 3 5 0 | 2 0 | D 3 | S 6 |
|---|---|---|---|---|---|---|
| Sumitomo CBN Product Special Mini | Solid Carbide Bar with Inner Coolant | R: Right Hand L: Left Hand | Minimum Bore Diameter (ø 3,5 mm) | Nose Radius of Edge (ø 0,20 mm) | L/D - Ratio of Working Length | Shank Diameter |





● = Euro stock
❑ = Delivery on request

Recommended Tightening Torque (N·m)

# SEXC Series


## SEXC-Type with Internal Coolant




## Spare Parts







## Boring Bar

| Description | Stock | | Dimensions (mm) | | | | | | | Applicable Sleeve | Insert Screw | N·m | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | DMIN | DN | WF | CDX | LF | DCON | GAMF | | | | |
| E06D2 SEXC R/L 03-04P | ● | ● | 4,0 | 3,75 | 1,95 | 8 | 33,75 | 6,0 | 13° | HBSM6020 | MIB1,6–2,0 | 0,2 | SDBSM |
| E06D3 SEXC R/L 03-04P | ● | ● | | | | 12 | 37,75 | | | | | | |
| E06D2 SEXC R/L 03-05P | ● | ● | 5,0 | 4,75 | 2,45 | 10 | 35,25 | | 12° | | MIB1,6–2,5 | | |
| E06D3 SEXC R/L 03-05P | ● | ● | | | | 15 | 40,25 | | | | | | |
| E06D2 SEXC R/L 03-06P | ● | ● | 6,0 | 5,75 | 2,95 | 12 | 36,75 | | 11° | | MIB1,6–3,0 | | |
| E06D3 SEXC R/L 03-06P | ● | ● | | | | 18 | 42,75 | | | | | | |

## Adapter Sleeve and Parts







| Description | Stock | Dimensions (mm) | | Sleeve Screw | Wrench |
|---|---|---|---|---|---|
| | | DCB | LF | | |
| HBSM6020 | ● | 6,0 | 80 | BT0506 | TH025 |

## Alignment Tool



| Description | Stock |
|---|---|
| AFBSM60 | ● |

## CBN Insert




| Description | Grade | | Nose Radius RE (mm) | Cutting Edge Preparation |
|---|---|---|---|---|
| | BN2000 | BN7000 | | |
| ECXA030X02 LE NU2 | ● | | 0,2 | sharp + hone |
| ECXA030X02 LF NU2 | ● | ● | 0,2 | sharp |

Notes:

Applicable wrench SDBSM is recommended when fastening the insert screw.
Please check insert screw occasionally and replace it in time.

## Identification Details


**E 06 D2 S E X C R/L 03 - 04 P**


- **E** — Carbide Bar with Coolant Hole
- **06** — Shank Diameter (ø 6 mm)
- **D2** — L/D Ratio of Working Length
- **S** — Insert Clamp System S = Screw Type
- **E** — Insert Shape E = Diamond 75°
- **X** — Approch Angle of Main Cutting Edge
- **C** — Insert Relief Angle C = 7°
- **R/L** — R: Right Hand L: Left Hand
- **03** — Insert Size (ø IC)
- **04** — Minimum Bore Diameter (ø 4,0 mm)
- **P** — Standard Content includes Wrench

# BNBB Type


For Hardened Steel

**BNBB** type small hole boring tools for hardened work pieces up to diameter 3,5 mm






## „Sumiboron“ Brazed Boring Tools for Small Hole Boring


| | Cat. No. | Stock | Dimensions (mm) | | | | | Applicable holder | Grade of brazed cutting edge |
|---|---|---|---|---|---|---|---|---|---|
| | | | DMIN | DCON | LF | H | RE | | |
| BNBB (Carbide shank)   | BNBB 03 R | ▲ | 3,5 | 3 | 60 | 2,4 | 0,2 | HBB 316 | **SUMIBORON (CBN)** **BN250** |
| | BNBB 04 R | ▲ | 4,5 | 4 | 60 | 3,4 | 0,2 | HBB 416 | |
| | BNBB 05 R | ▲ | 5,5 | 5 | 80 | 4,4 | 0,2 | HBB 516 | |
| | BNBB 06 R | ▲ | 6,5 | 6 | 80 | 5,4 | 0,2 | HBB 616 | |
| | BNBB 08 R | ▲ | 8,5 | 8 | 100 | 7,4 | 0,2 | HBB 816 | |

## Holder




| Cat. No. | Stock | Dimensions (mm) | | | |
|---|---|---|---|---|---|
| | | $d_1$ | LF | $d_2$ | H |
| HBB 316 | ● | 16 | 100 | 3 | 15 |
| HBB 416 | ● | | | 4 | |
| HBB 516 | ● | | | 5 | |
| HBB 616 | ● | | | 6 | |
| HBB 816 | ● | | | 8 | |


## Spare Parts

| Screw | Wrench |
|---|---|
|  |  |
| BT 0404 | TH 020 |

## Recommended Cutting Conditions

| Work Material | SUMIBORON BN250 | | Notes |
|---|---|---|---|
| Hardened steels ($H_RC45–68$) | Cutting speed ($v_c$) | 30–150 m/min | Low speed may cause chattering in cutting process and chipping occurence on the cutting edge. |
| | Feed rate (f) | 0,03–0,1 mm/rev | – |
| | Depth of cut ($a_p$) | 0,03–0,2 mm | Excessive depth of cut may cause larger deformation of tool,resulting in deterioration of bore accuracy. |

## Precaution On Use




- Adjust overhang to achieve absolute minimum.
- For use of a small diameter brazed boring tool, select high speed and small feed rate, as much as possible.




● = Euro stock
❍ = Japan stock
▲ = To be replaced by new item
❑ = Delivery on request
Recommended Tightening Torque (N·m)


SUMIBORON Small Hole Boring Bars

# BNZ / BNB Type

BNZ type







BNB type








## Boring Bars for Small Hole Boring

| | Cat. No. | Stock | Dimensions (mm) | | | | | Applicable insert | |
|---|---|---|---|---|---|---|---|---|---|
| | | | DMIN | DCON | LF | H | GAMF | | |
| BNZ (Carbide shank)   | BNZ 606 R | ● | 7 | 6 | 80 | 5,5 | -14° | ZNEX 0401○○ |  ZNEX (CBN) |
| | BNZ 608 R | ● | 9 | 8 | 100 | 7,5 | -12° | | |
| | BNZ 610 R | ● | 11 | 10 | 125 | 9,5 | -10° | | |
| | BNZ 612 R | ● | 13 | 12 | 130 | 11 | -8 | | |
| | Holder "HBB616" for BNZ606 (ø d = 6 mm)  | | | | | | | | |
| BNB (Carbide shank)   | BNB 508 R/L | ● ● | 10 | 8 | 140 | 7 | -9° | TBGN 0601○○ |  TBGN (CBN) |
| | BNB 510 R/L | ❍ ❑ | 12 | 10 | 140 | 9 | -8° | | |
| | BNB 512 R/L | ● ● | 14 | 12 | 160 | 11 | -6° | | |
| | BNB 516 R/L | ● ● | 18 | 16 | 180 | 14 | -5° | | |
| | BNB 520 R/L | ● ● | 22 | 20 | 180 | 18 | -4° | | |

## Spare Parts for BNZ

| Holder | Screw | Wrench |
|---|---|---|
| |  |  |
| BNZ 606 R | | |
| BNZ 608 R | BFTX 0204 N | TRX 06 |
| BNZ 610 R | **0,5** (N·m) | |
| | | |


## Spare Parts for BNB


| Holder | Clamp | Clamp bold | Nut | Wrench |
|---|---|---|---|---|
| |  |  |  |  |
| BNB 508 R/L | BNBC | BH 0306 | BNBW-2 | TH 020 |
| BNB 512 R/L | BNBC | FBUP-3-A0-9 | BNBW-4 | TH 020 |
| BNB 516 R/L | BNBC | BH 0310 | BNBW-4 | TH 020 |
| BNB 520 R/L | BNBC | BH 0310 | BNBW-7 | TH 020 |

## Recommended Cutting Conditions

| | |
|---|---|
| Cutting speed | 80–120 m/min |
| Feed rate | 0,03–0,1 mm/rev |
| Depth of cut | 0,03–0,2 mm |

## Holders Performance Area




Work material: Alloy steel ($H_RC$ 60)
Cutting conditions: $v_c$ = 100 m/min
f = 0,1 mm/rev
$a_p$ = 0,2 mm

# GWB / PSC Type



CBN Grooving System for Hardened Steels

GWB Type

ISO-PSC Polygon Modular

CGA Inserts




## Features

### Tangential insert

80 degree tangentially mounted insert improves rigidity



### Double clamping system

The double clamping system increases stability so even axial feeds are possible.

### Coated CBN grade BNC30G




Tough new coated CBN grade for interrupted hard grooving




### Wide insert range 1,5–6,0 mm

Wide range of width's and grades for continuous and interrupted cut grooving operations


## Grades

| Grade | Application | Features |
|---|---|---|
| BN250  | Continuous grooving  | Uncoated CBN grade for continuous cut grooving applications |
| BNC30G  | Interrupted grooving  | Tough new CBN coated grade developed for interrupted cut grooving applications |


## Grooving Tool Holder GWB Type




External




## Spare Parts




## Holders

| Cat. No. | Stock | | Dimensions (mm) | | | | | | | | Appl. Insert No. | Clamp finger | Clamp screw | Insert screw | Spring | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | R | L | H | B | LF | WF | HF | HBH | CW (*) | CDX | | | | | | |
| GWB R/L 2020-45 | ❑ | ❑ | 20 | 20 | 151 (150) | 25 | 20 | 5 | 1,5≤cw≤4,5 | 3,5 – 5,0 | ❶ | TF 72 (Right handed) TF 73 (Left handed) | BX 0520T | BFTX 0511N | GSP 06 | TRX 20 |
| GWB R/L 2525-45 | ● | ● | 25 | 25 | 151 (150) | 30 | 25 | – | | | | | | | | |
| GWB R/L 2525-60 | ● | ● | 25 | 25 | 151 | 30 | 25 | – | 4,5≤cw≤6,0 | 5,0 | ❷ | | | | | |

Right handed tool holders are applicable with right handed inserts.

Remark: Inserts are not included.



● = Euro stock
❑ = Delivery on request


▲ = To be replaced by new item


Recommended Tightening Torque (N·m)

# GWB / PSC Type

## ISO-PSC Polygon Modular CGA Grooving System







## Holders

| Cat. No. | R | L | Ø (mm) | F (mm) | L (mm) | Cap Screw (7,5 N·m) | Wrench |
|---|---|---|---|---|---|---|---|
| PSC 40GM00 R/L | ● | ● | 40 | 22 | 82,0 | BFTX0619N | LT25 |
| PSC 50GM00 R/L | ● | ● | 50 | 27 | | | |
| PSC 40GM90 R/L | ● | ● | 40 | 43 | 52,5 | | |
| PSC 50GM90 R/L | ● | ● | 50 | 48 | 55,0 | | |

## Cassette

| Cat. No. | R | L | Grooving Width (mm) | Grooving Depth (mm) | Inserts | Insert Screw (5,0 N·m) | Wrench | Spring | Clamp Finger | Cap Screw (3,0 N·m) | Wrench |
|---|---|---|---|---|---|---|---|---|---|---|---|
| GWBCM R/L 45 | ● | ● | 1,5–2,0 | 3,5 | CGA1504□□0 | BFTX0511N | TRX20 | SCP4A | | | LH030 |
| | | | 2,5–3,0 | 4,0 | | | | | | | |
| GWBCM R/L 60 | ● | ● | 3,5–6,0 | 5,0 | CGA1506□□0 | | | | | | |

## CGA Inserts




| Cat. No. | Stock BN250 R | Stock BN250 L | Stock BNC30G R | Stock BNC30G L | Stock BN2000 R | Stock BN2000 L | Dimensions (mm) CW | CDX | IC | S | Insert No. | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| CGA R/L 1504 150 | ▲ | ▲ | ● | ● | | | 1,5 | 3,5 | 15,875 | 4,76 | | GWB R/L 2020-45<br>GWB R/L 2525-45<br>GWBCM R/L-45 |
| R/L 1504 200 | ▲ | ▲ | ● | ❑ | | ❍ | 2,0 | | | | | |
| R/L 1504 250 | ▲ | ▲ | ● | ● | | | 2,5 | 4,0 | | | | |
| R/L 1504 300 | ▲ | ▲ | ● | ● | | | 3,0 | | | | | |
| R/L 1504 350 | ▲ | ▲ | ● | ● | | | 3,5 | 5,0 | | | | |
| R/L 1504 400 | ▲ | ▲ | ● | ❑ | | | 4,0 | | | | | |
| R/L 1504 450 | ▲ | ▲ | ❑ | ● | | | 4,5 | | | | | |
| CGA R/L 1506 500 | ▲ | ▲ | ● | ● | | ❍ | 5,0 | | | 6,35 | | GWB R/L 2525-60<br>GWBCM R/L-60 |
| R/L 1506 550 | ▲ | ▲ | ● | ● | | | 5,5 | | | | | |
| R/L 1506 600 | ▲ | ▲ | ● | ❑ | | | 6,0 | | | | | |

Special widths available on request

## Recommended Cutting Conditions


| Material | Hardened steel |
|---|---|
| Cutting speed (m/min) | 60 80 120 150 |
| Feed rate (mm/rev) | 0,03 0,04 0,08 0,1 |
| Grade | BN250, BNC30G |

Coolant:
Dry / wet (for continuous cut)
Dry only (for interrupted cut)


Remarks:
To avoid thermal cracking of the cutting edge when interrupted cutting please ensure workpiece remains dry.

# BNGG Type


For Hardened Steel



BNGG_TT




## „Sumiboron“ Holders




| Cat. No. | Stock | | Dimensions (mm) | | | Applicable Insert |
|---|---|---|---|---|---|---|
| | R | L | WF | CDX | LF | |
| BNGG R/L 2525-TT | ▲ | ❑ | 28,5 | 5 | 150 | BNTT 1020 R/L<br>BNTT 1530 R/L |




## Inserts




| Cat. No. | Stock | | | | Dimensions (mm) | | | | Applicable Holder |
|---|---|---|---|---|---|---|---|---|---|
| | BN250 | | BNX20 | | | | | | |
| | R | L | R | L | Pitch | RE | LF | S | |
| BNTT 1020 R/L | ▲ | ▲ | ● | ❑ | 1,0–2,0 | 0,14 | 25 | 6,0 | BNGG R/L 2525 -TT |
| BNTT 1530 R/L | ▲ | ▲ | ● | ❑ | 1,5–3,0 | 0,2 | 25 | 6,0 | |

● Inserts also suitable for existing BNG2525R type holders

## Spare Parts

| Holder | Support | Clamp | Adjust screw | Spring | Screw | Wrench | |
|---|---|---|---|---|---|---|---|
|  |  |  |  |  |  |  |  |
| BNGG R/L 2525 - TT | BNGS R/L TT | BNGC R/L | FMJ | GSP 6 | BX 0615 (for clamp )<br>BX 0414 (for support) | LH 050<br>LH 030 | ø1,8x45 |

## Recommended Cutting Conditions

Threading

| | |
|---|---|
| Cutting speed ($v_c$) | 80–120 m/min |
| Feed rate (f) | Max. pitch: 3,0 mm |






● = Euro stock
❑ = Delivery on request


▲ = To be replaced by new item

# SUMIDIA Small Hole Boring Bars
# DABB Type






## ■ „Sumidia“ Brazed Boring Tools for Small Hole Boring

**DABB-CR**



**DABB-NR**




| DABB (Solid carbide shank) | Cat. No. | Stock | Dimensions (mm) | | | | | Applicable Holder |
|---|---|---|---|---|---|---|---|---|
| | | DA2200 | DMIN | DCON | LF | H | RE | |
| For small boring   | DABB 025 CR | ▲ | 3,0 | 2,5 | 60 | 2,2 | 0,1 | HBB 2516 |
| | DABB 035 CR | ▲ | 4,0 | 3,5 | 60 | 3,2 | 0,1 | HBB 3516 |
| | DABB 045 CR | ▲ | 5,0 | 4,5 | 80 | 4,1 | 0,1 | HBB 4516 |
| | DABB 060 CR | ▲ | 7,0 | 6,0 | 80 | 5,2 | 0,1 | HBB 616 |
| For profiling and corner grooving   | DABB 025 NR | ▲ | 3,0 | 2,5 | 60 | 2,2 | 0,1 | HBB 2516 |
| | DABB 035 NR | ▲ | 4,0 | 3,5 | 60 | 3,2 | 0,1 | HBB 3516 |
| | DABB 045 NR | ▲ | 5,0 | 4,5 | 80 | 4,1 | 0,1 | HBB 4516 |
| | DABB 060 NR | ▲ | 7,0 | 6,0 | 80 | 5,2 | 0,1 | HBB 616 |

## ■ Recommended Cutting Conditions


| Spindle revolution | Feed rate | Depth of cut | Coolant |
|---|---|---|---|
| > 2000 rpm | 0,03 – 0,1 mm/rev | 0,03 – 0,2 mm | Wet |

## ■ Holder




| Cat. No. | Stock | Dimensions (mm) | | | |
|---|---|---|---|---|---|
| | | $d_1$ | LF | $d_2$ | H |
| HBB 2516 | ● | 16 | 100 | 2,5 | 15 |
| HBB 3516 | ● | | | 3,5 | |
| HBB 4516 | ● | | | 4,5 | |
| HBB 616 | ● | | | 6,0 | |

## ■ Spare Parts

| Screw | Wrench |
|---|---|
|  |  |
| BT 0404 | TH 020 |

Expansion



## Features









- **Drastically Reduced Runout Adjustment Time**
  Simple screw-fastening structure enables fine adjustments to be made easily.
- **Blade Through Coolant**
  Secures a supply of coolant to the cutting edge and breaks chips thoroughly.
- **Lightweight Aluminum Alloy Body**
  Utilizing aluminum alloy to achieve a total weight of less than 1,3 kg for a Ø 125 mm cutter with 22 teeth.

## Product Range

| Type | Cat. No. | Body Material | Diameter Range (mm) / No of Teeth | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | Ø 25 | Ø 30 | Ø 32 | Ø 40 | Ø 50 | Ø 63 | Ø 80 | Ø 100 | Ø 125 | Ø 160 |
| Shell | ANXA 16000RS | Aluminum Alloy | → G78 | | | | | | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | 12, 20, 28 |
| | ANXA 16000R (Inch) | Aluminum Alloy | | | | | | | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | 12, 20, 28 |
| | ANXS 16000RS | Steel | → G80 | | | 4, 6 | 4, 6, 9 | 6, 8, 12 | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | |
| | ANXS 16000R (Inch) | Steel | | | | | | 6, 8, 12 | 6, 10, 14 | 8, 12, 18 | 10, 14, 22 | |
| Shank | ANXS 16000E | Steel | 2 | 3, 4 | 3, 4 | 4, 6 | 4, 6, 9 | → H84 | | | | |
| Modular | ANXS 16000M | Steel | 2 | 3, 4 | 3, 4 | 4, 6 | | → H86 | | | | |


Inch Inch Bore


## Blade Selection Guide

| Work Material | N | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| Applications | Finishing / Light Cutting | General Purpose | Roughing | | Combined Milling *1 | Corner Radius Milling | Corner Radius Milling | Finishing | Burr-free / Mirror Finishing |
| Features | Low Cutting Force | Standard | Long Edge | High Strength | High Strength | Corner Radius 0,4 | Corner Radius 0,8 | Wiper | Wiper |
| Type | L | G | GX | H | GB | - | - | W | WS |
| Cutting Edge Shape |  |  |  |  |  |  |  |  |  |
| Edge Length(*2) | 6,0 mm | 6,0 mm | 9,0 mm | 6,0 mm | 6,0 mm | 6,0 mm | 6,0 mm | 2,0 mm | — |

*1 Machining of components combining aluminum alloy and cast iron

## Edge Selection Guide








*2 Edge length
GX type = 9,0 mm

- **Reduces Running Costs by Drastically Increasing Blade, Insert Regrinding Allowance (to 1,0 mm)**

Assuming 0,2 mm of regrinding each time, an edge can be used up to 6 times.
(Peripheral edge cannot be reground.)




If you wish to use reground blades you shall use sets of blades with matching size of the same level in order to keep the balance.

## Performances


### High-Speed / High-Efficiency Cutting

Realizes ultra-high efficiency machining with $v_f$ = 30.000 mm/min




Comparison: Cutter Diameter Ø 100 mm


| | Spindle Speed $min^{-1}$ | Number of Teeth | Feed Rate $v_f$ (mm/min) |
|---|---|---|---|
| ANX Series | 18.000 | 18 | 32.400 |
| Competitor | 9.500 | 12 | 11.400 |




### Drastically Reduces Runout Adjustment Time

– Simple screw-fastening structure
– Enables fine adjustments to be made easily
– High-rigidity body




### Chip Control




Blade-Through Coolant Chip Breaking




ALNEX ANX Series




Competitor

| | |
|---|---|
| Work Material: | G-AlSi12Cu |
| Cutting Conditions: | $v_c$ = 2500 m/min, $f_z$ = 0,05 mm/t, $a_p$ = 0,5 mm, wet |

## Adjustment of the Blades, Runout Alignment

① 

② 

③ 

④ 

| ① | ② | ③ | ④ |
|---|---|---|---|
| Insert the blade into its seat. | While holding the blade against the seat, install the clamping bolt using the provided wrench, pre-tightening the bolt. (recommended pre-torque is 1 N·m) | Using the provided wrench for the height adjustment screw, set the height to your predetermined value. | Fully tighten the clamp bolt. (recommended torque is 2 N·m) |

Expansion




## CVD Single Crystal Diamond SCV10 Wiper Blade

Wiper blade adopts high-strength single-crystal diamond using Sumitomo Electric Hardmetal's vapour phase synthesis technology.
Sharp cutting edge realises burr-free, mirror finish surface quality in aluminum alloy machining.
Superior wear resistance maintains cutting edge sharpness for a long time, reducing total tool costs.


## Burr-free

Sharp cutting edge and excellent wear resistance suppress burrs over the long term.




## Mirror Finishing

Sharp cutting edge achieves mirror finish with cutting alone.




Workpiece surface after machining

## Polycrystalline Diamond SUMIDIA DA1000 / DA90

Through the ideal combination of diamond particle size and binder, SUMIDIA DA1000/DA90 possess various features and is suitable for all kinds of applications such as machining of aluminum alloy and cemented carbide.

## Grades, Features and Applications

| Grade | Features | Applications | Diamond share (%) | Average grain size of diamond particles (μm) | Hardness HK (GPa) | TRS (GPa) |
|---|---|---|---|---|---|---|
| DA1000 | High-density sintered grade made of ultra-fine grain diamond that exhibits excellent wear and fracture resistance as well as edge sharpness. | Machining of High-Silicon Aluminum Alloy, Rough, Interrupt and Finish Machining of Aluminum Alloy, Woodcraft or Wooden Board Cutting/Facing, General Finishing of Non-Ferrous Metals | 90–95 | ≤ 0,5 | 50–60 | ≈ 2,60 |
| DA90 | Contains coarser diamond particles than other grades, giving it good wear resistance suitable for the machining of carbides and high-silicon aluminum. Shows the highest diamond content for excellent wear resistance. | Machining of High-Silicon Aluminum Alloy, Machining of Aluminum Composite (MMC), Green or Semi-Sintered Cemented Carbide & Ceramic Roughing, Machining of Sintered Ceramic/Stone/Rock | 90–95 | ≤ 50 | 50–65 | ≈ 1,10 |

## Grade Applications

| | Work Material | Applicable Grade | Example Parts |
|---|---|---|---|
| Aluminum | Sintered Aluminum, Wrought Aluminum Alloy | DA1000 | Piston Liners, Machine Parts, etc. |
| | Alloys for Die Casting | | Transmission Case, Oil Pan, Cylinder Block |
| | Alloys for Casting Low Si (≤ 12%) | | Cylinder Head |
| | Alloys for Casting High Si (> 12%) | | Cylinder Block |
| Non-ferrous metal | Non-Ferrous Sintered Alloy | DA1000 | Bush |
| | Gunmetal, Carbon | | Connecting Rod |
| | Fe Combined | DA90 | Cylinder Block, Bearing Cap |


# ANXA 16000 R(S)

Expansion

| Rake Angle | Radial | +5° |
|---|---|---|
| | Axial | +5° |

3 mm 90°






## Body - ANXA (Aluminum Alloy)

Dimensions (mm)

| | Cat. No. | Stock | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | ANXA 16080RS06 | ❍ | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 6 | 0,5 |
| | 16080RS10 | ● | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 10 | 0,5 |
| | 16080RS14 | ● | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 14 | 0,5 |
| | 16100RS08 | ❍ | 98 | 100 | 50 | 59 | 27 | 12,4 | 7 | 34 | 35 | 14 | 8 | 0,8 |
| | 16100RS12 | ● | 98 | 100 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 12 | 0,8 |
| | 16100RS18 | ● | 98 | 100 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 18 | 0,9 |
| | 16125RS10 | ❍ | 123 | 125 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 10 | 1,2 |
| | 16125RS14 | ● | 123 | 125 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 14 | 1,2 |
| | 16125RS22 | ● | 123 | 125 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 22 | 1,3 |
| | 16160RS12 | ❍ | 158 | 160 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | 29 | 12 | 2,6 |
| | 16160RS20 | ❍ | 158 | 160 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | 29 | 20 | 2,6 |
| | 16160RS28 | ❍ | 158 | 160 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | 29 | 28 | 2,6 |
| Inch | ANXA 16080R06 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 6 | 0,5 |
| | 16080R10 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 10 | 0,5 |
| | 16080R14 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 14 | 0,5 |
| | 16100R08 | ❍ | 98 | 100 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 8 | 0,8 |
| | 16100R12 | ❍ | 98 | 100 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 12 | 0,9 |
| | 16100R18 | ❍ | 98 | 100 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 18 | 0,9 |
| | 16125R10 | ❍ | 123 | 125 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 10 | 1,2 |
| | 16125R14 | ❍ | 123 | 125 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 14 | 1,2 |
| | 16125R22 | ❍ | 123 | 125 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 22 | 1,3 |
| | 16160R12 | ❍ | 158 | 160 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 55 | 30 | 12 | 2,3 |
| | 16160R20 | ❍ | 158 | 160 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 55 | 30 | 20 | 2,4 |
| | 16160R28 | ❍ | 158 | 160 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 55 | 30 | 28 | 2,6 |

Blades are sold separately. If using a blade for corner radius machining (ANB1604R/ANB1608R), DC = DCX.
The weight includes the weight of the blade and parts (excluding the centre bolt).
All aluminium alloy bodies with a maximum blade diameter (DCX) of Ø 80 to Ø 125 have the same diameter (DCB) of the retainer hole (metric Ø 27/in Ø 25,4).

## Identification Details

| ANX | A | 16 | 100 | R | S | 18 |
|---|---|---|---|---|---|---|
| Cutter Series | Aluminum Alloy Body | Blade Size | Cutter Diameter | Feed Direction | Metric | Number of Teeth |



● = Euro stock
❍ = Japan stock
❑ = Delivery on request
Recommended Tightening Torque (N·m)

Expansion

## Blades

Dimensions (mm)

| Application | SUMIDIA | | CVD |
|---|---|---|---|
| High Speed / Light Cut | N | KN | N |
| General Purpose | N | KN | |
| Roughing | N | KN | |

| Cat. No. | DA1000 | DA90 | SCV10 | Cutting Edge Length | RE | Wiper Edge Shape | Applications | Fig. |
|---|---|---|---|---|---|---|---|---|
| ANB 1600R-L | ● | | – | 6,0 | – | Linear | Low Cutting Force | 1 |
| 1600R-G | ● | | – | 6,0 | – | Arc-Shaped | General Purpose | 1 |
| 1600R-GB | | ● | – | 6,0 | – | Arc-Shaped | Combined Milling* | 1 |
| 1600R-H | ● | – | – | 6,0 | – | Arc-Shaped | Strong Edge | 1 |
| 1600R-GX | ❍ | | – | 9,0 | – | Arc-Shaped | Long Edge | 2 |
| 1604R | ❍ | | – | 6,0 | 0,4 | Linear | Corner Radius | 3 |
| 1608R | ❍ | | – | 6,0 | 0,8 | Linear | Corner Radius | 3 |
| 1600R-W | ❍ | | – | 2,0 | – | Arc-Shaped | Wiper | 4 |
| 1600R-WS | – | – | ❒ | – | – | Arc-Shaped | Wiper | 5 |


Fig. 1 



Fig. 2 



Fig. 3 




Fig. 4 


Fig. 5 


Wiper Blade

Wiper Blade

* Cast Iron/Aluminum Alloy

## Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 2.000–**2.500**–3.000 | 0,05–**0,13**–0,20 | DA1000 |

Si content > 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 400–**600**–800 | 0,05–**0,13**–0,20 | DA1000 DA90 |

Combined Milling of Cast Iron/Aluminum Alloy

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| K N | Cast Iron/ Aluminum Alloy | – | 300–**400**–500 | 0,05–**0,13**–0,20 | DA90 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

## Max. Allowable Spindle Speed

| Cat. No. | n max (min$^{-1}$) |
|---|---|
| ANXA 16080RS06 | 20.000 |
| 16080RS10 | 20.000 |
| 16080RS14 | 20.000 |
| 16100RS08 | 18.000 |
| 16100RS12 | 18.000 |
| 16100RS18 | 18.000 |
| 16125RS10 | 16.000 |
| 16125RS14 | 16.000 |
| 16125RS22 | 16.000 |
| 16160RS12 | 14.000 |
| 16160RS20 | 14.000 |
| 16160RS28 | 14.000 |
| ANXA 16080R06 | 20.000 |
| 16080R10 | 20.000 |
| 16080R14 | 20.000 |
| 16100R08 | 18.000 |
| 16100R12 | 18.000 |
| 16100R18 | 18.000 |
| 16125R10 | 16.000 |
| 16125R14 | 16.000 |
| 16125R22 | 16.000 |
| 16160R12 | 14.000 |
| 16160R20 | 14.000 |
| 16160R28 | 14.000 |

## Spare Parts


Sold separately.

| Applicable Cutters | Clamp Screw | | Adjustment Screw | Wrench | Adjustment Wrench | Centre Bolt | | Assembly Wrench |
|---|---|---|---|---|---|---|---|---|
| ANXA 16080R(S)_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | BXH1235-D33 | 50 | HFVT |
| 16100R(S)_ _ | | | | | | | | |
| 16125R(S)_ _ | | | | | | | | |
| 16160R(S)_ _ | | | | | | BXH2036-D50 | 200 | |

The adjustment spanner (ANT) can also be used for height adjustment of the RF type cutters for high speed machining and the HF type cutters for high efficiency machining.

### Wiper Blade Step Amount

When using the wiper blade, in order to maintain balance, be sure to use a cutter with an even number of cutting edges and place the wiper blades at opposite positions.



# ANXS 16000 R(S)

Expansion

| Rake Angle | | |
|---|---|---|
| | Radial | +5° |
| | Axial | +5° |

3 mm 90°



Fig. 1






Fig. 2




## Body - ANXS (Steel)

Dimensions (mm)

| | Cat. No. | Stock | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | D1 | D2 | No. of Teeth | Weight (kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Metric | ANXS 16040RS04 | ❍ | 38 | 40 | 38,5 | 40 | 16 | 8,4 | 5,6 | 26 | 14 | 9 | 4 | 0,3 | 1 |
| | 16040RS06 | ● | 38 | 40 | 38,5 | 40 | 16 | 8,4 | 5,6 | 26 | 14 | 9 | 6 | 0,3 | 1 |
| | 16050RS04 | ❍ | 48 | 50 | 48,5 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 4 | 0,4 | 1 |
| | 16050RS06 | ● | 48 | 50 | 48,5 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 6 | 0,4 | 1 |
| | 16050RS09 | ❍ | 48 | 50 | 48,5 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 9 | 0,5 | 1 |
| | 16063RS06 | ❍ | 61 | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 6 | 0,7 | 1 |
| | 16063RS08 | ● | 61 | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 8 | 0,7 | 1 |
| | 16063RS12 | ● | 61 | 63 | 50 | 40 | 22 | 10,4 | 6,3 | 26 | 18 | 11 | 12 | 0,7 | 1 |
| | 16080RS06 | ❍ | 78 | 80 | 50 | 40 | 27 | 12,4 | 7 | 34 | 35 | 14 | 6 | 1,2 | 1 |
| | 16080RS10 | ❍ | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 10 | 1,2 | 1 |
| | 16080RS14 | ❍ | 78 | 80 | 50 | 50 | 27 | 12,4 | 7 | 34 | 35 | 14 | 14 | 1,2 | 1 |
| | 16100RS08 | ❍ | 98 | 100 | 80 | 50 | 32 | 14,4 | 8 | 32 | 46 | – | 8 | 1,9 | 2 |
| | 16100RS12 | ❍ | 98 | 100 | 80 | 50 | 32 | 14,4 | 8 | 32 | 46 | – | 12 | 2,0 | 2 |
| | 16100RS18 | ❍ | 98 | 100 | 80 | 50 | 32 | 14,4 | 8 | 32 | 46 | – | 18 | 2,0 | 2 |
| | 16125RS10 | ❍ | 123 | 125 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | – | 10 | 3,8 | 2 |
| | 16125RS14 | ❍ | 123 | 125 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | – | 14 | 3,9 | 2 |
| | 16125RS22 | ❍ | 123 | 125 | 80 | 63 | 40 | 16,4 | 9 | 35 | 52 | – | 22 | 3,9 | 2 |
| Inch | ANXS 16063R06 | ❍ | 61 | 63 | 50 | 50 | 25,4 | 9,5 | 6 | 31 | 20 | 14 | 6 | 0,9 | 1 |
| | 16063R08 | ❍ | 61 | 63 | 50 | 50 | 25,4 | 9,5 | 6 | 31 | 20 | 14 | 8 | 0,9 | 1 |
| | 16063R12 | ❍ | 61 | 63 | 50 | 50 | 25,4 | 9,5 | 6 | 31 | 20 | 14 | 12 | 0,9 | 1 |
| | 16080R06 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 6 | 1,2 | 1 |
| | 16080R10 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 10 | 1,2 | 1 |
| | 16080R14 | ❍ | 78 | 80 | 50 | 50 | 25,4 | 9,5 | 6 | 34 | 35 | 14 | 14 | 1,2 | 1 |
| | 16100R08 | ❍ | 98 | 100 | 80 | 50 | 31,75 | 12,7 | 8 | 36 | 42 | – | 8 | 1,9 | 2 |
| | 16100R12 | ❍ | 98 | 100 | 80 | 50 | 31,75 | 12,7 | 8 | 36 | 42 | – | 12 | 2,0 | 2 |
| | 16100R18 | ❍ | 98 | 100 | 80 | 50 | 31,75 | 12,7 | 8 | 36 | 42 | – | 18 | 2,0 | 2 |
| | 16125R10 | ❍ | 123 | 125 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 52 | – | 10 | 3,9 | 2 |
| | 16125R14 | ❍ | 123 | 125 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 52 | – | 14 | 3,9 | 2 |
| | 16125R22 | ❍ | 123 | 125 | 80 | 63 | 38,1 | 15,9 | 10 | 42,5 | 52 | – | 22 | 3,9 | 2 |

Blades are sold separately. If using a blade for corner radius machining (ANB1604R/ANB1608R), DC = DCX.
The weight includes the weight of the blade and parts (excluding the centre bolt).

## Identification Details

| ANX | S | 16 | 100 | R | S | 18 |
|---|---|---|---|---|---|---|
| Cutter Series | Steel Body | Blade Size | Cutter Diameter | Feed Direction | Metric | Number of Teeth |



● = Euro stock
❍ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

Expansion

## Blades

Dimensions (mm)

| Application | SUMIDIA | | CVD |
|---|---|---|---|
| High Speed / Light Cut | N | KN | N |
| General Purpose | N | KN | |
| Roughing | N | KN | |

| Cat. No. | DA1000 | DA90 | SCV10 | Cutting Edge Length | RE | Wiper Edge Shape | Applications | Fig. |
|---|---|---|---|---|---|---|---|---|
| ANB 1600R-L | ● | | – | 6,0 | – | Linear | Low Cutting Force | 1 |
| 1600R-G | ● | | – | 6,0 | – | Arc-Shaped | General Purpose | 1 |
| 1600R-GB | | ● | – | 6,0 | – | Arc-Shaped | Combined Milling* | 1 |
| 1600R-H | ● | – | – | 6,0 | – | Arc-Shaped | Strong Edge | 1 |
| 1600R-GX | ❍ | | – | 9,0 | – | Arc-Shaped | Long Edge | 2 |
| 1604R | ❍ | | – | 6,0 | 0,4 | Linear | Corner Radius | 3 |
| 1608R | ❍ | | – | 6,0 | 0,8 | Linear | Corner Radius | 3 |
| 1600R-W | ❍ | | – | 2,0 | – | Arc-Shaped | Wiper | 4 |
| 1600R-WS | – | – | ❒ | – | – | Arc-Shaped | Wiper | 5 |


Fig. 1




Fig. 2






Fig. 3



Fig. 4



Wiper Blade

Fig. 5



Wiper Blade

* Cast Iron/Aluminum Alloy

## Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 2.000–**2.500**–3.000 | 0,05–**0,13**–0,20 | DA1000 |

Si content > 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 400–**600**–800 | 0,05–**0,13**–0,20 | DA1000 DA90 |

Combined Milling of Cast Iron/Aluminum Alloy

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| K N | Cast Iron/ Aluminum Alloy | – | 300–**400**–500 | 0,05–**0,13**–0,20 | DA90 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

## Max. Allowable Spindle Speed

| Cat. No. | n max (min$^{-1}$) |
|---|---|
| ANXS 16040RS04 | 25.000 |
| 16040RS06 | 25.000 |
| 16050RS04 | 25.000 |
| 16050RS06 | 25.000 |
| 16050RS09 | 25.000 |
| 16063RS06 | 22.000 |
| 16063RS08 | 22.000 |
| 16063RS12 | 22.000 |
| 16080RS06 | 20.000 |
| 16080RS10 | 20.000 |
| 16080RS14 | 20.000 |
| 16100RS08 | 18.000 |
| 16100RS12 | 18.000 |
| 16100RS18 | 18.000 |
| 16125RS10 | 16.000 |
| 16125RS14 | 16.000 |
| 16125RS22 | 16.000 |
| ANXS 16063R06 | 22.000 |
| 16063R08 | 22.000 |
| 16063R12 | 22.000 |
| 16080R06 | 20.000 |
| 16080R10 | 20.000 |
| 16080R14 | 20.000 |
| 16100R08 | 18.000 |
| 16100R12 | 18.000 |
| 16100R18 | 18.000 |
| 16125R10 | 16.000 |
| 16125R14 | 16.000 |
| 16125R22 | 16.000 |

## Spare Parts


Sold separately.

| Applicable Cutters | Clamp Screw | | Adjustment Screw | Wrench | Adjustment Wrench | Centre Bolt | | Assembly Wrench |
|---|---|---|---|---|---|---|---|---|
| |  | N·m |  |  |  |  | N·m |  |
| ANXS 16040RS_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | BXH0825-D13 | 15 | HFVT |
| 16050RS_ _ | | | | | | BXH1030-D16 | 25 | |
| 16063RS_ _ | | | | | | | | |
| 16080RS_ _ | | | | | | BXH1235-D33 | 50 | |
| 16100RS_ _ | | | | | | BXH1635-D40 | 100 | |
| 16125RS_ _ | | | | | | BXH2036-D50 | 200 | |
| 16063R_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | BXH1235-D18 | 40 | |
| 16080R_ _ | | | | | | BXH1235-D33 | 50 | |
| 16100R_ _ | | | | | | BXH1635-D40 | 100 | |
| 16125R_ _ | | | | | | BXH2036-D50 | 200 | |

The adjustment spanner (ANT) can also be used for height adjustment of the RF type cutters for high speed machining and the HF type cutters for high efficiency machining.

### Wiper Blade Step Amount

When using the wiper blade, in order to maintain balance, be sure to use a cutter with an even number of cutting edges and place the wiper blades at opposite positions.





# ANXS 16000 E

Expansion

| Rake Angle | Radial | -2 – 0° |
|---|---|---|
| | Axial | +5° |

3 mm 90°






## Body - ANXS (Steel)

Dimensions (mm)

| Cat. No. | Stock | DC | DCX | DMM | LH | LS | LF | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|
| ANXS 16025E02 | ● | 23 | 25 | 20 | 35 | 60 | 95 | 2 | 0,2 |
| 16030E03 | ● | 28 | 30 | 20 | 35 | 60 | 95 | 3 | 0,3 |
| 16030E04 | ● | 28 | 30 | 20 | 35 | 60 | 95 | 4 | 0,3 |
| 16032E03 | ● | 30 | 32 | 20 | 35 | 60 | 95 | 3 | 0,3 |
| 16032E04 | ● | 30 | 32 | 20 | 35 | 60 | 95 | 4 | 0,3 |
| 16040E04 | ● | 38 | 40 | 20 | 40 | 60 | 100 | 4 | 0,4 |
| 16040E06 | ● | 38 | 40 | 20 | 40 | 60 | 100 | 6 | 0,5 |
| 16050E04 | ❍ | 48 | 50 | 32 | 40 | 80 | 120 | 4 | 1,0 |
| 16050E06 | ● | 48 | 50 | 32 | 40 | 80 | 120 | 6 | 1,0 |
| 16050E09 | ● | 48 | 50 | 32 | 40 | 80 | 120 | 9 | 1,0 |

Blades are sold separately. If using a blade for corner radius machining (ANB1604R/ANB1608R), DC = DCX.
The weight includes the weight of the blade and parts.

## Identification Details

| ANX | S | 16 | 032 | E | 04 |
|---|---|---|---|---|---|
| Cutter Series | Steel Body | Blade Size | Cutter Diameter | Round Shank | Number of Teeth |



● = Euro stock
❍ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

## Blades

Dimensions (mm)

| Application | SUMIDIA | | CVD |
|---|---|---|---|
| High Speed / Light Cut | N | KN | N |
| General Purpose | N | KN | |
| Roughing | N | KN | |

| Cat. No. | DA1000 | DA90 | SCV10 | Cutting Edge Length | RE | Wiper Edge Shape | Applications | Fig. |
|---|---|---|---|---|---|---|---|---|
| ANB 1600R-L | ● | | – | 6,0 | – | Linear | Low Cutting Force | 1 |
| 1600R-G | ● | | – | 6,0 | – | Arc-Shaped | General Purpose | 1 |
| 1600R-GB | | ● | – | 6,0 | – | Arc-Shaped | Combined Milling* | 1 |
| 1600R-H | ● | – | – | 6,0 | – | Arc-Shaped | Strong Edge | 1 |
| 1600R-GX | ❍ | | – | 9,0 | – | Arc-Shaped | Long Edge | 2 |
| 1604R | ❍ | | – | 6,0 | 0,4 | Linear | Corner Radius | 3 |
| 1608R | ❍ | | – | 6,0 | 0,8 | Linear | Corner Radius | 3 |
| 1600R-W | ❍ | | – | 2,0 | – | Arc-Shaped | Wiper | 4 |
| 1600R-WS | – | – | ❒ | – | – | Arc-Shaped | Wiper | 5 |


Fig. 1




Fig. 2




Fig. 3





Fig. 4



Fig. 5



Wiper Blade

Wiper Blade

* Cast Iron/Aluminum Alloy

## Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 2.000–**2.500**–3.000 | 0,05–**0,13**–0,20 | DA1000 |

Si content > 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 400–**600**–800 | 0,05–**0,13**–0,20 | DA1000 DA90 |

Combined Milling of Cast Iron/Aluminum Alloy

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| K N | Cast Iron/ Aluminum Alloy | – | 300–**400**–500 | 0,05–**0,13**–0,20 | DA90 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

## Max. Allowable Spindle Speed

| Cat. No. | n max (min$^{-1}$) |
|---|---|
| ANXS 16025E02 | 10.000 |
| 16030E03 | 10.000 |
| 16030E04 | 10.000 |
| 16032E03 | 10.000 |
| 16032E04 | 10.000 |
| 16040E04 | 10.000 |
| 16040E06 | 10.000 |
| 16050E04 | 10.000 |
| 16050E06 | 10.000 |
| 16050E09 | 10.000 |

## Spare Parts


Sold separately.

| Applicable Cutters | Clamp Screw | | Adjustment Screw | Wrench | Adjustment Wrench | Assembly Wrench |
|---|---|---|---|---|---|---|
| |  |  |  |  |  |  |
| ANXS 160_ _E_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | HFVT |

The adjustment spanner (ANT) can also be used for height adjustment of the RF type cutters for high speed machining and the HF type cutters for high efficiency machining.

### Wiper Blade Step Amount

When using the wiper blade, in order to maintain balance, be sure to use a cutter with an even number of cutting edges and place the wiper blades at opposite positions.



# Alnex
# ANXS 16000 M


New


Modular Type


| Rake Angle | | |
|---|---|---|
| | Radial | -2 – 0° |
| | Axial | +5° |

3 mm 90°








## Body - ANXS (Steel)

Dimensions (mm)

| Cat. No. | Stock | DC | DCX | DCON | CRKS | OAL | LF | LS2 | LS | L11 | H | No. of Teeth | Weight (kg) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| ANXS 16025M12Z02 | ❍ | 23 | 25 | 12,5 | **M12** | 61 | 40 | 5 | 21 | 10 | 19 | 2 | 0,1 |
| 16030M16Z03 | ❍ | 28 | 30 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 3 | 0,2 |
| 16030M16Z04 | ❍ | 28 | 30 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 4 | 0,2 |
| 16032M16Z03 | ❍ | 30 | 32 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 3 | 0,3 |
| 16032M16Z04 | ❍ | 30 | 32 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 4 | 0,3 |
| 16040M16Z04 | ❍ | 38 | 40 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 4 | 0,4 |
| 16040M16Z06 | ❍ | 38 | 40 | 17,0 | **M16** | 70 | 47 | 5 | 23 | 10 | 24 | 6 | 0,4 |

Blades are sold separately. If using a blade for corner radius machining (ANB1604R/ANB1608R), DC = DCX.
The weight includes the weight of the blade and parts.

## Identification Details

| ANX | S | 16 | 032 | M16 | Z03 |
|---|---|---|---|---|---|
| Cutter Series | Steel Body | Blade Size | Cutter Diameter | Screw size | Number of Blades |





● = Euro stock
❍ = Japan stock
❑ = Delivery on request
Recommended Tightening Torque (N·m)

## Blades

Dimensions (mm)

| Application | SUMIDIA | | CVD |
|---|---|---|---|
| High Speed / Light Cut | N | KN | N |
| General Purpose | N | KN | |
| Roughing | N | KN | |

| Cat. No. | DA1000 | DA90 | SCV10 | Cutting Edge Length | RE | Wiper Edge Shape | Applications | Fig. |
|---|---|---|---|---|---|---|---|---|
| ANB 1600R-L | ● | | – | 6,0 | – | Linear | Low Cutting Force | 1 |
| 1600R-G | ● | | – | 6,0 | – | Arc-Shaped | General Purpose | 1 |
| 1600R-GB | | ● | – | 6,0 | – | Arc-Shaped | Combined Milling* | 1 |
| 1600R-H | ● | – | – | 6,0 | – | Arc-Shaped | Strong Edge | 1 |
| 1600R-GX | ❍ | | – | 9,0 | – | Arc-Shaped | Long Edge | 2 |
| 1604R | ❍ | | – | 6,0 | 0,4 | Linear | Corner Radius | 3 |
| 1608R | ❍ | | – | 6,0 | 0,8 | Linear | Corner Radius | 3 |
| 1600R-W | ❍ | | – | 2,0 | – | Arc-Shaped | Wiper | 4 |
| 1600R-WS | – | – | ❒ | – | – | Arc-Shaped | Wiper | 5 |

Fig. 1 Fig. 2 Fig. 3






Fig. 4 Fig. 5




Wiper Blade Wiper Blade

* Cast Iron/Aluminum Alloy

## Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 2.000–**2.500**–3.000 | 0,05–**0,13**–0,20 | DA1000 |

Si content > 12,6 %

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| N | Aluminum Alloy | – | 400–**600**–800 | 0,05–**0,13**–0,20 | DA1000 DA90 |

Combined Milling of Cast Iron/Aluminum Alloy

Min. - **Optimum** - Max.

| ISO | Work Material | Hard-ness | Cutting Speed $v_c$ (m/min) | Feed Rate $f_z$ (mm/t) | Grade |
|---|---|---|---|---|---|
| K N | Cast Iron/ Aluminum Alloy | – | 300–**400**–500 | 0,05–**0,13**–0,20 | DA90 |

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

## Max. Allowable Spindle Speed

| Cat. No. | n max (min$^{-1}$) |
|---|---|
| ANXS 16025M12Z02 | 10.000 |
| 16030M16Z03 | 10.000 |
| 16030M16Z04 | 10.000 |
| 16032M16Z03 | 10.000 |
| 16032M16Z04 | 10.000 |
| 16040M16Z04 | 10.000 |
| 16040M16Z06 | 10.000 |

## Spare Parts


Sold separately.

| Applicable Cutters | Clamp Screw | | Adjustment Screw | Wrench | Adjustment Wrench | Assembly Wrench |
|---|---|---|---|---|---|---|
| |  |  |  |  |  |  |
| ANXS160_ _M_Z_ _ | BXA0310IP | 2,0 | HFJ | TRXW10IP | ANT | HFVT |

The adjustment spanner (ANT) can also be used for height adjustment of the RF type cutters for high speed machining and the HF type cutters for high efficiency machining.

### Wiper Blade Step Amount

When using the wiper blade, in order to maintain balance, be sure to use a cutter with an even number of cutting edges and place the wiper blades at opposite positions.



# RF Type

## High Speed Finishing of Aluminium Alloy



Fig. 1






Fig. 2




## ■ Body

| Cat. No. | Stock | Dimensions (mm) | | | | | | | | Number of teeth | max. depth of cut | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | | | | |
| RF 4080 RS | ● | 80 | 82 | 60 | 50 | 27 | 12,4 | 7,0 | 29 | 6 | 3,0 | 0,7 | 1 |
| RF 4100 RS | ❑ | 100 | 102 | 75 | 50 | 32 | 14,4 | 8,5 | 29 | 6 | | 1,0 | 1 |
| 4125 RS | ● | 125 | 127 | 75 | 63 | 40 | 16,4 | 9,5 | 29 | 8 | | 1,6 | 1 |
| 4160 RS | ❑ | 160 | 162 | 100 | 63 | 40 | 16,4 | 9,5 | 29 | 10 | | 2,6 | 2 |

Remark: PCD blades and inserts are not included.

## ■ Insert for Roughing and Finishing





Fig. 1





Fig. 2






Fig. 3

| Application | Carbide | SUMIDIA | |
|---|---|---|---|
| High Speed / Light cut | N | N | N |
| General Purpose | N | N | N |
| Roughing | N | N | N |

| Cat. No. | H1 | DA1000 | DA2200 | Fig. |
|---|---|---|---|---|
| SDET 1204 ZDFR | ● | | | 1 |
| SNEW 1204 ADFR-NF | | ● | ▲ | 2 |
| SNEW 1204 ADFR-W-NF | | ● | ▲ | 3 |

## ■ Structure




## ■ "Sumidia" Blade

| PCD grade DA2200 | Cat. No. | Stock |
|---|---|---|
| Standard type  | RFB | ▲ |
| Wiper type  | RFBW | ▲ |

## ■ Cartridge

| Shape | Cat. No. | Stock |
|---|---|---|
| For carbide insert  | RFR | ● |
| For Sumidia insert  | RFF | ● |

## ■ Dummy Blade

| | | |
|---|---|---|
|  | RFD | ❍ |

## ■ Cutting Insert Selection

For easy assembling:
- PCD blade RFB
- PCD blade RFB (wiper type)

For finishing:
- Cartridge RFF
- PCD insert SNEW 1204 ADFR-NF (standard type)
  SNEW 1204 ADFR-W-NF (wiper type)
  PCD grade: DA2200

For roughing:
- Cartridge RFR
- Uncoated carbide insert
  SDET 1204 ZDFR, grade: H1

## ■ Spare Parts

| Cover | Position setting stoper | Main clamp screw | Sub clamp screw | Cover clamp screw | Adjustment screw | Insert clamp screw | Hex wrench | Torque wrench |
|---|---|---|---|---|---|---|---|---|
|  |  |  10,0 N·m |  3,0 N·m |  |  |  5,0 N·m |   |  |
| RFC | RFS | BX0620 | BTD0510 | FBUP2-A0-8 | RFJ | BFTX0509N | TH015, TH025 TH050 | TTX20 |

## ■ Setting Gauge



RF-SET

Dial-gauge is not included.



● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item

## High Speed Finishing of Aluminium Alloy



Fig. 1






Fig. 2




## Body

| Cat. No. | Stock | Dimensions (mm) | | No. of teeth | Fig. | Weight (Kg) |
|---|---|---|---|---|---|---|
| | | DC | DCSFMS | | | |
| SRF 30 R-ST | ❍ | 30 | - | 3 | 1 | 0,34 |
| SRF 40 R-ST | ❍ | 40 | - | 4 | 1 | 0,50 |
| SRF 50 RS | ❑ | 50 | 46,5 | 5 | 2 | 0,59 |
| SRF 63 RS | ❑ | 63 | 45,0 | 6 | 2 | 0,67 |

Inserts are sold seperately.

## Insert





Fig. 1





Fig. 2






Fig. 3





| Application | SUMIDIA |
|---|---|
| High Speed / Light cut | N |
| General Purpose | N |
| Roughing | N |

| Cat. No. | DA1000 | Cutting Edge | Fig. |
|---|---|---|---|
| SNEW 09T3 ADTR-NF | ❑ | Standard | 1 |
| 09T3 ADTR-U-NF | ❑ | Wiper | 2 |
| 09T3 ADTR-R-NF | ❍ | Nose Radius | 3 |

- Standard inserts and Wiper inserts can be used on the same cutter body.
- Standard inserts with nose radius should be used where vibration is present. As such, Wiper-inserts will not be applicable.
- Inserts can be regrind 3 times (up to minimum IC diameter 9,225 mm).
- When using reground inserts, it is advisable to reconfirm insert height and cutting diameter with a tool pre-setter.
- Do not mix new and reground inserts, or even inserts with different regrind amount on the same cutter.

## Spare Parts




## Maximum D.O.C. Guide (SRF50RS, 5 teeth)

The contains guidelines on the maximum D.O.C., determined from internal tests. "O" mark indicates the possible application range. Actual cutting conditions should be set, based on actual machine and work characteristics.

| D.O.C. (mm) \ Feed | Feed Speed, $v_f$ (mm/min) | | |
|---|---|---|---|
| | 2.500 | 4.000 | 5.000 |
| | Feed Rate, $f_z$ (mm/tooth) | | |
| | 0,05 | 0,08 | 0,10 |
| 0,5 | ○ | ○ | ○ |
| 1,0 | ○ | ○ | ○ |
| 1,5 | ○ | ○ | ○ |
| 2,0 | ○ | ○ | ○ |
| 2,5 | ○ | ○ | ○ |
| 3,0 | ○ | ○ | ○ |
| 3,5 | ○ | ○ | – |
| 4,0 | ○ | – | – |
| 4,5 | ○ | – | – |
| 5,0 | ○ | – | – |

● Cutting Conditions

Cutter: SRF 50 RS
Insert: SNEW 09T3 ADFR-NF (DA1000)
n : 10.000 rpm
Width: 35 mm at D.O.C. indicated above



## Recommended Cutting Conditions for RF and SRF Type Cutters

| Work Material | | Process | Grade | Cutting Speed (m/min) | | Feed Rate (mm/tooth) | Depth of Cut (mm) | |
|---|---|---|---|---|---|---|---|---|
| | | | | RF Type | SRF Type | | RF Type | SRF Type |
| Aluminium Alloy | Si < 13 % | Finishing | **DA1000** (PCD) | 2.000–5.000 | – 4.000 | 0,05–0,2 | – 3,0 | – 5,0 |
| | | Roughing | H1 (Carbide) | 1.000–2.500 | – | | | |
| | Si ≥ 13 % | Finishing | **DA1000** (PCD) | 400–800 | – 800 | | | |
| | | Roughing | H1 (Carbide) | 200–400 | – | | | |

# FMU Type

## High Speed Finishing of Grey Cast Iron



### Features

- High speed machining $v_c$ = 1.500 m/min
- Excellent surface roughness Rz = 3,2 (Ra = 1,0)
- Safety structure for the centrifugal force under high speed cutting conditions
- Run-out is less than 10 µm
- Easy assembling method using the setting gauge
- Running cost is reduced because of economical insert

### Application

GG25 – GG30 (HB200 – 250) grey cast iron with pearlite matrix, and ferrite matrix (HB130 – 160)
Application examples: engine block, cylinder block, etc



### Specifications


FMU Type: ø 80–ø 315 mm
Insert: SNEW1203ADTR/L
Low cutting force type: SNEW1203ADTR/L-S

### Recommended Cutting Conditions

Speed: $v_c$ = 800–2000 m/min
Feed: $f_z$ = 0,1–0,3 mm/tooth
Depth: $a_p$ = 0,5 mm or less
Dry cutting


### Performance

● Tool Life Diagram




Work material : GG25 $H_B$240 (Pearlite)
Cutting speed : $v_c$ = 600–4000 m/min
Feed rate : $f_z$ = 0,15 mm/tooth
Depth of cut : $a_p$ = 0,5 mm, Dry

● Estimated Tool Life




Work material : GG25 $H_B$240 (Pearlite)
Cutting speed : $v_c$ = 400–4000 m/min
Feed rate : $f_z$ = 0,15 mm/tooth
Depth of cut : $a_p$ = 0,5 mm, Dry

● Milling of ductile cast iron and alloy steel casting do not produce the best results.
● Dry cutting is recommended. Wet cutting will result in chipping of cutting edges in the early stages due to thermal cracking.




● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
(N·m) Recommended Tightening Torque (N·m)

# FMU Type


## Specifications

Approach angle: 90°
Axial rake angle: + 8°
Radial rake angle: + 2°




Max. depth of cut: 0,5 mm

## Structure




## Body

Fig. 1





Fig. 2





Fig. 3





Fig. 4






Fig. 5




| Cat. No. | Stock | Dimensions (mm) | | | | | | | | No. of Teeth | Max. Depth of Cut | Weight (Kg) | Fig. |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | DC | DCX | DCSFMS | LF | DCB | KWW | KDP | CBDP | | | | |
| FMU 4080 RS | ❑ | 80 | 82,8 | 60 | 63 | 27 | 12,4 | 7,0 | 25 | 6 | 0,5 | 1,6 | 1 |
| FMU 4100 RS | ● | 100 | 102,8 | 76 | 63 | 32 | 14,4 | 8,5 | 29 | 8 | | 2,4 | 2 |
| 4125 RS | ❑ | 125 | 127,8 | 75 | 63 | 40 | 16,4 | 9,5 | 29 | 10 | | 3,4 | 2 |
| 4160 RS | ❑ | 160 | 162,8 | 100 | 63 | 40 | 16,4 | 9,5 | 29 | 12 | | 5,6 | 3 |
| FMU 4200 RS | ❑ | 200 | 202,8 | 130 | 63 | 60 | 25,7 | 14,0 | 38 | 16 | | 9,2 | 4 |
| 4250 RS | ❑ | 250 | 252,8 | 130 | 63 | 60 | 25,7 | 14,0 | 38 | 20 | | 14,3 | 4 |
| FMU 4315 RS | | 315 | 317,8 | 240 | 80 | 60 | 25,7 | 14,0 | 40 | 24 | | 27,8 | 5 |

## Inserts

Fig. 1







Fig. 2




| Application | CBN | |
|---|---|---|
| High Speed / Light cut | K | K |
| General Purpose | K | K |
| Roughing | | |


| Cat. No. | BN700 | BN7000 | Figure |
|---|---|---|---|
| SNEW 1203 ADT R | ▲ | ❍ | 1 |
| 1203 ADT R-S | ▲ | ❍ | 2 |

## Cartridge




| Cartridge | Insert Screw | Adjustment Screw | O-ring | Insert Wrench | Pin |
|---|---|---|---|---|---|
| FMUU | BFTX0509N | FMUJ | P3 | TRX20 | 1,8 x 45 |

## Spare Parts



| Screw | Screw | Setting clamp | Double screw | Wrench | Wrench | Wrench |
|---|---|---|---|---|---|---|
| BH0620 | BTD0609 | FMUE | WB5–10 | TH040 | LH030 | LH025 |

## Gauge




RF-SET

Dial-gauge is not included.


# BNES Type

Spiral CBN Endmill for Hardened Steel






## ■ Endmills BNES Type with 1 Spiral Flute





Helix angle : 15°
right-hand cut, right-hand helix

| Cat. No. | Stock | Dimensions (mm) | | | | |
|---|---|---|---|---|---|---|
| | BN350 | DC | DMM | APMX | LU | LF |
| BNES 1060 | ❍ | 6,0 | 10 | 7,0 | 11 | 60 |
| BNES 1080 | ❍ | 8,0 | 10 | 10,0 | 14 | 70 |
| BNES 1100 | ❍ | 10,0 | 12 | 12,0 | 17 | 75 |
| BNES 1120 | ❍ | 12,0 | 12 | 14,0 | 20 | 80 |
| BNES 1140 | ❍ | 14,0 | 16 | 16,0 | 21,5 | 80 |

## ■ Recommended Cutting Conditions

Cutting speed: $v_c$ (m/min), Spindle revolutions: n (rpm), Feed per tooth: $f_z$ (mm/tooth), Feed speed: $v_f$ (mm/min)

| Tooling example | DC | Hardened steel ($H_RC$ 50–57) $v_c$ = 100–170 m/min | | | Hardened steel ($H_RC$ 58–65) $v_c$ = 80–150m/min | | |
|---|---|---|---|---|---|---|---|
|  | ø 6–8 | $a_e \leq$ 0,1 mm | n = 4000–9000 | $v_f$ (mm/min) = 240–540 | $a_e \leq$ 0,08 mm | n = 3200–8000 | $v_f$ (mm/min) = 150–370 |
| | ø 10–12 | $a_e \leq$ 0,15 mm | n = 2700–5400 | $v_f$ (mm/min) = 180–360 | $a_e \leq$ 0,12 mm | n = 2100–4800 | $v_f$ (mm/min) 120–270 |
| | ø 14–16 | $a_e \leq$ 0,2 mm | n = 2000–3800 | $v_f$ (mm/min) = 140–260 | $a_e \leq$ 0,15 mm | n = 1600–3400 | $v_f$ (mm/min) = 110–230 |





Depth of cut : $a_p \leq$ DC

Recommendation: Dry cutting (Air coolant)
Down-cut milling
Minimise the overhang
Use a rigid machine

## ■ Performance

### ● Long Tool Life and High Efficiency





Work material: X155CrVMo12-1
Hardness: $H_RC$ 60

Cutting data:
$v_c$ = 100 m/min (Helical Master)
$v_c$ = 40 m/min (Competitor's coated solid carbide endmill)
$v_f$ = 186 mm/min


Down-cut milling
Dry cutting


### ● Excellent Surface Roughness

"Helical Master" BNES 1080 ø 8,0




Conventional straight flute CBN endmill, ø 8,0




Work material: 15Cr3
Hardness: $H_RC$ 55–58
Cutting data: $v_c$ = 130 m/min
$v_f$ = 310 mm/min

Down-cut milling
Dry cutting



● = Euro stock
❍ = Japan stock

SUMIBORON "MOULD Finish Master"


# BNBP Type




## Characteristics / Application

- High precision machining of hardened steels < HRC 70 with long tool life
- Super tough grade SUMIBORON BN350 prevents chipping of the cutting edge
- R accuracy : ±0,005 mm

## Endmills




## Identification Details





Dimensions (mm)

| Cat. No. | Stock | RE | DC | APMX | LU | LF | DN | DMM |
|---|---|---|---|---|---|---|---|---|
| BNBP 2R0200124 | ● | 0,20 | 0,4 | 0,3 | 1,2 | 50 | 0,37 | 4 |
| 2R0200126 | ● | 0,20 | 0,4 | 0,3 | 1,2 | 50 | 0,37 | 6 |
| 2R0200204 | ❍ | 0,20 | 0,4 | 0,3 | 2,0 | 50 | 0,37 | 4 |
| 2R0200304 | ❍ | 0,20 | 0,4 | 0,3 | 3,0 | 50 | 0,37 | 4 |
| 2R0200404 | ❍ | 0,20 | 0,4 | 0,3 | 4,0 | 50 | 0,37 | 4 |
| BNBP 2R0300154 | ● | 0,30 | 0,6 | 0,4 | 1,5 | 50 | 0,57 | 4 |
| 2R0300156 | ● | 0,30 | 0,6 | 0,4 | 1,5 | 50 | 0,57 | 6 |
| 2R0300304 | ❍ | 0,30 | 0,6 | 0,4 | 3,0 | 50 | 0,57 | 4 |
| 2R0300404 | ❍ | 0,30 | 0,6 | 0,4 | 4,0 | 50 | 0,57 | 4 |
| 2R0300504 | ❍ | 0,30 | 0,6 | 0,4 | 5,0 | 50 | 0,57 | 4 |
| 2R0300604 | ❍ | 0,30 | 0,6 | 0,4 | 0,6 | 50 | 0,57 | 4 |
| BNBP 2R0500254 | ● | 0,50 | 1,0 | 0,6 | 2,5 | 50 | 0,97 | 4 |
| 2R0500256 | ● | 0,50 | 1,0 | 0,6 | 2,5 | 50 | 0,97 | 6 |
| 2R0500304 | ❍ | 0,50 | 1,0 | 0,6 | 3,0 | 50 | 0,97 | 4 |
| 2R0500404 | ❍ | 0,50 | 1,0 | 0,6 | 4,0 | 50 | 0,97 | 4 |
| 2R0500604 | ❍ | 0,50 | 1,0 | 0,6 | 0,6 | 50 | 0,97 | 4 |
| 2R0500804 | ❍ | 0,50 | 1,0 | 0,6 | 8,0 | 50 | 0,97 | 4 |
| BNBP 2R0750404 | ❍ | 0,75 | 1,5 | 0,9 | 4,0 | 50 | 1,47 | 4 |
| 2R0750406 | ● | 0,75 | 1,5 | 0,9 | 4,0 | 50 | 1,47 | 6 |
| BNBP 2R1000554 | ● | 1,00 | 2,0 | 1,4 | 5,5 | 50 | 1,97 | 4 |
| 2R1000556 | ● | 1,00 | 2,0 | 1,4 | 5,5 | 50 | 1,97 | 6 |
| 2R1000804 | ❍ | 1,00 | 2,0 | 1,4 | 8,0 | 50 | 1,97 | 4 |

Grade: BN350

## Recommended Cutting Conditions

| Work Material | | STAVAX, NAK80, SKD61 (< 52HRC) | | | | ELMAX, DC53, SKD11 (< 62HRC) | | | | YXR3, SKH (< 70HRC) | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| RE (mm) | LU (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | ap (mm) | pf (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | ap (mm) | pf (mm) | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | ap (mm) | pf (mm) |
| 0,2 | 1,2 | 40.000 | 1.000 | 0,005 | 0,010 | 40.000 | 800 | 0,005 | 0,010 | 40.000 | 600 | 0,005 | 0,005 |
| | 2,0 | 40.000 | 800 | 0,005 | 0,010 | 40.000 | 600 | 0,005 | 0,010 | 40.000 | 400 | 0,005 | 0,005 |
| | 3,0 | 40.000 | 600 | 0,005 | 0,010 | 40.000 | 500 | 0,005 | 0,010 | 40.000 | 300 | 0,005 | 0,005 |
| | 4,0 | 40.000 | 500 | 0,005 | 0,010 | 40.000 | 400 | 0,005 | 0,005 | 40.000 | 200 | 0,005 | 0,005 |
| 0,3 | 1,5 | 40.000 | 1.600 | 0,020 | 0,020 | 40.000 | 1.400 | 0,010 | 0,020 | 40.000 | 1.200 | 0,010 | 0,020 |
| | 2,0 | 40.000 | 1.500 | 0,010 | 0,020 | 40.000 | 1.300 | 0,010 | 0,020 | 40.000 | 1.100 | 0,010 | 0,010 |
| | 3,0 | 40.000 | 1.400 | 0,010 | 0,020 | 40.000 | 1.200 | 0,010 | 0,020 | 40.000 | 1.000 | 0,010 | 0,010 |
| | 4,0 | 30.000 | 1.200 | 0,010 | 0,010 | 30.000 | 1.000 | 0,010 | 0,010 | 30.000 | 700 | 0,005 | 0,010 |
| | 5,0 | 30.000 | 800 | 0,010 | 0,010 | 30.000 | 700 | 0,005 | 0,010 | 30.000 | 600 | 0,005 | 0,005 |
| | 6,0 | 30.000 | 600 | 0,005 | 0,010 | 30.000 | 500 | 0,005 | 0,005 | 30.000 | 400 | 0,005 | 0,005 |
| 0,5 | 2,5 | 40.000 | 2.800 | 0,040 | 0,050 | 40.000 | 2.800 | 0,030 | 0,040 | 40.000 | 2.200 | 0,020 | 0,030 |
| | 3,0 | 40.000 | 2.600 | 0,040 | 0,050 | 40.000 | 2.600 | 0,030 | 0,040 | 40.000 | 2.100 | 0,020 | 0,030 |
| | 4,0 | 40.000 | 2.400 | 0,030 | 0,050 | 40.000 | 2.400 | 0,020 | 0,030 | 40.000 | 2.000 | 0,020 | 0,020 |
| | 6,0 | 25.000 | 1.500 | 0,020 | 0,030 | 25.000 | 1.500 | 0,010 | 0,020 | 25.000 | 1.300 | 0,010 | 0,010 |
| | 8,0 | 16.000 | 1.200 | 0,020 | 0,020 | 16.000 | 1.100 | 0,010 | 0,020 | 16.000 | 850 | 0,010 | 0,010 |
| 0,75 | 4,0 | 32.000 | 2.400 | 0,030 | 0,030 | 32.000 | 2.200 | 0,020 | 0,030 | 32.000 | 2.000 | 0,020 | 0,020 |
| 1,0 | 5,5 | 40.000 | 4.000 | 0,050 | 0,050 | 40.000 | 4.000 | 0,030 | 0,030 | 40.000 | 3.000 | 0,020 | 0,030 |
| | 8,0 | 32.000 | 3.000 | 0,030 | 0,050 | 32.000 | 2.600 | 0,020 | 0,030 | 32.000 | 2.200 | 0,010 | 0,020 |






Important Notes

(1) For stable machining, a more rigid machine is recommended.
(2) Air blast or oil mist coolant is recommended.
(3) Shorten overhang as much as possible.

# NPDRS Type

## SUMIDIA Binderless Radius Endmill **NPDRS** Type




## NPDRS Type Body (for Standard Finishing)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | Real effective length with respect to work material gradient angle | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | NPD10 | DC | RE | APMX | LU | LF | DN | DMM | 0,5° | 1° | 1,5° | 2° | 3° |
| NPDRS 1020 R002-006 | ❍ | 0,2 | 0,02 | 0,10 | 0,6 | 40 | 0,175 | 4 | 0,61 | 0,62 | 0,63 | 0,64 | 0,66 |
| 1020 R005-006 | ❍ | 0,2 | 0,05 | 0,10 | 0,6 | 40 | 0,175 | 4 | 0,61 | 0,62 | 0,63 | 0,64 | 0,66 |
| 1030 R002-010 | ❍ | 0,3 | 0,02 | 0,15 | 1,0 | 40 | 0,27 | 4 | 1,01 | 1,03 | 1,04 | 1,06 | 1,09 |
| 1030 R005-010 | ❍ | 0,3 | 0,05 | 0,15 | 1,0 | 40 | 0,27 | 4 | 1,01 | 1,03 | 1,04 | 1,06 | 1,09 |
| 1050 R005-015 | ❍ | 0,5 | 0,05 | 0,25 | 1,5 | 40 | 0,47 | 4 | 1,61 | 1,66 | 1,72 | 1,78 | 1,92 |
| NPDRS 1050 R010-015 | ❍ | 0,5 | 0,10 | 0,25 | 1,5 | 40 | 0,47 | 4 | 1,61 | 1,66 | 1,71 | 1,77 | 1,91 |
| 1100 R005-030 | ❍ | 1,0 | 0,05 | 0,55 | 3,0 | 40 | 0,95 | 4 | 3,40 | 3,52 | 3,65 | 3,78 | 4,08 |
| 1100 R010-030 | ❍ | 1,0 | 0,10 | 0,55 | 3,0 | 40 | 0,95 | 4 | 3,40 | 3,52 | 3,64 | 3,77 | 4,07 |
| 1100 R020-030 | ❍ | 1,0 | 0,20 | 0,55 | 3,0 | 40 | 0,95 | 4 | 3,40 | 3,51 | 3,63 | 3,76 | 4,05 |
| 1200 R005-040 | ❍ | 2,0 | 0,05 | 0,55 | 4,0 | 40 | 1,95 | 4 | 4,44 | 4,59 | 4,75 | 4,93 | 5,33 |
| NPDRS 1200 R010-040 | ❍ | 2,0 | 0,10 | 0,55 | 4,0 | 40 | 1,95 | 4 | 4,43 | 4,59 | 4,75 | 4,92 | 5,31 |
| 1200 R020-040 | ❍ | 2,0 | 0,20 | 0,55 | 4,0 | 40 | 1,95 | 4 | 4,43 | 4,58 | 4,74 | 4,91 | 5,29 |

## Identification Details

| NPDR | S | 1 | 020 | R002 | - | 006 |
|---|---|---|---|---|---|---|
| Series Code | For standard finishing | No. of flutes | Cutting diameter | Corner radius | | Length below neck |

## Cutting Diameter and Nose Radius Combinations

| DC | RE 0,02 | RE 0,05 | RE 0,1 | RE 0,2 |
|---|---|---|---|---|
| 0,2 | ❍ | ❍ | | |
| 0,3 | ❍ | ❍ | | |
| 0,5 | | ❍ | ❍ | |
| 1,0 | | ❍ | ❍ | ❍ |
| 2,0 | | ❍ | ❍ | ❍ |

## Recommended Cutting Conditions

- Use a machine with high rigidity for stable cutting.
- Non-water soluble coolant recommended. Supply as a mist or external coolant.
  Take fire prevention precautions to avoid fire hazards caused by sparks igniting during machining or tool breakage.
- Shorten overhang as much as possible.
- Adjust cutting conditions as necessary as machine rigidity and other conditions may vary.
- Depth of cut shown in the table of conditions are maximum depths. Adjust the actual depth of cut to the desired machined surface finish.


| Work Material | | Carbide | | | |
|---|---|---|---|---|---|
| RE (mm) | LU | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | $a_p$ (mm) | $a_e$ (mm) |
| 0,2 | 0,10 | 40.000 | 100 | 0,001 | 0,001 |
| 0,3 | 0,15 | 40.000 | 150 | 0,002 | 0,001 |
| 0,5 | 0,25 | 40.000 | 200 | 0,003 | 0,001 |
| 1,0 | 0,55 | 40.000 | 400 | 0,005 | 0,003 |
| 2,0 | 0,55 | 40.000 | 600 | 0,010 | 0,005 |




❍ = Japan stock

# NPDB(S) Type

## SUMIDIA Binderless Ballnose Endmill **NPDBS** Type / **NPDB** Type




### NPDBS Type Body (for Standard Finishing)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | Real effective length with respect to work material gradient angle | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | NPD10 | RE | DC | APMX | LU | LF | DN | DMM | 0,5° | 1° | 1,5° | 2° | 3° |
| NPDBS 1010–004 | ❍ | 0,1 | 0,2 | 0,1 | 0,4 | 40 | 0,18 | 4 | 0,44 | 0,45 | 0,46 | 0,47 | 0,49 |
| 1020–008 | ❍ | 0,2 | 0,4 | 0,2 | 0,8 | 40 | 0,38 | 4 | 0,83 | 0,84 | 0,85 | 0,86 | 0,89 |
| 1030–010 | ❍ | 0,3 | 0,6 | 0,3 | 1,0 | 40 | 0,58 | 4 | 1,05 | 1,08 | 1,10 | 1,13 | 1,20 |
| 1050–020 | ❍ | 0,5 | 1,0 | 0,5 | 2,0 | 40 | 0,95 | 4 | 2,08 | 2,13 | 2,19 | 2,24 | 2,38 |
| 1100–030 | ❍ | 1,0 | 2,0 | 1,0 | 3,0 | 40 | 1,95 | 4 | 3,13 | 3,20 | 3,27 | 3,35 | 3,53 |

### NPDB Type Body (for Precision Finishing)

| Cat. No. | Stock | Dimensions (mm) | | | | | | | Real effective length with respect to work material gradient angle | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | NPD10 | RE | DC | APMX | LU | LF | DN | DMM | 0,5° | 1° | 1,5° | 2° | 3° |
| NPDB 1010–004 | ❍ | 0,1 | 0,2 | 0,1 | 0,4 | 40 | 0,18 | 4 | 0,44 | 0,45 | 0,46 | 0,47 | 0,49 |
| 1020–008 | ❍ | 0,2 | 0,4 | 0,2 | 0,8 | 40 | 0,38 | 4 | 0,83 | 0,84 | 0,85 | 0,86 | 0,89 |
| 1030–010 | ❍ | 0,3 | 0,6 | 0,3 | 1,0 | 40 | 0,58 | 4 | 1,05 | 1,08 | 1,10 | 1,13 | 1,20 |
| 1050–020 | ❍ | 0,5 | 1,0 | 0,5 | 2,0 | 40 | 0,95 | 4 | 2,08 | 2,13 | 2,19 | 2,24 | 2,38 |
| 1100–030 | ❍ | 1,0 | 2,0 | 1,0 | 3,0 | 40 | 1,95 | 4 | 3,13 | 3,20 | 3,27 | 3,35 | 3,53 |

### Identification Details

| **NPDB** | **(S)** | **1** | **030** | **-** | **010** |
|---|---|---|---|---|---|
| Series Code | For standard finishing | No. of flutes | Ballnose radius | | Length below neck |

### Recommended Cutting Conditions


- Use a machine with high rigidity for stable cutting.
- Non-water soluble coolant recommended. Supply as a mist or external coolant.
  Take fire prevention precautions to avoid fire hazards caused by sparks igniting during machining or tool breakage.
- Shorten overhang as much as possible.
- Adjust cutting conditions as necessary as machine rigidity and other conditions may vary.
- Depth of cut shown in the table of conditions are maximum depths. Adjust the actual depth of cut to the desired machined surface finish.

● Flat Surface Finishing


| Work Material | | Carbide | | | |
|---|---|---|---|---|---|
| RE (mm) | LU | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | $a_p$ (mm) | $a_e$ (mm) |
| 0,1 | 0,4 | 40.000 | 100 | 0,001 | 0,001 |
| 0,2 | 0,8 | 40.000 | 150 | 0,001 | 0,001 |
| 0,3 | 1,0 | 40.000 | 200 | 0,001 | 0,001 |
| 0,5 | 2,0 | 40.000 | 400 | 0,001 | 0,003 |
| 1,0 | 3,0 | 40.000 | 600 | 0,001 | 0,005 |

● Copy Finishing

| Work Material | | Carbide | | | |
|---|---|---|---|---|---|
| RE (mm) | LU | Spindle Speed ($min^{-1}$) | Feed Rate (mm/min) | $a_p$ (mm) | $a_e$ (mm) |
| 0,1 | 0,4 | 40.000 | 100 | 0,001 | 0,001 |
| 0,2 | 0,8 | 40.000 | 150 | 0,002 | 0,001 |
| 0,3 | 1,0 | 40.000 | 200 | 0,003 | 0,001 |
| 0,5 | 2,0 | 40.000 | 400 | 0,005 | 0,003 |
| 1,0 | 3,0 | 40.000 | 600 | 0,010 | 0,005 |




# DAL/DDL/DML Type



## From general to High Precision Drilling of Aluminum Alloys!


- High precision DAL type is able to produce holes of IT Class of 7 – 8.
- General DDL type is able to produce holes of IT class of 11 – 12, mainly for drilling of pre-tap holes.
- DML type is DDL type with a chamfer edge, incorporating 2 processes in one operation.

## ■ DAL Type




| Cat. No. | DA2200 | DC (DMM) | LCF | OAL | PL |
|---|---|---|---|---|---|
| DAL 0500H – 0600H | ❑ | Ø5 ≤ DC ≤ Ø6 | 31,6 | 84,6 | 1,6 |
| 0601H – 0700H | ❑ | Ø6 < DC ≤ Ø7 | 36,9 | 91,9 | 1,9 |
| 0701H – 0800H | ❑ | Ø7 < DC ≤ Ø8 | 37,2 | 92,2 | 2,2 |
| 0801H – 0900H | ❑ | Ø8 < DC ≤ Ø9 | 42,5 | 102,5 | 2,5 |
| 0901H – 1000H | ❑ | Ø9 < DC ≤ Ø10 | 42,8 | 102,8 | 2,8 |
| 1001H – 1100H | ❑ | Ø10 < DC ≤ Ø11 | 53,1 | 113,1 | 3,1 |
| 1101H – 1200H | ❑ | Ø11 < DC ≤ Ø12 | 53,4 | 113,4 | 3,4 |

## ■ DDL Type




| Cat. No. | DA2200 | DC (DMM) | LCF | OAL | PL |
|---|---|---|---|---|---|
| DDL 050V – 060V | ❑ | Ø5 ≤ DC ≤ Ø6 | 31,5 | 81,0 | 1,0 |
| 061V – 070V | ❑ | Ø6 < DC ≤ Ø7 | 36,2 | 91,2 | 1,2 |
| 071V – 080V | ❑ | Ø7 < DC ≤ Ø8 | 36,4 | 91,4 | 1,4 |
| 081V – 090V | ❑ | Ø8 < DC ≤ Ø9 | 41,6 | 101,6 | 1,6 |
| 091V – 100V | ❑ | Ø9 < DC ≤ Ø10 | 41,7 | 101,7 | 1,7 |
| 101V – 110V | ❑ | Ø10 < DC ≤ Ø11 | 51,9 | 111,9 | 1,9 |
| 111V – 120V | ❑ | Ø11 < DC ≤ Ø12 | 52,1 | 112,1 | 2,1 |




## ■ Recommended Conditions

| DC (mm) | Cutting Speed (m/min) | Feed Rate (mm/rev) | Drilling Length L/D | Oil |
|---|---|---|---|---|
| <8 | 80–250 | 0,05–0,2 | Below 3 x D | Water soluble |
| ≥ 8 ≤ 12 | | 0,1–0,3 | | |




## ■ Important Notes

- Select a high rigidity machine and high precison tool holder.
- Enough coolant to drilled hole.


## ■ Application Examples (DAL Type)

| Work Shape | Work | Conditions | Results |
|---|---|---|---|
|   | A390<br>High silicon Aluminum | Vc=100m/min<br>f=0,1mm/rev | • Holes by carbide drill was out of specifications after 2.000 holes/reg.<br>• SumiDia drill could drill up to 30.000 holes/reg.<br>• 15 times tool life that of carbide drills. |
|   | A390<br>High silicon Aluminum<br>(pre-cast hole of ø10) | Vc=120m/min<br>f=0,12mm/rev | • Average 40,000 holes/reg<br>• Surface roughness Ry = 1 µm |
|   | ADC10<br>Aluminum Die Cast | Vc=90m/min<br>f=0,08mm/rev | • More than 50.000 holes and still running |


## ■ Application Examples (DDL Type)

| Work Shape | Work | Conditions | Results |
|---|---|---|---|
|   | ADC12<br>Aluminum Die Cast<br>M8 Pre-tap holes | Vc=214m/min<br>f=0,14mm/rev | • Regrind after 100.000 holes |
|   | ADC12<br>Aluminum Die Cast | Vc=200m/min<br>f=0,17 mm/rev | • Regrind after 74.000 holes (2.000m) (Preset tool change) |
|   | AC2A<br>Aluminum Casting | Vc=234m/min<br>f=0,28 mm/rev | • Regrind after 80.000 holes (Preset tool change) |

❑ = Delivery on request






## ■ DML Type





| Applicable Tap Size | Cat. No. | Stock DA2200 | øD | ød | L | ℓ1 | ℓ2 |
|---|---|---|---|---|---|---|---|
| M6 | DML 050V | ❑ | 5 | 8 | 90 | 18 | 36 |
| M8 | DML 068V | ❑ | 6,8 | 10 | 104 | 24 | 48 |
| M10 | DML 085V | ❑ | 8,5 | 12 | 122 | 30 | 60 |
| M12 | DML 103V | ❑ | 10,3 | 14 | 136 | 36 | 72 |

## ■ Application Examples (DML Type)

| Work Shape | Work | Conditions | Results |
|---|---|---|---|
|   | AC4C-T6<br>Aluminum Casting<br>M6 Pre-tap holes | Vc=100m/min<br>f=0,1mm/rev<br>m/c=6 spindles | • Regrind after 150.000 holes<br>• Tool life for carbide drill is 500 holes.<br>• 30 times tool life that of carbide drills |
|   | AC2C-T2<br>Aluminum Casting<br>M8 Pre-tap holes | Vc=210m/min<br>f=0,15mm/rev | • 100.000 holes/reg (2.000m) and still running.<br>• Dilling and chamfering in the same process |
|   | AC4C-T6<br>Aluminum Casting<br>M10 Pre-tap holes | Vc=250m/min<br>f=0,2mm/rev | • 80.000 holes/reg (1,840m) and still running.<br>• Drilling and chamfering in the same process |

## ■ DML Type Possible Profiles





(1) Tolerance for dimension L is more than 0,2mm.
(2) θ° is less than 180°.

# Technical Guidance References

N



**N1–N28**





**Basics of Turning** ..... N2
Tool Failures and Remedies ..... N3–4
Chip Control ..... N5

**Basics of Milling** ..... N6–8
Tool Failures and Remedies ..... N9

**Basics of Endmilling** ..... N10–11
Tool Failures and Remedies ..... N12

**Basics of Drilling** ..... N13–15
Tool Failures and Remedies ..... N16

**SUMIBORON for**
Hardened Steel Machining ..... N17
Cast Iron Machining ..... N18

Hard-to cut Materials Machining ..... N19
Tool Failure and Remedies ..... N20

**References** Expansion
Steel and Non-Ferrous Metal Symbols Chart .... N21-25
Hardness Scale Comparison Chart ..... N26
Finished Surface Roughness ..... N27

# Basics of Turning

## Calculating Power Requirement

$$P_c = \frac{a_p \cdot f \cdot v_c \cdot K_c}{60 \times 10^3 \times \eta}$$


$$H = \frac{P_c}{0{,}75}$$

$P_c$ : Net power requirement (KW)
$v_c$ : Cutting speed (m/min)
$f$ : Feed rate (mm/rev)
$a_p$ : Depth of cut (mm)
$\eta$ : Machine efficiency (0,70 ~ 0,85)
$K_c$ : Specific cutting force (N/mm²)
$H$ : Required horsepower (HP)

### Rough value of specific cutting force ($K_c$)

| | |
|---|---|
| General steel : | 2.500 ~ 3.000 N/mm² |
| Cast iron : | 1.500 N/mm² |
| Aluminum : | 800 N/mm² |

## Cutting Force





$F_1$ : Principal force
$F_2$ : Feed force
$F_3$ : Back force

### Calculating cutting force


$$P = K_c \cdot q = \frac{k_c \times a_p \times f}{1000}$$

$P$ : Cutting force (N)
$K_c$ : Specific cutting force (N/mm²)
$q$ : Chip area (mm²)
$a_p$ : Depth of cut (mm)
$f$ : Feed rate (mm/rev)

## Cutting Speed and Cutting Force




## Rake Angle and Cutting Force




## Calculating Cutting Speed

① Calculating rotational speed from cutting speed

$$n = \frac{1000 \cdot v_c}{\pi \cdot D}$$

$n$ : Spindle speed (min⁻¹)
$v_c$ : Cutting speed (m/min)
$D$ : Diameter of workpiece (mm)
$\pi \approx 3{,}14$


(Eg.) $v_c$ = 150 m/min, D = 100 mm

$$n = \frac{1000 \times 150}{3{,}14 \times 100} = 478 \text{ (min}^{-1}\text{)}$$

② Calculating cutting speed from rotational speed

$$v_c = \frac{\pi \cdot D \cdot n}{1.000}$$


Refer to the above table




$n$ : Spindle speed (min⁻¹)
$v_c$ : Cutting speed (m/min)
$f$ : Feed rate (mm/rev)
$a_p$ : Depth of cut (mm)
$D_m$ : Diameter of workpiece (mm)

## Feed Rate and Specific Cutting Force

(For carbon steel)





**When feed rate decreases, specific cutting force increases.**

## Roughness

### Theoretical Surface Finish

$$Rz = \frac{f^2}{8 \times r}$$

Rz : Surface finish (mm)
f : Feed rate (mm/rev)
r : Nose radius (mm)




### Actual surface roughness

Steel :
Theoretical surface finish x 1,5–3
Cast iron :
Theoretical surface finish x 3–5

### Ways to Improve Surface Finish


① Use an insert with a larger nose radius.

② Optimize the cutting speed and feed rate so that built-up edge does not occur.

③ Select an appropriate insert grade.

④ Use wiper insert.

## Nose Radius and Cutting Force





**Large nose radius increases back force.**

Work : 42CrMo4 (Hs38)
Inserts : TNGA2204○○
Holder : PTGNR2525-43
Condition : $v_c$ = 100m/min
$a_p$ = 4mm
f = 0,45 mm/rev

# Tool Failures and Tool Life


## ■ Forms of Tool Failures






| Cat. | No. | Name of Failure | Cause of Failure |
|---|---|---|---|
| Resulting from Mechanical causes | 1~5 | Flank Wear | Due to the scratching effect of hard grains contained in the work material. |
| | 6 | Chipping | Fine breakages caused by high cutting loads or chattering. |
| | 7 | Fracture | Due to the impact of an excessive mechanical force acting on the cutting edge. |
| Resulting from Chemical reactions | 8 | Crater Wear | Swaft chips removing tool material as it flow over the top face at high temperatures. |
| | 9 | Plastic Deformation | Cutting edge is depressed due to softening at high temperatures. |
| | 10 | Thermal Crack | Fatigue from rapid, repeated heating and cooling cycles during machining. |
| | 11 | Built-up Edge | Work material is pressure welded on the top face of the cutting edge. |

## ■ Tool Wear





### Forms of Tool Wear




| Flank wear | Crater wear |
|---|---|
|   |   |
| Wear is rapid initially, then it proceeds more gradually in proportion with cutting time until a certain limit, beyond which it increases rapidly again. | Crater wear is more progressive with no sudden breakdown pattern. |








## ■ Tool Life (V-T)

Measure the relative tool lives of the specified wear, over a range of cutting speeds, then plot the tool life along the X-axis and the cutting speed along the Y-axis on a double logarithm graph.

| | Flank wear | Crater wear |
|---|---|---|
| Tool wear |   |   |
| Tool life |   |   |

# Tool Failure and Remedies

## ■ Trouble Shooting Guide for Turning

| | Damage | Cause | Countermeasures |
|---|---|---|---|
| Tool Edge Failure | Excessive flank wear  | - Grade lacks wear resistance.<br><br>- Cutting speed ist too fast.<br>- Feed rate ist far too slow. | - Select a wear resistant grade.<br>P30 ⇨ P20 ⇨ P10<br>K20 ⇨ K10 ⇨ K01<br>- Use an insert with a larger rake angle.<br>- Decrease the cutting speed.<br>- Increase feed rates. |
| | Excessive crater wear  | - Grade lacks crater wear resistance.<br>- Rake angle is too small.<br>- Cutting speed is too fast.<br>- Feed rate and depth of cut are too large. | - Select a more crater-resistant grade.<br>- Use an insert with a larger rake angle.<br>- Select an appropriate chipbreaker.<br>- Decrease the cutting speed.<br>- Decrease the D.O.C. and feed rate. |
| | Cutting edge chipping  | - Grade lacks toughness.<br>- Insert falls off due to chip build-up.<br>- Cutting edge lacks toughness.<br>- Feed rate and depth of cut are too large. | - Change to tougher grades.<br>P10 ⇨ P20 ⇨ P30<br>K01 ⇨ K10 ⇨ K20<br>- Increase amount of honing on cutting edge.<br>- Reduce rake angle.<br>- Reduce feed rates and depth of cut. |
| | Cutting edge fracture  | - Grades lacks toughness.<br>- Cutting edge lacks toughness.<br>- Holder lacks toughness.<br>- Feed rarte is too fast.<br>- Depth of cut is too large. | - Change to tougher grades.<br>P10 ⇨ P20 ⇨ P30<br>K01 ⇨ K10 ⇨ K20<br>- Select a chipbreaker with a strong cutting edge.<br>- Select a holder with a larger approach angle.<br>- Select a holder with a larger shank size.<br>- Decrease the D.O.C. and feed rate. |
| | Build-up edge  | - Inappropriate grade selection.<br>- Dull cutting edge.<br>- Cutting speed is too slow.<br>- Feed rate ist too slow. | - Select a grade with less affinity to the work material. Coated carbide or cermet grades.<br>- Select a grade with a smooth coating.<br>- Use an insert with a larger rake angle.<br>- Reduce amount of honing.<br>- Increase cutting speeds.<br>- Increase feed rates. |
| | Plastic deformation  | - Grade lacks thermal resistance.<br>- Cutting speed is too fast.<br>- Feed rate is too fast.<br>- Depth of cut is too large.<br>- Not enough cutting fluid. | - Select a more crater-wear-resistant grade.<br>- Use an insert with a larger rake angle.<br>- Decrease the cutting speed.<br>- Reduce feed rates and depth of cut.<br>- Supply a sufficient amount of coolant. |
| | Notch wear  | - Grade lacks wear resistance.<br>- Rake angle is too small.<br>- Cutting speed is too fast. | - Select a wear resistant grade.<br>P30 ⇨ P20 ⇨ P10<br>K20 ⇨ K10 ⇨ K01<br>- Use an insert with a larger rake angle.<br>- Alter depth of cutto shift the notch location. |

## Type of Chip Generation

| | a | b | c | d |
|---|---|---|---|---|
| Shape |  |  |  |  |
| Condition | Continuous chips with good surface finish. | Chip is sheared and separated by the shear angle. | Chips appear to be torn from the surface. | Chips crack before reaching the cutting point. |
| Application | Steel, Stainless steel | Steel, Stainless steel (Low speed) | Steel, Cast iron (Very low speed, very small feedrate) | Cast iron, Carbon |
| Influence factor | Easy ← Work deformation → Difficult<br>Large ← Rake angle → Small<br>Small ← D.O.C. → Large<br>Fast ← Cutting speed → Slow | | | |

## Type of Chip Control


| Feed rate | A | B | C | D | E |
|---|---|---|---|---|---|
| Large feed rate |  |  |  |  |  |
| Small feed rate |  |  |  |  |  |
| NC lathe (For automation) | × | × | ○ | ○ | △ |
| General lathe (For safety) | × | ○ | ○ | ○ ~ △ | × |

Good : C type, D type


Poor
- A type : Twines around the tool or workpiece, damages the machined surface and affects safety.
- B type : Bulky, causes problems in the automatic chip conveyor and chipping occurs easily.
- E type : Causes spraying of chips, poor machined surface due to chattering, chipping, large cutting force and high temperatures.

## Factor of Improvement Chip Control


### ① Increase feed rate





When feedrate increase, chips become thick and chip control improves.





### ② Decrease side cutting edge




Even if feed rate is the same, smaller side cutting edge angle makes chips thick and chip control improves.





### ③ Decrease nose radius





Even if depth of cut is the same, smaller nose radius makes chip thick and chip control improves.

* Cutting resistance increases in proportion with the width of the contact surface. Therefore, with a larger nose radius, cutting resistance and back force increases, chattering may also occur. However, with the same feedrate, a smaller nose radius would produce a poorer surface finish.



# Basics of Milling

## ■ Parts of a Milling Cutter




## ■ Power Requirement

### ● Calculating cutting force

$$P_c = \frac{a_p \cdot a_e \cdot v_f \cdot K_c}{60 \times 10^6 \times \eta} \text{ (kW)}$$

### ● Horsepower

$$H = \frac{Pc}{0{,}75}$$

### ● Chip removal amount

$$Q = \frac{a_p \times a_e \times v_f}{1.000} \text{ (cm}^3\text{/min)}$$


$P_c$ : Net power requirement (kW)
H : Horsepower requirement (HP)
Q : Chip removal amount ($cm^3$/min)
$a_e$ : Cutting width (mm)
$v_f$ : Feed speed (mm/min)
$a_p$ : Depth of cut (mm)
η : Machine efficiency (0,70 ~ 0,85)
$K_c$ : Specific cutting forrce (N/$mm^2$)

Eg. rough value
( Steel : 2.500 ~ 3.000
Cast iron : 1.500 )

### ● Relation between feed rate, work material, specific cutting force

| Work-piece No. | Alloy steel | Carbon steel | Cast iron | Aluminum alloy |
|---|---|---|---|---|
| ① | 1.800 | 800 | 200 | – |
| ② | 1.400 | 600 | 160 | – |
| ③ | 1.000 | 400 | 120 | – |

Values in the table show the following properties:
- Tensile strength (N/$mm^2$) for alloy steel and carbon steel
- Hardness ($H_B$) for cast iron




### ● Calculating cutting speed


$$v_c = \frac{\pi \times D \times n}{1.000}$$

### ● Calculating feed rate

$$v_f = f_z \times z \times n$$

$$f_z = \frac{v_f}{z \times n}$$


$v_c$ : Cutting speed (m/min)
π ≈ 3,14
D : Cutter diameter (mm)
n : Rotation speed (rpm)
$v_f$ : Feed speed (mm/min)
$f_z$ : Feed rate (mm/tooth)
z : Number of teeth



## Functions of the Various Cutting Angles

| | Description | Code | Functions | Influences |
|---|---|---|---|---|
| ①<br>② | Axial rake angle<br>Radial rake angle | $\gamma_y$<br>$\gamma_x$ | Controls chip removal direction, effects adhesion of the chips and thrust force etc. | Rake angles can vary from positive to negative (large to small) with typical combinations of positive and negative, positive and positive or negative and negative configurations. |
| ③ | Approach angle | $\kappa$ | Controls chip thickness and chip removal direction | The effect of the small approach angle is to reduce the chip thickness and cutting force. |
| ④ | True rake angle<br>(Effective rake angle) | $\gamma$ | Controls cutting performance and ability to retain a cutting edge | - With a positive (large) angle, cutting ability and adhesion resistance are improved but the strength of the cutting edge is weakened.<br>- With negative (small) angle, the strength of the cutting edge is improved but chips will tend to adhere more easily. |
| ⑤ | Inclination angle | $\lambda$ | Controls chip removal direction | - With a positive (large) angle, the chip removal is satisfactory with less cutting resistance but the strengh of the corner is weaker. |
| ⑥ | Wiper flat clearance angle | $\alpha_f$ | Controls surface finish | A smaller clearance angle will produce a better surface finish. |
| ⑦ | Clearance angle | $\alpha$ | Controls edge strength, tool life and chattering, etc | |


**True Rake Angle Chart**




| Example in using the above chart: | | Solution: |
|---|---|---|
| ① $\gamma_y$ : | Axial rake angle = +10° | True rake angle |
| ② $\gamma_x$ : | Radial rake angle = -30° | ④ $\gamma$ = - 8° |
| ③ $\kappa$ : | Approach angle = 30° | |

Formula : $\tan\gamma = \tan\gamma_x \cdot \sin\kappa + \tan\gamma_y \cdot \cos\kappa$





**Inclination Angle Chart**




| Example in using the above chart : | | Solution: |
|---|---|---|
| ① $\gamma_y$ : | Axial rake angle = -10° | Inclination angle |
| ② $\gamma_x$ : | Radial rake angle = +10° | ⑤ $\lambda$ = - 15° |
| ③ $\kappa$ : | Approach angle = 65° | |


Formula : $\tan\lambda = \tan\gamma_y \cdot \sin\kappa - \tan\gamma_x \cdot \cos\kappa$

## Rake Angle Combination

| | Negative - Positive Type | Double Positive Type | Double Negative Type |
|---|---|---|---|
| The effects of the various angle configurations with relation to chip formation and chip removal.<br>Chip removal direction<br>Rotation |  |  |  |
| Advantage | Excellent chip removal and good cutting action | Good cutting action | Double-sided inserts can be use and higher cutting edge strength |
| Disadvantage | Only single-sided inserts can be use | Lower cutting edge strength and only single-sided inserts can be use | Dull cutting action |
| Application | For Steel, Cast iron, Stainless steel, Alloy steel | For general milling of steel<br>For low rigidly work piece | For light milling of cast iron and steel |
| Typical cutter | WGX, WGC, UFO | DPG | DNX, DGC, DNF |
| Chips (Eg.)<br>Workpiece: 37Cr4<br>$v_c$ = 130 m/min<br>$f_t$ = 0.23 mm/tooth<br>$a_p$ = 3 mm |  |  |  |


# Basics of Milling

## ■ Relation Between Engage Angle and Tool Life





Engage angle denotes the angle by which the full length of the cutting edge comes in contact with the workpiece, with reference to the feed direction. The larger E is, the shorter the tool life.

To change the value of E:
1) Increase the cutter size
2) Shift the position of the cutter




● Relation between the number of simultaneously engaged cutting edges and cutting force:




0 or 1 edge in contact

Only 1 edge in contact at any time.

1 or 2 edges in contact

2 edges in contact at any time.

2 to 3 edges in contact

## ■ To Improve Surface Roughness

### ① Milling inserts with wiper flat

When all the cutting edges have wiper flats, a few teeth are intentionally elevated to play the role of a wiper insert.


- Insert equipped with straight wiper flat (Face angle: Approx 15' - 1°)
- Insert equipped with curved wiper flat (Eg. curvature R500)

### ② Integral wiper insert system


A system to protrude one or two inserts (wiper insert) with a smooth curved edge just a little beyond the other teeth to wipe the milled surface.

- (Applies to WGC, RF types etc.)


● Surface roughness without wiper flat





● Surface roughness with straight wiper flat




h : Projected value of wiper insert
Steels : 0,05 mm
Al : 0,03 mm





f : Feed rate per revolution





Hc : Surface roughness with only normal teeth
Hw : Surface roughness with wiper insert

● Influence of different face angles on surface finish




- Workpiece: 34CrMo4
- Cutter: DPG 5160 R (Single tooth)
- $v_c$ = 154 m/min
  $f_z$ = 0,234 mm/tooth
  $a_p$ = 2 mm
- Face angle
  Ⓐ : 28'
  Ⓑ : 6'





● Effects of having wiper insert (example)




- Workpiece: GG25
- Cutter: DPG 4100 R
- Insert: SPKN 1203
- Axial run-out: 0,015 mm
- Radial run-out: 0,04 mm
- $v_c$ = 105 m/min
- $f_z$ = 0,29 mm/tooth (1,45 mm/rev)


Ⓒ : Only normal teeth
Ⓓ : with 1 wiper insert

## ■ Trouble Shooting Guide for Milling

<table>
<tr><th colspan="2">Trouble</th><th colspan="2">Basic Remedies</th><th>Remedy Examples</th></tr>
<tr><td rowspan="5">Cutting Edge Failure</td><td>Excessive Flank Wear<br></td><td>Tool Material<br><br><br><br>Cutting Conditions</td><td>- Select a more wear resistant grade.<br>Carbide<br>P30 ⇨ P20<br>K20 ⇨ K10 ⇨ { Coated / Cermet<br>- Reduce cutting speeds.<br>- Increase feedrate.</td><td>- Recommended insert grades<br><table><tr><th></th><th>Steel</th><th>Cast Iron</th><th>Non-Ferrous Alloy</th></tr><tr><td>Finishing</td><td>T250A (Cermet)</td><td>ACK200 (Coated Carbide)<br>BN700 (SUMIBORON)</td><td>DA1000 (SUMIDIA)</td></tr><tr><td>Roughing</td><td>ACP100 (Coated Carbide)</td><td>ACK200 (Coated Carbide)</td><td>DL1000 (Coated Carbide)</td></tr></table></td></tr>
<tr><td>Excessive Crater Wear<br></td><td>Tool Material<br><br>Cutting Conditions</td><td>- Select a crater resistant grade.<br>- Reduce cutting speeds.<br>- Reduce depth-of-cut and feed rate.</td><td>- Recommended insert grades<br><table><tr><th></th><th>Steel</th><th>Cast Iron</th><th>Non-Ferrous Alloy</th></tr><tr><td>Finishing</td><td>T250A (Cermet)</td><td>ACK200 (Coated Carbide)</td><td>DA1000 (SUMIDIA)</td></tr><tr><td>Roughing</td><td>ACP100 (Coated Carbide)</td><td>ACK200 (Coated Carbide)</td><td>DL1000 (Coated Carbide)</td></tr></table></td></tr>
<tr><td>Cutting Edge Chipping<br></td><td>Tool Material<br><br>Cutting Conditions<br><br>Tool Design</td><td>- Select tougher grade.<br>P10 ⇨ P20 ⇨ P30<br>K01 ⇨ K10 ⇨ K20<br>- Reduce feed rates.<br>- Select a negative-positive cutter configuration with a large approach angle.<br>- Reinforce the cutting edge (Honing).<br>- Select a strong edge insert (G → H).</td><td>- Recommended insert grades<br><table><tr><th></th><th>Steel</th><th>Cast Iron</th></tr><tr><td>Finishing</td><td>ACP200 (Coated Carbide)</td><td>ACK200 (Coated Carbide)</td></tr><tr><td>Roughing</td><td>ACP300 (Coated Carbide)</td><td>ACK300 (Coated Carbide)</td></tr></table>- Recommended cutter: WaveMill WGX type<br>- Cutting conditions:<br>Refer to recommended conditions listed in the general catalogue</td></tr>
<tr><td>Partial Fracture of Cutting Edges<br></td><td>Tool Material<br><br><br>Cutting Conditions<br><br>Tool Design</td><td>- If it is due to excessive low speeds or very low feed rates, select an adhesion resistant grade.<br>- If it is due to thermal cracking, select a thermal impact resistant grade.<br>- Select appropriate conditions with regards to the particular application.<br>- Select a negative-positive (or negative) cutter configuration with a large approach angle.<br>- Reinforce the cutting edge (Honing).<br>- Select a strong edge insert (G → H).<br>- Increase insert size -<br>(Thickness in particular).</td><td>- Recommended insert grades<br><table><tr><th></th><th>Steel</th><th>Cast Iron</th></tr><tr><td>Roughing</td><td>ACP300<br>(Coated Carbide)</td><td>ACK300<br>(Coated Carbide)</td></tr></table>- Recommended cutter: WaveMill WGX type<br>- Insert thickness: 3,18 → 4,76 mm<br>- Insert type: Standard → Strong edge type<br>- Cutting conditions:<br>Refer to recommended conditions listed in the general catalogue</td></tr>
<tr><td rowspan="4">Others</td><td>Unsatisfactory Machined Surface Finish</td><td>Tool Material<br>Cutting Conditions<br>Tool Design</td><td>- Select an adhesion resistant grade.<br>Carbide → Cermet<br>- Increase cutting speeds.<br>- Improve axial run-out of cutting edges.<br>(Use a cutter with less run-out)<br>(Attach correct inserts)<br>- Use wiper inserts.<br>- Use special purpose cutters designed for finishing.</td><td>- Recommended insert grades<br><table><tr><th colspan="2"></th><th>Steel</th><th>Cast Iron</th><th>Non-Ferrous Alloy</th></tr><tr><td>Roughing</td><td>Cutter Insert</td><td>WGX type*<br>ACP200<br>(Coated Carbide)</td><td>DGC type*<br>ACK200<br>(Coated Carbide)</td><td>FF type*<br>H1 (Carbide)<br>DL1000 (Coated Carbide)</td></tr><tr><td>Finishing</td><td>Cutter Insert</td><td>WGC type<br>T250A<br>(Cermet)</td><td>FMU type<br>BN700<br>(SUMIBORON)</td><td>RF type<br>DA1000<br>(SUMIDIA)</td></tr></table>* marked cutters can be fitted with wiper inserts.</td></tr>
<tr><td>Chattering</td><td>Cutting Conditions<br>Tool Design<br><br>Others</td><td>- Reduce feed rates.<br>- Select a high rake cutter with sharp cutting edges<br>- Use an irregular pitched cutter.<br>- Improve workpiece and cutter clamp rigidity.</td><td>- Recommended cutters:<br>For steel: WaveMill WGX type<br>For cast iron: DNX type<br>For Non-ferrous alloy: High speed cutter for aluminium<br>RF type</td></tr>
<tr><td>Unsatisfactory Chip Control</td><td>Tool Design</td><td>- Select cutter with good chip removal features.<br>- Reduce number of teeth.<br>- Enlarge chip pocket.</td><td>- Recommended cutter: WaveMill WGX type</td></tr>
<tr><td>Edge Chipping on Workpiece</td><td>Tool Design<br><br>Cutting Conditions</td><td>- Select a large approach angle.<br>- Select a sharp cutting edge insert (G → L).<br>- Reduce feed rates.</td><td>- Recommended cutter: WaveMill WGX type</td></tr>
<tr><td>Burr on Workpiece</td><td>Tool Design<br><br>Cutting Conditions</td><td>- Select a cutter with sharp cutting edges.<br>- Increase feed rates.</td><td>- Recommended cutter: WaveMill WGX type + FG breaker<br>DGC type + FG breaker</td></tr>
</table>

# Basics of Endmilling

## Parts of an Endmill




## Calculating Cutting Conditions

### Cutting speed

$$v_c = \frac{\pi \cdot D \cdot n}{1.000} \qquad n = \frac{1.000 \cdot v_c}{\pi \cdot D}$$

### Feed rate

$$v_f = f \times n$$

$$v_f = f_z \times z \times n \qquad f_z = \frac{v_f}{z \times n}$$


### Depth of cut (D.O.C)

$a_p$ : Axial D.O.C. (depth)
$a_e$ : Radial D.O.C. (width)


### Notch width ($D_1$)


$$D1 = 2 \times \sqrt{2 \times R \times a_p - a_p^2}$$

### Cutting speed and feedrate are calculated using the same formula as square endmill.





$v_c$ : Cutting speed (m/min)
$\pi \approx 3{,}14$
D : Endmill diameter (mm)
n : Rotational speed ($min^{-1}$)
$v_f$ : Feed speed (mm/min)
$f_r$ : Feed rate per revolution (mm/rev)
$f_z$ : Feed rate per tooth (mm/tooth)
z : Number of teeth






(Ball Endmill)

## ■ Up-cut and Dowm-cut




## ■ Relation Between Cutting Condition and Deflection




| Endmill | | | Side milling<br>Work material: Pre-hardened steel (40HRC)<br>Cutting data: $v_c$ = 25 m/min, $a_p$ = 12 mm, $a_e$ = 0,8 mm | | Slotting<br>Work material: Pre-hardened steel (40HRC)<br>Cutting data: $v_c$ = 25 m/min, $a_p$ = 8 mm, $a_e$ = 8 mm<br>Up-cut side / Down-cut side | |
|---|---|---|---|---|---|---|
| Cat. No. | Number of teeth | Helix angle | Feed rate 0,16 mm/rev<br>Style | | Feed rate 0,11 mm/rev<br>Style | |
| | | | Up-cut | Down-cut | Up-cut | Down-cut |
| SSM 2080 | 2 | 30° | | | | |
| SSM 4080 | 4 | 30° | | | | |

| Endmill | | | Slotting | |
|---|---|---|---|---|
| Cat. No. | Number of teeth | Helix angle | Feed rate 0,05 mm/rev<br>Style | |
| | | | Up-cut | Down-cut |
| SSM 2080 | 2 | 30° | | |
| SSM 4080 | 4 | 30° | | |

| Endmill | | | Slotting | |
|---|---|---|---|---|
| Cat. No. | Number of teeth | Helix angle | Feed rate 0,03 mm/rev<br>Style | |
| | | | Up-cut | Down-cut |
| SSM 2080 | 2 | 30° | | |
| SSM 4080 | 4 | 30° | | |


# Tool Failure and Remedies

## ■ Trouble Shooting Guide for Endmilling


| Failure | | Cause | | Remedies |
|---|---|---|---|---|
| Cutting Edge Failure | Excessive Wear | Cutting Conditions | - Cutting speed is too fast<br>- Feed rate is too fast | - Decrease cutting speed and feed rate. |
| | | Tool Shape<br>Tool Material | - The flank relief angle ist too small<br>- Insufficient wear resistance | - Change to an appropriate flank relief angle.<br>- Select a substrate with more wear resistance<br>- Use a coated tool |
| | Chipping | Cutting Conditions | - Feed rate ist too fast<br>- Cutting depth is too deep<br>- Tool overhang ist too long | - Decrease cutting speed.<br>- Reduce depth of cut<br>- Adjust tool overhang for correct length |
| | | Machine Area | - Work clamps are weak<br>- Tool is not firmly attached | - Clamp the work piece firmly<br>- Make sure the tool is seated in the chuck properly |
| | Tool Fracture | Cutting Conditions | - Feed rate ist too fast<br>- Cutting depth is too deep<br>- Tool overhang ist too long<br>- Cutting edge is too long | - Decrease cutting speed.<br>- Reduce depth of cut<br>- Reduce tool overhang as much as possible<br>- Select a tool with a shorter cutting edge |
| Others | Shoulder Deflection | Cutting Conditions | - Feed rate is too fast<br>- Cutting depth is too deep<br>- Tool overhang is too long<br>- Cutting on the down-cut | - Decrease cutting speed.<br>- Reduce depth of cut<br>- Adjust tool overhang for correct length<br>- Change directions to up-cut |
| | | Tool Shape | - Helix angle is large | - Use a tool with a smaller helix angle |
| | Unsatisfactory Machined Surface Finish | Cutting Conditions | - Feed rate is too fast | - Decrease cutting speed. |
| | | | - Packing of chips | - Use air blow<br>- Use an insert with a larger relief pocket. |
| | Chattering | Cutting Conditions | - Cutting speed is too fast<br>- Cutting on the up-cut<br>- Tool overhang is too long | - Decrease cutting speed.<br>- Change directions to down-cut<br>- Adjust tool overhang for correct length |
| | | Tool Shape<br>Machine Area | - Rake angle is large<br>- Work clamps are weak<br>- Tool is not firmly attached | - Use a tool with an appropriate rake angle<br>- Clamp the work piece firmly<br>- Make sure the tool is seated in the chuck properly |
| | Packing of Chip | Cutting Conditions | - Feed rate is too fast<br>- Cutting depth is too deep | - Decrease cutting speed.<br>- Reduce depth of cut |
| | | Tool Shape | - Too many teeth<br>- Packing of chips | - Reduce number of teeth<br>- Use air blow |

# Basics of Drilling

## Parts of a Drill





### ● Point Angle and Force





When point angle is large, thrust becomes large but torque becomes small.

### ● Point Angle and Burr





When point angle is large, burr height becomes low.

### ● Min. Requirement Relief Angle





＊Large relief angle is needed at the center of the drill.

### ● Web Thickness and Thrust





Web thinning decreases the thrust concentrated at chisel edge, makes the drill edge sharp and improves chip control. Tool life is also longer.

### ● Decrease Chisel Width by Thinning




S type : Standard type used generaly.
N type : Suitable for thin web drills.
X type : For hard-to-cut material or deep hole drilling.


### ● Width of Edge Threatment and Cutting Force





Drill: KDS 215 MAK
Work material: C50 (230HB)
Cutting conditions:
$v_c$ = 50 m/min, Water soluble

# Basics of Drilling

## ■ Reference of Power Requirement and Thrust




Work material:
C48 (220 HB)

## ■ Cutting Condition Selection

● Control cutting force for low rigid machine

The following table shows the relation between edge treatment width and cutting force. If a problem caused by cutting force occurs, reduce either the feedrate or the edge treatment width.


| Condition | | Edge treatment width | | | |
|---|---|---|---|---|---|
| | | 0,15 mm | | 0,05 mm | |
| $v_c$ (m/min) | f (mm/rev) | Torque (N• m) | Thrust (N) | Torque (N• m) | Thrust (N) |
| 40 | 0,38 | 12,8 | 2.820 | 12,0 | 2.520 |
| 50 | 0,30 | 10,8 | 2.520 | 9,4 | 1.920 |
| 60 | 0,25 | 9,2 | 2.320 | 7,6 | 1.640 |
| 60 | 0,15 | 6,4 | 1.640 | 5,2 | 1.100 |

Drill : ø10
Work material:
C50 (230 HB)

● High speed machining recommendation

When there is surplus capacity with enough machine power and rigidity drilling at normal recommended cutting conditions, we recommend higher drilling speeds.

Wear example





Vc = 60 m/min　　Vc = 120 m/min

Work material: C50 (230HB)
Cutting data: f = 0,3 mm/rev
$a_p$ = 50 mm
Tool life: 600 holes (Cutting length : 30 m)


## ■ Explanation of Margins (Difference between single and double margins)

● Single Margin (2 guides: circled parts)



● Shape used on most drills


● D Double Margin (4 guides: circled parts)




● 4-point guiding reduces hole bending and undulation for improved stability and accuracy during deep hole drilling.

## ■ Run-out Accuracy

Run-out of the lip height B and thinning point A are important.





Ⓐ : The run-out accuracy of thinning point
Ⓑ : The difference of lip height





## ■ Peripheral Run-out Accuracy when Tool Rotates

Drill run-out when mounted on the machine spindle must be within 0,03 mm. If the run-out is large, the drilled hole will also be large causing an increase in the horizontal cutting force, which may result in drill breakage if the machine or work clamping is not rigid.




Run-out: within 0,03 mm




Drill: MDS120MK
Work material: C50 (230HB)
Cutting data: $v_c$ =5 0 m/min, f = 0,3 mm/rev, $a_p$ = 38mm
Water soluble

## ■ Peripheral Run-out Accuracy when Workpiece Rotates


When use on a lathe, run-out at point A must be within 0,03 mm, this value must be similar when taken at position B.




## ■ Influence of Workpiece Surface

### ● Workpiece with slanted or uneven surface


If the surface of the hole entrance or exit is slanted or uneven, decrease the feedrate to 0,1–0,15 mm/rev at these points.




## ■ How to Use Long Drill


### ● Problem

When using a long drill (e.g. XHGS type and XHT type), DAK type or SMDH-D type drills at high rotational speeds, the run-out of the drill tip may cause a position shift at the entry point making the drill hole bent and resulting in drill breakage.





### ● Remedies

Method 1.




Method 2. Low rotational speed minimizes centrifugal forces and prevents drill bending.




# Tool Failure and Remedies


## ■ Trouble Shooting Guide for Drilling

| Failure | | Basic Remedies | | Remedies Examples |
|---|---|---|---|---|
| Drill Failure | Excessive Wear on Cutting Edge | Cutting Conditions | - Use higher cutting speeds.<br>- Increase feed rates. | - Vc = 80–100 m/min<br>- Refer to rec ommended cutting conditions listed in the general catalogue. |
| | | Cutting Fluid | - Reduce pressure if useing internal coolant.<br>- Use cutting fluid with more lubricity. | - Below 1,5 MPa. |
| | Chisel Point Chipping | Tool Design | - Increase size of chisel width.<br>- Increase amount of honing on cutting edge. | |
| | | Cutting Conditions | - Reduce depth-of cut.<br>- Reduce feed rate at entry point. | - f = 0,05–0,1 mm/rev . |
| | | Others | - Improve workpiece clamping rigidity. | |
| | Chipping on Peripheral Cutting Edge | Tool Design | - Increase amount of honing on cutting edge.<br>- Reduce the amount of front flank angle. | |
| | | Cutting Conditions | - Reduce cutting speeds.<br>- Increase feed rates. | - Refer to recommended cutting conditions listed in the general catalogue. |
| | | Cutting Fluid<br>Others | - Use cutting fluid with more lubricity.<br>- Improve workpiece clamp rigidity. | |
| | Margin Wear | Tool Design | - Increase amount of back taper.<br>- Reduce margin width. | |
| | | Cutting Conditions | - Reduce cutting speeds.<br>- Increase feed rates. | - Refer to recommended cutting conditions listed in the general catalogue. |
| | | Cutting Fluid<br>Others | - Use cutting fluid with more lubricity.<br>- Schedule for earlier regrind. | |
| | Drill Breakage | Tool Design | - Increase amount of back taper.<br>- Reduce margin width. | |
| | | Cutting Conditions | - Reduce cutting speeds. | - Refer to recommended cutting conditions listed in the general catalogue. |
| | | Cutting Fluid<br>Others | - Use cutting fluid with more lubricity.<br>- Improve workpiece clamp rigidity. | |
| Unsatisfactory Hole Accuracy | Oversized Holes | Tool Design | - Improve overall dril rigidity. (large web, small flute).<br>- Reduce drill point angle. | - 130°–120° |
| | | Cutting Conditions | - Reduce feed rate at entry phase.<br>- Reduce cutting speeds. | - f = 0,05–0,1 mm/rev<br>- Refer to recommended cutting conditions listed in the general catalogue. |
| | | Cutting Fluid<br>Others | - Improve workpiece clamp rigidity.<br>- Improve drill clamp precision.<br>- Improve drill clamp rigidity. | - Drill run-out below 0,02 mm |
| | Poor Surface Finish | Tool Design | - Increase amount of back taper. | |
| | | Cutting Conditions | - Increase cutting speeds. | - Refer to recommended cutting conditions listed in the general catalogue. |
| | | Cutting Fluid | - Use cutting fluid with more lubricity. | |
| | Holes are Not Straight | Tool Design<br>Cutting Conditions | - Reduce amount of edge honing.<br>- Reduce feedrates. | - Refer to recommended cutting conditions listed in the general catalogue. |
| | | Others | - Improve workpiece clamp rigidity.<br>- Improve drill clamp precision.<br>- Improve drill clamp ridigity. | - Drill run-out below 0,02 mm |
| Unsatisfactory Chip Control | Packing of Chips | Cutting Conditions | - Increase cutting speeds.<br>- Increase feed rates. | - Refer to recommended cutting conditions listed in the general catalogue. |
| | | Cutting Fluid | - Reduce pressure if using internal coolant. | - Below 1,5 MPa. |
| | Long Stringy Chips | Tool Design<br>Cutting Conditions | - Reduce amount of edge honing.<br>- Increase feed rates. | - Refer to recommended cutting conditions listed in the general catalogue. |
| | | Cutting Fluid | - Reduce pressure if using internal coolant. | - Below 1,5 MPa. |

## Application Map of the Various Tool Materials





## Work Materials and Cutting Speed Recommendations





## Influence of Coolant on Tool Life

● Continuous cutting




● Interrupted cutting


Work material: X155CrVMo12-1
Cutting data: $v_c$ = 100 m/min
$a_p$ = 0,2 mm
f = 0,1 mm/rev





Work material: 100Cr6 (HRC58–62)
Insert: TPGN160304
Cutting data: $v_c$ = 100 m/min
$a_p$ = 0,15 mm
f = 0,1 mm/rev

**For continuous cutting, the influence of coolant on tool life is minimal. However for interrupted cutting, coolant will shorten the tool life because of thermal cracking.**

## Relation Workpiece Hardness and Cutting Forces





Work material: C105W1
Cutting data: $v_c$ = 120 m/min
$a_p$ = 0,2 mm
f = 0,1 mm/rev

**Back force increases substantially for harder work materials.**


## Relation between Flank Wear and Cutting Force





Cutting data: $v_c$ = 80 m/min
$a_p$ = 0,15 mm
f = 0,1 mm/rev

**For hardened steel machining, back force increases substantially due to the expansion of flank wear.**

## Workpiece Hardness on Cutting Force and Accuracy





Cutting data: $v_c$ = 120 m/min
$a_p$ = 0,5 mm
f = 0,3 mm/rev
dry




**External dimension at the soft zone is smaller due to lower cutting forces.**

## Relation Cutting Speed and Surface Roughness





Work material: 25CrMo4 (HRC58–62)
Holder: MTXNR2525
Insert: TNMA160408NU

Cutting data:
$v_c$= 120, 150, 180 m/min
$a_p$ = 0,15 mm
f = 0,045 mm/rev
Wet

**At high cutting speeds, surface roughness is more stable.**

## Improvement of Surface Roughness by Altering the Feedrate


| Constant Feedrate | Variable Feedrate |
|---|---|
| Previous edge position<br>f<br>Stationary notch location | f<br>Shifting notch location |
|  |  |

**Varying the feedrate spreads the notch location over a larger area, surface finish improves and notch wear decreases.**

# Cast Iron Machining


## ■ Advantages of Using SUMIBORON for Cast Iron Machining

● Higher accuracy





● Longer tool life at higher cutting speeds

GG: Grey cast iron






GGG: Ductile cast iron





## ■ Turning


● Cast iron structure and wear shape examples

| | | GG | GGG |
|---|---|---|---|
| Structure | |  |  |
| | Matrix | Pearlite | Pearlite + Ferrite |
| Tool wear shape | Wet |  |  |
| | Dry |  Crater wear |  |

($v_c \geq$ 200 m/min)




Work material: GG25
Insert: SNGN120408(BN500)
Cutting data: $v_c$ = 450 m/min
$a_p$ = 0,25 mm
f = 0,15 mm/rev
Continuous cutting







**For machining cast iron with SUMIBORON, cutting speeds (Vc) should be 200m/min and above. WET cutting is recommended.**


Machine: N/C lathe
Work material: GG25 (HB200)
Holder: MTJNP2525
Insert: TNMA160408(BN500)
Cutting data: $v_c$ = 110–280 m/min
$a_p$ = 0,1 mm
f = 0,1 mm/rev
WET

## ■ Milling


SUMIBORON BN Finish Mill EASY



- High speed machining Vc = 2000 m/min
- Surface Roughness Rz = 3,2 (Ra = 1,0)
- Running cost is reduced because of economical insert
- Easy insert setting with the aid of a setting gauge
- Safe, anti-centrifugal force construction for high speed conditions





Work material: GG25
Tool material: BN700
Cutting data: $a_p$ = 0,5 mm, $f_z$ = 0,1 mm/tooth, DRY




Dry cutting is recommended for high speed milling of cast iron with SUMIBORON.

## Powder Metal





Work material: SMF4040 equivalent
Process details: ø100–300 mm heavy interrupted facing with grooves and drilled holes. (after 40 passes)
Insert: TNGA160404 Cutting data: f = 0.1 mm/rev, d = 0.1 mm, Wet

For general power metal components, carbide and cermet grades can perform up to Vc = 100 m/min. However, around Vc= 120 m/min, wear becomes rapid and surface roughness deteriorates with increased burrs.
SUMIBORON on the other hand, exhibits stability and superior wear resistance, burr prevention and surface roughness especially at high speeds.


## Heat Resistive Alloy

### Ni based alloy

Typical tool damage of CBN tool when cutting Inconel 718





Cutting data: f = 0,06 mm/rev, $a_p$ = 0,3 mm, WET





Tool life criteria
Notch wear = 0,25 mm
Or flank wear = 0,25 mm
BNX20 is recommended for high speed and low feedrate condition.
BN700 is recommended for cutting speeds below 240 m/min

Cutting data: f = 0,12 mm/rev, $a_p$ = 0,3 mm, WET





Tool life criteria
Notch wear = 0,25 mm
Or flank wear = 0,25 mm
BN700 is recommended for cutting at high feedrates.
(Over f = 0,1 mm/rev)


### Ti based alloy




Work Material: Ti-6Al-4V
Insert: DNM120404NF
Cutting data: $v_c$ = 100 m/min, $a_p$ = 0,1 mm, f = 0,05 mm/rev, WET
SUMIDIA positive type inserts are extremely good for Ti alloy, due to high cutting edge strength and high wear resistance.




Work Material: Ti-6Al-4V
Insert: DNM120404NF
Cutting data: $v_c$ = 100 m/min, $a_p$ = 0,1 mm, f = 0,05 mm/rev, WET
SUMIDIA positive type inserts are extremely good for Ti alloy, due to high cutting edge strength and high wear resistance.





Work Material: Ti-6Al-4V
Insert: DNMA150412
Cutting data: Vc = 120 m/min, $a_p$ = 0,3 mm, f = 0,25 mm/rev, WET
Negative type insert BN700 is excellent for high efficiency cutting. (For large depth of cut and high feedrates)

### Hard facing alloys


Work material: Colmonoy No.6 (Ni-based self fluxing alloy)

Insert: SNGN090308
Cutting data:
$v_c$ = 50, 300 m/min
f = 0,1 mm/rev
$a_p$ = 0,2 mm
Wet




Work material: Stellite SF-20 (Co-based Self-fluxing alloy)

Insert: SNGN090308
Cutting data:
$v_c$ = 50 m/min
f = 0,1 mm/rev
$a_p$ = 0,2 mm
Dry







BNS800
(Vc = 300 m/min, After 2 km Cutting)



Whisker reinforced ceramic
(Vc = 50 m/min, After 10 m Cutting)





BNS800
(After 2 km of cutting)




Competitor's solid CBN
(After 2 km of cutting)

# Tool Failure and Remedies

| | Damage | | Remedies |
|---|---|---|---|
| Cutting Edge Failure | Large flank wear  | Tool material<br>Tool design<br><br>Cutting condition | - Select a more wear resistant grade.<br>- Reduce the cutting force.<br>- Reduce the NL width and angle.<br>- Positive inserts preferred<br>- Check the cutting speed.<br>- Reduce the cutting speed to less than 200 m/min.<br>- Higher feed rate reduces the overall tool-to-work contact time. |
| | Large crater wear  | Tool material<br><br><br><br>Tool design<br><br><br><br>Cutting condition | - Crater wear resistant grades are recommended.<br>- Continuous ~ Light interrupted cutting = BNC2010<br>- Light ~ Medium interrupted cutting = BNX20<br>- Medium ~ Heavy interrupted cutting = BNX25<br><br>- Determine the cutting edge geometry after inspecting the used inserts closely.<br>- Sharpen the cutting edge to prevent crater wear.<br>- Strengthen the cutting edge to prevent crater breakage.<br><br>- Check the cutting speed.<br>- Reduce the cutting speed to less than 200 m/min.<br>- Higher feed rates are recommended. |
| | Breakage at bottom of crater  | | |
| | Flaking  | Tool material<br><br>Tool design<br><br><br>Cutting condition | - Flaking is caused by high back forces and back force is related to flank wear.<br>- Select a more wear resistant grade.<br>- A sharper cutting edge helps prevent flaking.<br>- Reduce the NL angle and width<br>- Positive inserts preferred<br>- Reduce flank wear with lower speed and higher feed rates.<br>- Reducing tool-to-work contact time effectively reduces flank wear. |
| | Chipping at notch position  | Cutting condition | - If surface finish is affected, consider using the “Variable Feed rate” method to improve finishing.<br>- For other cases, use remedies similar to that for normal wear. |
| | Chipping at notch position  | Tool material<br><br><br>Tool design<br><br>Cutting condition | - Caused by impact shocks to the cutting edge.<br>- Chattering may also be a contributing factor.<br>- Select a tougher grade.<br>- Strengthen the cutting edge.<br>- Large NL angle, Honing.<br>- Higher feed rates are recommended to lessen the number of impacts. |
| | Chipping at nose position  | Tool material<br><br><br>Tool design<br><br>Cutting condition | - Caused by impact shocks to the cutting edge.<br>- Chattering may also be a contributing factor.<br>- Select a tougher grade.<br>- Strengthen the cutting edge.<br>- Large NL angle, Honing.<br>- Higher feedrates are recommended to lessen the number of impacts. |
| | Thermal crack  | Cutting condition<br><br><br><br><br>Tool design<br>Tool material | - Thermal shocks generate vertical crack lines across the cutting edge.<br>- Completely dry condition is recommended.<br>- If dry condition machining is already observed, then reduction of cutting temperatures and cutting force is necessary.<br>- Decrease cutting speed, feedrate, depth of cut.<br>- Sharpen cutting edge.<br>- Select more thermal conductivity grade. |

## ■ Steel and Non-Ferrous Metal Symbols Chart

### ● Carbon Steels

| JIS | AISI | DIN |
|---|---|---|
| S10C | 1010 | C10 |
| S15C | 1015 | C15 |
| S20C | 1020 | C22 |
| S25C | 1025 | C25 |
| S30C | 1030 | C30 |
| S35C | 1035 | C35 |
| S40C | 1040 | C40 |
| S45C | 1045 | C45 |
| S50C | 1049 | C50 |
| S55C | 1055 | C55 |

### ● Ni-Cr-Mo Steels

| | | |
|---|---|---|
| SNCM220 | 8620 | 21NiCrMo2 |
| SNCM240 | 8640 | — |
| SNCM415 | — | — |
| SNCM420 | 4320 | — |
| SNCM439 | 4340 | 40NiCrMo6 |
| SNCM447 | — | 34NiCrMo6 |

### ● Cr Steels

| | | |
|---|---|---|
| SCr415 | — | 15CrMo5 |
| SCr420 | 5120 | 20Cr4 |
| SCr430 | 5130 | 34Cr4 |
| SCr435 | 5132 | 37Cr4 |
| SCr440 | 5140 | 41Cr4 |
| SCr445 | 5147 | — |

### ● Cr-Mo Steels

| | | |
|---|---|---|
| SCM415 | — | 15CrMo5 |
| SCM420 | — | 20CrMo5 |
| SCM430 | 4131 | 25CrMo4 |
| SCM435 | 4137 | 34CrMo4 |
| SCM440 | 4140 | 42CrMo4 |
| SCM445 | 4145 | — |

### ● Mn Steels and Mn-Cr Steels for Structural Use

| | | |
|---|---|---|
| SMn420 | 1522 | — |
| SMn433 | 1534 | — |
| SMn438 | 1541 | — |
| SMn443 | 1541 | — |
| SMnC420 | — | — |
| SMnC443 | — | — |

### ● Cr-Mo Steels

| | | |
|---|---|---|
| SK1 | — | — |
| SK2 | W1-11 1/2 | — |
| SK3 | W1-10 | C105W1 |
| SK4 | W1-9 | — |
| SK5 | W1-8 | C80W1 |
| SK6 | — | C80W1 |
| SK7 | — | C70W2 |

### ● High Speed Steels

| JIS | AISI | DIN |
|---|---|---|
| SKH2 | T1 | — |
| SKH3 | T4 | S18-1-2-5 |
| SKH10 | T15 | S12-1-4-5 |
| SKH51 | M2 | S6-5-2 |
| SKH52 | M3–1 | — |
| SKH53 | M3–2 | S6-5-3 |
| SKH54 | M4 | — |
| SKH56 | M36 | — |

### ● Alloy Tool Steels

| | | |
|---|---|---|
| SKS11 | F2 | — |
| SKS51 | L6 | — |
| SKS43 | W2-9 1/2 | — |
| SKD1 | D3 | X210Cr12 |
| SKD11 | D2 | X155CrVMo12-1 |
| SKD61 | — | X40CrVMo5-1 |

### ● Grey Cast Iron

| | | |
|---|---|---|
| FC100 | No 20B | GG-10 |
| FC150 | No 25B | GG-15 |
| FC200 | No 30B | GG-20 |
| FC250 | No 35B | GG-25 |
| FC300 | No 45B | GG-30 |
| FC350 | No 50B | GG-35 |

### ● Nodular Cast Iron

| | | |
|---|---|---|
| FCD400 | 60-40-18 | GGG-40 |
| FCD450 | — | GGG-40.3 |
| FCD500 | 80-55-06 | GGG-50 |
| FCD600 | — | GGG-60 |
| FCD700 | 100-70-03 | GGG-70 |

### ● Ferritic Stainless Steels

| | | |
|---|---|---|
| SUS405 | 405 | X10CrAl13 |
| SUS429 | 429 | — |
| SUS430 | 430 | X6Cr17 |
| SUS430F | 430F | X7CrMo18 |
| SUS434 | 434 | X6CrMo17 1 |

### ● Martensitic Stainless Steels

| | | |
|---|---|---|
| SUS403 | 403 | — |
| SUS410 | 410 | X10Cr13 |
| SUS416 | 416 | — |
| SUS420JI | 420 | X20Cr13 |
| SUS420F | 420F | — |
| SUS431 | 431 | X20CrNi17 2 |
| SUS440A | 440A | — |
| SUS440B | 440B | — |
| SUS440C | 440C | — |

### ● Austenitic Stainless Steels

| JIS | AISI | DIN |
|---|---|---|
| SUS201 | 201 | — |
| SUS202 | 202 | — |
| SUS301 | 301 | X12CrNi17 7 |
| SUS302 | 302 | — |
| SUS302B | 302B | — |
| SUS303 | 303 | X10CrNiS18 9 |
| SUS303Se | 303Se | — |
| SUS304 | 304 | X5CrNiS18 10 |
| SUS304L | 304L | X2CrNi19 11 |
| SUS304NI | 304N | — |
| SUS305 | 305 | X5CrNi18 12 |
| SUS308 | 308 | — |
| SUS309S | 309S | — |
| SUS310S | 310S | — |
| SUS316 | 316 | X5CrMo17 12 2 |
| SUS316L | 316L | X2CrNiMo17 13 2 |
| SUS316N | 316N | — |
| SUS317 | 317 | — |
| SUS317L | 317L | X2CrNiMo18 16 4 |
| SUS321 | 321 | X6CrNiTi18 10 |
| SUS347 | 347 | X6CrNiNb18 10 |
| SUS384 | 384 | — |

### ● Heat Resisting Steels

| | | |
|---|---|---|
| SUH31 | — | — |
| SUH35 | — | — |
| SUH36 | — | X53CrMnNi21 9 |
| SUH37 | — | — |
| SUH38 | — | — |
| SUH309 | 309 | — |
| SUH310 | 310 | CrNi2520 |
| SUH330 | N08330 | — |

### ● Ferritic Heat Resisting Steels

| | | |
|---|---|---|
| SUH21 | — | CrAl1205 |
| SUH409 | 409 | X6CrTi12 |
| SUH446 | 446 | — |

### ● Martensitic Heat Resisting Steels

| | | |
|---|---|---|
| SUH1 | — | X45CrSi9 3 |
| SUH3 | — | — |
| SUH4 | — | — |
| SUH11 | — | — |
| SUH600 | — | — |

# References

## Steel and Non-Ferrous Metal Symbols Chart

Expansion

### P Carbon Steel for Structural Use

| JIS | AISI/ASTM | DIN/EN | GB | BS | AFNOR | ГОСТ |
|---|---|---|---|---|---|---|
| S10C | 1008<br>1010 | C10E<br>C10R<br>1.1122 | 08<br>10 | 040A10<br>045A10<br>045M10 | XC10 | 08<br>10 |
| S12C | 1012 | — | — | 040A12 | XC12 | — |
| S15C | 1015 | C15E<br>C15R<br>1.1132 | 15 | 055M15 | — | 15 |
| S20C | 1020 | C22<br>CK22 | 20 | 070M20 | — | 20 |
| S25C | 1025 | C25<br>C25E<br>C25R<br>C16D<br>1.0415 | 25 | — | — | 25 |
| S30C | 1030 | C30<br>C30E<br>C30R | 30 | 080A30<br>080M30 | — | 30 |
| S35C | 1035 | C35<br>C35E<br>C35R<br>1.1172 | 35 | 080A35<br>080M36 | — | 35 |
| S40C | 1040<br>C40E | C40<br>C40E<br>C40R<br>1.1186 | 40 | 060A40<br>080A40<br>080M40 | — | 40 |
| S43C | 1042<br>1043 | — | — | 080A42 | XC42H1<br>XC42H2 | 40Г |
| S45C | 1045<br>1045H | C45<br>C45E<br>C45R<br>1.1191<br>1.1192 | 45 | 060A45<br>080M46 | XC45 | 45 |
| S50C | 1049 | C50<br>C50E<br>C50R<br>1.1206 | 50 | 080M50 | XC50 | 50 |
| S53C | 1050<br>1053 | — | 50Mn | 080A52 | XC54 | — |
| S55C | 1055 | C55<br>C55E<br>C55R<br>1.1203 | 55 | 070M55 | XC55H1<br>XC55H2 | 55 |
| S58C | 1060 | C60<br>C60E<br>C60R | 60 | 060A57<br>080A57 | XC60 | — |
| S60C | 1059 | C60E<br>1.1221 | 60<br>60Mn | — | — | 60 |
| S09CK | 1010 | C10E<br>C10R | — | 045A10<br>045M10 | XC10 | — |
| S15CK | 1015 | C15E<br>C15R | — | — | XC12 | — |
| S20CK | — | CK22 | — | — | XC18 | — |

### P Cr-Mo Steel

| JIS | AISI/ASTM | DIN/EN | GB | BS | AFNOR | ГОСТ |
|---|---|---|---|---|---|---|
| SCM415 | — | 18CrMo4<br>1.7243 | 15CrMo | — | — | 15ХМ |
| SCM420 | — | 20MoCr4<br>1.7321 | 20CrMo | 708M20 | — | 20ХМ |
| SCM421 | 4121 | 18CrMo4<br>22CrMoS35<br>1.7243 | 20CrMn-<br>Mo | — | — | 25ХГМ |
| SCM425 | — | 25CrMo<br>1.7218 | 25CrMo | — | — | — |
| SCM430 | 4130 | — | 30CrMo | 708A30 | 30CD4 | 30ХМ |
| SCM435 | 4135<br>4137 | 34CrMo4<br>1.7220 | 35CrMo | 708A37<br>709A37 | 34CD4<br>38CD4<br>35CD4 | 35ХМ |
| SCM440 | 4142<br>4140 | 42CrMo4<br>42CrMoS4<br>1.7225 | 42CrMo | 708M40<br>708A40<br>708A42<br>709A42<br>709M40 | 42CD4 | 38ХМ |
| SCM445 | 4145<br>4150 | 50CrMo4<br>1.7228 | 50CrMo | 708A47 | — | — |

### P Manganese Chromium Steel/Manganese Steel

| | | | | | | |
|---|---|---|---|---|---|---|
| SMn420 | 1522<br>1524 | 18Mn5<br>1.0436 | 20Mn2 | 150M19<br>120M19 | 20M5 | 20Г |
| SMn433 | 1330 | 28Mn6<br>1.1170 | 30Mn2 | — | — | 30Г2 |
| SMn438 | 1335<br>1541 | — | 35Mn2 | 150M36 | 40M6 | 35Г2 |
| SMn443 | 1340<br>1345<br>1541 | — | 40Mn2<br>45Mn2 | 135M40<br>150M36 | 35M5 | 35Г2<br>45Г2 |
| SMnC420 | 5120 | 20MnCr5<br>1.7147 | 20CrMn | — | — | 18ХГ |
| SMnC443 | 5140 | 41Cr4<br>1.7035 | 40CrMn | — | — | — |

### P Carbon Tool Steel

| | | | | | | |
|---|---|---|---|---|---|---|
| SK140<br>SK1 | W2-13A<br>W1-13 | — | T13 | — | $Y_2$140 | — |
| SK120<br>SK2 | W1-11 1/2 | C120U<br>1.1555 | T12 | BW1C | $Y_2$120 | y12 |
| SK105<br>SK3 | W1-10<br>W1-10 1/2 | C105U<br>1.1545<br>C105W1 | T11 | BW1B | $Y_1$105 | — |
| SK95<br>SK4 | W1-9<br>W1-9 1/2 | C105U<br>1.1545 | T10 | BW1A | $Y_1$90<br>$Y_1$80 | y10 |
| SK85<br>SK5 | W1-8C<br>W1-8 | C80W1 | T8Mn | BW1A | — | y8Г |
| SK80 | W1-8A | C80U<br>1.1525 | T8 | — | — | y8 |
| SK70 | 1070 | C70U<br>1.1520 | T7 | — | — | y7 |

## Cr Steel

| JIS | AISI/ASTM | DIN/EN | GB | BS | AFNOR | ГОСТ |
|---|---|---|---|---|---|---|
| SCr415 | 5115 | 17Cr3<br>1.7016 | 15Cr | — | — | 15X |
| SCr420 | 5120 | — | 20Cr | — | 20MC5 | 20X |
| SCr430 | 5130<br>5132 | 34Cr4<br>34CrS4<br>1.7033 | 30Cr | 530A30<br>530A32 | 32C4 | 30X |
| SCr435 | 5135 | 37Cr4<br>1.7034 | 35Cr | 530A36 | 38C4 | 35X |
| SCr440 | 5140 | 41Cr4<br>41CrS4<br>1.7035 | 40Cr | 530M40<br>530A40 | 42C4 | 40X |
| SCr445 | 5147 | — | 45Cr | — | — | 45X |

## Nickel Chromium Steel

| | | | | | | |
|---|---|---|---|---|---|---|
| SNC415 | 4720<br>4715 | 20NiCrMo2-2<br>10NiCr5-4<br>17CrNi6-6<br>1.5918<br>1.5805<br>1.6523 | 20CrNi<br>12CrNi2<br>15CrNi6K | — | — | 20XH<br>12XH |
| SNC236 | 3140<br>4337 | 41crCrMo7-3-2<br>34CrNiMo6 | 40CrNi<br>34CrNi2 | — | — | 40XH |
| SNC246 | 8645 | — | 45CrNi | — | — | 45XH |
| SNC815 | E3310 | 15NiCr13<br>1.5752 | 12CrNi3 | — | — | 12XH3A |
| SNC620 | — | 20NiCrMo13-4<br>1.6660 | 20CrNi3 | — | — | 20XH3A |
| SNC631 | — | 30NiCrMo16-6<br>1.6747 | 30CrNi3 | — | — | 30XH3A |
| SNC836 | — | 35NiCrMo16<br>1.6773 | 37CrNi3 | — | — | — |

## Ni-Cr-Mo Steel

| | | | | | | |
|---|---|---|---|---|---|---|
| SNCM220 | 8615<br>8617<br>8620<br>8622<br>4718 | 20NiCrMo2-2<br>20NiCrMoS2-2<br>17NiCrMo6<br>1.6566<br>1.6523 | 20CrNiMo<br>18CrMnNiMo<br>20NiCrMoK | 805A20<br>805M20<br>805A22<br>805M22 | 20NCD 2 | 20XH2M<br>18ХНГМ |
| SNCM240 | 8637<br>8640 | 39NiCrMo3<br>1.6510 | 40CrNiMo | — | — | 40XH2MA |
| SNCM415 | — | — | — | — | — | |
| SNCM420 | 4320 | 17NiCrMo6-4 | 20CrNi2Mo | — | — | 20XH2M<br>(20XHM) |
| SNCM439 | 4340 | 41NiCrMo7-3-2<br>1.6563 | 40CrNi2Mo | — | — | 40XH2MA |
| SNCM447 | 4340 | 41NiCrMo7-3-2<br>1.6563 | 45CrNiMoV | — | — | — |

## High Speed Steel

| JIS | AISI/ASTM | DIN/EN | GB | BS | AFNOR | ГОСТ |
|---|---|---|---|---|---|---|
| SKH2 | T1 | HS18-0-1<br>1.3355 | W18Cr4V | BT1 | Z80WCV<br>18-04-01 | P18 |
| SKH3 | T4 | S18-1-2-5 | — | BT4 | Z80WKCV<br>18-05-04-01 | — |
| SKH4 | T5 | — | — | BT5 | Z80WKCV<br>18-10-04-02 | — |
| SKH10 | T15 | S12-1-4-5 | W12Cr4V5Co5 | BT15 | Z160WKCV<br>12-05-05-04 | P12K5V5 |
| SKH51 | M2 | S6-5-2<br>1.3339 | W6Mo5Cr4V2 | BM2 | Z160WDCV<br>06-05-04-02 | P6M5ø2 |
| SKH52 | M3-1 | HS6-6-2<br>1.3350 | W6Mo6Cr4V2 | — | — | — |
| SKH53 | M3-2 | S6-5-3<br>HS6-5-3<br>1.3344 | W6Mo5Cr4V3 | — | Z160WDCV<br>06-05-04-03 | P6M5ø3 |
| SKH54 | M4 | — | W6Mo5Cr4V4 | BM4 | Z130WDCV<br>06-05-04-04 | — |
| SKH55 | M35<br>M41 | S6-5-2-5<br>HS6-5-2-5<br>1.3243 | W6Mo5Cr4V2Co5 | BM35 | Z190WDCV<br>06-05-05-04-02 | P6M5K5 |
| SKH56 | M36 | — | — | — | — | — |
| SKH57 | M48 | HS10-4-3-10<br>1.3207 | W10Mo4Cr4V3Co10 | — | Z130WKCDV<br>10-10-04-04-03 | — |
| SKH58 | M7 | HS2-8-2<br>1.3348 | W2Mo9Cr4V2 | — | Z100DCWV<br>09-04-02-02 | — |
| SKH59 | M42 | HS2-10-1-8<br>1.3247 | W2Mo9Cr4VCo8 | BM42 | Z130DKCWV<br>09-08-04-02-01 | P2M9K8ø |

## Alloy Tool Steel

| | | | | | | |
|---|---|---|---|---|---|---|
| SKS11 | F2 | — | — | — | — | — |
| SKS2 | — | 105WCr6 | — | — | 105WC13 | — |
| SKS51 | L6 | — | — | — | — | — |
| SKS41 | — | — | 4CrW2Si | — | — | 4XB2C |
| SKS43 | W2-9 1/2 | — | — | BW2 | Y1105V | — |
| SKS44 | W2-8 1/2 | — | — | — | — | — |
| SKS3 | O1 | 95MnWCr5<br>1.2825 | 9CrWMn | — | — | 9ХВГ |
| SKS31 | O7 | 105WCr6 | CrWMn | — | 105WC31 | ХВГ |
| SKD1 | D3 | X210Cr12<br>1.2080 | Cr12 | BD3 | X200Cr12 | X12 |
| SKD4 | — | — | 30W4Cr2V | BH21 | Z32WCV5 | — |
| SKD5 | H21 | X30WCrV9-3<br>1.2581 | 3Cr2W8V | BH21 | Z30WCV9 | 3X2B8ø |
| SKD6 | H11 | X37CrMoV5-1<br>1.2343 | 4Cr5MoSiV | BH11 | X38CrMoV5 | 4X5MøC |
| SKD61 | H13 | X40CrMoV5-1<br>1.2344 | 4Cr5MoSiV1 | BH13 | Z40CDV5 | 4X5Mø1C |
| SKD7 | H10 | X32CrMoV33<br>1.2365 | 3Cr3Mo3V | BH10 | 32DCV28 | — |
| SKD8 | H19 | 38CrCoWV18-17-17<br>1.2661 | 3Cr3Mo3VCo3 | BH19 | — | — |
| SKD10 | D2 | X153CrMoV12<br>1.2379 | Cr12Mo1V1 | — | — | X12M1ø1 |
| SKD11 | D2<br>D4 | — | Cr12MoV | BD2 | X160CrMoV12 | X12Mø |
| SKD12 | A2 | X100CrMoV5<br>1.2363 | Cr5Mo1V | BA2 | Z100CDV5 | — |

# References

## Steel and Non-Ferrous Metal Symbols Chart

Expansion

### Ferritic Stainless Steels

| JIS | AISI/ASTM | DIN/EN | GB | BS | AFNOR | ГОСТ |
|---|---|---|---|---|---|---|
| SUS405 | 405<br>S40500 | X10CrAl13<br>1.4002 | 0Cr13Al<br>06Cr13Al | 405S17 | 26CA13 | — |
| SUS429 | 429<br>S42900 | — | 1Cr15<br>10Cr15<br>022Cr15NbTi | — | — | — |
| SUS430 | 430<br>S43000 | X6Cr17<br>1.4016 | 1Cr17<br>10Cr15<br>S11710 | 430S17 | Z8C17 | 12X17 |
| SUS430F | 430F<br>S43020 | X12CrMoS17 | Y1Cr17<br>Y10Cr17 | — | 210CF17 | — |
| SUS434 | 434<br>S43400 | X6CrMo17-1<br>1.4113 | 1Cr17Mo<br>10Cr17Mo | 434S17 | Z8CD17.01 | — |

### Martensitic Stainless Steels

| | | | | | | |
|---|---|---|---|---|---|---|
| SUS410 | 410<br>S41010 | X10Cr13<br>1.4006 | 12Cr13<br>1Cr13 | 410S21 | Z13C13 | 12X13 |
| SUS403 | 403<br>S40300 | — | 12Cr12<br>1Cr12 | — | — | — |
| SUS444 | 444<br>S44400 | X2CrMoTi18-2<br>1.4521 | 019Cr19Mo2NbTi<br>00Cr18Mo2 | — | — | — |
| SUS416 | 416<br>S41600 | X12CrS13<br>1.4005 | Y12Cr13<br>Y1Cr13 | 416S21 | Z12CF13 | — |
| SUS420J1 | 420<br>S42000 | X20Cr13<br>1.4021 | 20Cr13<br>2Cr13 | 420S29 | Z20C13 | 20X13 |
| SUS420J2 | 420<br>S42000 | X30Cr13<br>1.4028 | 30Cr13<br>3Cr13 | 420S45 | Z30C13 | 30X13 |
| SUS420F | 420G<br>S42020 | X29Cr13<br>1.4029 | Y30Cr13<br>Y3Cr13 | — | Z30CF13 | — |
| SUS431 | 431<br>S43100 | X17CrNi16-2 | 17Cr16Ni2 | 431S29 | — | — |
| SUS440C | 440C<br>S44004 | — | 108Cr17<br>11Cr17 | — | Z100CD17 | — |

### Stainless Steel (Precipitation Hardened Structure)

| | | | | | | |
|---|---|---|---|---|---|---|
| SUS630 | 630<br>S17400 | X5CrNiCuNb16-4<br>1.4542 | 0Cr17Ni4Cu4Nb<br>05Cr17Ni4Cu4Nb | — | Z6CNU17.04 | — |
| SUS631 | 631<br>S17700 | X7CrNiAl17-7<br>1.4568 | 0Cr17Ni7Al<br>07Cr17Ni7Al | — | Z8CNA17.07 | 09Х17Н7 Ю |

### Austenitic Stainless Steels

| JIS | AISI/ASTM | DIN/EN | GB | BS | AFNOR | ГОСТ |
|---|---|---|---|---|---|---|
| SUS201 | 201<br>S20100 | X12crMnNiN17-7-5<br>1.4372 | 1Cr17Mn6Ni5N<br>12Cr17Mn6Ni5N | — | Z12CMN17-07Az | — |
| SUS202 | 202<br>S20200 | X12CrMnNiN18-9-5<br>1.4373 | 1Cr18Mn9Ni5N<br>12Cr18Mn9Ni5N | 284S16 | — | — |
| SUS301 | 301<br>S30100 | X12CrNi17 7<br>1.4319<br>1.4310 | 1Cr17Ni7<br>12Cr17Ni7 | — | Z12CN17.07 | 17Х18Н9 |
| SUS302 | 302<br>S30200 | X9CrNi18-9<br>1.4325 | 1Cr18Ni9<br>12Cr18Ni9 | 302S25 | Z10CN18.09 | 12Х18Н9 |
| SUS302B | 302B<br>S30215 | — | 1Cr18Ni9Si3<br>12Cr18Ni9Si3 | — | — | — |
| SUS303 | 303<br>S30300 | X8CrNiS18-9<br>X10CrNiS189<br>1.4305 | Y1Cr18Ni9<br>Y12Cr18Ni9 | 303S21 | Z10CNF18.09 | — |
| SUS303Se | 303Se<br>S30323 | — | Y12Cr18Ni9Se<br>Y1Cr18Ni9Se | 303S41 | — | 12Х18Н10Е |
| SUS304 | 304<br>S30400 | X5CrNi18-10<br>1.4301 | 0Cr18Ni9<br>06Cr19Ni10 | 304S31 | Z6CN18.09 | 08Х18Н10 |
| SUS304L | 304L<br>S30403 | X2CrNi19-11<br>1.4306 | 00Cr19Ni10<br>022Cr19Ni10 | 304S11 | Z2CN18.10 | 03Х18Н11 |
| SUS304N1 | 304N<br>S30451 | X5CrNiN19-9<br>1.4315 | 06Cr19Ni10N<br>06Cr19Ni10NbN | — | Z6CN19-09Az | — |
| SUS305 | 305<br>S30500 | X2CrNiN18-10<br>1.4311 | 1Cr18Ni12<br>10Cr18Ni12 | 305S19 | Z8CN18.12 | — |
| SUS309S | 309S<br>S30908 | X6CrNi23-13<br>1.4950 | 0Cr23Ni13<br>06Cr23Ni13 | — | — | 0Х23Н12 |
| SUS310S | 310S<br>S31008 | X6CrNi25-20<br>1.4951 | 0Cr25Ni20<br>06Cr25Ni20 | — | — | 08Х23Н20 |
| SUS316 | 316<br>S31600 | X5CrNiMo17-12-2<br>1.4401 | 0Cr17Ni12Mo2<br>06Cr17Ni12Mo2 | 316S31 | Z7CND17.12 | — |
| SUS316L | 316L<br>S31603 | X2CrNiMo17-12-2<br>1.4404 | 00Cr17Ni12Mo2<br>022Cr17Ni12Mo2 | 316S11 | Z2CND17.12 | 03Х17Н14М2 |
| SUS316N | 316N<br>S31651 | — | 0Cr17Ni12Mo2N<br>06Cr17Ni12Mo2N | — | — | — |
| SUS317 | 317<br>S31700 | — | 0Cr19Ni13Mo3<br>06Cr19Ni13Mo3 | 317S16 | — | — |
| SUS317L | 317L<br>S31703 | X2CrNiMo18-15-4<br>1.4438 | 00Cr19Ni13Mo3<br>022Cr19Ni13Mo3 | 317S12 | Z2CND19.15 | 03Х19Н13М3 |
| SUS321 | 321<br>S32100 | X6CrNiTi18-10<br>1.4541 | 0Cr18Ni10Ti<br>06Cr18Ni1Ti | 321S31 | Z6CNT18.10 | 08Х18Н10Т |
| SUS347 | 347<br>S34700 | X6CrNiNb18-10<br>1.4550 | 0Cr18Ni11Nb<br>06Cr18Ni11Nb | 347S31 | Z6CNNb18.10 | 08Х18Н12Б |

# References

## S Ferritic Heat Resistant Steels

| JIS | AISI/ASTM | DIN/EN | GB | BS | AFNOR | ГОСТ |
|---|---|---|---|---|---|---|
| SUH409 | 409<br>S40900 | X6CrTi12 | 06Cr11Ti<br>0Cr11T1 | 409S19 | Z6CT12 | — |
| SUH446 | 446<br>S44600 | — | 2Cr25N<br>16Cr25N | — | Z12C24 | — |

## S Martensitic Heat Resistant Steel

| | | | | | | |
|---|---|---|---|---|---|---|
| SUH1 | — | — | 45Cr9Si3 | 401S45 | Z45CS9 | — |
| SUH3 | — | — | 4Cr10Si2Mo<br>40Cr10Si2Mo | — | Z40CSD10 | 40X10C2M |
| SUH4 | — | — | 8Cr20Si2Ni<br>80Cr20Si2Ni | 443S65 | Z80CSN20.02 | — |
| SUH11 | — | — | 4Cr9Si2<br>42Cr9Si2 | — | — | 40X 9C2 |
| SUH600 | — | — | 2Cr12MoVNbN<br>18Cr12MoVNbN | — | — | — |
| SUH616 | 616<br>S42200 | — | 2Cr12NiMoWV<br>22Cr12NiWMoV | — | — | — |

## S Austenitic Heat Resistant Steel

| | | | | | | |
|---|---|---|---|---|---|---|
| SUH31 | — | — | 4Cr14Ni14W2Mo | 331S42 | — | 45X14H14B2M |
| SUH35 | — | X53CrMnNiN21-9-4<br>1.4871 | 5Cr21Mn9Ni4N<br>53Cr21Mn9Ni4N | 349S52 | Z52CMN21.09 | 55X20Г9AH4 |
| SUH36 | — | X53CrMnNi21 9 | — | 349S54 | Z55CMN21-09Az | 55X20Г9AH4 |
| SUH37 | — | X15CrNiSi20-12<br>1.4828 | 22Cr21Ni12N<br>2Cr21Ni12N | 381S34 | — | — |
| SUH38 | — | — | — | — | — | — |
| SUH309 | 309<br>S30900 | X12CrNi23-13<br>1.4833 | 16Cr23Ni13<br>2Cr23Ni13 | 309S24 | Z15CN24.13 | 20X23H12 |
| SUH310 | 310<br>S31000 | — | 2Cr25Ni21<br>20Cr25Ni20 | 310S24 | Z15CN25.20 | — |
| SUH330 | — | X12CrNiMnMoN25-18-6-5<br>1.4565 | 1Cr16Ni35<br>12Cr16Ni35 | — | Z12NCS35.16 | — |

## K Gray Cast Iron

| | | | | | | |
|---|---|---|---|---|---|---|
| FC100 | No 20B | GG-10 | HT100 | 100 | — | Cy10 |
| FC150 | No 25B | GG-15 | HT150 | 150 | FGL150 | Cy15 |
| FC200 | No 30B | GG-20 | HT200 | 200 | FGL200 | Cy20 |
| FC250 | No 35B | GG-25 | HT250 | 250 | FGL250 | Cy25 |
| FC300 | No 45B | GG-30 | HT300 | 300 | FGL300 | Cy30 |
| FC350 | No 50B | GG-35 | HT350 | 350 | FGL350 | Cy35 |

## K Nodular Cast Iron

| | | | | | | |
|---|---|---|---|---|---|---|
| FCD400 | 60-40-18 | GGG-40 | QT400-18 | 400/17 | FGS370-17 | By40 |
| FCD450 | — | GGG-40.3 | QT450-10 | 420/12 | FGS400-12 | By45 |
| FCD500 | 80-55-06 | GGG-50 | QT500-7 | 500/7 | FGS500-7 | By50 |
| FCD600 | — | GGG-60 | QT600-3 | 600/7 | FGS600-2 | By60 |
| FCD700 | 100-70-03 | GGG-70 | QT700-2 | 700/2 | FGS700-2 | By70 |
| FCD800 | 120-90-02 | GGG-80 | — | 800/2 | FGS800-2 | By80 |

## N Aluminum and Al Alloys - Sheets, plates and strips

| JIS | AISI/ASTM | DIN/EN | GB | BS | AFNOR | ГОСТ |
|---|---|---|---|---|---|---|
| A1060P | 1060 | EN AW-1060 | L2 | — | — | — |
| A1050P | 1050 | A199.50 | 1A50 | — | — | — |
| A1100P | 1100 | EN AW-1100 | L5-1 | — | — | — |
| A1200P | 1200 | EN AW-1200 | L5 | EN AW-1200 | EN AW-1200 | — |
| A2014P | 2014 | EN AW-2014 | LD10 | EN AW-2014 | EN AW-2014 | — |
| A2017P | 2017 | EN AW-2017 | 2A11(LY11) | EN AW-2017 | EN AW-2017 | — |
| A2219P | 2219 | EN AW-2219 | 2A16(LY16) | — | — | — |
| A2024P | 2024 | EN AW-2024 | 2A12(LY12) | EN AW-2024 | EN AW-2024 | — |
| A2124P | 2124 | EN AW-2124 | 2A12(LY12) | — | — | — |
| A3003P | 3003 | EN AW-3003 | LF21 | EN AW-3003 | EN AW-3003 | — |
| A3004P | 3004 | EN AW-3004 | 3004 | — | — | — |
| A3005P | 3005 | EN AW-3005 | 3005 | — | — | — |
| A3015P | 3105 | EN AW-3105 | 3105 | — | — | — |
| A5005P | 5005 | EN AW-5005 | 5005 | — | — | — |
| A5050P | 5050 | EN AW-5050 | — | — | — | — |
| A5052P | 5052 | EN AW-5052 | 5A02 | EN AW-5052 | EN AW-5052 | — |
| A5154P | 5154 | — | LF3 | — | — | — |
| A5254P | 5254 | — | LF3 | — | — | — |
| A5454P | 5454 | EN AW-5454 | 5454 | EN AW-5454 | EN AW-5454 | — |
| A5456P | 5456 | EN AW-5456 | — | | | |
| A6101P | 6101 | EN AW-6101 | 6101 | | | |
| A6061P | 6061 | EN AW-6061 | 6061(LD30) | EN AW-6061 | EN AW-6061 | — |
| A7075P | 7075 | EN AW-7075 | 7A04 | EN AW-7075 | EN AW-7075 | — |
| A7178P | 7178 | EN AW-7178 | 7A03(LC3) | — | — | — |

## N Aluminum Alloy Die Castings

| | | | | | | |
|---|---|---|---|---|---|---|
| ADC1 | A413.0 | EN AC-44300 | YL102 | — | — | — |
| ADC3 | A360.0 | EN AC-43400 | YL104 | EN AC-43400 | EN AC-43400 | — |
| ADC5 | 518.0 | — | Al-Mg7 | — | — | — |
| ADC10 | — | EN AC-46000 | YL112 | — | — | — |
| ADC12 | — | — | YL113 | LM20 | — | — |
| ADC14 | B390.0 | — | — | — | — | — |
| AC4C | 357 | G-AlSi7Mg | ZAlSi7Mg1A | LM25 | A-S7G-03 | — |
| AC4CH | 356 | G-AlSi7Mg | ZALSi7Mg | LM25 | A-S7G | — |
| — | 308 | G-AlSi6Cu4 | ZAlSi5Cu6Mg | LM21 | — | — |

## H Hardened Steel

| | | | | | | |
|---|---|---|---|---|---|---|
| C4BS | 440A | X100CrMo13 | 7Cr17 | — | — | — |
| AC4A | 610 | X110CrMoV15 | — | — | — | — |
| AC4A | 0-2 | X65CrMo14 | — | — | — | — |

# References

## Hardness Scale Comparision Chart




● Approx. metric value and Brinell hardness of steel

| Brinell Hardness 10mm Ball 3.000kgf (HB) | Rockwell Hardness | | | | Vickers Hardness 50kgf | Shore Hardness | Traverse Rupture Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|
| | „A“ Scale Diamond, brale 60kgf (HRA) | „B“ Scale 100kgf 1/10“ Ball (HRB) | „C“ Scale Diamond, brale 150kgf (HRC) | „D“ Scale Diamond, brale 100kgf (HRD) | (HV) | (HS) | |
| — | 85,6 | — | 68,0 | 76,9 | 940 | 97 | — |
| — | 85,3 | — | 67,5 | 76,5 | 920 | 96 | — |
| — | 85,0 | — | 67,0 | 76,1 | 900 | 95 | — |
| 767 | 84,7 | — | 66,4 | 75,7 | 880 | 93 | — |
| 757 | 84,4 | — | 65,9 | 75,3 | 860 | 92 | — |
| 745 | 84,1 | — | 65,3 | 74,8 | 840 | 91 | — |
| 733 | 83,8 | — | 64,7 | 74,3 | 820 | 90 | — |
| 722 | 83,4 | — | 64,0 | 73,8 | 800 | 88 | — |
| 712 | — | — | — | — | — | — | — |
| 710 | 83,0 | — | 63,3 | 73,3 | 780 | 87 | — |
| 698 | 82,6 | — | 62,5 | 72,6 | 760 | 86 | — |
| 684 | 82,2 | — | 61,8 | 72,1 | 740 | — | — |
| 682 | 82,2 | — | 61,7 | 72,0 | 737 | 84 | — |
| 670 | 81,8 | — | 61,0 | 71,5 | 720 | 83 | — |
| 656 | 81,3 | — | 60,1 | 70,8 | 700 | — | — |
| 653 | 81,2 | — | 60,0 | 70,7 | 697 | 81 | — |
| 647 | 81,1 | — | 59,7 | 70,5 | 690 | — | — |
| 638 | 80,8 | — | 59,2 | 70,1 | 680 | 80 | — |
| 630 | 80,6 | — | 58,8 | 69,8 | 670 | — | — |
| 627 | 80,5 | — | 58,7 | 69,8 | 667 | 79 | — |
| 601 | 79,8 | — | 57,3 | 68,7 | 640 | 77 | — |
| 578 | 79,1 | — | 56,0 | 67,7 | 615 | 75 | — |
| 555 | 78,4 | — | 54,7 | 66,7 | 591 | 73 | 2055 |
| 534 | 77,8 | — | 53,5 | 65,8 | 569 | 71 | 1985 |
| 514 | 76,9 | — | 52,1 | 64,7 | 547 | 70 | 1890 |
| 495 | 76,3 | — | 51,0 | 63,8 | 528 | 68 | 1820 |
| 477 | 75,6 | — | 49,6 | 62,7 | 508 | 66 | 1730 |
| 461 | 74,9 | — | 48,5 | 61,7 | 491 | 65 | 1670 |
| 444 | 74,2 | — | 47,1 | 60,8 | 472 | 63 | 1585 |
| 429 | 73,4 | — | 45,7 | 59,7 | 455 | 61 | 1510 |
| 415 | 72,8 | — | 44,5 | 58,8 | 440 | 59 | 1460 |
| 401 | 72,0 | — | 43,1 | 57,8 | 425 | 58 | 1390 |
| 388 | 71,4 | — | 41,8 | 56,8 | 410 | 56 | 1330 |
| 375 | 70,6 | — | 40,4 | 55,7 | 396 | 54 | 1270 |
| 363 | 70,0 | — | 39,1 | 54,6 | 383 | 52 | 1220 |
| 352 | 69,3 | (110,0) | 37,9 | 53,8 | 372 | 51 | 1180 |
| 341 | 68,7 | (109,0) | 36,6 | 52,8 | 360 | 50 | 1130 |
| 331 | 68,1 | (108,5) | 35,5 | 51,9 | 350 | 48 | 1095 |
| 321 | 67,5 | (108,0) | 34,3 | 50,1 | 339 | 47 | 1060 |
| 311 | 66,9 | (107,5) | 33,1 | 50,0 | 328 | 46 | 1025 |
| 302 | 66,3 | (107,0) | 32,1 | 49,3 | 319 | 45 | 1005 |
| 293 | 65,7 | (106,0) | 30,9 | 48,3 | 309 | 43 | 970 |
| 285 | 65,3 | (105,5) | 29,9 | 47,6 | 301 | — | 950 |
| 277 | 64,6 | (104,5) | 28,8 | 46,7 | 292 | 41 | 925 |
| 269 | 64,1 | (104,0) | 27,6 | 45,9 | 284 | 40 | 895 |
| 262 | 63,6 | (103,0) | 26,6 | 45,0 | 276 | 39 | 875 |
| 255 | 63,0 | (102,0) | 25,4 | 44,2 | 269 | 38 | 850 |
| 248 | 62,6 | (101,0) | 24,2 | 43,2 | 261 | 37 | 825 |
| 241 | 61,8 | 100,0 | 22,8 | 42,0 | 253 | 36 | 800 |
| 235 | 61,4 | 99,0 | 21,7 | 41,4 | 247 | 35 | 785 |
| 229 | 60,8 | 98,2 | 20,5 | 40,5 | 241 | 34 | 765 |
| 223 | — | 97,3 | (18,8) | — | 234 | — | — |
| 217 | — | 96,4 | (17,5) | — | 228 | 33 | 725 |
| 212 | — | 95,5 | (16,0) | — | 222 | — | 705 |
| 207 | — | 94,6 | (15,2) | — | 218 | 32 | 690 |
| 201 | — | 93,8 | (13,8) | — | 212 | 31 | 675 |
| 197 | — | 92,8 | (12,7) | — | 207 | 30 | 655 |
| 192 | — | 91,9 | (11,5) | — | 202 | 29 | 640 |
| 187 | — | 90,7 | (10,0) | — | 196 | — | 620 |
| 183 | — | 90,0 | (9,0) | — | 192 | 28 | 615 |
| 179 | — | 89,0 | (8,0) | — | 188 | 27 | 600 |
| 174 | — | 87,8 | (6,4) | — | 182 | — | 585 |
| 170 | — | 86,8 | (5,4) | — | 178 | 26 | 570 |
| 167 | — | 86,0 | (4,4) | — | 175 | — | 560 |
| 163 | — | 85,0 | (3,3) | — | 171 | 25 | 545 |
| 156 | — | 82,9 | (0,9) | — | 163 | — | 525 |
| 149 | — | 80,8 | — | — | 156 | 23 | 505 |
| 143 | — | 78,7 | — | — | 150 | 22 | 490 |
| 137 | — | 76,4 | — | — | 143 | 21 | 460 |
| 131 | — | 74,0 | — | — | 137 | — | 450 |
| 126 | — | 72,0 | — | — | 132 | 20 | 435 |
| 121 | — | 69,8 | — | — | 127 | 19 | 415 |
| 116 | — | 67,6 | — | — | 122 | 18 | 400 |
| 111 | — | 65,7 | — | — | 117 | 15 | 385 |

1) Figures within the ( ) are not commonly used
2) Rockwell A, C and D scales utilises a diamond brale
3) 1 $N/mm^2$ = 1 MPa

## ■ Finished Surface Roughness

### ● Types of Surface Roughness Measurements

| Types | Symbol | Method of Determination | Descriptive Figure |
|---|---|---|---|
| Maximum Height | ※1) Ry | This is the value (expressed in µm) measured from the deepest valley to the highest peak of the reference line, ℓ, extracted from the profile.<br><br>(Disregard unusually high peaks and deep valleys as they are considered as flaws.) |  |
| Ten-point Mean Roughness | ※2) Rz | From the profile, extract a portion to be the reference line, ℓ.<br><br>Select the 5 highest peak and 5 deepest valleys. Measure the distance between the two lines and express it in µm.<br>(1 µm = 0,001mm) |  |
| Calculated Roughness | Ra | This method is to obtain a center line between the peaks and valleys within the reference line, ℓ. Fold along the center line to superimpose the valleys against the peaks. (Shaded portions with dashed outline on the right figure). Take the total shaded area and divided it by ℓ in µm. |  |

Designated values of the above types of surface roughness, standard reference length values and the triangular symbol classifications are shown on the table on the right.

※1) Ry : According to new **JIS B 0601**:2001 (Old symbol: Rz)
※2) Rz : According to new **JIS B 0601**:2001 (Old symbol: $Rz_{JIS}$)

| Designated values for ※1) Ry | Designated values for ※2) Rz | Designated values for Ra | Standard reference length values, ℓ (mm) | Triangular Symbols |
|---|---|---|---|---|
| (0,05S)<br>0,1S<br>0,2S<br>0,4S | (0,05Z)<br>0,1Z<br>0,2Z<br>0,4Z | (0,013a)<br>0,025a<br>0,05a<br>0,10a | — | ▽▽▽▽ |
| 0,8S | 0,8Z | 0,20a | 0,25 | |
| 1,6S<br>3,2S<br>6,3S | 1,6Z<br>3,2Z<br>6,3Z | 0,4a<br>0,8a<br>1,6a | 0,8 | ▽▽▽ |
| 12,5S<br>(18S)<br>25S | 12,5Z<br>(18Z)<br>25Z | 3,2a<br>6,3a | 2,5 | ▽▽ |
| (35S)<br>50S<br>(70S)<br>100S | (35Z)<br>50Z<br>(70Z)<br>100Z | 12,5a<br>25a | — | ▽ |
| (140S)<br>200S<br>(280S)<br>400S<br>(560S) | (140Z)<br>200Z<br>(280Z)<br>400Z<br>(560Z) | (50a)<br>(100a) | — | — |

Remarks: The designated values in the brackets do not apply unless otherwise stated.

# Spare Parts

P

P1–P8





Screw ..... P2-P4
Lever Pin, Shim, Nut ..... P4-P6
Shim Pin, Eccentric Pin ..... P7
Wrench ..... P8

# Screw

## ■ Screw


### High Precision Screw





| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | α° | |
| **BFTG0408F** | ● | M4 | 0,5 | 7,5 | 5,7 | T15 | 61 | 3,4 |
| **BTTG0409F** | ● | M4 | 0,5 | 8,4 | 6,15 | T15 | 61 | 3,4 |
| **BFTG0513F** | ● | M5 | 0,5 | 13 | 6,8 | T20 | 61 | 5,0 |
| **BFTG0617F** | ● | M6 | 0,75 | 16,5 | 8 | T25 | 61 | 7,5 |
| **BFTG0621F** | ❍ | M6 | 0,75 | 21 | 9,5 | T25 | 61 | 7,5 |
| **BFTG0825F** | ● | M8 | 0,75 | 24,5 | 12 | T25 | 61 | 7,5 |

### Torx Flat Head Screw

| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | α° | |
| **BFTX016033** | ❍ | M1,6 | 0,35 | 3,3 | 2,6 | T6 | 60 | 0,2 |
| **BFTX02508** | ● | M2,5 | 0,45 | 7,5 | 3,45 | T8 | 60 | - |
| **BFTX0309** | | M3 | 0,5 | 8,8 | 4,2 | T10 | 60 | - |
| **BFTX03508** | ● | M3,5 | 0,6 | 8 | 5,1 | T10 | 52 | 2,0 |
| **BFTX03584** | ● | M3,5 | 0,6 | 7,4 | 5,2 | T15 | 60 | 3,0 |
| **BFTX03588** | ● | M3,5 | 0,6 | 8,8 | 5,2 | T15 | 60 | 3,4 |
| **BFTX0408** | ● | M4 | 0,7 | 8 | 5,5 | T15 | 60 | - |
| **BFTX0414** | ● | M4 | 0,7 | 14,5 | 5,5 | T15 | 60 | 3,0 |
| **BFTX0515** | | M5 | 0,8 | 15 | 7 | T20 | 60 | - |
| **BFTX0613** | | M6 | 1,0 | 13 | 9 | T25 | 60 | - |
| **BFTX0615** | | M6 | 1,0 | 15 | 9 | T25 | 60 | - |
| **BFTX0617** | | M6 | 1,0 | 17 | 9 | T25 | 60 | - |





| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | α° | |
| **BFTX0203A** | ● | M2 | 0,4 | 3 | 2,7 | T6 | 90 | 0,5 |
| **BFTX0204A** | ● | M2 | 0,4 | 4,3 | 2,7 | T6 | 90 | 0,5 |
| **BFTX0305A** | ● | M3 | 0,5 | 5,3 | 4,3 | T10 | 90 | - |
| **BFTX0306A** | ● | M3 | 0,5 | 5,8 | 4,3 | T10 | 90 | 2,0 |
| **BFTX0307A** | ● | M3 | 0,5 | 6,8 | 4,3 | T10 | 90 | 2,0 |
| **BFTX0407A** | ● | M4 | 0,7 | 7,3 | 5,6 | T15 | 90 | 3,4 |
| **BFTX0410A** | ● | M4 | 0,7 | 10,3 | 5,6 | T15 | 90 | 3,4 |
| **BFTX0509A** | ● | M5 | 0,8 | 9,3 | 6,9 | T20 | 90 | 5,0 |




| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | α° | |
| **BFTX01604N** | ● | M1,6 | 0,35 | 4,2 | 2,4 | T6 | 60 | 0,2 |
| **BFTX0203N** | ● | M2 | 0,4 | 3 | 2,7 | T6 | 60 | 0,5 |
| **BFTX0204N** | ● | M2 | 0,4 | 4,3 | 2,7 | T6 | 60 | 0,5 |
| **BFTX02205N** | ● | M2,5 | 0,45 | 4,5 | 3 | T6 | 60 | 0,5 |
| **BFTX2206NT** | ❍ | M2,2 | 0,45 | 6 | 3,2 | T1,8 | 60 | 0,7 |
| **BFTX02505N** | ● | M2,5 | 0,45 | 4,5 | 3,45 | T8 | 60 | 1,1 |
| **BFTX02506N** | ● | M2,5 | 0,45 | 5,5 | 3,45 | T8 | 60 | 1,5 |
| **BFTX02508NV** | ● | M2,5 | 0,45 | 7,5 | 3,5 | T8 | 60 | 1,5 |
| **BFTX0306N** | ❍ | M3 | 0,5 | 5,8 | 4,2 | T10 | 60 | 2,0 |
| **BFTX0307N** | ● | M3 | 0,5 | 6,5 | 4,2 | T10 | 60 | 2,0 |
| **BFTX03085N** | ❍ | M3 | 0,5 | 8,5 | 5,4 | T10 | 60 | - |
| **BFTX0309N** | ● | M3 | 0,5 | 9 | 4,2 | T10 | 60 | 3,0 |
| **BFTX0312N** | ❍ | M3 | 0,5 | 12 | 5,4 | T10 | 60 | - |
| **BFTX03509N** | ● | M3,5 | 0,6 | 8,5 | 4,9 | T10 | 60 | - |
| **BFTX0406N** | ● | M4 | 0,7 | 6 | 5,6 | T15 | 60 | - |
| **BFTX0407N** | ● | M4 | 0,7 | 7 | 5,6 | T15 | 60 | 3,0 |
| **BFTX0409N** | ● | M4 | 0,7 | 9 | 5,6 | T15 | 60 | 3,4 |
| **BFTX0412N** | ● | M4 | 0,7 | 12 | 5,5 | T15 | 60 | 3,0 |
| **BFTX0509N** | ● | M5 | 0,8 | 9 | 7 | T20 | 60 | 5,0 |
| **BFTX0511N** | ● | M5 | 0,8 | 11,5 | 7 | T20 | 60 | 5,0 |
| **BFTX0513N** | ● | M5 | 0,8 | 13 | 7 | T20 | 60 | 5,0 |
| **BFTX0515N** | ● | M5 | 0,8 | 15 | 7 | T20 | 60 | - |
| **BFTX0615N** | ● | M6 | 1,0 | 15 | 9 | T25 | 60 | 5,0 |
| **BFTX0619N** | ● | M6 | 1,0 | 19 | 9 | T25 | 60 | 5,0 |


### Torx Flat Head Screw




| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | α° | |
| **BFTX0410T8L** | ● | M4 | 0,7 | 9,6 | 5,6 | T8 | 60 | 1,1 |
| **BFTX0410T8R** | ● | | | | | | | |


## ■ Screw

### Torx Plus Flat Head Screw





| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | α° | |
| **BFTX01804IP** | ❍ | M1,8 | 0,35 | 3,7 | 2,45 | 6IP | 60 | 0,5 |
| **BFTX02505IP** | ● | M2,5 | 0,45 | 4,5 | 3,45 | 8IP | 60 | - |
| **BFTX02506IP** | ● | M2,5 | 0,45 | 5,5 | 3,45 | 8IP | 60 | - |
| **BFTX0305IP** | ● | M3 | 0,5 | 5,3 | 3,8 | 8IP | 60 | 2,0 |
| **BFTX0306IP** | ● | M3 | 0,5 | 6 | 3,8 | 8IP | 60 | 2,0 |
| **BFTX0307IP** | ● | M3 | 0,5 | 7 | 4,3 | 10IP | 55 | 2,0 |
| **BFTX0308IP** | ● | M3 | 0,5 | 8 | 3,8 | 8IP | 60 | - |
| **BFTX03510IP** | ● | M3,5 | | | | | | |
| **BFTX03512IP** | ● | M3,5 | 0,6 | 11,5 | 5,3 | 15IP | 60 | 3,0 |
| **BFTX03584IP** | ● | M3,5 | 0,6 | 7,4 | 5,1 | 15IP | 60 | - |
| **BFTX03510IP08** | ● | M3,5 | 0,6 | 10 | 5,3 | 8IP | 60 | - |
| **BFTX03510IP15** | ● | M3,5 | 0,6 | 10 | 5,3 | 15IP | 60 | - |
| **BFTX0407IP** | ● | M4 | 0,7 | 8,0 | 5,6 | 15IP | 60 | 3,0 |
| **BFTX0409IP** | ● | M4 | 0,7 | 9,0 | 5,6 | 15IP | 60 | 3,0 |
| **BFTX0412IP** | ● | M4 | 0,7 | 12 | 5,5 | 15IP | 60 | 3,0 |
| **BFTX0418IP** | ● | M4 | 0,7 | 18 | 5,5 | 15IP | 60 | - |
| **BFTX04513IP20** | ● | M4,5 | 0,75 | 13,1 | 6,8 | 20IP | 60 | - |
| **BFTX0511IP** | ● | M5 | 0,8 | 11,5 | 7 | 20IP | 60 | - |
| **BFTX0513IP** | ● | M5 | 0,8 | 13 | 7 | 20IP | 60 | - |
| **BFTX0615IP** | ● | M6 | 1,0 | 15 | 9 | 25IP | 60 | - |

### Torx Flat Head Screw




| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | α° | |
| **BFTX03510SD** | | M3,5 | 0,6 | 10 | 5,3 | T10 | 60 | 2,0 |
| **BFTX03517SD** | | M3,5 | 0,6 | 17 | 5,3 | T10 | 60 | 2,0 |
| **BFTX0517SD** | | M5 | 0,8 | 17 | 7,2 | T20 | 60 | 5,0 |
| **BFTX0618SD** | | M6 | 1,0 | 18 | | T25 | 60 | 7,5 |


### Torx Flat Head Screw




| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | α° | |
| **BFTY02205** | ● | M2,2 | 0,45 | 5,0 | 3,05 | T7 | 60 | - |
| **BFTY02206** | ● | M2,2 | 0,45 | 5,6 | 3,05 | T7 | 60 | 1,0 |

### Button Head Cap Screw

### Hexagonal Hole Type




### T Type with Torx Hole





(BH410T)

| Cat. No. | Stock | Dimensions (mm) | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | ℓ | D | B | |
| **BH0304** | | M3 | 0,5 | 4 | Full | 5,5 | 2 | - |
| **BH0306** | ● | M3 | 0,5 | 6 | Full | 5,5 | 2 | - |
| **BH0308 ( FBUP3-A0-9)** | ● | M3 | 0,5 | 8 | Full | 5,5 | 2 | 1,0 |
| **BH0310** | ● | M3 | 0,5 | 10 | Full | 5,5 | 2 | - |
| **BH0315** | ❍ | M3 | 0,5 | 10 | Full | 5,5 | 2 | - |
| **BH03504** | ● | M3,5 | 0,6 | 4 | Full | 7 | 2 | - |
| **BH0408** | ❍ | M4 | 0,7 | 8 | Full | 6 | 2,5 | - |
| **BH0415** | | M4 | 0,7 | 15 | Full | 7,5 | 2,5 | - |
| **BH0510** | | M5 | 0,8 | 10 | Full | 9,5 | 3 | - |
| **BH0516** | ● | M5 | 0,8 | 16 | 14,4 | 9,5 | 3 | - |
| **BH0616** | ● | M6 | 1,0 | 16 | 14 | 10,5 | 4 | - |
| **BH0620** | ● | M6 | 1,0 | 20 | Full | 10,5 | 4 | - |
| **BH0824R** | | M8 | 1,25 | 24 | 20 | 12 | 4 | - |
| **BH0824L** | | M8 | 1,25 | 24 | 20 | 12 | 4 | - |
| **BH0825** | | M8 | 1,25 | 25 | 22,5 | 14 | 5 | - |
| **BH0830R** | ❍ | M8 | 1,25 | 30 | 26 | 12 | 4 | - |
| **BH0830L** | ● | M8 | 1,25 | 30 | 26 | 12 | 4 | - |
| **BH0832** | | M8 | 1,25 | 32 | 29,5 | 14 | 5 | - |
| **BH1030R** | | M10 | 1,5 | 30 | 26 | 14 | 5 | - |
| **BH1030L** | ● | M10 | 1,5 | 30 | 26 | 14 | 5 | - |
| **BH1036R** | | M10 | 1,5 | 36 | 32 | 14 | 5 | - |
| **BH1036L** | | M10 | 1,5 | 36 | 32 | 14 | 5 | - |


## ■ Screw

### Phillip Head Cap Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| BHA0525 | ● | M5 | 0,8 | 25,5 | 9,5 | 8,5 | 3 | 4,0 |
| BHA0625 | ● | M6 | 1,0 | 30 | 11,3 | 10,5 | 4 | 4,5 |
| BHA0834 | | M8 | 1,25 | 34,2 | 12,7 | 12,0 | 5 | - |
| BHE0407 | | M4 | 0,7 | 9,5 | 2 | 5,7 | 2,5 | 1,8 |
| BHE0510 | | M5 | 0,8 | 13 | 3 | 7,7 | 3 | 2,7 |

### Button Head Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | D | B | α° | N·m |
|---|---|---|---|---|---|---|---|---|
| BHF0203L | | M2 | 0,4 | 4 | 3 | 1,5 | 90 | |
| BHF0203B | | M2 | 0,4 | 5,5 | 3,5 | 1,5 | 90 | |
| BHF0306R | ● | M3 | 0,5 | 6,3 | 4,2 | 2 | 90 | 1,0 |
| BHF0308R | ● | M3 | 0,5 | 8 | 4,2 | 2 | 90 | 1,0 |
| BHF0410 | ● | M4 | 0,7 | 11,5 | 6 | 3 | 90 | – |
| BHF0623 | ❍ | M6 | 1,0 | 23 | 12 | 4 | 90 | 7,0 |

### Set Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | D | B | α° | N·m |
|---|---|---|---|---|---|---|---|---|
| BT0306 | | M3 | 0,5 | 6 | - | 1,5 | - | - |
| BT0310 | | M3 | 0,5 | 10 | - | 1,5 | - | - |
| BT0404 | ● | M4 | 0,7 | 4 | - | 2 | - | - |
| BT0408 | ❍ | M4 | 0,7 | 8 | - | 2 | - | - |
| BT0412 | ❍ | M4 | 0,7 | 12 | - | 2 | - | - |
| BT0506 | ● | M5 | 0,8 | 6 | - | 2,5 | - | - |
| BT0510 | | M5 | 0,8 | 10 | - | 2,5 | - | - |
| BT0610 | ❍ | M6 | 1,0 | 10 | - | 3 | - | - |
| BT0612 | | M6 | 1,0 | 12 | - | 3 | - | - |
| BT0620 | | M6 | 1,0 | 20 | - | 3 | - | - |
| BT06035T | | M6 | 1,0 | 3,5 | - | T15 | - | - |

### Set Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| BTD0408 | | M4 | 0,7 | 8 | 2 | 2,8 | 2 | - |
| BTD0410 | | M4 | 0,7 | 10 | 2 | 2,8 | 2 | - |
| BTD0412 | | M4 | 0,7 | 12 | 2 | 2,8 | 2 | - |
| BTD0508 | | M5 | 0,8 | 8 | 3 | 3,5 | 2,5 | - |
| BTD05F09 | | M5 | 0,5 | 9 | 2 | 4 | T15 | - |
| BTD0510 | ❍ | M5 | 0,8 | 10 | 3 | 3,5 | 2,5 | 3,0 |
| BTD0518 | | M5 | 0,8 | 18 | 4 | 3,5 | 2,5 | - |
| BTD0609 | ❍ | M6 | 1,0 | 9 | 2 | 4 | 3 | - |
| BTD0615 | | M6 | 1,0 | 15 | 5 | 4 | 3 | - |
| BTD0618 | | M6 | 1,0 | 18 | 5 | 4 | 3 | - |
| BTD0620 | | M6 | 1,0 | 20 | 5 | 4 | 3 | - |
| BTD0812 | ❍ | M8 | 1,25 | 12 | 2 | 5 | 4 | - |
| BTD0818 | | M8 | 1,25 | 18 | 6 | 5 | 4 | - |
| BTD0820 | | M8 | 1,25 | 20 | 6 | 5 | 4 | - |
| BTD0825 | | M8 | 1,25 | 25 | 8,5 | 5 | 4 | - |
| BTD0615T | | M6 | 1,0 | 15 | 5 | 4,3 | T20 | - |

### Set Screw




| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | B | α° | N·m |
|---|---|---|---|---|---|---|---|---|
| BTT0407 | ● | M4 | 0,5 | 7 | 2,6 | 2 | 60 | - |
| BTT0411 | ● | M4 | 0,5 | 11 | 2,6 | 2 | 60 | - |
| BTT0511 | | M5 | 0,8 | 11 | 5 | 2 | 20 | - |
| BTT0615 | | M6 | 1,0 | 15 | 6 | 2,5 | 20 | |


### Special Hollow Screw




| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| BW0507F | ● | M5 | 0,5 | 7 | 1,2 | 6,3 | 3,5 | - |
| BW0609F | ● | M6 | 0,75 | 9 | 1,5 | 7,7 | 4 | - |
| BW0508F-SD | | M5 | 0,5 | 8 | 1,2 | 6,3 | 3,5 | |
| BW0810F-SD | | M8 | 0,75 | 10 | 1,8 | 10 | 5 | |
| BW0912F-SD | | M9 | 0,75 | 12 | | | | |


## ■ Screw

### Cap Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| BX0304 | ❍ | M3 | 0,5 | 4 | Full | 5,5 | 2,5 | - |
| BX0308 | ● | M3 | 0,5 | 8 | Full | 5,5 | 2,5 | - |
| BX0315 | ❍ | M3 | 0,5 | 15 | Full | 5,5 | 2,5 | - |
| BX0410 | | M4 | 0,7 | 10 | Full | 7 | 3 | - |
| BX0414 | ● | M4 | 0,7 | 14 | Full | 7 | 3 | - |
| BX0425 | ❍ | M4 | 0,7 | 25 | 20 | 7 | 3 | - |
| BX0508 | | M5 | 0,8 | 8 | Full | 8,5 | 4 | - |
| BX0510 | | M5 | 0,8 | 10 | Full | 8,5 | 4 | - |
| BX0512 | ● | M5 | 0,8 | 12 | Full | 8,5 | 4 | - |
| BX0515 | ● | M5 | 0,8 | 15 | Full | 8,5 | 4 | - |
| BX0520 | ● | M5 | 0,8 | 20 | Full | 8,5 | 4 | 5,0 |
| BX0520T | ● | M5 | 0,8 | 20 | 16 | 8,5 | T20 | - |
| BX0615 | ❍ | M6 | 1,0 | 15 | Full | 10 | 5 | - |
| BX0620 | ❍ | M6 | 1,0 | 20 | Full | 10 | 5 | - |
| BX0622 | ● | M6 | 1,0 | 22 | 18 | 10 | 5 | - |
| BX1045 | ❍ | M10 | | | | | | |
| BX1060 | ❍ | M10 | 1,5 | 60 | | 16 | 8 | |
| BX1070 | ❍ | M10 | | | | | | |
| BX1240 | ❍ | M12 | | | | | | |

### Cap Screw (Torx Plus)





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| BXD02208IP | ● | M2,2 | 0,45 | 7,5 | 5,7 | 3,5 | 8IP | - |
| BXD02509IP | ● | M2,5 | 0,45 | 9 | 7 | 4,1 | 10IP | - |
| BXD03011IP | ● | M3 | 0,5 | 10,5 | 8 | 4,9 | 15IP | - |
| BXD03512IP | ● | M3,5 | 0,6 | 11,5 | 8,8 | 5,5 | 15IP | - |
| BXD04014IP | ● | M4 | 0,7 | 12,5 | 9,5 | 6 | 20IP | - |
| BXD04515IP | ● | M4,5 | 0,75 | 14,3 | 10,8 | 6,8 | 25IP | - |

### Cap Screw (Torx Plus)





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | H | B | N·m |
|---|---|---|---|---|---|---|---|---|---|
| BXA0310IP | ❍ | M3 | 0,5 | 7,5 | Full | 5,3 | 2,4 | 10IP | 2,0 |
| | | | | | | | | | - |
| | | | | | | | | | - |

### Cap Screw with Oil Hole





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | H | B | N·m |
|---|---|---|---|---|---|---|---|---|---|
| BXH0825-D13 | | M8 | 1,25 | 25 | Full | 13 | 8 | 6 | - |
| BXH1030-D16 | | M10 | 1,5 | 30 | Full | 16 | 10 | 8 | - |
| BXH1235-D18 | | M12 | 1,75 | 35 | Full | 18 | 12 | 10 | - |

### Cap Screw with Oil Hole





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | H1 | H2 | B | N·m |
|---|---|---|---|---|---|---|---|---|---|---|
| BXH1235-D33 | | M12 | 1,75 | 35 | Full | 33 | 10 | 2 | 10 | - |
| BXH1635-D40 | | M16 | 2,0 | 35 | 30 | 40 | 10 | - | 14 | - |
| BXH2036-D50 | | M20 | 2,5 | 36 | 29 | 50 | 14 | 4 | 17 | - |

### Cap Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| EHBX0512 | ● | M5 | 0,8 | 12 | 10,5 | 8 | 4 | - |

### Flat Head Screw




| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | B | α° | N·m |
|---|---|---|---|---|---|---|---|---|
| FBUP2-A0-8 | ❍ | M3 | 0,5 | 10 | 5,5 | 2 | 82 | 1,0 |
| FBUP3-A0-9 | ● | | | | | | | |
| FBUP4-A0-8 | | M5 | 0,8 | 15 | 9,3 | 3 | 82 | 2,7 |

### Button Head Cap Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| FBUP3-A0-9 | ● | M3 | 0,5 | 8 | Full | 5,5 | 2 | 1,0 |


# Screw, Lever Pin

## ■ Screw


### Axial adjustment Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| **FMJ** | ● | M4 | 0,5 | 15 | 5 | 6 | 3 | - |




| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| **FMUJ** | ❍ | M4 | 0,7 | 17 | 10,5 | 6 | 1 | - |





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| **RFJ** | ❍ | M4 | 0,7 | 12 | 6 | 6 | 2 | - |





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| **SRFJ** | | M4 | 0,7 | 17 | 10,5 | 6 | 2 | - |

### Special Hollow Screw




| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| **KGBS1111** | ● | M5 | 0,5 | 8 | 1,2 | 6 | 3,5 | |
| **KGBS1221** | ● | M6 | 0,75 | 9 | 1,5 | 7,5 | 4,5 | |

### Torx Flat Head Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | D | B | α° | N·m |
|---|---|---|---|---|---|---|---|---|
| **KSS1111** | ● | 3,5 | 0,6 | 11 | 5,2 | T15 | 55 | 3,5 |
| **KSS1221** | ● | 4,5 | 0,75 | 12 | 6,6 | T15,3 | 55 | 4,5 |


### Screw for Lever Lock

(LCS2B)







| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| **LCS2B** | | M3 | 0,5 | 10 | 3,05 | 3,6 | 2 | - |
| **LCS3** | ● | M6 | 1,0 | 17 | 10 | 6 | 2,5 | - |
| **LCS3B-SD** | | M5 | 0,8 | 9,5 | 4,2 | 5 | 2 | - |
| **LCS3DB-SD** | | M5 | 0,8 | 12 | 6 | 5 | 2 | - |
| **LCS3S** | | M6 | 1,0 | 15 | 10 | 6 | 2,5 | - |
| **LCS3TB-SD** | | M6 | 1,0 | 16,7 | 9,6 | 6 | 2,5 | - |
| **LCS3TE** | ● | M6 | 1,0 | 15,5 | 8,5 | 6 | 2,5 | - |
| **LCS4** | ● | M8 | 1,0 | 21 | 10 | 8 | 3 | - |
| **LCS4B-SD** | | M6 | 1,0 | 13,4 | 9 | 6 | 2,5 | - |
| **LCS41BS-SD** | | M8 | 1,0 | 17 | 9,3 | 8 | 3 | - |
| **LCS42BS-SD** | ● | M8 | 1,0 | 20,7 | 9,8 | 8 | 3 | - |
| **LCS4CA** | ● | M8 | 1,0 | 17,5 | 10 | 8 | 3 | - |
| **LCS5** | ● | M8 | 1,0 | 25 | 12 | 8 | 3 | - |
| **LCS5B-SD** | | M8 | 1,0 | 20,5 | 12,3 | 8 | 3 | - |
| **LCS5DB-SD** | | M8 | 1,0 | 21,1 | 11,4 | 8 | 3 | - |
| **LCS6** | ❍ | M10 | 1,0 | 27,2 | 14,4 | 9,8 | 4 | - |
| **LCS6B-SD** | ● | M10 | 1,0 | 27,2 | 14,4 | 10 | 4 | - |
| **LCS10** | ● | M5 | 0,8 | 14,5 | 8,5 | 5 | 2 | - |
| **LCS12** | ● | M6 | 1,0 | 17 | 9,6 | 6 | 2,5 | - |
| **LCS16** | ● | M6 | 1,0 | 21 | 13,6 | 6 | 2,5 | - |
| **LCS20** | ● | M8 | 1,0 | 23,5 | 13,2 | 8 | 3 | - |
| **LCS25** | | M10 | 1,0 | 30 | 17,4 | 10 | 4 | - |
| **LCS32** | | M12 | 1,0 | 36 | 19,3 | 12 | 5 | - |




| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | - | D | - | N·m |
|---|---|---|---|---|---|---|---|---|
| **MIB1.6-2** | ● | M1,6 | 0,35 | 2,0 | - | 2,4 | - | 0,2 |
| **MIB1.6-2.5** | ● | M1,6 | 0,35 | 2,5 | - | 2,4 | - | 0,2 |
| **MIB1.6-3** | ● | M1,6 | 0,35 | 3,0 | - | 2,4 | - | 0,2 |


## ■ Double Screw

### Double Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| **WB4-8** | | M4 | 0,7 | 7,5 | 3 | 3,0 | 2 | - |
| **WB5-10** | ● | M5 | 0,8 | 10 | 4 | 3,8 | 2,5 | - |
| **WB5-12** | ❍ | M5 | 0,8 | 12 | 5 | 3,8 | 2,5 | - |
| **WB5-18** | ❍ | M5 | | | | | | |
| **WB6-13** | ❍ | M6 | 1,0 | 13 | 5 | 4,5 | 3 | - |
| **WB6-16** | ● | M6 | 1,0 | 16 | 6 | 4,5 | 3 | - |
| **WB6-20** | ❍ | M6 | 1,0 | 20 | 8,5 | 4,5 | 3 | - |
| **WB6-30** | ❍ | M6 | 1,0 | 30 | 12 | 4,5 | 3 | - |
| **WB8-20** | ● | M8 | 1,25 | 20 | 8,5 | 6,2 | 4 | - |
| **WB8-24** | ● | M8 | 1,25 | 24 | 8,5 | 6,2 | 4 | - |
| **WB8-30** | ● | M8 | 1,25 | 30 | 11,5 | 6,2 | 4 | - |
| **WB8F-30** | | M8 | 1,0 | 30 | 11,5 | 6,2 | 4 | - |

### Torx Double Screw





| Cat. No. | Stock | Dimensions (mm) d | Pitch | L | ℓ | D | B | N·m |
|---|---|---|---|---|---|---|---|---|
| **WB6-16T** | ● | M6 | 1,0 | 16 | 6 | 4,5 | T20 | - |
| **WB6-20T** | ❍ | M6 | 1,0 | 20 | 8,5 | 4,5 | T20 | - |
| **WB6-20TL** | ❍ | M6 | 1,0 | 20 | 8,5 | 4,5 | T20 | - |
| **WB7-15T** | ● | M7 | 1,0 | 15 | 5,5 | 5 | T25 | - |
| **WB7F-15T** | | M7 | 0,75 | 15 | 8,5 | 5,5 | T25 | - |
| **WB7F-20TL** | | M7 | 0,75 | 20 | 8,5 | 5,5 | T25 | - |
| **WB8-22T** | ● | M8 | 1,25 | 22 | 8,5 | 6,2 | T27 | - |
| **WB8-22TL** | ❍ | M8 | 1,25 | 22 | 8,5 | 6,2 | T27 | - |
| **WB8-30T** | ● | M8 | 1,25 | 30 | 11,5 | 6,2 | T27 | - |
| **WB8-30TL** | | M8 | 1,25 | 30 | 11,5 | 6,2 | T27 | - |
| **WB8R-16T** | ❍ | M8 | 1,25 | 14 | 5,5 | 6,2 | T27 | - |

## ■ Lever Pin





| Cat. No. | Stock | Dimensions (mm) A | H | L | C | | | |
|---|---|---|---|---|---|---|---|---|
| **LCL3** | | 3,7 | 12 | 10 | 3,6 | | | |
| **LCL3-SD** | ● | 3,7 | 12 | 10 | 3,55 | | | |
| **LCL3C-SD** | | 3,1 | 7,8 | 9,9 | 3,1 | | | |
| **LCL3D-SD** | ● | 3,7 | 11,5 | 12 | 3,55 | | | |
| **LCL3DB-SD** | | 3,1 | 9,4 | 11,5 | 3,1 | | | |
| **LCL3S** | ● | 3,7 | 10,6 | 10 | 3,6 | | | |
| **LCL3T-SD** | | 2,6 | 6,3 | 7,2 | 2,15 | | | |
| **LCL4** | | 4,7 | 14 | 14,55 | 4,7 | | | |
| **LCL4-SD** | ● | 4,65 | 13,2 | 13,35 | 4,7 | | | |
| **LCL4C-SD** | | 4,65 | 10 | 13,35 | 4,7 | | | |
| **LCL4D-SD** | ● | 4,65 | 14,8 | 16 | 4,7 | | | |
| **LCL4T-SD** | | 4,65 | 13,2 | 13,35 | 4,7 | | | |
| **LCL5** | | 6 | 17 | 17,1 | 6 | | | |
| **LCL5-SD** | | 6 | 17,3 | 16,65 | 6 | | | |
| **LCL5C-SD** | | 7,5 | 18,1 | 20,5 | 7,5 | | | |
| **LCL6-SD** | | 7,5 | 21 | 20,5 | 7,5 | | | |
| **LCL8** | | 8,6 | 25,4 | 25,4 | 8,6 | | | |





| Cat. No. | Stock | Dimensions (mm) A | H | L | C | | | |
|---|---|---|---|---|---|---|---|---|
| **LCL06** | ● | 2,5 | 6,28 | 7,0 | 2 | | | |
| **LCL09** | ● | 3,5 | 9,3 | 10,75 | 3 | | | |
| **LCL10** | ● | 3,4 | 11,8 | 10,8 | 3 | | | |
| **LCL12** | ● | 3,7 | 13,4 | 12,9 | 3,5 | | | |
| **LCL16** | ● | 4,6 | 17,6 | 18,4 | 4,4 | | | |
| **LCL20** | ❍ | 6 | 18,9 | 20,4 | 5,6 | | | |
| **LCL32** | | 8,5 | 26,8 | 29,8 | 8 | | | |


## ■ Shim





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| CCS09T3 | ● | 8,525 | 2,38 | 5,4 | 6,4 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| CNS1204 | ● | 12,57 | 4,76 | 4,4 | 6,0 | | |
| CNS1606 | ● | 15,75 | 4,76 | 5,5 | 7,5 | | |
| CNS1906 | ● | 18,70 | 6,35 | 5,5 | 7,5 | | |
| CNS2509 | ❍ | 25,27 | 6,35 | 6,6 | 9,5 | | |
| CNS1203B | ● | 12,57 | 3,18 | 3,4 | 4,5 | | |
| CNS1204B | ● | 12,57 | 4,76 | 4,4 | 6,0 | | |




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| DCS11T3 | ● | 8,5 | 2,38 | 5,3 | 6,4 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | θ° |
| DGCS13R | ● | 13,7 | 3,9 | 6,8 | 8,8 | | 5 |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| DNS1504 | ● | 12,57 | 6,35 | 4,4 | 6,0 | | |
| DNS1506 | ● | 12,57 | 4,76 | 4,4 | 6,0 | | |
| DNS1104B | ❍ | 9,45 | 4,73 | 3,4 | 4,5 | | |
| DNS1504B | ❍ | 12,57 | 6,35 | 4,4 | 6,0 | | |
| DNS1506B | ❍ | 12,57 | 4,76 | 4,4 | 6,0 | | |


| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| HE060011E | ● | | | | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | |
| LST317SD | ● | 9,5 | 2,7 | 5,2 | | | |
| LST42SD | | 12,65 | 3,18 | 6,9 | | | |




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | |
| LSS32SD | | 9,48 | 3,18 | 5 | | | |
| LSS42SD | ● | 12,65 | 3,18 | 6,9 | | | |
| LSS53SD | | 15,85 | 4,76 | 7,9 | | | |
| LSS63SD | | 19 | 4,76 | 10 | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | |
| LSC32SD | | | 3,18 | 5 | | | |
| LSC42SD | ● | 12,65 | 3,18 | 6,9 | | | |
| LSC53SD | | 15,85 | 4,76 | 7,9 | | | |
| LSC63SD | ● | 19 | 4,76 | 10 | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | |
| LSD32SD | ● | 8,5 | 3,18 | 5 | | | |
| LSD42SD | | 12,65 | 3,18 | 6,9 | | | |


## ■ Shim





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | |
| LSR817 | ❍ | 8,4 | 2,7 | 5,2 | | | |
| LSR10 | ● | 8,4 | 3,18 | 4,7 | | | |
| LSR12 | ● | 10 | 3,18 | 4,7 | | | |
| LSR16 | ● | 13,5 | 4,76 | 6,3 | | | |
| LSR20 | ● | 17,2 | 4,76 | 7,9 | | | |
| LSR25 | | 22 | 6,35 | 9,5 | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | $T_1$ | $T_2$ | $d_2$ | | |
| LSTE31-0 | ● | 9,5 | 2,7 | 2,7 | 5,2 | | |
| LSTE31-1 | ● | 9,5 | 2,67 | 2,91 | 5,2 | | |
| LSTE31-2 | ● | 9,5 | 2,64 | 3,11 | 5,2 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | θ° |
| SCND433 | ❍ | 12,65 | 4,76 | 3,4 | | | 80 |
| SCN0903 | | 9,5 | 3,18 | 3,4 | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| SCS1204 | | 11,5 | 3,18 | 6,4 | 7,9 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| SNS1204 | ● | 12,57 | 4,76 | 4,4 | 6,0 | | |
| SNS1506 | | 15,75 | 4,76 | 5,5 | 7,5 | | |
| SNS1906 | ● | 18,92 | 6,35 | 5,5 | 7,5 | | |
| SNS2507 | ❍ | 25,27 | 7,93 | 6,6 | 9,5 | | |
| SNS2509 | ● | 25,27 | 6,35 | 6,6 | 9,5 | | |




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | θ° |
| SVW322 | ❍ | 9,5 | 3,18 | 4,7 | 6,5 | | 35 |
| SFW433 | | 12,65 | 4,76 | 6,2 | 8,0 | | 50 |
| SDW323 | ● | 9,5 | 3,18 | 4,7 | 6,5 | | 55 |
| SDW423 | ● | 12,65 | 3,18 | 6,2 | 8,0 | | 55 |
| SDW433 | | | | | | | |
| SCW423 | ● | 12,65 | 3,18 | 6,2 | 8,0 | | 80 |
| SCW433 | | | | | | | |
| SCW635 | ❍ | 19 | 4,76 | 9 | 11,5 | | 80 |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | D | | | | | |
| SRND32 | ● | 9,5 | | | | | |
| SRND42 | ❍ | 12,7 | | | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | |
| SSND423 | | 12,5 | 3,18 | 3,4 | | | |
| SSND423Z | ❍ | | | | | | |
| SSND433 | ❍ | 12,5 | 4,76 | 3,4 | | | |

# Shim, Nut


## ■ Shim





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **SSW423** | | 12,65 | 3,18 | 6,2 | 8 | | |
| **SSW433** | ● | 12,65 | 4,76 | 6,2 | 8 | | |
| **SSW635** | | 19 | 4,76 | 9 | 11,5 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | θ° |
| **STPD322** | ● | 8,4 | 3,18 | 3,4 | | | 6 |
| **STPD422** | ❍ | 11,0 | 3,18 | 3,4 | | | 6 |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **STW323** | ● | 9,5 | 3,18 | 4,7 | 6,5 | | |
| **STW434** | ● | 12,65 | 4,76 | 6,2 | 8 | | |
| **STW333** | ❍ | | | | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **SWW433** | ● | 12,65 | 5,15 | 6,2 | 8 | | |
| **LSW317** | ● | | | | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | θ° |
| **TCS16T3** | | 8,8 | 2,38 | 5,3 | 6,3 | | 7 |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **TNS1604** | ● | 9,45 | 4,76 | 3,4 | 4,5 | | |
| **TNS1603B** | ❍ | 9,45 | 3,18 | 3,4 | 4,5 | | |
| **TNS1604B** | ❍ | 9,45 | 4,76 | 3,4 | 4,5 | | |




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **TRW5505** | ● | 10,5 | 4,76 | 3,4 | 4,5 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **VCS1604** | ● | 8,25 | 3,18 | 5,3 | 6,4 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **VNS1604** | ● | 9,45 | 4,76 | 3,4 | 4,5 | | |

## ■ Shim


| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **WFXS4R** | ● | 10,17 | 3,0 | 5,5 | 7,5 | | |




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | θ° |
| **WGCS13R** | ● | 10,7 | 3,0 | 5,5 | 7,5 | | 5 |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | $d_1$ | $d_2$ | | |
| **WNS0604** | ● | 9,52 | 3,18 | 3,5 | 4,5 | | |
| **WNS0804** | ● | 12,57 | 4,76 | 4,4 | 6,3 | | |
| **WNS0603B** | | 9,27 | 3,18 | 3,4 | 4,5 | | |
| **WNS0803B** | ❍ | 12,57 | 3,18 | 3,4 | 4,5 | | |
| **WNS0804B** | ❍ | 12,57 | 4,76 | 4,4 | 6,0 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | T | d | | | |
| **YE3** | ● | 9,5 | 3,2 | 4 | | | |
| **YI3** | ● | 9,5 | 3,2 | 4 | | | |

## ■ Seat





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | L | H | | | |
| **PWSS4R** | ▲ | 4,6 | 15 | 8 | | | |

## ■ Ring





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | A | B | T | d | | |
| **ER03** | | 7 | 2,6 | 0,6 | 3 | | |
| **ER04** | ● | 9 | 3,5 | 0,6 | 4 | | |
| **ER05** | ● | 11 | 4,3 | 0,6 | 5 | | |


## ■ Nut




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | L | | | | | |
| **BNBW-2** | ● | 3 | | | | | |
| **BNBW-4** | ❍ | 4 | | | | | |
| **BNBW-7** | ❍ | 7 | | | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | L | D | B | | |
| **CPM32N** | ● | M4 | 7,5 | 7 | 3 | | |
| **CPM43N** | ● | M5 | 8,5 | 7 | 3 | | |
| **CPM43S** | ❍ | M5 | 6 | 7 | 3 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | B | |
| **CPV33N** | ● | M4 | 0,5 | 6,0 | 6,0 | 2,5 | |

# Shim Pin, Eccentric Pin


## ■ Shim Pin





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | $d_1$ | B |
| **HE060011P** | ● | M6 | 0,75 | 14,5 | 7,8 | 5,0 | 2,5 |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | D | L | | | |
| **LP04** | ● | 0,4 | 1,1 | 4,7 | | | |
| **LP06** | ● | 0,4 | 1,1 | 6,0 | | | |
| **LP07** | ● | 0,4 | 1,1 | 7,7 | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | H | L | | | |
| **LSP3** | | 5 | 3,5 | 5,5 | | | |
| **LSP3SD** | ● | 5 | 3,5 | 5,5 | | | |
| **LSP4** | | 6,7 | 4 | 7 | | | |
| **LSP4SD** | | 6,7 | 4 | 7 | | | |
| **LSP5SD** | | 7,7 | 4,5 | 8,5 | | | |
| **LSP6SD** | | 9,85 | 5,9 | 11,1 | | | |
| **LSP8** | | 13,05 | 10 | 12 | | | |
| **LSP10** | ● | 5 | 3,3 | 6,5 | | | |
| **LSP16** | ● | 6,6 | 4,5 | 9 | | | |
| **LSP20** | ● | 8,2 | 5,5 | 9 | | | |
| **LSP25** | ❍ | 9,8 | 6,5 | 11 | | | |
| **LSP32** | | 13 | 10 | 12 | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | D | $D_1$ | $d_1$ |
| **MP317** | ● | M4 | 0,7 | 15,5 | 6 | 4 | 3,7 |
| **MP320** | ● | M4 | 0,7 | 19,5 | 6 | 4 | 3,7 |
| **MP416** | ● | M5 | 0,8 | 14 | 7,5 | 6 | 5 |
| **MP420** | ● | M5 | 0,8 | 20 | 7,5 | 6 | 5 |
| **MP432** | | M5 | 0,8 | 32 | 7,5 | 6 | 5 |
| **MP531** | | | | | | | |
| **MP534** | | | | | | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | | L | D | | θ° |
| **SPP308** | | 3,2 | | 8 | 4,8 | | 120 |




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | | | L | D | | |
| **SPP3** | ● | | | 14 | 3,2 | | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | $d_1$ | $d_2$ | L | D | $\ell_1$ | $\ell_2$ |
| **VP20** | ● | M3,5 | M4 | 12,0 | 5,0 | ≥4,5 | ≥4,5 |
| **VP25** | ● | M3,5 | M4 | 17,0 | 5,0 | ≥4,5 | ≥4,5 |
| **VP32** | ● | M3,5 | M4 | 24,0 | 5,0 | ≥4,5 | ≥4,5 |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | Pitch | L | ℓ | $D_1$ | $D_2$ |
| **VP32B** | ● | M3,5 | 0,6 | 8,0 | 1,4 | 5,0 | 6,5 |
| **VP40B** | ● | M3,5 | 0,6 | 11,5 | 1,4 | 5,0 | 6,5 |

## ■ Eccentric Pin





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | $D_1$ | $D_2$ | L | ℓ | B |
| **CPB34** | ● | 3,4 | 4,1 | 5,5 | 14 | 5 | 2,5 |
| **CPB35** | ❍ | 3,4 | 4,1 | 5,5 | 17 | 5 | 2,5 |
| **CPB42** | ● | 4,5 | 5,5 | 7 | 14 | 5 | 3 |
| **CPB43** | ● | 4,5 | 5,5 | 7 | 19 | 5 | 3 |
| **CPB43S** | ● | 4,5 | 5,5 | 7 | 16 | 5 | 3 |
| **CPB44T** | ❍ | 4,5 | 5,5 | 7 | 22 | 5 | 3 |
| **CPB45T** | ❍ | 4,5 | 5,5 | 7 | 27 | 5 | 3 |
| **CPB64** | ❍ | 6,8 | 8,2 | 10,5 | 24 | 6,6 | 4 |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | d | $D_1$ | $D_2$ | L | ℓ | B |
| **CPU304C** | ❍ | 3,3 | 5,5 | - | 10 | 3,5 | 3 |

## ■ Wrench


Hex Wrench (Torx Plus)




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | d | C | $b_1$ | $b_2$ | |
| **TRXW10IP** | | 10IP | 2,6 | 40 | 75 | 40 | |





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | d | | | | |
| **TRB10IP** | ● | 10IP | 4 | | | | |
| **TRB15IP** | ● | 15IP | 4 | | | | |
| **TRB20IP** | ● | 20IP | 4,55 | | | | |
| **TRB25IP** | ● | 25IP | 5 | | | | |




| Cat. No. | Stock | Dimensions (mm) | | |
|---|---|---|---|---|
| | | D | L | Remarks |
| **HPS1015** | ● | 32 | 99,4 | For 10IP, 15IP |
| **HPL2025** | | 35,5 | 110,3 | For 20IP, 25IP |

## ■ Wrench

### Socket Wrench




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | $d_1$ | $d_2$ | L | H | | |
| **ANT** | | 5 | 2 | 100 | 4,5 | | |


### Hex Wrench (Hexagonal)




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | L | ℓ | | | |
| **LH020** | ● | 2 | 50 | 16 | | | |
| **LH025** | ● | 2,5 | 56 | 18 | | | |
| **LH030** | ● | 3 | 63 | 20 | | | |
| **LH035** | ● | 3,5 | 68 | 22 | | | |
| **LH040** | ● | 4 | 70 | 25 | | | |
| **LH050** | ❍ | 5 | 80 | 28 | | | |
| **LH060** | | 6 | 90 | 32 | | | |

| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | | | | | | |
| **LH035K** | ● | | | | | | |
| **LH045K** | | | | | | | |


### Torx Wrench




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | d | L | ℓ | | |
| **LT15** | ❍ | T15 | | | | | |
| **LT20** | ❍ | T20 | 3,9 | 57,2 | 19,1 | | |
| **LT25** | ❍ | T25 | 4,4 | 60,3 | 20,2 | | |
| **LT27** | ● | T27 | 4,96 | 63,5 | 21,5 | | |
| **LT1510** | ❍ | T15 | 3,26 | 62 | 10 | | |

| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | | | | | | |
| **LT15K** | ● | | | | | | |


### Torx Plus Wrench




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | d | L | ℓ | | |
| **LT15IP** | ❍ | | | | | | |
| **LT20IP** | | T20 | 4,0 | 57 | 18,5 | | |
| **LT25IP** | | T25 | 4,5 | 60 | 19,5 | | |


| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | | | | | | |
| **SDBSM** | ● | | | | | | |

### Hex Wrench (Hexagonal)




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | $b_1$ | C | | | |
| **TH015** | | 1,5 | 35 | 30 | | | |
| **TH020** | ● | 2 | 35 | 39 | | | |
| **TH025** | ● | 2,5 | 35 | 39 | | | |


### Hex Wrench (Hexagonal)




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | $b_1$ | C | | | |
| **TH030** | ● | 3 | 48 | 28 | | | |
| **TH040** | ● | 4 | 48 | 37 | | | |
| **TH050** | ❍ | 5 | 48 | 45 | | | |


## ■ Wrench

### Hex Wrench (Hexagonal)





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | C | $b_1$ | | | |
| **HD040** | ❍ | 4 | 75 | 111 | | | |

### Torx Wrench





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | d | C | $B_1$ | | |
| **TRD07** | ● | T7 | 2,0 | 45 | 70 | | |
| **TRD08** | ● | T8 | 2,3 | 55 | 70 | | |
| **TRD15** | ❍ | T15 | 3,3 | 70 | 100 | | |
| **TRD20** | ● | T20 | 3,9 | 100 | 90 | | |
| **TRD25** | ● | T25 | 5,3 | 80 | 110 | | |

### Torx Plus Wrench





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | C | $b_1$ | | | |
| **TRDR06IP05** | ● | | | | | | |
| **TRDR08IP** | ● | 8IP | 60 | 104 | | | |
| **TRDR10IP** | ● | 10IP | 80 | 111 | | | |
| **TRDR15IP** | ● | 15IP | 80 | 111 | | | |
| **TRDR20IP** | ● | 20IP | 100 | 118 | | | |
| **TRDR25IP** | ● | 25IP | 100 | 118 | | | |

### Torx Wrench





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | C | $b_1$ | $b_2$ | | |
| **TRX06** | ● | T6 | 35,5 | 15 | 15 | | |
| **TRX08** | ● | T8 | 38,5 | 19 | 19 | | |
| **TRX10** | ● | T10 | 42,1 | 22 | 22 | | |
| **TRX15** | ● | T15 | 46 | 22 | 27 | | |
| **TRX20** | ● | T20 | 49 | 22 | 30 | | |

### Torx Plus Wrench





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | C | $b_1$ | $b_2$ | | |
| **TRX06IP** | ● | 6IP | 34 | 15 | 15 | | |

### Hex Wrench (Hexagonal)





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | C | $b_1$ | $b_2$ | | |
| **TSW040** | ● | 4 | 60 | 20 | 40 | | |

### Torx Wrench





| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | d | | | | |
| **TT25** | ● | T25 | 4,4 | | | | |
| **TT27** | ● | T27 | 5,0 | | | | |

### Torx Plus Wrench




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | d | C | $b_1$ | | |
| **TTR15IP** | ● | 15IP | 4,0 | 80 | 25,5 | | |

### Torx Wrench




| Cat. No. | Stock | Dimensions (mm) | | | | | |
|---|---|---|---|---|---|---|---|
| | | B | d | | | | |
| **TTX15W** | ● | T15 | 4,0 | | | | |
| **TTX20** | ● | T20 | 3,9 | | | | |

# Index

P

P9–P22

# Index

## A - B


| A | | |
|---|---|---|
| 16ER******CB | F64 | Threading inserts |
| 16IR******CB | F65 | Threading inserts |
| 1,8x45 | G83, G85, M56, M71, M73 | Spare parts |
| AECT******PEFRA | G72, G73, H61, H63 | Indexable insert |
| AFBSM** | M50, M51 | Spare parts |
| ANB****R | G79, G81, H85, H87, M63, M65, M67, M69 | SUMIDIA blades |
| ANB****R-G | G79, G81, H85, H87, M63, M65, M67, M69 | SUMIDIA blades |
| ANB****R-GB | G79, G81, H85, H87, M63, M65, M67, M69 | SUMIDIA blades |
| ANB****R-H | G79, G81, H85, H87, M63, M65, M67, M69 | SUMIDIA blades |
| ANB****R-L | G79, G81, H85, H87, M63, M65, M67, M69 | SUMIDIA blades |
| ANB****R-W | G79, G81, H85, H87, M63, M65, M67, M69 | SUMIDIA blades |
| ANB****R-WS | G79, G81, H85, H87, M63, M65, M67, M69 | SUMIDIA blades |
| ANB****R-GX | G79, G81, H85, H87, M63, M65, M67, M69 | SUMIDIA blades |
| ANT | P3 | Spare parts |
| ANXA*****R** | G74, G78, H82, M58, M62 | Cutter |
| ANXA*****RS** | G74, G78, H82, M58, M62 | Cutter |
| ANXS*****E** | G74, H82, H84, M58, M66 | Cutter |
| ANXS*****M** | G74, H82, H86, M58, M68 | Modular cutter |
| ANXS*****R** | G74, G80, H82, M58, M64 | Cutter |
| ANXS*****RS** | G74, G80, H82, M58, M64 | Cutter |
| AOET******PEER-F | G41, G51, G57, H27, H37, H39, H41, H45, H49, H53 | Indexable insert |
| AOET******PEER-P** | G41, H27, H37, H39, H41, H49, | Indexable insert |
| AOET******PEFR-S | G41, G51, G57, H27, H37 H39, H41, H45, H49, H53 | Indexable insert |
| AOET**T3**PEER-F | G41, G49, G55, H27, H31, H33, H35, H43, H47, H51 | Indexable insert |
| AOET**T3**PEER-P** | G41, H27, H31, H33, H35, H43, H47, | Indexable insert |
| AOET**T3**PEFR-S | G41, G49, G55, H27, H31, H33, H35, H43, H47, H51 | Indexable insert |
| AOMT******PEER-G | G41, G51, G57, H27, H37, H39, H41, H45, H49, H53 | Indexable insert |
| AOMT******PEER-H | G41, G51, G57, H27, H37, H39, H41, H45, H49, H53 | Indexable insert |
| AOMT******PEER-L | G41, G51, G57, H27, H37, H39, H41, H45, H49, H53 | Indexable insert |
| AOMT**T3**PEER-G | G41, G49, G55, H27, H31, H33, H35, H43, H47, H51 | Indexable insert |
| AOMT**T3**PEER-H | G41, G49, G55, H27, H31, H33, H35, H43, H47, H51 | Indexable insert |
| ASM**** | J36 | Solid endmill |
| ASM****DL | J30 | Solid endmill |
| ASM****DL-R** | J30 | Solid endmill |
| AXET******PEFR-S | G58, G59, H57, H58, H65, H66 | Indexable insert |
| AXMT******PDER-G | G58, H56 | Indexable insert |
| AXMT******PDER-H | G58, H56 | Indexable insert |
| AXMT******PDER-L | G58, H56 | Indexable insert |
| AXMT******PDFR-S | G58, H56 | Indexable insert |
| AXMT******PEER-E | G58, G59, H57, H58, H65, H66 | Indexable insert |
| AXMT******PEER-EH | G58, G59, H57, H58, H65, H66 | Indexable insert |
| AXMT******PEER-G | G58, G59, H57, H58, H65, H66 | Indexable insert |
| AXMT******PEER-H | G58, G59, H57, H58, H65, H66 | Indexable insert |
| AXMT******PEER-L | G58, G59, H58, H66 | Indexable insert |

| B | | |
|---|---|---|
| B***-SCLC R/L ****-** | E14 | Boring bar |
| B***-SDQC R/L ****-** | E17 | Boring bar |
| B***-SDUC R/L ****-** | E16 | Boring bar |
| B***-STUP R/L ****-** | E20 | Boring bar |
| BBT**M*-** | H5 | Integreted Arbor |
| BBT**M**-** | H5 | Integreted Arbor |
| BCS** | F56, F58 | Spare parts |
| BFTG****F | P2 | Spare parts |
| BFTX**** | P2 | Spare parts |
| BFTX***** | P2 | Spare parts |
| BFTX****A | P2 | Spare parts |
| BFTX****IP | P2 | Spare parts |
| BFTX****IPS | F43 | Spare parts |
| BFTX*****IP** | P2 | Spare parts |
| BFTX*****IPS | F43 | Spare parts |
| BFTX****N | P2 | Spare parts |
| BFTX*****N | P2 | Spare parts |
| BFTX*****NV | P2 | Spare parts |
| BFTX****SD | P2 | Spare parts |
| BFTX*****SD | P2 | Spare parts |
| BFTX****T8 R/L | F20, P2 | Spare parts |
| BFTY***** | P2 | Spare parts |
| BH**** | P2 | Spare parts |
| BH***** | P2 | Spare parts |
| BH**** R/L | P2 | Spare parts |
| BHA**** | P3 | Spare parts |
| BHF**** | P3 | Spare parts |
| BNB*** R/L | M53 | Boring bar |
| BNBB**R | M52 | Boring bar |
| BNBC | M53 | Spare parts |
| BNBP 2R***-*** * | J41, M75 | SUMIBORON endmill |
| BNBW-* | P6 | Spare parts |
| BNES**** | J40, M74 | SUMIBORON endmill |
| BNGC R/L | M56 | Spare parts |
| BNGG R/L ****-TT | M56 | Tool holder |
| BNGS R/L TT | M56 | Spare parts |
| BNTT**** R/L | M56 | SUMIBORON insert |
| BNZ***R | M53 | Boring bar |
| BSME R/L *****D*S6 | M50 | Boring bar |
| BT**** | P3 | Spare parts |
| BT****E | F26, F30 | Spare parts |
| BT*****T | P3 | Spare parts |
| BTD**** | P3 | Spare parts |
| BTR**** | D30 | Indexable insert |
| BTT**** | P3 | Spare parts |
| BW****F | P3 | Spare parts |
| BW****F-SD | P3 | Spare parts |
| BWS** | F56, F58 | Spare parts |
| BX**** | P3 | Spare parts |
| BX****T | P3 | Spare parts |
| BXA****IP | P3 | Spare parts |
| BXH****D** | P3 | Spare parts |
| BXBR*****R | E24 | Boring bar |
| BXBR*****R-NB | E24 | Boring bar |
| BXD*****IP | P3 | Spare parts |

| C | | |
|---|---|---|
| C***-SCLP R/L ** | E15 | Boring bar |
| C***-SSKP R/L ** | E18 | Boring bar |
| C***-STUB R/L ** | E20 | Boring bar |
| C***-STUP R/L ** | E20 | Boring bar |
| C***-SWUB R/L ** | E23 | Boring bar |
| CBC* | D25 | Spare parts |
| CBC**** | D25 | Spare parts |
| CBD4 R/L | D25 | Spare parts |
| CBS** | D25 | Spare parts |
| CCET******LFY/RFY | C63 | Indexable insert |
| CCET**T***LFY/RFY | C63 | Indexable insert |
| CCET**X***LFY/RFY | C63 | Indexable insert |
| CCET**X****LFY/RFY | C63 | Indexable insert |
| CCEW**X***LF-NU | M5 | SUMIBORON insert |
| CCEW**X***LT-NU | M5 | SUMIBORON insert |
| CCGT******LAY/RAY | C65 | Indexable insert |
| CCGT**X***LFY/RFY | C65 | Indexable insert |
| CCGT******LFX/RFX | C64 | Indexable insert |
| CCGT*******LFX/RFX | C64 | Indexable insert |
| CCGT**T***LFX/RFX | C64 | Indexable insert |
| CCGT**T****LFX/RFX | C64 | Indexable insert |
| CCGT**X***LFYS/RFYS | C64 | Indexable insert |
| CCGT**X****LFYS/RFYS | C64 | Indexable insert |
| CCGT******M NFC | C64 | Indexable insert |
| CCGT******M NSC | C65 | Indexable insert |
| CCGT******M NSI | C65 | Indexable insert |
| CCGT******NAG | C65 | Indexable insert |
| CCGT******NFV NC2 | M4 | SUMIBORON insert |
| CCGT******NFV NU2 | M6 | SUMIBORON insert |
| CCGT******NLV NC2 | M4 | SUMIBORON insert |
| CCGT******NLV NU2 | M6 | SUMIBORON insert |
| CCGT******NSC | C65 | Indexable insert |
| CCGW**T*** | M5 | SUMIBORON insert |
| CCGW******HS-NC2 | M4 | SUMIBORON insert |
| CCGW******HS-NU | M5 | SUMIBORON insert |
| CCGW******HS-NU2 | M6 | SUMIBORON insert |
| CCGW******LE-NC2 | M4 | SUMIBORON insert |
| CCGW******LS-NC2 | M4 | SUMIBORON insert |
| CCGW******LT-NU | M5 | SUMIBORON insert |
| CCGW******LT-NC2 | M4 | SUMIBORON insert |
| CCGW******NC-2 | M4 | SUMIBORON insert |
| CCGW******NC-W2 | M4 | SUMIBORON insert |
| CCGW******NC-WG2 | M4 | SUMIBORON insert |
| CCGW******NC-WH2 | M4 | SUMIBORON insert |
| CCGW******NS | M5 | SUMIBORON insert |
| CCGW******NU | M5 | SUMIBORON insert |
| CCGW******NU-2 | M6 | SUMIBORON insert |
| CCGW******NU-WG2 | M6 | SUMIBORON insert |
| CCGW******NU-WH2 | M6 | SUMIBORON insert |
| CCH*** | G67, H11, H12 | Spare parts |
| CCLN R/L ****-*** | D25 | Tool holder |
| CCM 6B L/R | F50 | Spare parts |
| CCM 8 LONG | D25, D26 | Spare parts |
| CCM 8 UL | D25, F50 | Spare parts |
| CCM 8 UR | F50 | Spare parts |
| CCMT****** | M8 | SUMIDIA insert |
| CCMT******L/R-DM NU | M8 | SUMIDIA insert |
| CCMT******NF | M8 | SUMIDIA insert |
| CCMT******NFB | C66 | Indexable insert |
| CCMT******NFP | C66 | Indexable insert |
| CCMT******NGD NF | M8 | SUMIDIA insert |
| CCMT******NGU | C67 | Indexable insert |
| CCMT******NLD NF | M8 | SUMIDIA insert |
| CCMT******NLB | C66 | Indexable insert |
| CCMT******NLU | C66 | Indexable insert |
| CCMT******NLU-W | C66 | Indexable insert |
| CCMT******NMU | C67 | Indexable insert |
| CCMT******NSC | C67 | Indexable insert |
| CCMT******NSK | C67 | Indexable insert |
| CCMT******NSU | C66 | Indexable insert |
| CCMT**T***NUS | C67 | Indexable insert |
| CCMW****** | C67 | Indexable insert |
| CCMW******NF | M8 | SUMIDIA insert |
| CCMW******RH | M8, M45 | SUMIDIA insert |
| CCMW**T*** | C67 | Indexable insert |
| CCS**T* | P5 | Spare parts |
| CGA R/L **** *** | M55 | SUMIBORON insert |
| CNGA****** | C26 | Indexable insert |
| CNGA******ES-NC4 | M9 | SUMIBORON insert |
| CNGA******HS-NC2 | M10 | SUMIBORON insert |
| CNGA******HS-NC4 | M10 | SUMIBORON insert |
| CNGA******HS-NU2 | M12 | SUMIBORON insert |
| CNGA******HT-NU2 | M11 | SUMIBORON insert |
| CNGA******LE-NU2 | M11 | SUMIBORON insert |
| CNGA******LE-NC2 | M9 | SUMIBORON insert |
| CNGA******LF-NU2 | M11 | SUMIBORON insert |
| CNGA******LS-NU2 | M11 | SUMIBORON insert |
| CNGA******LS-NC2 | M9 | SUMIBORON insert |
| CNGA******LS-NC4 | M9 | SUMIBORON insert |
| CNGA******LT-NU2 | M11 | SUMIBORON insert |
| CNGA******LT-NC2 | M9 | SUMIBORON insert |
| CNGA******NC-2 | M9 | SUMIBORON insert |
| CNGA******NC-4 | M9 | SUMIBORON insert |
| CNGA******NC-W4 | M9 | SUMIBORON insert |
| CNGA******NC-WG4 | M9 | SUMIBORON insert |
| CNGA******NC-WH4 | M9 | SUMIBORON insert |
| CNGA******NU | M12 | SUMIBORON insert |
| CNGA******NU-2 | M11 | SUMIBORON insert |
| CNGA******NS-2 | M11 | SUMIBORON insert |
| CNGA******NU-W2 | M11 | SUMIBORON insert |
| CNGA******NU-WG2 | M11 | SUMIBORON insert |
| CNGA******NU-WH2 | M11 | SUMIBORON insert |
| CNGA******US-NU2 | M12 | SUMIBORON insert |
| CNGG******LAX/RAX | C28 | Indexable insert |
| CNGG******NEF | C28 | Indexable insert |
| CNGG******NFV NC4 | M10 | SUMIBORON insert |
| CNGG******NLV NC4 | M10 | SUMIBORON insert |
| CNGG******NSV NC4 | M10 | SUMIBORON insert |
| CNGG******NGH | C28 | Indexable insert |
| CNGG******NSU | C28 | Indexable insert |
| CNGM******NLV NU2 | M12 | SUMIBORON insert |
| CNGN****** | M13 | SUMIBORON insert |
| CNGX****** | M13 | SUMIBORON insert |
| CNMA****** | C28 | Indexable insert |
| CNMA****** | M13 | SUMIBORON insert |
| CNMA******NS | M13 | SUMIBORON insert |
| CNMA******NU | M13 | SUMIBORON insert |
| CNMA******NU-W | M13 | SUMIBORON insert |
| CNMG******NEF | C20 | Indexable insert |
| CNMG******NEG | C22 | Indexable insert |
| CNMG******NEM | C23 | Indexable insert |
| CNMG******NEX | C22 | Indexable insert |
| CNMG******NFA | C20 | Indexable insert |

# Index

## C - D


| | | |
|---|---|---|
| CNMG******NFB | C20 | Indexable insert |
| CNMG******NFE | C20 | Indexable insert |
| CNMG******NFL | C20 | Indexable insert |
| CNMG******NGE | C22 | Indexable insert |
| CNMG******NGU | C21 | Indexable insert |
| CNMG******NGU-W | C21 | Indexable insert |
| CNMG******NGZ | C25 | Indexable insert |
| CNMG******NLU | C20 | Indexable insert |
| CNMG******NLU-W | C20 | Indexable insert |
| CNMG******NME | C23 | Indexable insert |
| CNMG******NMU | C23 | Indexable insert |
| CNMG******NMX | C24 | Indexable insert |
| CNMG******NSE | C21 | Indexable insert |
| CNMG******NSE-W | C21 | Indexable insert |
| CNMG******NSU | C21 | Indexable insert |
| CNMG******NSX | C21 | Indexable insert |
| CNMG******NUG | C22 | Indexable insert |
| CNMG******NUP | C23 | Indexable insert |
| CNMG******NUX | C24 | Indexable insert |
| CNMG******NUZ | C25 | Indexable insert |
| CNMM******NHF | C26 | Indexable insert |
| CNMM******NHG | C26 | Indexable insert |
| CNMM******NHP | C26 | Indexable insert |
| CNMM******NHU | C27 | Indexable insert |
| CNMM******NHW | C27 | Indexable insert |
| CNMM******NMH | C26 | Indexable insert |
| CNMM******NMP | C26 | Indexable insert |
| CNMX******NF | M13 | SUMIDIA insert |
| CNMX******L/R | C26 | Indexable insert |
| CNS**** | P5 | Spare parts |
| CNS****B | P5 | Spare parts |
| CPB** | P7 | Spare parts |
| CPB**S | P7 | Spare parts |
| CPB**T | P7 | Spare parts |
| CPGT******NSD | C66 | Indexable insert |
| CPGW******NC2 | M7 | SUMIBORON insert |
| CP-M*-**-* | F20 | Spare parts |
| CPM**N | P6 | Spare parts |
| CPM**S | P6 | Spare parts |
| CPMH******NUS | C69 | Indexable insert |
| CPMT******NFB | C68 | Indexable insert |
| CPMT******NGU | C69 | Indexable insert |
| CPMT******NLB | C68 | Indexable insert |
| CPMT******NLU | C68 | Indexable insert |
| CPMT******NLU-W | C68 | Indexable insert |
| CPMT******NMU | C69 | Indexable insert |
| CPMT******NSU | C69 | Indexable insert |
| CPMT******NUS | C69 | Indexable insert |
| CPMW******NF | M7 | SUMIDIA insert |
| CPU***C | P7 | Spare parts |
| CPV**N | P6 | Spare parts |
| CRDN N****-*** | D26 | Tool holder |
| CRSN R/L ****-*** | D26 | Tool holder |
| CSBN R/L ****-*** | D25 | Tool holder |
| CSKN R/L ****-*** | D25 | Tool holder |
| CTL******N/L/R | F54 | Indexable insert |
| CTR******N/L/R NB | F54 | Indexable insert |
| CTR******N/L/R | F54 | Indexable insert |

**D**

| | | |
|---|---|---|
| D***-DCLC R/L ****-** | E8 | Boring bar |
| D***-DDUN R/L ****-** | E9 | Boring bar |
| D***-DTFN R/L ****-** | E12 | Boring bar |
| D***-DWLN R/L ****-** | E13 | Boring bar |
| D***-SCLC R/L ****-** | E14 | Boring bar |
| D***-SDQC R/L ****-** | E17 | Boring bar |
| D***-SDUC R/L ****-** | E16 | Boring bar |
| D***-STUP R/L ****-** | E20 | Boring bar |
| D***-SVUB R/L ****-** | E21 | Boring bar |
| D***-SVZB R/L ****-** | E21 | Boring bar |
| DABB***C-R | M57 | SUMIDIA-Bohrstange |
| DABB***N-R | M57 | SUMIDIA-Bohrstange |
| DAL****H | M78 | SUMIDIA-Bohrer |
| DC R/L-* | D25 | Spare parts |
| DCGT******LAY/RAY | C72 | Indexable insert |
| DCGT******LFX/RFX | C70 | Indexable insert |
| DCGT*******LFX/RFX | C70 | Indexable insert |
| DCGT******LFY/RFY | C71 | Indexable insert |
| DCGT*******LFY/RFY | C71 | Indexable insert |
| DCGT******LFYS/RFYS | C70 | Indexable insert |
| DCGT*******LFYS/RFYS | C70 | Indexable insert |
| DCGT******LSD/RSD | C71 | Indexable insert |
| DCGT******M NFC | C70 | Indexable insert |
| DCGT******M NSC | C72 | Indexable insert |
| DCGT******M NSI | C72 | Indexable insert |
| DCGT******NAG | C71 | Indexable insert |
| DCGT******N-FV NC2 | M14 | SUMIBORON insert |
| DCGT******N-FV NU2 | M15 | SUMIBORON insert |
| DCGT******N-LV NC2 | M14 | SUMIBORON insert |
| DCGT******N-LV NU2 | M15 | SUMIBORON insert |
| DCGT******NSC | C72 | Indexable insert |
| DCGW****** | C72 | Indexable insert |
| DCGW******HS-NC2 | M14 | SUMIBORON insert |
| DCGW******HS-NU | M16 | SUMIBORON insert |
| DCGW******HS-NU2 | M15 | SUMIBORON insert |
| DCGW******LE-NC2 | M14 | SUMIBORON insert |
| DCGW******LE-NU2 | M15 | SUMIBORON insert |
| DCGW******LF-NU | M16 | SUMIBORON insert |
| DCGW******LF-NU2 | M15 | SUMIBORON insert |
| DCGW******LS-NC2 | M14 | SUMIBORON insert |
| DCGW******LT-NU | M16 | SUMIBORON insert |
| DCGW******LT-NC2 | M14 | SUMIBORON insert |
| DCGW******LU-NC2 | M15 | SUMIBORON insert |
| DCGW******NC-2 | M14 | SUMIBORON insert |
| DCGW******NC-WG2 | M14 | SUMIBORON insert |
| DCGW******NC-WH2 | M14 | SUMIBORON insert |
| DCGW******NS | M16 | SUMIBORON insert |
| DCGW******NU | M16 | SUMIBORON insert |
| DCGW******NU-2 | M15 | SUMIBORON insert |
| DCGW******NU-WG2 | M15 | SUMIBORON insert |
| DCGW******NU-WH2 | M15 | SUMIBORON insert |
| DCLN R/L ****-*** | D12 | Tool holder |
| DCMT****** | M17 | SUMIDIA insert |
| DCMT******L/R-DM NU | M17 | SUMIDIA insert |
| DCMT******NF | M17 | SUMIDIA insert |
| DCMT******NFB | C73 | Indexable insert |
| DCMT******NFP | C73 | Indexable insert |
| DCMT******NGD NF | M17 | SUMIDIA insert |
| DCMT******NGU | C73 | Indexable insert |
| DCMT******NLD NF | M17 | SUMIDIA insert |
| DCMT******NLB | C73 | Indexable insert |

| | | |
|---|---|---|
| DCMT******NLU | C73 | Indexable insert |
| DCMT******NMU | C73 | Indexable insert |
| DCMT******NSK | C73 | Indexable insert |
| DCMT******NSU | C73 | Indexable insert |
| DCMW****** | C73 | Indexable insert |
| DCMW******NF | M17 | SUMIDIA insert |
| DCMW******RH | M17, M45 | SUMIDIA insert |
| DCMX**T***NLUW | C73 | Indexable insert |
| DCS**T* | P5 | Spare parts |
| DDHN R/L ****-*** | D13 | Tool holder |
| DDJN R/L ****-*** | D13 | Tool holder |
| DDL***V | M78 | SUMIDIA drill |
| DDNN N ****-*** | D13 | Tool holder |
| DFC*****E | H16, H17 | Indexable endmill |
| DFC*****E** | H17 | Indexable endmill |
| DFCM*****E | H16, H17 | Indexable endmill |
| DFCM*****E** | H17 | Indexable endmill |
| DFC*****RS | G24, H16 | Cutter |
| DFCF*****RS | G24, H16 | Cutter |
| DFCM*****RS | G24, H16 | Cutter |
| DGC*****EW | H6 | Indexable endmill |
| DGC*****RS | G8 | Cutter |
| DGCF*****RS | G8 | Cutter |
| DGCM*****RS | G8 | Cutter |
| DGCS**R | P5 | Spare parts |
| DML***V | M79 | SUMIDIA drill |
| DMSW*****E | H8 | Indexable endmill |
| DMSW*****EL | H8 | Indexable endmill |
| DMSW*****M | H9 | Indexable endmill |
| DMSW*****R | G63, G66 | Cutter |
| DMSW*****RS | G63, G66 | Cutter |
| DNGA****** | C34 | Indexable insert |
| DNGA******ES-NC2 | M19 | SUMIBORON insert |
| DNGA******ES-NC4 | M19 | SUMIBORON insert |
| DNGA******HS-NC2 | M19 | SUMIBORON insert |
| DNGA******HS-NC4 | M19 | SUMIBORON insert |
| DNGA******HS-NU2 | M20 | SUMIBORON insert |
| DNGA******LE-NC2 | M18 | SUMIBORON insert |
| DNGA******LF-NU2 | M20 | SUMIBORON insert |
| DNGA******LS-NC2 | M19 | SUMIBORON insert |
| DNGA******LS-NC4 | M19 | SUMIBORON insert |
| DNGA******LT-NC2 | M18 | SUMIBORON insert |
| DNGA******LT-NU2 | M20 | SUMIBORON insert |
| DNGA******NC-2 | M18 | SUMIBORON insert |
| DNGA******NC-4 | M18 | SUMIBORON insert |
| DNGA******NC-WG4 | M18 | SUMIBORON insert |
| DNGA******NC-WH4 | M18 | SUMIBORON insert |
| DNGA******NU | M20 | SUMIBORON insert |
| DNGA******NU-2 | M20 | SUMIBORON insert |
| DNGA******NU-WG2 | M20 | SUMIBORON insert |
| DNGA******NU-WH2 | M20 | SUMIBORON insert |
| DNGG******LAX/RAX | C36 | Indexable insert |
| DNGG******LUM/RUM | C36 | Indexable insert |
| DNGG******NEF | C36 | Indexable insert |
| DNGG******NFV NC4 | M19 | SUMIBORON insert |
| DNGG******NLV NC4 | M19 | SUMIBORON insert |
| DNGG******NGH | C36 | Indexable insert |
| DNGG******NSU | C36 | Indexable insert |
| DNGG******N-SV NC4 | M19 | SUMIBORON insert |
| DNGM******N-LV NU2 | M20 | SUMIBORON insert |
| DNGA****** | M21 | SUMIBORON insert |
| DNGN****** | M21 | SUMIBORON insert |
| DNMA****** | C35 | Indexable insert |
| DNMA****** | M21 | SUMIBORON insert |
| DNMA******NF | M21 | SUMIDIA insert |
| DNMA******NS | M21 | SUMIBORON insert |
| DNMA******NU | M21 | SUMIBORON insert |
| DNMA******RH | M21, M45 | SUMIDIA insert |
| DNMG******LHM/RHM | C33 | Indexable insert |
| DNMG******LUM/RUM | C32 | Indexable insert |
| DNMG******NEF | C30 | Indexable insert |
| DNMG******NEG | C31 | Indexable insert |
| DNMG******NEM | C32 | Indexable insert |
| DNMG******NEX | C31 | Indexable insert |
| DNMG******NFA | C29 | Indexable insert |
| DNMG******NFB | C29 | Indexable insert |
| DNMG******NFE | C29 | Indexable insert |
| DNMG******NFL | C29 | Indexable insert |
| DNMG******NGE | C31 | Indexable insert |
| DNMG******NGU | C30 | Indexable insert |
| DNMG******NGZ | C33 | Indexable insert |
| DNMG******NLU | C29 | Indexable insert |
| DNMG******NME | C32 | Indexable insert |
| DNMG******NMU | C32 | Indexable insert |
| DNMG******NMX | C33 | Indexable insert |
| DNMG******NSE | C30 | Indexable insert |
| DNMG******NSU | C30 | Indexable insert |
| DNMG******NSX | C30 | Indexable insert |
| DNMG******NUG | C31 | Indexable insert |
| DNMG******NUP | C32 | Indexable insert |
| DNMG******NUX | C33 | Indexable insert |
| DNMG******NUZ | C33 | Indexable insert |
| DNMM******NHG | C34 | Indexable insert |
| DNMM******NHP | C34 | Indexable insert |
| DNMM******NMP | C34 | Indexable insert |
| DNMX******L/R | C35 | Indexable insert |
| DNMX******NSE-W | C35 | Indexable insert |
| DNS**** | P5 | Spare parts |
| DNS****B | P5 | Spare parts |
| DNX***** RS | G14 | Cutter |
| DNXF***** RS | G14 | Cutter |
| DNXK**R | G14 | Spare parts |
| DSBN R/L ****-*** | D14 | Tool holder |
| DSDN N ****-*** | D14 | Tool holder |
| DSLX* | D27 | Spare parts |
| DSP* | D25 | Spare parts |
| DTFN R/L ****-*** | D15 | Tool holder |
| DTGN R/L ****-*** | D15 | Tool holder |
| DTJN R/L ****-*** | D15 | Tool holder |
| DTR**C R/L ****-*** | D11 | Tool holder |
| DTR**Q R/L ****-*** | D11 | Tool holder |
| DVJN R/L ****-*** | D16 | Tool holder |
| DVQN R/L ****-*** | D16 | Tool holder |
| DVVN N ****-*** | D16 | Tool holder |
| DWLN R/L ****-*** | D17 | Tool holder |

# Index

## E - H

### E

| | | |
|---|---|---|
| ECXA***X**LE NU* | M51 | SUMIBORON insert |
| ECXA***X**LF NU* | M51 | SUMIBORON insert |
| E**D*SEXCR/L**-**P | M51 | Boring bar |
| EHBX**** | P3 | Spare parts |
| EHHM****ZX | J31 | Solid endmill |
| EPMS****U***R** | J23 | Solid endmill |
| ER** | P6 | Spare parts |
| E***SSHM N***** | F43 | Tool holder |

### F

| | | |
|---|---|---|
| FBUP*-A*-* | P3 | Spare parts |
| FMJ | P4 | Spare parts |
| FMU****R-S | G85, M73 | Cutter |
| FMUE | G85, M73 | Spare parts |
| FMUJ | P4 | Spare parts |
| FMUU | G85, M73 | Spare parts |

### G

| | | |
|---|---|---|
| GCG N**** GA | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F35, F37, F39, F47, F49 | |
| GCM N**** GF | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F35, F37, F39, F47, F49 | |
| GCM N***** GF | F19, F21, F23, F25, F29, F37 | Indexable insert |
| GCM N**** GG | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F35, F37, F39, F47, F49 | |
| GCM N**** GL | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F35, F37, F39, F47, F49 | |
| GCM N**** MG | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F35, F37, F39, F47, F49 | |
| GCM N**** ML | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F35, F37, F39, F47, F49 | |
| GCM N**** RG | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F35, F37, F39, F47 | |
| GCM N**** RN | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F33, F37, F39, F47, F49 | |
| GCM R/L**** CF** | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F47 | |
| GCM R/L**** CG** | F19, F21, F23, F25, F27, F29, F31, | Indexable insert |
| | F47 | |
| GNDCF R/L***-*** | F48 | Cassette |
| GNDCM R/L *** | F46 | Cassette |
| GNDM R/L ****JX*** | F18 | Tool holder |
| GNDM R/L ****JX**** | F18 | Tool holder |
| GNDM R/L ****JX***** | F18 | Tool holder |
| GNDM R/L ****JX***J | F20 | Tool holder |
| GNDM R/L ****JX****J | F20 | Tool holder |
| GNDM R/L ****JX*****J | F20 | Tool holder |
| GNDM R/L ****K*** | F24 | Tool holder |
| GNDM R/L ****K**** | F24 | Tool holder |
| GNDM R/L ****K***** | F24 | Tool holder |
| GNDM R/L ****M*** | F24 | Tool holder |
| GNDM R/L ****M**** | F24 | Tool holder |
| GNDM R/L ****M***** | F24 | Tool holder |
| GNDM R/L ****P*** | F24 | Tool holder |
| GNDM R/L****X***JE | F26, F30 | Tool holder |
| GNDMS R/L****K*** | F24 | Tool holder |
| GNDMS R/L****M*** | F24 | Tool holder |
| GNDL R/L ****JX*** | F18 | Tool holder |
| GNDL R/L ****JX**** | F18 | Tool holder |
| GNDL R/L ****JX***** | F18 | Tool holder |
| GNDL R/L ****K*** | F28 | Tool holder |
| GNDL R/L ****K**** | F28 | Tool holder |
| GNDL R/L ****K***** | F28 | Tool holder |
| GNDL R/L ****M*** | F28 | Tool holder |
| GNDL R/L ****M**** | F28 | Tool holder |
| GNDL R/L ****M***** | F28 | Tool holder |
| GNDL R/L ****P*** | F28 | Tool holder |
| GNDLS R/L ****K*** | F28 | Tool holder |
| GNDLS R/L ****M*** | F28 | Tool holder |
| GNDF R/L ****K***-*** | F34 | Tool holder |
| GNDF R/L ****M***-*** | F34 | Tool holder |
| GNDFS R/L ****M***-*** | F36 | Tool holder |
| GNDFS R/L ****P***-*** | F36 | Tool holder |
| GNDI R/L ****T*** | F38 | Tool holder |
| GNDIS R/L ****T**** | F40 | Tool holder |
| GNDN R/L ****K***-*** | F32 | Tool holder |
| GNDN R/L ****M***-*** | F32 | Tool holder |
| GNDS R/L ****K*** | F22 | Tool holder |
| GNDS R/L ****M*** | F22 | Tool holder |
| GSP* | M56 | Spare parts |
| GSP** | D27, M54 | Spare parts |
| GSH****SF | J28 | Solid endmill |
| GSRE****SF | J27 | Solid endmill |
| GSX*****C-***D | J7, J12, J15 | Solid endmill |
| GSX*****C-*D | J9, J10, J11, J13, J17, J18, J19 | Solid endmill |
| GSX*****S-*D | J8, J16 | Solid endmill |
| GSXB***** | J34 | Solid endmill |
| GSXSLT*****C-***D | J14 | Solid endmill |
| GSXVL****-***D | J20 | Solid endmill |
| GSXVL****S-R**-***D | J21 | Solid endmill |
| GSXVL****-R**-***D | J21 | Solid endmill |
| GSXVL****S-***D | J20 | Solid endmill |
| GWB R/L ****-*** | M54 | Tool holder |
| GWBCM R/L ** | M55 | Cassette |
| GWC R/L ****-** | F50 | Tool holder |
| GWCCM R/L ** | F51 | Cassette |
| GWCI R/L *** | F51 | Tool holder |
| GWCS R/L ****-** | F50 | Tool holder |
| GXM N**** S ML | F41 | Indexable insert |
| GXM N**** S GF | F41 | Indexable insert |
| GXM N****** S GF | F41 | Indexable insert |

### H

| | | |
|---|---|---|
| HBB*** | M52, M57 | Tool holder |
| HBB**** | M57 | Tool holder |
| HBSM**** | M50, M51 | Boring bar |
| HD*** | P8 | Spare parts |
| HE******E | P5 | Spare parts |
| HE******P | P7 | Spare parts |
| HE******W | E13 | Spare parts |
| HFJ | G79, G81, H85, H87, M63, | Spare parts |
| | M65, M67, M69 | |
| HFVT | G79, G81, H85, H87, M63, | Spare parts |
| | M65, M67, M69 | |
| HPL**** | P7 | Spare parts |
| HPS**** | P7 | Spare parts |

| J | | |
|---|---|---|
| J-G1/8-G1/8-** | F21 | Parts |
| J-G1/8-G1/8-**E | F21, F26, F30 | Parts |
| J-G1/8-G1/8F-**E | F21, F26, F30 | Parts |
| J-HOSE-G1/8-G1/8***-E | F21, F26, F30 | Parts |

| K | | |
|---|---|---|
| KGBS**** | P4 | Spare parts |
| KSS**** | P4 | Spare parts |

| L | | |
|---|---|---|
| LCL* | P4 | Spare parts |
| LCL** | P4 | Spare parts |
| LCL*C-SD | P4 | Spare parts |
| LCL*D-SD | P4 | Spare parts |
| LCL*DB-SD | P4 | Spare parts |
| LCL*S | P4 | Spare parts |
| LCL*-SD | P4 | Spare parts |
| LCL*T-SD | P4 | Spare parts |
| LCS* | P4 | Spare parts |
| LCS** | P4 | Spare parts |
| LCS**BS-SD | P4 | Spare parts |
| LCS*B-SD | P4 | Spare parts |
| LCS*CA | P4 | Spare parts |
| LCS*DB-SD | P4 | Spare parts |
| LCS*TB-SD | P4 | Spare parts |
| LCS*TE | P4 | Spare parts |
| LH*** | P8 | Spare parts |
| LH***K | P8 | Spare parts |
| LHHM****ZX | J31 | Solid endmill |
| LNEX******PNER-G | G33, G34, G35, H18, H19 | Indexable insert |
| LNEX******PNER-H | G33, G35, H18, H19 | Indexable insert |
| LNEX******PNER-L | G33, G34, G35, H18, H19 | Indexable insert |
| LP** | P7 | Spare parts |
| LSC**SD | P5 | Spare parts |
| LSD**SD | P5 | Spare parts |
| LSP*D | D34 | Spare parts |
| LSP* | P7 | Spare parts |
| LSP** | P7 | Spare parts |
| LSP*SD | P7 | Spare parts |
| LSR** | P5 | Spare parts |
| LSR*** | P5 | Spare parts |
| LSS**SD | P5 | Spare parts |
| LST**SD | P5 | Spare parts |
| LST***SD | P5 | Spare parts |
| LSTE**-* | P5 | Spare parts |
| LSW*** | P6 | Spare parts |
| LT** | P8 | Spare parts |
| LT**-** | P8 | Spare parts |
| LT**IP | P8 | Spare parts |
| LT**K | P8 | Spare parts |

| M | | |
|---|---|---|
| M* | H5 | Spare parts |
| M** | H5 | Spare parts |
| MA**M**L***C | H5 | Tool holder |
| MA**M**L***S | H5 | Tool holder |
| MDF****S2D | K26 | Multi-drill |
| MDF****L2D | K27 | Multi-drill |
| MDF****H3D | K29, K30 | Multi-drill |
| MDF****H5D | K29, K30 | Multi-drill |
| MDS*****SDC* | K41 | Multi-drill |
| MDSS**** | K40 | Multi-drill |
| MDUS****-**C | K40 | Multi-drill |
| MDW****GS* | K22, K23 | Multi-drill |
| MDW****NHGS | K36, K37 | Multi-drill |
| MDW****PHT | K34, K35 | Multi-drill |
| MDW***XHG-S**HAK | K34 | Multi-drill |
| MDW***XHT-A**HAK | K35 | Multi-drill |
| MIB*-* | P4 | Spare parts |
| MLDH****L** | K39 | Multi-drill |
| MLDH****P | K39 | Multi-drill |
| MMW** | D23 | Spare parts |
| MP*** | P7 | Spare parts |
| MSX*****EM | H11 | Indexable endmill |
| MSX*****ES | H11 | Indexable endmill |
| MSX*****EW | H11 | Indexable endmill |
| MSX*****M**Z* | H12 | Indexable endmill |
| MSX*****RS | G67 | Cutter |
| MTIX******E** | H69 | Indexable endmill |
| MTIX******E**** | H69 | Indexable endmill |
| MTIX****RS** | G61 | Cutter |
| MTJN R/L ****-** | D23 | Tool holder |
| MTJN R/L V-** | D23 | Tool holder |
| MTXN R/L ****-** | D23 | Tool holder |
| MWLN R/L ****-*** | D24 | Tool holder |
| MWW** | D24 | Spare parts |

| N | | |
|---|---|---|
| NPDB****-*** | J43, M77 | SUMIDIA endmill |
| NPDBS****-*** | J43, M77 | SUMIDIA endmill |
| NPDRS****R***-*** | J42, M76 | SUMIDIA endmill |

| O | | |
|---|---|---|
| ONEU****ANER L | G9, H6 | Indexable insert |
| ONEU****ANER G | G9, H6 | Indexable insert |
| ONMU****ANER L | G9, H6 | Indexable insert |
| ONMU****ANER G | G9, H6 | Indexable insert |

| P | | |
|---|---|---|
| P* | G85, M73 | Spare parts |
| PCBN R/L ****-*** | D18 | Tool holder |
| PCLC R/L ****-*** | D31 | Tool holder |
| PCLN R/L ****-*** | D18 | Tool holder |
| PCT***D*S** | K67 | Multi-drill |
| PDJC R/L ****-*** | D32 | Tool holder |
| PDJN R/L ****-*** | D19 | Tool holder |
| PDL***D*S** | K67 | Multi-drill |

# Index

## P - S


| P | | |
|---|---|---|
| PRDC N****-*** | D34 | Tool holder |
| PRGC R/L ****-*** | D34 | Tool holder |
| PSBN R/L ****-*** | D20 | Tool holder |
| PSC**DCLN R/L*****-12 | D41 | Polygon tool holder |
| PSC**DDJN R/L*****-15 | D41 | Polygon tool holder |
| PSC**DDHN R/L*****-15 | D41 | Polygon tool holder |
| PSC**DSBN R/L*****-12 | D41 | Polygon tool holder |
| PSC**DTJN R/L*****-16 | D42 | Polygon tool holder |
| PSC**DWLN R/L*****-0* | D42 | Polygon tool holder |
| PSC**GM** R/L***** | F46, F48, M55 | Polygon modular tool holder |
| PSC**SCLC R/L*****-09 | D43 | Polygon tool holder |
| PSC**SDJC R/L*****-11 | D43 | Polygon tool holder |
| PSC**SDHC R/L*****-11 | D43 | Polygon tool holder |
| PSC**SSBC R/L*****-12 | D43 | Polygon tool holder |
| PSC**STJC R/L*****-16 | D44 | Polygon tool holder |
| PSC**SVJB R/L*****-16 | D44 | Polygon tool holder |
| PSC**SVVB R/L*****-16 | D44 | Polygon tool holder |
| PSC**SVHB R/L*****-16 | D44 | Polygon tool holder |
| PSC**SVJC R/L*****-16 | D45 | Polygon tool holder |
| PSC**SVVC R/L*****-16 | D45 | Polygon tool holder |
| PSC**SVHC R/L*****-16 | D45 | Polygon tool holder |
| PSDN N ****-*** | D20 | Tool holder |
| PSKN R/L ****-*** | D21 | Tool holder |
| PSSN R/L ****-*** | D21 | Tool holder |
| PTFN R/L ****-*** | D22 | Tool holder |
| PTGN R/L ****-*** | D22 | Tool holder |
| PTTN R/L ****-*** | D22 | Tool holder |
| PW* | F63 | Spare parts |
| PWLN R/L ****-*** | D24 | Tool holder |
| PWSS*R | P6 | Spare parts |

| Q | | |
|---|---|---|
| QPET******PPFR-S | G16, H74, H75 | Indexable insert |
| QPMT******PPEN | G16, H74, H75 | Indexable insert |
| QPMT******PPEN-CP | G16 | Indexable insert |
| QPMT******PPEN-H | G16, H74, H75 | Indexable insert |

| R | | |
|---|---|---|
| RCMT****M0 NRH | C74 | Indexable insert |
| RCMT****M0 NRX | C74 | Indexable insert |
| RCMX****M0 NRP | C74 | Indexable insert |
| RDET**T*M0EN-G | G21, H76, H77 | Indexable insert |
| RDET**T*M0EN-H | G21, H76, H77 | Indexable insert |
| RDET****M0EN-G | G21, H76, H77 | Indexable insert |
| RDET****M0EN-H | G21, H76, H77 | Indexable insert |
| RF-SET | G82, G85, M70, M73 | Spare parts |
| RF****RS | G82, M70 | Cutter |
| RFB | G82, M70 | SUMIDIA insert |
| RFBW | G82, M70 | SUMIDIA insert |
| RFC | G82, M70 | Spare parts |
| RFD | G82, M70 | Spare parts |
| RFF | G82, M70 | Spare parts |
| RFJ | P4 | Spare parts |
| RFR | G82, M70 | Spare parts |
| RFS | G82, M70 | Spare parts |
| RNGN****** | M22 | SUMIBORON insert |
| RNGN******B | M22 | SUMIBORON insert |
| RSX*****ES | G18, H76 | Indexable endmill |
| RSXF*****ES | G18, H76 | Indexable endmill |
| RSX*****M | G18, H77 | Indexable endmill |
| RSXF*****M | G18, H77 | Indexable endmill |
| RSX*****RS | G18, G20 | Cutter |
| RSXF*****RS | G18, G20 | Cutter |

| S | | |
|---|---|---|
| S***-DTR**C-R/L-** | E11 | Boring bar |
| S***-MWLN R/L ** | E13 | Boring bar |
| S***-PCLN R/L ** | E8 | Boring bar |
| S***-PDUN R/L ** | E9 | Boring bar |
| S***-PSKN R/L ** | E10 | Boring bar |
| S***-PTFN R/L ** | E12 | Boring bar |
| S***-SCLC R/L ** | E14 | Boring bar |
| S***-SCLP R/L ** | E15 | Boring bar |
| S***-SDQC R/L ** | E17 | Boring bar |
| S***-SDUC R/L ** | E16 | Boring bar |
| S***-SSKP R/L ** | E18 | Boring bar |
| S***-STFC R/L ** | E19 | Boring bar |
| S***-STUB R/L **-** | E20 | Boring bar |
| S***-STUP R/L ** | E20 | Boring bar |
| S***-STUP R/L **-** | E20 | Boring bar |
| S***-SVQB R/L ** | E22 | Boring bar |
| S***-SVUB R/L ** | E22 | Boring bar |
| S***-SVZB R/L ** | E23 | Boring bar |
| S***-SWUB R/L ** | D11, E11 | Boring bar |
| SBN**-** | F56, F58 | Tool holder |
| SBU**-** | F56, F58 | Tool holder |
| SCAC R/L ****-*** | D31 | Tool holder |
| SCGT**T***LFX/RFX | C75 | Indexable insert |
| SCGT******M NSC | C75 | Indexable insert |
| SCGW******NU | M19 | SUMIBORON insert |
| SCLC R/L ****-*** | D31 | Tool holder |
| SCMT******NFB | C76 | Indexable insert |
| SCMT******NFP | C76 | Indexable insert |
| SCMT******NGU | C76 | Indexable insert |
| SCMT******NLB | C76 | Indexable insert |
| SCMT******NLU | C76 | Indexable insert |
| SCMT******NMU | C76 | Indexable insert |
| SCMT******NSK | C76 | Indexable insert |
| SCMT******NSU | C76 | Indexable insert |
| SCMW****** | C76 | Indexable insert |
| SCN**** | P5 | Spare parts |
| SCND*** | P5 | Spare parts |
| SCP-* | D12, D13, D14, D15, D16, D17, D41, D42, E8, E9, E12, E13 | Spare parts |
| SCP*A | F51, M55 | Spare parts |
| SCS**** | P5 | Spare parts |
| SCT R/L **** | F54 | Tool holder |
| SCW*** | P5 | Spare parts |
| SDAC R/L ****-*** | D33 | Tool holder |
| SDBSM | M51 | Spare parts |
| SDET****ZDFR | G82, M70 | Indexable insert |
| SDHC R/L ****-*** | D32 | Tool holder |
| SDJC R/L ****-*** | D32 | Tool holder |
| SDM****U*HAK | K17, K18, K19 | Multi-drill |
| SDNC N ****-*** | D33 | Tool holder |
| SDP****U*HAK | K8, K9, K10, K10, K11 | Multi-drill |
| SDW*** | P5 | Spare parts |

| | | |
|---|---|---|
| SEET****AGFR-L | G11, H7 | Indexable insert |
| SEET****AGSR-L | G11, H7 | Indexable insert |
| SEET****AGSR-G | G11, H7 | Indexable insert |
| SEMT****AGSR-L | G11, H7 | Indexable insert |
| SEMT****AGSR-G | G11, H7 | Indexable insert |
| SEMT****AGSR-H | G11, H7 | Indexable insert |
| SEMT****AGSR-FG | G11, H7 | Indexable insert |
| SFKN****AZFN | G13 | Indexable insert |
| SFKN****AZTN | G13 | Indexable insert |
| SFKR****AZTN | G13 | Indexable insert |
| SFW*** | P5 | Spare parts |
| SL-* | F56, F58, F59 | Spare parts |
| SMDH***S/M/L/D* | K44, K48, | Multi-drill |
| SMDT****MFS | K49 | Indexable insert |
| SMDT****MTL | K51 | Indexable insert |
| SMDT****D MEL | K46 | Indexable insert |
| SMDT****D MTL | K45 | Indexable insert |
| SNB****DL | J35 | Solid endmill |
| SNEU****ANER-FG | G9, H6 | Indexable insert |
| SNEU****ANER-FL | G9, H6 | Indexable insert |
| SNEU****ANER-G | G9, H6 | Indexable insert |
| SNEU****ANER-L | G9, H6 | Indexable insert |
| SNEW****ADFR-NF | G66, M70 | SUMIDIA insert |
| SNEW****ADFR-W-NF | G66, M70 | SUMIDIA insert |
| SNEW****ADTR-NF | G67, M71 | SUMIDIA insert |
| SNEW****ADTR-R-NF | G67, M71 | SUMIDIA insert |
| SNEW****ADTR-U-NF | G67, M71 | SUMIDIA insert |
| SNEW****ADT L/R | G69, M73 | SUMIBORON insert |
| SNEW****ADT L/R-S | G69, M73 | SUMIBORON insert |
| SNGA****** | C44 | Indexable insert |
| SNGA******HS-NC2 | M23 | SUMIBORON insert |
| SNGA******HS-NU2 | M23 | SUMIBORON insert |
| SNGA******LT-NU2 | M23 | |
| SNGA******NC2 | M23 | SUMIBORON insert |
| SNGA******NC4 | M23 | SUMIBORON insert |
| SNGA******NU2 | M23 | SUMIBORON insert |
| SNGA******NU4 | M23 | SUMIBORON insert |
| SNGG******LAX/RAX | C44 | Indexable insert |
| SNGG******LST/RST | C44 | Indexable insert |
| SNGG******LUM/RUM | C44 | Indexable insert |
| SNGN****** | C45 | Indexable insert |
| SNGN****** | M24 | SUMIBORON insert |
| SNGX****** | M24 | SUMIBORON insert |
| SNMA****** | C44 | Indexable insert |
| SNMA******NS | M24 | SUMIBORON insert |
| SNMA******NU | M24 | SUMIBORON insert |
| SNMA******NF | M24 | SUMIDIA insert |
| SNMA******RH | M24, M45 | SUMIDIA insert |
| SNMG******LUM/RUM | C39 | Indexable insert |
| SNMG******LHM/RHM | C41 | Indexable insert |
| SNMG******NEF | C38 | Indexable insert |
| SNMG******NEG | C39 | Indexable insert |
| SNMG******NEM | C40 | Indexable insert |
| SNMG******NEX | C39 | Indexable insert |
| SNMG******NFB | C37 | Indexable insert |
| SNMG******NFE | C37 | Indexable insert |
| SNMG******NFL | C37 | Indexable insert |
| SNMG******NGE | C38 | Indexable insert |
| SNMG******NGU | C38 | Indexable insert |
| SNMG******NGZ | C41 | Indexable insert |
| SNMG******NLU | C37 | Indexable insert |
| SNMG******NME | C40 | Indexable insert |
| SNMG******NMU | C40 | Indexable insert |
| SNMG******NMX | C41 | Indexable insert |
| SNMG******NSE | C37 | Indexable insert |
| SNMG******NSJ | C38 | Indexable insert |
| SNMG******NSU | C37 | Indexable insert |
| SNMG******NSX | C38 | Indexable insert |
| SNMG******NUG | C39 | Indexable insert |
| SNMG******NUP | C39 | Indexable insert |
| SNMG******NUX | C40 | Indexable insert |
| SNMG******NUZ | C41 | Indexable insert |
| SNMN****** | C45 | Indexable insert |
| SNMM******NHF | C43 | Indexable insert |
| SNMM******NHG | C42 | Indexable insert |
| SNMM******NHGS | C42 | Indexable insert |
| SNMM******NHP | C42 | Indexable insert |
| SNMM******NHU | C43 | Indexable insert |
| SNMM******NHW | C43 | Indexable insert |
| SNMM******NMH | C42 | Indexable insert |
| SNMM******NMP | C42 | Indexable insert |
| SNMT****ZNEN-G | G15 | Indexable insert |
| SNMT****ZNEN-H | G15 | Indexable insert |
| SNMT****ZNEN-L | G15 | Indexable insert |
| SNMT****ZNEN-SH | G15 | Indexable insert |
| SNMU****ANER FG | G9, H6 | Indexable insert |
| SNMU****ANER FL | G9, H6 | Indexable insert |
| SNMU****ANER G | G9, H6 | Indexable insert |
| SNMU****ANER H | G9, H6 | Indexable insert |
| SNMU****ANER L | G9, H6 | Indexable insert |
| SNS**** | P5 | Spare parts |
| SOET******PDFR-S | G26, G29, G71, H15, H19, H79, H80 | Indexable insert |
| SOET******PZER-G | G26, G28, G70, H15, H18, H79, H80 | Indexable insert |
| SOET******PZFR-S | G26, G28, G70, H15, H18, H79, H80 | Indexable insert |
| SOMT******PDER-L | G26, G29, G71, H15, H19, H79, H80 | Indexable insert |
| SOMT******PDER-G | G26, G29, G71, H15, H19, H79, H80 | Indexable insert |
| SOMT******PDER-H | G26, G29, G71, H15, H19, H79, H80 | Indexable insert |
| SOMT******PZER-L | G26, G28, G70, H15, H18, H79, H80 | Indexable insert |
| SOMT******PZER-G | G26, G28, G70, H15, H18, H79, H80 | Indexable insert |
| SOMT******PZER-H | G26, G28, G70, H15, H18, H79, H80 | Indexable insert |
| SPGN****** | C79 | Indexable insert |
| SPGT******LSD/RSD | C78 | Indexable insert |
| SPGW****** | C78 | Indexable insert |
| SPGW******T | C78 | Indexable insert |
| SPMH******NUS | C77 | Indexable insert |
| SPMN****** | C79 | Indexable insert |
| SPMR******NFK | C79 | Indexable insert |
| SPMR******NSF | C79 | Indexable insert |
| SPMR******NUJ | C79 | Indexable insert |
| SPMT****** | C39, H71 | Indexable insert |
| SPMT******NFB | C77 | Indexable insert |
| SPMT******NFK | C77 | Indexable insert |
| SPMT******NLB | C77 | Indexable insert |
| SPMT******NLU | C77 | Indexable insert |
| SPMT******NSF | C77 | Indexable insert |

## S - T


| | | |
|---|---|---|
| SPMT******NUS | C77 | Indexable insert |
| SPP* | P7 | Spare parts |
| SPP*** | P7 | Spare parts |
| SRDC N ****-*** | D35 | Tool holder |
| SRF**R-ST | G83, M71 | Cutter |
| SRF**RS | G83, M71 | Cutter |
| SRFJ | P4 | Spare parts |
| SRND** | P5 | Spare parts |
| SRNS***SD | D35 | Spare parts |
| SRSC R/L ****-*** | D35 | Tool holder |
| SSBC R/L ****-*** | D36 | Tool holder |
| SSEH****-R** | J37 | Solid endmill |
| SSEH****W-R** | J26 | Solid endmill |
| SSEH****WS-R** | J26 | Solid endmill |
| SSEHVL****-R** | J37 | Solid endmill |
| SSEHVL****W-R** | J25 | Solid endmill |
| SSEHVL****WS-R** | J25 | Solid endmill |
| SSHC R/L******** | F43 | Indexable insert |
| SSHG R/L******* | F43, F44 | Indexable insert |
| SSHR R/L***** | F43, F44 | Indexable insert |
| SSM**** | J38, J39 | Solid endmill |
| SSND*** | P5 | Spare parts |
| SSTE R******** | F63 | Tool holder |
| SSTI R******** | F63 | Tool holder |
| SSUP****ZX | J33 | Solid endmill |
| SSUP****ZX-R** | J33 | Solid endmill |
| SSW*** | P6 | Spare parts |
| STAC R/L ****-*** | D37 | Tool holder |
| STFH**-* | F56 | Tool holder |
| STFS R/L ****-* | F56 | Tool holder |
| STGC R/L ****-*** | D37 | Tool holder |
| STPD*** | P6 | Spare parts |
| STW*** | P6 | Spare parts |
| SUF*S R/L | G12 | Spare parts |
| SVJB R/L ****-*** | D38 | Tool holder |
| SVLC R/L ****-*** | D39 | Tool holder |
| SVP** | D38, E21, E22 | Spare parts |
| SVPB R/L ****-*** | D38 | Tool holder |
| SVPC R/L ****-*** | D39 | Tool holder |
| SVVB N ****-*** | D38 | Tool holder |
| SVW*** | P5 | Spare parts |
| SWW | P6 | Spare parts |


### T


| | | |
|---|---|---|
| TBGN****** | C88 | Indexable insert |
| TBGN******B | M25 | SUMIBORON insert |
| TBGN******NF | M25 | SUMIDIA insert |
| TBGR******LW | C88 | Indexable insert |
| TBGT******LAY/RAY | C80 | Indexable insert |
| TBGT******LFW/RFW | C80 | Indexable insert |
| TBGT******LFX/RFX | C80 | Indexable insert |
| TBGT******LFY/RFY | C80 | Indexable insert |
| TBGT******LW/RW | C80 | Indexable insert |
| TBGW****** | C80 | Indexable insert |
| TBGW******NF | M25 | SUMIDIA insert |
| TCGT******LFX/RFX | C81 | Indexable insert |
| TCGT******LFY/RFY | C81 | Indexable insert |
| TCGT******M NSC | C81 | Indexable insert |
| TCGT******M NSI | C81 | Indexable insert |
| TCGT******NAG | C81 | Indexable insert |
| TCGW******NC | M26 | SUMIBORON insert |
| TCGW******NC-3 | M26 | SUMIBORON insert |
| TCGW******NU | M26 | SUMIBORON insert |
| TCMT******NF | M26 | SUMIDIA insert |
| TCMT******NFB | C82 | Indexable insert |
| TCMT******NFP | C82 | Indexable insert |
| TCMT******NLB | C82 | Indexable insert |
| TCMT******NLU | C82 | Indexable insert |
| TCMT******NSK | C82 | Indexable insert |
| TCMT******NSU | C82 | Indexable insert |
| TCMW****** | C82 | Indexable insert |
| TCS**T* | P6 | Spare parts |
| TEGN****** | C89 | Indexable insert |
| TGA R/L ****BF | F51 | Indexable insert |
| TGA R/L ****(E) | F52 | Indexable insert |
| TGA R/L ****R | F53 | Indexable insert |
| TGA R/L *T** | F53 | Indexable insert |
| TF** | M42 | Spare parts |
| TH*** | P8 | Spare parts |
| TNGA****** | C54 | Indexable insert |
| TNGA******ES-NC6 | M27 | SUMIBORON insert |
| TNGA******HS-NC3 | M27 | SUMIBORON insert |
| TNGA******HS-NC6 | M27 | SUMIBORON insert |
| TNGA******HS-NU3 | M29 | SUMIBORON insert |
| TNGA******HT-NU3 | M29 | SUMIBORON insert |
| TNGA******LE-NC3 | M27 | SUMIBORON insert |
| TNGA******LE-NU3 | M29 | SUMIBORON insert |
| TNGA******LS-NC3 | M27 | SUMIBORON insert |
| TNGA******LS-NU3 | M29 | SUMIBORON insert |
| TNGA******LT-NC3 | M27 | SUMIBORON insert |
| TNGA******LF-NU3 | M29 | SUMIBORON insert |
| TNGA******NC3 | M27 | SUMIBORON insert |
| TNGA******NC6 | M27 | SUMIBORON insert |
| TNGA******NU3 | M29 | SUMIBORON insert |
| TNGA******T NU3 | M29 | SUMIBORON insert |
| TNGA******US-NU3 | M29 | SUMIBORON insert |
| TNGG******LAX/RAX | C54 | Indexable insert |
| TNGG******LFT/RFT | C53 | Indexable insert |
| TNGG******LFY/RFY | C53 | Indexable insert |
| TNGG******LFX/RFX | C53 | Indexable insert |
| TNGG******LST/RST | C53 | Indexable insert |
| TNGG******LUM/RUM | C54 | Indexable insert |
| TNGG******N-FV NC6 | M28 | SUMIBORON insert |
| TNGG******N-LV NC6 | M28 | SUMIBORON insert |
| TNGG******NGH | C54 | Indexable insert |
| TNGG******NSU | C53 | Indexable insert |
| TNGG******N-SV NC6 | M28 | SUMIBORON insert |
| TNGM******N-LV NU3 | M29 | SUMIBORON insert |
| TNGN****** | M29 | SUMIBORON insert |
| TNMA****** | C52 | Indexable insert |
| TNMA****** | M30 | SUMIBORON insert |
| TNMA******NU | M30 | SUMIBORON insert |
| TNMA******NS | M30 | SUMIBORON insert |
| TNMG******LHM/RHM | C50 | Indexable insert |
| TNMG******LUM/RUM | C48 | Indexable insert |
| TNMG******NEF | C46 | Indexable insert |
| TNMG******NEG | C48 | Indexable insert |
| TNMG******NEM | C49 | Indexable insert |
| TNMG******NEX | C48 | Indexable insert |
| TNMG******NFA | C46 | Indexable insert |
| TNMG******NFB | C46 | Indexable insert |
| TNMG******NFE | C46 | Indexable insert |

| | | |
|---|---|---|
| TNMG******NFL | C46 | Indexable insert |
| TNMG******NGE | C47 | Indexable insert |
| TNMG******NGU | C47 | Indexable insert |
| TNMG******NGZ | C50 | Indexable insert |
| TNMG******NLU | C46 | Indexable insert |
| TNMG******NME | C49 | Indexable insert |
| TNMG******NMU | C49 | Indexable insert |
| TNMG******NMX | C49 | Indexable insert |
| TNMG******NSE | C47 | Indexable insert |
| TNMG******NSU | C46 | Indexable insert |
| TNMG******NSX | C47 | Indexable insert |
| TNMG******NUG | C48 | Indexable insert |
| TNMG******NUP | C48 | Indexable insert |
| TNMG******NUX | C49 | Indexable insert |
| TNMG******NUZ | C50 | Indexable insert |
| TNMM******NHG | C51 | Indexable insert |
| TNMM******NHP | C51 | Indexable insert |
| TNMM******NMP | C51 | Indexable insert |
| TNMM****** | C51 | Indexable insert |
| TNMX******NF | M30 | SUMIDIA insert |
| TNS**** | P6 | Spare parts |
| TNS****B | P6 | Spare parts |
| TPGN****** | C88 | Indexable insert |
| TPGN****** | M31 | SUMIBORON insert |
| TPGN******HS | M31 | SUMIBORON insert |
| TPGN******LT | M31 | SUMIBORON insert |
| TPGN******NF | M31 | SUMIDIA insert |
| TPGN******T NF | M31 | SUMIBORON insert |
| TPGN******NU | M31 | SUMIBORON insert |
| TPGR******LW/RW | C88 | Indexable insert |
| TPGT******LAY/RAY | C84 | Indexable insert |
| TPGT******LFW/RFW | C83 | Indexable insert |
| TPGT******LFX/RFX | C83 | Indexable insert |
| TPGT******LFY/RFY | C84 | Indexable insert |
| TPGT******LSD/RSD | C85 | Indexable insert |
| TPGT******LW/RW | C85 | Indexable insert |
| TPGT******M NFC | C83 | Indexable insert |
| TPGT******N-FV NC3 | M32 | SUMIBORON insert |
| TPGT******N-FV NU3 | M33 | SUMIBORON insert |
| TPGW****** | C84 | Indexable insert |
| TPGW****** | M32 | SUMIBORON insert |
| TPGW******HS-NC3 | M32 | SUMIBORON insert |
| TPGW******HS-NU | M34 | SUMIBORON insert |
| TPGW******LE-NC3 | M32 | SUMIBORON insert |
| TPGW******LE-NU3 | M34 | SUMIBORON insert |
| TPGW******LF-NU | M33 | SUMIBORON insert |
| TPGW******LF-NU3 | M34 | SUMIBORON insert |
| TPGW******LS-NC3 | M32 | SUMIBORON insert |
| TPGW******LT-NC3 | M32 | SUMIBORON insert |
| TPGW******LT-NU | M33 | SUMIBORON insert |
| TPGW******NC | M32 | SUMIBORON insert |
| TPGW******NC3 | M32 | SUMIBORON insert |
| TPGW******NF | M34 | SUMIDIA insert |
| TPGW******NU | M33 | SUMIBORON insert |
| TPGW******NU3 | M34 | SUMIBORON insert |
| TPGX******L/R-SDW | C85 | Indexable insert |
| TPMH******NSF | C87 | Indexable insert |
| TPMN****** | C89 | Indexable insert |
| TPMR******NFK | C89 | Indexable insert |
| TPMR******NSF | C89 | Indexable insert |
| TPMR******NUJ | C89 | Indexable insert |
| TPMT******L-DM NU | M35 | SUMIDIA insert |
| TPMT******NFB | C86 | Indexable insert |
| TPMT******NFK | C86 | Indexable insert |
| TPMT******N-GD NF | M35 | SUMIDIA insert |
| TPMT******NGU | C87 | Indexable insert |
| TPMT******N-LD NF | M35 | SUMIDIA insert |
| TPMT******NLB | C86 | Indexable insert |
| TPMT******NLU | C86 | Indexable insert |
| TPMT******NMU | C87 | Indexable insert |
| TPMT******NSF | C87 | Indexable insert |
| TPMT******NSU | C87 | Indexable insert |
| TPMW******RF | M35 | SUMIDIA insert |
| TPMW******RH | M35, M45 | SUMIDIA insert |
| TRB**IP | P7 | Spare parts |
| TRCP* | D11, E11 | Spare parts |
| TRD** | P8 | Spare parts |
| TRDR**IP | P8 | Spare parts |
| TRM******-FL | C52, D11, E11 | Indexable insert |
| TRM******-GU | C52, D11, E11 | Indexable insert |
| TRM******-LU | C52, D11, E11 | Indexable insert |
| TRM******-SU | C52, D11, E11 | Indexable insert |
| TRW**** | P6 | Spare parts |
| TRX** | P8 | Spare parts |
| TRX**IP | P8 | Spare parts |
| TRX**IP** | D35 | Spare parts |
| TRXW**IP | P7 | Spare parts |
| TSX*****E | G30, H20, H22, H23 | Indexable endmill |
| TSXF*****E | G30, H20, H22, H23 | Indexable endmill |
| TSXM*****E | G30, H20, H23, | Indexable endmill |
| TSX*****RS | G30, G34, G35, H20 | Cutter |
| TSXF*****RS | G30, G34, G37, H20 | Cutter |
| TSXM*****RS | G30, G36, H20 | Cutter |
| TSXR*****E | G30, H20, H24, H25 | Indexable endmill |
| TSXR*****RS | G30, G38, G39, H20 | Cutter |
| TSW*** | P8 | Spare parts |
| TT** | P8 | Spare parts |
| TTR**IP | P8 | Spare parts |
| TTX** | P8 | Spare parts |

**U**

| | | |
|---|---|---|
| UF*K R/L | G12 | Spare parts |
| UF*S R/L | G12 | Spare parts |
| UFKW R/L | G12 | Spare parts |
| UFO**** R/L-S | G12 | Cutter |
| UFOF**** R/L-S | G13 | Cutter |
| UFTW R/L | G12 | Spare parts |
| UW*****R | G13 | Indexable insert |

# Index

## V- W


| V | | |
|---|---|---|
| VBGT******LAY/RAY | C91 | Indexable insert |
| VBGT******LFX/RFX | C91 | Indexable insert |
| VBGT******LFY/RFY | C91 | Indexable insert |
| VBGT******LFYS/RFYS | C91 | Indexable insert |
| VBGT******M NSI | C91 | Indexable insert |
| VBGW******HS-NC2 | M37 | SUMIBORON insert |
| VBGW******HS-NU | M36 | SUMIBORON insert |
| VBGW******LE-NC2 | M37 | SUMIBORON insert |
| VBGW******LE-NU2 | M37 | SUMIBORON insert |
| VBGW******LS-NC2 | M37 | SUMIBORON insert |
| VBGW******LT-NC2 | M37 | SUMIBORON insert |
| VBGW******LT-NU | M36 | SUMIBORON insert |
| VBGW******NC | M36 | SUMIBORON insert |
| VBGW******NC2 | M37 | SUMIBORON insert |
| VBGW******NU | M36 | SUMIBORON insert |
| VBGW******NU2 | M37 | SUMIBORON insert |
| VBMT******NFB | C90 | Indexable insert |
| VBMT******NFP | C90 | Indexable insert |
| VBMT******NGU | C90 | Indexable insert |
| VBMT******NLB | C90 | Indexable insert |
| VBMT******NLU | C90 | Indexable insert |
| VBMT******NMU | C90 | Indexable insert |
| VBMT******NSK | C90 | Indexable insert |
| VBMT******NSU | C90 | Indexable insert |
| VBMW****** | C90 | Indexable insert |
| VCGT******LFX/RFX | C92 | Indexable insert |
| VCGT******LFY/RFY | C92 | Indexable insert |
| VCGT******M NFC | C92 | Indexable insert |
| VCGT******M NSI | C92 | Indexable insert |
| VCGT******NAG | C92 | Indexable insert |
| VCGW******HS NC2 | M38 | SUMIBORON insert |
| VCGW******LS NC2 | M38 | SUMIBORON insert |
| VCGW******LT NU | M38 | SUMIBORON insert |
| VCGW******NC2 | M38 | SUMIBORON insert |
| VCGW******NU | M38 | SUMIBORON insert |
| VCMT****** | M39 | SUMIDIA insert |
| VCMT******NF | M39 | SUMIDIA insert |
| VCMT******NFB | C93 | Indexable insert |
| VCMT******NGU | C93 | Indexable insert |
| VCMT******NLD NF | M39 | SUMIDIA insert |
| VCMT******NGD NF | M39 | SUMIDIA insert |
| VCMT******NLB | C93 | Indexable insert |
| VCMT******NLU | C93 | Indexable insert |
| VCMT******NSK | C93 | Indexable insert |
| VCMT******NSU | C93 | Indexable insert |
| VCMW****** | M39 | SUMIBORON insert |
| VCMW******NF | M39 | SUMIDIA insert |
| VCMW******RH | M39, M45 | SUMIDIA insert |
| VCS**** | P6 | Spare parts |
| VNGA******ES-NC4 | M41 | SUMIBORON insert |
| VNGA******HS-NC4 | M41 | SUMIBORON insert |
| VNGA******HS-NU2 | M40 | SUMIBORON insert |
| VNGA******LS-NC2 | M41 | SUMIBORON insert |
| VNGA******LS-NC4 | M41 | SUMIBORON insert |
| VNGA******LT-NC2 | M41 | SUMIBORON insert |
| VNGA******LT-NU2 | M40 | SUMIBORON insert |
| VNGA******NC2 | M41 | SUMIBORON insert |
| VNGA******NC4 | M41 | SUMIBORON insert |
| VNGA******NU | M40 | SUMIBORON insert |
| VNGA******NU2 | M40 | SUMIBORON insert |
| VNGG******LAX/RAX | C57 | Indexable insert |
| VNGG******NEF | C57 | Indexable insert |
| VNGG******NFV NC4 | M41 | SUMIBORON insert |
| VNGG******NLV NC4 | M41 | SUMIBORON insert |
| VNGG******NSU | C57 | Indexable insert |
| VNGM******NLV NU2 | M42 | SUMIBORON insert |
| VNMA****** | C55 | Indexable insert |
| VNMA****** | M42 | SUMIBORON insert |
| VNMA******NU | M42 | SUMIBORON insert |
| VNMA******NS | M42 | SUMIBORON insert |
| VNMA******NF | M42 | SUMIDIA insert |
| VNMA******RH | M42, M45 | SUMIDIA insert |
| VNMG******NEF | C55 | Indexable insert |
| VNMG******NEG | C56 | Indexable insert |
| VNMG******NEX | C56 | Indexable insert |
| VNMG******NFA | C55 | Indexable insert |
| VNMG******NFB | C55 | Indexable insert |
| VNMG******NFE | C55 | Indexable insert |
| VNMG******NFL | C55 | Indexable insert |
| VNMG******NGE | C56 | Indexable insert |
| VNMG******NGU | C56 | Indexable insert |
| VNMG******NGZ | C57 | Indexable insert |
| VNMG******NLU | C55 | Indexable insert |
| VNMG******NSE | C56 | Indexable insert |
| VNMG******NSU | C56 | Indexable insert |
| VNMG******NSX | C56 | Indexable insert |
| VNMG******NUG | C56 | Indexable insert |
| VNMG******NUP | C57 | Indexable insert |
| VNMG******NUX | C57 | Indexable insert |
| VNMG******NUZ | C57 | Indexable insert |
| VNMX****** | M42 | SUMIDIA insert |
| VNMX******NF | M42 | SUMIDIA insert |
| VNS**** | P6 | Spare parts |
| VP** | P7 | Spare parts |
| VP**B | P7 | Spare parts |

| W | | |
|---|---|---|
| WAS******. | K66 | Eccentric sleeve |
| WAX****E** | H62, H63 | Indexable endmill |
| WAX****EL** | H62, H63 | Indexable endmill |
| WAX****RS | G72, G73 | Cutter |
| WB*-** | P4 | Spare parts |
| WB*-**T | P4 | Spare parts |
| WB*F-**T | P4 | Spare parts |
| WB*-**TL | P4 | Spare parts |
| WB*F-**TL | P4 | Spare parts |
| WB*R-**T | P4 | Spare parts |
| WBGT******LFW/RFW | C94 | Indexable insert |
| WBGT******LFX/RFX | C94 | Indexable insert |
| WBGT******LFY/RFY | C94 | Indexable insert |
| WBGT******LW/RW | C94 | Indexable insert |
| WBMF****L | H73 | Indexable endmill |
| WBMF****M | H73 | Indexable endmill |
| WBMF****MM**N | H73 | Indexable endmill |
| WBMF****S | H73 | Indexable endmill |
| WBMR****LL | H71 | Indexable endmill |
| WBMR****LLW | H71 | Indexable endmill |
| WBMR****M | H71 | Indexable endmill |
| WBMR****MW | H71 | Indexable endmill |
| WBMR****S | H71 | Indexable endmill |
| WCFH**-* | F58, F59 | Tool holder |

| | | |
|---|---|---|
| WCFN/R/L* | F57, F60 | Indexable insert |
| WCFN/R/L*A | F57, F60 | Indexable insert |
| WCFN/R/L*B | F57, F60 | Indexable insert |
| WCFN/R/L*T | F57, F60 | Indexable insert |
| WCFN*GF | F57, F60 | Indexable insert |
| WCFN*GG | F57, F60 | Indexable insert |
| WCF R/L*CF | F57, | Indexable insert |
| WCFS R/L **-* | F59 | Tool holder |
| WDMT****ZDTR | G67, H11, H12 | Indexable insert |
| WDMT****ZDTR-H | G67, H11, H12 | Indexable insert |
| WDX***D2S** | K56 | Multi-drill |
| WDX***D3S** | K58 | Multi-drill |
| WDX***D4S** | K60 | Multi-drill |
| WDX***D5S** | K62 | Multi-drill |
| WDXT******-G | K57, K59, K61, K63, K67 | Indexable insert |
| WDXT******-H | K57, K59, K61, K63, K67 | Indexable insert |
| WDXT******-L | K57, K59, K61, K63, K67 | Indexable insert |
| WDXT******-M | K57, K59, K61, K63 | Indexable insert |
| WEX****E | H56, H57, H58 | Indexable endmill |
| WEX****E** | H58 | Indexable endmill |
| WEX****EL | H56, H57, H58 | Indexable endmill |
| WEX****EL** | H56, H57 | Indexable endmill |
| WEX****EL**Z* | H57 | Indexable endmill |
| WEX****EW | H57, H58 | Indexable endmill |
| WEX****F | G58 | Cutter |
| WEX****M**Z* | H57, H58, | Indexable endmill |
| WEZ*****E** | G40, H26, H30, H36, | Indexable endmill |
| WEZ*****E**** | G40, H26, H30, H36, | Indexable endmill |
| WEZ*****EL** | G40, H26, H34, H40, | Indexable endmill |
| WEZ*****ES**** | G40, H26, H32, H38, | Indexable endmill |
| WEZ*****M****Z* | G40, H26, H46, H48 | Indexable endmill |
| WEZ*****R** | G40, G44, G46, H26 | Cutter |
| WEZ*****RS** | G40, G44, G46, H26 | Cutter |
| WEZR*****E****Z** | G40, H26, H42, H44 | Indexable endmill |
| WEZR*****M****Z* | G40, H26, H50, H52 | Indexable endmill |
| WEZR*****RS****Z** | G40, G54, G56, H26 | Cutter |
| WFX*****E | G26, H18, H19 | Indexable endmill |
| WFX*****R | G26 | Cutter |
| WFX*****E ** | H18 | Indexable endmill |
| WFXF*****E | G26, H19 | Indexable endmill |
| WFXM*****E | G26, H18 | Indexable endmill |
| WFX*****M | G26 | Indexable endmill |
| WFX*****M**Z* | H18, H58 | Indexable endmill |
| WFX*****RS | G26, G28, G29 | Cutter |
| WFXC*****E | G26, H78, H79 | Indexable endmill |
| WFXC*****M | G26, H80 | Indexable endmill |
| WFXF*****R | G26 | Cutter |
| WFXF*****RS | G26, G28, G29 | Cutter |
| WFXH*****M | G26, H14 | Indexable endmill |
| WFXH*****M**Z* | H15 | Indexable endmill |
| WFXH*****RS | G26, G70, G71 | Cutter |
| WFXH*****RSZ6 | G70 | Cutter |
| WFXM*****R | G26 | Cutter |
| WFXM*****RS | G26, G28 | Cutter |
| WFXS*R | P6 | Spare parts |
| WGCS**R | P6 | Spare parts |
| WGX*****EW | H7 | Indexable endmill |
| WGX*****RS | G10 | Cutter |
| WGXF*****RS | G10 | Cutter |
| WGXM*****RS | G10 | Cutter |
| WNGA******HS-NC6 | M43 | SUMIBORON insert |
| WNGA******LS-NC3 | M43 | SUMIBORON insert |
| WNGA******LS-NC6 | M43 | SUMIBORON insert |
| WNGA******LT-NC3 | M43 | SUMIBORON insert |
| WNGA******NC6 | M43 | SUMIBORON insert |
| WNGA******NC-WG6 | M43 | SUMIBORON insert |
| WNGA******NC-WH6 | M43 | SUMIBORON insert |
| WNGG******NSU | C60 | Indexable insert |
| WNMA****** | C62 | Indexable insert |
| WNMA******NU | M43 | SUMIBORON insert |
| WNMG******NEF | C59 | Indexable insert |
| WNMG******NEG | C60 | Indexable insert |
| WNMG******NEM | C60 | Indexable insert |
| WNMG******NEX | C60 | Indexable insert |
| WNMG******NFA | C58 | Indexable insert |
| WNMG******NFB | C58 | Indexable insert |
| WNMG******NFE | C58 | Indexable insert |
| WNMG******NFL | C58 | Indexable insert |
| WNMG******NGE | C60 | Indexable insert |
| WNMG******NGU | C59 | Indexable insert |
| WNMG******NGU-W | C59 | Indexable insert |
| WNMG******NGZ | C61 | Indexable insert |
| WNMG******NLU | C58 | Indexable insert |
| WNMG******NLU-W | C58 | Indexable insert |
| WNMG******NME | C61 | Indexable insert |
| WNMG******NMU | C61 | Indexable insert |
| WNMG******NMX | C61 | Indexable insert |
| WNMG******NSE | C59 | Indexable insert |
| WNMG******NSE-W | C59 | Indexable insert |
| WNMG******NSU | C59 | Indexable insert |
| WNMG******NSX | C59 | Indexable insert |
| WNMG******NUG | C60 | Indexable insert |
| WNMG******NUP | C60 | Indexable insert |
| WNMG******NUX | C61 | Indexable insert |
| WNMG******NUZ | C61 | Indexable insert |
| WNMM******NHG | C62 | Indexable insert |
| WNMM******NMP | C62 | Indexable insert |
| WNMU****ZNER-G | G66, H8, H9 | Indexable insert |
| WNMU****ZNER-H | G66, H8, H9 | Indexable insert |
| WNS**** | P6 | Spare parts |
| WNS****B | P6 | Spare parts |
| WPMT******NLB | C95 | Indexable insert |
| WRCX*****EL | H74 | Indexable endmill |
| WRCX*****EM | H74 | Indexable endmill |
| WRCX*****ES | H74 | Indexable endmill |
| WRCX*****M**Z* | H75 | Indexable endmill |
| WRCX*****RS | G17 | Cutter |
| WRCXF*****RS | G17 | Cutter |
| WRCXX*****RS | G17 | Cutter |
| WRX****RH **E** | H65, H66 | Indexable endmill |
| WRX****RH **F** | G59 | Cutter |
| WRX****RH **W** | H65, H66 | Indexable endmill |

# Index

## X - Z


| X | | |
|---|---|---|
| XCLN R/L ****-*** | D27 | Tool holder |
| XEEW****AGER-W | G13 | Indexable insert |
| XEEW****AGER-WR | G11, H7 | Indexable insert |
| XEEW****AGFR-W-NF | G13 | Indexable insert |
| XNEU****ANEN-W | G9, H6 | Indexable insert |
| XNMU****PNER-G | G25, G27, H14, H15 | Indexable insert |
| XNMU****PNER-GS | G25, H17 | |
| XNMU****PNER-H | G25, G27, H14, H15 | Indexable insert |
| XNMU****PNER-L | G25, G27, H14, H15 | Indexable insert |
| XOEW******PDTR-W | G31, H17 | Indexable insert |
| XOEW******PZTR-W | G30, H14 | Indexable insert |
| XOMT*****PEER-E | G61, H69 | Indexable insert |
| XP** | F20 | Spare parts |
| XP**-E | F26, F30 | Spare parts |
| XSBN R/L ****-*** | D27 | Tool holder |

| Y | | |
|---|---|---|
| YE* | P6 | Spare parts |
| YI* | P6 | Spare parts |

| Z | | |
|---|---|---|
| ZNEX******LE-NC | M44 | SUMIBORON insert |
| ZNEX******LT-NC | M44 | SUMIBORON insert |
| ZNEX******NC | M44 | SUMIBORON insert |
| ZNEX******NU | M44 | SUMIBORON insert |
| ZNMT******* | H71 | Indexable insert |
| ZNMT*******-C | H71 | Indexable insert |
| ZNMT*******-N | H71 | Indexable insert |
| ZNMT*******-S | H71 | Indexable insert |
| ZPGU******* | H73 | Indexable insert |

SUMITOMO
CARBIDE - CBN - DIAMOND
Global Support, Global Solutions.

# Sumitomo Electric Cutting Tools Official Apps







## Smart Calculation

Just enter figures

## Easy to Find

Just select conditions

for iOS/Android

Cutting calculation app

### SumiTool Calculator

Download on the App Store

Google Play

Grade and chipbreaker comparison app

### SumiTool Converter

Download on the App Store

Google Play

https://www.SumitomoTool.com

SUMITOMO ELECTRIC GROUP

## Notes

| Target Products | Hazards | Measures |
|---|---|---|
| **General precautions for cutting tools** | The tools have sharp cutting edges. There is a risk of injury if held directly with bare hands. | Always wear protective equipment, such as protective tools when removing the tool from the case or mounting it onto a machine. |
| | Improper use or incorrect use conditions may cause the tool to breake or scatter, and could cause injury. | Always use protective equipment such as safety covers and protective eyewear.<br>Always use within the scope of the recommended conditions. Refer to the intruction manual, catalogue and other relevant documents. |
| | The tool could break and fly off if the cutting force increases suddenly because of impact loads or excessive wear and could cause injury. | Always use protective equipment such as safety covers and protective eyewear.<br>Replace the tool at an early stage. |
| | Very hot chips could scatter or elongated chips could be discharged, and cause injury or burns. | Always use protective equipment such as safety covers and protective eyewear.<br>When removing the chips, always stop the machine, wear protective gloves, and use tools such as nippers or clippers. |
| | The tool and work materials will become very hot during turning. There is a risk of burn if these are touched directly with bare hands immediately after machining. | Always wear protective equipment such as protective gloves. |
| | There is a risk of igniting or fires from the sparks generated during turning, or the heat generated from broken pieces and chips. | Do not use in an area where there is a risk of fires or explosions.<br>Always provide fire prevention measures when using water-insoluble turning oil solution. |
| | When using at a high rotation speed, if the balance including the machine tool holder is poor, the deflection or vibration could cause tool damage and injury. | Always use protective equipment such as safety covers and protective eyewear.<br>Always carry out trial operation, and confirm that there is no deflection, vibration or abnormal noise. |
| | There is a risk of injury if you touch the burrs formed on the workpiece with bare hands. | Do not touch with bare hands. |
| **General precautions for cutting edge indexable tools** | If insert or parts are not properly clamped, they could come off or fly off during turning and cause injury. | Clean the mounting surface and fixing parts free of foreign matter, before mounting the insert.<br>When mounting, use the enclosed spanner and confirm that the insert and parts are securely clamped. Never use parts other than the designated inserts or parts. |
| | If the parts are tightened excessively with an auxiliary tool such as a pipe, the insert or part could break and come off or fly off. | Do not use auxiliary tools such as pipes. Use the enclosed spanner. |
| | Using the tool with high-speed rotation is extremely dangerous as the parts or inserts could fly off with the centrifugal force. Pay special attention to safety when handling. | Always use within the scope of the recommended conditions. Refer to the instruction manual, catalog and other relevant documents. |
| **Various cutters and other tools used with rotation** | The cutters have very sharp cutting edges. Touching these with bare hands could result in injury. | Always wear protective equipment such as protective gloves. |
| | Tools could sway or vibrate if the eccentric rotation or balance is poor. There is a risk of injury if they break or fly off. | Keep the rotation speed within the scope of the recommended conditions.<br>Periodically adjust the accuracy and balance of the rotating sections so that eccentric rotation or deflection do not occur because of bearing wear, etc. |
| **Drills** | When machining a through hole while rotating the workpiece, a disc-shaped uncut section may fly off at the point of penetration. This disc is sharp and very dangerous. | Always use protective equipment such as safety covers and protective eyewear.<br>Also take measures such as attaching a cover to the chuck section. |
| | The very small drill has a pointed end, and is very sharp. It could stab or break when directly touched with a finger, and be difficult to remove. The end could fly off if it breaks. | Take special care to safety when handling.<br>Always wear protective gloves and protective eyewear, etc. |
| **Brazing tool** | There is a risk of injury if the insert comes off or breaks, etc. | Confirm that the insert is properly brazed before using.<br>Do not use in conditions that could become very hot. |
| **Others** | Repeated brazing is dangerous as the insert could break during use. | Do not use an insert that has been repeated brazed as the strength will have dropped. |
| | Using this product for a purpose other than the designated application can break the machine or tool and is very dangerous. | Observe the designated usage. |

Finally,
this brochure describes the basic safety information. For further information, refer to the instruction manual, catalog and other relevant documents for each tool, or contact Sumitomo Electric Hardmetal. Sumitomo Electric Hardmetal will not be held liable for any damage and injuries resulting from changes to the specifications, including alterations and modifications, made without consent from Sumitomo Electric Hardmetal.

# Tool Engineering Services

In order to provide a higher level of support and satisfaction for our customers,
Sumitomo Electric Industries has created the Tool Engineering Service system.
We have created several Tool Engineering Centers around the world as bases for this support.
The Tool Engineering Centers provide a wide range of support to assist user manufacturing activities,
with services including training (at the Center), test cuts, technical consulting,
line diagnostics (at the user's site) and tooling proposals.



## Tool Engineering Center Locations

**Japan**

- ▶Itami Tool Engineering Center (**I-TEC**)
- ▶Yokohama Tool Engineering Center (**Y-TEC**)
- ▶Hokkaido Igetalloy Tool Engineering Center (**H-TEC**)
- ▶Tokai Tool Engineering Center (**T-TEC**)
- ▶Kyushu Tool Engineering Center (**K-TEC**)

**Overseas**


- ▶**Germany / European Design & Engineering Center** (**E-DEC**)
- ▶Thailand / Thailand Tool Engineering Center (**Ti-TEC**)
- ▶Shanghai / Shanghai Tool Engineering Center (**S-TEC**)
- ▶U.S.A. / Americas Tool Engineering Center (**A-TEC**)
- ▶Indonesia / Indonesia Tool Engineering Center (**In-TEC**)
- ▶India Tool Engineering Center

## 1 Training

To make it easy for anyone to take part, the Centers offer training courses designed for a variety of different training objectives and participants.
*Contact your nearest SEI sales office for detailed training curricula.

## 2 Performance evaluation technology

To attain improvements in machining on sites, manufacturers must rely on more than just the subjective guidance provided by experience and instinct. Today's advanced measuring instruments can make machining phenomena observable, and clarify problems.




## 3 Test cuts and technical consulting

The Tool Engineering Centers can make test cuts on user workpieces, and work with users to create more detailed technical proposals. The Centers can also provide solutions to various machining problems, general line diagnostics for machining lines, and tooling support for new lines.
*Contact your nearest SEI sales office for more information.


SUMITOMO
CARBIDE - CBN - DIAMOND


# SUMITOMO ELECTRIC

## CUTTING TOOLS

# WORLDWIDE LOCATIONS

We are strengthening its global position for high-quality products and services, while contributing technology to market needs around the world.




- Sales Network (●)
- Production Network
- Tool Engineering Center



H Sumitomo Electric Industries Ltd. Hardmetal Div.
Sumitomo Electric Hardmetal Corp.

## Production Network



P1 Hokkaido Sumiden Precision Co., Ltd.



P2 Hokkaido Precision Tool Co., Ltd.



P3 Tokai Sumiden Precision Tool Co., Ltd.



P4 Kyushu Sumiden Seimitsu Ltd.



P5 Asdex Corporation



P6 Sumitomo Electric Hartmetallfabrik GmbH



P7 Sumitomo Electric Hartmetallfabrik GmbH, organizační složka.



P8 Sumitomo Electric Hardmetal Manufacturing (Changzhou) Co., Ltd



P9 Sumitomo Electric Hardmetal Manufacturing (Thailand), Ltd



P10 PT. Sumiden Hardmetal Manufacturing Indonesia



P11 Motherson Techno Tools Ltd.



P12 Sumitomo Electric Carbide Manufacturing, Inc. (WI)



P13 Sumitomo Electric Carbide Manufacturing, Inc. (OH)

# HARDMETAL GROUP

## CUTTING TOOLS
# EUROPEAN LOCATIONS



S2 Sumitomo Electric Hartmetall GmbH




THE TEC

- T1 Itami Tool Engineering Center (I-Tec)
- T2 Hokkaido Tool Engineering Center (H-Tec)
- T3 Yokohama Tool Engineering Center (Y-Tec)
- T4 Tokai Tool Engineering Center (T-Tec)
- T5 Kyushu Tool Engineering Center (K-Tec)
- T6 European Design & Engineering Center (E-DEC)
- T7 Shanghai Tool Engineering Center (S-Tec)
- T8 Thai Tool Engineering Center (Ti-Tec)
- T9 Indonesia Tool Engineering Center (In-Tec)
- T10 Americas Tool Engineering Center (A-Tec)
- T11 India Tool Engineering Center

Sales Network
Production Network
Tool Engineering Center

## Sales Network



S1 Sumitomo Electric Tool Net, Inc.



S3 Sumitomo Electric Hardmetal Ltd.



S4 SumiSermetal Ticaret ve Sanayi Limited Şirketi



S5 Sumitomo Electric Hardmetal Trading (Shanghai) Co., Ltd.



S6 Superior Engineering Tool Trading (Shanghai) Co., Ltd.



S7 Sumitomo Electric Hardmetal Asia Pacific Pte Ltd.



S8 Sumitomo Electric Hardmetal (Thailand) Ltd.



S9 PT. Sumitomo Electric Hardmetal Indonesia



S10 SEI Carbide Australia Pty Ltd.



S11 Motherson Techno Tools Ltd.



S12 Sumitomo Electric Carbide, Inc.



S13 Sumicarbide Canada Inc.



S14 Sumitomo Electric Hardmetal de Mexico, S.A. de C.V.



S15 Sumitomo Electric Hardmetal do Brasil Ltda.



S16 Taiwan Hong-Yu Precision Tool Co., Ltd.

SUMITOMO

CARBIDE - CBN - DIAMOND

(Germany)
SUMITOMO ELECTRIC Hartmetall GmbH
Konrad-Zuse-Str. 9, 47877 Willich

Tel. +49 2154 4992-0, FAX +49 2154 4992-161
Info@SumitomoTool.com
www.SumitomoTool.com

(UK and Ireland)
SUMITOMO ELECTRIC Hardmetal Ltd.
3 Paper Mill Drive
Redditch, B98 8QJ, UK

Tel. +44 1844 342081, FAX +44 1844 342415
InfoUK@sumitomoTool.com
www.SumitomoTool.com

Distributed by :

( 08/22_SHG_Engl.)